

Polyamide Resin Alcohol Solvent soluble

Index	Acid Value (mgKOH/g)	Amine Value (mgKOH/g)	Viscosity MPas/25°C	Color (Fe-Co)	Softening Point °C
PAA-010	<4	<4	80-150	<10	110±5
PAA-010A	<3	<6	80-150	<10	105 ± 5
PAA-010C	<6	<6	80-150	<10	110-120
PAA-010E	<6	<5	70-120	<10	110-120
PAA-010J	<5	<5	120-170	<8	115-125

Polyamide Resin Co-Solvent soluble

Index	Acid Value (mgKOH/g)	Amine Value (mgKOH/g)	Viscosity (mpas/25°C)	Color (Fe-Co)	Softening Point °C
PAA-011	<5	<4	130-210	<10	110±5
PAA-011A	<5	<4	150-280	<10	110 ± 5
PAA-010B	<5	<3	100-200	<10	100 ± 5