

Item	index
Lead content	27.5 ±1.0
Free Fatty Acid	1.0% Max
Moisture	1.0% Max
Melting Point °C	105±5
Size (through 0.075 mm mesh rate), %	99.90 Min