

Grade	Yb ₂ O ₃	Yb ₂ O ₃	Yb ₂ O ₃
	2N5	3N	4N
TREO(%min)	99.00	99.00	99.00
Yb ₂ O ₃ /TREO(%min)	99.5	99.9	99.99
Fe ₂ O ₃ (%max)	0.005	0.003	0.0005
SiO ₂ (%max)	0.005	0.003	0.0005
CaO(%max)	0.008	0.005	0.002
Cl-(%max)	0.005	0.003	0.003