



## CHONGQING CHANGFENG CHEMICAL CO.,LTD

30<sup>th</sup> Floor, Longhu Ziduxingzuo Building A, 1<sup>st</sup> Branch, YuSong Rd., Yubei District,  
Chongqing, China E-mail: info@changfengchem.com  
<http://www.changfengchem.com>

### Polychloroprene Rubber CR244

A Xanthogen-modified polychloroprene rubber with fast crystallization rate, high cohesion force and adhesion strength at normal temperature, Used mainly for production of adhesives.

Properties		Specification
Viscosity in 5% toluene solution, mPa.s	CR2441	25-34
	CR2442	35-53
	CR2443	54-75
	CR2444	76-115
	CR244 high A	116-150
	CR244 high B	150 above
Viscosity in 15% toluene solution, mPa.s	CR2441	1000-2000
	CR2442	2001-3000
	CR2443	3001-5000
	CR2444	5001-7000
	CR244 high A	7001-9000
	CR244 high B	9001-10000
Peel strength, N/cm		90min.
Volatile matter, %		1.5max
Ash content, %		1.5max.

Package: Woven polypropylene lined-kraft paper bags with a release polyethylene liner, 25kg net wt.

Storage life: One year below 25°C from the date of production