# **Inorganic Chemistry**

### Novel Heterotetranuclear V<sub>2</sub>Mo<sub>2</sub> or V<sub>2</sub>W<sub>2</sub> Complexes with 4,4'-Di-*tert*butyl-2,2'-bipyridine: Syntheses, Crystal Structures, and Catalytic **Activities**

Shintaro Kodama,<sup>†</sup> Akihiro Nomoto,<sup>†</sup> Shigenobu Yano,<sup>‡</sup> Michio Ueshima,<sup>†</sup> and Akiya Ogawa<sup>\*,†</sup>

<sup>†</sup>Department of Applied Chemistry, Graduate School of Engineering, Osaka Prefecture University, 1-1 Gakuen-cho, Nakaku, Sakai, Osaka 599-8531, Japan

<sup>‡</sup>Graduate School of Materials Science, Nara Institute of Science and Technology, 8916-5 Takayama, Ikoma, Nara 630-0192, Japan

Supporting Information

**ABSTRACT:** Two novel heterotetranuclear complexes [V<sub>2</sub>O<sub>2</sub>- $(\mu-\text{MeO})_2(\mu-\text{WO}_4)_2(4,4'-^t\text{Bubpy})_2$  (1) and  $[V_2O_2(\mu-\text{MeO})_2 (\mu$ -MoO<sub>4</sub>)<sub>2</sub>(4,4'-<sup>t</sup>Bubpy)<sub>2</sub>] (2) were synthesized, and the solid state structures of these complexes were revealed by single crystal X-ray crystallography. The heterotetranuclear complexes 1 and 2 are centrosymmetric building blocks, considered as consisting of two  $[VO(4,4'-{}^{t}Bubpy)]^{3+}$  units bridged by  $\mu$ -MO<sub>4</sub><sup>2-</sup> (M = W or Mo) anions connected with methoxy groups. Furthermore, catalytic activities of 1 and 2 in the alcohol oxidation with hydrogen peroxide as terminal oxidants in water as solvent were investigated.

## W 1 2 Mo

#### INTRODUCTION

Development of new heteropolynuclear complexes is of great importance in many fields of catalysis and materials chemistry because complexes with different metals are known to modify the properties of the individual metals.1 The heteropolynuclear complexes as catalysts are known to have potential to exhibit distinct activity different from the one shown by mononuclear complexes.<sup>2</sup> However, it is often difficult to combine different metals together in a single molecule without controlling their individual chemical properties. Complexation of the cationic metal complexes by metal oxyanions, such as WO<sub>4</sub><sup>2-</sup> and  $MoO_4^{2-}$ , is an attractive method for the synthesis of heteropolynuclear complexes, but the examples of such simple anions used as ligands to the cationic metal complexes are still limited, compared with those of complexation by polyoxoanions.<sup>3</sup> Also, most of heterometallic complexes bridged by metal oxyanions are used for the investigation of their magnetic properties,<sup>4</sup> and the catalysis of those complexes is not investigated sufficiently. Here, we report the development of new heterotetranuclear complexes from a cationic vanadium complex bearing appropriate organic ligands and metal oxyanions  $(WO_4^{2-} \text{ or } MO_4^{2-})$ . In addition, the catalytic activity of these heterotetranuclear complexes was investigated.

#### RESULTS AND DISCUSSION

In a typical procedure, to an aqueous suspension of the vanadium(IV) complex,  $[VO(4,4'-{}^{t}Bubpy)_{2}]SO_{4}$ , prepared from VOSO<sub>4</sub> and 4,4'-di-*tert*-butyl-2,2'-bipyridyl (4,4'-<sup>t</sup>Bubpy),<sup>5</sup> an aqueous solution of Na2WO4 was added, and the mixture was

stirred at ambient temperature to form a brown precipitate. A heterotetranuclear  $V_2W_2$  complex (vanadium(V)-tungsten(VI) complex),  $[V_2O_2(\mu-MeO)_2(\mu-WO_4)_2(4,4'-{}^tBubpy)_2]$  (1), was obtained as a yellow crystal by recrystallization of the precipitate from a mixture of methanol and chloroform. A heterotetranuclear  $V_2Mo_2$  complex (vanadium(V)-molybdenum(VI) complex),  $[V_2O_2(\mu-MeO)_2(\mu-MoO_4)_2(4,4'-^tBubpy)_2]$  (2) was also obtained by the reaction of  $[VO(4,4'-{}^{t}Bubpy)_{2}]SO_{4}$  with Na<sub>2</sub>MoO<sub>4</sub>.<sup>6</sup> The use of 4,4'-<sup>t</sup>Bubpy as a bipyridyl ligand was necessary for the syntheses of this type of heterotetranuclear V<sub>2</sub>W<sub>2</sub> or V<sub>2</sub>Mo<sub>2</sub> complexes.<sup>7</sup> The structures of these complexes 1 and 2 were characterized by NMR, IR, ESI-MS, and elemental analysis (see Experimental Section). The solid state structures of 1 and 2 were determined by single crystal X-ray crystallography. Crystal data for complexes 1 and 2 are summarized in Table 1. The crystal structures of 1 and 2 are shown in Figures 1-3. They have similar structures. Vanadium, tungsten, and molybdenum atoms in 1 and 2 are present in octahedral coordination. The heterotetranuclear complexes 1 and 2 are centrosymmetric building blocks, considered as consisting of two [VO(4,4'-<sup>t</sup>Bubpy)]<sup>3+</sup> units bridged by  $\mu$ -MO<sub>4</sub><sup>2-</sup> (M = W or Mo) anions connected with methoxy groups. Selected bond lengths (Å) and angles (deg) for 1 and 2 are listed in Table 2. The V=O distances in 1 and 2 are almost the same (1.60 Å). The W=O distances in 1 and the Mo=O distances in 2 are 1.73 Å and 1.71 Å, respectively. The cyclic tetranuclear eight-membered structures exist in these complexes 1 and 2. The V-O distances within the eight-membered



Received: February 8, 2011 Published: September 09, 2011

	1	2
formula	$C_{38}H_{54}N_4O_{12}V_2W_2$	$C_{38}H_{54}N_4O_{12}V_2Mo_2$
T (K)	113	123
cryst syst	triclinic	triclinic
space group	$P\overline{1}$	$P\overline{1}$
a (Å)	10.1338(3)	10.2163(2)
b (Å)	15.6779(5)	16.2648(4)
c (Å)	19.7520(6)	19.0493(4)
$\alpha$ (deg)	72.9803(9)	105.0638(7)
$\beta$ (deg)	80.3509(9)	97.1994(7)
$\gamma$ (deg)	88.1885(9)	93.2327(7)
$V(Å^3)$	2957.75(15)	3019.4(1)
Ζ	1	1
$D_{\rm calcd}  ({\rm g/cm^3})$	1.644	1.672
$\mu$ (MoK $\alpha$ ) (cm <sup>-1</sup> )	44.149	12.911
F(000)	1434.50	1516.00
$2\theta \max (\text{deg})$	50.6	55.0
$N_{ m measured}$	24398	52629
$N_{ m unique}$	10737	13821
GOF	1.05	1.03
$R_1$	0.0335	0.0597
$wR_2$	0.0960	0.1651

 Table 1. Crystallographic Data and Structure Refinement of

 Complexes 1 and 2

ring are longer (1.78-1.79 Å) compared with the V=O distances. The W–O distances within the eight-membered ring are in the range 1.95-1.96 Å, and the Mo-O distances within the eightmembered ring are in the range 1.95-1.97 Å, which are longer than the M=O (M = W or Mo) distances. In 1, the O2-V1-O4#1 angle and the O2-W1-O4 angle are 102.34(17)° and  $153.56(16)^\circ$ , respectively. Also, in 2, the O2–V1–O4#1 angle and the O2-Mo1-O4 angle are 102.77(14)° and 153.71(13)°, respectively. These complexes also have the four-membered ring structure  $(M_2(\mu-MeO)_2 (M = W \text{ or } Mo))$  and two kinds of sixmembered ring structures (VM<sub>2</sub>O<sub>2</sub>( $\mu$ -MeO) (M = W or Mo)). The tungsten or molybdenum centers are connected through methoxy groups. The W1-O3 and W1-O3#1 distances are 2.26 Å and 2.24 Å, respectively, and the Mo1–O3 and Mo1–O3#1 distances are almost the same (2.25 Å). In 1, the O3-W1-O3#1 angle, the W1-O3-W1#1 angle, the O3-W1-O4 angle, and the O3#1-W1-O4 angle are 70.64(12)°, 109.36(13)°, 82.38(13)°, and 75.66(15)°, respectively. In 2, the O3-Mo1-O3#1 angle, the Mo1-O3-Mo1#1 angle, the O3-Mo1-O4 angle, and the O3#1-Mo1-O4 angle are 70.85(11)°, 109.15(12)°, 81.88(11)°, and  $75.38(12)^\circ$ , respectively.

Oxoperoxo vanadium(V), molybdenum(VI), and tungsten-(VI) complexes are known to serve as useful oxidation catalysts.<sup>8</sup> Therefore, we next investigated the catalytic activity of these heterotetranuclear complexes, 1 and 2, for the oxidation of alcohols with hydrogen peroxide as terminal oxidants.

Oxidation of 1-phenylethanol (3a) was examined with hydrogen peroxide in the presence of 1 or other metal complexes using water as solvent. The results are shown in Table 3. VOSO<sub>4</sub> and VO(Hhpic)<sub>2</sub><sup>9</sup> exhibited moderate catalytic activity in the oxidation of 3a (entries 1 and 2). 4,4'-Di-*tert*-butyl-2,2'-bipyridyl (4,4'-<sup>t</sup>Bubpy) was not effective as an additional ligand to VOSO<sub>4</sub> (entry 3). Na<sub>2</sub>WO<sub>4</sub> was not effective as catalysts for the oxidation (entries 4 and 5). The complex 1 was found to be an effective



Figure 1. Crystal structure of 1 (symmetry-expanded structures). Ellipsoids are shown at the 50% probability level.



Figure 2. Crystal structure of 2 (symmetry-expanded structures). Ellipsoids are shown at the 50% probability level.

precatalyst for the oxidation reaction in Table 3, and 4a was produced selectively in a good yield (entry 6).<sup>10,11</sup>

Furthermore, when the oxidation of **3a** (1.5 mmol) was conducted using  $H_2O_2$  (1.57 mmol) at 90 °C for 24 h in the presence of **1** (0.1 mol %), the turnover number (TON) of **1** increased from 292 (see, Table 3, entry 6) to 630 (eq 1).<sup>12,13</sup>  $V_2Mo_2$  complex **2** could also be employed as a precatalyst for the oxidation of **3a**, but the yield of **4a** and TON were lower compared with the case using **1** as a precatalyst (eq 2).

$$\begin{array}{c|cccc} OH & 1 & (0.1 \text{ mol}\%) & O \\ \hline Ph & H_2O & (3.0 \text{ mL}), 90 \ ^\circ\text{C}, 24 \text{ h} & Ph \\ \hline \textbf{3a} & (1.5 \text{ mmol}) & H_2O_2 & (1.57 \text{ mmol}) & \textbf{4a} \\ & 63\% & (TON = 630) \\ & \text{recovery of } \textbf{3a} \text{: } 30\% & (1) \end{array}$$

$$\begin{array}{ccc} OH & 2 (0.1 \text{ mol}\%) & O \\ H_2O (3.0 \text{ mL}), 90 ^{\circ}C, 24 \text{ h} & Ph \\ \hline \textbf{3a} (1.5 \text{ mmol}) & H_2O_2 (1.57 \text{ mmol}) & \textbf{4a} \\ & 28\% (TON = 280) \\ & \text{recovery of } \textbf{3a} : 58\% \quad (2) \end{array}$$

The results of the oxidation of various secondary alcohols using 1 are shown in Table 4. Diphenylmethanol (3b) was oxidized under the reaction condition to afford benzophenone (4b) in a moderate yield (entry 2). The oxidation of cyclohexyl-(phenyl)methanol (3c) proceeded very slowly (entry 3). From these results, steric hindrance may influence the reactivity of 1. Oxidations of 1-(*p*-substituted phenyl)ethanols 3d and 3e



Figure 3. Numbering of selected atoms of heterotetranuclear  $V_2M_2$  (M = W or Mo) complexes 1 or 2.

proceeded selectively to afford the corresponding ketones 4d and 4e, respectively (entries 4 and 5). Furthermore, 4-*tert*-butylcy-clohexanol (3f) could be oxidized by prolonging the reaction time (entry 6).<sup>14</sup>

The examples of metal-complex-catalyzed oxidation of alcohols with  $H_2O_2$  using water as solvent are still limited, <sup>15</sup> although oxidations using water as solvent could be cheaper, more ecofriendly, and safer than current oxidation processes in organic solvents.<sup>16</sup> Also, oxidation of alcohols using water as solvent often proceeds in an organic—aqueous biphasic system, and therefore, phase transfer catalysts are often required. In our reaction system, however, the oxidation of alcohols with 1 proceeded without the addition of any phase transfer catalyst. The result suggests that affinity of 1 to organic substrates was improved by the selection of appropriate organic ligands, that is, 4,4'-<sup>t</sup>Bubpy. In addition, from the result of Table 3, we believe that preparation of heteropolynuclear complexes enables us to develop new oxidation catalysts with improved catalytic activity to realize efficient oxidation reactions.<sup>17</sup>

#### CONCLUSIONS

Two new heterotetranuclear complexes 1 and 2 were synthesized, and the solid state structures of 1 and 2 were revealed by single crystal X-ray crystallography. These complexes had unique structures linked through  $\mu$ -MO<sub>4</sub><sup>2-</sup> (M = W or Mo) and  $\mu$ -MeO<sup>-</sup> bridges, and contained two different metals known to have a potential to act as useful oxidants. Preliminary results of alcohol oxidation with H<sub>2</sub>O<sub>2</sub> using water as solvent in the presence of 1 as a precatalyst suggest that polynucleation of the complex with appropriate organic ligands leads to the development of new catalysts for environmentally friendly oxidation systems.

#### EXPERIMENTAL SECTION

**General Procedures.** <sup>1</sup>H NMR spectra were recorded on a JEOL JNM–AL–300 (300 MHz) spectrometer using CDCl<sub>3</sub> as the solvent with tetramethylsilane (TMS) as an internal standard. <sup>13</sup>C NMR spectra were obtained on a JEOL JNM–AL–400 (100 MHz) spectrometer using CDCl<sub>3</sub> as the solvent. Chemical shifts in <sup>13</sup>C NMR were measured relative to CDCl<sub>3</sub> by using  $\delta$  77.0 ppm. <sup>51</sup>V NMR spectra were obtained on a JEOL ECX–400 (105 MHz) spectrometer using CDCl<sub>3</sub> as the solvent with VOCl<sub>3</sub> (–4 ppm) as an external standard. IR spectra were determined on a Shimadzu FTIR 8400 infrared spectrometer. Substrates **3c**, <sup>18</sup> **3d**, <sup>19</sup> and **3e**<sup>20</sup> were prepared by reduction of the corresponding ketones with NaBH<sub>4</sub>. Unless otherwise noted, other reactants and reagents were purchased from commercial source and used without further purification.

X-ray Crystallography. Crystals of 1 or 2 were mounted on a glass fiber and cooled in the cold stream of nitrogen gas. All measurements were made on a Rigaku RAXIS RAPID imaging plate area detector with graphite monochromated Mo-K $\alpha$  radiation. The structure was solved by direct methods (SHELX97). For 1, the *tert*-butyl group was found disordered.

Table 2. Selected Bond Lengths (Å) and Angles (deg) for 1 and 2  $\,$ 

	1 (16 147) <sup>a</sup>	$(\lambda \epsilon \lambda \epsilon)^b$
	I(M = W)	2 (M = Mo)
V1-O1	1.602(3)	1.602(4)
V1-O2	1.783(3)	1.787(3)
V1-O4#1	1.784(4)	1.783(4)
V1-N1	2.153(3)	2.165(3)
V1-N2	2.139(4)	2.150(4)
M1-O2	1.947(3)	1.948(3)
M1-O3	2.259(3)	2.254(3)
M1-O3#1	2.238(4)	2.247(4)
M1-O4	1.957(3)	1.972(3)
M1-O5	1.730(3)	1.714(3)
M1-O6	1.731(4)	1.709(4)
O3-C1	1.440(5)	1.437(5)
O1-V1-O2	103.27(17)	102.86(14)
O1-V1-O4#1	104.84(19)	104.95(16)
O1-V1-N1	95.34(17)	93.16(14)
O1-V1-N2	96.24(18)	96.74(16)
O2-V1-O4#1	102.34(17)	102.77(14)
O2-V1-N1	155.91(17)	158.29(15)
O2-V1-N2	89.33(17)	90.48(14)
O4#1-V1-N1	87.24(16)	86.82(14)
O4#1-V1-N2	152.62(15)	151.12(12)
N1-V1-N2	73.39(17)	72.97(14)
O2-M1-O3	75.20(13)	74.61(11)
O2-M1-O3#1	83.73(15)	85.78(12)
O2-M1-O4	153.56(16)	153.71(13)
O2-M1-O5	97.14(16)	98.19(14)
O2-M1-O6	99.15(17)	99.39(15)
O3-M1-O3#1	70.64(12)	70.85(11)
O3- M1-O4	82.38(13)	81.88(11)
O3-M1-O5	160.79(18)	159.81(15)
O3- M1-O6	93.15(16)	94.19(13)
O3#1-M1-O4	75.66(15)	75.38(12)
O3#1- M1-O5	91.22(17)	90.03(14)
O3#1- M1-O6	162.38(14)	162.43(12)
04- M1-05	99.64(15)	99.97(14)
O4- M1-O6	95.85(17)	93.83(15)
05-M1-06	105.6(2)	105.68(16)
M1 - O2 - V1	120.12(16)	119.58(14)
M1-04-V1#1	119.1(2)	117.68(17)
M1 - O3 - M1#1	109.36(13)	109 15(12)
M1 - O3 - C1	1183(3)	117 3(3)
M1#1 = 03 = C1	116.9(3)	116.8(3)
<sup>a</sup> Symmetry operators: $(\#1)$	-X+1 - V+1 -	7+1 <sup>b</sup> Symmetry opera
tors: $(#1) - X + 1 - Y - 7$	21 I I I I I I I I I I I I I I I I I I I	2.1. Cymmetry opera

Synthesis of  $[V_2O_2(\mu-MeO)_2(\mu-WO_4)_2(4,4'-t^Bubpy)_2]$  (1). To a solution of 4,4'-di-*tert*-butyl-2,2'-bipyridyl (4,4'-t^Bubpy) (930.4 mg, 3.5 mmol) in EtOH (40 mL) was added a solution of VOSO<sub>4</sub> · 5H<sub>2</sub>O (437.6 mg, 1.7 mmol) in EtOH (20 mL). After stirring for 2.5 h at 40 °C, the solution was concentrated under reduced pressure, and the precipitate was filtered using diethyl ether and dried in vacuo to afford  $[VO(4,4'-t^Bubpy)_2]SO_4$  as a green powder (700.6 mg). HR-ESI MS (MeOH) calcd for  $C_{36}H_{49}N_4O_5SV$ 

Table 3. Catalytic Activities for Oxidation of 1-Phenyl	lethanol with 1 and Other Metal Complexes
---	---

		OH 	catalyst, ligand	O		
		Ph	H <sub>2</sub> O (1.0 mL), 90 <sup>o</sup> C, 1	7 h Ph		
		<b>3a</b> (0.5 mmol)	H <sub>2</sub> O <sub>2</sub> (0.98 mmol)	4a		
entry	catalyst (mol %)	ligand (mol %)	yield $(\%)^a$	selectivity $(\%)^b$	conversion (%) <sup>c</sup>	$\mathrm{TON}^d$
1	$VOSO_4(1)$	none	44	66	67	44
2	$VO(Hhpic)_2(1)$	none	43	65	66	43
3	$VOSO_4(1)$	4,4'- <sup>t</sup> Bubpy (2)	33	50	66	33
4	$Na_2WO_4(1)$	none	7	70	10	7
5	$Na_2WO_4(1)$	4,4′- <sup><i>t</i></sup> Bubpy (2)	8	42	19	8
6	1 (0.25)	none	73	82	89	292
<sup>a</sup> Determine	d by <sup>1</sup> H NMR. <sup>b</sup> Selectivit a)/(mmol of catalyst).	ty = (formed 4a)/(conve	rted <b>3a</b> ). <sup><i>c</i></sup> Conversion	of <b>3a</b> to <b>4a</b> . <sup><i>d</i></sup> The turn	nover number (TON) of	the catalyst =

#### Table 4. Oxidation of Various Secondary Alcohols in the Presence of 1

OH	<b>1</b> (0.1 mol%)	
R <sup>17</sup> `R <sup>2</sup> —	H <sub>2</sub> O (3.0 mL), 90 <sup>o</sup> C	→ R' `R <sup>2</sup>
<b>3</b> (1.5 mmol)	H <sub>2</sub> O <sub>2</sub> (1.57 mmol)	4

entry	substrate		product		time (h)	yield (%) <sup>a</sup>	selectivity $(\%)^b$	TON <sup>c</sup>
			$R^1 \xrightarrow{O} R^2$					
1	$\mathbf{R}^1 = \mathbf{P}\mathbf{h},  \mathbf{R}^2 = \mathbf{M}\mathbf{e}$	3a		4a	24	63	90	630
2	$\mathbf{R}^1 = \mathbf{P}\mathbf{h},  \mathbf{R}^2 = \mathbf{P}\mathbf{h}$	3b		4b	24	25	86	250
3	$\mathbf{R}^1 = \mathbf{P}\mathbf{h},  \mathbf{R}^2 = {}^c\mathbf{H}\mathbf{e}\mathbf{x}$	3c		4c	24	6	100	60
4	$R^1 = 4$ -Br $C_6H_4$ , $R^2 = Me$	3d		4d	24	33	83	330
5	$R^1 = 4-NO_2C_6H_4, R^2 = Me$	3e		4e	24	43	83	430
6	'BU OH	3f	<sup>I</sup> Bu O	4f	90	18	55	180

#### <sup>*a*</sup> Determined by <sup>1</sup>H NMR. <sup>*b*</sup> Selectivity = (formed 4)/(converted 3). <sup>*c*</sup> The turnover number (TON) of the catalyst = (mmol of 4)/(mmol of catalyst).

 $[M + H]^+$  700.2863, found 700.2881. Next, water (10 mL) was added to the green powder to form a suspension in a glass vessel. After addition of an aqueous solution of Na2WO4·2H2O (494.3 mg, 1.5 mmol) in water (10 mL) to the suspension, the reaction mixture was stirred for 3 h at ambient temperature. After the reaction, the precipitate was filtered using water and dried in vacuo to afford a brown powder. Next, methanol was added to the brown powder, forming a brown suspension, followed by filtration of the suspension to give a yellow solution. Chloroform was added to the yellow solution, and the resulting mixture was let stand for recrystallization at room temperature for 2 weeks, affording 1 (428.4 mg, yield = 40% based on vanadium) as a yellow crystal. <sup>1</sup>H NMR (CDCl<sub>3</sub>, 300 MHz)  $\delta$  9.15 (d, J = 6.1 Hz, 4H), 8.05 (d, J = 1.7 Hz, 4H), 7.70 (dd, J = 6.3, 1.7 Hz, 4H), 3.18 (s, 6H), 1.46 (s, 36H);  $^{13}$ C NMR (CDCl<sub>3</sub>, 100 MHz)  $\delta$  166.82, 154.01, 152.21, 124.78, 117.15, 57.38, 35.87, 30.34;  $^{51}$  V NMR (CDCl<sub>3</sub>, 105 MHz)  $\delta$  -544;IR (KBr, cm<sup>-1</sup>) 3442, 2964, 1618, 1413, 977, 906, 758; HR-ESI MS (CHCl\_3) calcd for  $C_{38}H_{54}N_4O_{12}V_2W_2Na$  [M + Na]<sup>+</sup> 1251.153, found 1251.150. Anal. Calcd for  $C_{38.5}H_{54.5}Cl_{1.5}N_4O_{12}V_2W_2$ : C, 35.90; H, 4.26; N, 4.35. Found: C, 35.82; H, 4.18; N, 4.29.

Synthesis of  $[V_2O_2(\mu-MeO)_2(\mu-MoO_4)_2(4,4'-{}^{t}Bubpy)_2]$  (2). To a solution of 4,4'-di-*tert*-butyl-2,2'-bipyridyl (4,4'-{}^{t}Bubpy) (539.5 mg, 2.0 mmol) in MeOH (20 mL) was added a solution of VOSO<sub>4</sub> · 5H<sub>2</sub>O (253.6 mg, 1.0 mmol) in MeOH (20 mL). After stirring for 2.5 h at 40 °C, the solution was concentrated under reduced pressure to afford  $[VO(4,4' - Bubpy)_2]SO_4$  as a green powder, and water (10 mL) was added to the green powder to form a suspension in a glass vessel. After addition of an aqueous solution of  $Na_2MoO_4 \cdot 2H_2O$  (366.7 mg, 1.5 mmol) in water (10 mL) to the suspension, the reaction mixture was stirred for 3 h at ambient temperature. After the reaction, the precipitate was filtered using water and dried in vacuo to afford a brown powder. Next, methanol was added to the brown powder, forming a brown suspension, followed by filtration of the suspension to give a yellow solution. Chloroform was added to the yellow solution, and the resulting mixture was let stand for recrystallization at room temperature for 2 weeks, affording 2 (192.2 mg, yield = 37% based on vanadium) as a yellow crystal. <sup>1</sup>H NMR (CDCl<sub>3</sub>, 300 MHz)  $\delta$  9.04 (d, *J* = 5.9 Hz, 4H), 8.05 (d, *J* = 1.7 Hz, 4H), 7.65 (dd, *J* = 6.0, 1.8 Hz, 4H), 3.10 (s, 6H), 1.45 (s, 36H);  $^{13}$ C NMR (CDCl<sub>3</sub>, 100 MHz)  $\delta$  166.34, 153.40, 152.20, 124.52, 117.06, 57.38, 35.80, 30.36; <sup>51</sup>V NMR (CDCl<sub>3</sub>, 105 MHz)  $\delta$  -533; IR (KBr, cm<sup>-1</sup>) 3442, 2962, 1618, 1411, 968, 904, 742; HR-ESI MS (CHCl<sub>3</sub>) calcd for C<sub>38</sub>H<sub>54</sub>N<sub>4</sub>O<sub>12</sub>V<sub>2</sub>Mo<sub>2</sub>Na [M + Na]<sup>+</sup> 1079.062, found 1079.058. Anal. Calcd for C38.8H54.8Cl2.4N4O12V2M02: C, 40.70; H, 4.72; N, 4.98. Found: C, 40.59; H, 4.81; N, 4.88.

General Procedure for Oxidation of Alcohols with Hydrogen Peroxide in the Presence of 1 (Table 4). The  $V_2W_2$  complex 1 (1.8 mg, 0.0015 mmol) and alcohols 3 (1.5 mmol) were placed in a 25 mL two necked flask, and then water (3.0 mL) was added. The mixture was heated to 90 °C, 30%  $H_2O_2$  aq. (0.16 mL, 1.57 mmol) was added to the mixture, and then the reaction was conducted with magnetic stirring for the appropriate time. After the reaction, the mixture was diluted with diethyl ether, and the organic phase was evaporated. The crude product was dissolved in CDCl<sub>3</sub>, and an appropriate amount of 1,3,5-trioxane was added as an internal standard to determine the yield of the product by <sup>1</sup>H NMR spectroscopy.

#### ASSOCIATED CONTENT

**Supporting Information.** X-ray crystallographic data in CIF format, NMR spectra, and IR spectra. This material is available free of charge via the Internet at http://pubs.acs.org.

#### AUTHOR INFORMATION

#### Corresponding Author

\*Phone: +81-72-254-9290. Fax: +81-72-254-9290. E-mail: ogawa@ chem.osakafu-u.ac.jp.

#### ACKNOWLEDGMENT

This research was supported by JST Research Seeds Quest Program (Lower Carbon Society), from the Ministry of Education, Culture, Sports, Science and Technology, Japan, and Kansai Research Foundation for Technology Promotion (KRF). S.K. acknowledges Research Fellowships of the Japan Society for the Promotion of Science (JSPS) for Young Scientists. We acknowledge Mr. Shouhei Katao, Ms. Mika Yamamura, and Professor Kiyomi Kakiuchi of Nara Institute of Science and Technology in Kyoto-Advanced Nanotechnology Network for their help with X-ray crystallography and mass spectrometry. We also thank Mr. Suguru Hashidate and Mr. Kuniaki Marui of Osaka Prefecture University for their experimental support.

#### REFERENCES

 (a) Roesky, H. W.; Haiduc, I.; Hosmane, N. S. Chem. Rev. 2003, 103, 2579.
 (b) Singh, S.; Roesky, H. W. Dalton Trans. 2007, 1360.
 (c) Mezei, G.; Zaleski, C. M.; Pecoraro, V. L. Chem. Rev. 2007, 107, 4933.

(2) (a) McCollum, D. G.; Bosnich, B. Inorg. Chim. Acta 1998, 270, 13. (b) Bosnich, B. Inorg. Chem. 1999, 38, 2554.

(3) (a) Day, V. W.; Klemperer, W. G. *Science* **1985**, *228*, 533. (b) Gouzerh, P.; Proust, A. *Chem. Rev.* **1998**, *98*, 77. (c) Dolbecq, A.; Dumas, E.; Mayer, C. R.; Mialane, P. *Chem. Rev.* **2010**, *110*, 6009.

(4) (a) Holz, R. C.; Elgren, T. E.; Pearce, L. L.; Zhang, J. H.;
O'Connor, C. J.; Que, L., Jr. *Inorg. Chem.* 1993, 32, 5844. (b) Oshio, H.;
Kikuchi, T.; Ito, T. *Inorg. Chem.* 1996, 35, 4938. (c) Choi, K.-Y.; Ryu, H.;
Suh, I.-H. *Inorg. Chim. Acta* 2000, 299, 268. (d) Rarig, R. S., Jr.; Lam, R.;
Zavalij, P. Y.; Ngala, J. K.; LaDuca, R. L., Jr.; Greedan, J. E.; Zubieta, J. *Inorg. Chem.* 2002, 41, 2124. (e) Lozan, V.; Kersting, B. *Eur. J. Inorg. Chem.* 2007, 1436. (f) Liu, M.-L.; Gu, W.; Ma, Z.-P.; Zhu, P.; Gao, Y.-Q.;
Liu, X. J. Coord. Chem. 2008, 61, 3476.

(5) (a) Selvin, J. Chem. Rev. **1965**, 65, 153. (b) Sakurai, H.; Tamura, H.; Okatani, K. Biochem. Biophys. Res. Commun. **1995**, 206, 133. (c) D'Cruz, O. J.; Dong, Y.; Uckun, F. M. Biol. Reprod. **1999**, 60, 435. (d) Triantafillou, G. D.; Tolis, E. I.; Terzis, A.; Deligiannakis, Y.; Raptopoulou, C. P.; Sigalas, M. P.; Kabanos, T. A. Inorg. Chem. **2004**, 43, 79. (e) Salavati-Niasari, M.; Elzami, M. R.; Mansournia, M. R.; Hydarzadeh, S. J. Mol. Catal. A: Chem. **2004**, 221, 169. (f) Waidmann, C. R.; DiPasquale, A. G.; Mayer, J. M. Inorg. Chem. **2010**, 49, 2383. (g) Kodama, S.; Hashidate, S.; Nomoto, A.; Yano, S.; Ueshima, M.; Ogawa, A. Chem. Lett. **2011**, 40, 495.

(6) We presume that the oxidation state of vanadium atoms changed from V(IV) to V(V) by air-oxidation during recrystallization to form 1 or 2.
(7) Other vanadium(IV) complexes with substituted 2,2'-bipyridyl

(5,5'-dimethyl-2,2'-bipyridyl) or 1,10-phenanthroline were employed

for the syntheses of heterotetranuclear  $V_2W_2$  or  $V_2Mo_2$  complexes. However, the materials obtained in the reaction of the vanadium(IV) complexes with  $Na_2WO_4$  or  $Na_2MoO_4$  in water have low solubility to organic solvents such as methanol, and therefore, recrystallization using methanol have been so far unsuccessful. We feel that the selection of the appropriate ligands to increase the solubility to organic solvents is important to obtain heterotetranuclear  $V_2W_2$  or  $V_2Mo_2$  complexes in the present synthetic method.

(8) (a) Johnson, M. K.; Rees, D. C.; Adams, M. W. W. *Chem. Rev.* **1996**, 96, 2817. (b) Ligtenbarg, A. G. J.; Hage, R.; Feringa, B. L. *Coord. Chem. Rev.* **2003**, 237, 89.

(9) (a) Nakai, M.; Obata, M.; Sekiguchi, F.; Kato, M.; Shiro, M.; Ichimura, A.; Kinoshita, I.; Mikuriya, M.; Inohara, T.; Kawabe, K.; Sakurai, H.; Orvig, C.; Yano, S. *J. Inorg. Biochem.* **2004**, *98*, 105. (b) Kodama, S.; Ueta, Y.; Yoshida, J.; Nomoto, A.; Yano, S.; Ueshima, M.; Ogawa, A. Dalton Trans. **2009**, *9708*. (c) Kodama, S.; Yoshida, J.; Nomoto, A.; Ueta, Y.; Yano, S.; Ueshima, M.; Ogawa, A. Tetrahedron Lett. **2010**, *51*, 2450.

(10) The oxidation of **3a** was examined using both metal precursors (VOSO<sub>4</sub> and Na<sub>2</sub>WO<sub>4</sub>) with and without the ligand (4,4'-'Bubpy) according to the reaction conditions of Table 3. As a result, the product of **4a** was formed in moderate yields, respectively (eq 3). Although the real active species is still unknown, we believe that the structure of **1** (Figure 1) is important as a precatalyst for the present oxidation reaction.

OH	cataly	0 III		
Ph	H <sub>2</sub> O (2.0 m	L), 90 °C, 17 h	Ph	
3a (1.0 mmol)	H <sub>2</sub> O <sub>2</sub> (1.96	mmol)	4a	
catalyst (mol%)		ligand (mol%)	yield (%)	
VOSO <sub>4</sub> (0.5), N	a <sub>2</sub> WO <sub>4</sub> (0.5)	none	50	
VOSO <sub>4</sub> (0.5), N	a <sub>2</sub> WO <sub>4</sub> (0.5)	4,4'- <sup>t</sup> Bubpy (0.5	) 51	(3)

(11) When hydrogen peroxide was added to the reaction mixture of 1 and 1-phenylethanol (3a) at 90 °C, the color of the mixture turned from pale yellow to orange. This suggests that a peroxo complex was formed immediately by the addition of hydrogen peroxide. In addition, no significant induction period was observed in the oxidation of 3a with 1 (Table 3, entry 6) varying the reaction time: the yield of 4a (time) = 16% (2 h); 44% (6 h); 73% (17 h). Hydrogen peroxide was completely consumed after the reaction time of 17 h.

(12) Hydrogen peroxide was completely consumed after the reaction.

(13) Additional hydrogen peroxide (1.57 mmol) was added to the reaction mixture after 24 h, and the mixture was stirred at 90 °C for 24 h. As a result, the turnover number (TON) of 1 increased from 630 (see, eq 1) to 710, but the unchanged substrate 3a (13%) was recovered and hydrogen peroxide was left at the end of the reaction (eq 4). We assume that the high concentration of substrate 3 in the reaction mixture is effective in the present oxidation reaction.<sup>14</sup>

$$\begin{array}{ccc} OH & 1 (0.1 \text{ mol}\%) & O \\ Ph & H_2O (3.0 \text{ mL}), 90 \ ^\circ\text{C}, 48 \text{ h} & Ph \\ \hline \textbf{3a} (1.5 \text{ mmol}) & H_2O_2 (3.14 \text{ mmol}) & \textbf{4a} \\ & 71\% (\text{TON} = 710) \\ & \text{recovery of } \textbf{3a}: 13\% & (\textbf{4}) \end{array}$$

(14) The oxidation of 4-*tert*-butylcyclohexanol (3f) was examined by changing only the amount of 3f from 1.5 to 0.5 mmol, according to the condition of Table 4, entry 6. As a result, the turnover number (TON) of 1 decreased from 180 (see, Table 4, entry 6) to 53 (eq 5). From the results of eqs  $4^{13}$  and 5, we consider that higher molar ratio of substrate 3 to 1 may be required in the oxidation reaction to maintain reaction efficiency.



(15) (a) Noyori, R.; Aoki, M.; Sato, K. Chem. Commun. 2003, 1977.
(b) Matsumoto, T.; Ueno, M.; Wang, N.; Kobayashi, S. Chem.—Asian J. 2008, 3, 196. (c) Cavani, F. Catal. Today 2010, 157, 8.

(16) For reviews concerning organic reactions using water as solvent, see: (a) Pirrung, M. C. Chem.—Eur. J. 2006, 12, 1312. (b) Li, C.-J.; Chen, L. Chem. Soc. Rev. 2006, 35, 68. (c) Hailes, H. C. Org. Process. Res. Dev. 2007, 11, 114. (d) Herrerías, C. I.; Yao, X.; Li, Z.; Li, C.-J. Chem. Rev. 2007, 107, 2546. (e) Shaughnessy, K. H. Chem. Rev. 2009, 109, 643. (f) Chanda, A.; Fokin, V. V. Chem. Rev. 2009, 109, 725. (g) Butler, R. N.; Coyne, A. G. Chem. Rev. 2010, 110, 6302.

(17) We are interested in development of a reusable catalyst with high TON for oxidation reactions.<sup>9b</sup> In the present work, we found the possibility that polynucleation of the complex was effective in improving its catalytic ability, because the yield of 4a afforded by 1 and TON of 1 (Table 3) were difficult to achieve by using the mononuclear complexes in Table 3, although the TONs of 1 may not be very encouraging numbers at this stage. We believe that it is possible to further improve the ability of 1 as a precatalyst (or a catalyst) by preventing deactivation of catalysts with the selection of the appropriate reaction condition<sup>13,14</sup> and the bulkier ligand.<sup>21</sup>

(18) Kuriyama, M.; Shimazawa, R.; Shirai, R. J. Org. Chem. 2008, 73, 1597.

(19) Liu, S.; Wolf, C. Org. Lett. 2007, 9, 2965.

(20) Cao, L.; Ding, J.; Gao, M.; Wang, Z.; Li, J.; Wu, A. Org. Lett. 2009, 11, 3810.

(21) Iwasawa, T.; Tokunaga, M.; Obora, Y.; Tsuji, Y. J. Am. Chem. Soc. 2004, 126, 6554.