

Article

Acid is Key to the Radical-Trapping Antioxidant Activity of Nitroxides

Evan A Haidasz, Derek Meng, Riccardo Amorati, Andrea Baschieri, Keith U. Ingold, Luca Valgimigli, and Derek A. Pratt

J. Am. Chem. Soc., Just Accepted Manuscript • DOI: 10.1021/jacs.6b00677 • Publication Date (Web): 29 Mar 2016

Downloaded from http://pubs.acs.org on March 31, 2016

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



Journal of the American Chemical Society is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036 Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

Acid is Key to the Radical-Trapping Antioxidant Activity of Nitroxides

Evan A. Haidasz,[‡] Derek Meng,[‡] Riccardo Amorati,[¶] Andrea Baschieri,[¶] Keith U. Ingold,[§] Luca Valgimigli^{¶,*} and Derek A. Pratt^{‡,*}

[‡]Department of Chemistry, University of Ottawa, Ottawa, Ontario K1N 6N5, Canada. [¶]Department of Chemistry "G. Ciamician", University of Bologna, Bologna, I-40126, Italy. [§]National Research Council of Canada, Ottawa, Ontario K1A 0R6, Canada.

ABSTRACT: Persistent dialkylnitroxides (e.g. 2,2,6,6-tetramethylpiperidinoxyl, TEMPO) play a central role in the activity of hindered amine light stabilizers (HALS) – additives that inhibit the (photo)oxidative degradation of consumer and industrial products. The accepted mechanism of HALS comprises a catalytic cycle involving the rapid combination of a nitroxide with an alkyl radical to yield an alkoxyamine that subsequently reacts with a peroxyl radical to eventually reform the nitroxide. Herein, we offer evidence in favour of an alternative reaction mechanism involving the acid-catalyzed reaction of a nitroxide with a peroxyl radical to yield an oxoammonium ion followed by electron transfer from an alkyl radical to the oxoammonium ion to reform the nitroxide. In preliminary work we showed that TEMPO reacts with peroxyl radicals at diffusion-controlled rates in the presence of acids. Now we show that TEMPO can be regenerated from its oxoammonium ion by reaction with alkyl radicals. We have determined that this reaction, which has been proposed to be a key step in TEMPO-catalyzed synthetic transformations, occurs with $k \sim 1-3 \times 10^{10} \text{ M}^{-1} \text{s}^{-1}$ – thereby enabling it to compete with O₂ for alkyl radicals. The addition of weak acids facilitates this chemistry, whereas the addition of strong acids slows the reaction by enabling back electron transfer. The chemistry is shown to occur in hydrocarbon autoxidations at elevated temperatures without added acid due to the *in situ* formation of carboxylic acids, accounting for the long-known catalytic radical-trapping antioxidant activity of TEMPO that prompted the development of HALS.

INTRODUCTION

Radical-trapping antioxidants (RTAs) inhibit the autoxidation of hydrocarbons by trapping the peroxyl radicals (ROO•) that propagate the chain reaction.^{1,2} Phenols and diphenylamines are the archetype RTAs (represented by A-H in Eqs. 1 and 2); they undergo efficient formal H-atom transfer to peroxyl radicals to yield stable RTA-derived radicals that do not continue the chain reaction (A•, Eq. 1). Instead, A• reacts with another peroxyl to yield non-radical products (Eq. 2). Thus, the overall stoichiometry of the ROO•:A-H reaction is 2.

 $A-H + ROO \bullet \to A \bullet + ROOH \tag{1}$

$$A \bullet + ROO \bullet \rightarrow non-radical products$$
 (2)

Nitroxides, such as 2,2,6,6-tetramethylpiperidinoxyl (TEMPO, Scheme 1), have long been of interest as RTAs. Although early work by Brownlie and Ingold found TEMPO to be unreactive to peroxyl radicals at 65°C,³ later work showed that nitroxides were incredibly reactive at higher temperatures.^{4,5} For example, a reaction stoichiometry of 510 was reported for the TEMPO-inhibited autoxidation of paraffin oil at 130°C, making TEMPO (and related hindered nitroxides) the most efficacious RTA(s) ever reported.⁵ This remarkable result coincided with the development of Hindered Amine Light Stabilizers (HALS) - technology now universally used to slow the (photo)oxidation of polymers and other petroleumderived products. HALS generally comprise secondary or tertiary hindered amines that undergo in situ oxidation to nitroxides.⁶ In addition to this application, nitroxides have been explored as potential therapeutic and preventive agents against

degenerative diseases in which lipid autoxidation (peroxidation) have been implicated.⁷

Although nitroxides do not react with peroxyl radicals,^{3,8} they react very quickly with alkyl radicals (Eq. 3).⁹ At low concentrations of O_2 and sufficiently high concentrations of nitroxide, this reaction competes with addition of O_2 to alkyl radicals (which propagates autoxidation) to break one chain reaction. To account for the apparent catalytic RTA activity of TEMPO (or HALS), it is widely accepted that TEMPO is regenerated from the alkoxyamine.⁶ Among the various mechanisms proposed for regeneration,¹⁰ the most reasonable starts with H-atom abstraction from the alkoxyamine by a chain-carrying peroxyl radical (Eq. 4, Scheme 1).^{10,11} This reaction



Scheme 1. The proposed mechanism of hindered amine light stabilizer (HALS) activity.

produces an alkyl radical that rapidly undergoes β fragmentation to yield a carbonyl compound and aminyl radical (Eq. 5), from which TEMPO can be regenerated following reaction with a peroxyl radical (Eq. 6). This series of reactions completes a catalytic cycle wherein the substrate undergoing autoxidation serves as the stoichiometric reductant, and each pass through the cycle traps two chain-carrying radicals.

A short time ago we found that the long-held dogma that nitroxides do not react with oxygen-centered radicals¹² must be applied with care. When autoxidations were carried out at ambient temperatures in the presence of added acid (e.g. acetic acid or trifluoroacetic acid), nitroxides were excellent radicaltrapping antioxidants.¹³ In our preliminary report we showed that TEMPO, when protonated (Eq. 7), reacts with peroxyl radicals at rates approaching the diffusion-controlled limit (e.g. $k_{inh} \sim 1 \times 10^8 \text{ M}^{-1} \text{s}^{-1}$ with 10 mM *p*-TsOH) as in Eq. 8.¹⁴



Furthermore, we showed that in the presence of weak carboxylic acids (e.g. acetic or benzoic acid), very long inhibited periods are observed, during which the nitroxide is not consumed – corresponding to massive stoichiometric numbers 13 – such as those observed in high temperature autoxidations.⁵ Thus, under weakly acidic conditions, TEMPO must be regenerated from its corresponding oxoammonium ion, TEMPO^{+,13} In sharp contrast, in the presence of strong acids (e.g. trifluoroacetic acid), only one peroxyl radical was trapped, suggesting that TEMPO could not be regenerated from TEMPO⁺. At the time of our preliminary communication, the mechanism by which TEMPO was regenerated was elusive, as was the reason it occurred in the presence of weak acids, but not stronger ones. Herein we offer an explanation for these results and demonstrate that it accounts for the remarkable inhibition of autoxidation by nitroxides, and by extension, HALS.

RESULTS

Mechanistic Possibilities. The oxoammonium ion derived from TEMPO is best known for its role as the catalytic oxidant in the oxidation of alcohols to carbonyl compounds.^{15,16} This is believed to occur via a hydride transfer in a non-covalent pre-reaction complex (Eq. 9):

$$R \frown OH + \begin{pmatrix} X^{-} \\ +N = O \end{pmatrix} R \frown O + \begin{pmatrix} N - OH \\ + HX \end{pmatrix} (9)$$

As such, at the conclusion of our preliminary work,¹³ we wondered whether a (somewhat) similar reaction could occur with hydroperoxide products formed during an autoxidation. This reaction would require hydride transfer from the β -carbon with concomitant formation of ¹O₂ (Eq. 10):



The resultant hydroxylamine could then react with a peroxyl radical to regenerate TEMPO - known to proceed readily with $k = 5 \times 10^5 \text{ M}^{-1} \text{s}^{-1}$.³ No precedent exists in the literature for this mechanism. However, the reaction of hydrogen peroxide with TEMPO⁺ was suggested some time ago by Denisov as a key step in the TEMPO-inhibited autoxidation of ethylbenzene.¹ More recently, Goldstein et al. investigated the kinetics of this reaction in water.7b They found that the reaction was only particularly facile at alkaline pH, where electron transfer from the peroxide anion was possible, $cf. k = 5 \times 10^4 \text{ M}^{-1} \text{s}^{-1}$ at pH 8 and 5.1 M⁻¹s⁻¹ at pH 4.^{7b} Given that the latter value must represent the upper bounds in acidified organic solvent, this mechanism would appear to be irrelevant in the current context. Moreover, the reductant in the current context must be a hydroperoxide, not H_2O_2 , which is less acidic and therefore less reactive as an ET reagent. Indeed, when we monitored the kinetics of the reaction of the tetrafluoroborate salt of the oxoammonium ion derived from TEMPO (hereafter TEMPO⁺BF₄⁻) with t-BuOOH in acetonitrile, we obtained a rate constant of only $(4.5\pm0.5)\times10^{-3}$ M⁻¹s⁻¹ (see Supporting Information for details). This value, in light of the modest amount of hydroperoxides that are formed in the early stages of an (inhibited) autoxidation, suggests that this cannot be the mechanism of TEMPO regeneration.

Further consideration of all the species present in the inhibited autoxidations left only one possible candidate to reduce the oxoammonium ion: the chain-carrying alkyl radical, R^{\bullet} (Eq. 11):¹⁸

$$R^{\bullet} + \bigvee_{+N=0} \longrightarrow \bigvee_{N=0^{\bullet}} R^{+} R^{+} (11)$$

Computations carried out at the CBS-QB3 level of theory¹⁹ suggest that this electron transfer reaction is exergonic, with $\Delta G^{\circ} = -3.9$ and -6.1 kcal/mol in the gas phase and acetonitrile, respectively, for R = cumyl (cumene was one of the substrates that we autoxidized in our previous studies).¹³

Product Studies in a Model Reaction. Since inhibited autoxidations are inherently complex, evidence for the reaction in Eq. 11 was initially sought in a model system. Cumyl radicals were generated from the thermal decomposition of azocumene in acetonitrile at 50°C in the presence of TEMPO⁺BF₄⁻ and Me₄NOAc. The latter was included to produce the same TEMPO⁺AcO⁻ species that is expected to form in a TEMPO-inhibited autoxidation in the presence of acetic acid. The reaction products were analyzed by HPLC with UV detection. The results are shown in Figure 1.

In the absence of O_2 (via sparging the solutions extensively with argon), the cumyl-TEMPO adduct was the sole product formed and appeared at a rate coinciding with the rate at which azocumene decomposed.²⁰ This is consistent with the expected reaction sequence shown in Scheme 2. Thus, decom-

 position of azocumene proceeds to yield two cumyl radicals – one of which reduces the oxoammonium ion to TEMPO, and the other reacts with TEMPO to give the observed alkoxyamine product. The same profile was observed in chlorobenzene (see Supporting Information). Similar results were obtained in experiments where azo(phenylethane), which yields secondary 1-phenylethyl radicals, was used in lieu of azocumene (see Supporting Information).



Figure 1. Decomposition of azocumene (\blacksquare) and formation of the cumyl-TEMPO adduct in the presence of TEMPO⁺BF₄⁻ (25 mM) and Me₄N⁺AcO⁻ (25 mM) in acetonitrile at 50°C in the presence of argon (\bullet), air (\blacktriangle) or O₂ (\checkmark).



Scheme 2. Formation of the cumyl-TEMPO adduct from azocumene and TEMPO⁺BF₄⁻.

In the presence of air, the cumyl-TEMPO adduct was also formed, but at a much lower level, whereas when the reaction was carried out under an atmosphere of O₂, no adduct was observed. The lower yields of alkoxyamine in the presence of air were expected given the rapid reaction of cumyl radicals with O₂ ($k \sim 3 \times 10^9$ M⁻¹s⁻¹),²¹ which outcompetes the reaction of cumyl radicals with TEMPO ($k = 1.2 \times 10^8$ M⁻¹s⁻¹).⁹ This is underscored by the complete lack of alkoxyamine formed when the reaction was carried out in the presence of O₂. The addition of acetic acid (25 mM) had no effect on the reaction (see Supporting Information).²² **Inhibited** Autoxidations. If TEMPO is formed from $TEMPO^+$ in an autoxidation, the oxoammonium ion should inhibit the autoxidation similarly to the nitroxide from the outset. Thus, matched styrene autoxidations were carried out where either TEMPO or TEMPO⁺ were added with or without acetic acid. The results are shown in Figure 2. Similar results were obtained in autoxidations of cumene (see Supporting Information).



Figure 2. O₂ consumption during the autoxidation of styrene (4.3 M) in acetonitrile initiated by AIBN (0.05 M) at 30°C (**a**, dotted line), and corresponding experiments carried out in the presence of 13 μ M of either TEMPO⁺BF₄⁻ (**b**, **d**) or TEMPO (**c**, **e**) without (**b**, **c**) or with (**d**, **e**) acetic acid (43 mM).

As we reported in our preliminary communication,¹³ TEMPO + AcOH gave rise to a lengthy inhibited period corresponding to a reaction stoichiometry of n >> 1. When TEMPO⁺BF₄⁻ was used in place of TEMPO, the initial rate of autoxidation was not suppressed to the same extent as with TEMPO, but significant inhibition was still observed. Each of the TEMPO-inhibited and TEMPO⁺-inhibited autoxidations could be modeled using the standard kinetic scheme for the inhibited autoxidation of styrene,²³ but including the proposed inhibition reactions in Eq. (7), (8) and (11), and fit by numerical integration to yield the unknown rate constant $k_{11} = (2.4\pm0.4)\times10^{10} \text{ M}^{-1}\text{s}^{-1}$ (see Supporting Information for the details). The magnitude of this rate constant accounts for the successful competition of TEMPO⁺ with O₂ for reaction with alkyl radicals necessary for this mechanism to be viable.

The combination of TEMPO and AcOH is also effective at inhibiting the autoxidation of styrene in chlorobenzene, but no significant inhibitory activity is observed past n = 1, implying that oxidation by TEMPO⁺ no longer effectively competes with O₂ for alkyl radicals. Indeed, when used directly, TEMPO⁺BF₄⁻ had only a small effect on the autoxidation (Figure 3.). Modelling the data as above yields the rate constant $k_{11} = 1.5 \times 10^9 \text{ M}^{-1} \text{s}^{-1}$, which is similar to the rate constant for the competing reaction of the styryl radicals with O₂ (~3 ×10⁹ M⁻¹ s⁻¹). However, since [O₂] = 2 mM >> [TEMPO⁺] = 13 μ M, this reaction is not competitive and no catalytic activity is observed.



2

3

4

5

6

7

8 9

10

11

12

13 14

15

16

17

18 19 20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

59 60

Figure 3. O₂ consumption during the autoxidation of styrene (4.3 M) in chlorobenzene initiated by AIBN (0.05 M) at 30°C (**a**, dotted line) and corresponding experiments in the presence of 13 μ M of either TEMPO⁺BF₄ (**b**) or TEMPO (**c**) and AcOH (44 mM).

EPR Spectroscopy. To corroborate the foregoing product studies and inhibited autoxidation data, we sought to directly demonstrate that TEMPO is produced from TEMPO⁺ under the conditions of a typical autoxidation. In fact, upon addition of TEMPO⁺BF₄⁻ to an air-saturated solution of either cumene or styrene in acetonitrile containing AIBN as radical initiator, the formation of TEMPO could be observed directly by EPR (Figure 4A).

The evolution of the spectra revealed a rate of TEMPO formation $(3.5 \times 10^{-9} \text{ Ms}^{-1})$ that was only slightly lower than the rate of radical initiation from AIBN decomposition (R_i = 6.1×10⁻⁹ Ms⁻¹).²⁴ (The rate determined in a cumene autoxidation was 5.0×10^{-9} Ms⁻¹ – see Supporting Information.) As a result, since the rate constant for O2 addition to the alkyl radicals derived from AIBN and styrene (or cumene) is $k \sim 3 \times 10^9$ $M^{-1}s^{-1}$, $[O_2] \sim 2 \text{ mM}$ and $[TEMPO^+ BF_4^-] = 0.66 \text{ mM}$, we can estimate that under these conditions $k_{11} \sim 1 \times 10^{10} \text{ M}^{-1} \text{s}^{-1}$. Interestingly, when acetic acid (35 mM) was added to the reaction mixture, the formation of TEMPO was accelerated (compared data sets in Figure 4B), yielding an observed rate that was indistinguishable from the rate of radical initiation and implying that the rate constant for electron transfer had increased to $k_{11} \sim 3 \times 10^{10} \text{ M}^{-1} \text{s}^{-1}$ – in excellent agreement with the rate constant derived from fitting the inhibited autoxidation data (vide supra). It is important to note that no TEMPO was observed in the absence of AIBN. Moreover, in the absence of either cumene or styrene, the formation of TEMPO due to reduction of TEMPO⁺ by AIBN-derived radicals was determined to be much slower $(k_{11} \sim 1 \times 10^8 \text{ M}^{-1} \text{s}^{-1} - \text{see Supporting Infor$ mation).

In chlorobenzene, the rate of formation of TEMPO from TEMPO⁺BF₄⁻ in the presence of the same amount of acetic acid enables derivation of a rate constant of $k_{11} = 2.6 \times 10^9 \text{ M}^{-1} \text{ s}^{-1}$ for the electron transfer – just over an order of magnitude slower than in acetonitrile and in excellent agreement with the kinetic data from the inhibited autoxidations.²⁵



Figure 4. TEMPO formation during the autoxidation of styrene (4.3 M) in acetonitrile initiated by AIBN (50 mM) at 30°C in the presence of TEMPO⁺BF₄⁻ (0.66 mM). Top: representative EPR spectra. Bottom: rate with (\bullet) and without (\blacksquare) added acetic acid (35 mM).

On the Addition of Strong Acids. Each of the three foregoing experiments were also carried out with TFA in place of AcOH. The data are presented in the Supporting Information. To summarize the results: 1) significantly lower yields of the cumyl-TEMPO adduct were observed when azocumene was decomposed in the presence of TEMPO⁺BF₄⁻ and TFA instead of AcOH, 2) the combination of TEMPO⁺BF₄⁻ and TFA did not inhibit the autoxidation of styrene in acetonitrile, and 3) no TEMPO was observed by EPR spectroscopy when AIBN was decomposed in the presence of TEMPO⁺BF₄⁻ and TFA instead of AcOH.

The simplest explanation for the lack of regeneration of TEMPO from TEMPO⁺ in the presence of a strong acid is that it is destroyed under these conditions. Indeed, Ma and coworkers have suggested that TEMPO⁺ is unstable in the presence of H₂SO₄ at elevated temperatures (100°C, monitored by UV-Vis spectroscopy),²⁶ where it is believed to eliminate HNO, eventually yielding unsaturated aliphatic products (Scheme 3). However, when we subjected TEMPO⁺BF₄⁻ (400 μ M) to 10 mM TFA in acetonitrile at 50°C, no change was observed in the UV-Vis spectrum over the course of 1 hour.²⁷

2

3

4

5 6 7

8

9

10

11

12

13

14

15

16

17

18

19

20

21 22

27

28

29

30 31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58 59 60



Scheme 3. Proposed mechanism for the decomposition of TEMPO^+ in the presence of strong acid.

Since the oxoammonium ion was stable under the reaction conditions, we next considered the possibility that the key electron transfer reaction (Eq. 11) was reversible. If so, the strength of the acid and/or the nucleophilicity of its conjugate base, are expected to influence the position of the key redox equilibrium in Scheme 4.



Scheme 4. Reactions influencing the reversibility of the electron transfer between TEMPO⁺ and an alkyl radical.

Thus, the more acidic the medium, the less favourable will be loss of a proton from the carbocation and/or the trapping of the carbocation by the less nucleophilic conjugate base. Indeed, if a strong acid (e.g. HBF_4) is added to a TEMPO/AcOH-inhibited autoxidation, the catalytic effect disappears (Figure 5).²⁸ Likewise, if an excess of the conjugate base of the strong acid (e.g. Oct_4NBF_4) is added, the catalytic effect decreases substantially (Figure 5). The latter result suggests that the oxidation potential of TEMPO⁺ is also dependent on the identity of the counterion.



Figure 5. O_2 consumption during the autoxidation of styrene (4.3 M) in acetonitrile containing 1% H₂O initiated by AIBN (0.05 M)

at 30°C (**a**) and corresponding experiments in the presence of TEMPO (13 μ M) and acetic acid (43 mM) (**b**), acetic acid (43 mM) and Oct₄NBF₄ (0.13 M) (**c**), acetic acid (43 mM) and HBF₄ (43 mM) (**d**), and acetic acid (43 mM) with HBF₄ (43 mM) added at the time indicated by the arrow (**e**).

Autoxidations at Elevated Temperatures. Given the effect of weak acids on the RTA activity of nitroxides at ambient temperatures, we wondered whether the addition of a weak acid could bolster the activity of nitroxides at elevated temperatures as well. Consequently, we examined the effect of a nitroxide/acid combination on the autoxidation of paraffin oil in a stirred flow reactor at 160°C.^{29,30} The reaction was initiated with a small amount of tetralin hydroperoxide (5 mM) and a dispersed stream of O₂ was continuously passed through the solution to stir the medium and prevent mass transfer of O₂ from becoming rate limiting. Aliquots were removed at regular time intervals and the hydroperoxide concentration in each was determined using our previously described pro-fluorescent phosphine (1).³¹



Since TEMPO is somewhat volatile at 160°C, a higher molecular weight analogue (2) was investigated, along with palmitic acid in lieu of the acetic acid used at ambient temperatures.³² The results are shown in Figure 6A.



Addition of the bis-nitroxide 2 to the paraffin autoxidation vielded the expected sigmoidal profile of hydroperoxide production in an inhibited autoxidation at elevated temperatures.³³ Although inclusion of 4 mM palmitic acid to the reaction mixture did not significantly improve the inhibitory activity of 2, a higher loading (40 mM) produced a significant increase in the inhibited period. At first glance, the lack of effect of the lesser amount of acid and the fact that 2 is capable of inhibiting the autoxidation in the absence of added acid, suggested that the acid-catalyzed reaction mechanism accounts for only a fraction of the activity of nitroxides at elevated temperatures. However, the autoxidation of paraffinic hydrocarbons is known to produce carboxylic acids (in addition to hydroperoxides) from the very early stages of the reaction.^{34,35} Therefore, acids formed in situ may activate the nitroxide to reaction with peroxyl radicals. To probe this possibility, we added 4 and 40 mM of the non-volatile, non-nucleophilic base 2,4,6-tri-tertbutylpyridine (TTBP) to autoxidations inhibited by 2, and found that it progressively diminished the RTA activity of the nitroxide. Importantly, the addition of either acid or base had no effect on the rate of the uninhibited autoxidation, suggesting that these additives play no role other than modulating the pH of the reaction (see Supporting Information for more data).

To confirm that carboxylic acids were present in the paraffin autoxidations, they were determined using the aminated coumarin derivative **3**, whose fluorescence is greatly enhanced (38-fold) upon protonation (see Supporting Information for details).³⁶ The results are shown in Figure 6B.



1

2

3

4

5

6

7 8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57 58

59 60 The commercially-sourced light paraffin oil contained 0.14 mM carboxylic acid, and upon equilibrating the sample under a N₂ atmosphere and then heating to 160°C this increased to 0.5 mM.³⁷ Addition of the initiator and changing the atmosphere to O₂ lead to a rapid accumulatation of acid, reaching 15 mM within 1500 s. In the inhibited autoxidations, the production of carboxylic acids mirrored the formation of hydroperoxides (albeit at lower absolute levels) - consistent with the potent antioxidant activity of **2** and its diminution upon addition of base to the autoxidation.



Figure 6. Hydroperoxide (top) and acid (bottom) formation in the autoxidation of light paraffin oil at 160°C initiated by 5 mM tetralin hydroperoxide (\blacksquare) and inhibited by 40 μ M 2 (\checkmark) with 4 mM palmitic acid (\succ), 40 mM palmitic acid (\diamond), 4 mM 2,4,6-(*t*-Bu)₃pyridine (\blacklozenge) or 40 mM 2,4,6-(*t*-Bu)₃pyridine (\blacklozenge).

DISCUSSION

Despite the widespread use of HALS, their mechanism has remained a mystery since the suggestion that nitroxides must be the key intermediate in a catalytic radical-trapping cycle.⁶ The commonly presented mechanism (Scheme 1) requires the nitroxide to compete with O₂ for alkyl radicals, but it is well known that the $R^{\bullet} + O_2$ reaction is 20- to 30-fold faster than the reaction of R^{\bullet} with TEMPO.^{9,21} This is irrelevant if the TEMPO/O₂ concentration ratio is large, but in many of the experiments that established the unique reactivity of HALS this condition is not fulfilled (likewise for the conditions under which HALS-containing materials are manipulated and/or used). For example, in the pioneering experiments carried out by Bolsman, Blok and Frijns,⁵ which showed a stoichiometric number of 510 for the inhibition of paraffin oil autoxidation, only 1-4 μ M TEMPO was used. Given that $[O_2] \sim 2 \text{ mM}$,³⁸ the rate of alkoxyamine formation must be at least 10,000-times *slower* than the rate of peroxyl radical formation.

Nevertheless, if alkoxyamines are indeed formed in these reactions, they must decompose to regenerate the nitroxide to complete the catalytic cycle. Recent computations and a reinterpretation of literature data, led to the conclusion¹⁰ that it must be via the sequence of Eq. (4), (5) and (6) in Scheme 1: H-atom abstraction from the position adjacent the O-atom in the alkoxyamine, followed by β -fragmentation of the resultant alkyl radical to give an aminyl radical, and then oxidation to give the nitroxide - as suggested earlier by Bolsman, Blok and Frijns.¹¹ Whilst it seems guite clear that this is the mechanism of the reaction of an alkoxyamine with peroxyl radicals, it is unlikely to be kinetically relevant in an inhibited autoxidation. In fact, we have attempted to measure the rate constant for the reaction of a model alkoxyamine (O-allyl-TEMPO) with peroxyl radicals using the radical clock approach and found that it proceeds with $k \le 1 \text{ M}^{-1}\text{s}^{-1}$ at 37°C, expectedly similar to Hatom abstraction from the α -CH₂ group of an ether.³⁹ Assuming $\log A = 8$ for this H-atom transfer⁴⁹ suggests that the rate constant could be as big as $\sim 70 \text{ M}^{-1}\text{s}^{-1}$ at 130°C, but given that the alkoxyamine can be present at only 1-4 µM at most (assuming all of the TEMPO added in the first place is converted to the alkoxyamine), this means that this reaction must be ca. 6 orders of magnitude too slow to compete with chain propagation (which has k[substrate] ~ 90 s⁻¹)^{11,40} in Bolsman, Blok and Frijns' pioneering experiment.

Given our observation that TEMPO becomes an effectively catalytic RTA in the presence of weak acid at room temperature, it seemed reasonable to consider this as an alternative to the currently accepted mechanism. Indeed, the addition of acid to a paraffin oxidation at 160°C improved the already catalytic RTA activity of bis(nitroxide) 2, but more importantly, the addition of base was able to wipe it out in a dose-dependent manner (i.e. the activity of the nitroxide correlated with the amount of acid present). This must rule out the mechanism in Scheme 1, or any mechanism which invokes H-atom abstraction from the alkoxyamine in the turnover limiting step, since it cannot account for these observations. Moreover, the bis(oxoammonium) derived from 2 inhibited the paraffin oxidation similarly to 2 itself. Therefore, we suggest that the unique reactivity of nitroxides as RTAs (and HALS, in general) is better accounted for by the mechanism shown in Scheme 5.

2

3

4

5

6

7

8

9 10

11 12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44 45 46

47

48

49

50

51 52

53

54

55

56

57

58 59 60



Scheme 5. Proposed mechanism of acid-catalyzed RTA activity of nitroxides.

Although this mechanism still requires the participation of an alkyl radical in the catalytic cycle, the reaction it undergoes is an electron transfer (to regenerate the nitroxide from the oxoammonium ion), which has been shown to compete effectively with its combination with O_2 (*vide supra*).

Diarylamines are also common additives to petroleumderived products, but because their oxidation products are highly coloured, they are generally not used in applications where colour changes are undesirable (e.g. in lightly coloured plastics). Given that diarylamines are secondary amines whose catalytic activity also depends on the formation of a nitroxide intermediate (cf. Scheme 6),⁴¹ it is possible that the mechanism in Scheme 5 could also contribute to their activity.^{42,43} However, it is expected that: 1) alkoxyamine formation will be slightly faster for $Ar_2NO^{\bullet} + R^{\bullet}$ than for TEMPO $^{\bullet} + R^{\bullet}$ due to reduced steric hindrance, 2) unimolecular decomposition of the resultant Ar_2NOR to regenerate Ar_2NH has a lower barrier than the return of the nitroxide,⁴³ 3) the diaryl nitroxide will be less basic than TEMPO, and 4) the diaryloxoammonium ion will be a weaker oxidant than the TEMPO⁺. Moreover, in related work, we found that acid formation diminishes the activity of some Ar₂NH.³⁰



Scheme 6. Proposed mechanism of catalytic activity of diarylamine RTAs.

Although the secondary amines found in HALS are far less reactive toward peroxyl radicals than diarylamines, HALS have the distinct advantage that the nitroxide intermediate in their catalytic cycle is persistent and does not undergo deleterious reactions with peroxyl radicals. The same cannot be said for the nitroxides derived from diarylamines, which undergo competing reactions with peroxyl radicals at ring carbon atoms,³ leading to complex mixtures of products,⁴⁴ and precluding continuation of the cycle in Scheme 5.

$$ROO^{\bullet} + \bigcup^{\bullet} \stackrel{\circ}{\bigvee} \stackrel{\circ}{\longrightarrow} \underset{H}{\longrightarrow} \stackrel{\circ}{\longrightarrow} \stackrel{\circ}{\longrightarrow} \stackrel{\circ}{\longrightarrow} \stackrel{\circ}{\longrightarrow} (12)$$

This fact underscores the unique reactivity of HALS, but also prompts the question: what eventually leads to exit from the nitroxide's catalytic cycle? Why are nitroxides not infinitely reactive? The answer to this question may provide the key to the design of the ultimate hindered amine light stabilizers.

CONCLUSIONS

For the past 40 years there has been widespread agreement that nitroxides are key intermediates in the catalytic activity of hindered amine light stabilizers, but the precise mechanism has been elusive. The formation of an alkoxyamine, and its subsequent decomposition to reform a nitroxide, was believed to comprise the catalytic cycle. However, for the reasons discussed above, this cannot account for the reactivity of nitroxides as autoxidation inhibitors under most conditions. Instead, we have advanced the more plausible proposal that 1) protonation of the nitroxide creates a potent formal H-atom donor which reacts with a peroxyl radical,¹⁴ and 2) the resultant oxoammonium ion oxidizes an alkyl radical, regenerating the nitroxide. The latter electron transfer has been shown to be competitive with O2 addition in both model systems and authentic autoxidations $(k_{11} = 1-3 \times 10^{10} \text{ M}^{-1} \text{s}^{-1})$. This pathway provides a more plausible explanation for the catalytic activity of nitroxides as RTAs and also supports a role for this electron transfer reaction in TEMPO-mediated synthetic transformations. The ability of nitroxides to inhibit the autoxidation of hydrocarbons at high temperature is shown to depend on acid formation in situ. We have shown that the proposed catalytic cycle is also fully operative at ambient temperatures, suggesting that it may be of biological relevance and may contribute to the biological activity of TEMPO and related nitroxides.⁷

EXPERIMENTAL SECTION

Reagents and solvents were purchased from commercial sources and used without further purification unless otherwise indicated. TEMPO⁺BF₄^{-,45} azocumene,⁴⁶ bis(nitroxide) $\mathbf{1}$,⁴⁷ phosphine $\mathbf{2}^{31}$ and BODIPY $\mathbf{3}^{36}$ were synthesized by literature precedent. Oxidizable substrates (cumene, styrene, paraffin oil) were carefully purified from stabilizers and hydroperoxides before use and were stored refrigerated under nitrogen.

Model Reactions. TEMPO⁺BF₄⁻ (12 mg, 50 μ mol) and tetramethylammonium acetate (6.7 mg, 50 μ mol) were added to a 3 mL vial. The contents were dissolved in acetonitrile (sparged

with either argon or oxygen if necessary) and placed under the appropriate atmosphere. To this, azocumene (13 mg, 50 μ mol) was added. The contents were heated and stirred at 50°C. Aliquots (100 μ L) were removed every 40 minutes and diluted to 1 mL with methanol containing 2.8 mM hexylbenzene. Samples were analyzed on a Waters Acquity H-Class UPLC equipped with a XTerra® RP-18 Column (5 μ M × 4.6 mm × 150 mm) using 20% H₂O in methanol at a flow rate of 0.4 mL/min and detection at 216 nm.

Inhibited Autoxidations. Experiments were performed in a two-channel oxygen uptake apparatus, based on a Validyne DP 15 differential pressure transducer.⁴⁸ In a typical experiment, an air-saturated solution of either styrene or cumene containing AIBN was equilibrated with an identical reference solution containing also excess of 2,2,5,7,8-pentamethyl-6hydroxychromane (PMHC) (25 mM). After equilibration, and when a constant O₂ consumption was reached, a stock solution of TEMPO or TEMPO⁺BF₄⁻ (final concentration: 5-50 μ M) and a stock solution of the desired acid were injected in the sample flask. The oxygen consumption in the sample was measured, after calibration of the apparatus, from the differential pressure recorded with time between the two channels. Rates of initiation, R_{i} , were determined for each conditions in preliminary experiments by the inhibitor method using PMHC as reference antioxidant: $R_i = 2$ [PMHC] / τ , where τ is the length of the induction period. Kinetic traces were analyzed by numerical fitting using GEPASI software.

EPR measurements. EPR spectra were recorded in a Xband spectrometer equipped with temperature control, with the following settings: microwave power 6.3 mW, time constant and conversion time 20.48 ms, modulation amplitude 1.0 G. Typical samples contained TEMPO⁺BF₄ (0.5 - 5 mM), AIBN (0.05 M) and styrene or cumene (40-50% v/v) in MeCN or PhCl and were air-saturated. Samples were transferred in a capillary glass tube and were placed in the thermostatted instrument cavity at 303 K, so to cover the entire sensitive area. CH₃COOH and CF₃COOH (30-50 mM), where added to the sample as indicated. Absolute concentration of TEMPO formed in the sample was determined upon calibration with standard solutions in the corresponding solvent mixture. Time evolution of the EPR signal was monitored by an automated acquisition routine and analyzed using either the intensity of the first spectral line or the double integration of the whole spectrum.

Paraffin Autoxidations. Paraffin autoxidations were carried out using an analogous procedure to hexadecane autoxidations previously carried out by our group.^{30,31} Light paraffin oil (100 mL) was thoroughly degassed with N₂ and then heated to 160° C in a stirred flow reactor. Once the temperature stabilized, 0.04 mmol of bis(2,2,6,6-tetramethylpiperidin-1-oxyl-4yl) decanedioate (2), the appropriate amount of either palmitic acid or 2,4,6-tri-*tert*-butyl pyridine, and 82 mg (0.5 mmol) of tetralin hydroperoxide⁴⁹ were added to the solution. The flow of N₂ was replaced with 1 L/min O₂. Aliquots (0.5 mL) were removed every 5 minutes and allowed to cool to room temperature for analysis.

Four duplicates (30 μ L) of each sample were loaded into a 96-well microplate. Each well was read sequentially following manipulation as follows: an automated reagent dispenser was used to dilute the sample with *tert*-amyl alcohol (200 μ L) and

the plate was stirred for 28 s, after which a solution of fluorogenic phosphine **1** (20 μ L of a 250 μ M stock solution in acetonitrile) was injected and the plate stirred for an additional 8 seconds and then allowed to rest for 2 more seconds. The fluorescence of each well was measured every 1.3 seconds for 30 seconds (excitation = 340 nm; emission = 425 nm). The concentration of hydroperoxide was determined from the rate of phosphine oxidation using the rate constant for the reaction of the dye with secondary hydroperoxides in *tert*-amyl alcohol (1.2 M⁻¹ s⁻¹) assuming pseudo-first-order kinetics.³¹

In tandem, four duplicates (1.2 μ L) of each sample were loaded into separate wells of a 96-well microplate and the automated reagent dispenser of the microplate reader used to dilute each sample with 25% isopropyl alcohol in methanol (280 μ L) and the plate was stirred for 15 seconds. Afterward, a solution of fluorogenic amine **3** (20 μ L of a 630 μ M stock in methanol) was added. The plate was stirred for 8 seconds and the fluorescence of each well was measured every second for 10 s (excitation = 315 nm; emission = 395 nm).

ASSOCIATED CONTENT

Supporting Information

Synthetic details and results of model studies, inhibited autoxidations, EPR experiments, and paraffin autoxidations referred to, but not included in, the manuscript. The Supporting Information is available free of charge on the ACS Publications website.

AUTHOR INFORMATION

Corresponding Authors

dpratt@uottawa.ca

luca.valgimigli@unibo.it

ACKNOWLEDGEMENTS

This work was supported by grants from the Natural Sciences and Engineering Research Council of Canada, the Canada Foundation for Innovation, the Italian Ministry of Education (MIUR, Rome; project 2010PFLRJR, PROxi) and the University of Bologna (FARB project FFBO123154). DAP acknowledges support from the University of Ottawa and the Canada Research Chairs program, respectively. EAH acknowledges the support of an Ontario Graduate Scholarship. We thank Prof. Claudio Zannoni and Prof. Alberto Arcioni for access to EPR equipment, and Dr. Isabella Miglioli for assistance with EPR experiments.

REFERENCES

- ¹ Ingold, K. Chem. Rev. 1961, 61, 563-589.
- ² Ingold, K. U.; Pratt, D. A. Chem. Rev. 2014, 114, 9022–9046.
- ³ Brownlie, I. T.; Ingold, K. U. Can. J. Chem. 1967, 45, 2427-2432.

⁴ Sudnik, M. V.; Romantsev, M. F.; Shapiro, A. B.; Rozantsev, E. G. Bull. Acad. Sci. USSR **1976**, 24, 2702-2704.

⁵ Bolsman, T.; Blok, A.; Frijns, J. Reel. des Trav. Chim. des Pays-Bas 1978, 97, 310–312.

⁶ See the following reviews on the subject: (a) Allen, N. S. *Chem. Soc. Rev.* **1986**, *15*, 373-404; (b) Gugumus, F. *Polym. Degrad. Stab.* **1993**, *40*, 167–215; (c) Pospisil, J. *Adv. Polym. Sci.* **1995**, *124*, 87–189.

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56 57

58 59 60

⁷ See for example: (a) Samuni, A. M.; Goldstein, S.; Russo, A.; Mitchell, J. B.; Krishna, M. C.; Neta, P. J. Am. Chem. Soc. 2002, 124, 8719-8724; (b) Goldstein, S.; Merenyi, G.; Russo, A.; Samuni, A. J. Am. Chem. Soc. 2003, 125, 789-795; (c) Borisenko G. G.; Martin I.; Zhao Q.; Amoscato A. A.; Kagan, V. E. J. Am. Chem. Soc. 2004, 126, 9221-9232; (d) Wipf, P.; Xiao, J.; Jiang, J.; Belikova, N. A.; Tyurin, V.; Fink, M. P.; Kagan, V. E. J. Am. Chem. Soc. 2005, 127, 12460-12461; (e) Dikalova, A. E., Bikineyeva, A. T., Budzyn, K., Nazarewicz, R. R., McCann, L., Lewis, W., Harrison, D. G., and Dikalov, S. I. Circ. Res. 2010, 107, 106-116; (f) Ji, J., Kline, A. E., Amoscato, A., Samhan-Arias, A. K., Sparvero, L. J., Tyurin, V. A., Tyurina, Y. Y., Fink, B., Manole, M. D., Puccio, A. M., Okonkwo, D. O., Cheng, J. P., Alexander, H., Clark, R. S. B., Kochanek, P. M., Wipf, P., Kagan, V. E., and Bayir, H. Nature Neurosci. 2012, 15, 1407-1413; (g) Canistro, D.; Boccia, C.; Falconi, R.; Bonamassa, B.; Valgimigli, L.; Vivarelli, F.; Soleti, A.; Genova, M. L.; Lenaz, G.; Sapone, A.; Zaccanti, F.; Abdel-Rahman, S. Z.; Paolini, M. J. Gerontol. A Biol. Sci. Med. Sci. 2015, 70, 936-943.

⁸ Kovtun, G. A.; Aleksandrov, A. L.; Golubev, V. A. Bull. Acad. Sci. USSR **1974**, 22, 2115-2121.

⁹ (a) Bowry, V. W.; Ingold, K. U. J. Am. Chem. Soc. **1992**, 114, 4992– 4996; (b) Sobek, J.; Martschke, R.; Fischer, H. J. Am. Chem. Soc. **2001**, 123, 2849–2857.

¹⁰ Gryn'ova, G.; Ingold, K. U.; Coote, M. L. J. Am. Chem. Soc. **2012**, 134, 12979–12988.

¹¹ Bolsman, T.; Blok, A.; Frijns, J. Recl. des Trav. Chim. des Pays-Bas **1978**, 97, 313–319.

¹² This can be found throughout the literature, in particular the two areas where nitroxide radical chemistry is particularly important: radical polymerization (Matyjaszewski, K.; Davis, T. P. *Handbook of Radical Polymerization*; Wiley: Hoboken, NJ, 2002) and spin-labeling (Kocherginsky, N.; Swartz, H. M. *Nitroxide Spin Labels: Reactions in Biology and Chemistry*; CRC Press: Boca Raton, FL, 1995).

¹³ Amorati, R.; Pedulli, G. F.; Pratt, D. A.; Valgimigli, L. *Chem. Commun. (Camb).* **2010**, *46*, 5139–5141.

¹⁴ The role of an acid-mediated disproportionation of TEMPO to produce the corresponding hydroxylamine was ruled out on kinetic grounds (see reference 13). However, it is also possible that the reaction takes place by a coupled proton-electron transfer wherein a proton is transferred from the acid to the peroxyl radical concerted with the movement of an electron from TEMPO to the peroxyl. Since we found that there is a primary kinetic isotope effect on these reactions, a Hatom must be in flight in the RDS of the reaction, precluding any rapid pre-equilibrium between peroxyl and protonated peroxyl, such as that which is involved when phenols react with peroxyl radicals under acidic conditions, see: Valgimigli, L.; Amorati, R.; Petrucci, S.; Pedulli, G. F.; Hu, D.; Hanthorn, J. J.; Pratt, D. A. *Angew. Chem. Intl. Ed.* **2009**, *48*, 8348-8351.

¹⁵ Sheldon, R. A.; Arends, I. W. C. E.; Brink, G.-J.; Dijksman, A. *A*α. *Chem. Res.* **2002**, *35*, 774–781.

¹⁶ (a) Bailey, W. F.; Bobbitt, J. M.; Wiberg, K. B. J. Org. Chem. 2007, 72, 4504–4509; (b) Hoover J. M.; Ryland B. L.; Stahl S. S.; J. Am. Chem. Soc., 2013, 135, 2357–2367; (c) Ryland B. L.; McCann S. D.; Brunold, T. C.; Stahl S. S. J. Am. Chem. Soc., 2014, 136, 12166–12173.

¹⁷ Denisov, E. T. Polym. Degrad. Stab. 1991, 34, 325-332.

¹⁸ Baran has invoked this electron transfer in a mechanistic proposal for the guided desaturation of unactivated alkanes. See: Voica, A.-F.; Mendozza, A.; Gutekunst, W. R.; Fraga, J. O.; Baran, P. S. *Nature Chem.* **2012**, *4*, 629-635.

¹⁹ Montgomery, J. A.; Frisch, M. J.; Ochterski, J. W.; Petersson, G. A. *J. Chem. Phys.* **1999**, *110*, 2822-2827.

²⁰ The induction period observed in the alkoxyamine formation is due to the necessary accumulation of TEMPO to outcompete the oxoammonium ion for the cumyl radicals.

²¹ Maillard, B.; Ingold, K. U.; Scaiano, J. C. J. Am. Chem. Soc. **1983**, 105, 5095–5099.

²² Interestingly, corresponding reactions carried out in the absence of Me₄NAcO yielded lower amounts of alkoxyamine were observed. The effect of couterions to the oxoammonuim ion will be discussed below.

²³ Burton, G. W.; Doba, T.; Gabe, E.; Hughes, L.; Lee, F. L.; Prasad, L.; Ingold, K. U. J. Am. Chem. Soc. **1985**, 107, 7053-7065.

 $^{\rm 24}$ Calculated from the inhibition time in ${\rm O}_2$ uptake auotxidations inhibited by PMHC.

 25 In the absence of acid the initial rate is noticeably slower and nonlinear – increasing with time, perhaps due to depletion of O₂ over the longer period of time and improving the competition with alkyl radicals – see Figure S16 in the Supporting Information.

²⁶ Ma, Y.; Loyns, C.; Price, B.; Chechik, V. Org. Biomol. Chem., **2011**, 9, 5573-5578.

 27 It should be pointed out that the spectral characteristics ascribed to TEMPO⁺ by Ma *et al.*²⁶ do not correspond to those reported by other investigators, e.g. Goldstein et al.^{7b} or those determined in our own laboratory. See ref. 7b for a discussion.

²⁸ Numerical fitting of styrene autoxidations in MeCN (30°C) inhibited by TEMPO (or TEMPO⁺) in the presence of TFA (4.3 mM) and HBF₄ (4.3 mM) afforded $k_{11} \sim 1 \times 10^9 \,\text{M}^{-1}\text{s}^{-1}$ and $< 10^9 \,\text{M}^{-1}\text{s}^{-1}$, respectively.

²⁹ Jensen, R. K.; Korcek, S.; Mahoney, L. R.; Zinbo, M. J. Am. Chem. Soc. **1979**, 101, 7574–7584.

³⁰ Shah, R.; Haidasz, E. A.; Valgimigli, L.; Pratt, D. A. J. Am. Chem. Soc. 2015, 137, 2440–2443.

³¹ Hanthorn, J.; Haidasz, E.; Gebhardt, P.; Pratt, D. *Chem. Commun.* **2012**, *48*, 10141–10143.

 32 A sample of TEMPO heated in a vial to 160°C lost aa 60% of its mass over the course of 1 hour.

 33 This arises due to the three distinct phases observable in the initial part of the reaction; the inhibited autoxidation, the uninhibited autoxidation where propagation proceeds at a constant rate and the slowing of propagation in favour of termination with increasing concentration of hydroperoxides, which increase radical concentration upon thermolysis. Similar data was obtained when the corresponding bis-oxoammonium ion was added in lieu of **2** (see Supporting Information).

³⁴ Jensen, R. K.; Korcek, S.; Mahoney, L. R.; Zinbo, M. J. Am. Chem. Soc. **1981**, 103, 1742–1749.

³⁵ Jalan, A.; Alecu, I. M.; Meana-Pañeda, R.; Aguilera-Iparraguirre, J.; Yang, K. R.; Merchant, S. S.; Truhlar, D. G.; Green, W. H. *J. Am. Chem. Soc.* **2013**, *135*, 11100–11114.

³⁶ Shah, R.; Pratt, D. A. In preparation.

 37 This increase is likely the result of thermal decomposition of γ -dihydroperoxides present at concentration below those reliably determined by our method (*aa.* 1 mM).

³⁸ Bolsma, Blok and Frijns suggest $[O_2] \sim 10^{-3}$ mM in paraffin at 130°C under an atmosphere of O₂, but do not provide a reference or details of the measurement.¹¹ Korcek and co-workers report $[O_2] = 2.65$ mM in hexadecane at 160°C under an atmosphere of O₂, which they determined directly, see: Jensen, R. K.; Korcek, S.; Zinbo, M. *Oxid. Commun.* **1990**, *13*, 258-262.

³⁹ Up to 2.7 M of 2,2,6,6-tetramethyl-1-(2-propenyloxy)-piperidine had no detectable influence on the product distribution in a methyl linoleate clocking experiment (carried out as described in Roschek, B.; Tallman, K. A.; Rector, C. L.; Gillmore, J. G.; Pratt, D. A.; Punta, C.; Porter, N. A. J. Org. Chem. **2006**, *71*, 3527–3532). The maximum rate

constant for transfer from the H-atom donor under these conditions is 1 $M^{-1}s^{-1}$. For comparison, the propagation rate constant for H-atom transfer from isopropyl *tert*-butyl ether (a reasonably similarly hindered ether) has been measured as $k_p = 0.02 M^{-1}s^{-1}$, see: Howard, J. A.; Ingold, K. U. *Can. J. Chem.* **1970**, *48*, 873–880.

⁴⁰ Bennett, J. E.; Eyre, J. A.; Summers, R. J. Chem. Soc. Perkin Trans. 2 1974, 797–800.

⁴¹ Adamic, K.; Dunn, M.; Ingold, K. U. *Can. J. Chem.* **1969**, *47*, 287–294.

⁴² Jensen, R. K.; Korcek, S.; Zinbo, M.; Gerlock, J. L. J. Org. Chem. **1995**, *60*, 5396–5400.

⁴³ Haidasz, E. A.; Shah, R.; Pratt, D. A. J. Am. Chem. Soc. **2014**, *136*, 16643–16650.

44 Pospisil, J. Polymer Degrad. Stab. 1991, 34, 85-109.

⁴⁵ Holan, M.; Jahn, U. Org. Lett. **2014**, 16, 58–61.

⁴⁶ Ikeda, H.; Hoshi, Y.; Namai, H.; Tanaka, F.; Goodman, J. L.;
Mizuno, K. *Chem. - A Eur. J.* 2007, *13*, 9207–9215.

⁴⁷ Valgimigli, L.; Pedulli, G. F.; Paolini, M. *Free Radic. Biol. Med.* **2001**, *31*, 708-716.

⁴⁸ Amorati, R.; Pedulli, G. F.; Valgimigli, L. Org. Biomol. Chem., **2011**, *9*, 3792–3800

49 Knight, H. B.; Swern, D. Org. Synth. 1954, 34, 90-91.

⁵⁰ Benson, S. W. *Thermochemical Kinetics, 2nd Ed.*; Wiley: New York, NY, 1976.

TOC Graphic:

