View Article Online View Journal

# ChemComm

# Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: Y. Shen, S. M. Shepard, C. J. Reed and P. L. Diaconescu, *Chem. Commun.*, 2019, DOI: 10.1039/C9CC01076A.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the **author guidelines**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the ethical guidelines, outlined in our <u>author and reviewer resource centre</u>, still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/chemcomm

# **Journal Name**



# Zirconium Complexes Supported by a Ferrocene-Based Ligand as Redox Switches for Hydroamination Reactions

Yi Shen,<sup>a</sup> Scott M. Shepard,<sup>a,b</sup> Christopher J. Reed,<sup>c</sup> and Paula L. Diaconescu<sup>a,\*</sup>

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

Published on 08 April 2019. Downloaded by Idaho State University on 4/10/2019 9:13:55 AM

The synthesis of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> (thiolfan\*= 1, 1'-bis(2,4-di-*tert*butyl-6-thiophenoxy)ferrocene) and its catalytic activity for intramolecular hydroamination are reported. *In situ* oxidation and reduction of the metal complex results in reactivity towards different substrates. The reduced form of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> catalyzes hydroamination reactions of primary aminoalkenes, whereas the oxidized form catalyzes hydroamination reactions of secondary aminoalkenes.

Redox-switchable catalysis is a field of growing importance, in which a redox-active functionality is incorporated within the framework of a metal complex.1-7 Historically, the oxidation or reduction of a transition metal catalyst results in a change in the metal's oxidation state; this may result in compound degradation or loss of catalytic activity. As an alternative, the integration of a redoxactive ligand into a metal complex provides a controllable way of tuning its electronic properties, potentially inducing selectivity or new catalytic activity with changing the redox state.<sup>5-7</sup> The activity of a metal complex supported by a redox-active ligand can be influenced in situ by the redox event occurring at the ligand via a chemical or electrochemical process. Redox switchable catalysis has been applied successfully to the ring-opening polymerization of cyclic esters and ethers,<sup>8-21</sup> and to olefin polymerization.<sup>5, 22-26</sup> Polymerization is so far the only area of redox switchable catalysis in which two orthogonal reactions could be coupled, resulting in the synthesis of block copolymers.<sup>9-12, 14-16, 19, 20, 27-32</sup>

The first example using a metallocene redox switch in order to influence catalytic activity was reported by Wrighton and co-workers in 1995 (Figure 1).<sup>33</sup> In that seminal work, the authors showed that a rhodium complex containing cobaltocene (reduced form) is a better catalyst for the hydrogenation of olefins than the corresponding compound incorporating cobaltocenium (oxidized form). The reverse trend was observed in the hydrosilylation of acetone. It is important to note that the two states of the catalytically active species did not achieve an on/off switch for either reaction.

\* Corresponding author, email: pld@chem.ucla.edu

Electronic Supplementary Information (ESI) available: synthetic and catalytic data. See DOI: 10.1039/x0xx00000x

This journal is C The Royal Society of Chemistry 20xx



Fig. 1 The first reported example of a redox switchable catalyst.

Since then, several groups have become interested in applying redox switchable catalysis to organic synthesis using homogeneous catalysts.<sup>34-54</sup> These efforts fall into two categories: (1) different reaction rates for the two catalytically distinct states that apply to a single reaction (including on/off switches); (2) different reaction rates for the two catalytically distinct states that apply to distinct reactions but without orthogonality, i.e., each catalytic state is active in both reactions but with different rates. The first category contains ring closing metathesis,<sup>34, 35, 41, 47</sup> ring-opening metathesis polymerization,<sup>48</sup> oxidation of dihydrogen,<sup>36, 37</sup> oxazoline formation, furan formation, phenol formation,<sup>43, 49, 50</sup> cyclization of alkynes with furans,<sup>52</sup> hydroalkoxylation,<sup>46</sup> hydroamination,<sup>51, 52</sup> hydrosilylation,<sup>45</sup> acetonitrile dissociation,<sup>39</sup> Kumada coupling,<sup>42</sup> Buchwald-Hartwig cross-coupling,<sup>44</sup> Mitsunobu reaction,<sup>53</sup> and allylic alcohol isomerization.54 The only example in the second category is the comparative study of hydrogenation/hydrosilylation reported by Wrighton and coworkers and discussed above.<sup>33</sup> Other examples similar to the second category but using a different type of external trigger are: ring closing metathesis and ring opening metathesis polymerization studied with a photoswitchable ruthenium complex,<sup>40</sup> and a hydrogenation and a dehydrogenative coupling performed by an acid-base triggered ruthenium complex.55 The last example is the only reported instance in which the two catalytic cycles were combined for assisted tandem catalysis.

Although examples of tandem catalysis<sup>56-58</sup> are numerous, the number of examples of assisted tandem catalysis is relatively small,<sup>59-77</sup> likely because of issues associated with reagent/substrate compatibility and the complexity in designing such a single 'multitasking' catalyst. As such, switchable catalysis may provide a general method for obtaining complex products. The first step in achieving assisted tandem switchable catalysis is to demonstrate

<sup>&</sup>lt;sup>a.</sup> Department of Chemistry & Biochemistry, University of California, Los Angeles

<sup>&</sup>lt;sup>b.</sup> Current address: Department of Chemistry, Massachusetts Institute of Technology <sup>c.</sup> Division of Chemistry & Chemical Engineering, California Institute of Technology

#### Journal Name

that the two states of a catalyst show complementary on/off reactivity for each reaction. In the case of ring opening polymerization, the two substrates are rather similar and follow similar mechanisms. Therefore, we decided to take an analogous approach in order to develop applications to organic synthesis and focus on hydroelementation reactions.<sup>46</sup>

COMMUNICATION

Zirconium catalysts were reported to exhibit hydroamination selectivity in dependent on the charge of the complex and the type of aminoalkene used. With few exceptions,<sup>78</sup> neutral zirconium compounds exclusively catalyse reactions of primary aminoalkenes.<sup>79-84</sup> On the other hand, cationic zirconium complexes have displayed either no selectivity, where they catalyse both primary and secondary aminoalkenes,<sup>85-88</sup> or selective catalysis for secondary aminoalkenes.<sup>85,89</sup>



Fig. 2 A redox-active zirconium complex catalyses hydroamination reactions selectively.

Herein, we report the development of an [OSSO]-type zirconium complex, (thiolfan\*) $Zr(NEt_2)_2$  (thiolfan\*= 1, 1'-bis (2,4-di-*tert*-butyl-6-thiophenoxy) ferrocene), which can be switched *in situ* between a neutral and a cationic species when triggered by the oxidation/reduction of the ferrocene backbone. The two catalytic states generated by electron transfer react with different types of substrates.

The reaction of H<sub>2</sub>(thiolfan\*) with Zr(NEt<sub>2</sub>)<sub>4</sub> results in the clean formation of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub>,<sup>17,24</sup> as confirmed by NMR spectroscopy (<sup>1</sup>H NMR spectrum - Figure S1, <sup>13</sup>C NMR spectrum - Figure S2, and heteronuclear single quantum coherence, HSQC, spectrum - Figure S3), and elemental analysis.



**Fig. 3** Cyclic voltammetry diagram of  $(\text{thiolfan}^*)Zr(\text{NEt}_2)_2$  recorded in  $o-F_2C_6H_4$  at 100 mV s<sup>-1</sup> with 0.1 M [TPA][BAr<sup>F</sup>] as the electrolyte and referenced to the Fc/Fc<sup>+</sup> couple.

To investigate the redox properties of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub>, cyclic voltammetry experiments were performed in o-F<sub>2</sub>C<sub>6</sub>H<sub>4</sub> using [TPA][BAr<sup>F</sup>] ([TPA][BAr<sup>F</sup>] = tetrapropylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate) as an electrolyte, revealing two irreversible oxidation events (Figure 3). The electrochemical behaviour of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> contrasts that of the corresponding alkoxide complex, (thiolfan\*)Zr(O<sup>t</sup>Bu)<sub>2</sub>, which can be reversibly oxidized and reduced.<sup>11</sup> Although a cyclic voltammetry study of (thiolfan\*)Zr(O<sup>t</sup>Bu)<sub>2</sub> was not reported, the titanium (thiolfan\*)Ti(O<sup>i</sup>Pr)<sub>2</sub><sup>11</sup> and aluminium (thiolfan\*)Al(O<sup>i</sup>Pr)<sup>9</sup> alkoxide complexes exhibit a reversible and quasi-reversible, respectively,

redox event near 0 V versus the Fc/Fc<sup>+</sup> couple that was attributed to the oxidation of the ferrocene backbone. Dtherefore, an acrower region was chosen for the second scan from -0.5 to 0.5 V to isolate the corresponding oxidation peak, observed at 0.12 V versus the Fc/Fc<sup>+</sup> couple, but it still did not result in a reversible event (Figure S42), indicating that the species that is generated is not reduced back to the starting compound.

Table	1	Intramolecular	hydroaminations	catalysed	by
(thiolfa	n*)Zr	(NEt <sub>2</sub> ) <sub>2</sub> . <sup>a</sup>			

Entry		Reduced State		Oxidized State		
			Conversion	Time	Conversion	Time
1	Ph, Ph		95%	72 h		
2	1a NH <sub>2</sub>	Ph 1b			0%	20 h
3	Ph Ph <sub>H</sub> ≪ X N →	Ph J N -	0%	16 h		
4	2a	Ph 2b			100%	20 h
5	Ph Ph H ⇔ X N →		0%	24 h		
6	3a TMS	Ph 3b			0%	30 h
7	Ph Ph <sub>H</sub> ≪ × N <sub>-</sub> →		0%	18 h		
8	4a	Ph 4b			0%	20 h
9	Ph Ph H		0%	21 h		
10	5a Ac	Ph 5b			0%	24 h
11	Ph Ph H	Ts N	0%	20 h		
12	6a	Ph 6b			0%	21 h
13	Ph Ph	Ph, N	99%	4 h		
14	7a 7a	Ph 7b			99%	2 h
15	PhPhH		0%	20 h		
16		Ph 8b			99%	1 h <sup>b</sup>
17	$\vee$ NU -		0%	21 h		
18	9a 9a	9b			0%	24 h
19	. X X	\	0%	23 h		
20	10a	10b			99%	3 h <sup>b</sup>
21		ol L	66%	60 h <sup>c</sup>		
22	11a	11b			0%	21 h
23	$\overbrace{N}^{\text{Tol}} \stackrel{H}{\underset{N}} \rightarrow \text{Tol}$		0%	24 h		
24	12a	12h			77%	15 b <sup>b</sup>

<sup>a</sup> Conditions: 10 mmol% (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub>, 0.5 mL C<sub>6</sub>D<sub>6</sub>, 100 °C. Conversions were calculated from the corresponding NMR spectra using hexamethylbenzene (HMB) as an internal standard, except for entry 24, when the conversion was calculated by HRMS because of overlapping peaks in the corresponding NMR spectra. The oxidized state was generated in situ by the addition of 0.9 equiv. of [<sup>Ac</sup>Fc][BAr<sup>F</sup>]. <sup>b</sup> Reactions were carried out in a 4:1 by volume C<sub>6</sub>D<sub>6</sub>:*o*-C<sub>6</sub>H<sub>4</sub>F<sub>2</sub> solution instead of C<sub>6</sub>D<sub>6</sub>. <sup>c</sup> Reaction was carried out in *o*-F<sub>2</sub>C<sub>6</sub>H<sub>4</sub>.

#### Journal Name

Besides studying the electrochemical oxidation of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub>, chemical oxidation studies were also carried out. [<sup>Ac</sup>Fc][BAr<sup>F</sup>] (acetylferrocenium tetrakis(3,5bis(trifluoromethyl)phenyl)borate), AgOTf, AgBF<sub>4</sub>, AgBPh<sub>4</sub>, and NOBF<sub>4</sub> were used as oxidants, and the addition of CoCp<sub>2</sub> was employed to reduce the chemically oxidized species. However, no reversible oxidation/reduction was observed according to <sup>1</sup>H NMR spectra (Figure S4). Furthermore, a determination of the solution state magnetic susceptibility using the Evans method<sup>90</sup> of the oxidized species was unsuccessful due to the low solubility of this compound in benzene at ambient temperature. Adding a few drops of o-difluorobenzene resulted in loss of signal. However, elemental analysis agrees with the formula [(thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub>][BAr<sup>F</sup>] for the oxidized compound.

<sup>57</sup>Fe Mössbauer spectroscopic studies at 80 K, with no applied magnetic field, indicate that both (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> and [(thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub>][BAr<sup>F</sup>] contain a low-spin iron(II) (Figure S43). An X-band electron paramagnetic resonance (EPR) spectrum acquired at 77 K indicates the presence of an organic radical (q = 2.006, Figure Furthermore, UV-Vis spectra (Figure S44). S45) of [(thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub>][BAr<sup>F</sup>] are different than those of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> or [<sup>Ac</sup>Fc][BAr<sup>F</sup>] supporting the Mössbauer results that [(thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub>][BAr<sup>F</sup>] does not contain an Fe(III) species, but the oxidation occurs on the organic portion of a ligand.

Nonetheless, these data are consistent with an oxidized species being generated with  $[AcFc][BAr^F]$ , and it was reasoned that the coordination of substrate may enhance the stability of the catalytically active species.

To investigate the reactivity of  $(thiolfan^*)Zr(NEt_2)_2$  in intramolecular hydroamination reactions, a catalytic amount (10 mol%) of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> was added to a J-Young NMR tube with the aminoalkene/alkyne of interest and an internal standard, hexamethylbenzene(HMB), and the reaction mixture was heated to 100 °C in C<sub>6</sub>D<sub>6</sub>. Control experiments were performed with [AcFc][BAr<sup>F</sup>] in order to determine if the oxidant can act as a catalyst for the reactions of interest by itself. No conversion of 1a (Table 1) to 1b was observed when heated to 100 °C for 20 h in presence of catalytic amount of [AcFc][BAr<sup>F</sup>] (Figure S34). However, full conversion of 2a (Table 1) to 2b was observed under the same reaction condition (Figure S35). To understand further the reasons behind this observation, several experiments using catalytic amounts of AcFc, FcPF<sub>6</sub>, NaBAr<sup>F</sup>, or [Fc][BAr<sup>F</sup>] were performed with **2a**. After 19 hours, no conversion was observed in the presence of <sup>Ac</sup>Fc (Figure S36). After 2 hours, a partial conversion (34%) was observed with NaBAr<sup>F</sup> (Figure S37), a full conversion was observed with [Fc][BAr<sup>F</sup>] (Figure S38), and no conversion was observed with FcPF<sub>6</sub> (Figure S39). The peaks corresponding to acetylferrocene were observed in the <sup>1</sup>H NMR spectra of control reactions catalysed by [AcFc][BArF], and a peak corresponding to ferrocene was observed in the <sup>1</sup>H NMR spectra of control reactions catalysed by FcPF<sub>6</sub> and [Fc][BAr<sup>F</sup>]. A possible explanation is that the aminoalkene reduced [AcFc][BArF] to acetylferrocene and the reaction was catalysed by a Brønsted acid.91, <sup>92</sup> Michon and co-workers reported that HBF<sub>4</sub>, generated *in situ* from AgBF<sub>4</sub> catalysed the hydroamination of secondary aminoalkynes.<sup>93</sup> Similarly, when [AcFc][BArF] served as a precatalyst in the hydroamination reactions, HBAr<sup>F</sup> was generated in situ and combined with the amine substrate to generate an ammonium [BAr<sup>F</sup>] salt as the active catalyst. The difference in reaction rates likely resulted from the difference in solubility of the [BAr<sup>F</sup>] precatalysts. Therefore, we decided to use a ratio of zirconium compound to the oxidant of 10:9 molar equivalents. By premixing the oxidant (9 mol%) with (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> (10 mol%) before the addition of the substrate, we ensured that all [AcFc][BAr<sup>F</sup>] was consumed to form the corresponding oxidized species. The results reported in Table 1 account for these modifications.

The reactivity studies show that (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> can catalyse the cyclization of the primary aminoalkene 1a in 72 h (Table 1, entry 1), while the oxidized species showed no conversion after 20 h (Table 1, entry 2). In contrast, (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> showed no reactivity toward the secondary aminoalkene 2a (Table 1, entry 3), but the oxidized species can catalyse the cyclization of 2a in 20 h (Table 1, entry 4). Similarly, a 66% conversion of 11a was achieved in the presence of (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> after 60 h in o-DFB (Table 1, entry 21), while the oxidized species showed no conversion after 21 h (Table 1, entry 22). (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> showed no reactivity toward 12a (Table 1, entry 23), but 77% conversion was achieved in 15 h in the presence of the oxidized species (Table 1, entry 24). Furthermore, the hydroamination of the secondary aminoalkyne 8a (Table 1, entry 16) and secondary aminoalkene 10a (Table 1, entry 20) could only be catalysed by the oxidized catalyst. Unfortunately, (thiolfan\*)Zr(NEt<sub>2</sub>)<sub>2</sub> was not active towards other secondary aminoalkene substrates: no conversion was observed for substrates 3a-6a with either state of the catalyst (Table 1, entries 5-12). However, the results obtained with 1a and 2a indicate that there is selectivity between primary and secondary aminoalkenes triggered by the oxidation state of the zirconium catalyst. Unfortunately, the selectivity was lost with primary aminoalkynes: 7a cyclized in the presence of both the reduced and oxidized species (Table 1, entries 13-14).

In our search for redox-switchable catalysts for organic transformations, (thiolfan\*) $Zr(NEt_2)_2$  was successfully synthesized and characterized. We found that (thiolfan\*) $Zr(NEt_2)_2$  catalyses the hydroamination of primary aminoalkenes, whereas an oxidized species generated in situ catalyses the hydroamination of secondary aminoalkenes. The selectivity of the two oxidation states observed in these reactions will form the basis of developing redox switchable catalysts for assisted tandem reactions.

## Acknowledgments

This work was supported by the National Science Foundation (Grant CHE-1809116 to P. L. D. and CHE-1048804 for NMR spectroscopy) and UCLA. Yi Shen is grateful for an INFEWS fellowship (NSF Grant DGE-1735325).

## **Conflicts of interest**

There are no conflicts to declare.

## References

- 1. V. Blanco, D. A. Leigh and V. Marcos, Chem. Soc. Rev., 2015, 44, 5341.
- 2. A. J. Teator, D. N. Lastovickova and C. W. Bielawski, *Chem. Rev.*, 2016, **116**, 1969-1992.

3. S. M. Guillaume, E. Kirillov, Y. Sarazin and J.-F. Carpentier, *Chem. Eur. J.*, 2015, **21**, 7988-8003.

4. F. A. Leibfarth, K. M. Mattson, B. P. Fors, H. A. Collins and C. J. Hawker, Angew. Chem. Int. Ed., 2013, **52**, 199-210.

- 5. C. Chen, ACS Catal., 2018, 8, 5506-5514.
- 6. J. M. Kaiser and B. K. Long, Coord. Chem. Rev., 2018, 372, 141-152.
- 7. J. Wei and P. L. Diaconescu, Acc. Chem. Res., 2019, 52, 415-424.

0160

### Journal Name

8. M. Abubekerov, V. Vlček, J. Wei, M. E. Miehlich, S. M. Quan, K. Meyer, D. Neuhauser and P. L. Diaconescu, iScience, 2018, 7, 120-131.

COMMUNICATION

- 9. J. Wei, M. N. Riffel and P. L. Diaconescu, Macromolecules, 2017, 50, 1847.
- 10. S. M. Quan, J. Wei and P. L. Diaconescu, Organometallics, 2017, 36, 4451. 11. M. Y. Lowe, S. Shu, S. M. Quan and P. L. Diaconescu, Inorg. Chem. Front., 2017, 4, 1798-1805.
- 12. S. M. Quan, X. Wang, R. Zhang and P. L. Diaconescu, Macromolecules, 2016, 49, 6768-6778.
- 13. W. Huang and P. L. Diaconescu, Inorg. Chem., 2016, 55, 10013–10023.
- 14. X. Wang, A. Thevenon, J. L. Brosmer, I. Yu, S. I. Khan, P. Mehrkhodavandi and P. L. Diaconescu, J. Am. Chem. Soc., 2014, 136, 11264-11267.
- 15. E. M. Broderick, N. Guo, T. Wu, C. S. Vogel, C. Xu, J. Sutter, J. T. Miller, K. Meyer, T. Cantat and P. L. Diaconescu, Chem. Commun., 2011, 47, 9897-9899.
- 16. E. M. Broderick, N. Guo, C. S. Vogel, C. Xu, J. Sutter, J. T. Miller, K. Meyer,
- P. Mehrkhodavandi and P. L. Diaconescu, J. Am. Chem. Soc., 2011, 133, 9278. 17. C. Hermans, W. Rong, T. P. Spaniol and J. Okuda, Dalton Trans., 2016, 45, 8127-8133.
- 18. A. Sauer, J.-C. Buffet, T. P. Spaniol, H. Nagae, K. Mashima and J. Okuda, ChemCatChem, 2013, 5, 1088-1091.
- 19. M. Qi, Q. Dong, D. Wang and J. A. Byers, J. Am. Chem. Soc., 2018, 140, 5686-5690.
- 20. A. B. Biernesser, K. R. Delle Chiaie, J. B. Curley and J. A. Byers, Angew. Chem. Int. Ed., 2016. 55, 5251-5254.
- 21. A. B. Biernesser, B. Li and J. A. Byers, J. Am. Chem. Soc., 2013, 135, 16553.
- 22. M. Abubekerov, S. I. Khan and P. L. Diaconescu, Organometallics, 2017, **36**, 4394-4402.
- 23. M. Abubekerov, S. M. Shepard and P. L. Diaconescu, Eur. J. Inorg. Chem., 2016, 2016, 2634-2640.
- 24. W. Zou, W. Pang and C. Chen, Inorg. Chem. Front., 2017, 4, 795-800.
- 25. M. Zhao and C. Chen, ACS Catal., 2017, 7, 7490-7494.
- 26. M. Chen, B. Yang and C. Chen, Angew. Chem. Int. Ed., 2015, 54, 15520.
- 27. T. T. D. Chen, Y. Zhu and C. K. Williams, *Macromolecules*, 2018, **51**, 5346. 28. C. Romain, Y. Zhu, P. Dingwall, S. Paul, H. S. Rzepa, A. Buchard and C. K. Williams, J. Am. Chem. Soc., 2016, 138, 4120-4131.
- 29. Y. Zhu, C. Romain and C. K. Williams, J. Am. Chem. Soc., 2015, 137, 12179. 30. S. Paul, C. Romain, J. Shaw and C. K. Williams, Macromolecules, 2015, 48, 6047-6056.
- 31. C. Romain and C. K. Williams, Angew. Chem. Int. Ed., 2014, 53, 1607-1610. 32. F. Eisenreich, M. Kathan, A. Dallmann, S. P. Ihrig, T. Schwaar, B. M. Schmidt and S. Hecht. Nat. Catal., 2018. 1, 516-522.
- 33. I. M. Lorkovic, R. R. Duff and M. S. Wrighton, J. Am. Chem. Soc., 1995, 117. 3617-3618.
- 34. M. Süßner and H. Plenio, Angew. Chem. Int. Ed., 2005, 44, 6885-6888.
- 35. G. Liu, H. He and J. Wang, Adv. Synth. Catal., 2009, 351, 1610-1620.
- 36. M. R. Ringenberg, M. J. Nilges, T. B. Rauchfuss and S. R. Wilson, Organometallics, 2010, 29, 1956-1965.
- 37. M. R. Ringenberg, S. L. Kokatam, Z. M. Heiden and T. B. Rauchfuss, J. Am. Chem. Soc., 2007, 130, 788-789.
- 38. I. V. Kourkine, C. S. Slone, C. A. Mirkin, L. M. Liable-Sands and A. L. Rheingold, Inorg. Chem., 1999, 38, 2758-2759.
- 39. C. S. Slone, C. A. Mirkin, G. P. A. Yap, I. A. Guzei and A. L. Rheingold, J. Am. Chem. Soc., 1997, 119, 10743-10753.
- 40. A. J. Teator, H. Shao, G. Lu, P. Liu and C. W. Bielawski, Organometallics, 2017, 36, 490-497.
- 41. D. N. Lastovickova, A. J. Teator, H. Shao, P. Liu and C. W. Bielawski, Inorg. Chem. Front., 2017, 4, 1525-1532.
- 42. A. G. Tennyson, V. M. Lynch and C. W. Bielawski, J. Am. Chem. Soc., 2010, 132, 9420-9429.
- Organometallics, 2017, 36, 2026-2035.
- 7402-7408
- 46. S. M. Shepard and P. L. Diaconescu, Organometallics, 2016, 35, 2446.
- 47. K. Arumugam, C. D. Varnado, S. Sproules, V. M. Lynch and C. W. Bielawski, Chem. Eur. J., 2013, 19, 10866-10875.
- 48. C. D. Varnado, Jr, E. L. Rosen, M. S. Collins, V. M. Lynch and C. W. Bielawski, Dalton Trans., 2013, 42, 13251-13264.
- 49. L. Hettmanczyk, S. Manck, C. Hoyer, S. Hohloch and B. Sarkar, Chem. Commun., 2015, 51, 10949-10952.

- 50. L. Hettmanczyk, L. Suntrup, S. Klenk, C. Hoyer and B. Sarkar, Chem. Eur. J., 2017. 23, 576-585.
- *J.*, 2017, **23**, 576-585. DOI: 10.1039/C9CC01076A 51. H. Yang and F. P. Gabbaï, *J. Am. Chem. Soc.*, 2015, **137**, 13425-13432.
- 52. S. Ibáñez, M. Poyatos, L. N. Dawe, D. Gusev and E. Peris, Organometallics, 2016, 35, 2747-2758.
- 53. C. A. Fleckenstein and H. Plenio, Adv. Synth. Cat., 2006, 348, 1058-1062. 54. P. Neumann, H. Dib, A.-M. Caminade and E. Hey-Hawkins, Angew. Chem. Int. Ed., 2015, 54, 311-314.
- 55. S. Semwal and J. Choudhury, Angew. Chem. Int. Ed., 2017, 56, 5556-5560. 56. A. Behr, A. J. Vorholt, K. A. Ostrowski and T. Seidensticker, Green Chem., 2014, 16, 982-1006.
- 57. T. L. Lohr and T. J. Marks, Nat. Chem., 2015, 7, 477-482.
- 58. D. E. Fogg and E. N. dos Santos, Coord. Chem. Rev., 2004, 248, 2365-2379. 59. M. Arisawa, Y. Fujii, H. Kato, H. Fukuda, T. Matsumoto, M. Ito, H. Abe, Y.
- Ito and S. Shuto, Angew. Chem. Int. Ed., 2013, 52, 1003-1007.
- 60. A. Aillerie, V. Rodriguez-Ruiz, R. Carlino, F. Bourdreux, R. Guillot, S. Bezzenine-Lafollée, R. Gil, D. Prim and J. Hannedouche, ChemCatChem, 2016, 8, 2455-2460.
- 61. B. Schmidt, S. Krehl and E. Jablowski, Org. Biomol. Chem., 2012, 10, 5119.
- 62. B. Schmidt, S. Krehl and S. Hauke, J. Org. Chem., 2013, 78, 5427-5435.
- 63. H. Kato, T. Ishigame, N. Oshima, N. Hoshiya, K. Shimawaki, M. Arisawa and S. Shuto, Adv. Synth. Catal., 2011, 353, 2676-2680.
- 64. P. K. Maity and J. A. Tunge, ChemCatChem, 2018, 10, 3419-3423.
- 65. A. Beyer, T. Castanheiro, P. Busca and G. Prestat, ChemCatChem, 2015, 7, 2433-2436.
- 66. A. Heutling, F. Pohlki, I. Bytschkov and S. Doye, Angew. Chem. Int. Ed., 2005, 44, 2951-2954.
- 67. J. Louie, C. W. Bielawski and R. H. Grubbs, J. Am. Chem. Soc., 2001, 123, 11312-11313.
- 68. P. Børsting and P. Nielsen, Chem. Commun., 2002, 2140-2141.
- 69. S. Beligny, S. Eibauer, S. Maechling and S. Blechert, Angew. Chem. Int. Ed., 2006. 45. 1900-1903.
- 70. A. A. Scholte, M. H. An and M. L. Snapper, Org. Lett., 2006, 8, 4759-4762.
- 71. A. N. Thadani and V. H. Rawal, Org. Lett., 2002, 4, 4321-4323.
- 72. A. N. Thadani and V. H. Rawal, Org. Lett., 2002, 4, 4317-4320.
- 73. R. Lira and J. P. Wolfe, J. Am. Chem. Soc., 2004, 126, 13906-13907.
- 74. Q. Yang, J. E. Ney and J. P. Wolfe, Org. Lett., 2005, 7, 2575-2578.
- 75. B. M. Trost, D. A. Thaisrivongs and M. M. Hansmann, Angew. Chem. Int. Ed., 2012, 51, 11522-11526.
- 76. A. Carrër, J.-D. Brion, M. Alami and S. Messaoudi, Adv. Synth. Catal., 2014, **356**, 3821-3830.
- 77. M. Roche, J. Bignon, J.-D. Brion, A. Hamze and M. Alami, J. Org. Chem., 2014, 79, 7583-7592.
- 78. D. C. Leitch, R. H. Platel and L. L. Schafer, J. Am. Chem. Soc., 2011, 133, 15453-15463
- 79. S. Majumder and A. L. Odom, Organometallics, 2008, 27, 1174-1177.
- 80. B. D. Stubbert and T. J. Marks, J. Am. Chem. Soc., 2007, 129, 6149-6167.
- 81. C. Müller, W. Saak and S. Doye, Eur. J. Org. Chem., 2008, 2008, 2731.
- 82. D. C. Leitch, P. R. Payne, C. R. Dunbar and L. L. Schafer, J. Am. Chem. Soc., 2009, 131, 18246-18247.
- 83. Y.-C. Hu, C.-F. Liang, J.-H. Tsai, G. P. A. Yap, Y.-T. Chang and T.-G. Ong, Organometallics, 2010, 29, 3357-3361.
- 84. A. L. Reznichenko and K. C. Hultzsch, in Organic Reactions, 2015, DOI: doi:10.1002/0471264180.or088.01.
- 85. D. V. Gribkov and K. C. Hultzsch, Angew. Chem. Int. Ed., 2004, 43, 5542.
- 86. X. Wang, Z. Chen, X.-L. Sun, Y. Tang and Z. Xie, Org. Lett., 2011, 13, 4758. 87. L. Luconi, J. Klosin, A. J. Smith, S. Germain, E. Schulz, J. Hannedouche and
- G. Giambastiani, Dalton Trans., 2013, 42, 16056-16065.
- 88. Y. Zhang, Q. Sun, Y. Wang, D. Yuan, Y. Yao and Q. Shen, RSC Adv., 2016, 6, 10541-10548.
- 89. P. D. Knight, I. Munslow, P. N. O'Shaughnessy and P. Scott, Chem. Commun., 2004, 894-895
- 90. D. F. Evans, J. Chem. Soc., 1959, 2003-2005.
- 91. J. Chen, S. K. Goforth, B. A. McKeown and T. B. Gunnoe, Dalton Trans., 2017. 46. 2884-2891.
- 92. L. Ackermann, L. T. Kaspar and A. Althammer, Org. Biomol. Chem., 2007, 5. 1975-1978.
- 93. C. Michon, F. Medina, F. Capet, P. Roussel and F. Agbossou-Niedercorn, Adv. Synth. Catal., 2010, 352, 3293-3305.

43. S. Klenk, S. Rupf, L. Suntrup, M. van der Meer and B. Sarkar,

44. A. Feyrer and F. Breher, Inorg. Chem. Front., 2017, 4, 1125-1134.

45. A. Feyrer, M. K. Armbruster, K. Fink and F. Breher, Chem. Eur. J., 2017, 23,