

Synthesis, Characterization and Catalytic Properties of TBS-2 Zeolites†

J. Chem. Research (S),
1998, 764–765†

Zaihui Fu,* Dulin Yin, Donghong Yin, Luxi Zhang and Youyu Zhang

Institute of Fine Catalysis & Synthesis, Hunan Normal University, Changsha, 410081, P.R. China

Titanium and B co-substituted silicate-2 zeolites were characterized using XRD, FT-IR and NH₃-TPD, and the TBS-2's bifunctional catalytic properties as oxidative and acidic catalysts were investigated using the epoxidation of styrene and rearrangement of styrene oxide.

Co-incorporation of Ti and trivalent metal ions such as B³⁺, Al³⁺, Ga³⁺, or Fe³⁺ in MFI and MEL structures to modify their catalytic properties has been reported recently.^{1–6} However, details of the synthesis, characterization and catalytic properties of the co-incorporated zeolites are sparse. In the present work, we report the synthesis, characterization and catalytic properties of TBS-2 zeolites.

The observed XRD patterns for calcined TBS-2 zeolites, which are well crystallized, show no line broadening and match well those of TS-2, BS-2 and S-2, strongly suggest that Ti and B are simultaneously incorporated into the MEL structure. The unit cell volume of TS-2 (Table 1) is larger than that of pure S-2 and consistent with many reports.⁷ However, that of TBS-2 is smaller than that of pure S-2 and larger than that of BS-2. This is due to the replacement of the framework Si by the smaller B³⁺ ions, which can cause S-2 framework contraction. A decrease in the unit cell parameters should confirm that boron has been successfully incorporated into the framework of TS-2. The IR bands at 960 and 1380 cm^{−1} are used as fingerprints of Ti and B incorporation into the S-2 framework.^{7,8} The absence of any new IR features in TBS-2 other than framework Ti and B bands may indicate that, despite the presence of the two elements in the same crystallites, there are no mixed Ti–O–B sites in the framework.

Increasing the H₂O₂:SiO₂ ratio from 0.13 to 0.26:1 (corresponding to samples 2 and 1) will obviously cause a decrease in the framework B band, but varying this ratio in the range 0.13–0.08 will not affect the two framework bands (samples 2 and 3). However, when increasing B₂O₃:SiO₂ from 0.05 to 0.10:1 (samples 2, 3, 4 and 5) the framework B band is not obviously increased, and the framework Ti band is obviously decreased. Thus, the amounts of H₂O₂ and H₃BO₃ used for efficient incorporation of B and Ti into the

S-2 framework must be appropriate, the use of excessive H₂O₂ or H₃BO₃ will obviously inhibit such incorporation. The addition of 10% aq. TMAOH not only avoids serious gelation, but also efficiently enhances the incorporation of boron (samples 6 and 7).

NH₃-TPD was used to measure the acidic properties of these zeolites. The amounts of ammonia desorbed from these zeolites and the maximum temperatures are summarized in Table 1. There is only a desorption peak for the all samples with a desorption temperature range of 383–573 K. The NH₃ uptakes on the greater part of TBS-2 zeolites are higher than on TS-2 and BS-2; the two TBS-2 samples (samples 1 and 5) and BS-2 have lower NH₃ uptakes, which is attributed to the decrease in the framework Ti and B bands in these samples. The maximum temperatures of NH₃ desorption on TBS-2 and BS-2 zeolites are 20–30 K higher than that of TS-2. These results show that all these zeolites have weak acidic properties, and the incorporation of boron in TS-2 can enhance both the number and strength of its acid sites.

In the epoxidation of styrene, TS-2 has slightly higher oxidation activity and selectivity for rearrangement to phenylacetaldehyde than TBS-2, which is due to a higher Ti content in TS-2. The catalytic activity of TBS-2 increases with an increase in its framework Ti content, and the selectivity decreases with an increase in its framework B content. The products comprise 70–80% phenylacetaldehyde, arising from the Lewis acid-catalysed rearrangement of the epoxide,⁹ 20–28% benzaldehyde and formaldehyde and about 1.5% phenylethanol, in agreement with the results of Xia *et al.*¹⁰ In order to verify the formation of PhCHO and HCHO, phosphoric acid was added to the epoxidation reaction system. There was obviously an increase in the formation of PhCHO and HCHO. Thus, we

Table 1 Results of XRD, IR and NH₃-TPD for TBS-2 zeolites

No.	TBS-2 Samples			XRD results ^a V/Å ³	Framework IR band intensity ^b			NH ₃ -TPD	
	x	y	z		550 cm ^{−1}	960 cm ^{−1}	1380 cm ^{−1}	T _m /K	NH ₃ uptake
1	0.0	0.050	0.26	5343.2	2.12	0.59	0.02	468	0.15
2	0.0	0.050	0.13	5352.1	2.40	0.77	0.17	486	0.37
3	0.0	0.050	0.08	5349.5	2.19	0.75	0.17	489	0.36
4	0.0	0.075	0.10	5333.7	2.06	0.78	0.20	489	0.41
5	0.0	0.100	0.12	5314.6	2.06	0.49	0.17	485	0.26
6	0.2	0.075	0.12	5212.6	2.22	0.64	0.44	491	0.47
7	0.1	0.075	0.12	5239.5	2.31	0.55	0.25	483	0.36
TS-2	0.0	0.000	0.10	5448.7	2.20	1.03	—	465	0.30
BS-2	0.0	0.050	0.00	5214.1	2.62	—	0.32	491	0.12
S-2	0.0	0.000	0.00	5384.0	2.60	—	—	—	—

^aMeasured by a Siemens D-500 diffractometer with Cu-Kα radiation (λ = 1.54051 Å). ^bMeasured by a Nicolt 510P FT-IR spectrometer; band intensity (cm)/800 cm^{−1} band intensity (cm).

*To receive any correspondence (e-mail: yindh@hunnu.edu.cn).

†This is a **Short Paper** as defined in the Instructions for Authors, Section 5.0 [see *J. Chem. Research (S)*, 1998, Issue 1]; there is therefore no corresponding material in *J. Chem. Research (M)*.

propose that their formation is due to the catalysis of Brønsted acid sites produced by the co-ordination of H₂O/H₂O₂ to the Ti and B atoms of TBS-2.¹¹ In catalytic rearrangement of styrene oxide, TBS-2 is obviously more

Table 2 Results of epoxidation of styrene and rearrangement of styrene oxide over TBS-2 zeolites

Sample	Contents		Epoxidation of styrene ^a		Rearrangement of styrene oxide ^b	
	Si:Ti	SiO ₂ :B ₂ O ₃	Conv. (mol%)	PhCH ₂ CHO Sel. (%)	Conv. (mol%)	PhCH ₂ CHO Sel. (%)
BS-2	—	66.7	0	—	37.6	96.2
TBS-2(1)	78.9	546.7	7.1	78.0	46.3	98.3
TBS-2(7)	75.8	85.3	7.4	70.9	72.8	97.9
TBS-2(3)	62.1	125.6	8.2	75.4	91.4	98.5
TBS-2(4)	58.4	106.5	8.9	72.1	99.3	99.2
TS-2	45.2	—	10.7	78.2	56.2	96.8
TBS-2(4)	58.4	106.5	12.1 ^c	51.6 ^c	99.5 ^d	79.6 ^d

^aStyrene (2.08 g), 30% aq. H₂O₂ (2.28 g), acetone (10 ml), catalyst (0.2 g), reaction temperature 333 K and time 5 h. Besides phenylacetaldehyde, 20–28% benzaldehyde and formaldehyde, and 1.5% phenylethanol were obtained. ^bStyrene oxide (1 ml), acetone (7 ml), catalyst (0.1 g), reaction temperature 333 K and time 5 h. Besides phenylacetaldehyde, a small amount of benzaldehyde (≤3.8%) was obtained. ^c48.4% Benzaldehyde and formaldehyde were obtained by adding 0.25 ml of 85% aq. phosphoric acid to the epoxidation reaction system. ^d20.4% Benzaldehyde and formaldehyde were obtained by adding 1.14 g of 30% aq. H₂O₂ to the rearrangement reaction system.

active and slightly more selective than TS-2, which is attributed to the greater number and stronger Lewis acid sites in TBS-2.

Experimental

The synthesis of TBS-2 was as follows: titanium tetrabutoxide (0.172 g) was added to water (5.0 g), giving a white precipitate (hydrous titanium oxide). 30% aq. H₂O₂ was added to dissolve the oxide (solution 1). Solution 2 was prepared from 11.6 g of 10% aq. TBAOH and 10% aq. TMAOH was added to TEOS (4.76 g). A solution containing boric acid in water (10 g) was then added to solution 2. Stirring of 2 was maintained at 353 K for 2 h. Finally, solution 1 was added dropwise to solution 2. The molar composition of the reaction mixture was 0.2 TBAOH-*x*TMAOH-1.0SiO₂-0.02TiO₂-*y*B₂O₃-*z*H₂O₂-50H₂O. The crystallization was done statically at 448 K for 4 d. The solid obtained was filtered off, washed with water, dried at 393 K for 2 h, and calcined at 813 K for 16 h in air.

NH₃-TPD was carried out from 373 to 723 K with a heating rate β of 8 K min⁻¹ and with N₂ (30 ml min⁻¹) as carrier gas. The NH₃ uptake was determined using TCD by comparing with the integrated area of a known volume of NH₃.

The epoxidation of styrene or rearrangement of styrene oxide was performed under vigorous stirring in a three-necked glass flask equipped with a condenser and thermometer. The reaction products were analysed by GC on a SE-54 capillary column with a FID.

We thank the Chinese government for their financial support by the National Natural Sciences Foundation of China (29773013).

Received, 24th June 1998; Accepted, 12th August 1998
Paper E/8/04836C

References

- 1 G. Bellussi, *Eur. Pat.*, A1 0 272 496, 1987.
- 2 G. Bellussi, A. Carati, M. G. Clerici and A. Esposito, *Stud. Surf. Sci. Catal.*, 1991, **63**, 421.
- 3 K. K. Lam Shang Leen, *US Pat.*, 4 623 526, 4 519 998, 1985.
- 4 K. K. Lam Shang Leen and Ch. Jin Rang, *Eur. Pat.*, B1 0 480 038, 1984.
- 5 L. Forni and M. Pelozzi, *J. Mater. Chem.*, 1990, 1101.
- 6 L. Forni, M. Pelozzi and A. Guisti, *J. Catal.*, 1990, **122**, 44.
- 7 R. J. Sudhakar and R. Kumar, *J. Catal.*, 1991, **130**, 440.
- 8 D. Trong on, S. Kaliaguine and L. Bonnevot, *J. Catal.*, 1995, **157**, 235.
- 9 C. Cativiela and J. M. Fraile, *J. Mol. Catal. A: Chemical*, 1996, **112**, 259.
- 10 G. H. Xia, G. W. Wang and G. Y. Cao, *Chin. J. Mol. Catal.*, 1994, **8**, 313.
- 11 M. A. Camblor, A. Corma and P. Esteve, *Chem. Commun.*, 1997, 795.