Contents lists available at ScienceDirect

## Catalysis Communications

journal homepage: www.elsevier.com/locate/catcom

Short Communication

# Simple and green oxidation of cyclohexene to adipic acid with an efficient and durable silica-functionalized ammonium tungstate catalyst



Department of Chemistry, Sharif University of Technology, Tehran, Iran

#### ARTICLE INFO

Article history: Received 2 August 2013 Received in revised form 28 September 2013 Accepted 2 October 2013 Available online 11 October 2013

Keywords: Adipic acid Green oxidation Hydrogen peroxide Silica-functionalized ammonium tungstate N<sub>2</sub>O

### ABSTRACT

A novel silica-functionalized ammonium tungstate interphase catalyst has been reported as a non-nitric acid route for adipic acid production from one-pot oxidative cleavage of 30% hydrogen peroxide and catalytic amounts of p-toluenesulfonic acid (PTSA). The catalyst has been simply prepared by commercially available starting material. The structure of the catalyst has been investigated using FT-IR spectroscopy, atomic absorption, TEM, SEM and XRD analysis. The catalyst has shown good to high activity even up to 10 runs of reaction. Simple preparation of the catalyst, avoids using harmful phase transfer catalyst (PTC) and/or chlorinated additives are among the other benefits of this work.

© 2013 Elsevier B.V. All rights reserved.

#### 1. Introduction

Adipic acid (1,6-hexanedioic acid) is a very important raw material which is used in the chemical industries [1]. It is mainly used in the manufacture of nylon-6,6 as a precursor for synthetic fibers, tire reinforcements, plastics, urethane foams, elastomers, and synthetic lubricants [1,2]. The current industrial method for adipic acid production is oxidation of a cyclohexanone/cyclohexanol (so-called KA oil) mixture with nitric acid [1]. Emission of huge volume of environmentally harmful gas, nitrous oxide (N<sub>2</sub>O), is the major drawback of this process. N<sub>2</sub>O is a greenhouse gas with 120 years life-time in atmosphere [3,4]. Owing to the strong IR absorption, the ability of N<sub>2</sub>O on warming the atmosphere is about 310 times higher than that of carbon dioxide (CO<sub>2</sub>) [4]. The nitric oxide (NO) which is produced from the N<sub>2</sub>O decomposition can destroy ozone molecules in a series of reactions. Additionally, N<sub>2</sub>O is a harmful gas which forms acid rains.

One-step oxidative cleavage of cyclohexene to adipic acid with  $H_2O_2$  has been introduced as a green alternative to adipic acid [5]. In this method, in order to overcome organic starting material and aqueous oxidant incompatibility and accelerate the reaction; quaternary ammonium salt has been employed as a phase transfer

\* Corresponding author. Fax: +98 21 66029165.

E-mail address: mhashemi@sharif.edu (M. Mahmoodi Hashemi).

catalyst (PTC) into the reaction mixture. Although  $H_2O_2$  is a cheap oxidant with water as the sole by-product, the relatively expensive applied quaternary ammonium compounds generally are not environmentally benign reagents. Another limitation of this process is the cost of the applied oxidant ( $H_2O_2$ ) which is relatively higher than  $O_2$  in the traditional nitric acid oxidation route. However, applying recoverable catalyst accompanied by environmentally benign protocols would significantly cover the cost of adipic acid production with  $H_2O_2$  as oxidant.

In this regard, various methods have been developed to improve the cyclohexene oxidation reaction such as using of surfactant-type peroxotungstate and peroxomolybdates [6], H<sub>2</sub>WO<sub>4</sub>/H<sub>2</sub>SO<sub>4</sub>/H<sub>3</sub>PO<sub>4</sub> mixture [7], ionic liquids [8,9], MIL-101 metal–organic framework [10] complexes derived from heteropoly acid and glycine [11] and Ti–AlSBA mesostructured catalysts [12].

However, uses of relatively expensive and corrosive reagents, difficulties in catalyst recovery as well as catalysts degradation and/or deactivation are among the drawbacks of these methodologies. Hence, this oxidation reaction still requires further improvement in the point of reducing hazardous reagents, improving catalyst recovery and simplifying the overall process.

In the current study, we designed an interphase (organic–inorganic hybrid) catalyst for oxidation of cyclohexene to adipic acid. The catalyst comprises alkyl ammonium groups which covalently anchored on the surface of the silica gel. The surface functionalities provide the  $WO_4^{2-}$  species which is necessary for oxidation. Additionally, the functionalized porous material acts as quasi-homogenous system with a large area of amphiphilic surface for better mass transfer of







<sup>1566-7367/\$ -</sup> see front matter © 2013 Elsevier B.V. All rights reserved. http://dx.doi.org/10.1016/j.catcom.2013.10.001

organic starting material and aqueous oxidant. In other words, the surface-bonded ammonium groups act as heterogenized PTC and therefore there is no need to use harmful organic additive(s) to overcome reagent phase incompatibility.

#### 2. Results and discussion

The catalyst was easily prepared by commercially available starting materials (Scheme 1). The material **A** was prepared by grafting the 2-[2-(3-Trimethoxysilylpropylamino)ethylamino] ethylamine precursor onto the high surface area silica gel (see electronic supplementary information for details of the experimental procedure). Trifluor-omethanesulfonic acid treatment of **A** produces surface-bonded ammonium triflate **B**. The catalyst **1** is prepared by subsequence anion exchange of the material **B** with an aqueous solution of Na<sub>2</sub>WO<sub>4</sub>.2H<sub>2</sub>O at room temperature.

To investigate the structure of the functionalized materials, comparative FT-IR spectra of the pure silica, material A and the catalyst 1 are shown in Fig. 1. The top spectrum is for pure silica, while the next two are for intermediate **A** and the final catalyst, which show important differences relative to the silica. The characteristics bands of the **A** are at 2922 and 2855 cm<sup>-1</sup> which is attributed to C–H and N–H stretching frequencies of the surface alkyl amine functionalities. In the case of the catalyst **1**, a very important characteristic band was observed at 875 cm<sup>-1</sup> which belongs to the W–O stretching frequency [8,9] and proves the presence of the WO<sub>4</sub><sup>2–</sup> species in the catalyst. It is worth mentioning that the bands around 1470 and 1740 cm<sup>-1</sup> in both of **A** and catalyst **1** are attributed to the N–H bending frequencies of the surface-bonded amine and/or ammonium functionalities.

Atomic absorption analysis was performed to determine the accurate loading of  $WO_4^{2-}$  in the catalyst. The result indicates that the loading of  $WO_4^{2-}$  in the catalyst **1** is 1.02 mmol.g<sup>-1</sup>.

XRD analysis of the pure silica, material **A** and catalyst **1** is shown in Fig. 2. The diffraction peak which appeared at about 25° in all of the structures is attributed to the amorphous silica gel [13]. This observation proves that no essential changes in topological structure of the silica gel occurred during the grafting process, chlorosulfonic acid treatment and anion exchange of the **B**. In the case of catalyst **1**, the decrease of the intensity may be interpreted by the formation of hydrogen bond between  $WO_4^{2-}$  and surface ammonium functionalities [14]. Our explanation about the peaks which are observed at nearly 10 and 60° is that they may be attributed to the silica-bonded ammonium tungstate species in catalyst **1**. TEM and SEM of the catalyst are provided in the Supplementary data.

The activity of catalyst **1** was investigated in oxidation of cyclohexene to adipic acid (Table 1). Typically, conversion of cyclohexene to adipic acid theoretically needs 4 moles  $H_2O_2$  for four step oxidation (Scheme 2). However, 4.4 moles of hydrogen peroxide was used to ensure the complete conversion of cyclohexene [5]. Worthy of note is that the activity of the  $WO_4^{2-}$  species in oxidation of cyclohexene to adipic acid strongly depends on the acidity of the reaction media [15]. At the first



Fig. 1. FT-IR spectroscopy of the pure silica, material A and catalyst 1.

step, the efficiency of catalyst **1** was investigated for oxidation of cyclohexene to adipic acid in the presence of 200 mg of HCl and  $H_2SO_4$ . The results indicated that in these cases the corresponding adipic acid can be obtained in 29% and 47% (Table 1, entries 1 and 2).

The yield of the reaction significantly increases to 64% when ptoluenesulfonic acid (PTSA) was used (Table 1, entry3). The increase in the reaction yield may be attributed to better miscibility of the organic acid into both starting material/intermediates and aqueous oxidant.

Oxidation of the cyclohexane to adipic acid is also a temperaturedependent reaction with two distinct thermal steps [16]. To improve the yield of the reaction we considered this issue and the reaction was performed into two thermal steps. For this purpose, the mixture was first heated at 73 °C (near the boiling point of the cyclohexene–water mixture) to convert cyclohexene into 1,2-cyclohexanediol [16]. After 5 h, the flask immediately transfers into the second oil bath which its temperature was adjusted at 87 °C and was heated for 15 h. In this condition the pure adipic acid was obtained in 84% yield (Table 1, entry 4) and 99% selectivity (determined by gas chromatography (GC)) toward other dicarboxylic acids which might be produced from some rearrangement reactions [16]. Increasing the amount of H<sub>2</sub>O<sub>2</sub> to



Scheme 1. Schematic illustration of catalyst 1 preparation.



Fig. 2. XRD patterns of pure silica gel, material A and catalyst 1.

6 mmol per mol of cyclohexene had negative effect on the reaction yield (Table 1, entry 5). This observation can be explained via the effect on the reaction pH in the higher ratio of hydrogen peroxide/cyclohexene (H<sub>2</sub>O<sub>2</sub>/CyH). To investigate this issue, the initial pH of the reaction mixture in the optimum condition (Table 1, entry 4) was determined to be 0.89. According to the literature report [15], the suitable pH for formation of monoprotonated peroxotungstate species in the reaction mixture is between pH 0.4 and 3. By increasing the molar ratio (not concentration) of hydrogen peroxide to H<sub>2</sub>O<sub>2</sub>/CyH = 6, this value increased to 1.08. The increase of pH led to decrease of the amounts of

 Table 1

 The data of the catalytic performance in direct oxidation of cyclohexene to adipic acid.

					Product (%)		
Entry	Catalyst	Acid	CyH conv. (%)	T.O.N <sup>a</sup>	Adipic acid <sup>b,c,d</sup>	Diol	Other
1	Catalyst <b>1</b>	HC1	95	8	29	24	42
2	Catalyst <b>1</b>	$H_2SO_4$	98	13	47	14	33
3	Catalyst <b>1</b>	PTSA	100	18	64	-	31
4	Catalyst 1	PTSA	100	24	84 (89) <sup>e</sup>	-	11
5	Catalyst <b>1</b>	PTSA	100	21	75 <sup>f</sup>	-	10
6	Catalyst <b>1</b>	PTSA	100	17	88 <sup>g</sup>	-	6
7	Catalyst <b>1</b>	-	10	-	Trace	-	-
8	-	PTSA	0	-	N.R	-	-
9	Material A	PTSA	0	-	N.R <sup>h</sup>	-	-
10	Material <b>B</b>	PTSA	8	-	Trace <sup>h</sup>	-	-
11	Pure silica	PTSA	0	-	N.R <sup>i</sup>	-	-

<sup>a</sup> T.O.N (turnover number) refers to moles of adipic acid produced per mol of  $WO_4^{2-}$ .

<sup>b</sup> Yield refers to isolated pure product and gave satisfactory <sup>1</sup>H NMR spectra.

<sup>c</sup> 350 mg of catalyst **1** was used in all experiments, unless otherwise stated.

<sup>d</sup> Reaction time (h)/temperature: entries 1–3: 15/73; entries 4–11: 5/73 then 15/87. <sup>e</sup> GC yield.

<sup>f</sup> Molar ratio of  $H_2O_2/CyH = 6$ .

<sup>g</sup> 500 mg of catalyst **1** was used for the reaction.

<sup>h</sup> 300 mg of material **A** and **B** was used as catalyst.

<sup>i</sup> 200 mg of un-functionalized silica gel was used as catalyst.

monoprotonated peroxotungstate species and thus reduced the conversion of cyclohexene to adipic acid.

Increasing the amount of the catalyst to 500 mg did not significantly increase the yield of reaction (Table 1, entry 6). Thus the condition which has been stated in entry 4 of Table 1 which has higher turnover number (T.O.N) was selected as the optimum reaction condition. Notably, no noticeable adipic acid was obtained by using either solely catalyst **1** (Table 1, entry 7) or PTSA (Table 1, entry 8). Furthermore, neither material **A** nor **B** can catalyze the reaction (Table 1, entries 9 and 10).

A proposed mechanism of the reaction is shown in Scheme 2 considering four steps oxidation. In this mechanism, the reaction can be catalyzed via in situ formation of peroxotungstate species from  $WO_4^{2-}$  in the acidic media [15,17]. At the first oxidation step, cyclohexene is converted to 1,2-epoxycyclohexane (step 1) following formation of 1,2-cyclohexanediol (confirmed by GC) in the acidic media. Oxidation of the resulted diol to 2-hydroxy cyclohexanone (step 2) and 7-hydroxyoxepan-2-one (step 3) are the second and the third oxidation steps, respectively. The fourth oxidation step leads to produce adipic anhydride (step 4). The final intermediate undergoes ring opening to produce adipic acid. Table 1 provides some useful data about the by-products and intermediates.

The reusability of catalyst **1** was also investigated in direct oxidation of cyclohexene to adipic acid. In this regard after the reaction termination, the catalyst was vacuum filtrated and the material is dried in an oven. Nearly 97% of the initial weighted catalyst could be recovered. The recovered catalyst was then subjected into another reaction run with identical conditions which stated at the entry 4 of Table 1. The results indicated that the catalyst can be recovered at least for five reaction sequences with an average 82% yield of adipic acid (Fig. 3).

According to the FT-IR spectrum, the recovered catalyst after five runs had no noticeable changes in structure in comparison of initial prepared catalyst (See Supplementary material).

The loading of tungsten of the five-time recovered catalyst was determined by atomic absorption analysis to be 0.93 mmol g<sup>-1</sup>. The result indicates that after 5th reaction run, more than 91% of the WO<sub>4</sub><sup>2-</sup> species has been retained by the surface ammonium functionalities and a little (but not negligible) catalyst loss of ~9% occurred after 5th reaction run. It is worth mentioning that continuing reusability experiment of the catalyst up to 10 runs gave moderated yield (63%) of adipic acid at 10th run of reaction.

### 3. Conclusion

In summary, an efficient and reusable silica-functionalized ammonium tungstate catalyst was reported as a non-nitric acid route for oxidation of cyclohexene to adipic acid using commercially available reagents. In this method the adipic acid was synthesized using  $H_2O_2$  as an oxidant which produces only water as by-product. We showed that the surface ammonium functionalities strongly retain  $WO_4^2$  species. Additionally, it provided suitable polarity to the surface of the catalyst for efficient diffusions of both organic starting materials and aqueous hydrogen peroxide. The catalyst was simply separated and reused for five reaction runs with an average 82% yield. Because of elimination of nitrous oxide emission, the presented method is green and significantly less hazardous than nitric acid oxidation pathway.

#### Acknowledgment

The authors gratefully acknowledge Sharif University of Technology research council for financial support of this work.

#### Appendix A. Supplementary data

Picture of the catalyst; FT-IR spectra of the catalyst; TEM of catalyst **1**, SEM of catalyst **1** and <sup>1</sup>H NMR spectra of the adipic acid associated with



Scheme 2. Proposed mechanism of cyclohexene oxidation to adipic acid.



Fig. 3. Recycling experiment for catalyst 1.

this article. Supplementary data to this article can be found online at http://dx.doi.org/10.1016/j.catcom.2013.10.001.

#### References

- [1] R.A. Mayer, The 100 Most Important Chemical Compounds, 1st ed. Greenwood
- Press, London, 2007. M.T. Musser, Ullmann's Encyclopedia of Industrial Chemistry, Wiley–VCH, [2] Weinheim, 2005.
- R.E. Dickinson, R.J. Cicerone, Nature 319 (1986) 109-115. [3]
- Greenhouse Gas Emissions; Nitrous Oxide Emissions; United States Environmental [4] Protection Agency, http://epa.gov/climatechange/ghgemissions/gases/n2o.html. K. Sato, M. Aoki, R. Noyori, Science 281 (1998) 1646-1647.
- [6] W. Zhu, H. Li, X. He, Catal. Commun. 9 (2008) 551-555.
- [7] Y. Wen, X. Wang, H. Wei, B. Li, P. Jin, L. Li, Green Chem. 14 (2012) 2868-2875.
- [8] M. Vafaeezadeh, M. Mahmoodi Hashemi, M. Shakourian-Fard, Catal. Commun. 26 (2012) 54-57.
- [9] M. Vafaeezadeh, M. Mahmoodi Hashemi, Chem. Eng. J. 221 (2013) 254-257.
- [10] Z. Saedi, S. Tangestaninejad, M. Moghadam, V. Mirkhani, I. Mohammadpoor-Baltork, Catal. Commun. 17 (2012) 18-22.
- S. Ren, Z. Xie, L. Cao, X. Xie, G. Qin, J. Wang, Catal. Commun. 10 (2009) 464-467. [11]
- [12] G. Lapisardi, F. Chiker, F. Launay, J.-P. Nogier, J.-L. Bonardet, Catal. Commun. 5 (2004) 277-281.
- [13] J. Hukkamäki, T.T. Pakkanen, Microporous Mesoporous Mater. 65 (2003) 189–196. [14] R. Qu, M. Wang, C. Sun, Y. Zhang, C. Ji, H. Chen, Y. Meng, P. Yin, Appl. Surf. Sci. 255
- (2008) 3361-3370.
- R. Noyori, M. Aoki, K. Sato, Chem. Commun. (2003) 1977–1986. [15]
- P. Jin, Z. Zhao, Z. Dai, D. Wei, M. Tang, X. Wang, Catal. Today 175 (2011) 619-624. [16]
- [17] Z. Bohström, I. Rico-Lattes, K. Holmberg, Green Chem. 12 (2010) 1861-1869.