

Chemistry A European Journal

 **Chemistry
Europe**
European Chemical
Societies Publishing

Accepted Article

Title: One-step Chemo-, Regio- and Stereoselective Reduction of Ketosteroids to Hydroxysteroids over Zr-containing MOF-808 Metal-organic Frameworks

Authors: Hans-Hilmar Mautschke and Francesc X. Llabrés i Xamena

This manuscript has been accepted after peer review and appears as an Accepted Article online prior to editing, proofing, and formal publication of the final Version of Record (VoR). This work is currently citable by using the Digital Object Identifier (DOI) given below. The VoR will be published online in Early View as soon as possible and may be different to this Accepted Article as a result of editing. Readers should obtain the VoR from the journal website shown below when it is published to ensure accuracy of information. The authors are responsible for the content of this Accepted Article.

To be cited as: *Chem. Eur. J.* 10.1002/chem.202100967

Link to VoR: <https://doi.org/10.1002/chem.202100967>

WILEY-VCH

FULL PAPER

One-step Chemo-, Regio- and Stereoselective Reduction of Ketosteroids to Hydroxysteroids over Zr-containing MOF-808 Metal-organic Frameworks


H. –H. Mautschke,^[a] and F. X. Llabrés i Xamena^{*[a]}

[a] Dr. H. –H. Mautschke and Dr. F. X. Llabrés i Xamena
 Instituto de Tecnología Química, Universitat Politècnica de València, Consejo Superior de Investigaciones Científicas,
 Avda. de los Naranjos s/n, 46022 Valencia, Spain.
 E-mail: flabres@itq.upv.es
 Twitter handle: @ITQ_UPVCISIC

Supporting information for this article is given via a link at the end of the document.

Abstract: Zr-containing MOF-808 is a very promising heterogeneous catalyst for the selective reduction of ketosteroids to the corresponding hydroxysteroids through a Meerwein-Ponndorf-Verley (MPV) reaction. Interestingly, the process leads to the diastereoselective synthesis of elusive 17 α -hydroxy derivatives in one step, while most chemical and biological transformations produce the 17 β -OH compounds, or they require several additional steps to convert 17 β -OH into 17 α -OH by inverting the configuration of the 17 center. Moreover, MOF-808 is found to be stable and reusable, and it is also chemoselective (only keto groups are reduced, even in the presence of other reducible groups such as C=C bonds) and regioselective (in 3,17-diketosteroids only the keto group in position 17 is reduced, while the 3-keto group remains almost intact). Kinetic rate constant and thermodynamic parameters of estrone reduction to estradiol have been obtained by a detailed temperature-dependent kinetic analysis. The results evidence a major contribution of the entropic term, thus suggesting that the diastereoselectivity of the process is controlled by the confinement of the reaction inside the MOF cavities, where the Zr⁴⁺ active sites are located.

synthetic analogs used in medicine, such as glucocorticoids and corticoids in general.^[2] Meanwhile, hydroxysteroids are also relevant compounds in the pharmaceutical industry, and in particular those containing a hydroxyl group attached to C17, such as estradiol, androstanediol or testosterone/epitestosterone. One possible route to prepare these hydroxysteroids is by a direct stereoselective reduction of the corresponding ketosteroid, which can be carried out by using either a variety of microorganisms^[3] or with chemical reducing agents.



Scheme 1. Steroids skeleton and conventional atom and ring labeling.

Introduction


Steroids are a large group of chemical substances sharing a 17-carbon atom skeleton composed of four fused rings (three six-membered rings and one five-membered ring), conventionally denoted A-D, as shown in Scheme 1.^[1] Steroid compounds vary from each other in the type of groups attached to this skeleton, their position, and configuration. Small modifications in the structure of these steroids produce significant differences in their biological activity. Therefore, the development of novel routes to modify existing steroids in a controlled way to improve their activity or to prepare new steroid derivatives with potential pharmacologic activity is an area of active research. In this sense, chemo-, regio- and stereoselective (bio)transformation of steroids using highly selective catalysts or microorganisms is crucial.

Within the large family of steroids, ketosteroids (also denoted oxosteroids) are steroids in which at least one hydrogen atom of the steroid nucleus has been replaced by a keto group (C=O). Many endogenous hormones are ketosteroids, as well as their

In general, biotransformation has several advantages over chemical routes, including regio- stereo- as well as enantioselectivity, thus allowing the preparation of chiral products. From an economic point of view, biotransformations can also be cheaper than chemical methods. However, in many cases, the reduction of ketosteroids to hydroxysteroids by microorganisms is accompanied by unwanted side reactions, such as C=C bond reduction or hydroxylation at other positions of the steroid skeleton,^[4–6] that decrease the final yield of the target hydroxysteroids and complicate their purification and isolation. Additional complications may arise in biocatalytic processes due to the low solubility in aqueous medium of steroids in general, or related to the regeneration of the cofactors (NADH or NADPH) used as the source of hydride ions in the process.

FULL PAPER

Besides biocatalytic methods, reduction of ketosteroids can be also achieved by using chemical reducing agents, such as NaBH_4 , $\text{Zn}(\text{BH}_4)_2$ or LiAlH_4 , though these methods present their own limitations as well. For instance, reduction of 17-ketosteroids with NaBH_4 produces exclusively 17 β -OH isomers due to the steric hindrance of the 18-methyl group that blocks hydride attack from the upper face (see Scheme 2). Therefore, when the product of interest is the 17 α -OH isomer, most efforts have been focused on inverting the configuration of 17 β -OH through Mitsunobu reactions,^[7,8] or by the formation and displacement of sulfonyl ester derivatives.^[9–11] However, both methods introduce further synthetic steps, including protection/deprotection reactions using expensive or non-commercial reagents, and complicating product isolation and purification. As a result, the final yield obtained of the target 17 α -OH is usually very low.



Scheme 2. Reduction of 17-ketosteroids by most chemical reducing compounds yields 17 β -OH compounds due to the steric hindrance of the 18-methyl group.

Besides stereoselectivity, regioselectivity can also be an issue when chemical reducing agents are used for the reduction of steroids bearing more than one keto group. For instance, 3-ketosteroids are in general more reactive than 17- or 20-ketosteroids.^[12] Therefore, the preparation of 17-OH products can be challenging when more than one keto groups are present in the starting ketosteroid, so that mixtures of various mono- and polyhydroxylated products can be obtained. Finally, also chemoselectivity of the reaction must be taken into account when working with ketosteroids containing other reducible groups (such as C=C bonds) besides the target carbonyl group.

Zirconium trimesate MOF-808 is a metal-organic framework (see structure in Figure S1) that was first described in 2014 by Furukawa et al.^[13] This compound has recognized catalytic activity for the Meerwein-Ponndorf-Verley (MPV) reduction of various carbonyl compounds.^[14–16] In this sense, we have shown^[16] that pristine and defect-engineered MOF-808 are more active for this reaction than the archetypal zirconium terephthalate, UiO-66.^[17] This was attributed to a high availability of coordinatively unsaturated Zr^{4+} sites (*cus*) in MOF-808 upon removal of formate ions used during the synthesis. Meanwhile, *cus* in UiO-66 are only located at missing-linker defect sites and are thus much less abundant.^[18] A further advantage of MOF-808 compared to UiO-66 is its wider pore structure (pore apertures are 14 Å in MOF-808 and ~6 Å in UiO-66), which allows converting bulkier substrates. We showed this by comparing the MPV reduction of estrone, with approximate dimensions: 11.2 Å × 6.2 Å × 4.2 Å, using either MOF-808 or UiO-66 as catalyst. Our results showed that UiO-66 was basically inactive for this reaction, while MOF-808 produced the expected hydroxylated derivative quantitatively. Interestingly, MPV reduction of estrone with isopropanol over MOF-808 yielded the elusive 17 α -estradiol with moderate diastereoselectivity. Although the diastereoselectivity attained in that work was still far from optimum, it is worth


mentioning that 17 α -hydroxy-estradiol was obtained directly from estrone in a single reaction step, using only isopropanol as the sole reagent and avoiding any additional protection/deprotection steps (as required, for instance, in Mitsunobu type processes^[7,8]).

Encouraged by these promising results, we wanted to explore in more detail the diastereoselective reduction of estrone over MOF-808 materials. We have extended our studies to the synthesis of other challenging 17 α -hydroxysteroids of interest from the corresponding 17-ketosteroids. Selection of these compounds allowed us to further address other relevant aspects of the catalytic process, such as regio- and chemoselectivity of the MPV reaction as well as catalyst stability and reusability.

Results and Discussion

Diastereoselective reduction of estrone

The reduction of estrone (hereafter E1) at the 17 position can yield a mixture of two estradiols, as shown in Scheme 3. These two alcohols are diastereoisomers and are termed 17 α - and 17 β -estradiol (hereafter α -E2 and β -E2 for short), depending on the configuration of the 17-OH group relative to the 18-methyl group.



Scheme 3. Reduction of E1 yields a mixture of α -E2 and β -E2 diastereoisomers.

As shown in Table 1 (entry 1), when reduction of E1 was carried out over MOF-808 in isopropanol (iPrOH) at 393 K, the reaction was almost complete after 8 h (97% conversion). The corresponding turnover frequency (TOF), calculated at short reaction time, was 2.44 h⁻¹. As compared to iPrOH, the reaction was slightly slower when 2-butanol (2-BuOH) was used (TOF = 1.33 h⁻¹), but it eventually reached almost full conversion (91%) after 8 h, and complete conversion after 24 h of reaction (entry 2). The reaction also proceeded smoothly with 2-pentanol (2-PentOH) and 1-phenyl ethanol (entries 3 and 4). In all cases, the reduction of estrone produced only a mixture of α -E2 and β -E2, and no other byproducts were detected (100% selectivity).

The results obtained with MOF-808 are in sharp contrast with the little or no catalytic activity observed under the same reaction conditions with other Zr-containing compounds (entries 5–8), or using well-known MPV catalysts, such as Zr- and Al-isopropoxides (entries 9–10).

The diastereomeric ratio of the two alcohols formed, α -E2: β -E2, was determined at the end of the reaction from the corresponding ¹H NMR spectra of the reaction filtrate. The procedure used is detailed in the Supporting Information. The results obtained are also included in the last column in Table 1.

FULL PAPER

Table 1. Summary of the catalytic results for the MPV reduction of estrone over various catalysts. [a]

Entry	Catalyst	Alcohol	Conv. (time) ^[b]	TOF ^[c] (h ⁻¹)	d.r. ^[d]
1	MOF-808	iPrOH	97% (8 h)	2.44	60:40
2	MOF-808	2-BuOH	> 99% (24 h)	1.33	87:13
3	MOF-808	2-PentOH	91% (8 h)	2.11	73:28
4	MOF-808	1-phenylethanol	92% (8 h)	2.77	60:40
5	ZrO ₂	2-BuOH	2% (24 h)	-	44:56
6	ZrCl ₄	2-BuOH	13% (24 h)	-	50:50
7	Zr-beta ^[e]	2-BuOH	2% (24 h)	-	65:35
8	Zr-MCM-41 ^[e]	2-BuOH	2% (24 h)	-	52:48
9	Zr(iPrO) ₄ ·iPrOH	2-BuOH	2% (24 h)	-	50:50
10	Al(iPrO) ₃	2-BuOH	11% (24 h)	-	34:66
11	NaBH ₄ ^f		99%	-	3:97

[a] Reaction conditions: 20 mg of estrone (0.08 mmol), alcohol (ca. 16 eq) and Zr-catalyst (5 mg, ca. 18 mol% Zr), 393 K. [b] Conversion. Determined by GC. Estradiols were the only products detected. [c] Turnover frequency. Moles of estrone converted per mol of Zr and per hour of reaction. [d] α -E2: β -E2 diastereomeric ratio, calculated from the ¹H NMR spectra of the reaction filtrates (for the exact procedure used, see Supporting Information). [e] See Supporting Information for a detailed description of these catalysts. [f] The procedure used for estrone reduction with NaBH₄ is described in the Experimental Section.

As we reported in our previous work, the use of MOF-808 as catalyst for the MPV reduction of estrone produced a moderate amount of α -E2, while most available biotransformation methods and chemical routes produce almost exclusively the β -E2 isomer (see entry 11 in Table 1 for the results obtained with NaBH₄). This is a very motivating result from the practical point given the current interest in α -E2 for its anti-oxidative and anti-inflammatory properties and as a potent ligand for a membrane-associated ER-

X receptor and the activation of MAPK/ERK.^[19] α -E2 is of pharmaceutical interest for treating degenerative diseases, such as Alzheimer, Parkinson, Friedreich's ataxia or stroke, with much less secondary effects than the β -E2 isomer.^[20–23] Therefore, the development of new synthetic (catalytic) routes for the preparation of this compound from cheap starting compounds, such as estrone, has an obvious interest.

In our previous work,^[16] a ca. 60:40 d.r. was achieved when iPrOH was used at 353 K. Thus, although α -E2 was still the minor product of the reaction, the amount obtained was still considerably higher than in previous reports on the synthesis of similar 17 α -OH compounds.^[12,24,25] In the present case, the results obtained with iPrOH at 393 K were significantly better: 60% selectivity to α -E2 (entry 1), thus becoming the major product of the reaction. Since the diastereoselectivity attained in the MPV reduction of estrone does not seem to depend on the reaction temperature (see below, Figure 2), we attribute the higher selectivity to α -E2 attained in the present work to improvements in the MOF-808 preparation and activation procedure (viz. formate removal) compared to our previous study.

Still better results were obtained when 2-BuOH was used as a solvent and reducing alcohol, attaining an impressive 87:13 d.r. at 91% conversion after 8 h of reaction (entry 2). When the size of the secondary alcohol used was further increased (viz., 2-PentOH and 1-phenyl ethanol), the d.r. decreased to 73:28 and 60:40, respectively, thus evidencing that 2-BuOH provided the optimum diastereoselectivity among the alcohols tested.

We thus considered the reaction with 2-BuOH at 393 K to evaluate the stability and reusability of MOF-808. According to the XRD characterization of the catalyst recovered after the MPV reaction, the solid was found to be stable under the reaction conditions used, and both the catalytic activity and diastereoselectivity to α -E2 was maintained for at least 6 catalytic cycles, as shown in Figure 1. Meanwhile, ICP analysis of the filtrate after the reaction revealed a minimal Zr⁴⁺ leaching (less than 1% of the total zirconium used) from the catalyst to the reaction medium.




Figure 1. Reusability of MOF-808 for the MPV reduction of estrone with 2-BuOH at 393 K. (Left) Estrone conversion (white bars) and selectivity to α -E2 (■). (Right) X-ray powder diffraction pattern of fresh MOF-808 (down) and MOF-808 recovered after 6 catalytic cycles (top).

FULL PAPER

Effect of the reaction temperature. The effect of reaction temperature on the product distribution was assessed with both iPrOH and 2-BuOH in the temperature range from 353 to 403 K.

Figure 2 shows the time-conversion plots obtained and the corresponding α -E2: β -E2 d.r. measured at the end of the reaction (white bars in the insets).




Figure 2. Time-conversion plots of MPV reduction of estrone over MOF-808 using isopropanol (left) or 2-butanol (right) in the temperature range 353-403 K. In each plot, the inset shows the diastereomeric ratio of the reaction, d.r. (α -E2: β -E2).

Upon raising the reaction temperature from 353 K to 403 K, a sharp and progressive increase of the reaction rate was observed for both iPrOH and 2-BuOH. Thus, in the case of iPrOH, full estrone conversion was attained after only 4 h of reaction at 403 K, while up to 48 h were needed to reach 83% conversion at 353 K. Thus, calculated TOFs increased from 0.78 h^{-1} to 9.11 h^{-1} in the 353-403 K range. The same holds for 2-BuOH, for which TOF increased from 0.33 to 3.78 h^{-1} from 353 to 403 K.

Meanwhile, the diastereoselectivity of the reaction remained almost unchanged within the whole temperature range and depended only on the alcohol used (see insets in Figure 2). This lack of kinetic or thermodynamic control is in agreement with the reaction taking place inside the MOF cavities (where the Zr^{4+} are located) and being affected mainly by cavity confinement effects during the formation of the transition state (see below).

Kinetic analysis. Kinetic rate constants of α -E2 and β -E2 formation (hereafter k_{α} and k_{β}) were calculated for both iPrOH and 2-BuOH in the 353-403 K temperature range, as detailed in the Supporting Information. Apparent activation energies (E_a) for the formation of α -E2 and β -E2 were calculated from the slopes of the corresponding Arrhenius plots shown in Figure 3, while the intercept with the y-axis was used to calculate the pre-exponential factors, k_0 , which are correlated with entropic factors. To assess the goodness of the fit, the values of E_a and k_0 obtained for each solvent were used to plot the theoretical evolution of the reaction rate constant, k , as a function of the temperature according to the formula $k = k_0 \exp(-E_a/RT)$ and compared with the experimental data (see Figure S6 in the Supporting Information).




Figure 3. Arrhenius plots for the conversion of estrone to α -E2 and β -E2 in iPrOH (left) and 2-BuOH (right), with calculated apparent activation energies (E_a) and pre-exponential factors (k_0) for each compound.


FULL PAPER

The calculated activation energies are in general lower for iPrOH than for 2-BuOH, reflecting the faster E1 conversion observed for iPrOH (see Figure 2). For both iPrOH and 2-BuOH, the formation of α -E2 and β -E2 have very similar apparent activation energies, being only slightly lower for α -E2 than for β -E2: 79.7 and 81.7 kJ/mol for iPrOH, and 83.2 and 84.9 kJ/mol for 2-BuOH. Meanwhile, the pre-exponential factors are in all cases comparable, all of them of the same order of magnitude.

Given the small differences observed in both E_a and k_0 values, it is difficult at this point to determine what are the main factors governing the higher α -E2 diastereoselectivity obtained with 2-BuOH compared to iPrOH, or why the selectivity does not seem to be affected by the reaction temperature. Moreover, if only the differences in E_a between the two isomers (ΔE_a) are considered, one would expect a slightly higher selectivity towards α -E2 in iPrOH than in 2-BuOH (since $\Delta E_a = 2$ kJ/mol for iPrOH, and $\Delta E_a = 1.7$ kJ/mol for 2-BuOH). This obviously does not correspond to the d.r. observed for this reaction. It is thus evident that entropic contributions must play a relevant role in determining the observed dependence of the reaction diastereoselectivity on the alcohol used, as we will show below

While the Arrhenius equation is an empirical model, the Eyring-Polanyi equation, derived from the Transition State Theory, can be used to calculate directly the values of the entropy (ΔS^\ddagger), enthalpy (ΔH^\ddagger), and Gibbs free energy (ΔG^\ddagger) of activation for both α -E2 and β -E2 and for the two alcohols used (see Figure S7 and Table 2). Here, ΔG^\ddagger , ΔH^\ddagger , and ΔS^\ddagger represent the changes in energy upon forming an activated transition state complex between estrone, the secondary alcohol, and the Zr^{4+} active site of MOF-808. In this sense, we recall here that the generally accepted mechanism for the MPV reduction of ketones over Lewis acid catalysts assumes the simultaneous adsorption of the alcohol and the ketone on the active site, involving a six-membered cyclic transition state,^[26] which in the case of estrone should have the structure shown in Scheme 4.

For a given solvent, we can also evaluate differential activation parameters ($\Delta\Delta G^\ddagger$, $\Delta\Delta H^\ddagger$ and $\Delta\Delta S^\ddagger$), which correspond to the difference between the transition states leading to α -E2 and β -E2. These differential parameters are also reported in the bottom part of Table 2 (α - β). To help interpret the meaning of these parameters, Figure 4 shows a schematic representation (not to scale) of the energy profile of the reaction with iPrOH and 2-BuOH, as well as simple snapshots representing the most relevant structures formed in the course of the reaction.



Scheme 4. Proposed structure of the two possible transition states for the MPV reduction of estrone leading to α -E2 and β -E2 over MOF-808, with either iPrOH or 2-BuOH.

As can be seen in Table 2, when the MPV reaction is carried out in 2-BuOH at 393 K, the formation of the activated complex leading to α -E2 is preferred over the other transition state by 4.1 kJ mol⁻¹ ($\Delta\Delta G^\ddagger$ in bottom part in Table 2, see also Figure 4), while this difference is only 1.4 kJ mol⁻¹ in the case of iPrOH. Thus, $\Delta\Delta G^\ddagger$ values in Table 2 directly reflect the higher d.r. obtained for 2-BuOH than for iPrOH: ca. 82% and 61% in the whole 353-403 K temperature range (see insets in Figure 2).

Table 2. Enthalpy, entropy and Gibbs free activation energy (ΔH^\ddagger , ΔS^\ddagger and ΔG^\ddagger) for α -E2 and β -E2 over MOF-808 using iPrOH and 2-BuOH. The bottom part reports the differential activation thermodynamic parameters, calculated as the difference between the transition states leading to α -E2 and β -E2 (α - β) in terms of Gibbs free energy ($\Delta\Delta G^\ddagger$), and breakdown into enthalpic ($\Delta\Delta H^\ddagger$) and entropic contributions ($-\Delta\Delta S^\ddagger$).

		ΔS^\ddagger (J mol ⁻¹ K ⁻¹)	$-\Delta\Delta S^\ddagger$ [a] (kJ mol ⁻¹)	ΔH^\ddagger (kJ mol ⁻¹)	ΔG^\ddagger [a] (kJ mol ⁻¹)
iPrOH	α -E2	-61.8	24.3	76.6	100.9
	β -E2	-60.5	23.8	78.5	102.3
2-BuOH	α -E2	-56.0	22.0	80.0	102.0
	β -E2	-61.9	24.3	81.8	106.1
		$\Delta\Delta S^\ddagger$ (J mol ⁻¹ K ⁻¹)	$-\Delta\Delta S^\ddagger$ [a] (kJ mol ⁻¹)	$\Delta\Delta H^\ddagger$ (kJ mol ⁻¹)	$\Delta\Delta G^\ddagger$ [a] (kJ mol ⁻¹)
α - β	iPrOH	-1.3	+0.5	-1.9	-1.4
	2-BuOH	+5.9	-2.3	-1.8	-4.1

[a] Calculated at 393 K.

FULL PAPER

iPrOH

2-BuOH




Figure 4. Schematic energy diagram (not to scale) showing the differences in energies between the two activated complexes leading to α -E2 and β -E2 in iPrOH (left) and 2-BuOH (right). The bottom part shows simple snapshots representing the most relevant structures formed in the course of the reaction.


For the reaction in 2-BuOH, the entropy loss upon the formation of the transition state is lower for α -E2 than for β -E2 (-56.0 vs $-61.9 \text{ J mol}^{-1} \text{ K}^{-1}$). Therefore, both the differential enthalpic ($\Delta\Delta H^\ddagger = -1.8 \text{ kJ/mol}$) and entropic contributions ($-T\Delta\Delta S^\ddagger = -2.3 \text{ kJ/mol}$) have the same sign, and both contribute to lowering the energy of the transition state of α -E2 compared to β -E2. On the contrary, for the reaction in iPrOH, the differential enthalpic and entropic terms have opposite signs (-1.9 and $+0.5 \text{ kJ/mol}$, respectively), partially counteracting each other. As a consequence, the energy difference between both transition states is much lower in iPrOH.

Taken the above data together, our results thus suggest that the space available inside the MOF cavities can accommodate better the transition state $TS-\alpha$ than $TS-\beta$, and this difference is higher with 2-BuOH than with iPrOH. This is not surprising if we consider that 2-BuOH (or iPrOH) directly participate in the formation of the activated complex (see Scheme 4).

Therefore, in the case of 2-BuOH, the important contribution from the entropic term on the total energy difference between the two possible transition states strongly indicates that confinement effects and steric hindrance inside the MOF cavity are the main reasons determining the preferred reaction pathway and the observed diastereoselectivity. Accordingly, the selectivity to α -E2 is much lower for the reaction with iPrOH, for which the entropic term partially neutralizes the enthalpic contribution, and the energy difference is therefore lower.

Diastereoselective reduction of 5 α -androstane-3 β -ol,17-one (epiandrosterone)

Given the excellent diastereoselectivity attained with MOF-808 for the reduction of estrone to 17 α -estradiol, we wanted to extend the study to the reduction of other ketosteroids. In this case, we considered the reduction of epiandrosterone (hereafter EPIA), which also bears a keto group in position 17. Similar to estrone, EPIA reduction can yield two diastereoisomers, 5 α -androstane-3 β ,17 α -diol (α -EPIAdiol) and 5 α -androstane-3 β ,17 β -diol (β -EPIAdiol), depending on the relative conformation of the 17-OH group with respect to the 18-CH₃ group (Scheme 5):



Scheme 5. Reduction of epiandrosterone (EPIA) can yield a mixture of androstadiols (α -EPIAdiol and β -EPIAdiol).

Analogous to the case of estrone reduction, the presence of the CH₃ group in position 18 introduces a strong steric hindrance to the hydride addition to the carbonyl from the upper face, so β -EPIAdiol is usually the only product obtained in most synthetic routes. Thus, the preparation of the elusive α -EPIAdiol compound is a challenging synthetic process. Nevertheless, α -EPIAdiol can

FULL PAPER

be an interesting target for the treatment of cancer, due to anti-androgenic properties, and in the treatment of osteoporosis,^[27,28] so new selective synthetic routes are also sought for this compound.

To our delight, MPV reduction of EPIA using MOF-808 as catalyst produces α -EPIAdiol as the main product with excellent diastereoselectivities, depending on the secondary alcohol used: 77% d.r. and 84% d.r. in the case of iPrOH and 2-BuOH, respectively, as shown in Figure 5. In both cases, androstadiols were the only products observed, and the catalyst was found to be stable and reusable.




Figure 5. MPV reduction of epiandrosterone (EPIA) to androstadiols using iPrOH and 2-BuOH. The obtained diastereoselectivity (*d.r.*) to α -EPIAdiol is indicated. *d.r.* was calculated by ^1H NMR of the filtrate at the end of the reaction (see Supporting Information). Reaction conditions: 23 mg of EPIA (0.08 mmol), alcohol (ca. 16 eq) and Zr-catalyst (5 mg, ca. 18 mol% Zr), 393 K.

Together with estrone, the results obtained for the MPV reduction of EPIA confirm the general applicability of MOF-808 as a stable and reusable catalyst for the diastereoselective reduction of 17-ketosteroids to the corresponding 17 α -hydroxysteroids. Thus, MPV reduction of ketosteroids over MOF-808 represents a very attractive and reliable one-step catalytic alternative for the existing stoichiometric reactions using hydride transfer compounds. As mentioned in the introduction, most existing chemical methods usually yield 17 β -OH compounds, so preparation of 17 α -OH isomers require several synthetic steps and they use toxic and/or expensive reagents, leading to very low final yields of the target compound.


Regio- and diastereoselective reduction of androstenedione

To increase further the scope of MOF-808 as a catalyst for the MPV reduction of ketosteroids, it would be highly desirable to develop a catalyst not only diastereoselective but also chemo- and regioselective. It is well-known that MPV is, in general, a chemoselective process, which only transforms carbonyl groups whilst leaving other easily reducible functional groups intact, as in the case of unsaturated ketones.^[29] However, a more demanding situation is found when the substrate contains more than one carbonyl group that, in principle, can be reduced, leading to a mixture of mono- and polyhydroxylated compounds. In this case, the regioselectivity of the reduction process may become an issue.

Δ^4 -androstene-3,7-dione (androstenedione, hereafter A4) contains a C=C bond in position 4 and two keto groups in positions 3 and 17, so we considered it as an appropriate

substrate to assess both chemo- and regioselectivity of the MPV reduction using MOF-808 catalyst.

In our hands, upon reduction of A4 over MOF-808 with either iPrOH or 2-BuOH, we did not observe the formation of products coming from the reduction of the C=C bond (100% chemoselectivity) or the mono-reduction of the carbonyl group in position 3 (see Supporting Information for more details on product identification by ^1H and ^{13}C -NMR). Therefore, the only products detected were testosterone (T) and epitestosterone (E) from the reduction of the 17 keto group, and a mixture of diol isomers coming from the reduction of both keto groups, as shown in Scheme 6:



Scheme 6. MPV reduction of androstenedione (A4) over MOF-808 yields testosterone (T), epitestosterone (ET) and a mixture of diol isomers with different local configurations of the OH groups at positions 3 and 17.

Figure 6 shows the time-conversion plots and product distribution obtained with 2-BuOH at 353 K, while iPrOH afforded very similar results (see Figure S8 in the Supporting Information).




Figure 6. (■) A4 conversion; (○) yield of mono-hydroxylated (T+ET); and (▲) yield of dihydroxylated products obtained over MOF-808 with 2-BuOH at 353 K. Reaction conditions: 10 mg of A4 (0.035 mmol), 1 mL 2-BuOH (ca. 30 eq) and 10 mg MOF-808.

According to the time evolution of products shown in Figure 6, A4 reduction at the 17 position occurs in the first place, yielding a mixture of mono-hydroxylated T and ET as primary products, followed afterwards by the reduction of the keto group also in position 3, to form the corresponding 3,17-diols, at longer reaction times. Thus, the amount of 17-mono-hydroxylated products increases during the first 8 hours of reaction, reaching a maximum yield of 58%, and then starts to decrease gradually as more diols are formed.

FULL PAPER

Identification of the products using ^{13}C and ^1H NMR spectroscopy (see Supporting Information) revealed that the amount of T formed was very low, close to the detection limits of the technique, and in any case, less than 5% referred to ET. Therefore, as in the case of estrone and epiandrosterone discussed above, MOF-808 yielded the corresponding $17\alpha\text{-OH}$ compound (*viz.*, epitestosterone) with excellent diastereoselectivity over the 17β -compound, higher than 95%. This result is also interesting from the practical point of view, since ET has applications in the treatment of prostate cancer, due to its

inhibitory effects of 5 α -reductase,^[30] and it has agonistic effects on a Prostate-Specific G-Protein Receptor (PSGR/OR51E2).^[31]

In an attempt to improve the selectivity to mono-hydroxylated products (T and ET) and minimize the formation of diols, the reaction temperature was varied within the 333–393 K range. Figure 7 shows the A4 conversion curves and corresponding selectivity-conversion plots obtained as a function of the temperature. The complete kinetic data is given in Table S1 in the Supporting Information.




Figure 7. (Left) A4 conversion over MOF-808 in 2-BuOH at the indicated temperature. (Right) Selectivity to monohydroxylated products, ET+T, as a function of the A4 conversion and temperature.

As it is seen in Figure 7, the maximum selectivity to monohydroxylated products is around 85% at 10–20% conversion, but this value decreases gradually at higher levels of conversion, dropping faster as the reaction temperature increases. Therefore, increasing the reaction temperature has a clear detrimental effect on the selectivity to mono-hydroxylated products. Nevertheless, our data show that if the reaction temperature is kept at 333 K, it is possible to attain a level of A4 conversion as high as 70–80% after 30–35 hours, while maintaining a selectivity to monohydroxylated compounds above 80% (see the arrow in Figure 7) and a diastereoselectivity >95% to ET, which is considered an excellent result.

Overall, our study has revealed that MOF-808 affords a very good selectivity for the reduction of A4 to ET, since: i) the C=C bond in position 4 remains intact under the reaction conditions used (100% chemoselectivity); ii) no traces of 3-hydroxy-17-ketosteroids have been detected, so the 17-ketone group is selectively reduced before the 3-ketone (100% regioselectivity); iii) reduction of the 17-keto group produces epitestosterone almost exclusively (>95%); *i.e.*, the $17\alpha\text{-OH}$ isomer is selectively formed, as in the case of estrone and epiandrosterone (excellent diastereoselectivity); and iv) despite the eventual reduction of both carbonyl groups taking place at long reaction times, it is possible to minimize the formation of diols by proper selection of the reaction conditions, allowing very high A4 conversions (70–80%) while keeping very good selectivity (>80% to monohydroxylated compounds).

Conclusion

Herein we have shown that MOF-808 is a very interesting heterogeneous catalyst for the selective MPV reduction of ketosteroids to the corresponding hydroxysteroids. On the one hand, the particular structure of the Zr_6 clusters in MOF-808 (after activation and removal of the capping formate anions) provides coordination vacancies for substrate binding and transformation. On the other hand, the wide pore structure of MOF-808 compared to the steroid dimensions ensure a good diffusion of the reaction substrates and products to and from the Zr^{4+} active sites. Consequently, MOF-808 is a highly active catalyst for the MPV reduction, requiring the simultaneous coordination of the carbonyl substrate and the secondary alcohol used as a hydride source.

Interestingly, we have shown that reduction of 17-ketosteroids produces the corresponding $17\alpha\text{-OH}$ compound with very high diastereoselectivity, whereas most existing biotransformation methods and chemical routes yield the other isomer, $17\beta\text{-OH}$, as the main product. Therefore, MOF-808 provides a very attractive catalytic route for the preparation of these challenging compounds, with several improvements compared to alternative bio- and chemical processes. We have demonstrated the excellent diastereoselectivity of MOF-808 for the synthesis of three different 17α -hydroxysteroids; namely, 17α -estradiol, androstan-3 β , 17α -diol, and epitestosterone.

Temperature-dependent kinetic analysis has been used to calculate reaction rate constants, apparent activation energies and thermodynamic parameters of estrone reduction using either iPrOH or 2-BuOH. A close inspection of the energy differences between the two transition states leading to $\alpha\text{-E2}$ and $\beta\text{-E2}$ revealed a major contribution from the entropic term in the case of 2-BuOH, while in the case of iPrOH the entropic contribution partially neutralizes the enthalpic gain, thus lowering the energy differences between both transition states. These findings

FULL PAPER

strongly suggest that the diastereoselectivity to α -E2 originates from the confinement of the reaction inside the MOF cavities, in which the Zr^{4+} active sites are located. This cavity confinement inside the MOF drives the reaction preferentially through the α -E2 transition state in both iPrOH and 2-BuOH, but this preference is higher with 2-BuOH, in line with the direct participation of the secondary alcohol in the six-membered cyclic transition state.

Finally, MPV reduction of androstenedione, containing a C=C bond and two keto groups, has been used to evidence the excellent chemo-, regio- and diastereoselectivity of the reaction catalyzed by MOF-808.

Experimental Section

Catalyst preparation.

MOF-808. MOF-808 was prepared with slight modifications from an earlier reported procedure by Furukawa *et al.*^[13] Briefly, a solution was prepared with 242,5 mg of $ZrOCl_2 \cdot 8H_2O$ (0,75 mmol), 105 mg of trimesic acid (0,5 mmol) and 22,5 mL of a DMF/ HCO_2H 1:1 (v/v) mixture. The solution was transferred into a Teflon lined autoclave and heated inside an oven at 130 °C for 48 h. After cooling down to room temperature, the material was recovered by centrifugation and washed for 3 days with DMF (changing the solvent 2 times per day) and for another 3 days with EtOH (changing the solvent 2 times per day). After removing the solvent by centrifugation, the solid was dried in air. X-ray diffraction (PhillipsX'Pert, Cu K α radiation) was used to confirm the expected structure type and high crystallinity of the material. According to N_2 -adsorption experiments, calculated specific surface area (S_{BET}) and pore volume were 1345 m²g⁻¹ and 0.60 cm³g⁻¹, respectively. A summary of the most relevant characterization data of this material is shown in Figure S1 in the Supporting Information.

Other catalysts: The Supporting Information contains details of the preparation of other non-commercial catalysts used in this work for comparison purposes.

Catalytic experiments

MPV reduction of ketosteroids. Particular reaction conditions for each substrate are indicated in the text. To illustrate the typical procedure used, reduction of estrone over MOF-808 with iPrOH will be described. Estrone (20 mg, 0.08 mmols) was dissolved in iPrOH (1 mL, ca. 16 eq.) and introduced inside a screw cap glass reactor containing MOF-808 (5 mg, ca. 18 mol% Zr referred to estrone) and kept at the selected reaction temperature under magnetic stirring (stirring rate was kept > 600 rpm to ensure optimal mixing and to avoid diffusional limitations). Time-evolution of products was analyzed by GC (Agilent 7890 A, equipped with a FID detector and a DB5 30 m x 0,25 mm x 0,25 μ m column) on sample aliquots taken at fixed time intervals. Product identification was done by GC-MS and by comparison with pure standards. Peak separation of the different diastereoisomers in the resulting chromatograms was good enough to extract the concentration of the individual species. More accurate diastereomeric ratios were obtained at the end of the reaction from the corresponding ¹H NMR spectra, as detailed in the Supporting Information.

Estrone reduction with NaBH₄. A solution was prepared by dissolving estrone (40 mg, 0.15 mmols) in ethanol (5 mL). A second ethanolic solution (1 mL) containing NaBH₄ (18.9 mg) was added to the first one at 353 K under stirring and kept at this temperature for 15 min. Then, the temperature was raised to reflux, and the heating was stopped just after the boiling started, and let it stand for 5 min. To stop the reaction, 10 mL of H₂O was added and the mixture was cooled in a water-ice bath for 15 min, whereupon a white precipitate of the product formed. Finally, the product was recovered by filtration and washed with cold water and analyzed by GC as described above.

Acknowledgements

Financial support by the Spanish Government is acknowledged through projects MAT2017-82288-C2-1-P and the Severo Ochoa program (SEV-2016-0683). The Microscopy Service of the Universitat Politècnica de València is gratefully acknowledged for the electron microscopy images.

Keywords: Steroids • metal-organic frameworks • MOF-808 • Meerwein-Ponndorf-Verley • heterogeneous catalysis


- [1] G. P. Moss, *Pure Appl. Chem.* **1989**, *61*, 1783–1822.
- [2] F. Buttgerit, G. R. Burmester, B. J. Lipworth, *Lancet* **2005**, *365*, 801–803.
- [3] M. V. Donova, O. V. Egorova, V. M. Nikolayeva, *Process Biochem.* **2005**, *40*, 2253–2262.
- [4] M. A. Faramarzi, N. Zolfaghary, M. Tabatabaei Yazdi, S. Adrangi, H. Rastegar, M. Amini, M. Badiiee, *J. Chem. Technol. Biotechnol.* **2009**, *84*, 1021–1025.
- [5] W. H. Liu, C. W. Kuo, K. L. Wu, C. Y. Lee, W. Y. Hsu, *J. Ind. Microbiol.* **1994**, *13*, 167–171.
- [6] O. Schaaf, K. Dettner, *J. Steroid Biochem. Mol. Biol.* **1998**, *67*, 451–465.
- [7] F. Balssa, M. Fischer, Y. Bonnaire, *Steroids* **2014**, *86*, 1–4.
- [8] J. A. Dodge, C. W. Lugar III, *Bioorg. Med. Chem. Lett.* **1996**, *6*, 1–2.
- [9] T. Nambara, M. Numazawa, H. Takahashi, *Chem. Pharm. Bull. (Tokyo)*. **1969**, *17*, 1725–1729.
- [10] X. X. Shi, C. L. Shen, J. Z. Yao, L. D. Nie, N. Quan, *Tetrahedron Asymmetry* **2010**, *21*, 277–284.
- [11] P. P. Guo, K. Ding, *Tetrahedron Lett.* **2015**, *56*, 4096–4100.
- [12] G. Göndös, J. C. Orr, *J. Chem. Soc. Chem. Commun.* **1982**, 1238–1239.
- [13] H. Furukawa, F. Gandara, Y. B. Zhang, J. Jiang, W. L. Queen, M. R. Hudson, O. M. Yaghi, *J. Am. Chem. Soc.* **2014**, *136*, 4369–4381.
- [14] A. H. Valekar, K.-H. Cho, S. K. Chitale, D.-Y. Hong, G.-Y. Cha, U.-H. Lee, D. W. Hwang, C. Serre, J.-S. Chang, Y. K. Hwang, *Green Chem.* **2016**, *18*, 4542–4552.
- [15] E. Plessers, G. Fu, C. Y. X. Tan, D. E. de Vos, M. B. J. Roeffaers, *Catalysts* **2016**, *6*, 104.
- [16] H.-H. Mautschke, F. Drache, I. Senkovska, S. Kaskel, F. X. Llabrés i Xamena, *Catal. Sci. Technol.* **2018**, *8*, 3610–3616.
- [17] J. H. Cavka, S. Jakobsen, U. Olsbye, N. Guillou, C. Lamberti, S. Bordiga, K. P. Lillerud, *J. Am. Chem. Soc.* **2008**, *130*, 13850–13851.
- [18] F. G. Cirujano, A. Corma, F. X. Llabrés i Xamena, *Chem. Eng. Sci.* **2015**, *124*, 52–60.
- [19] C. D. Toran-Allerand, A. A. Tinnikov, R. J. Singh, I. S. Nethrapalli, *Endocrinology* **2005**, *146*, 3843–3850.
- [20] S. P. Kaur, S. Bansal, K. Chopra, *Steroids* **2015**, *96*, 7–15.
- [21] C. Behl, T. Skutella, F. Lezoualc'h, A. Post, M. Widmann, C. J. Newton, F. Holsboer, *Mol. Pharmacol.* **1997**, *51*, 535–541.
- [22] J. A. Dykens, W. H. Moos, N. Howell, *Ann. N. Y. Acad. Sci.* **2005**, *1052*, 116–135.
- [23] R. S. Santos, L. A. De Fatima, A. P. Frank, E. M. Carneiro, D. J. Clegg, *Biol. Sex Differ.* **2017**, *8*, 1–13.
- [24] G.-D. Han, Z.-Y. Lin, C.-P. Yan, *Zhongguo Yiyao Gongye Zazhi* **1994**, *25*, 490–491.
- [25] T. Ohta, H. Zhang, Y. Torihara, T. Hida, I. Furukawa, *Steroids* **1998**, *63*, 630–632.

FULL PAPER

- [26] C. F. de Graauw, J. A. Peters, H. Van Bekkum, J. Huskens, *Synthesis (Stuttg)*. **1994**, *10*, 1007–1017.
- [27] P. Wang, Y. Wen, G. Z. Han, P. K. Sidhu, B. T. Zhu, *Br. J. Pharmacol.* **2009**, *158*, 1796–1807.
- [28] T. F. H. Bovee, M. Thevis, A. R. M. Hamers, A. A. C. M. Peijnenburg, M. W. F. Nielen, W. G. E. J. Schoonen, *J. Steroid Biochem. Mol. Biol.* **2010**, *118*, 85–92.
- [29] M. De Bruyn, M. Limbourg, J. Denayer, G. V. Baron, V. Parvulescu, P. J. Grobet, D. E. De Vos, P. A. Jacobs, *Appl. Catal. A Gen.* **2003**, *254*, 189–201.
- [30] B. A. Nuck, A. W. Lucky, *J. Invest. Dermatol.* **1987**, *89*, 209–211.
- [31] T. Abaffy, H. Matsunami, *Modulators of Prostate-Specific G-Protein Receptor (PSGR/OR51E2) and Methods of Using Same*, **2018**, US2018116992.

FULL PAPER

Entry for the Table of Contents



Zr-containing MOF-808 is a stable and reusable catalysts for the chemo-, regio- and diastereoselective reduction of 17-ketosteroids to elusive 17 α -hydroxysteroids compounds, as we showed for the synthesis of 17 α -estradiol, androstan-3 β ,17 α -diol, and epitestosterone. The process is carried out in one single step and without using toxic and/or expensive reagents. A temperature-dependent kinetic analysis of estrone reduction revealed that the diastereoselectivity to 17 α -estradiol originates from the confinement of the reaction inside the MOF cavities, in which the Zr⁴⁺ active sites are located.