Journal of Materials Chemistry C

PAPER



View Article Online View Journal | View Issue

Cite this: J. Mater. Chem. C, 2014, 2, 1854

Received 1st November 2013 Accepted 5th December 2013

DOI: 10.1039/c3tc32158d

www.rsc.org/MaterialsC

Introduction

Nitrite (NO_2^{-}) is known to be able to form carcinogenic nitrosamines in the human stomach, from the reaction of nitrite with secondary amines under acidic conditions.¹ In addition, nitrate can oxidize Fe(II) in oxyhaemoglobin to Fe(III) and the oxyhaemoglobin turns into methaemoglobin. process is associated with infantile This methahemoglobinemia.² However; sodium nitrite is frequently used as a colour fixative and preservative in meat and fish. If the nitrite was over added, it would be harmful to human's health. Therefore, detecting the nitrite content of food and drinking water is really important and vital. Although numerous techniques have been developed for nitrite determination such as colorimetric procedures,³ spectroscopic determination after enzymatic reduction,⁴ and electrochemical techniques,⁵ most of them involve time-consuming and tedious procedures. In traditional spectroscopic methods, aromatic ortho-diamines are commonly used as reactive probes to detect nitrite, which are converted into benzotriazoles in the presence of NO₂⁻.⁶ However, the reaction could only take place in acidic conditions. Recently, Luis's group proved that films including acrylic acid and 1,2diaminoanthraquinone (DAQ) could detect nitrite.7 Herein, for consideration of environmental protection and limiting the production of solid wastes, we propose a new way for

Two-component organogel for visually detecting nitrite anion[†]

Qian Xia,^a Yueyuan Mao,^a Junchen Wu,^b Tianmin Shu^a and Tao Yi^{*a}

Low molecular weight two-component gels were obtained from naphthalene diimide undecanoic acid mixed with several aliphatic and aromatic diamines. The gelation properties, structural characteristics and fluorescence of these two-component gels were studied *via* scanning electron microscopy, X-ray diffraction and spectroscopy. Specifically, the gel containing diaminoanthraquinone (DAQ) was sensitive to nitrite anions. The absorbance and emission intensity of the gel in the visible range obviously decreased upon addition of an aqueous solution of sodium nitrite. The faded gel collapsed and changed to a sediment after detection and the organic acid could be recycled. Te NO_2^- detection with the gel provides a convenient method of nitrite analysis that is visible to the "naked eye".

sensing nitrite using a new kind of two-component low molecular weight (LMW) organogel containing DAQ, a probe for visually sensing nitrite in neutral aqueous solutions.

Over the past decades, LMW organogels have attracted considerable interest because of their diverse applications as smart soft materials.8 The solvent immobilized can be either organic or aqueous. The formation of organogels is facilitated by highly directional self-assembly through non-covalent interactions such as π - π stacking, hydrogen bonding, metalion coordination, dipole-dipole interactions⁹ into various 3D aggregates such as rods, long fibers, strands, tubules, or globules.¹⁰ Those gels have been applied as functional soft materials for sensors,11 electrophoretic and electrically conductive matrices,12 templates for cell growth or the growth of sol-gel structures,13 and in many other industrial fields such as cosmetics, oils, and foods.14 However, most gelators have complicated structures, such as aminophenol, long hydrophilic substituent chains, carbohydrates, dendritic substituents, cholesteryl groups and so on.15 The rationalized design and synthesis of a specifically functionalized gelator is still a challenge. So we hope to find an easier way to make functional gels without complex molecule structures and intricate synthesis processes.

Basit *et al.* reported a new kind of hydrogel expediently made from fatty acids and amines.¹⁶ Here, by introducing a fluorescent naphthalimide group,¹⁷ we designed and synthesized two novel fatty acids with emission characteristics (compounds **1** and **2**, Scheme 1). When the fatty acids are mixed with various amines, complexes could be formed that subsequently selfassembled into supramolecular networks in organic solvents. Interestingly, the red gel formed with **1** and diaminoanthraquinone (DAQ) has a colorimetric and fluorescent response to neutral solutions of sodium nitrite. The organic acid in the gel is recyclable without producing solid wastes.

^aDepartment of Chemistry and Collaborative Innovation Center of Chemistry for Energy Materials, Fudan University, Shanghai 200433, China. E-mail: yitao@fudan. edu.cn; Fax: +86 21 5566 4621

^bKey Laboratory for Advanced Materials and Institute of Fine Chemicals, East China University of Science and Technology, Shanghai 200237, China

[†] Electronic supplementary information (ESI) available: Additional absorption and emission spectra, IR spectra and LC-mass spectra. See DOI: 10.1039/c3tc32158d



Scheme 1 Chemical structures and synthesis routes to 1 and 2.

Experimental section

Materials and general methods

All reagents were used as received from the supplier without further purification unless stated otherwise. 11-Aminoundecanoic acid (99.5%), 4-bromo-1,8-naphthalic anhydride (\geq 95%), hexane-1,6-diamine (CP) and anhydrous ethane-1,2diamine (99%) were obtained from Sinopharm Chemical Reagent Co., Ltd. (Shanghai). Other chemicals and solvents were provided from Shanghai No. 1 Chemical Reagent Co. ¹H NMR and ¹³C NMR spectra were recorded on a Mercuryplus, at 400 and 100 MHz, respectively. Proton chemical shifts were reported in parts per million downfield from tetramethylsilane. ESI-MS data were recorded on a Waters Quattro Micro API LC-MS-MS spectrometer (Waters, USA). Elemental analysis was carried out on a VARIOEL3 apparatus (ELEMENTAR). Melting points were recorded on a hot-plate melting point apparatus XT4-100A without further correction.

Synthesis

The synthesis procedure for **1** and **2** is shown in Scheme 1. **1a** was synthesized according to our previous report.¹⁷

Synthesis of compound 1. LiOH (6.6 g, 276.87 mmol) in 40 mL water was added to a THF solution (40 mL) of **1a** (4.5 g, 9.23 mmol). The mixture was stirred for 3 days and organic

solvent was removed by evaporation. The water phase was acidified to pH 2–3 with HCl. The slurry was filtered and the solid was washed with ether to give 1 as a white powder. Yield 83%, m.p. 110–112 °C. ¹H NMR (400 MHz, DMSO): δ 11.90 (s, 1H), 8.69 (d, J = 8.4 Hz, 1H), 8.57 (d, J = 7.3 Hz, 1H), 8.41 (d, J = 8.3 Hz, 1H), 7.95–7.86 (m, 1H), 7.54 (t, J = 7.9 Hz, 2H), 7.39–7.25 (m, 3H), 6.98 (d, J = 8.3 Hz, 1H), 4.08–3.95 (m, 2H), 2.16 (t, J = 7.3 Hz, 2H), 1.61 (s, 2H), 1.45 (s, 2H), 1.37–1.13 (m, 12H); ¹³C NMR (100 MHz, CDCl₃): δ 177.87, 159.86, 154.91, 132.86, 131.94, 130.42, 129.73, 128.56, 126.53, 125.57, 123.99, 122.72, 120.77, 116.71, 110.70, 77.34, 77.02, 76.70, 40.45, 33.74, 29.36, 29.27, 29.11, 28.98, 28.13, 27.09, 24.68. MS (EI) calculated for C₂₉H₃₂NO₅: 474.2 [M + H]⁺, found: 474.4; anal. calcd for C₂₉H₃₁NO₅: C, 73.49; H, 6.55; N, 2.96. Found: C, 73.63; H, 6.55; N, 2.91%.

Synthesis of compound 2a. To a 50 mL anhydrous MeOH solution of (R)-2-amino-3-phenylpropanoic acid (4.50 g, 27.23 mmol), drops of thionyl chloride (98%) were added slowly during stirring. The mixture was refluxed for 8 h. Then the solvent was removed under reduced pressure. The pale powder was washed with ethyl acetate. This dried powder (2.35 g, 10.9 mmol) was then mixed with 1 (4.3 g, 9.08 mmol), DCC (3.75 g, 18.16 mmol), HOBt (1.23 g, 9.08 mmol) and Et₃N (9.18 g, 9.08 mmol) in dry CH₂Cl₂ (150 mL). The mixture was stirred and refluxed for 12 h at room temperature in nitrogen atmosphere. Then the solvent was removed under reduced pressure and the residue was subjected to column chromatography on silica gel (chloroform/petroleum ether = 4 : 1 (v/v)) to give 2a as a white powder. Yield 67%, m.p. 81–83 °C. ¹H NMR (400 MHz, CDCl₃): δ 8.65 (dd, J = 17.6, 7.6 Hz, 2H), 8.43 (d, J = 8.2 Hz, 1H), 7.76 (t, J = 7.7 Hz, 1H), 7.47 (t, J = 7.5 Hz, 2H), 7.34–6.94 (m, 8H), 6.88 (d, J = 8.2 Hz, 1H), 5.93 (d, *J* = 7.3 Hz, 1H), 4.82 (dd, *J* = 12.9, 7.0 Hz, 1H), 4.23-4.09 (m, 1H), 3.89 (q, J = 7.0 Hz, 1H), 3.66 (s, 3H), 3.29(dd, J = 14.5, 5.2 Hz, 1H), 3.06 (dd, J = 14.2, 5.6 Hz, 1H), 2.27 (t, J = 7.4 Hz, 2H), 1.63 (m, 4H), 1.32 (m, 12H). ¹³C NMR (100 MHz, CDCl₃): δ 174.45, 165.32, 164.45, 163.83, 159.91, 154.89, 134.14, 132.84, 131.93, 130.49, 129.73, 128.60, 127.73, 126.56, 125.90, 125.66, 123.97, 122.72, 120.87, 116.68, 110.64, 77.44, 77.12, 76.80, 53.12, 51.54, 40.48, 35.02, 34.20, 29.54, 29.47, 29.43, 29.30, 29.21, 28.22, 27.21, 25.04. MS (EI): m/z calculated for $C_{39}H_{43}N_2O_6 [M + H]^+$: 635.3, found: 635.7.

Synthesis of compound 2: LiOH (5.8 g, 241.66 mmol) in 50 mL water was added to a THF solution (50 mL) of 2b (5.0 g, 8.06 mmol). The mixture was stirred for 3 days and organic solvent was removed by evaporation. The water phase was acidified to pH 2-3 with HCl. The slurry was filtered and the solid was washed with ether to give 2 as a white powder. Yield 77%, m.p. 86–88 °C. ¹H NMR (400 MHz, CDCl₃): δ 8.69 (ddd, J = 8.4, 7.8,1.1 Hz, 1H), 8.46 (d, J = 8.3 Hz, 1H), 7.78 (dd, J = 8.3, 7.4 Hz, 1H), 7.57–7.41 (m, 1H), 7.38–7.09 (m, 9H), 6.91 (d, J = 8.3 Hz, 1H), 5.94 (d, *J* = 7.5 Hz, 1H), 4.87 (dd, *J* = 13.3, 6.0 Hz, 1H), 4.23– 4.07 (m, 1H), 3.73 (q, J = 7.0 Hz, 1H), 3.42 (s, 1H), 3.25 (dd, J = 14.1, 5.6 Hz, 1H), 3.14 (dd, J = 14.0, 6.2 Hz, 1H), 2.16 (t, J = 7.3Hz, 1H), 1.92 (d, J = 12.7 Hz, 1H), 1.71 (d, J = 9.3 Hz, 2H), 1.64-1.46 (m, 2H), 1.46–1.01 (m, 12H). ¹³C NMR (100 MHz, CDCl₃) δ 173.57, 165.10, 164.52, 163.93, 159.97, 154.86, 132.95, 132.00, 130.43, 129.71, 129.42, 128.55, 127.06, 126.53, 125.62, 123.97,

122.63, 120.79, 116.57, 110.67, 77.34, 77.22, 77.02, 76.71, 53.17, 49.64, 40.53, 36.49, 33.58, 29.20, 29.08, 28.04, 27.06, 25.52, 25.49, 24.79. MS (EI): m/z calculated for $C_{38}H_{41}N_2O_6$ [M + H]⁺: 621.3, found: 621.2; anal. calcd for $C_{38}H_{40}N_2O_6$: C, 73.53; H, 6.50; N, 4.51. Found: C, 73.63; H, 6.50; N, 4.43%.

Gelation test of organic fluids

When 1 or 2 mixed with diamines (shown in Scheme 2), dissolved in some organic solvent, the complexes show gelation behavior. For example, when 0.1 g (0.21 mmol) 1 and 7.35 µL (0.11 mmol) 1,2-diaminoethane were dissolved in chloroform, the two-component gelator 1+EDA was obtained after removing chloroform. Generally, the molar proportion of compound 1 or 2 with diamine is 2:1. The gelator (5 mg) and the solvent (200 μ L) were put in a hermetic test tube (1.5 mL) and heated (>75 °C) until the solid was dissolved. Then the sample vial was cooled to 25 °C (prepared sample). Qualitatively, gelation was considered successful if no sample flowed upon inverting the container at room temperature. The critical gelation concentrations (CGC) were tested using dilution method after the gels were formed (Table 1). For example, to a 200 μ L gel sample in a test tube, additional 50 µL solvent was added, followed by a heatingcooling process to see whether it could form a gel again. This process was repeated until the gel began flow, and this concentration was recorded as the CGC.

Techniques

UV-visible spectra were recorded on a UV-vis 2550 spectrometer (Shimadzu). Fluorescent spectra were obtained using an Edinburgh Instruments FLS 900 with an Xe lamp as the excitation source. Fourier transform infrared (FT-IR) spectra were recorded using an IRPRESTIGE-21 spectroscope (Shimadzu) with KBr pellets. SEM images of the xerogels were obtained using a SSX-550 (Shimadzu) with an accelerating voltage of 15 kV. Samples were prepared by diluting the gel and dropping it on the surface of a mica flake, which was then freeze dried and coated with Au. Powder X-ray diffraction patterns were generated by using a Philips PW3830 sealed-tube X-ray generator (Cu target, $\lambda = 0.1542$ nm) with a power of 40 kV and 50 mA. Samples were prepared as freeze dried gels. Freezing dry was performed in a FDU-1200 Freeze Dryer (Tokyo Rikakikai, Japan) with the trap temperature of -45 °C.



Scheme 2 Structures and abbreviations of different amines checked for gelation.

Results and discussion

Gel formation and characterization

Naphthalimide undecanoic acids 1 and 2 are used as the fundamental gel component. These two compounds have no capability to form gels by themselves. After mixing with various kinds of diamines (Scheme 2, details of preparation are given in the Experimental section), the two-component complexes can gel in a variety of organic solvents. Gelation behaviour of the complexes was checked in 14 organic solvents with the molar ratio of 1/amine or 2/amine of 2 : 1 (Table 1). It was observed that the complexes of 1 and amines were more capable of gelation than those of 2. 1 could form gel in alcohols, cyclohexane, acetonitrile and toluene with both aliphatic and aromatic amines. 2 could only gelate long chain alcohols in the presence of aliphatic amines. It was also found that the complexes with aliphatic amines, such as EDA and HDA, can gelate more kinds of solvents, especially in alcohol. In contrast, the complexes with aromatic amines such as NBDA and DAQ make compounds more soluble in most of the tested solvents. 1+DAQ has better gelation behavior in acetonitrile and ethanol, with critical gelation concentrations of 12.5 and 7.7 mg mL^{-1} , respectively.

The viscoelastic behaviour of gels of 1 with both aliphatic (1+HDA) and aromatic diamines (1+DQA) (1/amine = 2: 1, 25)mg mL^{-1} in ethanol) was studied by dynamic oscillatory measurements. The linear viscoelastic region (LVR), as a function of increasing amplitude of deformation due to shearing, was determined with strain amplitude in the range 0.005-1000% at an angular frequency of 6.28 rad s⁻¹ (Fig. 1a). The two gels show similar viscoelastic behaviour. The strength (storage modulus, G') of the gel is around 150 Pa with a small strain of 0.01%, which indicates that these gels were relatively weak compared to other gels in the field.¹⁰ With the small strain amplitudes, the storage modulus (G') is larger than the loss modulus (G'') in both gels, and G' and G'' remain nearly constant (LVR) up to approximately 0.3% and 2% strain, respectively. At larger strain amplitudes, the gels showed a catastrophic disruption accompanied by a step decrease in the values of both moduli, and the reversal of the viscoelastic signal (G' < G'') is 15% in 1+DAQ and 20% in 1+HDA. The implementation of a frequency sweep between 0.3 and 100 rad s^{-1} at a strain of 0.2% shows G' > G'' in both gels, which confirms that the gels have a predominantly elastic character (Fig. 1b). The elasticity of the gels was further evident from the facts that the G' and G'' values are minimally sensitive to frequency (ω), which indicated that the gel system formed a stable network structure.18

The network morphologies of the freeze-dried gels derived from gelators of compound **1** and **2** mixed with various amines in organic solvent were investigated by scanning electron microscopy (SEM) (Fig. 2). From the images, it can be seen that the architectures from gels of **1** with a variety of amines are similar in appearance. Those gels show ribbon structures with the width from 2–5 μ m (Fig. 2a–d). As for compound **2** with aliphatic amines, the morphologies show networks interweaved

Table 1	Gelation	ability	of 1	and	2	with	several	amines
---------	----------	---------	------	-----	---	------	---------	--------

	EDA		HDA		NBDA		DAQ	
Solvent	1	2	1	2	1	2	1	2
<i>n</i> -Octanol	G (10)	G (12.5)	G (5)	G (12.5)	S	S	S	S
<i>n</i> -Pentanol	G (10)	S	G (5)	G (25)	S	S	S	S
Methanol	G (9)	Р	G (5)	Р	G (10)	Р	G (10)	S
Ethanol	G (9)	Р	G (5)	Р	G (7.7)	S	G (7.7)	S
1,4-Dioxane	PG	G (14.3)	PG	S	S	S	S	S
DMSO	Р	S	S	S	S	S	S	S
Chloroform	S	S	S	S	Ι	Ι	S	Ι
Acetone	G (10)	Р	Р	Ι	S	Р	S	S
Cyclohexane	G (12)	Ι	G (7.7)	Ι	G (10)	Ι	G (12.5)	Ι
Acetonitrile	G (10)	Ι	G (5)	Ι	G (10)	G (10)	G (12.5)	Р
Ethyl acetate	PG	Р	PG	Р	S	G (25)	S	Р
Toluene	G (7.1)	G (12.5)	PG	Ι	Ι	G (12.5)	S	Р
1-Methyl-2-pyrrolidone	S	S	S	S	S	S	S	S
Tetrahydro-furan	S	S	PG	Р	S	S	S	S

 a G = gel; PG = partial gel; P = precipitation; S = solution; I = insoluble. Molar ratio of acid : amine = 2 : 1, concentration = 25 mg mL⁻¹. The critical gelation concentration is in parentheses (mg mL⁻¹). Gels were made by a heating-cooling process from 75 °C to 25 °C.



Fig. 1 Dynamic oscillatory data for gel 1+DAQ and 1+HDA (25 mg mL⁻¹ in ethanol) at 20 °C. (a) Strain sweep of the gels at a frequency of 6.28 rad s⁻¹. (b) Frequency sweep of the gel at a strain of 0.2%.



Fig. 2 SEM images of self-assembled complexes: (a) 1+EDA in ethanol, (b) 1+HDA in ethanol, (c) 1+NBDA in ethanol, (d) 1+DAQ in ethanol, (e) 2+EDA in octanol, (f) 2+HDA in octanol; scale bars for a, b, c, d, e and f are 20, 20, 20, 50, 5 and 10 μ m, respectively.

by fine flexible fibers with diameters smaller than 100 nm (Fig. 2e and f and Fig. S1 in the ESI[†]).

To investigate the interactions between **1** and amines, IR analysis of **1** and the complexes of **1**+EDA and **1**+DAQ was performed. As shown in Fig. 3, the characteristic peak of the

stretching vibration of C=O of 1 at around 1710 cm⁻¹ attributed to carboxylic acid drastically decreased and shifted to 1700 cm⁻¹ when interacted with EDA and DAQ in the gel formation (also see Fig. S2 in the ESI[†]). The stretching vibration of C–O of 1 at 1090 and 1020 cm⁻¹ was shifted to 1080 and 1030 cm⁻¹, which also suggested the strong interaction between carboxylic acid and amines. The disappearance of the strong vibration at 1600 cm⁻¹ of EDA (belonging to N–H bonds) and the appearance of the peak at 1608 cm⁻¹ in 1+EDA are attributable to the complex formation between –NH₂ of diamine and –COOH of 1. Moreover, the peaks of the stretching vibration of N–H at 3360 and 3280 cm⁻¹ almost vanished in 1+EDA gel, and the presence of multiple peaks in the range 3000–3100 cm⁻¹ strongly suggested the formation of ammonium ions. All these data were indicative of carboxylate salt formation between 1 and amines.

X-ray diffractions (XRD) can provide structural information for the self-assembly in the gel state. Here XRD patterns were recorded for powder of 1, DAQ and xerogel of the complex from ethanol (Fig. 4A). The molar ratio of 1 and diamines in the complex gelator is 2:1, just like all the above. The X-ray



Fig. 3 IR spectra of powder of 1, EDA and xerogel of 1+EDA formed in toluene (25 mg mL⁻¹).



Fig. 4 (A) XRD spectra of 1 (a), DAQ (b), and the xerogel of 1+DAQ (c). Numbers marked on the XRD peaks stand for values of distance (Å). (B) Proposed interaction mode of 1 and DAQ (left) and the supposed stacking method (right).

diffraction profile of the xerogel of the complex is quite different from those of the individual components 1 or DAQ, indicating the formation of the complex. The X-ray diffraction profile of the xerogel of 1 with aromatic amines showed a series of peaks at 24.35, 12.30, 8.43 Å for 1+DAQ, and 25.14, 12.58, 8.42 Å for 1+NBDA (Fig. S3 in ESI^{\dagger}), with a ratio of 1 : 1/2 : 1/3, characteristic of lamellar packing of the complexes. The distance of 24.35 Å for 1+DAQ is in agreement with the combined length of the molecules 1 (16 Å) and DAQ (9 Å). The dimensions of about 4.1 Å in the complexes may suggest π - π interactions. The existence of π - π stacking in 1+DAQ was also supported by spectral study discussed in the following part. The proposed aggregation mode of 1+DAQ is shown in Fig. 4B, in which the complexes of 1+DAQ are formed by acid-base interaction and then the complexes further aggregate into a layered structure. The X-ray diffraction in the gels of 1 with aliphatic amines, such as EDA and HDA, was much weaker and broader than that with aromatic amines, indicating the less ordered structure in those gels (Fig. S3[†]).

The spectroscopic study also supports the formation of π - π stacking between gelators. The maximum absorption and emission of compound 1 in CH₃CN (1 \times 10⁻⁵ M) is located at 360 nm and 429 nm, respectively (Fig. S4 in ESI†). The fluorescent quantum yield (φ) of **1** was 0.1366 using quinine sulfate as a reference. DAQ solution has an absorption band at 500 nm in the visible range and an emission band at 625 nm (φ = 0.0061). To investigate the fluorescence characteristics in the aggregated state, emission spectra of gels (25 mg mL^{-1}) and related sols (5 \times 10⁻⁴ M) were studied and are shown in Fig. 5a



Fig. 5 Emission and absorption spectra of the sols and gels of (a and c) 1+EDA in toluene and (b and d) 1+DAQ in acetonitrile. Insets are pictures of gels in 365 nm UV light (a and b) or in natural light (c and d). Molar ratio of acid : amine = 2:1, the concentration for sols are 5×10^{-4} M and for gels are 25 mg mL $^{-1}$

and b and S5 in ESI.† It is clear that all emission spectra have a red shift from sol to gel state. In the case of 1+EDA in toluene, the emission band of the naphthalimide group was modulated from 420 nm in sol to 478 nm in the gel, while for 1+DAQ in acetonitrile, this peak shifted from 421 to 434 nm. The weak emission band at 625 nm of 1+DAQ belongs to DAQ in the gel state, by comparison with pure DAQ solution (Fig. S4 in ESI†). A red shift of the absorption band from sol to gel state could also be observed as the absorption peak for the naphthalimide group shifted from 359 to 401 nm in 1+EDA and from 359 to 364 nm in 1+DAQ, respectively (Fig. 5c and d). This indicates that the π - π interaction between naphthalimide groups has a great contribution to the gel formation in complex gels.

Response to NO2⁻

Gel 1+DAQ was found to be sensitive to NO_2^- as we imagined (Fig. 6). The original colour of the two-component gel was red as shown in Fig. 6a due to the strong absorption of DAQ at 517 nm. With the addition of an aqueous solution of NaNO₂, the gel collapsed to a suspension and the colour of the gel gradually faded. Quantitatively, when 100 equiv. of NaNO2 aqueous solution was added to the top surface of the gel of 1+DAQ (25 mg mL⁻¹ in acetonitrile, molar ratio of **1** : DAQ = 2 : 1), in two hours which equals the average level of using DAQ to sense nitrite anions in the literature,19 the colour of the broken gel was completely faded with an obvious decrease of the absorption at 517 nm (Fig. 6b and d). What's more, the fluorescence emission of 1 at 434 nm quenched to 40% of its original intensity and fluorescence emission of the DAQ at 639 nm fell to nearly zero because of the existence of colourless triazole formed from the reaction of DAQ and NO₂⁻ (Fig. 6c and e). Results of LC-MS demonstrate this reaction. After reaction, the peak for DAQ (m/z= 239) in mass spectra was totally changed into benzotriazole (m/z = 249), but the peak for compound 1 (m/z = 474) was

View Article Online

Paper



Fig. 6 Photo of gel **1**+DAQ (25 mg mL^{-1} in acetonitrile) (a), and the gel with added NaNO₂ solution (left) and pure water (right) in natural light (b) and with 365 nm light irradiation (c). (d) Absorption and (e) emission spectra of gel **1**+DAQ before and after treatment with NO₂⁻. (f) The scheme of the reaction between DAQ and NO₂⁻.

unchanged (Fig. S6 in ESI[†]). The mechanism is shown in Fig. 6f. These facts indicate that the complex **1**+DAQ can serve as an indicator of NO_2^- that is visible to the naked eye. It should be pointed out that pure water or other solutions of salt can also destroy the gel, but the colour and emission characteristics would not be changed (Fig. 6b and c).

As for the practical application and recycling considerations, the quantitative change of detecting of gel 1+DAQ for both pure water and different concentrations of NO_2^{-} (0-200 eq. of DAQ) were checked. After reaction, the mixture consists of two parts: the liquid part (L) mainly including solvent, triazole product of DAQ or remaining DAQ, and the precipitation part mainly including 1 (P), as 1 could hardly dissolve in acetonitrile or water. The liquid part was taken out by a filter membrane and diluted with 4 mL THF solutions to make sure that the proportion stayed unchanged. The precipitation part was also dissolved in 4 mL of THF to see how much 1 remained that could be taken for reuse by means of absorption spectroscopy. As we observed from the absorption and emission spectra of the liquid part of the broken gel treated with nitrite (1+DAQ+-NaNO₂) (L) in Fig. 7, the gel mixture of 1+DAQ quickly faded after addition of 5 equiv. of NaNO₂ (40% of absorbance quenched), and gradually decreased after further addition of NaNO₂. The reaction was complete within two hours after 200 equiv. NaNO₂ (relative to DAQ) was added (98% of the absorbance quenched, Fig. 7a). Fig. 7b shows the absorbance change of 1+DAQ (liquid part) with the addition of different molar ratios of NaNO2, from which we can see that the 1+DAQ gel is very sensitive to NO₂⁻. Besides, because 1 hardly dissolved in the gelling solvent CH₃CN, it was easily recovered and reused. As shown in Fig. S7 in the ESI,† the comparison of the



Fig. 7 (a) UV-visible absorption spectra of the liquid part of gel 1+DAQ treated with pure water and different equiv. of NaNO₂ aqueous solution (cell: 1 mm); (b) the absorbance change at 520 nm with the addition of different molar ratios of NaNO₂. (c) The absorbance at 520 nm with the addition of different kinds of anions (100 equiv. of DAQ). Samples all diluted in THF.

absorbance at 359 nm belonging to **1** from the liquid part and the precipitation part of **1**+DAQ+NaNO₂ solution in THF shows that only 9% of **1** remains in the liquid part, which means the majority of **1** could be reused.

High-level selectivity is of paramount importance for an excellent chemosensor. In the present work, the common environmental salts such as NaF, NaHCO₃, Na₂SO₃ and Na₃PO₄ were checked with 1+DAQ by means of absorption spectroscopy. A gel of 1+DAQ (20 μ M) has little variation of absorption upon the addition of excess anions (100 equiv.) such as NaF, NaHCO₃, NaSO₃, Na₃PO₄ (Fig. 7c). This indicates a high selectivity of 1+DAQ towards NO₂⁻ compared with other anions.

Compared with the previous reported NO_2^- probes, the main advantages of this kind of two-component low molecular weight organogel are as follows: (1) it affords an easy way for sensing NO_2^- with obvious colour and emission change through selfassembly of an organic acid and DAQ; (2) additional HCl is not needed in the sensing process, as reported previously,⁶ because 1 provides necessary protons for the reaction between DAQ and NO_2^- ; (3) the two-component gel is decomposable and the part of the organic acid 1 could be recovered and used as a circulating material, showing that it is environmentally benign.

Conclusions

In conclusion, we made a kind of two-component low molecular weight organogel from naphthalene diimide undecanoic acid mixed with several aliphatic and aromatic diamines. The spectroscopic and morphological properties of the gels could be tuned by changing the associated amines. Besides, this conveniently prepared two-component gel containing diaminoan-thraquinone can be used as a new kind of probe for sensing NO_2^- in neutral environments. What's outstanding is that,

besides the colorimetric change, this gel state probe has a fluorescence emission response towards NO_2^- , which expands the field for more practical applications.²⁰ After sensing, the organic acid could be recycled. This two-component gel is thus an ideal platform for the design of supramolecular visual sensing systems with tuneable optical properties.

Acknowledgements

This work was supported by the National Basic Research Program of China (2013CB733700), the China National Funds for Distinguished Young Scientists (21125104), National Natural Science Foundation of China (91022021), Program for Innovative Research Team in University (IRT1117), Program of Shanghai Subject Chief Scientist (12XD1405900), and Shanghai Leading Academic Discipline Project (B108).

Notes and references

- 1 D. Forman, S. A. Al-Dabbagh and R. Doll, *Nature*, 1985, 313, 620–625.
- 2 J. O. Lundberg, E. Weitzberg, J. A. Cole and N. Benjamin, *Nat. Rev. Microbiol.*, 2004, 2, 593–602; R. Yue, Q. Lu and Y. Zhou, *Biosens. Bioelectron.*, 2011, 26, 4436–4441.
- 3 P. Mikuska and Z. Vecera, *Anal. Chim. Acta*, 2003, 495, 225–232; I. M. P. L. V. O. Ferreira and S. Silva, *Talanta*, 2008, 74, 1598–1602; J. C. Fanning, *Coord. Chem. Rev.*, 2000, 199, 159–179.
- 4 S. Girotti, E. N. Ferri, F. Fini, F. Ruffini, R. Budine, I. Moura, G. Almeida, C. Costa, J. J. G. Moura and G. Carrea, *Anal. Lett.*, 1999, **32**, 2217–2227.
- 5 V. Mani, A. P. Periasamy and S.-M. Chen, *Electrochem. Commun.*, 2012, 17, 75–78; P. Kalimuthu and S. A. John, *Electrochem. Commun.*, 2009, 11, 1065–1068.
- 6 T. Nagano and T. Yoshimura, *Chem. Rev.*, 2002, **102**, 1235–1270; O. B. Halbach, *Nitric Oxide*, 2003, **9**, 217–228.
- 7 M. I. Burguete, V. Fabregat, F. Galindo, M. A. Izquierdo and S. V. Luis, *Eur. Polym. J.*, 2009, **45**, 1516–1523.
- 8 P. Terech and R. G. Weiss, Chem. Rev., 1997, 97, 3133–3159;
 U. Beginn, Prog. Polym. Sci., 2003, 28, 1049–1105; T. Ishi-I and S. Shinkai, Top. Curr. Chem., 2005, 258, 119–160;
 T. Kato, N. Mizoshita, M. Moriyama and T. Kitamura, Top. Curr. Chem., 2005, 256, 219–236; N. M. Sangeetha and U. Maitra, Chem. Soc. Rev., 2005, 34, 821–836; S. Banerjee,
 R. K. Das and U. Maitra, J. Mater. Chem., 2009, 19, 6649–6687; L. E. Buerkle and S. J. Rowan, Chem. Soc. Rev., 2012, 41, 6089–6102; M. George and R. G. Weiss, Acc. Chem. Res., 2006, 39, 489–497; A. M. Jonker, D. W. P. M. Löik and J. C. M. van Hest, Chem. Mater., 2012, 24, 759–773;
 M. O. Piepenbrock, G. O. Lloyd, N. Clarke and J. W. Steed, Chem. Rev., 2010, 110, 1960–2004; N. M. Sangeetha and U. Maitra, Chem. Soc. Rev., 2005, 34, 821–836; R. G. Weiss, Langmuir, 2009, 25, 8369, and reviews in this special issue.
- 9 L. A. Estroff and A. D. Hamilton, *Chem. Rev.*, 2004, **104**, 1201–1217; J. H. van Esch and B. L. Feringa, *Angew. Chem., Int. Ed.*, 2000, **39**, 2263–2266; G. O. Lloyd and J. W. Steed, *Nat. Chem.*, 2009, **1**, 437–442; M. D. Segarra-Maset, V. J. Nebot, J. F. Miravet

and B. Escuder, *Chem. Soc. Rev.*, 2013, **42**(17), 7086; J. W. Steed, *Chem. Soc. Rev.*, 2010, **39**, 3686–3699; X. Yang, G. Zhang and D. Zhang, *J. Mater. Chem.*, 2012, **22**, 38–50.

- 10 L. A. Estroff, A. A. Lazarides, R. C. Mucic, C. A. Mirkin, R. L. Letsinger and G. C. Schatz, J. Am. Chem. Soc., 2000, 122, 4640-4650; Y. Negishi, Y. Takasuge, S. Sato, H. Yao, K. Kimura and T. Tsukuda, J. Am. Chem. Soc., 2004, 126, 6518-6519; M. Llusar and C. Sanchez, Chem. Mater., 2008, 20, 782-820; X. Ji, Y. Yao, J. Li, X. Yan and F. Huang, J. Am. Chem. Soc., 2013, 135, 74-77; S. Kawano, N. Fujita and S. Shinkai, J. Am. Chem. Soc., 2004, 126, 8592-8593; E. Krieg, E. Shirman, H. Weissman, E. Shimoni, S. G. Wolf, I. Pinkas and B. Rybtchinski, J. Am. Chem. Soc., 2009, 131, 14365-14373; J. Liu, Y. Feng, Z. X. Liu, Z. C. Yan, Y. M. He, C. Y. Liu and O. H. Fan, Chem.-Asian J., 2013, 8, 572-581; S. Samai and K. Biradha, Chem. Mater., 2012, 24, 1165-1173; T. Suzuki, S. Shinkai and K. Sada, Adv. Mater., 2006, 18, 1043-1046; A. Ajayaghosh and V. K. Praveen, Acc. Chem. Res., 2007, 40, 644-656; L. Y. You, S. G. Chen, X. Zhao, Y. Liu, W. X. Lan, Y. Zhang, H. J. Lu, C. Y. Cao and Z. T. Li, Angew. Chem., Int. Ed., 2012, 51, 1657-1661; Y. Zhou, T. Yi, T. Li, Z. Zhou, F. Li, W. Huang and C. Huang, Chem. Mater., 2006, 18, 2974-2981; Q. Wang, J. Wu, Z. Gong, Y. Zou, T. Yi and C. Huang, Soft Matter, 2010, 6, 2679-2684; M. Zhang, S. Sun, X. Yu, X. Cao, Y. Zou and T. Yi, Chem. Commun., 2010, 46, 3553-3555; M. Zhang, L. Meng, X. Cao, M. Jiang and T. Yi, Soft Matter, 2012, 8, 4495-4500.
- S. Li, V. T. John, G. C. Irvin, S. H. Bachakonda, G. L. McPherson and C. J. O'Connor, *J. Appl. Phys.*, 1999, **85**, 5965–5972; H. Maeda, Y. Haketa and T. Nakanishi, *J. Am. Chem. Soc.*, 2007, **129**, 13661–13674; H. Maeda, *Chem.-Eur. J.*, 2008, **14**, 11274–11282; Y.-M. Zhang, Q. Lin, T.-B. Wei, X.-P. Qin and Y. Li, *Chem. Commun.*, 2009, 6074– 6076; X. Cao, Y. Wu, K. Liu, X. Yu, B. Wu, H. Wu, Z. Gong and T. Yi, *J. Mater. Chem.*, 2012, **22**, 2650–2657; X. Yu, Q. Liu, X. Xu, H. Lan, X. Cao, L. Chen, B. Liu and T. Yi, *Acta Chim. Sin.*, 2012, **70**, 2016–2023.
- J. P. Luis, V. Laukhin, A. P. del Pino, J. Vida gancedo, C. Rovira, E. Laukhina and D. B. Amabilino, *Angew. Chem.*, *Int. Ed.*, 2007, 46, 238–241; W. Kubo, S. Kambe, S. Nakade, T. Kitamura, K. Hanabusa, Y. Wada and S. Yanagida, *J. Phys. Chem. B*, 2003, 107, 4374–4381; A. Ajayaghosh and V. K. Praveen, *Chem. Soc. Rev.*, 2008, 37, 109–122.
- C. Sanchez and M. Llusar, Chem. Mater., 2008, 20, 782–820;
 K. J. C. van Bommel, A. Friggeri and S. Shinkai, Angew. Chem., Int. Ed., 2003, 42, 980–999; A. Friggeri, K. J. C. van Bommel and S. Shinkai, in Molecular Gels, Springer, New York, 2006, pp. 857–893; A. M. Smith, R. J. Williams, C. Tang, P. Coppo, R. F. Collins, M. L. Turner, A. Saiani and R. V. Ulijn, Adv. Mater., 2008, 20, 37–41; S. Zhang, M. A. Greenfield, A. Mata, L. C. Palmer, R. Bitton, J. R. Mantei, C. Aparicio, M. O. de la Cruz and S. I. Stupp, Nat. Mater., 2010, 9, 594–601; S. S. Babu, S. Prasanthkumar and A. Ajayaghosh, Angew. Chem., Int. Ed., 2012, 51, 1766–1776.
- 14 D. J. Abdallah and R. G. Weiss, Adv. Mater., 2000, 12, 1237– 1247; O. Gronwald and S. Shinkai, Chem.-Eur. J., 2001, 7,

4328–4334; M. George and R. G. Weiss, *Acc. Chem. Res.*, 2006, **39**, 489–497; E. Carretti, L. Dei and R. G. Weiss, *Soft Matter*, 2005, **1**, 17–22.

- 15 J. F. Miravet and B. Escuder, Org. Lett., 2005, 7, 4791–4794;
 J. Wu, T. Yi, T. Shu, M. Yu, Z. Zhou, M. Xu, Y. Zhou,
 H. Zhang, J. Han, F. Li and C. Huang, Angew. Chem., Int. Ed., 2008, 47, 1063–1067; K. Liu, L. Meng, S. Mo,
 M. Zhang, Y. Mao, X. Cao, C. Huang and T. Yi, J. Mater. Chem. C, 2013, 1, 1753–1762; X. Xu, J. Zhang, X. Yu,
 L. Chen, D. Wang, T. Yi, F. Li and H. Yang, Chem.-Eur. J., 2012, 18, 16000–16013.
- 16 H. Basit, A. Pal, S. Sen and S. Bhattacharya, *Chem.-Eur. J.*, 2008, 14, 6534–6545; A. Pal, H. Basit, S. Sen, V. Aswal and S. Bhattacharya, *J. Mater. Chem.*, 2009, 19, 4325–4334.
- 17 T. Shu, J. Wu, M. Lu, L. Chen, T. Yi, F. Li and C. Huang, J. Mater. Chem., 2008, 18, 886-893; J. Wu, T. Yi, Q. Xia,

Y. Zou, F. Liu, H. Dong, T. Shu, F. Li and C. Huang, *Chem.-Eur. J.*, 2009, **15**, 6234-6243; X. Yu, Q. Liu, J. Wu, M. Zhang, X. Cao, S. Zhang, Q. Wang, L. Chen and T. Yi, *Chem.-Eur. J.*, 2010, **16**, 9099-9106.

- 18 M. Zhang, B. Wang, T. Jiang, M. Jiang and T. Yi, *CrystEngComm*, 2012, 14, 8057–8062; F. M. Menger and K. L. Caran, *J. Am. Chem. Soc.*, 2000, 122, 11679–11691.
- 19 M. Bru, M. I. Burguete, F. Galindo, S. V. Luis, M. J. Marín and L. Vigara, *Tetrahedron Lett.*, 2006, **47**, 1787–1791.
- 20 O. von Bohlen, Halbach, D. Albrecht, U. Heinemann and S. Schuchmann, *NeuroImage*, 2002, 15, 633–639; X. Chen, C. Sheng and X. Zheng, *Cell Biol. Int.*, 2001, 25, 593–598; J. J. Centelles, M. Fernández-Cancio and S. Imperial, *Anal. Lett.*, 2003, 36, 2139–2149; Y. Yan, S. Krishnakumar, H. Yu, S. Ramishetti, L. Deng, S. Wang, L. Huang and D. Huang, *J. Am. Chem. Soc.*, 2013, 135, 5312–5315.