

View Article Online View Journal

ChemComm

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: B. Escuder, J. F. Miravet, N. Singh, R. Ulijn and M. P. Conte, *Chem. Commun.*, 2015, DOI: 10.1039/C5CC04281J.



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/chemcomm

ChemComm

RSCPublishing

COMMUNICATION

Journal Name

Insight into the esterase like activity demonstrated by an imidazole appended self-assembling hydrogelator.

Cite this: DOI: 10.1039/x0xx00000x

Nishant Singh,^a Maria P. Conte,^b R. V. Ulijn,^{b,c*} Juan F. Miravet^{a*} and Beatriu Escuder^{a*}

Received 00th January 2012, Accepted 00th January 2012

DOI: 10.1039/x0xx00000x

www.rsc.org/

Published on 10 July 2015. Downloaded by University of Queensland on 11/07/2015 13:27:04.

A low molecular weight hydrogelator with covalently appended imidazole moiety is reported. Capable of percolating water in the pH range of 6 to 8, it proves to be an efficient catalyst upon self-assembly, showing Michaelis-Menten type kinetics. Activities at different pH correlated to dramatic structural changes observed. It can hydrolyse *p*nitrophenyl acetate (*p*NPA) as well as inactivated esters, *L* and *D*-phenylalanine methyl esters. The enhanced activity can be related to the conglomeration of catalytic groups upon aggregation resulting in their close proximity and the formation of hydrophobic pockets.

Mimicking and emulating enzymes by means of synthetic catalysts is currently an area of huge interest.¹Tertiary structure allows various functional groups to be precisely arranged in three-dimensional space, creating sites to bind substrates and positioning chemical functional groups to enable catalysis. Prediction and synthesis of enzyme performance from *de novo* designed primary sequence able to fold and function accordingly is currently not possible. However it is possible to attain enzyme like activity by using smaller selfassembling molecules or peptides owing to the ordered arrangement of the catalytically active sites/functional groups. Several groups have demonstrated esterase-like activity using metal based nanoparticles, micelles or dendrimers with large molecular weights and mostly with spherical symmetry.² Histidine-containing peptide nanofibrillar systems have been reported recently as catalysts for activated ester hydrolysis (2,4-dinitrophenyl acetate and pnitrophenyl acetate) and have revealed the role of the fibrillar

nanostructure and multivalency on the catalytic performance.³ In this communication we report low molecular weight hydrogelator (1) with covalently linked imidazole moieties demonstrating esterase like activity. The ordered arrangement of the catalytic centres upon self-assembly of molecules into a fibrillar network is taken advantage of to attain improved catalytic activity when compared to the non-aggregating analogue. In contrast to previously reported examples, 1 is a small synthetically simple compound that is able to hydrolyse not only activated but also non-activated aminoacyl esters.³



Scheme 1: Self-aggregating compound 1 and non-aggregating analogue 2.

Compound 1 with a minimum gel concentration of 5.7 mM was tested for the esterase like activity using pNPA as substrate. pNPA upon hydrolysis yields chromogenic *p*-nitrophenolate anion which can be monitored at 400nm using UV spectroscopy (see ESI for details). The initial parts of the kinetic curves for hydrolysis at different concentrations of substrate were fitted to Michaelis-Menten equation for respective pH values. The obtained K_M , k_{cat} and V_{max} values are presented in Table 1.

emComm Accepted Manusc

Table 1: Obtained K_M , k_{cat} and V_{max} values of hydrolysis of pNPA by1.



Fig. 1: (a) UV kinetic profile of pNPA (1.4 mM) hydrolysis at 400 nm catalysed by 0.17 Mm of compound 1 gel, compound 2 and background hydrolysis at pH 6.5. (b) k_{cat}/K_M values obtained by compound 1 at different pH values (black bars) and K_{sec} values for 2 (white bars, * not determined).

The calculated pKa values for aggregated compound 1 are 5.9 and 6.6, with monoprotonated species in abundance in this range (see Fig. S1). This drop in pKa value to 5.9 is only observed for the aggregated form of **1**, as in solution the pKa values are similar (6.2 and 6.3). This indicates the increase in basicity of one of the two imidazole moieties in molecule **1** only in the self-assembled state.

The catalytic efficiency (k_{cat}/K_M) for imidazole molecules in solution is known to drop significantly at lower pH values. ^{2a,3,4a} The higher amount of protonated imidazole moieties are held responsible for this which normally are not catalytically active. To our surprise for the pH 6 and 6.5 we don't observe this drop, infact a slight rise in the catalytic efficiency when compared to higher pH values like 7 and 7.5. This unusual catalytic efficiency around the pka values of selfassembling **1** suggests the involvement of both protonated and deprotonated imidazoles in the catalysis, often referred to as a cooperative mechanism in the prior art (Fig. S2c and d).^{2a,3,4a}

Well above the pK_a only the deprotonated imidazole residues are present and held responsible for the hydrolysis. The catalytic efficiency at pH 8 only due to the deprotonated imidazole groups is 7.37 M⁻¹s⁻¹. We know from the potentiometric titration curve that the mono-protonated imidazole is present in four-fold excess compared to the deprotonated imidazole at pH 6.5 (Fig. S1). According to these values, the extrapolated catalytic efficiency of the deprotonated imidazole at pH 6.5, assuming that the protonated imidazole is not active should be 1.65 M⁻¹s⁻¹ whereas that observed is 8.09 M⁻¹s⁻¹. Hence, based on these observations the catalytic efficiency at lower pH values 6 and 6.5, cannot simply be attributed to the contribution of the fraction of deprotonated imidazole. Instead, cooperativity between both protonated and deprotonated imidazole groups is likely responsible.

The solubility (K_{sol}) of compound **1** was obtained by NMR experiments for pH 6, pH 7 and pH 8 are 2.85 mM, 1.95 mM and 0.95 mM respectively (Fig. S4). The K_{sec} (second order rate constant) values observed at these pH respective non aggregating concentrations of compound **1**, were significantly lower than at the self-assembling concentration (Fig. S3). Thus, highlighting the fact that observed catalysis is not by the molecules in solution but due to the catalytically active fibers. This was further confirmed by the catalytic activity observed for the non-assembling analogue **2**. The K_{sec} for **2** at pH 6.5, pH 7 and pH 8 are 0.5 M⁻¹s⁻¹, 0.7 M⁻¹s⁻¹ and 2.2 M⁻¹s⁻¹ which are significantly lower than for **1** under identical conditions The obtained linear relationship between velocity of product formation and substrate concentration reflected lack of any binding events unlike **1** (Fig. 1a and S2b).



Fig.4 (a) Product formation upon hydrolysis of *L*-phenylanine methyl ester (12.3mM) by **1** (5.6mM) in the span of 80 hours as observed by HPLC. (b) Michaelis-Menten fitting at different concentrations for pH 7.

Owing to the fast hydrolysis trend shown by 1 we anticipated it to be capable of hydrolysing even stronger non activated ester linkages such as methyl esters. We chose *L* and *D*-phenyalanine methyl esters as our substrate and followed its hydrolysis by HPLC (see ESI for details). As expected, these substrates did not undergo any noticeable background hydrolysis at pH 7 whereas, with 33 mol% of 1 as catalyst, we could observe commendable hydrolysis rate of the methyl esters (Fig. 4a and S8). The calculated catalytic efficiency for the hydrolysis of *L* and *D*-phenyalanine methyl esters by 1 are

Published on 10 July 2015. Downloaded by University of Queensland on 11/07/2015 13:27:04

ChemComm

Journal Name

 $1.2 \times 10^{-3} \,\mathrm{M}^{-1} \mathrm{hr}^{-1}$ and $1.7 \times 10^{-3} \,\mathrm{M}^{-1} \mathrm{hr}^{-1}$ respectively. The Ksec (2.5×10⁻⁴ M⁻¹ hr⁻¹) for **2** is an order of magnitude smaller than for **1** exemplifying the aggregation effect, even though there doesn't seem to be any stereoselectivity shown by **1** (Fig. 4b). Thus, the hydrolysis of non-activated ester at the physiological pH, which to our knowledge has not been demonstrated before, reflects the fact that aggregation can lead to new emergent catalytic abilities even in small molecules owing to the high local concentration of the catalytic sites.



Fig.2: TEM images of gels at (a) pH 6 (scale bar: 50nm) (b) pH 6.5 (scale bar: 100nm (Inset: zoomed image of twisted fibre) (c) pH 7 (scale bar: 0.5µm) (d) pH 8 (scale bar: 0.5µm)

A series of experiments were performed to obtain the structure activity relationship. The nanoscale structures of the self-assembled networks of gels as observed by TEM differ depending on pH values (Fig. 2). TEM images reveal helical fibres of 15-20 nm width at pH 6 and 6.5. The higher V_{max} values for pNPA hydrolysis obtained at these pH values can be attributed to the observed high aspect ratio fibres, allowing higher extent of substrate binding thus releasing more product. At pH 7 and 8 the molecules aggregate in flat belt-like structures which are 0.5um wide and several micrometers long, with lower aspect ratio. The variation in morphologies based on pH can be attributed to the change in number of protonated imidazole residues. The repulsion between higher number of protonated imidazole present at pH 6 and 6.5 may result in stacking of molecules with higher slip angle between them; this gives rise to the twists observed in the nanofibers. This is not seen further away from the pKa by increasing the pH due to the significantly lower number of protonated imidazole residues.

The amide I' band in the 1630-1638 cm⁻¹ region of IR for different pH values denote the presence of β -sheet like structures, which is

also evident from the circular dichroism (CD) contours (Fig. 3(a) and S9). While moving from pH 8 to pH 6 an increase in ellipticity together with an apparent red-shift is observed in the CD spectra.^{5a,b,d}



Fig. 3: (a) CD spectra obtained for gels at different pH values and (b) fluorescence emission of ANS in gels and background at different pH values.

These kinds of spectral shifts to longer wavelengths are reported for twisted fibers having π - π * transitions with larger dipole moments which is expected to be the case in the protonated imidazole more than the deprotonated ones.^{5c} This information obtained from CD and IR are in agreement with the TEM images of the catalytic gels which switch from twisted helical fibers (pH 6 and 6.5) to flat belt like structures (pH 7 and 8).

In order to evaluate the presence of hydrophobic binding pockets, we probed the gels at different pH values with 1-anilinonaphthalene-8sulphonate(ANS), used extensively for this purpose in protein structure studies.⁶ When ANS was introduced in hydrogel 1, an apparent blue shift along with the rise in fluorescence was observed confirming the presence of hydrophobic pockets (Fig. 3(b)). These hydrophobic binding pockets could be formed by the central alkyl chain as well as by the L-valine isopropyl residues in 1. The molecular rigidity introduced by the two amide groups could be balanced by the flexibility of the alkyl spacer as well as the rotational freedom of the imidazole end fragments. Overall, a dynamic binding pocket could be confirmed in the vicinity of the catalytic fragment. It is also remarkable the effect of the L-valine residue as compound 2 lacking this amino acid fragment does not even aggregate under similar conditions. Moreover, the fluorescence intensity at pH 6 and 6.5 is higher and more blue shifted (472 nm for

suggesting stronger binding of the ANS and supporting the lower K_M values obtained for the pNPA hydrolysis at these pH values. In summary, the k_{cat} observed for pNPA hydrolysis shows little variation with pH, with the change in catalytic efficiency probably due to differences in substrate binding. Although the errors in K_M are significant, a clear trend is observed. This behaviour can be attributed to the difference in availability of binding pockets for each morphology. It is remarkable that a simple low molecular weight self-assembling compound bearing a minimal peptidic fragment is able to catalyse the hydrolysis of an activated ester as efficiently or even better than the few previously reported examples of longer selfassembled peptides.³ For instance, Stupp et al.^{3a}reported a rate constant of 1.67 x 10^{-2} s⁻¹ and a K_M of 0.4 mM for a bis-histidine containing decapeptide and a less efficient tetradecapeptide containing one histidine residue was described by Liang et al. $^{3c}(k_{cat})$ $0.19 \times 10^{-2} \text{ s}^{-1}$ and K_M 21.68 mM). The same group reported a shorter analogue (Fmoc-FFH-CONH₂) with lower reaction rate than in the case of compound 1 (k_{cat} 0.14 x 10⁻² s⁻¹) but with a stronger binding ability (K_M 0.76 mM).^{3b} Related results have been also reported by Korendovych et al. for amyloidogenic heptapeptides bearing H residues that after self-assembly are able to coordinate Zn⁺² and efficiently catalyse the hydrolysis of pNPA.^{3d} This example however follows a different catalytic mechanism based on metal ion Lewis-acid catalysis. All these examples highlight the undoubtable link between self-assembly and emergence of catalysis which is also exemplified by compound 1.

pH 6 and 474 nm for pH 6.5) than for the rest of the pH values,

Conclusions

Published on 10 July 2015. Downloaded by University of Queensland on 11/07/2015 13:27:04

In summary, we have reported an example of a catalytic supramolecular hydrogel in which binding and catalysis take place in reaction sites self-constructed solely with non-covalent interactions. We have been able to identify the probable structure-activity relationship between the different self-assembled structures and the subsequent catalytic performances of the gels. The results indicated that the presence of hydrophobic pockets, higher aspect ratio of fibres and the balance between the protonated and deprotonated imidazole can be the key factors for improved hydrolysis efficiency compared to related non-aggregating catalysts. It is remarkable the fact that enzyme-like catalytic behaviour emerges after selfassembly of small and simple molecular components. It is worth to mention that very simple low-molecular weight compounds can approach, although modestly by now, what evolution has achieved after millions of years. In fact, it has been proposed that short selfassembled peptides could have played a relevant role in the early stages of the origin of life.⁷ In this context, self-assembled catalytic peptides could have been potential precursors of enzymes.

Acknowledgments

This work was supported by the EU Marie Curie ITN-Smartnet and the Ministry of Economy and Competitiveness of Spain (Grant CTQ2012-37735). N.S. and M.P.C. thank EU for an ESR Marie Curie contract.

Notes and references

^aDepartament de Química Inorgànica i Orgànica, Universitat Jaume I, 12071 Castelló, Spain Fax: +34 964728214; Tel: +34 964729155; Email: miravet@uji.es, escuder@uji.es.

^bWestCHEM/Department of Pure & Applied Chemistry, University of Strathclyde, 295 Cathedral Street, Glasgow, G1 1XL, U.K.

^cAdvanced Science Research Center (ASRC) and Hunter College, City University of New York, 85 St Nicholas Terrace, New York NY10027, United States.

† Electronic Supplementary Information (ESI) available: experimental details on synthesis and characterisation of compounds and catalytic experiments. See DOI: 10.1039/c000000x/

References:

- (a) M. Raynal, P. Ballester, A. Vidal-Ferran and P. W. N. M. van Leeuwen, *Chem. Soc. Rev.*, 2014, **43**, 1660-1733.(b) M. Raynal, P. Ballester, A. Vidal-Ferran and P. W. N. M. van Leeuwen, *Chem. Soc. Rev.*, 2014, **43**,1734-1787.
- 2 (a) D. Zaramella, P. Scrimin and L. J. Prins, J. Am. Chem. Soc., 2012, 134, 8396-8399.(b) G. Pieters and L. J. Prins, New J. Chem., 2012, 36, 1931-1939. (c) G. Chadha and Y. Zhao, Org. Biomol. Chem., 2013,11,6849-6855.(d) G. Chadha and Y. Zhao, Chem. Commun., 2014, 50, 2718-2720.
- 3 (a) M. O. Guler and S. I. Stupp, J. Am. Chem. Soc., 2007, 129, 12082-12083.(b) Z. P. Huang, S. W. Guan, Y. G. Wang, G. N. Shi, L. N. Cao, Y. Z. Gao, Z. Y. Dong, J. Y. Xu, Q. Luo and J. Q. Liu, J. Mater. Chem. B, 2013, 1, 2297-2304. (c) C. Zhang, X. Xue, Q. Luo, Y. Li, K. Yang, X. Zhuang, Y. Jiang, J. Zhang, J. Liu, G. Zou and X.-J. Liang, ACS Nano 2014, 8, 11715-11723.(d) C. M. Rufo, Y. S. Moroz, O. V. Moroz, J. Stohr, T. A. Smith, X. Z.Hu, W. F. DeGrado and I. V. Korendovych, Nature Chem.2014, 6, 303-309.
- 4 (a) K. S. Broo, H. Nilsson, J. Nilsson, A. Flodberg and L. Baltzer, *J. Am. Chem. Soc.*, 1998, **120**, 4063-4068.(b)C. Guarise, F. Manea, G. Zuapa, L. Pasquato, L. J. Prins and P. Scrimin, *J. Pept. Sci.*, 2008, **121**, 174-184.
- 5 (a) B. A. Wallace, J. G. Lees, A. J. W. Orry, A. Lobley and R. W. Janes, *Prot. Sci.*, 2003, 12, 875-884.(b) E. T. Pashuck, H. Cui and S. I. Stupp, *J. Am. Chem. Soc.*, 2010, 132, 6041-6046.
 (c) U. Anand and M. Mukherjee, *Langmuir*, 2013, 29, 2713-2721 (d) S. M. Kelly and N. C. Price, *Current Protein and Peptide Science*, 2000, 1, 349-384.
- 6 (a) E. Schönbrumm, S. Eschenburg, K. Luger, W. Kabsch and N. Amrhein, *Proc. Natl. Acad. Sci. USA*, 2000, **97**, 6345-6349.
 (b) G. Chadha and Y. Zhao, *J. Coll. And Inter. Sci.*, 2013, **390**, 151-157.
- 7 O. Carny and E. Gazit, *FASEB J.*, 2005, **19**, 1051-1055.