

View Article Online View Journal

# **RSC Advances**

This article can be cited before page numbers have been issued, to do this please use: M. G. Mohamed, R. Lin, J. Tu, F. Lu, J. Hong, K. Jeong, C. Wang and S. Kuo, *RSC Adv.*, 2015, DOI: 10.1039/C5RA09409G.



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. This Accepted Manuscript will be replaced by the edited, formatted and paginated article as soon as this is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/advances

Published on 14 July 2015. Downloaded by California State University at Fresno on 15/07/2015 09:32:30.

# Thermal Property and Aggregation-Induced Emission Fluorophore That Forms Metal–Ligand Complexes with Zn(ClO<sub>4</sub>)<sub>2</sub> of Salicylaldehyde Azine–Functionalized Polybenzoxazine

Mohamed Gamal Mohamed,<sup>a</sup> Ruey-Chorng Lin,<sup>a</sup> Jia-Huei Tu,<sup>a</sup> Fang-Hsien Lu,<sup>a</sup> Jin-Long 5 Hong,<sup>a</sup> Kwang-Un Jeong,<sup>c</sup> Chih-Feng Wang,<sup>d</sup> and Shiao-Wei Kuo<sup>a,b,\*</sup>

Received (in XXX, XXX) Xth XXXXXXXX 200X, Accepted Xth XXXXXXXX 200X First published on the web Xth XXXXXXXX 200X DOI: 10.1039/b000000x

In this report, we designed a new and simple salicylaldehyde azine–functionalized benzoxazine (Azine-BZ) monomer via Mannich <sup>10</sup> condensation reaction of aniline and paraformaldehyde with 1,2-bis(2,4-dihydroxybenzylidene)hydrazine in 1,4-dioxane. Compared with 3-phenyl-3,4-dihydro-2*H*-benzooxazine monomer (263 °C), the maximum exothermic peak of Azine-BZ was shifted to a lower temperature (213 °C) based on differential scanning calorimetry (DSC) analyses because of the basicity of the phenolic group (OH) in the ortho position and the azine groups. Blending Azine-BZ with different weight ratios of zinc perchlorate [Zn(ClO<sub>4</sub>)<sub>2</sub>] to form benzoxazine/zinc ion complexes not only afflicted the thermal properties based on thermogravimetric analysis (TGA) due to physical <sup>15</sup> crosslinking through metal–ligand interactions, but also expedite ring-opening polymerization, decreasing the curing temperature from 213 to 184 °C (at 10 wt% Zn<sup>2+</sup>). Based on the fluorescence results, the Azine-BZ and AZine-BZ/Zn(ClO<sub>4</sub>)<sub>2</sub> complexes were nonemissive in THF solution. Their fluorescence increased gradually upon on the addition of water contents as poor solvent. Interestingly,

both the pure Azine-BZ and blending wotj  $Zn(ClO_4)_2$  still emitted light after thermal curing at 150 °C, as determined through photoluminescence measurements, indicating that the azine group could act as a probe of the curing behavior of the benzoxazine <sup>20</sup> monomer, as well as a fluorescent chemosensor for  $Zn^{2+}$  and, possibly, other transition metal ions through a metal–ligand charge transfer mechanism.

## Introduction

Benzoxazine monomer is a molecule where it contains on <sup>25</sup> an oxazine ring (a heterocyclic six-membered ring with oxygen and nitrogen atoms) is connected to a benzene ring. The last few decades, polybenzoxazine (PBZs) is a class of thermosetting resins which have been attracted widely due to their specific potential applications as phenolic resins <sup>30</sup> materials.<sup>1-3</sup> Polybenzoxazines (PBZs) produces from the thermal curing of oxazine ring in benzoxazine monomer without any catalyst, affording to highly dense cross-linked network materials with strongly intra and intermolecular hydrogen bonding between phenolic groups and tertiary amine

<sup>35</sup> in Mannich linkage after ring-opening polymerization.<sup>4</sup> Many literatures reported that the potential applications of polybenzoxazines in industrial field, due to their unique characteristics such as, flame resistance, low surface energies, high thermal and mechanical stabilities, and low water <sup>40</sup> adsorption.<sup>5,6</sup>

BZs are versatile thermoset resins synthesized through Mannich condensation between an aromatic phenol, a primary amine, and formaldehyde.<sup>7-12</sup> Nowadays, these phenolic resins can be used as thermoset to prepare polymer nanocomposites

<sup>45</sup> due to their unique excellent thermal properties.<sup>13-16</sup> The polybenozoxazine chemistry offers flexibility of many molecular designs, thereby facilitating the preparation of different PBZ nanocomposites. To control the properties of PBZs, several derivatives functionalized with reactive groups

<sup>50</sup> <sup>a</sup>Department of Materials and Optoelectronic Science, Centerfor Functional Polymers and Supramolecular Materials, National Sun Yat-Sen University, Kaohsiung, Taiwan E-mail: <u>kuosw@faculty.nsysu.edu.tw</u>

<sup>b</sup>Department of Medicinal and Applied Chemistry, Kaohsiung <sup>55</sup> Medical University, Kaohsiung, Taiwan.

<sup>c</sup>Department of Polymer-Nano Science and Technology, Chonbuk National University, Jeonju, Korea

<sup>d</sup>Department of Materials Science and Engineering, I-Shou University, Kaohsiung, Taiwan

- <sup>60</sup> (e.g., propargyl, nitrile, alkyl, carboxyl, hydroxyalkyl) have been synthesized.<sup>17-20</sup> Two types of BZ-based composites have been developed: fiber-reinforced PBZ composites and inorganic particle–reinforced PBZ composites (e.g., silica, TiO<sub>2</sub>, magnetic nanoparticles).<sup>21</sup>
- <sup>65</sup> Most fluorescing materials weaken the emissive properties, when they aggregated in a poor solvent or in the solid state. This phenomenon, known as aggregation-caused quenching (ACQ),<sup>22,23</sup> greatly decreased the applicability of such materials as organic light-emitting materials or fluorescent 70 chemosensors.<sup>24-26</sup> At the beginning of this century, Tang et al.
- <sup>70</sup> chemosensors. At the beginning of this century, rang et al. reported that many materials can be emitted light when dispersed in a poor solvent or fabricated into film in nanoaggregate state, these interesting phenomenon, namely as aggregation-induced emission (AIE) or aggregation-induced <sup>75</sup> enhanced emission (AIEE).<sup>27-28</sup> AIE fluorescent materials become very strongly emisters when aggregate or solid state, but become very strongly emisters when aggregate as powders or
- become very strongly emitters when aggregated as powders or nano-aggregates. There are many mechanisms behind AIE include restricted intramolecular rotation (RIR),<sup>29,30</sup> twisting <sup>80</sup> intramolecular charge transfer (TICT)<sup>31</sup> and planarity and rotation ability.<sup>32</sup> Tang et al. also reported that a series of salicylaldehyde azine derivatives exhibited AIE characteristics
- in good solvents, but displayed very weak emissions while being strongly luminescent in poor solvents.<sup>33</sup> Several <sup>85</sup> fluorescent chemosensors reported have been designed based
- on the mechanisms of photoinduced electron transfer (PET)<sup>34</sup>, fluorescence resonance intramolecular charge transfer (FRICT)<sup>35</sup>, and metal–ligand charge transfer (MLCT)<sup>36</sup>, respectively. Tain et al. reported that Schiff base–modified 90 triphenylaminobenzimidazole and pyridinecarboxaldehyde derivatives displaying AIEE characteristics acted as
- derivatives displaying AIEE characteristics acted as chemosensors for Cu(II) and Zn(II) ions.<sup>37</sup> As a result, in this article we synthesized a new BZ

As a result, in this article we synthesized a new BZ monomer containing a salicylaldehyde azine unit (Azine-BZ)

www.rsc.org/xxxxxxx 10.1XXXXXXXXXXX



Poly(Azine-BZ)

Poly(Azine-BZ)/Zn(ClO<sub>4</sub>)<sub>2</sub>

Scheme 1: Synthesis and chemical structures of (a) 2,4-dihydroxybenzaldehyde, (b) CN4OH, (c) Azine-BZ, (d, e) poly(Azine-BZ), and (f) the poly(Azine-BZ)/Zn(ClO<sub>4</sub>)<sub>2</sub> complex.

- <sup>5</sup> through facile and simple Mannich condensation reaction of 1,2-bis(2,4-dihydroxybenzylidene)hydrazine (CN4OH), paraformaldehyde, and aniline in the presence 1,4-dioxane as good solvent (Scheme 1). We also studied the thermal curing polymerization, thermal stabilities, the absorption and emission
   <sup>10</sup> behavior, specific metal-ligand interaction when Azine-BZ blended with various weight ratios of zinc perchlorate [Zn(ClO<sub>4</sub>)<sub>2</sub>], before and after thermal curing via chelation complexes by using differential scanning calorimetry (DSC),
- Fourier transform infrared (FTIR) spectroscopy, 15 thermogravimetric analysis (TGA), UV-Vis and photoluminescence (PL) spectroscopy. In addition, we used transmission electron microscopy (TEM) and dynamic light
- scattering (DLS) to characterize the self-assembled nanoaggregates morphology which formed from the Azine-BZ 20 monomer in THF/water solvent pairs.

#### Experimental Section Materials

Published on 14 July 2015. Downloaded by California State University at Fresno on 15/07/2015 09:32:30

Paraformaldehyde (96%), aniline, 2,4-Dihydroxybenzaldehyde <sup>25</sup> were used as received from Acros. Ethyl acetate (EA), hydrazine monohydrate (98%), chloroform, dichloromethane, ethanol, tetrahydrofuran (THF), and 1,4-dioxane were used as received from Scharlau. Zinc perchlorate hexahydrate [Zn(ClO<sub>4</sub>)<sub>2</sub>·6H<sub>2</sub>O] was purchased from Aldrich and dried

# Bis(2,4-dihydroxybenzylidene)hydrazine (CN4OH)<sup>33,38</sup>

30 overnight in a vacuum oven at 70 °C to remove water.

Under a N<sub>2</sub> atmosphere in a 150-mL two-neck round-bottom flask equipped with a stirrer bar, hydrazine monohydrate (0.900 <sup>35</sup> g, 18.1 mmol), 2,4-dihydroxybenzaldehyde (5.00 g, 36.2 mmol) were dissolved in absolute EtOH (100 mL) After stirring overnight at room temperature, the precipitate was filtered off and washed three times with EtOH. The yellow powder was recrystallized from a small amount of THF,

 <sup>40</sup> affording yellow crystals (8.50 g, 86%); FTIR (KBr, cm<sup>-1</sup>): 3200–3400 (OH stretching). <sup>1</sup>H NMR (500 MHz, DMSO-d<sub>6</sub>, δ, ppm): 11.94 (s, 1H, OH<sub>a</sub>), 10.10 (s, 1H, OH<sub>b</sub>), 8.75 (d, 2H, H<sub>c</sub>), 7.36 (t, 2H, H<sub>d</sub>), 7.04 (d, 1H, H<sub>e</sub>), 6.96 (t, 1H, H<sub>f</sub>). <sup>13</sup>C NMR (125 MHz, DMSO-d<sub>6</sub>, δ, ppm): 162.9, 162.6, 161.5, 133.6,
 <sup>45</sup> 110.8, 110.8, 108.8, 103.1. High resolution FT-MS (m/z) for MH<sup>+</sup> (C<sub>14</sub>H<sub>12</sub>N<sub>2</sub>O<sub>4</sub>): 273.09: calc.: 272.08 (Figure S2).

# Synthesis of Azine-BZ<sup>39</sup>

50 mL of 1,4-dioxane/ethanol, paraformaldehyde (0.882 g, 29.4 50 mmol), 1,2-bis(2,4-dihydroxybenzylidene)hydrazine CN4OH (2.00 g, 7.35 mmol), and aniline (1.37 g, 14.7 mmol) were

- mixed in a 150-mL two-neck round-bottom flask under a  $N_2$  atmosphere with a reflux condenser. The reaction solution was heated under reflux for 18 h at 90–110 °C. After that, cooling 55 the reaction mixture to room temperature, the solvent was
- evaporated under reduced pressure to give a yellow solid, which was purified through column chromatography (SiO<sub>2</sub>; EtOAc) to give a yellow solid (3.21 g, 87%). FTIR (KBr, cm<sup>-1</sup>): 3300–3200 (OH stretching), 931 and 1488 (vibrations of
- <sup>60</sup> trisubstituted benzene ring). <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>, δ, ppm): 11.93 (s, 1H, H<sub>a</sub>), 8.71 (s, 1H, H<sub>b</sub>), 4.70 (s, 2H, Ar-CH<sub>2</sub>. N), 5.33 (s, 2H, O-CH<sub>2</sub>.N), 6.92–8.43 (m, CH aromatic). <sup>13</sup>C NMR (125 MHz, CDCl<sub>3</sub>, δ, ppm): 45.93 (CCH<sub>2</sub>N), 80.04 (OCH<sub>2</sub>N). High resolution FT-MS (m/z) for MH<sup>+</sup> <sup>65</sup> (C<sub>14</sub>H<sub>12</sub>N<sub>2</sub>O<sub>4</sub>): 507.20: calc.: 506.20 (Figure S3).



Figure 1: <sup>1</sup>H NMR spectra of (a) CN4OH and (b) Azine-BZ



Figure 2: <sup>13</sup>C NMR spectra of (a) CN4OH and (b) Azine-BZ

#### Poly(Azine-BZ)/Zinc Complexes

- $Zn(ClO_4)_2$  (1, 2, 3, 4, 5, or 10 wt%) was dissolved in 5 mL of <sup>10</sup> THF 1 h. Then,  $Zn(ClO_4)_2$  solutions were added dropwise to Azine-Bz solutions. After that, the Azine-Bz/Zn(ClO<sub>4</sub>)<sub>2</sub> complexes solutions were stirred for 2 days, the removal of solvent under reduced pressure. Each blended mixture was poured into a stainless- mold and polymerized in a stepwise 15 manner, with heating at 110, 150, 180, 210, and 240 °C for 2 h
- at each temperature. The color of each cured sample was dark red.

#### Nanoaggregates of Azine-BZ and Azine-BZ/Zinc 20 Complexes

Stock solutions of Azine-BZ and Azine-BZ/Zinc were prepared in THF at 100-mL volumetric flask with concentrations of 1 × 10<sup>-4</sup> M. Then, water (poor solvent) was added dropwise under vigorous stirring to prepare different volume ratios (0-90%)

25 was reached. PL spectra of the suspension of nano-aggregates were recorded immediately.

#### Characterization

Nuclear magnetic resonance (<sup>1</sup>H and <sup>13</sup>C NMR) spectra were 30 recorded on an INOVA 500 by using DMSO-d<sub>6</sub> and CDCl<sub>3</sub> as solvents. Fourier transform infrared (FTIR) spectra of the KBr disks of CN4OH and Azine-BZ were measured by a Bruker Tensor 27 FTIR spectrophotometer and thirty-two scans were

collected at a spectral resolution of 4 cm<sup>-1</sup>. Differential 35 scanning calorimeter (DSC) measurements were conducted with TA Q-20 with operated under a N2 as purge gas (50 mL/min) at heating rate of 20 °C/min. The sample (ca. 3-5 mg) was placed in a sealed aluminum sample pan. Dynamic curing scans were recorded from 30 to 350 °C at a heating rate of 20 <sup>40</sup> °C min<sup>-1</sup>. The thermal stabilities of the samples were measured using a TA O-50 thermogravimetric analyzer operated under a N<sub>2</sub> as purge gas (60 mL/min) at heating rate of 20 °C/min from 30 to 800 °C under UV-Vis spectra were recorded using a Shimadzu mini 1240 spectrophotometer; the concentration of <sup>45</sup> Azine-BZ in THF was 10<sup>-4</sup> M. Photoluminescence spectra was collected at room temperature using a monochromatized Xe light source. Particle sizes of the aggregates in solution were measured by DLS using a Brookhaven 90 plus spectrometer equipped with a temperature controller. Argon into laser 50 operating at 658 nm was used as the light source. TEM images were recorded using a JEOL-2100 transmission electron microscope operated at an accelerating voltage of 200 kV. The molecular weights of CN4OH and Azine-BZ were recorded using a Bruker Solarix high resolution Fourier Transform Mass 55 spectroscopy system FT-MS (Bruker, Bremen, Germany).

# **Results and Discussion**

## Synthesis and Characterization of CN4OH and Azine-BZ

- Scheme 1 displays our synthesis of the salicyaldehyde azine-60 functionalized BZ monomer (Azine-BZ). First, we employed a Schiff base condensation of 2,4-dihydroxybenzaldehyde with hydrazine monohydrate in EtOH to obtain CN4OH; we then prepared Azine-BZ with high purity more than 95% in through Mannich condensation reaction of CN4OH а 65 paraformaldehvde, and aniline in 1.4-dioxane at 80-90 °C. We carefully confirmed the chemical structures of CN4OH and Azine-BZ via <sup>1</sup>H NMR, <sup>13</sup>C NMR, and FTIR spectroscopy. Figure 1 illustrated the <sup>1</sup>H NMR spectra of CN4OH and Azine-
- BZ. The spectrum of CN4OH [Figure 1(a)] features signals at 70 10.10 and 11.94 ppm, representing the OH groups of the phenolic units, as well as signals in the range 6.33-7.40 ppm for the aromatic protons and at 8.69 ppm for the N=CH groups. The spectrum of the AIE unit (azine)-based BZ monomer [Figure 1(b)] lacked the peak at 10.10 ppm for the OH<sub>b</sub> proton
- 75 of CN4OH, but featured peaks at 6.36-7.26 ppm for the aromatic protons and resonances at 4.70 (ArCH<sub>2</sub>N) and 5.33 (OCH<sub>2</sub>N) ppm at a 1:1 ratio; no signal was present near 4.0 ppm, corresponding to an NCH<sub>2</sub>Ph unit, as a result of ring opening of the BZ moiety; no other major peaks were evident
- <sup>80</sup> in the <sup>1</sup>H NMR spectrum, indicating that Azine-BZ had successfully formed. Figure 2 presents the <sup>13</sup>C NMR spectra of CN4OH and Azine-BZ. The spectrum of CN4OH [Figure 2(a)] features signals for the carbon nuclei in the aromatic rings and double bonds in the range 103.77-163.27 ppm. The spectrum
- 85 of Azine-BZ [Figure 2(b)] displays characteristic resonances for the ArCH<sub>2</sub>N and OCH<sub>2</sub>N units of the oxazine ring at 45.93 and 80.05 ppm, respectively. Figure S1 presents the FTIR spectra of CN4OH and Azine-BZ, recorded at room temperature. The spectrum of CN4OH [Figure S1(a)] features
- <sub>90</sub> three sharp peaks at 3217, 3481, and 3522  $\text{cm}^{-1}$  for the intra and intermolecular hydrogen-bonded and free OH groups, and sharp signals for the aromatic rings at 831, 1599, 1619, and 3033 cm<sup>-1</sup>. The spectrum of Azine-BZ [Figure S1(b)] features characteristic absorption bands at 1366 (tetrasubstituted
- 95 benzene ring), 1225 (asymmetric COC stretching), 1042 (symmetric COC stretching), and 931 (stretching vibrations of oxazine ring) cm<sup>-1</sup>.

**RSC Advances Accepted Manuscrip** 



Figure 3: (A, B) PL spectral changes of (A) CN4OH and (B) Azine-BZ ( $1.0 \times 10^{-4}$  mol L<sup>-1</sup>) and (C) PL intensity of Azine-BZ in THF/water mixtures at various water fractions.



**Figure 4:** (a) Particle size distributions of Azine-BZ in THF/water mixtures at water fractions of 50, 80, and 90%. (b, c) TEM images of Azine-BZ at a concentration of  $1.0 \times 10^{-4}$  mol L<sup>-1</sup> in THF/water mixtures at ratios of (b) 20:80 and (c) 10 10:90 (v/v)

High resolution FT-MS displayed the exactly molecular weights of CN4OH and Azine-BZ, respectively (supporting information Figure S2 and S3). Combined these spectral data are consistent with the successful synthesis of a new Azine-BZ <sup>15</sup> monomer.

WWW.rsc.org/xxxx00k 10.1XXXXXXXXXXXX

#### **Optical Properties and AIE of CN4OH and Azine-BZ**

The UV-Vis absorption spectrum of Azine-BZ monomer in THF (1  $\times$  10<sup>-4</sup> M) features (Figure S4) an absorption peak at 20 370 nm that we attribute to the  $\pi$ - $\pi$ \* transition of the salicylaldehyde azine unit. Most reported salicylaldehyde azine are fluorescent AIE materials and it can emit different light in their aggregated states, presumably because of RIR and excited state intramolecular proton transfer [ESIPT].33,38 We 25 investigated the AIE phenomena of CN4OH and Azine-BZ in THF/H<sub>2</sub>O mixtures at water contents in the range 0-90%. CN4OH and Azine-BZ are both soluble in common organic solvents (THF, DMSO, DMF), but insoluble in water and hexane. As expected, solutions of CN4OH and Azine-BZ in 30 THF are virtually non-luminescent, as determined from their fluorescence spectra [Figures 3(A) and 3(B)]. The fluorescence intensities increased gradually, however, when the water content was greater than 80% for CN4OH and 90% for Azine-BZ [Figure 3(C)], with the emissions of CN4OH and Azine-BZ 35 turning on and displaying green fluorescence. These emissions from CN4OH and Azine-BZ were presumably induced through aggregate formation, suggesting that both CN4OH and Azine-BZ exhibit AIE. In addition, we found that Azine-BZ could form nanoparticles in solution; we used transmission electron



Figure 5: (A) DSC profile and (B) FTIR spectra of Azine-BZ monomer recorded after thermal treatments



 $_{\rm 5}$  Figure 6: Thermogravimetric analyses of Azine-BZ monomer, recorded after thermal polymerization at 110, 150, 180, 210 and 240  $^{\circ}{\rm C}$ 

investigate the growth of these nano-aggregates at high water 10 contents 90% (Figure 4). The TEM images in Figures 4(b) and 4(c) reveal nano-aggregates having sizes of approximately 100–200 nm, consistent with the DLS data. The particle sizes decreased upon increasing the water content, reaching approximately 215 nm when the water content was 90 wt% 15 [Figure 4(a)]. The particle sizes determined from the TEM images were smaller than those measured using DLS, because evaporation was necessary to prepare the samples for TEM, unavoidably leading to collapse and shrinkage of the particles. We suspect that CN4OH and Azine-BZ emitted intensely in their aggregated states because the large amount of water leads to form spherical nano-aggregated structures thereby restricted intramolecular rotation of the phenyl rings rotors of CN4OH and Azine-BZ.

#### 25 Thermal Curing and AIE of Azine-BZ

Differential scanning calorimetry (DSC) is a convenient and simple method to understand and investigate the study the thermal curing and ring-opening polymerization of the Azine-BZ monomer. The DSC thermograms of the pure Azine-BZ <sup>30</sup> monomer, recorded at a heating rate of 20 °C min<sup>-1</sup> from 20 to 350 °C, reveal [Figure 5(A)] an exothermic peak with the curing temperature at 213 °C and a reaction heat of 262 J  $g^{-1}$ . Based on DSC profile the polymerization exotherm maximum temperature for Azine-BZ (213 °C) was lower than that (263 35 °C) for conventional 3-phenyl-3,4-dihydro-2H-benzooxazine (Pa-type)<sup>1</sup>, presumably because the basic azine group in the backbone structure catalyzed the ring-opening polymerization. Clearly, after thermal treatment at 180 and 240 °C for 2 h at each temperature of Azine-BZ, the maximum exothermic peak 40 completely disappeared which indicating the completion of ring-opening polymerization of Azine-BZ. We also studied the thermal polymerization of Azine-BZ at elevated temperatures in Figure 5(B). As shown in Figure 5(B) displays that the

RSC Advances Accepted Manuscript

ARTICLE TYPE

www.rsc.org/xxxxxxx 10.1XXXXXXXXXXXX



Figure 7: PL spectra of Azine-BZ monomer in the bulk state, recorded after each curing stage



**Figure 8:** (a) DSC scan and (b) PL intensity of pure Azine-BZ monomer after each thermal curing stag

- intensities of the characteristic absorption bands of <sup>10</sup> antisymmetric COC and out-of-plane of benzene mode with attached to benzene ring gradually disappeared after thermal curing at 180 °C, corresponding to ring-opening of benzoxazine monomer and formation of Poly(Azine-BZ). In addition, a new absorption signal appearing at 3433 cm<sup>-1</sup>, was corresponding to <sup>15</sup> the released OH group, consistent with the DSC analyses.
- Thermal stability of Azine-BZ has been investigated by thermogravimetric analysis as shown in Figure 6 after various thermal treatments. Our TGA analysis revealed (Figure 6) that the initial thermal decomposition temperature ( $T_{d5}$ ) was <sup>20</sup> strongly dependent on the curing exothermic peak in the DSC analysis [Figure 5(A)]. For example, the initial thermal decomposition temperatures were near 215 and 233 °C when the curing temperatures were 110 and 150 °C, respectively; these values are close to the curing exothermic peaks in the <sup>25</sup> DSC analyses in Figure 5(A). In addition, the value of  $T_{d5}$  and
- the char yield both increased upon increasing the curing temperature. When the curing temperature was 240 °C, the value of  $T_{d5}$  increased significantly to 340 °C and the char yield was approximately 55 wt%. This char yield is higher than that
- <sup>30</sup> of conventional 3-phenyl-3,4-dihydro-2*H*-benzooxazine (ca. 48 wt%) at 700 °C, indicating a more highly cross-linked structure arising from the presence of the azine groups, as well as from



<sup>35</sup> **Figure 9:** DSC thermograms of Azine-BZ in the presence of various weight ratios of Zn(ClO<sub>4</sub>)

intramolecular hydrogen bonding involving the azine groups [Scheme 1(d)]. Figure 7 presents the PL spectra of pure Azine-40 BZ recorded after thermal curing at various temperatures. The maximum intensity emission of the uncured Azine-BZ was higher than those after curing. Interestingly, Azine-BZ still emitted light after curing at 150 °C. The <sup>1</sup>H NMR spectrum of Azine-BZ after thermal curing at 150 °C indicated that ring-<sup>45</sup> opening polymerization had not occurred: the two peaks at 4.70 and 5.33 ppm representing the oxazine ring were still present [Figure S5(b)]. The emission was quenched after curing at 180, 210, and 240 °C. As a result, the emission from the azine could also be used as a probe of the extent of curing of the BZ 50 monomer. Figure 8 summarizes the PL intensity of pure Azine-BZ after each curing and DSC thermal scan. The emission intensity was quenched after curing at 180 °C [Figure 8(b)], consistent with the initial thermal curing based on DSC analysis [Figure 8(a)]. In addition, the characteristic absorption 55 bands at 923 cm<sup>-1</sup> disappeared completely after curing at 180 °C [Figure 5(B)]. To the best of our knowledge, this report provides the first example of emission behavior being used to monitor curing behavior in a manner consistent with DSC and FTIR spectroscopic data.

# <sup>60</sup> AIE Phenomena and Thermal Polymerization of Azine-BZ/Zn(ClO<sub>4</sub>)<sub>2</sub> Complexes

The thermal uncuring behavior of Azine-BZ/Zn(ClO<sub>4</sub>)<sub>2</sub> complexes was investigated using DSC and FTIR, respectively. <sup>65</sup> Figure 9 reveals that the thermal curing peaks shifted to lower temperature upon increasing the Zn(ClO<sub>4</sub>)<sub>2</sub> content, decreasing from 213 °C initially to 184 °C in the presence of 10 wt% Zn(ClO<sub>4</sub>)<sub>2</sub>, suggesting that the Zn<sup>2+</sup> ions enhanced the ring opening process.<sup>39,41</sup> FTIR analyses was carried out to

To investigate the specific interaction (metal-ligand interaction) of Azine-BZ after blended with various  $Zn(ClO_4)_2$  contents at ambient temperature and the spectra displayed in Figure 10. Analysis of these spectra suggests that the shifts observed in the absorption peaks of the polymer structures were caused by

<sup>75</sup> specific ion–dipole interactions. Concentrating on the azine band at 1632 cm<sup>-1</sup>, we assign the new band at 1664 cm<sup>-1</sup> that appeared at 5 or 10 wt% Zn(ClO<sub>4</sub>)<sub>2</sub> to the azine groups coordinating as  $\pi$ -bonding ligands to zinc cations (inset to Figure 10). Therefore, the higher energy of this new absorption

<sup>&</sup>lt;sup>80</sup> was the result of formation of such a metal-ligand complex.

#### Page 7 of 11

Published on 14 July 2015. Downloaded by California State University at Fresno on 15/07/2015 09:32:30.

CREATED USING THE RSC ARTICLE TEMPLATE (VER. 3.1) -SEE WWW.RSC.ORG/ELECTRONICFILES FOR DETAILS

ARTICLE TYPE



Figure 10: FTIR spectra of Azine-BZ in the presence of various amounts of Zn(ClO<sub>4</sub>)<sub>2</sub>, recorded at ambient temperature



5 Figure 11: (A) DSC thermograms and (B) FTIR spectra of Azine-BZ monomer in the presence of 5 wt% Zn(ClO<sub>4</sub>)<sub>2</sub>, recorded after each curing stage

**RSC Advances Accepted Manuscrip** 

WWW.rsc.org/xxxx00k 10.1XXXXXXXXXXXX



Scheme 2: (Left) Possible model of a poly(Azine-BZ)/ $Zn(ClO_4)_2$  complex. (Right) Possible modes of metal-ligand complexes between  $Zn(ClO_4)_2$  and poly(Azine-BZ).



Figure 12: PL spectra of Azine-BZ blended with a various weight ratios of  $Zn(ClO_4)_2$  in the bulk state, recorded at room temperature.

- <sup>10</sup> In addition, the thermal polymerization of Azine-BZ/5 wt%  $Zn(ClO_4)_2$  complex was studied by DSC measurement. As revealed in Figure 11(A), the enthalpy of the curing exotherm decreased gradually upon increasing the temperature of the curing process, reaching zero at a curing temperature of 180
- <sup>15</sup> °C. Figure 11(B) presents corresponding FTIR spectra recorded after thermal curing of the 5 wt% Zn(ClO<sub>4</sub>)<sub>2</sub> blend at various temperatures. The characteristic absorption bands of the ozaxine units at 1223 and 931 cm<sup>-1</sup> disappeared after thermal curing at temperatures from 180 to 240 °C. Much literature <sup>20</sup> reported there are many catalysts (e.g. Li<sup>+</sup>, Fe<sup>+3</sup>...) can act as
- 20 reported mere are many catalysts (e.g. L1, Fe<sup>-1</sup>...) can act as effective promotors and accelerating for ring-opening polymerization of benzoxazine. The mechanism of ringopening polymerization of benzoxazines using catalyst is divided into three steps; coordination-ring opening, 25 electrophilic attack and finally rearrangement affording to



**Figure 13:** (A) PL spectral changes and (B) PL intensities of Azine-BZ blended with 3 wt%  $Zn(ClO_4)_2$  (1.0 × 10<sup>-4</sup> mol L<sup>-1</sup>) in THF/water mixtures at various water fractions.

- phenolic and phenoxy structure.<sup>42</sup> We suspect that the  $Zn^{2+}$  ions coordinated effectively to the O and/or N atoms during ring opening of the BZ units; Scheme 2 presents some possible structures.
- <sup>35</sup> As mentioned above, the salicylaldehyde azine derivatives exhibit AIE features and emit light in their aggregated state because of restricted rotation of their N–N single bonds; in addition, salicylaldehyde azines bearing ortho OH groups on their phenyl rings can undergo intramolecular hydrogen
- <sup>40</sup> bonding, which could lead to excited state intramolecular proton transfer (ESIPT). <sup>33,43</sup> Azine-BZ exhibits weak emission in solution because of intramolecular hydrogen bonding between the phenolic OH group and the N atom of the imino group that undergoes ESIPT phenomena. We were also
- <sup>45</sup> interested in examining the AIE-active behavior of Azine-BZ when blended with  $Zn(ClO_4)_2$ . Figure 12 presents the PL spectra of Azine-BZ in the presence of various amounts of  $Zn(ClO_4)_2$  in the bulk state. Interestingly, the PL intensities



**Figure 14:** PL spectra of Azine-BZ blended with 3 wt%  $Zn(ClO_4)_2$  in the bulk state, recorded at room temperature after each thermal curing stage



**Figure 15:** TGA analyses of Azine-BZ blended with various amounts of  $Zn(ClO_4)_2$ , recorded after thermal curing at 210 °C

- <sup>10</sup> when the contents of zinc ions were 1, 2, 3, and 4 wt% were higher than that of pure Azine-BZ, due to the Zn<sup>2+</sup> ion having closed-shell *d*-orbitals; thus, the energy transfer process could not occur, leading to enhance metal–ligand charge transfer (MLCT),<sup>36,37</sup> as depicted in Scheme 2. In contrast, the PL
   <sup>15</sup> intensity decreased when content of Zn<sup>2+</sup> ions was 5 or 10 wt%, presumably because the Zn<sup>2+</sup> ions coordinated to the azine units as displayed in Figure 10, changing the mechanism of the MLCT. To further study the optical properties of the aggregated Azine-BZ/3 wt% Zn<sup>2+</sup> ion complex, we examined
- aggregated time in THF in the presence of a poor solvent (water). As revealed in Figure 13, Azine-BZ in the presence of 3 wt%  $Zn^{2+}$  ions in pure THF displayed a non-emissive PL intensity, with the PL intensity increasing upon addition of water up to a fraction of 90%—characteristic AIE behavior.
- <sup>25</sup> Figure 14 presents PL spectra of the Azine-BZ/3 wt% Zn(ClO<sub>4</sub>)<sub>2</sub> complex after thermal curing at various temperatures. The PL intensity of this complex was higher than that of pure Azine-BZ prior to curing, consistent with MLCT. Upon increasing the curing temperature, the PL intensity
- <sup>30</sup> decreased gradually until quenching completely at curing temperatures from 180 to 240 °C, similar to the behavior of the pure Azine-BZ monomer.

Figure 15 presents the thermal stability of Azine-BZ blended with various contents of Zn(ClO<sub>4</sub>)<sub>2</sub> after thermal <sup>35</sup> curing at 210 °C under N<sub>2</sub> at heating rate 20 °C/min, as investigated using TGA. As expected, the thermal decomposition temperature and char yield both increased upon increasing the Zn(ClO<sub>4</sub>)<sub>2</sub> content. we found that the decomposition temperature value (Td<sub>5</sub>) and char yield for the <sup>40</sup> Azine-BZ/5 wt% Zn<sup>2+</sup> complex was higher (350 °C, 61 wt%) than that for pure Azine-BZ (312 °C, 48 wt%), because the Zn<sup>2+</sup> ions increased the degree of crosslinking (inset to Figure 15), in addition to the crosslinking through intra- and intermolecular hydrogen bonding, after ring opening.

#### Conclusions

A new Azine-based BZ monomer has been designed and that exhibits aggregation induced emission (AIE) behavior. DSC <sup>50</sup> analysis revealed that the exothermic peak for the ring opening polymerization of Azine-BZ shifted to lower temperature, compare to that for a standard BZ, because the basicity of the phenolic unit facilitated the ring opening process. Furthermore, the azine unit in the BZ monomer has high affinity for Zn<sup>2+</sup>

- <sup>55</sup> ions, not only promoting ring opening polymerization at a lower curing temperature (from 213 °C in the absence of the Zn<sup>2+</sup> ions to 184 °C in their presence). Based on thermogravametric results, the improving of thermal stability of Azine-BZ/Zn(ClO<sub>4</sub>)<sub>2</sub> complexes, due to the presence of strong
- <sup>60</sup> polymer-metal complexes. Azine-BZ coordinated with  $[Zn(ClO_4)_2]$  through metal–ligand interactions, increasing the fluorescence emission intensity relative to that of the pure Azine-BZ monomer as a result of MLCT. The PL properties of the azine units and the metal–ligand complexes mode suggest
- 65 that such monomers might be act as probes for realizing the thermal curing behavior of BZ rings; as fluorescent chemosensors for Zn<sup>2+</sup> and other transition metal ions, even at high curing temperatures (e.g., 150 °C); and as components within polymer/inorganic hybrid materials.

#### Acknowledgment

This study was supported financially by the Ministry of Science and Technology, Taiwan, Republic of China, under contracts MOST103-2221-E-110-079-MY3 and MOST102-

75 2221-E-110-008-MY3. We thank Mr. Hsien-Tsan Lin of the Regional Instruments Center at National Sun Yat-Sen University for help with the TEM experiments.

**Electronic Supplementary Information (ESI) Available:** <sup>80</sup> FTIR, UV, MS, and <sup>1</sup>H NMR spectra of pure Azine-BZ.

#### References

- (1) H. Ishida, "Handbook of Polybenzoxazine", ed. Ishida, H. and Agag, T., Elsevier, Amsterdam 2011, ch. 1, p. 1.
- 85 (2) N. Ghosh. B. Kiskan and Y. Yagci , Prog. Polym. Sci., 2007, **32**:1344-1391.
  - (3) Y. Yagci Y, B. Kiskan and N.N. Ghosh, J. Polym. Sci. Part A: Polym. Chem., 2009, 47, 5565-5576.
- (4) (a) T. Takeichi and T. Agag, *High Perform. Polym.*, 2006, **18**, 777-797. (b) Y. X. Wang and H. Ishida, *Polymer*,
- 10, 777-777. (6) 1. X. Wang and H. Ishida, *Polymer*, 1999, 40, 4563-4570. (c) M. Zhang, Z. Tan, S. Hu, J. Qiu and C. Liu, *RSC. Adv.*, 2104, 4, 44234-44243.
- (5) (a) H. Ishida and Y. H. Lee, *Polym. Polym. Compos.*, 2011, 9, 121-134. (b) H. D. Kim and H. Ishida, *J. Phys.*
- <sup>95</sup> Chem. A., 2002, **106**, 3271-3280. (c) H. D. Kim and H. Ishida, *Macromol. Symp.*, 2003, **195**, 123-140. (d) S. W. Kuo, Y. C. Wu, C. F. Wang and K. U. Jeong, *J. Phys.*

Chem. C., 2009, 13, 20666-20673. (e) C. F. Wang, S. F. Chiou, F. H. Ko, J. K. Chen, C. T. Chou, C. F. Huang, S. W. Kuo and F. C. Chang, *Langmuir.*, 2007, 23, 5868-5871.
(f) W. H. Hu, K. W. Huang, and S. W. Kuo, *Polym. Chem.*, 2012, 3, 1546-1554.

- (6) (a) Q. Li, and X. Zhong, *Langmuir*, 2007, 27, 8365-8369.
  (b) H. Oie, A. Sudo and T. Endo, *J. Polym. Sci., Part A: Polym. Chem.*, 2011, 49, 3174-3183. (c) A. Sudo, R. Kudo, H. Nakuyama, K. Airma and T. Endo, *Macromolecules*, 2008, 41, 9030-9034. (d) S. W. Kuo and F. C. Chang, *Prog. Polym. Sci.*, 2011, 36, 1649-1696. (e) M. G. Mohamed, K. C. Hsu, and S. W. Kuo, *Polym. Chem.*, 2015, 6, 2423-2433. (f) C. Li, Q. Ran, R. Zhu, and Y. Gu, *RSC Adv.*, 2015, 5, 22593-22600.
- 15 (7) C. K. Chozhan, M. Alagar and P. Gnanasundarm, *Acta Mater.*, 2009, 28, 338-794.
  - (8) M. G. Mohamed, H. K. Shih, and S. W. Kuo, *RSC Adv.*, 2015, 5, 12763-12772.
  - (9) H. Ishida and H. Y. Low, *Macromolecules*, 1997, 30, 1099-1106.
  - (10) T. Agag and T. Takeichi, Polymer, 2000, 41, 7083-7090.
  - (11) P. Phirivawirut, R. Magaraphan and H. Ishida, *Mater: Res. Innova.*, 2001, **4**, 187-198.
- (12) M. R. Vengatesan, S. Devaraiu, K. Dinkaran and M. Alagar, *J. Mater. Chem.*, 2012, **22**, 7559-7559.
- (13) C. F. Wang, Y. C. Su, S.W. Kuo, C.F. Huang, Y. C. Sheen and F. C. Chang, *Angew. Chem. Int. Ed.*, 2006, 45, 2248-2251.
- (14) T. Agag, R. C. Arza, F. H. J. Maurer and H. Ishida, *Macromolecules*, 2010, 43, 2748-2758.
- (15) A. Chernykh, T. Agag and H. Ishida, *Polymer*, 2009, 50, 3153-3157.
- (16) H. M. Qi, G. Y. Pan and Q. Y. Zhuang, *Polym. Eng. Sci.*, 2010, **50**, 1751-1757.
- 35 (17) Z. Brunovska, and H. Ishida, J. Appl. Polym. Sci., 1999, 73, 2937-2949.
  - (18) T. Takeichi, K. Nakamura, T. Agag and H. Muto, Des. Monomers Polym., 2004, 7, 727-740.
- (19) R. Kudoh, A. Sudo and T. Endo, *Macromolecules*, 2010,
   43, 1185-1187.
- (20) Y. C. Ye, Y. J. Huang, F. C. Chang, Z. G. Xue and X. L. Xie, *Polym. Chem.*, 2014, 5, 2863-2871.
- (21) (a) J. Liu, C. Scott, S. Winroth, J. Maia, and H. Ishida, *RSC Adv.*, 2015, **5**, 16785-16791. (b) K. Sethuraman, and
- <sup>45</sup> M. Alagar, *RSC Adv.*, 215, **5**, 9607-9617. (c) R. Sasikumar, M. Ariraman, M. and M. Alagar, *RSC Adv.*, 2014, **4**, 19127-19136.
- (22) S. W. Thomass, G. D. Joly and T. M. Swager, *Chem. Rev.*, 2007, **107**, 1339-1386.
- 50 (23) C. T. Chen, Chem. Mater., 2004, 16, 4389-4400.
- (24) R. T. K. Kwok, J. L. Geong, J. W. Y. Lam, E. G. Zhao, G. Wang, R. Y. Zhan, B. Liu and B. Z. Tang, *J. Mater. Chem. B.*, 2014, **2**, 4134.
- (25) Y. Q. Dong, J. W. Y. Lam, A. J. Qin, Z. Li, J. Z. Sun, H. Y.
   <sup>55</sup> Sung, I. D. Williams and B. Z. Tang, *Chem. Commun.*, 2007, 40-42.
- (26) H. Saigusa and E. C. Lim, J. Phys. Chem., 1995, 99, 15738-15747.
- (27) J. Luo, Z. Xie, J. W. Y. Lam, L. Cheng, H. Chen, C. Qiu,
- H. S. Kwok, X. Zhan, Y. Liu, D. Zhu and B. Z. Tang, *Chem. Commun.*, 2001, 1740-1741.
- (28) J. Chen, C. C. W. Law, J. W. Y. Lam, Y. Dong, S. M. F. Lo, I. D. Williams, D. Zhu and B. Z. Tang, *Chem. Mater.*, 2003, 15, 1535-1546.
  (20) V. D. Li S. Li S.
- 65 (29) Y. P. Li, F. Li, H. Y. Zhang, Z. Q. Xie, W. J. Xie, H. Xu, B.

Li, F. Y. Z. Shen and L. M. Hanif, *Chem. Commun.*, 2007, 231-233.

- (30) Z. P. Yu, Y. Y. Duan, L. H. Cheng, Z. L. Han, Z. Zheng, H. P. Zhou, J. Y. Wu and Y. P. Tian, *J. Mater. Chem.*, 2012, 22, 16927-16932.
- (31) Y. Qian, M. M. Cai, X. H. Zhou, Z. Q. Gao, X. P. Wang, Y. Z. Zhao, X. H. Yan, W. Wei, L. H. Xie and W. Huang, J. Phys. Chem. C, 2012, 116, 12187-12195.
- (32) Z. Q. Xie, B. Yang, G. Cheng, L. L. Liu, F. He, F. Z. Shen,
   Y. G. Ma and S. Y. Liu, *Chem. Mater.*, 2005, 17, 1287-1289.
- (33) W. Tang, Y. Xiang and A. Tong, J. Org. Chem., 2009, 74, 2163-2166.
- (34) S. L. Liu, D. Li, Z. Zhang, G. K. S. Prakash, P. S. Conti, Z. B. Li, *Chem. Commun.*, 2014, **50**, 7371.
- (35) L. L. Long, W. Y. Lin, B. B. Chen, W. S. Gao, L. Yuan, *Chem. Commun.*, 2011, **47**, 893.
- (36) B. K. An, S. K. Kwon, S. D. Jung, S. Y. Park, J. Am. Chem. Soc., 2002, **124**, 14410-14415.
- 85 (37) W. Tang, Y. Xiang and A. Tong, J. Org. Chem., 2009, 74, 2163-2166.
  - (38) G. Liu, M. Yang, L. Wang, J. Zheng, H. Zhou, J. Wu and Y. Tian, J. Mater. Chem. C., 2014, 2, 2684-2691.
- (39) M. G. Mohamed, W. C. Su, Y. C. Lin, C. F. Wang, J. K. Chen, K. U. Jeong and S. W. Kuo, *RSC Adv.*, 2014, 4, 50373-50385.
- (40) Y. H. Low and H. Ishida, *Polym. Degrad. Stab.*, 2006, **91**, 805-815.
- (41) O. T. Lekesiz and J. Hacaloglu, *Polymer*, 2014, **55**, 3533-3542.
- (42) C. Liu, D. Shen, M. R. Sebastian, J. Marquet and R. Schonfold, *Macromolecules*, 2011, 44, 4616-4622.
- (43) T. S. Hsiao, S. L. Deng, K. Y. Shih and J. L. Hong, J. Mater. Chem. C, 2014, 2, 4828-4834.

100

10 | Journal Name, [year], [vol], 00-00

20

Published on 14 July 2015. Downloaded by California State University at Fresno on 15/07/2015 09:32:30

# Graphical abstract



A new salicylaldehyde azine–functionalized benzoxazine s (Azine-BZ) monomer formed benzoxazine/zinc ion complexes that not only improved the thermal properties but also facilitated ring-opening polymerization.