A pH-responsive silica-metal-organic framework hybrid nanoparticle for the delivery of hydrophilic drugs, nucleic acids, and CRISPR-Cas9 genome-editing machineries



Yuyuan Wang, Pawan K. Shahi, Ruosen Xie, Huilong Zhang, Amr A. Abdeen, Nisakorn Yodsanit, Zhenqiang Ma, Krishanu Saha, Bikash Pattnaik, Shaoqin Gong

PII:	S0168-3659(20)30266-2
DOI:	https://doi.org/10.1016/j.jconrel.2020.04.052
Reference:	COREL 10305
To appear in:	Journal of Controlled Release
Received date:	29 September 2019
Revised date:	14 April 2020
Accepted date:	30 April 2020

Please cite this article as: Y. Wang, P.K. Shahi, R. Xie, et al., A pH-responsive silica-metal-organic framework hybrid nanoparticle for the delivery of hydrophilic drugs, nucleic acids, and CRISPR-Cas9 genome-editing machineries, *Journal of Controlled Release* (2019), https://doi.org/10.1016/j.jconrel.2020.04.052

This is a PDF file of an article that has undergone enhancements after acceptance, such as the addition of a cover page and metadata, and formatting for readability, but it is not yet the definitive version of record. This version will undergo additional copyediting, typesetting and review before it is published in its final form, but we are providing this version to give early visibility of the article. Please note that, during the production process, errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

© 2019 Published by Elsevier.

### A pH-Responsive Silica–Metal–Organic Framework Hybrid Nanoparticle for the Delivery of Hydrophilic Drugs, Nucleic Acids, and CRISPR-Cas9 Genome-Editing Machineries

Yuyuan Wang<sup>1, 2</sup>, Pawan K. Shahi<sup>3</sup>, Ruosen Xie<sup>1, 2</sup>, Huilong Zhang <sup>4</sup>, Amr A. Abdeen<sup>2</sup>, Nisakorn Yodsanit<sup>2, 5</sup>, Zhenqiang Ma<sup>4</sup>, Krishanu Saha<sup>2, 5</sup>, Bikash Pattnaik<sup>3, 6</sup> and Shaoqin Gong<sup>1, 2, 5, 6, 7 \*</sup>

- 1. Department of Materials Science and Engineering, University of Wisconsin-Madison, Madison, WI 53715, USA
- 2. Wisconsin Institute for Discovery, University of Wisconsin–Madison, Madison, WI 53715, USA
- 3. Department of Pediatrics, University of Wisconsin Madison, Madison, WI 53706, USA.
- 4. Department of Electrical and Computer Engineering, University of Wisconsin-Madison, Madison, WI 53706, USA
- 5. Department of Biomedical Engineering, University of W.scorsin-Madison, Madison, WI 53715, USA
- 6. McPherson Eye Research Institute, University of Victorian Madison, Madison, WI 53705, USA
- 7. Department of Chemistry, University of Wiscon, n-Nadison, Madison, WI 53715, USA

\*: Correspondence should be addressed to SG (s'.a. cingong@wisc.edu)

#### Abstract

Efficient delivery of hydrophil'e a 2gs, nucleic acids, proteins, and any combination thereof is essential for values biomedical applications. Herein, we report a straightforward, yet versatile approach to efficiently encapsulate and deliver various hydrophilic payloads sin, a pH-responsive silica-metal-organic framework hybrid nanoparticle (SMOF NT) consisting of both silica and zeolitic imidazole framework (ZIF). This unique SMOF NP offers a high loading content and efficiency, excellent stability, and robust intracellular delivery of a variety of payloads, including hydrophilic small molecule drugs (e.g., doxorubicin hydrochloride), nucleic acids (e.g., DNA and mRNA), and genome-editing machineries (e.g., Cas9-sgRNA ribonucleoprotein (RNP), and RNP together with donor DNA (e.g., RNP+ssODN)). The superior drug delivery/gene transfection/genome-editing efficiencies of the SMOF NP are attributed to its pH-

controlled release and endosomal escape capabilities due to the proton sponge effect enabled by the imidazole moieties in the SMOF NPs. Moreover, the surface of the SMOF NP can be easily customized (e.g., PEGylation and ligand conjugation) via various functional groups incorporated into the silica component. RNP-loaded SMOF NPs induced efficient genome editing *in vivo* in murine retinal pigment epithelium (RPE) tissue via subretinal injection, providing a highly promising nanoplatform for the delivery of a wide range of hydrophilic payloads.

#### 1. Introduction

Intracellular delivery of hydrophilic drugs, nucleic *ecis* and proteins plays an important role in medicine, including targeted drug delivery, gene therapy, and genome editing[1-4]. Nevertheless, efficient encapsulation and delivery of hydrophilic payloads while retaining their active conformations remains a significant challenge. A desirable delivery system would be able to encapsulate bioactive molecules with a high loading efficiency without compromising their biological activity.

The use of inorganic nanor atives (NPs) (e.g., gold NPs, calcium phosphate NPs, silicabased NPs) has emerged as a promising strategy for efficient drug/gene delivery[5-7]. Silica NPs have shown remarkable potential in nanomedicine due to their unique properties, such as high stability, multifunctionality, and biocompatibility[8-10]. However, stimuli-responsive silica NPs are either difficult to design (i.e., pH-responsive), or require unstable/hard-tosynthesize silica monomers (i.e., GSH-responsive)[11, 12], thus hindering their delivery efficiency.

Metal-organic frameworks (MOFs), a class of materials formed by the covalent assembly of polydentate bridging ligands and metal-connecting points, have been studied for drug, gene, and genome-editing machinery delivery[13-15]. Zeolitic imidazolate framework (ZIF) is a

subclass of metal–organic frameworks formed by coordination between Zn<sup>2+</sup> ions and 2methylimidazole (2-MIM) with good biocompatibility[16, 17]. Moreover, the excellent pHbuffering capacity of the imidazole bridging ligand confers pH-responsive capabilities to the ZIF, as well as an enhanced ability to escape the endocytic pathway[18]. ZIF-based nanosystems have been used for drug, gene, and protein delivery[18-20].

Herein, we report the fabrication of a pH-responsive silica-metal-organic framework hybrid NP (SMOF NP) consisting of both silica and ZIF via a facile water-in-oil emulsion approach, allowing for the delivery of a variety of hydrogram payloads including small molecule drugs, nucleic acids, and genome-editing machineries. Hydrophilic payloads can be encapsulated in the NPs with a high loading content (> ? wt%) and a high loading efficiency (>90%). The proton sponge effect of imidazole in the ZIF molety of the SMOF NPs contributes to the pH-controlled release and endosomal escape capabilities, while the surface of the SMOF NP is customizable via functional groups the silica component.

We studied the genome editing eliminary in murine retinal pigmented epithelium (RPE), as genetic disorders in the RPE on cause a variety of eye diseases (e.g., retinal degeneration and blindness) [21]. SMOF NPs were decorated with a targeting ligand, all-trans retinoic acid (ATRA) (i.e., SMOF-ATRA) ATRA binds to the inter-photoreceptor retinoid-binding protein, a major protein in the inter-photoreceptor matrix that selectively transports all-trans-retinol to the RPE and 11-cis-retinal to photoreceptor[22, 23]. SMOF-ATRA generated robust gene editing in murine retinal pigment epithelium (RPE) after local administration. This stable, biocompatible, and multifunctional SMOF NP is a promising nanoplatform capable of efficiently delivering a variety of hydrophilic payloads.

#### 2. Experimental Section

#### Materials

3

1*H*-imidazole-4-carboxylic acid, thionyl chloride (SOCl<sub>2</sub>), tetraethyl orthosilicate (TEOS), tetrahydrofuran (THF), Triton X-100, acetone, ethanol, ammonia (30% in water) 1ethyl-3-(3-dimethylaminopropyl)carbodiimide (EDC), and N-hydroxysuccinimide (NHS) were purchased from Fisher Scientific, USA. Hexanol, cyclohexane, 2-methyl-1H-imidazole (3-aminopropyl)triethoxysilane (APTES), and doxorubicin hydrochlor ide (2-MIM), (DOX·HCl) bought were from Tokyo Chemical Industry Co., Ltd., USA. Methoxypolyethylene glycol-N-succinimidyl ester (mPEG-NHS,  $M_n = 5000$ ) and hydroxylpolyethylene glycol-N-succinimidyl ester (HO-PEG-NHS,  $M_{\star} = 5000$ ) were obtained from Jenkem Technology, USA. Anhydrous zinc nitrate (ZnNO?) a.1 all-trans retinoic acid (ATRA) were purchased from Sigma-Aldrich, USA. Nuclear localization signal (NLS)-tagged streptococcus pyogenes Cas9 nuclease (sNLS-SpCass sNLS) was provided by Aldevron, USA.

#### Synthesis of N-(3-(Triethoxysilyl)propyl, (H-Imidazole-4-Carboxamide (TESPIC)

A 1*H*-imidazole-4-carboxylic *e*.x (500 mg, 3.85 mmol) solution in SOCb (8 ml) was heated while stirring to reflux ov mignt. The reaction mixture was cooled to room temperature and added into toluene. The propriate was then collected by filtration and dried *in vacuo* at room temperature to yielt the acid chloride intermediate, 1*H*-imidazole-4- carbonyl chloride. The freshly synthesized 1*H*-imidazole-4-carbonyl chloride was suspended in anhydrous THF (5 ml), followed by addition of Triethylamine (855 mg, 8.47 mmol) and APTES (851 mg, 3.85 mmol). The mixture was stirred at room temperature overnight under a nitrogen atmosphere. The mixture was subsequently filtered, and the solvent was then removed by rotary evaporation to yield the final product TESPIC. Since the silica reactants have the tendency to undergo hydrolysis/polymerization during column purification, TESPIC was synthesized and used without purification for SMOF NP formation[11, 24]. <sup>1</sup>H NMR (400 MHz, DMSO-*D6*):  $\delta$  0.60 (dd, 2.4 H, J = 14.6, 6.2 Hz),  $\delta$  1.12 (t, 0 H, J = 7.0 Hz),  $\delta$  1.57 (dt, 2 H, J = 15.9, 8.0 Hz),  $\delta$ 

2.83–2.61 (m, 2 H), δ 3.70 (q, 6 H, J = 6.0 Hz), δ 7.03 (s, 1 H), δ 7.40 (s, 1 H). <sup>13</sup>C NMR (100 MHz, DMSO-*D*6): δ 165.76, 135.50, 132.89, 128.21, 58.01, 42.55, 22.88, 18.64, and 7.55.

#### Preparation of Silica–Metal–Organic Framework Hybrid Nanoparticles (SMOF NPs)

SMOF NPs were synthesized by a water-in-oil emulsion method. Triton X-100 (1.75 ml) and hexanol (1.75 ml) were dissolved in cyclohexane (7.5 ml) to form the organic phase. An aqueous ZnNO<sub>3</sub> (0.5 M) solution (20 µl) containing the desirable payload (e.g., DOX·HCl, DNA, mRNA, RNP, and RNP+ssODN; 5 mg/ml) was mixed with 400 µl of the organic phase. This mixture was vortexed for 15 s and then sonicated in an ultra onic water bath for 15 s to form the water-in-oil emulsion, which was then magnetically stirred at 1500 rpm. To this emulsion, TEOS, TESPIC, APTES, and 2-MIM vith different feed weight ratios were dissolved in 100 µl organic phase and added to the above emulsion. For example, to achieve a feed weight ratio of silica reactants (i.e., TFOC TESPIC, APTES) to MOF reactant (i.e., 2-MIM) of 60:40, the total weight of TEOS+, FSPIC+APTES added to the emulsion would be 1.2 mg, while the weight of 2-MIM roud be 0.8 mg. Upon the addition of 3 µL of 30% ammonia aqueous solution, the vixtule was stirred for 4 h at room temperature. Thereafter, mPEG-NHS (100  $\mu$ g in 100  $\mu$ ; hexanol) was added to the above emulsion and was stirred for another 2 h. To prepare ATRA-modified SMOF NPs (i.e., SMOF-ATRA), HO-PEG-NHS was used instead of mPEG-NFS. The final payload-encapsulated SMOF NPs were precipitated by 600 µl acetone, and then washed by ethanol and water three times each.

ATRA was conjugated to the SMOF NP surface via EDC/NHS catalyzed esterification. Payload-encapsulated SMOF NPs (0.5 mg) were re-dispersed in 0.5 ml DI water. EDC ( $60 \mu g$ ), NHS ( $60 \mu g$ ) and a DMSO solution of ATRA ( $6 \mu g$  in 3  $\mu$ l DMSO) were added to the above solution, and the pH was adjusted to 8. The solution was stirred at room temperature for 6 h, and then the SMOF-ATRA was washed by water three times.

#### **Characterization**

The chemical structure of TESPIC was analyzed by nuclear magnetic resonance (NMR) spectroscopy (Avance 400, Bruker Corporation, USA). The hydrodynamic diameter and zeta potential of the SMOF NPs were characterized by a dynamic light scattering (DLS) spectrometer (Malvern Zetasizer Nano ZS) at a 90° detection angle with a concentration of 0.1 mg/ml. The morphologies of SMOF NPs were characterized by transmission electron microscopy (TEM, Tecnai 12, Thermo Fisher, USA) and scanning electron microscopy (SEM, Zeiss/LEO 1530, Carl Zeiss Microscopy, USA). X-ray powder difficultion of SMOF NPs was performed by Bruker D8 Discovery (Bruker Corporation, <sup>7</sup>USA<sup>+</sup>).

#### Loading Content/Loading Efficiency Study

To calculate the loading content and loading criticiency of the payloads in the SMOF NPs, 1 mg·mL<sup>-1</sup> of SMOF NP stock solution with do me of acetate buffer (0.1 M, pH 5.5) for 30 min to µL of SMOF NP was incubated with 40 µL of acetate buffer (0.1 M, pH 5.5) for 30 min to allow for complete dissociation of S'ver?F NPs. The DOX·HCl loading content/efficiency was studied by UV-Vis spectroscop; The RNP and RNP-ssODN loading contents/efficiencies were measured via a bicinchon. The acid assay (BCA assay, Thermo Fisher, USA). DNA and mRNA loading contents efficiencies were evaluated using a NanoDrop One (Thermo Fisher, USA).

#### **Cell Culture**

Cells were cultured in a cell culture incubator (Thermo Fisher, USA) at 37 °C with 5% carbon dioxide at 100% humidity. HEK 293 cells (a human embryonic kidney cell line), NHDF (a normal human dermal fibroblast cell line), and RAW 264.7 cells (a mouse macrophage cell line) were purchased from ATCC (USA) and cultured with DMEM medium (Gibco, USA) with 10% (v/v) fetal bovine serum (FBS, Gibco, USA) and 1% (v/v) penicillin–streptomycin

(Gibco, USA). HCT 116 cells (a human colon cancer cell line) were cultured with 89% McCoy's 5A medium, 10% FBS, and 1% penicillin–streptomycin. All the culture media used for hydrophilic drug delivery/nucleic acid transfection/genome editing efficiency studies were complete culture media containing 10% FBS.

#### Hydrophilic Drug Delivery Study

The cellular uptake behavior of DOX·HCl-loaded SMOF NPs was analyzed using flow cytometry. HEK 293 cells were seeded onto 96-well plates with 15,000 cells per well 24 h before treatment. The cells were incubated with free DOX·H 'l a) d DOX·HCl-loaded SMOF NPs for 4 h with a DOX·HCl concentration of 5 µg/ml. Thereafter, cells were harvested with 0.25% trypsin-EDTA (Thermo Fisher, USA), spun (own) and resuspended with 200 µl PBS (Thermo Fisher, USA). DOX·HCl uptake was clear cred with an Attune NxT flow cytometer system (Thermo Fisher, USA) and analyzec'. wh'r FlowJo 7.6.

#### DNA and mRNA Transfection Eff.cr. ncy Study

HEK 293, HCT116, NHD<sup>4</sup>, and RAW 264.7 cells were seeded onto 96-well plates at a density of 15,000 cells per well 24 h prior to treatment. Cells were transfected with either a green fluorescence protein (CFP) plasmid DNA (Addgene #40259, USA)-loaded SMOF NPs, or a GFP-mRNA (OZ Elosciences INC, San Diego, CA)-loaded SMOF NPs, The dosage of DNA or mRNA dosages is 200 ng/well, the SMOF NP concentrations for DNA- and mRNA-loaded SMOF NPs were 21  $\mu$ g/ml and 22  $\mu$ g/ml, respectively. DNA or mRNA was also transfected using a commercially available transfection agent, Lipofectamine 2000 (i.e., Lipo 2000, Thermo Fisher, USA), as a positive control group. The Lipofectamine-DNA complex was prepared as suggested by the manufacturer. The amount of Lipo 2000 and DNA (or mRNA) used per well was 0.5  $\mu$ l and 200 ng, respectively. An untreated group was used as the negative

control group. After 48 h, HEK 293, HCT116, and NHDF cells were harvested with 0.25% trypsin-EDTA. RAW264.7 cells were harvested by repeated pipetting. The cells were then spun down and resuspended with 200  $\mu$ l of PBS. GFP expression efficiencies were obtained with a flow cytometer and analyzed with FlowJo 7.6. Gating strategies are shown in Figure S7.

#### **RNP** Genome-Editing Efficiency Study

GFP-expressing HEK 293 cells (GenTarget Inc.) were used as an RNP-transfection cell model. Cells were seeded at a density of 5,000 cells per well  $c \neq 0.96$ -well plates, 24 h before treatment. RNP was prepared as previously reported [25] by t ixing sNLS–SpCas9–sNLS and *in vitro* transcribed sgRNA (Integrated DNA Technologies, Inc., GFP protospacer: 5'-GCACGGGCAGCTTGCCGG-3') at a 1:1 molar ratio. Cylls were treated with Lipo 2000 (0.5  $\mu$ /well) complexed with RNP or RNP-loaded S'*i*. OF NPs. The RNP dosage was kept at 150 ng/well (i.e., an equivalent Cas9 protein decreate of 125 ng/well). An untreated group was used as the control group. A quantity of 100  $\mu$  l of fresh culture medium was refreshed every 48 h. Six days after treatment, cells were harvested with 0.25% trypsin-EDTA, spun down, and resuspended with 200  $\mu$ l of PBS. The RNP genome-editing efficiencies were quantified via flow cytometry. Data were an lyze 1 with FlowJo 7.6.

#### RNP+ssODN Co-Delivery for Precise Gene Correction

The RNP+ssODN mixture was prepared by simply mixing the as-prepared RNP and singlestranded oligonucleotide DNA (ssODN) donor template at 4 °C for 5 min at a 1:1 molar ratio. Blue fluorescence protein (BFP)-expressing HEK 293 cells generated through lentiviral transduction of a BFP dest clone (Addgene, Cambridge, MA) was employed as a model cell line[25]. When cells are transfected with RNP+ssODN-targeting BFP (Integrated DNA Technologies, Inc., BFP protospacer: 5'-GCTGAAGCACTGCACGCCAT-3'), if precise

### Intracellular Trafficking of RNP SMOF NIS

Intracellular trafficking of RNP SMOr NPs was investigated by confocal laser scanning microscopy (CLSM, Nikon, Japan). In this case, ATTO550-labeled sgRNA (Integrated DNA Technologies, Inc.) was used to form the Cas9/ATTO-sgRNA RNP loaded into the SMOF NPs. HEK 293 cells were seeded onto a Nunc<sup>TM</sup> Lab-Tek<sup>TM</sup> II CC2<sup>TM</sup> chamber slide (Thermo Fisher, USA) at 50,000 cells per wei 24 h prior to treatment. At each time point (i.e., 0.5, 2, and 4 h) after SMOF NP treatment, the cells were washed by PBS and then stained with endosome/lysosome marker LysoTracker Green DND-26 (100 nM) and nucleus marker Hoechst 33342 (10 µg/mL) for 30 min at 37 °C.

#### **Cell Viability Assay**

The cytotoxicity of the DOX·HCl-loaded SMOF NPs was studied using an MTT assay. HEK 293 cells were seeded onto 96-well plates with 20,000 cells per well 24 h prior to treatment. The cells were then treated with free DOX·HCl, DOX·HCl-loaded SMOF NPs, and

empty SMOF NPs (DOX·HCl concentrations of 6 and 12  $\mu$ g/ml). Cells without treatment were used as a control group. After 48 h, the cell viability was measured using a standard MTT assay (Thermo Fisher, USA). Briefly, cells were treated with media containing 500  $\mu$ g/ml MTT and incubated for 4 h. Then, the MTT-containing media was aspirated. Next, the purple precipitate was dissolved in 150  $\mu$ l of DMSO. The absorbance at 560 nm was obtained with a microplate reader (GloMax<sup>®</sup> Multi Detection System, Promega, USA).

The cytotoxicity of SMOF NPs was also studied by MTT assay. Cells were treated with complete medium, Lipo 2000 (0.5  $\mu$ l/well), and empty SMOF NPs, whose concentrations ranged from 10 to 200  $\mu$ g/ml. Cell viability was measured using a standard MTT assay 48 h after treatment (Thermo Fisher, USA), as mentioned for ve.

#### **Subretinal Injection**

All animal research was approved by UV-Madison animal care and use committee. Ail 4 reporter mice (obtained from The Jac.'son Laboratory) were used to assess the genome editing efficiency induced by RNP-loaded SNUF NPs. C57BI/6 mice were used as the controls for biocompatibility studies. RNPs were prepared using either a sgRNA targeting the stop cassette composed of 3 SV40 polyA bloc.'s (target sequence: 5'-AAGTAAAACCTCTACAAATG-3') in Ail4 mice or a 1700  $\circ$  regative control sgRNA (Integrated DNA Technologies, guide sequence: CGTTAATCCCGTATAATACG). Subretinal injection and subsequent RPE tissue collection were performed as reported previously [27]. Mice were maintained under tightly controlled temperature (23 ± 5 °C), humidity (40-50%), and light/dark (12/12 h) cycle conditions under a 200 lux light environment. The mice were anesthetized by intraperito neal injection of ketamine (80 mg/kg), xylazine (16 mg/kg) and acepromazine (5 mg/kg) cocktail. Before the subretinal injection, the cornea was anesthetized with a drop of 0.5% proparacaine HCl, and the pupil was dilated with 1.0% tropicamide ophthalmic solution. Mice were placed

on a temperature-regulated heating pad during the injection and for recovery purposes. All surgical manipulations were carried out under a surgical microscope (AmScope, Irvine, CA). SMOF-ATRA encapsulating RNP with a sgRNA targeting the Ail4 stop cassette (i.e., Ail4 RNP SMOF), SMOF-ATRA encapsulating RNP with a negative control sgRNA (i.e., negative control SMOF), and PBS were injected into the eyes subretinally. Two microliters of SMOF-ATRA solutions containing 4  $\mu$ g RNP or PBS was injected into the subretinal space using a UMP3 ultramicro pump fitted with a NanoFil syringe, and the RPE-KIT (all from World Precision Instruments, Sarasota, FL) equipped with a 34-gav<sub>c</sub> ceveled needle. Successful administration was confirmed by visualization of bleb non-nation. The tip of the needle remained in the bleb for 10 s after bleb formation, when a vas gently withdrawn.

To assess tdTomato expression generated by successful genome editing, the mice were sacrificed, and eyes were collected 13 to 14 d vs after injection and rinsed twice with PBS. A puncture was made at ora serrata with an 14-gauge needle, and the eye was opened along the corneal incisions. The lens was then renk ved. The eyecup was incised radially to the center and flattened to give a final floret subject. The RPE layer was then separated and flat-mounted on a cover-glass slide. RPE tiss were imaged with a NIS-Elements using a Nikon C2 confocal microscope (Nił.on Instruments Inc.). ImageJ (NIH) was used for image analysis.

#### Electroretinography of the Retina

To study the biocompatibility of SMOF NP after subretinal injection, we tested visual function before sacrificing the mice via electroretinography (ERG). PBS and Ai14 RNP-loaded SMOF-ATRA were injected to the eyes of C57BI/6 mice subretinally. Fourteen days post-injection, animals were anesthetized as described above. All experiments were performed in a dark room. An Espion Ganzfeld full-field system (Diagnosys LLC, Lowell, MA) was used for ERG recordings. A drop of 2% hypromellose (GONIOVISC, HUB Pharmaceuticals, LLC,

Rancho Cucamonga, CA) solution was placed on the cornea to keep it moistened and to provide an electrical contact with the ERG electrode. The mice were placed under the Ganzfeld dome to assure uniform illumination of the eyes. The eyes were exposed to a sequential increment of flash intensities (0.01 to 30 cd.s/m<sup>2</sup>) for 400 ms with a 2 s interval between each flash for a and b- wave and eyes were exposed 25 cd.s/m<sup>2</sup> for 4 secs to measure c-wave. The data were analyzed using Diagnosys software version 6.0.54 (Diagnosys LLC, Lowell, MA).

#### **Statistical Analysis**

Results are presented as mean  $\pm$  standard deviation (SD). O e-way analysis of variance (ANOVA) with Tukey's multiple comparisons was used to determine the difference between independent groups. Statistical analyses were conducted using GraphPad Prism software version 6.

#### 3. Results and Discussion

Silica-metal-organic framework Lybrid nanoparticles (SMOF NPs) were synthesized via a facile water-in-oil emulsion method F gure 1A and B). An aqueous solution containing zinc ions at a constant concentration ( $\gtrsim$ .5 M) and the desirable payload was emulsified in the continuous oil phase, followed by additions of the silica reactants and the imidazole reactant (i.e., 2-methylimidazok ( $\gtrsim$  MIM)), which coordinates with the zinc ions and forms the pHresponsive zeolitic imidazole framework (ZIF)) (Figure 1C). The silica-reactive components included tetraethyl orthosilicate (TEOS), a basic building block that constructs the silica network; imidazole-containing N-(3-(triethoxysilyl)propyl)-1*H*-imidazole-2-carboxa mide (TESPIC) that bridges the silica component with the ZIF component; and amine-containing (3aminopropyl)triethoxysilane (APTES) that enables surface modification. Polyethylene glycol (PEG) was subsequently incorporated onto the SMOF NP surface after the formation of the SMOF NP, which allowed for further surface functionalization (e.g., conjugation of targeting

ligands and imaging agents). The as-prepared SMOF NPs were then collected by precipitation in acetone, centrifuged, and washed by ethanol and deionized (DI) water three times each to remove all impurities.



**Figure 1. Design and \_vmhesis of SMOF NPs.** (A) Illustration of the SMOF NP for the delivery of various hydrophilic payloads such as hydrophilic small molecular drugs, DNA, mRNA, proteins, and a combination thereof (e.g., Cas9/sgRNA (RNP) and RNP+ssODN). (B) Synthesis of SMOF NPs via a water-in-oil emulsion method. (C) Schematic illustration of the intracellular trafficking pathways of SMOF NPs. SMOF NP: silica–metal–organic framework hybrid nanoparticle; 2-MIM: 2-methylimidazole; PEG: polyethylene glycol; TEOS: tetraethyl orthosilicate; TESPIC: N-(3-(triethoxysilyl)propyl)-1H-imidazole-2-carboxamide; APTES: (3-aminopropyl)triethoxysilane.

The SMOF NP formulation was first optimized in a human embryonic kidney cell line (HEK 293) using plasmid DNA (Figure 2) and mRNA (Figure S2) as the payloads. The zinc ion concentration in the aqueous phase was fixed at 0.5 M, while various factors were optimized including the feed ratio of the payload to the SMOF NP reactants, the feed ratio of the silica reactants (TEOS+APTES+TESPIC) to the MOF reactant (2-MIM), and the emulsification process (e.g., bath sonication versus probe sonication).

The feed weight ratio between the payload and the SMCF P reactants is important, as insufficient SMOF NP forming materials may lead to a limited encapsulation volume and subsequently, a low loading efficiency and premature release and degradation of the payloads. The optimal formulation showing the highest DNA transfection efficiency was obtained at a DNA:SMOF reactant feed ratio of 1:20, indicating successful encapsulation of the payload within the SMOF NPs and an efficient intra ellular release thereafter (Figure 2A).

The feed weight ratio between the rike reactants (i.e., TEOS+APTES+TESPIC) and the MOF reactant (i.e., 2-MIM) is an their critical factor for efficient payload delivery. Without the silica component, surface functionalization of the resulting MOF/ZIF NPs is very challenging because various functional groups can be conveniently introduced into the SMOF NPs through judicious selection of the silica reactants. Without the MOF component, silica NPs alone can neither escape endosomes and lysosomes efficiently nor release the payload rapidly in response to pH, thereby greatly minimizing the delivery efficiency. As shown in Figure 2A, both pure silica NPs and pure MOF NPs formed via water-in-oil emulsions exhibited limited DNA transfection efficiencies. Moreover, pure MOF NPs showed larger particle sizes (>350 nm and polydispersed) after purification, indicating inadequate PEGylation and thus NP aggregation. The molar ratio of the three silica reactants—namely, TEOS, APTES, and TESPIC—was

further optimized (Figure 2B). The optimal formulation showing the highest DNA transfection efficiency was obtained when the molar ratio of TEOS:APTES:TESPIC was 80:10:10.

To evaluate the necessity of using a TEOS:APTES:TESPIC ternary composition to form the silica component in the SMOF NP instead of unary or binary counterparts, the SMOF NP formulation without TESPIC (i.e., TEOS:APTES:TESPIC, molar ratio of 90:10:0) was first tested. The resulting SMOF NPs exhibited significantly lower DNA transfection efficiencies, indicating that TESPIC was essential for bridging the silica component to the MOF component within the hybrid SMOF NPs. Moreover, the formulation without APTES (i.e., TEOS:APTES:TESPIC, molar ratio of 90:0:10) also showed to rge and polydispersed particle sizes and limited the transfection efficacy due to  $t_{AE}$  by the sufface PEGylation and NP aggregation. However, higher APTES or TESPIC ratios did not provide any advantage in achieving higher transfection efficiencies (Figure 2B).

The sonication method also plays an in-portant role in SMOF NP synthesis as it facilitates emulsification and controls the water consist size in the emulsion. However, sonication that is too strong may affect the integrity of the biomacromolecular payload and thus reduce delivery efficiency. Using probe sonication for as short as 15 s can reduce the DNA transfection efficiency by 50% in comparison with the DNA transfection efficiency achieved via a gentler sonication method (i.e., vortex (15 s) + bath sonication (15 s)) (Figure 2A). This is consistent with previous reports in that probe sonication can damage DNA [28, 29]



Figure 2. Optimization of the DNA-los ded SMOF NP formulation using HEK 293 cells. (A) Optimization of the feed weight rails of the payload over the SMOF reactants, feed weight ratio of the silica reactants on the MOF reactant, and the emulsification method. (B) Optimization of the molecular ratio of the three silica reactants TEOS/APTES/TESPIC. The optimal SMOF NP form the highlighted by a black bar. NS: not significant; \*: p < 0.05; \*\*: p < 0.001; \*\*\*: p < 0.001; \*\*\*: p < 0.0001; n = 3.

The morphology of the DNA-loaded SMOF NP was characterized by scanning electron microscopy (SEM) and transmission electron microscopy (TEM). Spherical NPs with uniform sizes around 50–70 nm were observed, as shown in Figure 3A and B. The hydrodynamic diameter of DNA-loaded SMOF NPs, as measured by dynamic light scattering (DLS), was 110

nm (Figure 3C), similar to empty SMOF NPs, (119 nm, Figure S3). Zeta-potential measurements indicated that the DNA-loaded SMOF NPs had a slight positive surface charge  $(5.6 \pm 1 \text{ mV})$ , similar to empty SMOF NPs (4.8 mV). Powder X-ray diffraction (XRD) spectra showed that SMOF NPs had similar crystal structures to ZIF (Figure 3D). The ratio of the silica components and ZIF component in the SMOF NPs is controlled by the feed weight ratio of the silica reactants (i.e., TEOS, TESPIC, and APTES) and the ZIF reactant (i.e., 2-MIM). The ratio of the silica component and the ZIF component in the SMOF NPs was studied by energy-dispersive X-ray spectroscopy (EDS). As shown in Figure S1, which the optimal feed weight ratio of the silica reactants to the ZIF reactant at 6:4, the element all weight ratio between silicon (Si) and zinc (Zn) was 63:37 in the final SMOF NP, which is approximately equivalent to a 1:1 weight ratio of silica to ZIF.

17



Figure 3. Characterization of SMOF NPs. (A) TEM and (B) SEM micrographs of SMOF NPs. (C) Size distribution of SMOF NPs measured by DLS. (D) Powder XRD spectra of SMOF NP, pure MOF NP, and pure silica NP synthesized via the water-in-oil emulsion method.

The SMOF NP contains a pH-responsive ZIF component that degrades in acidic environments, leading to a rapid release of the payload [18]. Meanwhile, the ZIF component can also facilitate the endosomal escape of the payload because the imidazole groups (pKa  $\sim$  6.0) can be protonated in the acidic endocytic compartments (i.e., endosomes), leading to endosomal- membrane disruption by the proton sponge effect. To study the intracellular

trafficking of SMOF NPs, confocal laser scanning microscopy (CLSM) was used to image the subcellular distribution of Cas9/ATTO550-labeled sgRNA ribonucleoprotein (RNP) delivered by SMOF NPs (Figure 4). Cells without SMOF NP treatment were used as the control (Figure S4). No significant alternation in cell morphology and integrity was observed in the SMOF NP treated groups in comparison with the control group, indicating that SMOF NP treatment does not affect cell morphology. RNP was observed to co-localize with endo/lysosomes 0.5 h posttreatment, indicating that the uptake of RNP-loaded SMOF NPs occurred via endocytosis. The extent of co-localization of RNP and endo/lysosomes decreased 2. post-treatment, indicating the efficient endo/lysosomal escape capabilities of SMON NPs. Assisted by a nuclear localization signal (NLS) fused on both terminuses of the Cas9 nuclease, the RNP signal showed considerable overlap with .nd minimal co-localization the nucleu with endo/lysosomes as early as 4 h post-treatm n, thus indicating the efficient escape from endo/lysosomes and the successful nucle." t ansportation of RNP.



**Figure 4. Intracellular trafficking of RNP-loaded SMOF NPs by CLSM.** Colocalization of RNP and endo/lysosomes was studied at 0.5 h, 2 h, and 4 h post-treatment. Scale bar: 50 μm.

To investigate the versatility of SMOF NPs for the delivery of different hydrophilic payloads, including small molecule drugs (i.e., doxorubicin hydrochloride (DOX·HCl)), nucleic acids (i.e., DNA and mRNA), and CRISPR-Cas9 genome-editing machineries (i.e., RNP and RNP+ssODN (i.e., a combination of an RNP with a single-stranded oligonucleotide DNA (ssODN) donor template)), the loading content and loading efficiency of different payloads are quantified and summarized in Table 1. For small molecule DOX·HCl, the loading content was 17 wt%, with a loading efficiency of 92%. For hydrophilic biomacromolecules, the loading contents varied between 9.2–9.8 wt%, while the locatube efficiencies ranged from 91–97%. The high loading contents and efficiencies can be attributed to the water-in-oil emulsion method that confined the payloads within the water droplet, followed by the formation of the SMOF NP network.

Table	1. Summary	of loading	content	and loa ling	efficiency	of different	payloads	by SMOF
NPs.								

Payload	Loading Content (wt%)	Loading Efficiency (%)
Doxorubic in hydrochloride	17	92
DNA	9.5	94
mRNA	9.2	91
RNP	9.8	97
RNP+ssOLM	9.5	94

Efficient delivery of DOX·HCl via SMOF NPs was first studied by flow cytometry in HEK293 cells by taking advantage of the fluorescence of DOX·HCl. Cells without DOX·HCl treatment were used as a control. As shown in Figure 5A, DOX·HCl -loaded SMOF NP-treated cells exhibited a 3.2-fold higher level of DOX·HCl uptake than free DOX·HCl -treated cells 2 h post-treatment, indicating the efficient uptake of SMOF NPs by HEK293 cells. The cellular

uptake of DOX·HCl -loaded SMOF NPs was also confirmed by fluorescence microscopy (Figure S3) 4 h post-treatment. The therapeutic effect of DOX·HCl -loaded SMOF NPs was evaluated by an MTT assay (Figure 5B). At both 6  $\mu$ g/ml and 12  $\mu$ g/ml DOX·HCl concentrations, the DOX·HCl -loaded SMOF NPs exhibited identical cytotoxicity to free DOX·HCl, while empty SMOF NPs showed no significant cytotoxicity. These results demonstrated the efficient delivery and release of DOX·HCl by SMOF NPs.



Figure 5. Delivery Efficiency of a hyd op'alic drug by SMOF NPs. (A) Flow cytometry analysis on HEK293 cells treated with See DOX+HCl (5  $\mu$ g/ml) and DOX+HCl-loaded SMOF NPs (DOX+HCl concentration, 5  $\mu$ g/ml) or medium alone (control) for 2 h. (B) Cytotoxicity of empty SMOF NPs, free DOX +HCl and DOX+HCl-loaded SMOF NPs at different DOX+HCl concentrations (i.e., 6 and 12 ug ml) after co-incubation with HEK293 cells for 48 h.

The transfection enciency of DNA-loaded SMOF NPs was studied in four different cell types, including a HEK293 cell line, a human colon tumor (HCT116) cell line, a human normal dermal fibroblast (NHDF) cell line, and a rat macrophage (RAW264.7) cell line. In HCT116 cells, DNA-loaded SMOF NPs exhibited a similar transfection efficiency to the commercially available transfection agent Lipofectamine 2000 (Lipo 2000), while in the other three cell lines, SMOF NP showed statistically higher transfection efficiencies than Lipo 2000 (1.4-fold in HEK293 cells, 1.2-fold in NHDF cells and RAW264.7 cells, as shown in Figure 6A), . For mRNA-loaded SMOF NPs, they showed similar transfection efficiencies to Lipo 2000 in

HEK293 and NHDF cells, but statistically higher transfection efficiencies in HCT116 and RAW264.7 cells (1.9- and 1.3-fold, respectively, as shown in Figure 6B), indicating efficient delivery of nucleic acids by SMOF NPs.

Cas9 can cleave double-stranded DNA from a specific genomic locus under the guidance of sgRNA. After the double-stranded DNA break is generated, gene deletion can be achieved by the nonhomologous end-joining (NHEJ) DNA repair pathway[30, 31]. To investigate the genome-editing efficiency of RNP-loaded SMOF NPs, a sgRNA targeting the GFP gene in a transgenic GFP-expressing HEK 293 cell line was used. To cana.ce nuclear transportation, a Cas9 protein fused with two NLS peptides (sNLS–Cas9- sNI S) was used to form the RNP complexes. As shown in Figure 6C, SMOF NPs exhibited a statistically higher (1.3-fold) geneknockout efficiency than Lipo 2000.

Furthermore, to achieve precise genotic editing by co-delivery of RNP and a donor DNA template, gene correction or insertion can be achieved through the homology-directed repair (HDR) pathway[25]. RNP and a dono snigle-stranded oligonucleotide DNA (ssODN) were loaded into SMOF NPs, and the precise genome-editing efficiency was studied using BFP-expressing HEK293 cells. Precise gene editing will lead to the replacement of three nucleotides in the genome, thereby convirting BFP to GFP. The precise genome-editing efficiency was evaluated by the percentage of GFP-positive cells. As shown in Figure 6D, SMOF NPs showed a statistically higher (1.4-fold) gene-correction efficiency than Lipo 2000. These studies indicate that SMOF NPs are suitable for the delivery of CRISPR genome-editing machineries.

To study the biocompatibility of SMOF NPs, the cells were treated with SMOF NPs, and the cell viability was investigated by an MTT assay (Figure 6E and Figure S6). SMOF NPs did not induce significant cytotoxicity in HEK cells with concentrations up to 200  $\mu$ g/ml, which was at least 9.2-fold of the concentration used for our studies. Similar to previous reports, Lipo

2000 exhibited significant cytotoxicity (with 30% cell death) at the dosage indicated in the user's manual (i.e., 0.5  $\mu$ l/well in a 96-well plate, corresponding to 5  $\mu$ g/ml Lipo 2000) [32].



Figure 6. Delivery efficiency of nucleic acids and CRISPR-Cas9 genome-editing machineries by SMOF NPs. Transfection efficiency of the (A) DNA- and (B) mRNA-loaded SMOF NPs in HEK293, HCT116, NHDF, and RAW264.7 cells. (C) Genome-editing efficiency of RNP-loaded SMOF NPs in GFP-expressing HEK 293 cells. (D) Precise gene-correction efficiency of RNP+ssODN co-loaded SMOF NPs in BFP-expressing HEK 293 cells.

The precise gene-correction efficiency of RNP+ssODN repair template converting the BFP to the GFP was assayed by flow cytometry for gain of GFP fluorescence. NS: not significant; \*: p < 0.05; \*\*: p < 0.01; \*\*\*: p < 0.005; n = 3. (E) Viability of HEK293 cells treated with Lipo 2000 and SMOF NPs with different concentrations. NS: not significant; \*\*\*: p < 0.001; n = 5.

The genome editing efficiency of RNP-loaded SMOF NPs was further evaluated in vivo via subretinal injection in transgenic Ai14 mice (Figure. 7). All the cells of Ai14 mouse contain a CAGGS promoter and a loxP-flanked stop cassette (three repeats of the SV40 polyA sequence) that prevents expression of the tdTomato fluorescent protein, at the Rosa26 locus. The gain-offunction fluorescent signal in modified cells provides a robust and quantitative readout of genome editing at the stop cassette [27, 33, 34]. RNP (at study the excision of the SV40 polyA blocks can induce tdTomato expression (Figure. 7.1). The genome editing efficiency of the RNP-loaded SMOF NPs can be easily monite ed unrough fluorescence imaging. We studied the genome editing efficiency within the useted retinal pigmented epithelium (RPE) of Ail 4 mice, as RPE abnormality can cause a variety of eye diseases (e.g., retinal degeneration, blindness) [21]. SMOF NPs we e <sup>1</sup>ecorated with ATRA (i.e., SMOF-ATRA). Mice were subretinally injected with SMC-ATRA NPs loaded with RNPs targeting the Ail4 stop cassette (i.e., Ail4 RNP 515'OF) and SMOF-ATRA NPs loaded with negative control RNPs (i.e., negative control SM OF) (Figure. 7B). Thirteen or fourteen days post-injection, the entire RPE tissue was separated from the enucleated eye and flat-mounted to assess genome editing via CLSM (Figure. 7C and Figure S8). As shown in Figure 7C and D, strong tdTomato signals were visualized in the eyes injected with the RNP-loaded SMOF-ATRA targeting the Ail4 stop cassette, while little tdTomato signal was found in eyes treated with negative control SMOF-ATRA (i.e., SMOF-ATRA encapsulating RNP with negative control sgRNA), indicating successful delivery of RNP and robust in vivo genome editing induced by SMOF-ATRA.

The biocompatibility of SMOF after subretinal injection was evaluated by electroretinography (ERG) of the retina. ERG evaluates the electronic response of the eye, and any damage to the RPE or retina result in alternations in ERG recording [35-37]. PBS and Ail 4 RNP-loaded SMOF-ATRA were injected to the eyes of C57BI/6 mice. As shown in Figure S9, the a-wave and b-wave amplitude of SMOF injected eyes (131.04 ± 37.16  $\mu$ V, P= 0.713) were similar to the PBS injected eyes (128.1 ± 22.6  $\mu$ V, P= 0.643) 14 days post-injection. The c-wave amplitude were also not statistically significant when SMOF (329.4 ± 95.2  $\mu$ V, P= 0.664) was compared with the PBS control (274.2 ± 58.44  $\mu$ V, P = 0.855). I is there were no significant difference in ERG responses between the SMOF injected and PBS injected eyes, these findings suggest that SMOF is either nontoxic or the toxicity is negligible to the retinal/RPE cells.



Figure 7. SMOF NPs induced efficient genome editing *in vivo* in Ai14 mice via local administration. (A) The tdTomato locus in the Ai14 reporter mouse. A stop cassette containing 3 Ai14 sgRNA target sites prevents downstream tdTomato expression. RNP guided

excision of the stop cassette results in tdTomato expression. (**B**) Illustration of SMOF NP subretinal injection targeting the RPE tissue. (**C**) Representative images of tdTomato+ signal (red) 13 or 14 days after subretinal SMOF-ATRA injection. The whole RPE layer was outlined with a white dotted line. C1: RPE floret of Ai14 mouse subretinally injected with PBS. C2: RPE floret of Ai14 mouse subretinally injected with negative control SMOF-ATRA (SMOF-ATRA encapsulating RNP with negative control sgRNA). C3: RPE floret of Ai14 mouse eye subretinally injected with SMOF-ATRA encapsulating RNP targeting the Ai14 stop cassette (i.e., Ai14 RNP SMOF), and C4: zoom-in image (20X magnification) of genome-edited RPE tissue induced by RNP-loaded SMOF-ATRA. (**D**) Genome editing efficiency as quantified by percent of the area of whole RPE tissue with tdTomato+ signals. NS: not significant, \*: p<0.05.

#### 4. Conclusion

In conclusion, we have demonstrated a novel and versatile silica-metal-organic framework hybrid NP for the efficient delivery of hydrophilic payloads. The protonation of the imidazole component in the SMOF N network promoted the release and endosomal escape of the payload. SMOF NPs can encapsulate hydrophilic payloads with both a high loading content (17 wt% for small networks and about 9.5 wt% for nucleic acids/RNP) and high loading efficiency (highe than 90%). The biocompatible and stable SMOF NPs can efficiently deliver a diverse range of hydrophilic payloads, including hydrophilic drug DOX·HCl, nucleic acids, and CRISPR-Cas9 genome-editing machineries. Furthermore, ATRA-conjugated SMOF NP also induced efficient genome editing in mouse retinal pigmented epithelium via subretinal injection, indicating that it is a highly promising nanoplatform for many biomedical applications.

#### Acknowledgements

26

We acknowledge the generous financial support from the National Institute for Health

(1-UG3-NS-111688-01, R01HL129785, R01HL143469, and R01EY024995).

## Keywords

Silica • metal-organic framework • hybrid nanoparticle • gene delivery • genome editing machinery delivery

## References

 [1] E. Blanco, H. Shen, M. Ferrari, Principles of nanoparticle design for overcoming biological barriers to drug delivery, Nat. Biotechnol., 33 (2015) 941.

[2] A.A. Manzoor, L.H. Lindner, C.D. Landon, J.-Y. Park, A.J. Simnick, M.R. Dreher, S. Das, G. Hanna, W. Park, A. Chilkoti, Overcoming limitations in nanoparticle drug delivery: triggered, intravacru.ar release to improve drug penetration into tumors, Cancer Res, 72 (2012) 5566-5575.

[3] H. Yin, R.L. Kanasty, A.A. Eltoukhy, A.J. Vegas, J.R. Dorkin, D.G. Anderson, Non-viral vectors for gene-based theory py Nat. Rev. Genet., 15 (2014) 541-555.
[4] C. Liu, L. Zhang, H. Liu, K. Cheng, Celivery strategies of the CRISPR-Cas9 gene-editing system for theraperitic applications, J. Controlled Release, 266 (2017) 17-26.

[5] F. Scaletti, J. Hardie, Y.-W Lee, D.C. Luther, M. Ray, V.M. Rotello, Protein delivery into cells using incuganic nanoparticle–protein supramolecular assemblies, Chemical Society Reviews, 47 (2018) 3421-3432.

[6] Y. Piao, H.P. Bei, A. Tom Y. Yang, Q. Zhang, M. Yang, X. Zhao, Calcium Phosphate Nanopart cle-Based Systems for Therapeutic Delivery, in: Theranostic Bionano.materials, Elsevier, 2019, pp. 147-164.

[7] I.I. Slowing, J.L. Vivero-Escoto, C.-W. Wu, V.S.Y. Lin, Mesoporous silica nanoparticles as controlled release drug delivery and gene transfection carriers, Adv. Drug Delivery Rev., 60 (2008) 1278-1288.

[8] J.E. Lee, N. Lee, T. Kim, J. Kim, T. Hyeon, Multifunctional mesoporous silica nanocomposite nanoparticles for theranostic applications, Acc. Chem. Res., 44 (2011) 893-902.

[9] Y.-S. Lin, K.R. Hurley, C.L. Haynes, Critical considerations in the biomedical use of mesoporous silica nanoparticles, The journal of physical chemistry letters, 3 (2012) 364-374.

[10] D. Wang, Z. Xu, Z. Chen, X. Liu, C. Hou, X. Zhang, H. Zhang, Fabrication of single-hole glutathione-responsive degradable hollow silica nanoparticles for drug delivery, ACS Appl. Mater. Interfaces, 6 (2014) 12600-12608.

[11] P. Yuan, H. Zhang, L. Qian, X. Mao, S. Du, C. Yu, B. Peng, S.Q. Yao, Intracellular Delivery of Functional Native Antibodies under Hypoxic Conditions by Using a Biodegradable Silica Nanoquencher, Angew. Chem., 129 (2017) 12655-12659.

[12] E.A. Prasetyanto, A. Bertucci, D. Septiadi, R. Corradini, P. Castro-Hartmann, L. De Cola, Breakable hybrid organosilica nanocapsules for protein delivery, Angew. Chem. Int. Ed., 55 (2016) 3323-3327.

[13] P. Horcajada, T. Chalati, C. Serre, B. Gillet, C. Sebrie, T. Baati, J.F. Eubank, D. Heurtaux, P. Clayette, C. Kreuz, Porous metal–organic-framework nanoscale carriers as a potential platform for drug delivery and imaging, Nature materials, 9 (2010) 172.

[14] J. Della Rocca, D. Liu, W. Lin, Nanoscale metal-organic frameworks for biomedical imaging and drug delivery, Acc. Chen . Res., 44 (2011) 957-968.
[15] M.X. Wu, Y.W. Yang, Metal-organic framework (MOF)-based drug/cargo delivery and cancer therapy, Adv. Mater , 29 (2017) 1606134.

[16] C. Doonan, R. Ricco, K. Liang, D. Bradshaw, P. Falcaro, Metal–organic frameworks at the biointerface: synthetic strategies and applications, Acc. Chem. Res., 50 (2017) 1423-1432.

[17] P. Horcajada, R. Gref, T. Baati, P.K. Allan, G. Maurin, P. Couvreur, G. Ferey, R.E. Morris, C. Serre, Metal–organ a frameworks in biomedicine, Chem. Rev., 112 (2011) 1232-1268.

[18] S.K. Alsaiari, S. Patil, M. Aiyami, K. Alamoudi, f. Aleisa, J. Merzaban, M. Li, N.M. Khashab, Endosomai Escape and Delivery of CRISPR/Cas9 Genome Editing Machinery Enabled by Manoscale Zeolitic Imidazolate Framework, J. Am. Chem. Soc., (2017).

[19] T.-T. Chen, J.-T. Y, Y.-Y. Zhao, X. Chu, Biomineralized metal–organic framework nanoparticles enable intracellular delivery and endo-lysosomal release of native active proteins, J. Am. Chem. Soc., 140 (2018) 9912-9920.
[20] A. Poddar, J.J. Conesa, K. Liang, S. Dhakal, P. Reineck, G. Bryant, E. Pereiro, R. Ricco, H. Amenitsch, C. Doonan, Encapsulation, Visualization and Expression of Genes with Biomimetically Mineralized Zeolitic Imidazolate Framework-8 (ZIF-8), Small, (2019) 1902268.

[21] W. Berger, B. Kloeckener-Gruissem, J. Neidhardt, The molecular basis of human retinal and vitreoretinal diseases, Prog Retin Eye Res, 29 (2010) 335-375.

[22] D. Sun, B. Sahu, S. Gao, R.M. Schur, A.M. Vaidya, A. Maeda, K. Palczewski, Z.-R. Lu, Targeted multifunctional lipid ECO plasmid DNA nanoparticles as

efficient non-viral gene therapy for leber's congenital amaurosis, Molecular Therapy-Nucleic Acids, 7 (2017) 42-52.

[23] A. Carlson, D. Bok, Promotion of the release of 11-cis-retinal from cultured retinal pigment epithelium by interphotoreceptor retinoid-binding protein, Biochemistry-us, 31 (1992) 9056-9062.

[24] P. Yuan, X. Mao, K.C. Chong, J. Fu, S. Pan, S. Wu, C. Yu, S.Q. Yao,
Simultaneous Imaging of Endogenous Survivin mRNA and On-Demand Drug
Release in Live Cells by Using a Mesoporous Silica Nanoquencher, small, 13
(2017) 1700569.

[25] J. Carlson-Stevermer, A.A. Abdeen, L. Kohlenberg, M. Goedland, K. Molugu, M. Lou, K. Saha, Assembly of CRISPR ribonucleoproteins with biotinylated oligonucleotides via an RNA aptamer for procise gene editing, Nat. Commun., 8 (2017) 1711.

[26] C.D. Richardson, G.J. Ray, M.A. DeWitt, G.L. Curro, J.E. Corn, Enhancing homology-directed genome editing by catalytically active and inactive CRISPR-Cas9 using asymmetric donor DNA, Nat. Biotechnol., 34 (2016) 339.

[27] G. Chen, A.A. Abdeen, Y. Wang, P.K. Shahi, S. Robertson, R. Xie, M. Suzuki, B.R. Pattnaik, K. Saha, S. Gong, A biodegrar. able nanocapsule delivers a Cas9 ribonucleoprotein complex for in vivo genuine editing, Nature nanotechnology, 14 (2019) 974-980.

[28] M. Larguinho, H.M. Santos. G. Duria, H. Scholz, P.V. Baptista, J.L. Capelo, Development of a fast and efficient ultrasonic-based strategy for DNA fragmentation, Talanta, 81 (201/J) 381-886.

[29] N.A. Pchelintsev, P.D. A Jans, D.M. Nelson, Critical parameters for efficient sonication and improved chromatin immunoprecipitation of high molecular weight proteins, PloS one, 11 (2016) e0148023.

[30] J.A. Doudna, E. Charpentier, The new frontier of genome engineering with CRISPR-Cas9, Science, 346 (2014) 1258096.

[31] L. Cong, F.A. Ran D. Cox, S. Lin, R. Barretto, N. Habib, P.D. Hsu, X. Wu, W. Jiang, L. Marraffini, Multiplex genome engineering using CRISPR/Cas systems, Science, (2013) 1231143.

[32] Y. Wang, B. Ma, A.A. Abdeen, G. Chen, R. Xie, K. Saha, S. Gong, Versatile Redox-Responsive Polyplexes for the Delivery of Plasmid DNA, Messenger RNA, and CRISPR-Cas9 Genome-Editing Machinery, ACS Appl. Mater. Interfaces, 10 (2018) 31915–31927.

[33] B.T. Staahl, M. Benekareddy, C. Coulon-Bainier, A.A. Banfal, S.N. Floor, J.K. Sabo, C. Urnes, G.A. Munares, A. Ghosh, J.A. Doudna, Efficient genome editing in the mouse brain by local delivery of engineered Cas9 ribonucleoprotein complexes, Nat. Biotechnol., 35 (2017) 431.

[34] L. Madisen, T.A. Zwingman, S.M. Sunkin, S.W. Oh, H.A. Zariwala, H. Gu, L.L. Ng, R.D. Palmiter, M.J. Hawrylycz, A.R. Jones, A robust and high-throughput Cre reporting and characterization system for the whole mouse brain, Nat. Neurosci., 13 (2010) 133.

[35] T.Y.Y. Lai, W.-M. Chan, D.S.C. Lam, Transient reduction in retinal function revealed by multifocal electroretinogram after photodynamic therapy, Am J Ophthalmol, 137 (2004) 826-833.

[36] S.G. Jacobson, G.M. Acland, G.D. Aguirre, T.S. Aleman, S.B. Schwartz, A.V. Cideciyan, C.J. Zeiss, A.M. Komaromy, S. Kaushal, A.J. Roman, Safety of recombinant adeno-associated virus type 2–RPE65 vector delivered by ocular subretinal injection, Mol. Ther., 13 (2006) 1074-1084

[37] S. Becker, H. Wang, G.J. Stoddard, M.E. Hartnett, Effect of subretinal injection on retinal structure and function in a rat over n-induced retinopathy model, Mol Vis, 23 (2017) 832.



## **Graphical Abstract**



Figure 1. Design and synthesis of SMOF NPs. (A) Illustration of the SMOF NP for the delivery of various hydrophilic payloads such as hydrophilic small molecular drugs, DNA, mRNA, proteins, and a convinction thereof (e.g., Cas9/sgRNA (RNP) and RNP+ssODN). (B) Synthesis of SMOF NPs via a water-in-oil emulsion method. (C) Schematic illustration of the intracellular trafficking pathways of SMOF NPs. SMOF NP: silica–metal–organic framework hybrid nanoparticle; 2-MIM: 2-methylimidazole; PEG: polyethylene glycol; TEOS: tetraethyl orthosilicate; TESPIC: N-(3-(triethoxysilyl)propyl)-1H-imidazole-2-carboxamide; APTES: (3-aminopropyl)triethoxysilane.



Figure 2. Optimization of the DNA-los ded SMOF NP formulation using HEK 293 cells. (A) Optimization of the feed weight rails of the payload over the SMOF reactants, feed weight ratio of the silica reactants in the MOF reactant, and the emulsification method. (B) Optimization of the moler ratio of the three silica reactants TEOS/APTES/TESPIC. The optimal SMOF NP form atton is highlighted by a black bar. NS: not significant; \*: p < 0.05; \*\*: p < 0.01; \*\*\*: p < 0.001; \*\*\*\*: p < 0.0001; n = 3.



Figure 3. Characterization of SMOF NPs. (A) TEM and (B) SEM micrographs of SMOF NPs. (C) Size distribution of SMOF NPs measured by DLS. (D) Powder XRD spectra of SMOF NP, pure MOF NP, and pure silica NP synthesized via the water-in-oil emulsion method.



## Figure 4. Intracellular trafficking of RNP-loaded SNI-)F NPs by CLSM. Colocalization of

RNP and endo/lysosomes was studied at 0.5 h 2', and 4 h post-treatment. Scale bar: 50 µm.

34



Figure 5. Delivery Efficiency of a hydrophilic drug by SMOF NPs. (A) Flow cytometry analysis on HEK293 cells treated with free DOX·HCl (5  $\mu$ g/ml) and DOX·HCl-loaded SMOF NPs (DOX·HCl concentration, 5  $\mu$ g/ml) or medium alone (concentration, for 2 h. (B) Cytotoxicity of empty SMOF NPs, free DOX·HCl and DOX·HCl-loaded SMOF NPs at different DOX·HCl concentrations (i.e., 6 and 12  $\mu$ g/ml) after co-incubation with HEK293 cells for 48 h.



Figure 6. Delivery efficiency of nucleic acids and CRISPR-Cas9 genome-editing machineries by SMCF Product Transfection efficiency of the (A) DNA- and (B) mRNA-loaded SMOF NPs in HEK2>3, HCT116, NHDF, and RAW264.7 cells. (C) Genome-editing efficiency of RNP-loaded SMOF NPs in GFP-expressing HEK 293 cells. (D) Precise gene-correction efficiency of RNP+ssODN co-loaded SMOF NPs in BFP-expressing HEK 293 cells. The precise gene-correction efficiency of RNP+ssODN repair template converting the BFP to the GFP was assayed by flow cytometry for gain of GFP fluorescence. NS: not significant; \*: p < 0.05; \*\*: p < 0.01; \*\*\*: p < 0.005; n = 3. (E) Viability of HEK293 cells treated with Lipo 2000 and SMOF NPs with different concentrations. NS: not significant; \*\*\*: p < 0.001; n = 5.



Figure 7. SMOF NPs induced efficient genome chcing in vivo in Ai14 mice via local administration. (A) The tdTomato locus is for Ai14 reporter mouse. A stop cassette containing 3 Ai14 sgRNA target sites prepers downstream tdTomato expression. RNP guided excision of the stop cassette results in "dTomato expression. (B) Illustration of SMOF NP subretinal injection targeting the PPE fissue. (C) Representative images of tdTomato+ signal (red) 13 or 14 days after subreticed SMOF-ATRA injection. The whole RPE layer was outlined with a white dotted line. C1: PPE floret of Ai14 mouse subretinally injected with PBS. C2: RPE floret of Ai14 mouse subretinally injected with negative control SMOF-ATRA (SMOF-ATRA encapsulating RNP with negative control sgRNA). C3: RPE floret of Ai14 mouse eye subretinally injected with SMOF-ATRA encapsulating RNP targeting the Ai14 stop cassette (i.e., Ai14 RNP SMOF), and C4: zoom-in image (20X magnification) of genome-edited RPE tissue induced by RNP-loaded SMOF-ATRA. (D) Genome editing efficiency as quantified by percent of the area of whole RPE tissue with tdTomato+ signals. NS: not significant, \*: p<0.05.

 Table 1. Summary of loading content and loading efficiency of different payloads by SMOF

 NPs.

Payload	Loading Content (wt%)	Loading Efficiency (%)
Doxorubic in hydrochloride	17	92
DNA	9.5	94
mRNA	9.2	91
RNP	9.8	97
RNP+ssODN	9.5	94

### A pH-Responsive Silica–Metal–Organic Framework Hybrid Nanoparticle for the Delivery of Hydrophilic Drugs, Nucleic Acids, and CRISPR-Cas9 Genome-Editing Machineries

Yuyuan Wang<sup>1, 2</sup>, Pawan K. Shahi<sup>3</sup>, Ruosen Xie<sup>1, 2</sup>, Huilong Zhang <sup>4</sup>, Amr A. Abdeen<sup>2</sup>, Nisakorn Yodsanit<sup>2, 5</sup>, Zhenqiang Ma<sup>4</sup>, Krishanu Saha<sup>2, 5</sup>, Bikash Pattnaik<sup>3, 6</sup> and Shaoqin Gong<sup>1, 2, 5, 6, 7 \*</sup>

- 8. Department of Materials Science and Engineering, University of Wisconsin–Madison, Madison, WI 53715, USA
- 9. Wisconsin Institute for Discovery, University of Wisconsin–Madison, Madison, WI 53715, USA
- 10. Department of Pediatrics, University of Wisconsin Madison, Madison, WI 53706, USA.
- 11. Department of Electrical and Computer Engineering, University of Wisconsin-Madison, Madison, WI 53706, USA
- 12. Department of Biomedical Engineering, University of W.scorsin-Madison, Madison, WI 53715, USA
- 13. McPherson Eye Research Institute, University of Victorian Madison, Madison, WI 53705, USA
- 14. Department of Chemistry, University of Wiscon: n-Madison, Madison, WI 53715, USA
- \*: Correspondence should be addressed to SG (s'.av.cingong@wisc.edu)

#### **CReDiT Author Statement**

Yuyuan Wang: Conceptualization, M. bodology, Validation, Formal analysis, Investigation,

Data Curation, Writing-Original Dratt, Writing-Review & Editing, Visualization

Pawan K. Sashi: Methodology, Data Curation, Formal analysis, Investigation, Writing-

Review & Editing

Ruosen Xie: Methodology, Validation, Investigation, Data Curation, Writing - Original Draft

Huilong Zhang: Formal analysis, Investigation, Data Curation

Amr A Abdeen: Formal analysis, Investigation

Nisakorn Yodsanit: Formal analysis, Investigation

Zhenqiang Ma: Investigation, Resources, Supervision

Krishanu Saha: Investigation

**Bikash Pattnaik**: Methodology, Validation, Formal analysis, Resources, Writing-Review & Editing

**Shaoqin Gong**: Conceptualization, Methodology, Investigation, Resources, Writing-Original Draft, Writing-Review & Editing, Visualization, Supervision, Project administration, Funding acquisition

Journal of the second





Figure 2



Figure 3



Payload: Cas9/sgRNA-ATTO550 RNP Cell line: HEK293 cells



Figure 5



