Redox-active iron-containing polymers: synthesis and anionic polymerization of a *C*-ferrocenyl-substituted phosphaalkene

Kevin J. T. Noonan, Brian O. Patrick and Derek P. Gates*

Received (in Cambridge, UK) 3rd April 2007, Accepted 25th May 2007 First published as an Advance Article on the web 21st June 2007 DOI: 10.1039/b704967f

The addition polymerization of a ferrocenyl-substituted P=C bond leads to new redox-active polymers with functional ferrocene and phosphine moieties.

Macromolecules containing transition metals are known to possess unique redox, magnetic, optical and electronic properties and are attractive for use as ceramic precursors and catalyst supports.¹ The ferrocenyl moiety has played an integral role in the growth of metal-containing polymer science. Macromolecules are known where ferrocene is incorporated into the main chain, side-chain and even into dendrimers.² The earliest ferrocene-containing polymers were prepared from the addition polymerization of the C=C bond in vinyl ferrocene.^{3,4}

We have recently reported that P=C bonds, like C=C bonds, can be polymerized to afford macromolecules containing functional phosphine moieties.⁵ Interestingly, copolymerizations of phosphaalkenes and olefins afford either random copolymers or block copolymers depending on the method of initiation.^{6,7} The chemical functionality of poly(methylenephosphine)s is demonstrated by their effectiveness as polymeric ligands in Pd-catalyzed reactions. The preparation of macromolecules composed of both phosphines and ferrocenes is particularly attractive due to the prospect of accessing bimetallic polymers with interesting electronic, magnetic or catalytic properties. Primarily a consequence of the lack of effective synthetic routes to phosphine-ferrocene hybrid polymers, only a few examples have been reported.8-10 Herein we describe the synthesis and addition polymerization of C-ferrocenyl phosphaalkene 1 to afford a new redox active bifunctional poly(methylenephosphine) (2).

known,¹⁴ however very few non-heteroatom-substituted P=C systems have been reported. A rare example, 'BuP=CHFc, was detected in solution but dimerized upon attempted isolation.^{14e} For polymerization studies, isolable monomers with no heteroatoms directly attached to the P=C bond are desired to avoid possible side reactions during initiation. Consequently, methods to access new ferrocene-substituted phosphaalkenes are needed. The phospha-Peterson reaction is a general and convenient route to phosphaalkenes.^{15,16} This convenient reaction involves the condensation of a silyl phosphide Li[RP(SiMe₃)] with a ketone and affords phosphaalkenes with a variety of substituents provided that suitably bulky substituents are employed to protect the P=C bond.

The precursor to *C*-ferrocenyl phosphaalkene (1), benzoylferrocene, was prepared according to a modified literature procedure.¹⁷ A THF solution of *in situ* prepared Li[MesP(SiMe₃)] was treated with benzoylferrocene at 60 °C. Analysis of an aliquot removed from the deep red reaction mixture using ³¹P NMR spectroscopy revealed that Li[MesP(SiMe₃)] (δ –187) had been completely consumed. Two new signals were observed downfield at 218 and 211 ppm (70 : 30 ratio) which are consistent with the formation of *E*/*Z*-1.† Crystals suitable for X-ray diffraction were obtained from the slow evaporation of a hexanes solution of *E*/*Z*-1.‡ The molecular structure of the *C*-ferrocenyl-substituted phosphaalkene is shown in Fig. 1 and, interestingly, the Fc substituent is *cis* to the bulky P-Mes substituent (*i.e. Z*-1). The ³¹P NMR spectrum of a C₆D₆ solution of the crystals of *Z*-1 shows signals consistent with



Although metalla-phosphaalkenes are quite common,^{11–13} the target monomers, ferrocenyl-substituted phosphaalkenes, are not widely available. Becker-type phosphaalkenes [*i.e.* RP=C(OSiMe₃)R'] possessing C–Fc and P–Fc substituents are



Fig. 1 Molecular structure of *Z*-1 (hydrogen atoms omitted for clarity). Thermal ellipsoids at 30% probability. Selected bond lengths (Å) and angles (°): P1–C1 1.697(2), P(1)–C(18) 1.842(2), C(1)–C(2) 1.512(2), C(1)–C(8) 1.468(2); C(8)–C(1)–C(2) 114.95(13), C(8)–C(1)–P(1) 130.69(11), C(2)–C(1)–P(1) 114.16(11), C(1)–P(1)–C(18) 107.31(7).

Department of Chemistry, University of British Columbia, 2036 Main Mall, Vancouver, BC, Canada V6T 1Z1. E-mail: dgates@chem.ubc.ca; Fax: (+1) 604-822-2847; Tel: (+1) 604-822-9117

both *E*-1 and *Z*-1 isomers (*ca.* 85 : 15 ratio) and suggests facile *E*, *Z* isomerization in solution. Selective ¹H NMR NOE experiments provided confirmation that the major isomer in solution is *Z*-1. In particular, irradiating at the resonance frequency of the *ortho* CH₃ groups on the mesityl ring (δ 2.30) leads to enhancement of signals assigned to the *ortho* hydrogens of the substituted Cp ring (δ 4.61). This signal enhancement is consistent with the Mes and Fc substituents being *cis* configured and therefore the *Z*-1 isomer was concluded to be the major isomer in solution.

 $MesP(SiMe_3)_2 + \frac{O}{Fc} Ph \xrightarrow{1.MeLi}_{2.SiMe_3Cl} Ph \xrightarrow{P} C Fc$

The molecular structure of Z-1 is shown in Fig. 1. The P=C bond length in 1 (1.697(2) Å) is in the long end of the range typical for phosphaalkenes (1.61–1.71 Å), however is similar to the P=Cbond length in MesP=CPh₂ (1.692(3) Å).¹⁸ Interestingly, the *cis*-Fc substituent shows a larger angle to the P=C bond than the ideal sp² angle ($\angle P=C-C_{Fc}$ 130.69(11)°) and is greater than the typical *cis* aryl substituent of P-mesityl phosphaalkenes (∠P=C-C_{cis} 125-128°).¹⁶ We speculate that this is a consequence of increased steric repulsion between the cis configured Fc and Mes moieties in Z-1. Remarkably, the angle between the best planes of the C_5H_4 moiety and the P=C bond is just 13.2(1)°. For comparison, the analogous angle in the only other crystallographically characterized *C*-ferrocenyl phosphaalkene (Me₃SiP=C(OSiMe₃)Fc) is 36.6° , ^{14d} whilst that in MesP=CPh₂ is 42.9°.^{18,19} This data suggests that significant π -conjugation is present between the Fc substituent and the P=C bond in Z-1. Additional support for π -conjugation in Z-1 is provided by the shortening of C(1)–C(8) bond (1.468(2) Å) with respect to the typical C-C single bond length which is 1.54 Å and by the intense red colour of 1 compared with pale yellow MesP=CPh₂.

To determine whether anionic initiation of a C-ferrocenyl phosphaalkene was feasible, monomer 1 was treated with nBuLi (1 equiv) in glyme (1,2-dimethoxyethane). The ³¹P NMR spectrum of the reaction mixture showed only a singlet at -18.7 ppm which is consistent with the formation of Li[Mes(Bu)PC(Fc)Ph]. Once the feasibility of anionic initiation had been demonstrated, a solution of monomer 1 in 1,2-dimethoxyethane (glyme) was treated with nBuLi (5 mol%) as the anionic initiator.§ The progress of the polymerization was monitored by ³¹P NMR spectroscopy and, after seven days, 50-60% of monomer 1 had been cleanly converted to polymer 2 (δ -5 br). Due to facile isomerization in solution, the isomer ratio in monomer E/Z-1 (85 : 15) does not change during the polymerization reaction. The polymerization was terminated by quenching with methanol and polymer 2 was separated from 1 by reprecipitation from THF into methanol $(\times 4)$. The golden coloured polymer was analyzed by triple detection GPC and an absolute number average molecular weight $(M_{\rm n})$ was determined to be 9500 with a polydispersity index (PDI) of 1.21. The identical experiment was repeated and the same $M_{\rm p}$ was achieved with a PDI of 1.18. Further studies are underway to ascertain whether this polymerization may be conducted in a living fashion.

In order to investigate the electronic properties of 1 and 2, both were analyzed by UV-Vis spectroscopy (Fig. 2). Previous studies on phosphaalkenes have demonstrated that P=C bonds are



Fig. 2 UV/Vis spectra of monomer 1 (top) and polymer 2 (bottom) (0.1 mM in toluene).

capable of electronic communication through π conjugation.²⁰ The deep red solution of 1 exhibited two broad absorbances at $\lambda_{max} = 512$ and 331 nm which are assigned to the d-d transition of the ferrocenyl moiety and the π - π * transition for the P=C bond, respectively. Interestingly, the absorbance maximum at 512 nm is significantly red-shifted when compared to that for vinylferrocene ($\lambda_{max} = 442$ nm) and ferrocene ($\lambda_{max} = 440$ nm).^{4,21} The dramatic bathochromic shift is most likely attributable to a favourable electronic interaction between the ferrocene group and the P=C bond. The second transition at 331 nm, assigned to the π - π * transition of the P=C bond, is similar to that observed for MesP=CPh₂ ($\lambda_{max} = 324$ nm).²² In contrast, the gold coloured macromolecule **2** exhibits only a weak transition at 448 nm, which is very similar to the d-d transition for ferrocene (440 nm).

The electrochemical properties of poly(methylenephosphine) **2** were analyzed by cyclic voltammetry. The observed reversible one electron oxidation of **2** is consistent with the expected ferrocene–ferrocenium couple. The detection of a single wave suggests that the Fc moieties are electronically isolated; analogous to the case of poly(vinylferrocene). The half-cell potential (*vs.* SCE) for polymer **2** is ($\Delta E_{1/2} = 0.41$ V) is slightly lower than that for poly(vinylferrocene) ($\Delta E_{1/2} = 0.44 - 0.48$ V).²³ For comparison, FcCH₂PPh₂, a possible model compound for polymer **2**, similarly exhibits a reversible oxidation slightly lower than that for ferrocene ($\Delta E = -0.04$ V).²⁴

In summary, a phosphaalkene analogue of vinyl ferrocene has been prepared and polymerized anionically to afford new bifunctional redox active polymers. This development opens the door to the synthesis of bimetallic polymers possessing both Fc moieties and phosphine-metal complexes which may have interesting optoelectronic, magnetic and preceramic properties.

Notes and references

† Synthesis of MesP=C(Fc)Ph (1): To a stirred solution of MesP(SiMe₃)₂ (5.03 g, 17 mmol) in THF was added MeLi in Et₂O (12.2 mL, 1.4 M, 17 mmol) at 25 °C. The reaction mixture was heated to 60 °C for *ca*. 1 h and analysis of an aliquot by ³¹P NMR spectroscopy suggested total conversion to MesP(SiMe₃)Li (δ –187). Subsequently, benzoylferrocene (4.94 g, 17 mmol) was added and the reaction mixture was stirred at 60 °C for *ca*. 30 min. The ³¹P NMR spectrum showed signals at 218 and 211 ppm (70 : 30 ratio) assigned to *Z*-1 and *E*-1, respectively. To the solution was added Me₃SiCl (2.15 mL, 17 mmol) to quench the LiOSiMe₃. The volatiles were removed *in vacuo*, the residue was extracted into hexanes (3 × 50 mL),

Published on 21 June 2007. Downloaded by University of Warsaw on 28/10/2014 13:43:57.

filtered through Celite, and the solvent removed *in vacuo*. Single crystals of **1** (4.16 g, 58%) were obtained from slow evaporation of a hexanes solution of the crude product. ³¹P NMR (C₆D₆) δ (ppm): 218 (*Z*, 85%), 211 (*E*, 15%). ¹H NMR (CD₂Cl₂) δ (ppm): 7.5 (m, 5H, *E-o,m,p*-Ph), 7.10 (m, 5H, *Z-o,m,p*-Ph), 6.98 (s, 2H, *E-m*-Mes), 6.69 (s, 2H, *Z-m*-Mes), 4.61 (t, 2H, ²J_{H-H} = 1.2 Hz, *Z-o*-Fc), 4.45 (s, 2H, *Z-m*-Fc), 4.23 (m, 5H, *Z*-*O*-Fc, 2H, *E-m*-Fc, 4.10 (s, 5H, *E-Cp*-Fc), 3.79 (s, 2H, *E-o*-Fc), 2.44 (s, 6H, *E-o*-CH₃), 2.37 (s, 3H, *E-p*-CH₃), 2.30 (s, 6H, *Z-o*-CH₃), 2.17 (s, 3H, *Z-p*-CH₃). MS (EI, 70 eV): 424 [8, 36; M⁺]. UV/Vis (C₇H₉): $\lambda_{max}/mm (z/M^{-1} cm^{-1}) = 331 (4600), 512 (930). Anal. Calc. for C₂₆H₂₅PFe: C, 73.60; H, 5.94. Found: C, 73.30; H, 6.04%.$

‡ Crystal data for 1: C₂₆H₂₅PFe, M = 424.30, triclinic, space group $P\bar{1}$ (no. 2), a = 8.0754(8), b = 8.4767(7), c = 16.382(2) Å, $\alpha = 101.647(3)$, $\beta = 96.033(4)$, $\gamma = 96.270(4)^{\circ}$, U = 2547.2(5) Å³, T = 173(2) K, Z = 2, μ (Mo-K α) = 7.79 cm⁻¹, $D_c = 1.302$ g cm⁻³, 23518 reflections measured, 5083 unique reflections ($R_{int} = 0.032$) which were used in all calculations. The final $R_1(F)$ was 0.034, wR_2 (on F_2) was 0.095. CCDC 642679. For crystallographic data in CIF or other electronic format see DOI: 10.1039/ b704967f

§ Synthesis of [P(Mes)C(Fc)(Ph)]_n (2): A typical polymerization procedure is described. To a stirred solution of MesP=CPh(Fc) (1.00 g, 2.3 mmol) at room temperature in glyme (7 mL) was added *n*BuLi (1.5 M, 80 µL, 0.12 mmol). The reaction mixture was stirred at room temperature and monitored by ³¹P NMR spectroscopy. The growth of a broad signal in the ³¹P NMR spectrum was observed over 7 days and, subsequently, the reaction mixture was removed from the glovebox, quenched and precipitated using methanol (3 × 100 mL). Residual solvent was removed *in vacuo*. Yield = 250 mg (25%). ³¹P NMR (C₆D₆) δ (ppm): –5 ppm. ¹H NMR (C₆D₆) δ (ppm): 8–6.5 (br, 7H, aryl-H), 4.5–3.5 (br, 9H, Fc-H), 3–1.5 (br, H, Mes-H). GPC-LLS (THF): M_n = 9500, PDI = 1.21, R_h = 1.5 nm. UV/Vis (C₇H₉): λ_{max}/nm (ϵ/M^{-1} cm⁻¹) = 448 (210). Anal. Calc. for C₂₆H₂₅PFe: C, 73.60; H, 5.94. Found: C, 73.50; H, 6.29%.

- (a) J. E. Mark, H. R. Allcock and R. West, *Inorganic Polymers*, Oxford University Press, 2nd edn, 2005; (b) I. Manners, *Synthetic Metal-Containing Polymers*, Wiley-VCH, Weinheim, 2004; (c) A. S. Abd-El-Aziz, C. E. Carraher, Jr., C. U. Pittman, Jr., J. E. Sheats and M. Zeldin, *Macromolecules Containing Metal and Metal-Like Elements*, Wiley, New Jersey, 2003–2006, vol. 1–7.
- 2 (a) A. S. Abd-El-Aziz and I. Manners, J. Inorg. Organomet. Polym. Mater., 2005, 15, 157; (b) P. Nguyen, P. Gomez-Elipe and I. Manners, Chem. Rev., 1999, 99, 1515; (c) D. Astruc, J.-C. Blais, E. Cloutet, L. Djakovitch, S. Rigaut, J. Ruiz, V. Sartor and C. Valerio, Top. Curr. Chem., 2000, 210, 229.
- 3 C. U. Pittman, J. Inorg. Organomet. Polym. Mater., 2005, 15, 33.
- 4 F. S. Arimoto and A. C. Haven, Jr., J. Am. Chem. Soc., 1955, 77, 6295.
- 5 C.-W. Tsang, M. Yam and D. P. Gates, J. Am. Chem. Soc., 2003, 125, 1480.
- 6 K. J. T. Noonan and D. P. Gates, Angew. Chem., Int. Ed., 2006, 45, 7271.

- 7 C.-W. Tsang, B. Baharloo, D. Riendl, M. Yam and D. P. Gates, *Angew. Chem., Int. Ed.*, 2004, **43**, 5682.
- 8 H. P. Withers, D. Seyferth, J. D. Fellmann, P. E. Garrou and S. Martin, Organometallics, 1982, 1, 1283.
- 9 C. H. Honeyman, T. J. Peckham, J. A. Massey and I. Manners, *Chem. Commun.*, 1996, 2589.
- 10 R. C. Smith, X. Chen and J. D. Protasiewicz, *Inorg. Chem.*, 2003, 42, 5468.
- 11 L. Weber, Coord. Chem. Rev., 2005, 249, 741.
- 12 L. Weber, Angew. Chem., Int. Ed. Engl., 1996, 35, 271.
- 13 J. F. Nixon, Chem. Rev., 1988, 88, 1327.
- 14 (a) R. Pietschnig, E. Niecke, M. Nieger and K. Airola, J. Organomet. Chem., 1997, **529**, 127; (b) R. Pietschnig, M. Nieger, E. Niecke and K. Airola, J. Organomet. Chem., 1997, **541**, 237; (c) C. Moser, A. Orthaber, M. Nieger, F. Belaj and R. Pietschnig, Dalton Trans., 2006, 3879; (d) A. Grünhagen, U. Pieper, T. Kottke and H. W. Roesky, Z. Anorg. Allg. Chem., 1994, **620**, 716; (e) C. C. Cummins, R. R. Schrock and W. M. Davis, Angew. Chem., Int. Ed. Engl., 1993, **32**, 756.
- 15 See, for example: (a) H. Kawanami, K. Toyota and M. Yoshifuji, J. Organomet. Chem., 1997, 535, 1; (b) A. Jouaiti, M. Geoffroy and G. Bernardinelli, Chem. Commun., 1996, 437; (c) A. Jouaiti, M. Geoffroy and G. Bernardinelli, Tetrahedron Lett., 1992, 33, 5071; (d) A. Jouaiti, M. Geoffroy and G. Bernardinelli, Tetrahedron Lett., 1993, 34, 3413; (e) O. Daugulis, M. Brookhart and P. S. White, Organometallics, 2002, 21, 5935; (f) A. Termaten, M. van der Sluis and F. Bickelhaupt, Eur. J. Org. Chem., 2003, 2049; (g) A. S. Ionkin and W. J. Marshall, Heteroat. Chem., 2002, 13, 662.
- 16 M. Yam, J. H. Chong, C.-W. Tsang, B. O. Patrick, A. E. Lam and D. P. Gates, *Inorg. Chem.*, 2006, 45, 5225.
- 17 K. Tappe and P. Knochel, Tetrahedron: Asymmetry, 2004, 15, 91.
- 18 T. A. Van der Knaap, T. C. Klebach, F. Visser, F. Bickelhaupt, P. Ros, E. J. Baerends, C. H. Stam and M. Konijn, *Tetrahedron*, 1984, 40, 765.
- 19 In a separate determination of MesP=CPh₂ this angle was 59.2°. See: O. Mundt, G. Becker and W. Uhl, Z. Anorg. Allg. Chem., 1986, 540/ 541, 319.
- 20 (a) V. A. Wright, B. O. Patrick, C. Schneider and D. P. Gates, J. Am. Chem. Soc., 2006, **128**, 8836; (b) R. C. Smith and J. D. Protasiewicz, Eur. J. Inorg. Chem., 2004, 998; (c) A. Al Badri, A. Jouaiti and M. Geoffroy, Magn. Reson. Chem., 1999, **37**, 735; (d) H. Kawanami, K. Toyota and M. Yoshifuji, Chem. Lett., 1996, 533; (e) A. Jouaiti, M. Geoffroy, G. Terron and G. Bernardinelli, J. Am. Chem. Soc., 1995, **117**, 2251; (f) A. Jouaiti, M. Geoffroy, G. Terron and G. Bernardinelli, J. Chem. Soc., Chem. Commun., 1992, 155.
- 21 C. U. Pittman, J. C. Lai, D. P. Vanderpool, M. Good and R. Prado, *Macromolecules*, 1970, 3, 746.
- 22 C. Klebach, R. Lourens and F. Bickelhaupt, J. Am. Chem. Soc., 1978, 100, 4886.
- 23 J. B. Flanagan, S. Margel, A. J. Bard and F. C. Anson, J. Am. Chem. Soc., 1978, 100, 4248.
- 24 A. J. Downard, N. J. Goodwin and W. Henderson, J. Organomet. Chem., 2003, 676, 62.