www.rsc.org/chemcomm

ChemComm

Mesoporous silica anchored Ru catalysts for highly enantioselective hydrogenation of β -ketoesters \dagger

Banu Kesanli and Wenbin Lin*

Department of Chemistry, CB#3290, University of North Carolina, Chapel Hill, NC 27599, USA. E-mail: wlin@unc.edu

Received (in Columbia, MO, USA) 3rd May 2004, Accepted 1st July 2004 First published as an Advance Article on the web 25th August 2004

Recyclable and reusable mesoporous silica anchored Ru catalysts based on 4,4'-substituted BINAPs were synthesized and used for the hydrogenation of β -alkyl β -ketoesters with up to 98.6% e.e. and β -aryl β -ketoesters with up to 95.2% e.e.

New routes are being explored to achieve the economical synthesis of optically pure feedstocks through asymmetric catalysis.¹ Heterogenization of well-established soluble transition metalbased asymmetric catalysts on inorganic oxide or polymer supports allows easy separation and hence recycling and reuse of expensive asymmetric catalysts.² Appropriate covalent attachment of soluble transition metal-based asymmetric catalysts onto the supports can also prevent the leaching of toxic metals into the organic products which can present a formidable challenge if the organic products are to be used as pharmaceutical ingredients. We have recently developed a molecular building block approach toward the heterogenization of homogeneous asymmetric catalysts in zirconium phosphonate hybrid solids.³ Herein we wish to report the immobilization of Ru complexes of 4,4'-substituted BINAPs on well-ordered mesoporous silica SBA-15, and the applications of these heterogeneous asymmetric catalysts in highly enantioselective hydrogenation of β -ketoesters.

Since their discovery in the early 1990's, well-ordered mesoporous materials have been examined for a number of applications.⁴ Immobilization of homogeneous asymmetric catalysts on the inner walls of such mesoporous solids offers several advantages (including higher surface areas and larger open channels) over other less defined supports such as organic polymers. Mesoporous siliceous materials such as MCM-41 and SBA-15 have indeed been used as supports for the immobilization of several asymmetric catalysts.⁵ We have chosen SBA-15 as the supports for this work because of their ease of synthesis and very large pore sizes (so that diffusion of substrates and products would be more facile).⁶

4,4'-bis(cyclopentanol)-2,2'-bis(diphenylphoof Lithiation sphino)-1,1'-binaphthyl and 4-(cyclopentanol)-2,2'-bis(diphenylphosphino)-1,1'-binaphthyl7 followed by treatment with 3-iodopropyltrimethoxysilane afforded the modified BINAPs L_1 and L_2 (Scheme 1). Ligands L_1 and L_2 have been characterized by ${}^{1}H{}^{31}P{}$ and ${}^{31}P{}^{1}H{}$ NMR spectroscopy. RuL₁(DMF)₂Cl₂ and RuL₂(DMF)₂Cl₂ were synthesized by heating [RuCl₂(*p*-cymene)]₂ and L1 and L2 in DMF at 100 °C, respectively. A suspension of SBA-15 and RuL₁(DMF)₂Cl₂ or RuL₂(DMF)₂Cl₂ in toluene was refluxed overnight to give the heterogenized precatalysts 1 and 2.;⁸ The Ru precatalyst loadings were determined by direct current plasma (DCP) analysis of the Ru content in the modified SBA-15. The pristine SBA-15 has a BJH surface area of 724 m²/g and a BJH average pore size of 113 Å. Upon the immobilization of the Ru complexes, the solid catalysts 1 and 2 exhibited expected diminished surface areas and pore sizes (Table 1). 2 has slightly larger surface area, pore volume, and pore size than 1, consistent with the presence of the bulky 1-cyclopentanol group in 1.

Catalytic asymmetric hydrogenation of both β -alkyl and β -aryl β -ketoesters was carried out under a hydrogen pressure of 1400 psi in the presence of 1 or 2 in methanol at r.t. for 20 h.§ As shown in

† Electronic supplementary information (ESI) available: experimental section. See http://www.rsc.org/suppdata/cc/b4/b406697a/ Table 2 (entries 1–4), β -alkyl β -ketoesters were hydrogenated with complete conversions and e.e. values in the 96.3 to 98.6% range in the presence of 1 mol% of **1**. These β -alkyl β -ketoesters were hydrogenated over solid catalyst **2** (2 mol%) with similar e.e. values to **1** and complete conversions.¹⁰ The e.e. values exhibited by **1** and **2** are comparable to those of the parent Ru(BINAP) homogeneous catalyst¹¹ and are 4–5% higher than those of zirconium phosphonate-derived heterogeneous catalyst.^{3a} The level of e.e.'s exhibited by **1** and **2** is also comparable to the best polymeranchored Ru catalysts for the hydrogenation of β -alkyl β -ketoesters.¹²

The hydrogenation of β -aryl β -ketoesters was carried out in the presence of 2 mol% of solid catalyst **1** or 4 mol% of solid catalyst **2**. E.e. values in the range of 81.7–95.2% were obtained for **1**, while e.e. values in the range of 71.9–93.5% were obtained for **2** (Table 2,



Reagents and conditions: (1) a) "BuLi; b) 3-iodopropyltrimethoxysilane; (2) a) [Ru(p-cymene)Cl₂]₂, DMF, 100 °C; b) SBA-15, toluene, reflux

Scheme 1

 Table 1
 Surface area, pore volume, and pore size of SBA-15, 1, and 2

	SBA-15	1	2
BJH surface area (m ² /g)	724	487	529
BJH pore volume (mL/g)	1.98	1.38	1.52
BJH pore size (Å)	113	96	101



Fig. 1 N₂ adsorption isotherms for SBA-15, 1, and 2 at 77 K.

10.1039/b406697a

Ö

2^{13}	Cataly	/tic asyr	nmetri	c nydrog	genation	norp	-ketoes	sters by	I and
	0	0				OH	0		

$R_1 \xrightarrow{R_3} R_3 \xrightarrow{R_2} \frac{1 \text{ or } 2}{(R_3 = \text{H except for entry } 4)} \xrightarrow{R_1} R_3 \xrightarrow{R_2} R_3$						
Entry	R ₁	R ₂	1 ^{<i>a</i>}	2^{b}		
1	Me	Me	98.6	97.6		
2	Me	ⁱ Pr	98.4	98.6		
3	Me	'Bu	97.3	97.1		
4 ^c	Me	Me	96.3	96.3		
5	2'-CF ₃ -Ph	Me	95.2	93.5		
6	2'-Cl-Ph	Me	94.2	90.0		
7	3'-CF ₃ -Ph	Me	92.7	90.4		
8	4'-OMe-Ph	Et	91.5	82.3		
9	Ph	Et	91.0	79.9		
10	4'-CF ₃ -Ph	Me	87.4	71.9		
11	4'-F-Ph	Me	86.3	81.4		
12	4'-Cl-Ph	Me	81.7			

 a 1 mol% catalyst loading for entries 1–4 and 2 mol% catalyst loading for entries 5–12. b 2 mol% catalyst loading for entries 1–4 and 4 mol% catalyst loading for entries 5–12. c R₃ = Me.

entries 5–12). These e.e. values are much higher than those afforded by the homogeneous Ru(BINAP)(DMF)₂Cl₂ catalyst, but a few percent lower than those afforded by the parent Ru[4,4'-(1cyclopentanol)₂BINAP](DMF)₂Cl₂ catalyst reported by us recently.⁷ Consistent with our earlier discovery of the 4,4'substituent effects of BINAP in the hydrogenation of β-aryl β-ketoesters,⁷ **2** gave lower e.e.'s than **1** for all the substrates tested because of the lack of a bulky substituent in the 4'-position of the modified BINAP **L**₂.

We have attempted to recycle and reuse 1 in the hydrogenation of methyl acetoacetate. As shown in Table 3, 1 was successfully used for 5 consecutive runs of asymmetric hydrogenation of methyl acetoacetate. Complete conversions were obtained for the first three runs, and the conversion started to drop in the fourth and fifth run. The e.e. value also deteriorated as the conversion dropped. We believe that the loss of activity and the deterioration of enantioselectivity are probably a result of the air-sensitivity of the catalytically active Ru-hydride species (but not the leaching of Ru-containing complexes). Control experiments showed that the supernatant did not catalyze the hydrogenation of methyl acetoacetate. Consistent with this, DCP spectroscopy showed that less than 0.12% of Ru-containing complexes had leached into the organic phase during each run of asymmetric hydrogenation.

In summary, we have designed recyclable and reusable heterogeneous asymmetric catalysts *via* covalent anchoring to the inner walls of mesoporous SBA-15. These immobilized catalysts have been used for the hydrogenation of β -ketoesters with up to 98.6% e.e.

We acknowledge financial support from NSF (CHE-0208930). We thank Dr A. Hu for his generous help. W.L. is an Alfred P. Sloan Fellow, an Arnold and Mabel Beckman Young Investigator, a Cottrell Scholar of Research Corp, and a Camille Dreyfus Teacher-Scholar. Table 3 Recycling and reuse of 1 for the hydrogenation of methyl acetoacetate^a

Run	1	2	3	4	5
e.e. (%) Conversion (%)	98.6 > 99	98.4 > 99	96.2 > 99	89.2 91	82.1 83
^{<i>a</i>} All the reactions under 1400 psi of	were carri H ₂ for 20 h	ed out with	n 1 mol% c	atalyst in	MeOH

Notes and references

[‡] **Preparation of solid catalysts.** A mixture of $[Ru(p-cymene)Cl_2]_2$ (15.3 mg, 0.025 mmol) and L_1 (50 mg, 0.052 mmol) in anhydrous DMF (4 mL) was heated at 100 °C under Ar for 30 min and then cooled to 25 °C. All the volatile components were removed under vacuum to give a dark red solid. This solid was refluxed with 335 mg of SBA-15, that had been dried under vacuum at 135 °C for 3 h, in 10 mL of toluene overnight. The mixture was cooled to r.t. and centrifuged for 30 min, the supernatant was removed. The solid was washed with dry toluene and dried under vacuum. 400 mg of solid catalyst 1 was obtained after this treatment.

§ A typical procedure for asymmetric hydrogenation of β-ketoester. 19.2 mg of solid catalyst 1 (2.5 μmol) was weighed into a Teflon-capped vial inside a drybox, and to this vial was added ethyl benzoylacetoacetate (24 μL, 0.125 mmol) and anhydrous methanol (0.5 mL) under Ar. The vial was quickly transferred inside a stainless steel autoclave, and sealed. After purging with hydrogen for 6 times, final H₂ pressure was adjusted to 1400 psi; 20 h later, H₂ pressure was released and water (10 mL) was added. The hydrogenated product was extracted with diethyl ether and passed through a mini silica-gel column before chiral GC, HPLC and SFC analyses.

- (a) R. Noyori, Angew. Chem., Int. Ed., 2002, 41, 2008; (b) W. S. Knowles, Adv. Synth. Catal., 2003, 345, 3; (c) H.-U. Blaser, Adv. Synth. Catal., 2002, 344, 17.
- Q. H. Fan, Y.-M. Li and A. S. C. Chan, *Chem. Rev.*, 2002, **102**, 3385;
 P. McMorn and G. J. Hutchings, *Chem. Soc. Rev.*, 2004, **33**, 108.
- 3 (a) A. Hu, H. L. Ngo and W. Lin, Angew. Chem., Int. Ed., 2003, 42, 6000; (b) A. Hu, H. L. Ngo and W. Lin, J. Am. Chem. Soc., 2003, 125, 11490.
- 4 C. T. Kresge, M. E. Leonowicz, W. J. Roth, J. C. Vartuli and J. S. Beck, *Nature*, 1992, **359**, 710.
- 5 (a) S. J. Bae, S.-W. Kim, T. Hyeon and B. M. Kim, *Chem. Commun.*, 2000, 31; (b) A. Corma, H. Garcia, A. Moussaif, M. J. Sabater, R. Zniber and A. Redouane, *Chem. Commun.*, 2002, 1058; (c) S. Xiang, Y. Zhang, Q. Xin and C. Li, *Angew. Chem., Int. Ed.*, 2002, **41**, 821; (d) M. D. Jones, R. Raja, J. M. Thomas, B. F. G. Johnson, D. W. Lewis, J. Rouzaud and K. D. M. Harris, *Angew. Chem., Int. Ed.*, 2003, **42**, 4326.
- 6 (a) D. Zhao, J. Feng, Q. Huo, N. Melosh, G. H. Frederickson, B. F. Chmelka and G. D. Stucky, *Science*, 1998, **279**, 548; (b) P. Yang, D. Zhao, D. I. Margolese, B. F. Chmelka, G. D. Stucky and D. Galen, *Nature*, 1998, **396**, 152.
- 7 A. Hu, H. L. Ngo and W. Lin, Angew. Chem., Int. Ed., 2004, 43, 2501.
- 8 H. Gao and R. J. Angelici, *Organometallics*, 1998, 17, 3063.
 9 Typical loadings are 0.0125 mmol of 1 and 0.0112 mmol of 2 per gram of SBA-15, respectively.
- 10 Although β-alkyl β-ketoesters can be hydrogenated with complete conversions in the presence of 1% of 2, much inferior e.e. values (10–15% lower) were obtained.
- 11 R. Noyori, T. Ohkuma, M. Kitamura and H. Takaya, J. Am. Chem. Soc., 1987, 109, 5856.
- 12 R. Halle, B. Colasson, E. Schulz, M. Spagnol and M. Lemaire, *Tetrahedron Lett.*, 2000, 41, 643.
- 13 All the reactions were judged to have > 99% conversions based on integrations of NMR peaks. E.e.% values were determined by GC using a Superco γ -Dex 225 column or by HPLC using a Chiralpak AD column and by SFC using a Chiralpak AS column.