# Accepted Manuscript

On the design of new europium heteroaromatic carboxylates for OLED application

Daniil S. Koshelev, Tatyana Yu Chikineva, Vladislava Yu Khudoleeva, Alexey V. Medvedko, Andrew A. Vashchenko, Alexander S. Goloveshkin, Dmitriy M. Tsymbarenko, Alexey A. Averin, Anna Meschkov, Ute Schepers, Sergey Z. Vatsadze, Valentina V. Utochnikova

PII: S0143-7208(19)30709-0

DOI: https://doi.org/10.1016/j.dyepig.2019.107604

Article Number: 107604

Reference: DYPI 107604

- To appear in: Dyes and Pigments
- Received Date: 12 April 2019

Revised Date: 30 May 2019

Accepted Date: 30 May 2019

Please cite this article as: Koshelev DS, Chikineva TY, Khudoleeva VY, Medvedko AV, Vashchenko AA, Goloveshkin AS, Tsymbarenko DM, Averin AA, Meschkov A, Schepers U, Vatsadze SZ, Utochnikova VV, On the design of new europium heteroaromatic carboxylates for OLED application, *Dyes and Pigments* (2019), doi: https://doi.org/10.1016/j.dyepig.2019.107604.

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.





Bioimaging



OLED







# ACCEPTED MANUSCRIPT

### On the design of new europium heteroaromatic carboxylates for OLED application

Daniil S. Koshelev<sup>\*a</sup>, Tatyana Yu. Chikineva<sup>a</sup>, Vladislava Yu. Khudoleeva<sup>a</sup>, Alexey V. Medvedko<sup>b</sup>, Andrew A. Vashchenko<sup>c</sup>, Alexander S. Goloveshkin<sup>d</sup>, Dmitriy M. Tsymbarenko<sup>b</sup>, Alexey A. Averin<sup>e</sup>, Anna Meschkov<sup>f,g</sup>, Ute Schepers<sup>f,g</sup>, Sergey Z. Vatsadze<sup>b</sup>, and Valentina V Utochnikova<sup>a,b</sup>.

a. Faculty of Materials Science, M.V. Lomonosov Moscow State University, 1/73 Leninskye Gory, Moscow 119991, Russia.

b. Department of Chemistry, M.V. Lomonosov Moscow State University, 1/3 Leninskye Gory, Moscow 119991, Russia.

c. P.N. Lebedev Physical Institute, Leninsky prosp. 53, Moscow 119992, Russia.

d. A. N. Nesmeyanov Institute of Organoelement Compounds, Vavilova str., 28, Moscow 117312, Russia.

e. A. N. Frumkin Institute of Physical Chemistry and Electrochemistry, Leninsky prosp. 31/5 p.2, Moscow 119071, Russia.

f. Institute of functional interfaces, Karlsruhe Institute of Technology, Karlsruhe, Germany.

g. Institute of organic chemistry, Karlsruhe Institute of Technology, Karlsruhe, Germany.

† Electronic Supplementary Information (ESI) available

Corresponding author: Daniil S. Koshelev\* dan\_kosh@mail.ru)

#### Abstract:

The approach to the directed synthesis of lanthanide aromatic carboxylates – precursors to the electroluminescent materials, - was proposed, namely the conjugation length increase and heteroatom introduction in the appropriate position in combination with the neutral ligand introduction. This resulted in the isolation of a series of new lanthanide complexes, among which the highest electroluminescence efficiency was obtained for mixed-ligand europium benzothiazole-2-carboxylate with bathophenanthroline in a solution-processed OLED. The peculiarities of energy transfer processes allowed obtaining luminescence thermometer materials based on this system, which demontrated the sensitivity of 2.8%/K in the physiological range.

Keywords: Luminescence; Lanthanides; Carboxylates; OLED; Benzoxazole; Benzothiazole;

#### CCEPTED MANUSCRIPT

#### 1. Introduction

Luminescent lanthanide (III) coordination compounds (CC)are unique candidates for electroluminescent materials as they offer ultimate colour saturation due to their narrow luminescence bands. They also have potential for a high internal quantum efficiency of electroluminescence because they are capable of harvesting triplet excitons for light emission [1], so they have attracted considerable interest as OLED emission layer (EML) materials [2-8]. The mostly utilized technique of OLED processing is vacuum deposition, as it ensures high efficiency. However, volatility is required of luminescent materials in that case; besides, thermal evaporation is cost-ineffective and provides lower resolution than solution process [3,9,10]. In contrast, solution deposition of the emitting layers requires only solubility. In addition, this technique offers a whole number of variations, i.e. slot-die coating, blade coating, ink-jet printing, rollto-roll process [11–15] and enables the obtaining of OLEDs of any size. But the most critical problem of solution-processed devices is orders of magnitude lower efficiency. So, even europium mixed-ligand (ML) aromatic carboxylates, among which is the one with the record photoluminescence quantum yield (PLQY) value [16], demonstrated electroluminescence with the efficiency of only up to 25 Cd/m<sup>2</sup> that is too low even in comparison to europium volatile complexes, such as  $\beta$ -diketones (i.e. 400 Cd/m<sup>2</sup> for europium dibenzoylmethanate with phenanthroline [17] or 72 Cd/m<sup>2</sup> for recently reported europium pyrazolesubstituted  $\beta$ -diketone with batophenanthroline [18]. Still solution processing is promising in manufacturing and material cost decreasing, which requires simultaneous solution of two tasks: the search of the new materials and the development of the solution procession of OLEDs. The present work is aimed to give impact to the first one.

Thus, design of the luminescent material precursors based on lanthanide CCs must be started from the ligand design instead of the undirected synthesis. We selected aromatic carboxylates for the investigation, as they ensure high chemical stability and the high PLQY values of lanthanide CCs [19–28]. Their crucial issues usually are low solubility, particularly in water, due to the tendency to polymerize [22,29–33] and low charge carrier mobility [20,34–36]. Thus, the ligand design was aimed on the increase of the complex solubility and mobility, as well as absorption. The goal of the work was to verify the prospectiveness of such a material design for obtaining of the materials for potential use in bioimaging and OLEDs. In the present work their solution-processed OLED performance was demonstrated in particular.

There are several methods to increase the solubility, including in water for bioimaging and in organic solvents for solution-processable OLED. However, even though there is a large amount of experimental data that allows scientists to selectively modify the properties of the complexes (for example, solubility and luminescence intensity) unpredictable results still occur. So, the ML complex formation may result in both solubility increase [37–40] or decrease [16,41,42]. The introduction of the aliphatic chain into the ligand usually increases solubility [43–46] but decreases the luminescence quantum yield due to the quenching, originating from the CH-vibrations [44,47–50]. Ligand fluorination helps avoiding the latter problem, but leads to the decrease of the ligand molar absorption coefficient and complex stability in solution [24,51–54]. The introduction of a heteroatom (for instance N) into the  $\alpha$ -position relative to a carboxylic group of the ligand was recently shown as another efficient approach, still lacking the listed drawbacks [55]. It will be used in the present work.

Important is that the heteroatom introduction (not only N but also S,O) was also shown to increase electron mobility, particularly of the highly conjugated compounds [56]. It also helps increasing the triplet state energy (i.e. benzoate (24800 cm<sup>-1</sup>) [57] *vs* picolinate (25773 cm<sup>-1</sup>) [58] or even 2-furanoate (29200 cm<sup>-1</sup>) [58]). In order to achieve high sensitization efficiency of lanthanide luminescence, ligands triplet state energy should be above lanthanides excited state energy, and the optimal difference is usually believed to make up about 2500-4000 cm<sup>-1</sup> [59]. So, for instance, europium excited state ( ${}^{5}D_{0}$  (Eu<sup>3+</sup>) = 17200 cm<sup>-1</sup>) requires triplet state energy over 20000 cm<sup>-1</sup>, while for terbium ( ${}^{5}D_{4}$  (Tb<sup>3+</sup>) = 20500 cm<sup>-1</sup>) the triplet state energy over 23000 cm<sup>-1</sup> is preferential, though there are some exceptions [60].

Increasing of conjugation length, that is the number of conjugated double bonds, can also increase ligand molar absorption coefficient [61–65]. At the same time, it results in decrease of the triplet excited state energy [61], which can lead to the decrease of sensitization efficiency; but as mentioned above, the heteroatom introduction can help avoiding this problem. There are many studies concerning coordination compounds based on monocyclic benzoic[24,66–68] and picolinic [43,58,69] acids derivates as well as on bicyclic acids derivates (naphthoic [70], benzofuran carboxylic[71,72], quinoline carboxylic acid[73–76]). But basing on the mentioned above dependence it can be suggested new forms of perspective ligands.



Figure 1 a) Benzoxazole-2-carboxylic acid (H(boz)) b) benzothiazole-2-carboxylic acid (H(btz)). Positions of H atoms are enumerated for signals in <sup>1</sup>H NMR spectra assignment.

So, in order to combine high solubility, high absorption and charge carrier mobility, conjugated heteroaromatic carboxylate ligands were used in the present work, namely benzoxazole-2-carboxylate (boz)<sup>-</sup> and benzothiazole-2-carboxylate (btz)<sup>-</sup> were obtained, and the role of the second heteroatom (O or S) was studied. Lanthanide homo- and mixed-ligand carboxylates with these ligands and neutral *o*-phenanthroline (Phen) and bathophenanthroline (BPhen) ligands were obtained and studied as precursors to OLED emitting layer materials [27,77–79].

# 2. Experimental section

#### Materials and methods.

All solvents, including deuterated solvents ( $D_2O$ , DMSO-d<sup>6</sup>), and chemicals were purchased from commercial sources.

Aniline and 2-aminophenol were purchased from SigmaAldrich.

Lanthanide salts were purchased from Huizhou GL Technology Co.

All other chemicals were purchased from Component-Reactive. Deuterated solvents were purchased from Carl Roth Gmbh.

<sup>1</sup>H, <sup>13</sup>C NMR spectra were recorded at 25 °C using Agilent 400 MR spectrometer with the operating frequency of 400 and 100 MHz respectively. Chemical shifts are reported in ppm relative to residual solvent signals. Elemental analysis was performed on the microanalytical device Heraeus Vario Elementar.

**Thermal analyses** were carried out on a thermoanalyzer STA 409 PC Luxx (NETZSCH, Germany) in the temperature range of 20–1000 °C in argon atmosphere, heating rate 10 °/min. The composition of formed gases was determined by quadrupole mass spectrometer QMS 403C Aëolos (NETZSCH, Germany), combined by thermoanalizer NETZSCH STA 409 PC Luxx. Mass spectra were recorded for mass numbers 18 (H<sub>2</sub>O), 44 (CO<sub>2</sub>)  $\mu$  58 (CH<sub>3</sub>C(O)CH<sub>3</sub>).

**IR spectra** in the ATR mode were recorded on a spectrometer SpectrumOne (Perkin-Elmer) in the region of 400-4000 cm-1.

**X-ray powder diffraction (XRD)** measurements were performed on a Bruker D8 Advance Vario diffractometer with LynxEye detector and Ge (111) monochromator,  $\lambda$ (CuK $\alpha_1$ ) = 1.54060 Å,  $\theta/2\theta$  scan from 6.0° to 60°, step size 0.02°, in transmission mode, with the sample deposited between Mular films.

**Single crystal X-ray diffraction (SC-XRD) studies** were carried out on a Bruker APEX-II CCD diffractometer. The crystal was kept at 120 K during data collection. Using Olex2 [80], the structure was solved with the olex2.solve [81] structure solution program using Charge Flipping and refined with the XL [82] refinement package using Least Squares minimisation.

The solubility of the CC lanthanides was measured at room temperature according to the following procedure: a suspension of 150 mg of each compound in 10 mL of solvent was refluxed for 1 hour and thereafter cooled to room temperature. Then 5 mL of the solution were filtered into a cup with known mass, the solvent was evaporated. and the change of the cup's mass corresponded to the amount of the dissolved product.

Absorption spectra were recorded in the region 250–800 nm with a Perkin–Elmer Lambda 650 spectrometer. Emission spectra was measured with a Fluorolog 3 spectrofluorometer over excitation with a xenon lamp. For the determination of the photoluminescence quantum yields in solid state, an integration sphere Quanta Phi was used. Luminescence lifetime measurements were recorded and detected on the same system. Lifetimes are averages of at least three independent measurements. All luminescence decays proved to be perfect single-exponential functions. Photoluminescence spectra at two temperatures (77, 298 K) were obtained on a S2000 (Ocean Optics) multichannel spectrometer with excitation by LGI-21 nitrogen laser ( $\lambda_{ex} = 337$  nm). Thermal dependence of luminescence properties was measured on the same device using thermal control device and heating element. Electroluminescence spectra were measured on a PicoQuant time-correlated single photon counting system used as a conventional spectrofluorimeter. Spectral resolution was 4 nm. Electroluminescence intensity was normalized by integration time, which allows comparing different spectra.

**OLED manufacturing** took place in a clean room class 10000 (Lebedev Physical Institute, Moscow, Russia) in a glove-box under an argon atmosphere. The substrates were cleaned by ultrasonication in the following media: NaOH aqueous solution, distilled water, acetone and 2-propanol for 16 min each. A 40 nm-thick poly(3,4-ethylenedioxythiophene):poly(styre-nesulfonate) (PEDOT:PSS) hole-injective layer was first deposited. An aqueous solution of PEDOT:PSS (5 mL) was poured onto the preheated (70 °C) patterned ITO glass substrate, after which the substrate was rotated for 60 seconds at 2000 rpm. Finally, the deposited film was annealed in air at 80 °C for 60 min. As a hole-transport layer (20 nm) poly-TPD solution was spin-coated from chlorobenzene ( $c = 5 \text{ gL}^{-1}$ ) and was annealed in argon at 220 °C for 30 min. The emission layer was spin-coated from the solution ( $c = 5 \text{ gL}^{-1}$ ) on the heterostucture or on the glass substrate.

The ~15 nm-thick electron-transport/hole-blocking layer (TPBi) was thermally evaporated (Univex-300, LeybordHeraeus) followed by a ~1 nm-thick LiF layer and a >100 nm-thick aluminium layer as the cathode under a pressure below  $10^{-6}$  mm Hg. The thickness of the layers was controlled by using a quartz indicator. The contacts were attached to the electrodes, and the device was sealed with epoxy resin (Norland Optical Adhesive).

**Quantum chemical calculations**. The geometry of the ground state of the K(carb) and Eu(carb)<sub>3</sub> molecules was optimized using Firefly 8.2 package [83] in a framework of the DFT theory with PBE0 functional, full electron basis set 6-31G(d, p) for C, N, O, S and H atoms, and quasi-relativistic Stuttgart-Koeln ECP52MWB pseudopotential (f-electrons in core) with appropriate basis set for Eu atom [84].

For each molecule all relevant structural isomers were considered, optimized and the lowest-energy isomer was chosen for further calculations. The optimized molecular geometries were checked for the absence of imaginary frequencies in the vibrational spectra.

TD-DFT calculations were performed at the same PBE0/6-31G(d, p)+ECP52MWB level for the optimized geometry of molecules, 20 singlet single excited states were considered. The energies of the frontier orbitals were calculated using the DFT and TDDFT results. The energy of the HOMO was obtained as the eigenvalue of DFT calculation for the ground state, while the energy of the LUMO was computed as E(HOMO) + Eg, where Eg is the lowest vertical transition energy in TD-DFT specturm. The details of this approach were reported in [39].

#### **Synthesis**

#### Synthesis of K(boz)

**Methyl benzoxazole-2-carboxylate**. A mixture of 2-aminophenol (2.11 g, 19.4 mmol) and methyl 2,2,2-trimethoxyacetate (10.17 g, 62.0 mmol) were flushed with argon and stirred at 100°C for 42 h. Excess of methyl 2,2,2-trimethoxyacetate was distilled off under reduced pressure. The residue was suspended in diethyl ether (100.0 mL), filtered, and obtained powder was washed with diethyl ether until discoloration of filtrate. The beige powder was purified with column chromatography (silica gel, particle size 40-63  $\mu$ m) eluting with petroleum ether – ethyl acetate 3:1. R<sub>f</sub> (PE:EA 3:1) 0.28. Yield 1.04 g (31%). Light yellow powder.

<sup>1</sup>H-NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  (ppm): 7.90 (d, J = 8 Hz, 1H), 7.68 (d, J = 8 Hz, 1H), 7.51 (t, J = 8 Hz, 2H), 4.10 (s, 3H). <sup>13</sup>C-NMR (100 MHz, CDCl<sub>3</sub>)  $\delta$  (ppm): 156.89, 152.49, 150.87, 140.45, 128.24, 125.83. NMR spectra coincide with the literature data [85].



Scheme 1. Synthesis of K(boz) and K(btz). a)  $(MeO)_3CCO_2Me$ , 100°C, 42 h. b) KOH, THF, H<sub>2</sub>O, rt. c) 2-chloroacetamide, S, DMF, Et<sub>3</sub>N, rt. d) K<sub>3</sub>Fe(CN)<sub>6</sub>, NaOH, H<sub>2</sub>O, reflux.

**Potassium benzoxazole-2-carboxylate** was obtained according to the Scheme 1. 0.87 M aq. KOH (6.06 mL) were added to the solution methyl-benzoxazole-2-carboxylate (0.93 g, 5.3 mmol) in THF (10.5 mL). Orange solution was stirred at rt for 1 h and solvent removed completely. Yield 1.04 g (98%). Beige solid. Mp. 307-310°C (dec.). C<sub>8</sub>H<sub>5</sub>NO<sub>3</sub>: HRMS, m/z: calcd. for [M-H]<sup>-</sup>, 162.0197; found, 162.0189. IR-ATR (KBr, cm<sup>-1</sup>): 3279, 1652, 1542, 1389, 1330, 1255, 1161, 843, 738. <sup>1</sup>H-NMR (400 MHz, D<sub>2</sub>O) δ (ppm): 7.69 (d, J = 8 Hz, 1H), 7.65 (d, J = 8 Hz, 1H), 7.37 (t, J = 8 Hz, 1H), 7.32 (t, J = 8 Hz, 1H). <sup>13</sup>C-NMR (100 MHz, D<sub>2</sub>O) δ (ppm): 161.66, 157.92, 149.93, 139.32, 127.01, 125.11, 120.26, 111.40. Calcd: C, 58.90; H, 3.09; N, 8.59%; found: C, 59.02; H, 2.98; N, 8.60%.

#### Synthesis of K(btz)

**2-(Phenylamino)-2-thiooxoacetamide.** The freshly distilled aniline (3.82 g, 40.5 mmol) were dissolved in dry DMF (37 mL). To prepared solution of trimethylamine (7.4 mL) and sulphur (5.14 g, 161.1 mmol) were sequentially added under vigorous stirring. The light brown solution was stirred for 30 min and then chloroacetamide (3.43 g, 36.7 mmol) was added. The resulted red solution was stirred for 14 h at room temperature and diluted with water (440 mL). The sulfur was removed by filtration and washed with acetone until discoloration of filtrate. Solvents from filtrate were removed and the residue was recrystallized from ethanol. Yield 3.06 g (46%). Orange needles. <sup>1</sup>H-NMR (400 MHz, DMSO-d<sub>6</sub>)  $\delta$  (ppm): 12.10 (s, 1H), 8.14 (d, J = 16 Hz, 2H), 7.92 (d, J = 8 Hz, 2H), 7.42 (t, J = 8 Hz, 2H), 7.28 (t, J = 8 Hz, 1H). <sup>13</sup>C-NMR (100 MHz, DMSO-d<sub>6</sub>)  $\delta$  (ppm): 186.43, 162.31, 138.47, 128.58, 126.82, 123.41. All NMR spectra coincide with the literature data [86].

**Benzothiazole-2-carboxamide.** To the suspension of  $K_3Fe(CN)_6$  (215.00 g, 653.00 mmol) in water (400 mL) the solution of 2-(phenylamino)-2-thiooxoacetamide (9.20 g, 51.1 mmol) in 10% aq NaOH (810 mL) was added under stirring. Suspension was stirred for 1 h at room temperature and filtered. Brown product was filtered, washed with water and dried on air. Yield 6.37 g (70%). Light brown powder.  $R_f(DCM:MeOH 3:1) 0.66$ . <sup>1</sup>H-NMR (400 MHz, DMSO-d<sub>6</sub>)  $\delta$  (ppm): 8.48 (s, 1H), 8.20 (d, J = 8 Hz, 1H), 8.11 (d, J = 8 Hz, 1H), 8.07 (s, 1H), 8.20 (d, J = 8 Hz, 1H), 7.61 (t, J = 8 Hz, 1H), 7.55 (t, J = 8 Hz, 1H). <sup>13</sup>C-NMR (DMSO-d<sub>6</sub>)  $\delta$  (ppm): 165.01, 161.35, 152.85, 136.40, 127.04, 126.66, 124.02, 123.01. All NMR spectra coincide with the literature data [86].

**Potassium benzothiazole-2-carboxylate** was obtained according to the Scheme 1. The benzothiazole-2carboxamide (6.40 g, 35.8 mmol) were mixed with 10% aq KOH (194 mL) and refluxed for 45 min. Reaction mixture was filtered while hot and cooled to room temperature. Precipitate was filtered, washed with water and dried. Yield 4.15 g (53%). Beige flakes. Mp. >360°C (dec.). C<sub>8</sub>H<sub>5</sub>NO<sub>2</sub>S: HRMS, m/z: calcd. for [M-H]<sup>-</sup>, 162.0197; found, 162.0189. IR (KBr, cm<sup>-1</sup>): 3233, 1613, 1491, 1362, 1316, 1125, 845, 757, 731. <sup>1</sup>H-NMR (400 MHz, D<sub>2</sub>O) δ (ppm): 7.80 (d, J = 8 Hz, 1H), 7.73 (d, J = 8 Hz, 1H), 7.36 (t, J = 8 Hz, 1H), 7.29 (t, J = 8 Hz, 1H). <sup>13</sup>C-NMR (100 MHz, D<sub>2</sub>O) δ (ppm): 167.23, 165.93, 152.05, 136.02, 126.66, 126.58, 123.36, 122.32. Calcd: C, 53.62; H, 2.81; N, 7.82%; found: C, 53.57; H, 2.76; N, 7.92%.

# Synthesis of lanthanide complexes ( $Ln = Eu^{3+}, Gd^{3+}, Tb^{3+}$ )

Synthesis of  $Ln(boz)_3$ ·3H<sub>2</sub>O. To the solution potassium benzoxazole-2-carboxylate (0.06 g, 0.30 mmol) in acetone (10 mL) the solution lanthanide chloride hydrate (0.05 g, 0.12 mmol) in acetone (10 mL) was added. After prolonged stirring, the precipitate was filtered off. The filtrate was evaporated to dryness, redissolved in water (30 mL) and evaporated to dryness. Yield 0.05 g (65%). Pale brown powder.

**Eu(boz)**<sub>3</sub>·**3H**<sub>2</sub>**O**: Calcd. for EuC<sub>24</sub>H<sub>16</sub>N<sub>3</sub>O<sub>11</sub>: C 41.63, H 2.62, N 6.07%; found: C 41.78, H 2.56, N 6.13%. IR (KBr, cm<sup>-1</sup>): 3279, 1650, 1545, 1393, 1332, 1256, 1164, 845, 741.

**Gd(boz)<sub>3</sub>·3H<sub>2</sub>O:** Calcd. for Gd C<sub>24</sub>H<sub>16</sub>N<sub>3</sub>O<sub>11</sub>: C 41.32, H 2.60, N 6.02%; found, %: C 41.48, H 2.66, N 6.18. IR (KBr, cm<sup>-1</sup>): 3280, 1649, 1539, 1385, 1334, 1252, 1158, 843, 737.

**Tb(boz)**<sub>3</sub>·**3H**<sub>2</sub>**O:** Calcd. for Tb C<sub>24</sub>H<sub>16</sub>N<sub>3</sub>O<sub>11</sub>: C 41.22, H 2.59, N 6.01%; found %: C 41.65, H 2.61, N 6.07. IR (KBr, cm<sup>-1</sup>): 3279, 1649, 1543, 1387, 1329, 1253, 1162, 842, 735.

Synthesis of  $Ln(btz)_3 \cdot 3H_2O$ . To the solution lanthanide chloride hexahydrate (0.05 g, 0.12 mmol) in water (5 mL) the solution of the potassium benzothiazole-2-carboxylate (0.1 g, 0.46 mmol) in water (10 mL) was added. The precipitate was filtered and dried on air. Yield 0.07 g (70%). White powder.

**Eu(btz)**<sub>3</sub>· 3**H**<sub>2</sub>**O**: Calcd. for EuC<sub>24</sub>H<sub>18</sub>N<sub>3</sub>O<sub>9</sub>S<sub>3</sub>: C 38.92, H 2.45, N 5.67%; found: C 39.04, H 2.38, N 5.51%. IR (KBr, cm<sup>-1</sup>): 3232, 1611, 1490, 1364, 1315, 1131, 844, 758, 728.

**Gd(btz)**<sub>3</sub>· 3**H**<sub>2</sub>**O**: Calcd. for GdC<sub>24</sub>H<sub>18</sub>N<sub>3</sub>O<sub>9</sub>S<sub>3</sub>: C 38.65, H 2.43, N 5.63%; found: C 38.93, H 2.44, N 5.72%. IR (KBr, cm<sup>-1</sup>): 3234, 1615, 1487, 1362, 1317, 1129, 847, 757, 732.

**Tb(btz)**<sub>3</sub>·3**H**<sub>2</sub>**O**: Calcd. for TbC<sub>24</sub>H<sub>18</sub>N<sub>3</sub>O<sub>9</sub>S<sub>3</sub>: C 38.56, H 2.43, N 5.62%; found: C 38.62, H 2.45, N 5.59%. IR (KBr, cm<sup>-1</sup>): 3237, 1617, 1497, 1359, 1312, 1125, 855, 764, 725.

Synthesis of  $Eu(boz)_3$ ·Q, Q=Phen, BPhen (Phen – 1,10- phenanthroline, BPhen – 4,7-diphenyl-1,10-phenanthroline). To the solution lanthanide chloride hexahydrate (0.05 g, 0.12 mmol) in acetone (10 mL) the solution of Phen/BPhen (0.02/0.05, 0.12 mmol) in acetone (10 mL) was added. After prolonged stirring, the solution of 0.06 g of potassium benzoxazole-2-carboxylate in 10 mL of acetone was added to a mixture. Then mixture was stirred for 30 min and the precipitate was filtered off. The filtrate was evaporated to dryness, redissolved in 30 mL of water and evaporated on a rotary evaporator. Yield 0.05/0.05 g (48/41%). Pale brown powder.

**Eu(boz)<sub>3</sub>·Phen:** Calcd. for EuC<sub>24</sub>H<sub>16</sub>N<sub>3</sub>O<sub>11</sub>: C 52.81, H 2.44, N 8.56, found: C 51.96, H 2.38, N 8.60%. IR (KBr, cm<sup>-1</sup>): 3186, 1653, 1540, 1381, 1328, 1249, 1004, 840, 730.

**Eu(boz)**<sub>3</sub>·**BPhen:** Calcd. for EuC<sub>24</sub>H<sub>16</sub>N<sub>3</sub>O<sub>11</sub>: C 59.38, H 2.89, N 7.22, found: C 58.98, H 2.93, N 7.27%. IR (KBr, cm<sup>-1</sup>): 3203, 1642, 1542, 1382, 1330, 1248, 1160, 841, 741, 702.

**Synthesis of Eu(btz)**<sub>3</sub>**·Q, Q=Phen, BPhen.** To the solution lanthanide chloride hexahydrate (0.045 g, 0.12 mmol) in water (10 mL) the solution of Phen/BPhen (0.022/0.045 g, 0.12 mmol) in ethanol (10 mL) was added. After prolonged stirring, solution of the potassium benzothiazole-2-carboxylate (0.1 g, 0.46 mmol) in water (10 mL) was added to the mixture. The precipitate was filtered and dried on air. Yield 0.08/0.09 g (75%). White powder.

**Eu(btz)<sub>3</sub>·Phen:** Calcd. for EuC<sub>24</sub>H<sub>16</sub>N<sub>3</sub>O<sub>8</sub>S<sub>3</sub>: C 49.88, H 2.31, N 8.08, found: C 50.01, H 2.35, N 8.02%. IR (KBr, cm<sup>-1</sup>): 3255, 1624, 1493, 1364, 1314, 1127, 845, 760, 730.

**Eu(btz)**<sub>3</sub>**·BPhen:** Calcd. for EuC<sub>24</sub>H<sub>16</sub>N<sub>3</sub>O<sub>8</sub>S<sub>3</sub>: C 56.58 H 2.77, N 6.87, found: C 56.61, H 2.76, N 6.91%. IR (KBr, cm<sup>-1</sup>): 3135, 1620, 1494, 1358, 1315, 1113, 835, 762, 701.

**Cellular uptake**. Confocal microscopy (using a Leica SPE Scanning confocal inverted microscope) was performed in order to investigate the cellular uptake and the distribution of the compounds. Therefore, HeLa (human cervical carcinoma) cells were seeded in 8-well  $\mu$ -chamber slides (ibidi) the at the density of 2x10<sup>4</sup> cells/well in DMEM (Gibco) supplemented with 10% FCS (Gibco) and 1% penicillin/streptomycin (Gibco). After 24 h of incubation at 37°C, 5% CO<sub>2</sub>, the medium was removed and the cells were treated with the compounds (10  $\mu$ M) in DMEM and incubated for 72 h at 37°C, 5% CO<sub>2</sub>. For the negative control, the cell culture medium was exchanged in some wells without addition of the compounds. After incubation, cells were washed three times with DPBS (Gibco). The compounds were excited at 405 nm, emission was measured at 550-750 nm. Images were taken as sequential scans at 400 Hz with a resolution of 1024×1024 pixels.

**Cytotoxicity studies**. HeLa (human cervical carcinoma) cells were seeded in the 96 well plates at the density of  $1 \times 10^4$  cells/well in DMEM (Gibco) supplemented with 10% FCS (Gibco) and 1% penicillin/streptomycin (Gibco). After 24 h of incubation at 37°C, 5% CO<sub>2</sub>, the medium was removed and the cells were treated with various concentrations of the complexes in DMEM (solvent concentration  $\leq 0,5\%$  v/v) and incubated for 72 h at 37°C, 5% CO<sub>2</sub>. For the negative control, the cell culture medium was exchanged in some wells without addition of the compounds, for the solvent control the corresponding amount of the solvent was added. Thereafter, 15 µl of the MTT reagent (Promega) were given in each well. For the positive control, Triton X-100 (1%) (Serva) was added in some wells before treating them with the MTT reagent. After 3 h of incubation the cells were lysed using the Stop Solution (Promega) to release the blue-purple formazan. The cell viability was determined by measuring the absorbance of the resulting formazan at 595 nm using a multiwell plate reader (SpectraMax ID3, Molecular Devices, USA) and calculated in relation to the negative/solvent control.

### 3. Results and discussion

**Synthesis of heteroaromatic acids.** Both acids were prepared in the form of potassium salts since the corresponding acids are unstable against decarboxylation in acidic environment [87]. Benzoxazole-2-carboxylate was synthesized by ring closure reaction of ortho-ester with 2-aminophenol [88] with subsequent hydrolysis of obtained methyl ester. Benzothiazole-2-carboxylate was synthesized by the novel approach consisting of the sequential alkylation-oxidation of aniline [89] and oxidative ring closure with potassium ferricyanide [90] followed by hydrolysis. This approach was proved effective and will allow

obtaining other substituted benzothiazoles from commercially available anilines. The composition of the obtained compounds was established based on <sup>1</sup>H and <sup>13</sup>C NMR data; in addition, single crystals of 2-(phenylamino)-2-thiooxoacetamide and methyl benzoxazole-2-carboxylate were obtained (CCDC 1887593 and 1887587; see Electronic Supporting Information (ESI); Figure S 1, Figure S 2).

**Lanthanide complexes**  $Ln(btz)_{3} \cdot 3H_2O$  (Ln = Eu, Gd, Tb) were obtained by the interaction between aqueous solutions of potassium benzothiazole-2-carboxylate and lanthanide chloride hexahydrate solution. While  $Ln(boz)_3 \cdot 3H_2O$  (Ln = Eu, Gd, Tb) were obtained by the same exchange reaction in acetone due to K(boz) was insoluble in water. The obtained complexes were recrystallized from water to avoid toxic acetone in their composition. It turned out that  $Ln(boz)_3 \cdot 3H_2O$  rapidly degraded in water solution which was obvious from fast decrease of product yield. In contrast,  $Ln(btz)_3 \cdot 3H_2O$  was stable in the solution.

**Mixed-ligand** (ML) lanthanide complexes  $Eu(carb)_3 \cdot Q$  (carb=boz, btz, Q=Phen, BPhen) were obtained by the reaction between  $EuCl_3Q$  (*in situ* from  $EuCl_3.6H_2O$  and Q in EtOH) and corresponding K(carb) in ethanol. The ML complexes precipitated from ethanol, were filtered off, washed with ethanol and dried in air.

According to the XRD data all the complexes  $Ln(carb)_3 \cdot 3H_2O$  and  $Eu(carb)_3 \cdot Q$  (Ln = Eu, Gd, Tb; carb=boz, btz, Q = Phen, BPhen) were amorphous (Figure S 6;Figure S 7), which is important for OLED, as crystallization of the emission layer would immediately result in the device shorting. Thus their composition was determined by combination of TGA and elemental analyses, <sup>1</sup>H NMR spectroscopy and IR spectroscopy. The TGA data of  $Ln(carb)_3 \cdot Solv$  (Ln = Eu, Gd, Tb; carb=boz, btz) was carried out in the temperature range 200-800°C; mass-spectrometry of released gases was used (mass numbers 18 (H<sub>2</sub>O), 44 (CO<sub>2</sub>), 58 (MeC(O)Me)). It was shown that  $Ln(boz)_3 \cdot Solv$  (Ln = Eu, Gd, Tb) obtained from acetone contained both coordinated water and acetone molecules, while in the TGA pattern of  $Ln(boz)_3 \cdot 3H_2O$  (Ln = Eu, Gd, Tb), recrystallization in avoiding acetone presence (Figure 2). Hydrate composition of Ln(carb)\_3 \cdot 3H\_2O (Ln = Eu, Gd, Tb; carb=boz, btz) was determined from the temperature range of ca. 50-200 °, determined from water ionic current, and confirmed by elemental analysis. Water coordination was also evident from the IR spectroscopy data (Figure S 3).

TGA data of ML complexes proved the absence of coordinated water molecules and the presence only one neutral ligand according to weight loss (clcd 22% vs found 25% for Phen loss, clcd 33% vs found 30% for BPhen loss) in the range of 200 to 400 °C (Figure 2; Figure S 4;Figure S 5).



Figure 2 TGA data with normalized ionic currents of a) Eu(boz)<sub>3</sub>· Solv, b) Eu(boz)<sub>3</sub>· 3H<sub>2</sub>O

<sup>1</sup>H NMR spectroscopy of homoligand complexes in bioinert solvents (water and DMSO) was used to prove the presence of the metal-to-ligand bond in solution, which would ensure the sensitization of europium ionic luminescence and ensure bright luminescence of the complex in solution, which is important i.e. for bioimaging application. This is possible due to the shift and broadening of the proton signals occur in the <sup>1</sup>H NMR spectra, if the ligand, to which the protons belong, is coordinated by the europium ion, which is due to the europium magnetic moment, of the europium CC. While in the case of complete dissociation there is no influence of the ligand proton signals on the europium ion luminescence [91–93]. As a result of partial dissociation, there would be both coordinated and non-coordinated carboxylate anions present in the solution; however fast exchange [Eu(carb)<sub>3</sub>  $\leftrightarrow$  Eu(carb)<sub>3-x</sub><sup>x+</sup> + x(carb)<sup>-</sup>] results in the presence of only one set of signals, their position intermediate between that of free and coordinated (carb)<sup>-</sup>. For example, fluorobenzoates demonstrated complete dissociation in water, metal to ligand bonds were observed only in organic solvents [24,94].



Figure 3. a) Proton numbering and suggested ligand coordination mode and b) <sup>1</sup>H-NMR spectra of K(carb) (5 g/L) and Eu(carb)<sub>3</sub>·  $3H_2O$  (2 g/L) in D<sub>2</sub>O (carb= boz, btz)

Indeed, <sup>1</sup>H NMR spectra of Eu(carb)<sub>3</sub>·  $3H_2O$  (carb = boz, btz) in D<sub>2</sub>O revealed the proton signals shifts; their values depended on the proton position (Figure 3b). So, the largest shift (ca. 0.4 ppm) was observed for proton (1) (Figure 3a) for both Eu(carb)<sub>3</sub>·  $3H_2O$  (carb = boz, btz) witnessing not only the presence of the Eu–carb bond, but also the nitrogen atom participation in the coordination. Indeed, in the absence of the heteroatom coordination, such as for europium benzofuranoate, both protons of the benzene ring (1) and (4) underwent the same shift (Figure S 9) [72]. The reason for the presence of N,O-coordination of lanthanide atom and the absence of E,O-coordination (E= O, S) of lanthanide atom is apparently the possibility of decoupling an unbound electron pair by the nitrogen atom, while oxygen or sulfur have a saturated electron shell, which is not capable of forming a bond with lanthanide atom. Indeed, according to CSD, O and S heteroatom coordination is untypical, unlike N heteroatom coordination.

<sup>1</sup>H NMR spectra of ML complexes also approved the suggested composition  $Eu(carb)_3 \cdot Q$  (carb = boz, btz; Q=Phen, BPhen) according to the integral intensity ratio of anionic and neutral ligand proton signals (Figure S 10;Figure S 11).

**Solubility** of the obtained complexes was measured in  $H_2O$ ,  $C_2H_5OH$ , MeC(O)Me, MeOH,  $CHCl_3$  which is important for OLED thin film deposition ( $C_2H_5OH$ , MeC(O)Me, MeOH,  $CHCl_3$ ) and for

bioimaging (H<sub>2</sub>O) (Table 1). It turned out that the heteroatom introduction into the aromatic ligand keeps high solubility of complexes even when ligand conjugated length increases for both ligands. Thus, the solubility of  $Eu(carb)_3 \cdot 3H_2O$  (carb = boz<sup>-</sup>, btz<sup>-</sup>) reaches 2.2-2.4 mmol/L which is lower than of fluorobenzoates [23,24,94], but higher than of the whole number of europium aromatic carboxylates, i.e. 3,4-dimethoxybenzoate Eu(dmb)<sub>3</sub>·4H<sub>2</sub>O (0.97 mmol/L) [66] and naphthoate Eu(nph)<sub>3</sub>·2H<sub>2</sub>O (0.0353 mmol/L) [95]. Solubility in organic solvents is even higher and riches 20.2 mmol/L for Eu(btz)<sub>3</sub>·3H<sub>2</sub>O in chloroform. This is an indirect proof of the presence of the N-Eu bond.

Neutral phenanthroline-based ligand introduction decreases the solubility: so, water solubility of ML complexes is too low to be measured. Nevertheless, the solubility in ethanol and chloroform still reaches 5 mmol/L, which is enough for thin film deposition.

So, ligand design allows us to obtain highly soluble complexes in organic solvents and water, which did not completely dissociate in solution due to suggested N,O-coordination.





Figure 4. Absorption spectra of a) K(carb) (acetonitrile,  $10^{-5}$  M), b) Eu(carb)<sub>3</sub>·  $3H_2O$  (EtOH,  $10^{-5}$ M), c) K(carb) (TD-DFT calculated) d) Eu(boz)<sub>3</sub> (TD-DFT calculated) e) Eu(boz)<sub>3</sub>· Q (EtOH,  $10^{-5}$ M), (Q=Phen, BPhen) f) Eu(btz)<sub>3</sub>· Q (EtOH,  $10^{-5}$ M), (Q=Phen, BPhen)

The ligand optical absorption determination revealed that molar extinction coefficient was, indeed, very high and reached  $\varepsilon(\lambda = 275 \text{ nm}) = 13500 (\text{M} \cdot \text{cm})^{-1}$  for K(boz), while for K(btz) was slightly lower (Figure 4a). For comparison,  $\varepsilon (\lambda = 265 \text{ nm}) = 500 (\text{M} \cdot \text{cm})^{-1}$  and  $(\lambda = 270 \text{ nm}) 4000 (\text{M} \cdot \text{cm})^{-1}$  were measured for pentafluorobenzoate [24] and benzoate anions [51], correspondingly. Both homoligand europium complexes demonstrated  $\varepsilon$  up to 60000 (M·cm)<sup>-1</sup>, which ensures their visually bright luminescence. Even the introduction of highly absorbing Phen ligand did not further increase absorption, unlike Phen-containing fluorobenzoates [16,23]. The use of BPhen instead of Phen resulted in Eu(btz)<sub>3</sub>·BPhen absorption up to 10<sup>5</sup> (M·cm)<sup>-1</sup>, which is a very high value.

**Luminescent properties.** Prior to examination of the luminescence properties of  $Tb^{3+}$  and  $Eu^{3+}$  complexes, triplet states of the obtained ligands were determined from the phosphorescence spectra of corresponding Gd(carb)<sub>3</sub>·3H<sub>2</sub>O (carb = boz<sup>-</sup>, btz<sup>-</sup>) from the maximum of the 0-0 phonon band [34,38,58,96] (Figure S 12). The triplet states of both ligands were about 20400 cm<sup>-1</sup>, demonstrating no dependence on second heteroatom, and should be optimal for sensitization of  $Eu^{3+}$  luminescence [97] and coincided with the excited state energy of  $Tb^{3+}$ .



Figure 5. Luminescence spectra ( $\lambda_{ex} = 337 \text{ nm}$ ) at 298 K a) of Eu(carb)<sub>3</sub>·3H<sub>2</sub>O (carb = boz, btz), b) of Tb(carb)<sub>3</sub>·3H<sub>2</sub>O (carb = boz, btz).

In the case of  $Tb(carb)_3 \cdot 3H_2O$  for both carb = boz, btz pure terbium ionic luminescence was observed, carb<sup>-</sup> luminescence was not present in the spectra (Figure 5b). However, the quantum yield of terbium

luminescence reached only 1-2% (Table S 1). At the same time, Tb(boz)<sub>3</sub>. Solv obtained from acetone (Table S 1), demonstrated quantum yield of 20%, which seem to witness the quenching role of water molecules. However, water quenches terbium luminescence rather ineffectively; so, benzoate hydrate [98], phenoxybenzoate hydrate [40], pyrazolecarboxylate hydrate [20] of terbium demonstrate quantum yields up to 100%. We suggest that in present case we observe the cumulative quenching effect by the ligand, which provides the back energy transfer, and the water molecules. The same effect was observed in the case of Tb(carb)<sub>3</sub>. Phen [99], containing hydroxocarboxylate anions (carb): they demonstrated low intensity or no terbium luminescence at room temperature due to the cumulative effect of OH-groups in the composition of anionic ligand and Phen molecules. This suggestion is supported by the absence of ligand luminescence in the spectra (Figure 5b) as well as by much higher quantum yields of europium complex luminescence, since europium is known to be quenched by water molecules much more effectively [100–102]. In case of benzofuranoates [103] terbium complex demonstrated low luminescence intensity at room temperature due to back energy transfer (Tb  $\rightarrow$  carb) was dominating, which was indicated by presence of ligand luminescence in the spectra.

The cumulative influence of the back energy transfer and vibrational quenching is solidly demonstrated by the study of luminescence thermal dependence in solution. While the intensity of europium luminescence is almost independent on temperature in ethanol and almost independent even in water, terbium luminescence decreases significantly in water, ethanol, chloroform and acetone upon heating (), witnessing that back energy transfer is responsible for this behavior. The value of the luminescence intensity decrease depends on the solvent, witnessing the role of OH-vibrational quenching.



Figure 6. LIR and S values of  $Eu_xTb_{1-x}(btz)_3 \cdot 3H_2O$ , dissolved in ethanol (2.5 g/l):a) x = 0.01 and b) x = 0.025

Such a behavior allowed suggesting these complexes for luminescent thermometry applications.

The solutions in ethanol, containing the mixture of  $xEu(btz)_3 \cdot 3H_2O$  and  $(1-x)Tb(btz)_3 \cdot 3H_2O$  with x = 0.01 and 0.025 were tested as luminescence thermometry materials (Figure 6). As the luminescence intensity ratio (LIR) the ratio between the intensities of terbium and europium luminescence bands at 545 and 612 nm, correspondingly, was taken. While the sensitivity of the obtained systems was characterized by the commonly used parameter  $S_r = 1/LIR(dLIR/dT)$ , where T is temperature [104,105]. Both systems demonstrated  $S_r$  values up to 2.4-2.8, which are rather high: indeed, the sensitivity of 2.8 in the physiological range (35-50°C) is the highest obtained for the Tb-Eu system. This is not surprising: as some

#### CEPTED MANUSCRIP

of us have theoretically shown [106] and experimentally verified [107], the sensitivity of the thermometer based on the energy transfer between Tb and Eu only depends on temperature and is limited by ca. 0.5%/K in the physiological range. In the present system the ligand triplet state is involved in the temperature-dependent luminescence processes, which allows the significant increase in the sensitivity up to the record value. Important is that the luminescence is reversible when the samples were cooled down to its original temperature (Figure S 28).

It is also important that the sensitivities of both systems are very similar despite very different LIR values. This allows suggesting that in 4-level systems (ground state + 3 excited states, i.e. of Tb, Eu and btz ligand) the sensitivity is also dependent only on the level energies and temperature.

Both europium carboxylate hydrates demonstrated solely europium luminescence with the quantum yields of 7%, which is higher than of terbium complexes, additionally speaking in favour of the suggested mechanism of terbium luminescence quenching. These quantum yields, though rather moderate, were not limited by quenching of the water molecules. Indeed, introduction of the neutral ligands – both *o*-phenanthroline (Phen) and batophenanthroline (BPhen) – into the europium coordination sphere resulted in a very moderate increase of the quantum yield (in case carb = btz) or even decrease of the quantum yield (carb = boz). At the same time sensitization efficiency reaches 50%, which means that quantum yields of all complexes  $Eu(carb)_3Q$  (carb = boz, btz;  $Q = 3H_2O$ , Phen, BPhen) was caused by a quenching mechanism, which is, however, not associated with water OH vibrations.

CER CER

Sample	Eu(bfc) <sub>3</sub> · 3H <sub>2</sub> O*	Eu(boz) <sub>3</sub> · 3H <sub>2</sub> O	Eu(boz) <sub>3</sub> . Phen	Eu(boz) <sub>3</sub> . BPhen	Eu(btz) <sub>3</sub> · 3H <sub>2</sub> O	Eu(btz) <sub>3</sub> . Phen	$Eu(btz)_3$ ·BPhen	Eu(dmb) <sub>3</sub> . 4H <sub>2</sub> O [108]	Eu(pfb) <sub>3</sub> · H <sub>2</sub> O [24]	$Eu(nph)_{3} \cdot 2H_{2}O [95]$
H <sub>2</sub> O	1.4/1.0	2.2/1.5	0.5/0.4	0.1/0.1	2.4/1.8	0.2/0.2	0.1/0.1	0.97/0.75	68.5/55.21	0.035/0.02
C <sub>2</sub> H <sub>5</sub> OH	6.2/4.3	11.5/8.0	6.1/5.0	5.2/5.0	9.5/7.0	5.8/5.0	4.9/5.0	n/a	n/a	n/a
$Me_2C(O)$	0.58/0.4	2.6/1.8	n/a	n/a	1.4/1.0	n/a	n/a	n/a	n/a	n/a
MeOH	4.6/3.2	15.9/11.0	n/a	n/a	3.5/2.6	n/a	n/a	n/a	n/a	n/a
CHCl <sub>3</sub>	5.5/3.8	17.3/12.0	4.9/4.0	4.1/4.0	20.2/15	4.6/4.0	4.9/5.0	n/a	n/a	n/a

# Table 1. Solubility of europium complexes (mmol·L<sup>1</sup>/g·L<sup>1</sup>)

n/a – not available

\*Eu(bfc)<sub>3</sub>·3H<sub>2</sub>O was obtain in previous work [72] and tested in the present work for comparison.

The latter conclusion was supported by the values of luminescence lifetimes which were almost independent on the neutral ligand Q in the europium coordination sphere ( $Q = H_2O$ , Phen, BPhen) and rather slightly depended on the anionic ligand (boz, btz) (Table S 1).

Despite rather low quantum yield values, luminescence intensity of europium and terbium complexes was visually bright due to the high absorption of the ligands. Indeed, luminosity  $L = \varepsilon * PLQY$  of the complexes reached 9800 (M·cm)<sup>-1</sup>; this is lower than luminosity of europium 2-fluorobenzoate with phenanthroline (26550 (M·cm)<sup>-1</sup>) with the record quantum yield among europium complexes, however, is higher than that of some widely known luminescent materials as europium complexes with dipicolinate [43] and salicylic derivates [109].

Thus, ligand design allowed obtaining brightly luminescent europium complexes due to the ligand high absorption, though the PLQY values turned out to be rather moderate. This allowed successfully using them as bioimaging materials (see Figure S 18).

**Quantum chemical calculations.** Since the X-ray structures of considered metal carboxylates were not available, we have performed a series of DFT calculations to determine the geometry. First of all, the most energetically favourable carb<sup>-</sup> coordination mode, namely O,O'; O,Ch or O,N, was determined (see Figure 6a for atom assignment).

The localization and the energy of frontier orbitals, HOMO and LUMO, are of crucial importance for luminescent molecules use in OLEDs. It is well known that the DFT method, suitable for ground state calculations, significantly overestimates the energies of virtual orbitals containing no electrons, to which the LUMO belongs. Therefore, in our work we used a dual-stage approach to determine the LUMO energy, based on the calculation of vertical excitations and then the energy gap ( $E_g$ ) from TD-DFT, followed by the calculation of the LUMO energy as  $E(LUMO) = E(HOMO) + E_g$  as reported in previous work of some of us [39]. To verify the reasonableness of vertical excitation calculations, the TD-DFT absorption spectra were compared with those experimentally observed and were found to be in a good agreement as described above (Figure 4).



Figure 7. DFT optimized geometry of K(carb) (a) and Eu(carb)<sub>3</sub> (b) molecules (carb= boz. btz).

Therefore, accurate calculations of HOMO and especially LUMO energy levels for voluminous Eu triscarboxylates in the framework of DFT and TD-DFT require remarkable computation resources. One can expect that ionic bond nature in both rare earth and alkaline carboxylates, as well as the localization of frontier orbitals on organic ligand species, make it possible to perform calculation of K(carb) molecules instead of Eu(carb)<sub>3</sub> to simplify the system. In the present work, we have performed calculation of HOMO and LUMO levels for both K and Eu carboxylates to check the correctness of this simplification to reveal the impact of central ion on coordination mode and frontier molecular orbitals.

DFT calculations of K(carb) molecules (carb= boz, btz) revealed that the geometry with bidentate O,O' coordination mode of carb<sup>-</sup> has the lowest energy (Figure 7), while the structure containing O,N or O,Ch coordinated ligand is less favourable (Table S 1). In contrast to K(carb), for Eu(carb)<sub>3</sub> the N,O ligand coordination is energetically favourable (Figure 7b, Table S 1). This difference the most probably originates from the smaller ionic radius of Eu<sup>3+</sup> (1.17Å for CN = 6) rather than of K<sup>+</sup> (1.38Å) which is comparable with the bite size of carb ligand (2.70Å). Therefore, based on the combination of theoretical DFT results and experimental data of <sup>1</sup>H NMR and solubility measurements we can conclude the participation of nitrogen heteroatom in the coordination of europium ion.



Figure 8. Localization of HOMO (a) and LUMO (b) of K(boz) based on DFT converged density.

Difference in coordination mode of carb<sup>-</sup> and especially in number of coordinated ligands in molecules of K(carb) and Eu(carb)<sub>3</sub> resulted in different localization of frontier orbitals. So, in K(carb) HOMO is localized on the organic ligand (Figure 8a), while LUMO is mostly localized on the potassium ion (Figure 8b).



Figure 9. Localization of HOMO (a) and LUMO (b) of Eu(boz)<sub>3</sub> based on DFT converged density.

For both europium complexes, HOMO and LUMO are localized on different organic ligands in europium coordination sphere (Figure 9). This significantly reduces the energy levels of HOMO and LUMO by ca. 1.5eV (Table 2) and makes it impossible to use the energies calculated for K(carb) as an estimation of those for  $Eu(carb)_3$  (See ESI for more details).

According to DFT and TD-DFT results,  $Eu(boz)_3$  and  $Eu(btz)_3$  molecules demonstrate quite similar values of frontier orbital energies. However, it is worth noting that HOMO level of  $Eu(btz)_3$  is by ca. 0.2 eV higher, what is not important for photoluminescence properties but may play an important role in OLED. Table 2. Calculated DFT and TD-DFT calculated energy levels of frontier molecular orbitals for K(carb) and Eu(carb)\_3, (carb= boz. btz).

	HOMO.	Gap.	LUMO*.
	eV	eV	eV
K(boz)	-6.128	4.443	-1.685
K(btz)	-6.027	4.331	-1.696
Eu(boz) <sub>3</sub>	-7.554	4.751	-2.803
Eu(btz) <sub>3</sub>	-7.322	4.294	-3.028

\* - estimation of LUMO energy value is done on the basis of HOMO level and Gap values.

Thus, the obtained europium CCs possessed photoluminescence and sufficient solubility, and they can be expected to demonstrate the charge carrier mobility as a consequence of the electron-depleted heteroaromatic ring system and the dipole-dipole interaction of conjugated systems presence, and their HOMO and LUMO energies were calculated. This made it possible to test the europium CC as a material for the emission layer in OLED devices

**OLED preparation and testing**. Calculated HOMO energies are very low, which made it impossible to properly select the hole-transport layer (HTL) for OLED fabrication based on these values. Thus, poly-TPD was selected as hole transport layer due to its insolubility in most solvents after post-treatment (annealing at 220 °C for 30 minutes in argon-glovebox atmosphere) [110], which allowed us to investigate solvent influence on emission layer (EML) performance in OLED. As electron transport layer (ETL) well known and often used TPBi material was selected [5,23,39,111].



So, OLED devices with heterostructure ITO/PEDOT-PSS/poly-TPD/EML/TPBi/ LiF/Al, where EML =  $Eu(carb)_3Q$  (carb= boz, btz,  $Q = 3H_2O$ , as well as Phen and BPhen), were obtained. The lifetimes of the emission layers coincided with those of powders, obtained from corresponding solvents (see ESI). To be able to properly compare the performance of the obtained OLED devices, the electroluminescence (EL) spectra were measured at the same conditions (see Experimental section), only varying the integration time; thus, intensity is given in sec<sup>-1</sup>, which corresponds to the counts divided by the integration time.

I-V curves of the devices with both EML =  $Eu(carb)_3 \cdot 3H_2O$  (carb = boz, btz) demonstrated rather high current densities, witnessing that indeed the obtained complexes possessed enough charge carrier mobility proving our complex design hypothesis (Figure S 19). At the same time only the device with EML =  $Eu(btz)_3 \cdot 3H_2O$  possessed europium ionic luminescence, in contrast to the one with EML =  $Eu(boz)_3 \cdot 3H_2O$ . Indeed, as mentioned above,  $Eu(boz)_3 \cdot 3H_2O$  is unstable in solution, so it may undergo rapid degradation in the thin film. In addition, it was shown, that  $Eu(btz)_3 \cdot 3H_2O$  thin film obtained from ethanol demonstrated better EL performance than the one obtained from chloroform (Figure S 20).

Device	EML	Solvent
designation		
OLED 1	$Eu(btz)_3 \cdot 3H_2O$	EtOH
OLED 2	$Eu(btz)_3 \cdot 3H_2O$	CHCl <sub>3</sub>
OLED 3	Eu(boz) <sub>3</sub> 3H <sub>2</sub> O	EtOH
OLED 4	Eu(btz) <sub>3</sub> ·Phen	EtOH
OLED 5	Eu(btz) <sub>3</sub> ·BPhen	EtOH
OLED 6	Eu(btz) <sub>3</sub> ·BPhen	CHCl <sub>3</sub>

Table 3. The list of obtained OLED devices:

The presence of the poly-TPD emission band in the EL spectra of OLED1 and OLED2 reveals that electron-hole recombination occurs on the interface between EML and the hole transport layer. Indeed, it witnesses the electron, rather than hole, transport properties of EML; besides, due to very low HOMO level of EML, this layer plays rather hole-blocking role. Therefore, to improve the situation Phen and BPhen neutral ligands with relatively high HOMO energies were introduced to decrease HOMO-HOMO gap between poly-TPD and EML. It is worth noting that BPhen, known as ETL material, possesses own charge carrier mobility.



Figure 11. a) The OLEDs electroluminescence spectra at 0.2 mA/mm<sup>2</sup>: OLED 5, OLED 6, OLED 1, OLED 4 and b) their I-V curves.

Indeed, OLED devices with EML =  $Eu(btz)_3 \cdot Q$  (Q = Phen, BPhen) demontrated no poly-TPD luminescence (Figure 11a (1), (2)). However, it turned out that Phen performed as an electron blocking layer due to the high LUMO energy. It was witnessed by the presence of TPBi emission band in the electroluminescence spectra, and resulted in the absence of the overall EL intensity increase. While BPhen introduction resulted in the disappearance of the parasitic HTL emission, and OLED5 and OLED6 demonstrated pure europium ionic electroluminescence, twice more intense than the one of OLED1 at the same current density; the solvent comparison again proved that ethanol is preferential over chloroform. Important is that PLQYs of  $Eu(btz)_3 \cdot Q$  (Q =  $3H_2O$ , Phen, BPhen) are similar (Table S 1), thus their different performance in OLEDs is due to different HOMO and LUMO energies.

So, the ligand design allowed us to obtain soluble europium CC with high enough electron mobility. Though their application in OLEDs was hampered by too low HOMO energy, introduction of neutral ligand allowed solving this problem. It is well-known that BPhen is usually used in order to increase efficiency of OLED device [7,25,112,113] because of its high electron mobility. However, in present work the I-V curves only differ in the  $V_{on}$  value due to the different HOMO-LUMO gaps of Eu(btz)<sub>3</sub>· 3H<sub>2</sub>O, Phen, and BPhen (Figure 11) that indicates enough mobility of the designed carboxylate ligands, and BPhen helps solving the problem of too low HOMO energy.

### 4. Conclusions

The approach toward the directed synthesis of new lanthanide CC as a precursor to OLED emission layer material was proposed, and its effectiveness was shown. As such an approach, the combination of ligand conjugation extension together with heteroatom introduction was proposed. The appropriate selection of the heteroatom nature and position, namely the introduction of nitrogen heteroatom, able to be coordinated to lanthanide ions, in the  $\alpha$ -position to the carboxy-group, allowed obtaining europium benzoxazole-2-carboxylates and benzothiazole-2-carboxylates with enough solubility and stability in solution, while the extended conjugation length together with the presence of two heteroatoms ensured both bright europium ionic luminescence and electron mobility. The properties of the obtained compounds were



mainly independent on the second non-nitrogen heteroatom nature; the biggest difference was observed in the complex stability in solution, which made  $btz^-$  derivative prospective candidates to luminescent materials, unlike boz<sup>-</sup> derivatives. At the same time, quantum yield was rather moderate, while HOMO energy was too high for effective electroluminescence; these obstacles were overcome by the neutral ligand introduction in the complex composition. As a result, mixed ligand Eu(btz)<sub>3</sub>·BPhen with effective electroluminescence was obtained.

### 5. Conflicts of interest

There are no conflicts to declare.

# 6. Acknowledgements

This work was supported by RFBR (project №№ 18-33-00250, 16-53-76018).

The research is carried out using the equipment of the shared research facilities of HPC computing resources at Lomonosov Moscow State University.

AM and US thank the Research Training Group GRK2039.

#### 7. Notes and references

- G. a. Crosby, R.E. Whan, R.M. Alire, Intramolecular Energy Transfer in Rare Earth Chelates. Role of the Triplet State, J. Chem. Phys. 34 (1961) 743. doi:10.1063/1.1731670.
- [2] K. Walzer, B. Maennig, M. Pfeiffer, K. Leo, Highly Efficient Organic Devices Based on Electrically Doped Transport Layers, Chem. Rev. 107 (2007) 1233–1271. doi:10.1021/cr050156n.
- [3] S. Zhang, G.A. Turnbull, I.D.W. Samuel, Highly efficient solution-processable europium-complex based organic lightemitting diodes, Org. Electron. 13 (2012) 3091–3096. doi:10.1016/j.orgel.2012.09.006.
- [4] P.P. Sun, J.P. Duan, H.T. Shih, C.H. Cheng, Europium complex as a highly efficient red emitter in electroluminescent devices, Appl. Phys. Lett. 81 (2002) 792–794. doi:10.1063/1.1497714.
- [5] L. Zhang, B. Li, S. Yue, M. Li, Z. Hong, W. Li, A terbium (III) complex with triphenylamine-functionalized ligand for organic electroluminescent device, J. Lumin. 128 (2008) 620–624. doi:10.1016/j.jlumin.2007.10.008.
- [6] Y. Yip, H. Wen, W. Wong, P.A. Tanner, K. Wong, Increased Antenna E ff ect of the Lanthanide Complexes by Control of a Number of Terdentate N-Donor Pyridine Ligands, Inorg. Chem. 51 (2012) 7013–7015.
- [7] P. Martín-Ramos, C. Coya, Á.L. Álvarez, M. Ramos Silva, C. Zaldo, J.A. Paixão, P. Chamorro-Posada, J. Martín-Gil, Charge transport and sensitized 1.5 μm electroluminescence properties of full solution-processed NIR-OLED based on novel Er(III) fluorinated β-diketonate ternary complex, J. Phys. Chem. C. 117 (2013) 10020–10030. doi:10.1021/jp402174s.
- [8] N.P. Kuz'mina, S. V. Eliseeva, Photo and electroluminescence of lanthanide(III) complexes, Russ. J. Inorg. Chem. 51 (2006) 73–88. doi:10.1134/S0036023606010141.
- [9] J.H. Jou, W. Ben Wang, S.Z. Chen, J.J. Shyue, M.F. Hsu, C.W. Lin, S.M. Shen, C.J. Wang, C.P. Liu, C.T. Chen, M.F. Wu, S.W. Liu, High-efficiency blue organic light-emitting diodes using a 3,5-di(9H-carbazol-9-yl)tetraphenylsilane host via a solution-process, J. Mater. Chem. 20 (2010) 8411–8416. doi:10.1039/c0jm01163k.
- [10] H. Esfahani, M. Ghorbanpor, A. Tanasan, Implantable Port Devices, Complications and outcome in Pediatric Cancer, a Retrospective Study., Iran. J. Pediatr. Hematol. Oncol. 6 (2016) 1–8. doi:10.1038/nature01430.1.
- [11] V. V. Utochnikova, A. Grishko, A. Vashchenko, A. Goloveshkin, A. Averin, N. Kuzmina, Lanthanide Tetrafluoroterephthalates for Luminescent Ink-Jet Printing, Eur. J. Inorg. Chem. 2017 (2017) 1–6. doi:10.1002/ejic.201700896.
- [12] P.J. Lammie, A.W. Hightower, F.O. Richards, R.T. Bryan, H.C. Spencer, D.F. McNeeley, M.B. McNeeley, M.L. Eberhard, Alterations in filarial antigen-specific immunologic reactivity following treatment with ivermectin and diethylcarbamazine, Am. J. Trop. Med. Hyg. 46 (1992) 292–295. doi:10.1063/1.120807.
- [13] F.C. Krebs, Polymer solar cell modules prepared using roll-to-roll methods: Knife-over-edge coating, slot-die coating and screen printing, Sol. Energy Mater. Sol. Cells. 93 (2009) 465–475. doi:10.1016/j.solmat.2008.12.012.

	ACCEPTED MANUSCRIPT
[14]	F.C. Krebs, S.A. Gevorgyan, J. Alstrup, A roll-to-roll process to flexible polymer solar cells: Model studies,
[15]	manufacture and operational stability studies, J. Mater. Chem. 19 (2009) 5442–5451. doi:10.1039/b823001c.
[15]	(2008) 2044–2049. doi:10.1002/adma.200702650.
[16]	A.S. Kalyakina, V. V. Utochnikova, M. Zimmer, F. Dietrich, A.M. Kaczmarek, R. Van Deun, A.A. Vashchenko, A.S. Goloveshkin, M. Nieger, M. Gerhards, U. Schepers, S. Bräse, Remarkable high efficiency of red emitters using Eu(+3) ternary complexes, Chem. Commun. 54 (2018) 5221–5224. doi:10.1039/C8CC02930J.
[17]	K. Junji, H. Hiromichi, K. Hongawa, K. Nagai, O. Katsuro, Bright red light-emitting organic electroluminescent devices having a europium complex as an emitter. Appl. Phys. Lett. 2124 (1994) 65. doi:10.1063/1.112810
[18]	V.M. Korshunov, S.A. Ambrozevich, I. V Taydakov, A.A. Vashchenko, Dyes and Pigments Novel $\beta$ -diketonate complexes of Eu 3 + bearing pyrazole moiety for bright photo- and electroluminescence, Dye. Pigment. 163 (2019) 291–299. doi:10.1016/j.dyepig.2018.12.006.
[19]	V.V. Utochnikova, N.P. Kuzmina, Photoluminescence of lanthanide aromatic carboxylates, Russ. J. Coord. Chem. Khimiya. 42 (2016). doi:10.1134/S1070328416090074.
[20]	V. V. Utochnikova, A.S. Kalyakina, I.S. Bushmarinov, A.A. Vashchenko, L. Marciniak, A.M. Kaczmarek, R. Van Deun, S. Bräse, N.P. Kuzmina, Lanthanide 9-anthracenate: solution processable emitters for efficient purely NIR emitting host-free OLED, J Mater Chem C. 4 (2016) 9848–9855.
[21]	A.Y. Grishko, V. V. Utochnikova, A.A. Averin, A. V. Mironov, N.P. Kuzmina, Unusual Luminescence Properties of Heterometallic REE Terephthalates, Eur. J. Inorg. Chem. 2015 (2015) 1660–1664. doi:10.1002/ejic.201403071.
[22]	V.V. Utochnikova, A.Y. Grishko, D.S. Koshelev, A.A. Averin, L.S. Lepnev, N.P. Kuzmina, Lanthanide heterometallic terephthalates: Concentration quenching and the principles of the "multiphotonic emission," Opt. Mater. (Amst). 74 (2017) 1–8. doi:10.1016/j.optmat.2017.02.052.
[23]	V. V. Utochnikova, N.N. Solodukhin, A.N. Aslandukov, L. Marciniak, I.S. Bushmarinov, A.A. Vashchenko, N.P. Kuzmina, Lanthanide tetrafluorobenzoates as emitters for OLEDs: New approach for host selection, Org. Electron. 44 (2017) 85–93. doi:10.1016/j.orgel.2017.01.026.
[24]	A.S. Kalyakina, V. V. Utochnikova, I.S. Bushmarinov, I. V. Ananyev, I.L. Eremenko, D. Volz, F. Rönicke, U. Schepers, R. Van Deun, A.L. Trigub, Y. V. Zubavichus, N.P. Kuzmina, S. Bräse, Highly Luminescent, Water-Soluble Lanthanide Fluorobenzoates: Syntheses, Structures and Photophysics, Part I: Lanthanide Pentafluorobenzoates, Chem A Eur. J. 21 (2016) 17021, 17022, doi:10.1002/chem.201501816
[25]	<ul> <li>A.S. Kalyakina, E.Y. Sokolova, A.A. Vaschenko, L.S. Lepnev, V. V Utochnikova, N.P. Kuzmina, High Efficiency</li> <li>Organic Light-Emitting Diode Based on UV Stable Terbium Aromatic Carboxylates, Proc. to SID Mid-Europe Chapter</li> <li>Spring Meet. 1 (2013) 19–20.</li> </ul>
[26]	<ul> <li>A.S. Kalyakina, V. V. Utochnikova, I.S. Bushmarinov, I.M. Le-Deygen, D. Volz, P. Weis, U. Schepers, N.P. Kuzmina,</li> <li>S. Bräse, Lanthanide Fluorobenzoates as Bio-Probes: a Quest for the Optimal Ligand Fluorination Degree, Chem A</li> <li>Eur. J. 23 (2017) 14944–14953. doi:10.1002/chem.201703543.</li> </ul>
[27]	V. V. Utochnikova, A.S. Kalyakina, L.S. Lepnev, N.P. Kuzmina, Luminescence enhancement of nanosized ytterbium and europium fluorides by surface complex formation with aromatic carboxylates, J. Lumin. 170 (2015) 633–640. doi:10.1016/j.jlumin.2015.03.033.
[28]	V. V. Utochnikova, A.S. Kalyakina, N.N. Solodukhin, A.N. Aslandukov, On the Structural Features of Substituted Lanthanide Benzoates, Eur. J. Inorg. Chem. 2019 (2019) 2320–2332. doi:10.1002/ejic.201801561.
[29]	Y. Cui, B. Chen, G. Qian, Lanthanide metal-organic frameworks for luminescent sensing and light-emitting applications, Coord. Chem. Rev. 273–274 (2014) 76–86. doi:10.1016/i.ccr.2013.10.023.
[30]	L. Shen, L. Yang, Y. Fan, L. Wang, J. Xu, Constructions of a series of lanthanide metal-organic frameworks: synthesis, structure, luminescence and white light emission, CrystEngComm. (2015). doi:10.1039/b000000x.
[31]	O. Kotova, V. Utochnikova, S. Samoilenkov, N. Kuzmina, Thin Films of Tb(pobz)3 (Hpobz = 2-phenoxybenzoic acid): Reactive CVD and Optical Properties, ECS Trans. 25 (2009) 1107–1114. doi:10.1017/CBO9781107415324.004
[32]	O. V. Kotova, V. V. Utochnikova, S. V. Samoylenkov, A.D. Rusin, L.S. Lepnev, N.P. Kuzmina, Reactive chemical vapour deposition (RCVD) of non-volatile terbium aromatic carboxylate thin films, J. Mater. Chem. 22 (2012) 4897–4903. doi:10.1039/C2JM13643K.
[33]	V. V Utochnikova, O. V Kotova, E.M. Shchukina, S. V Eliseeva, N.P. Kuz'mina, Gas-Phase Synthesis of Terbium and Lutetium Carboxylates, Russ, J. Inorg. Chem. 53 (2008) 1878–1884. doi:10.1134/S0036023608120085.
[34]	S. V. Eliseeva, JC.G. Bünzli, Lanthanide luminescence for functional materials and bio-sciences, Chem. Soc. Rev. 39 (2010) 189–227. doi:10.1039/B905604C.
[35]	<ul> <li>J.I. Urgel, B. Cirera, Y. Wang, W. Auwärter, R. Otero, J.M. Gallego, M. Alcamí, S. Klyatskaya, M. Ruben, F. Martín,</li> <li>R. Miranda, D. Ecija, J. V. Barth, Surface-Supported Robust 2D Lanthanide-Carboxylate Coordination Networks,</li> <li>Small, 11 (2015) 6358–6364. doi:10.1002/smll.201502761.</li> </ul>
	5. mail 11 (2013) 0500 0507. doi:10.1002/05001.201302/01.

[36] L.S. Lepnev, A.A. Vashchenko, A.G. Vitukhnovskii, S. V. Eliseeva, O. V. Kotova, N.P. Kuzmina, Degradation of organic light-emitting diodes based on different-ligand complexes of terbium (III) salicylate and 2-phenoxybenzoate, Bull. Lebedev Phys. Inst. 34 (2007) 102–106. doi:10.3103/S1068335607040021.

- [37] V. Utochnikova, A. Kalyakina, N. Kuzmina, New approach to deposition of thin luminescent films of lanthanide aromatic carboxylates, Inorg. Chem. Commun. 16 (2012) 4–7. doi:10.1016/j.inoche.2011.11.009.
- [38] V. V. Utochnikova, O. Pietraszkiewicz, M. Koźbiał, P. Gierycz, M. Pietraszkiewicz, N.P. Kuzmina, M. Kózbial, P. Gierycz, M. Pietraszkiewicz, N.P. Kuzmina, Mixed-ligand terbium terephthalates: Synthesis, photophysical and thermal properties and use for luminescent terbium terephthalate thin film deposition, J. Photochem. Photobiol. A Chem. 253 (2013) 72–80. doi:10.1016/j.jphotochem.2012.12.021.
- [39] A.N. Aslandukov, V. V. Utochnikova, D.O. Goriachiy, A.A. Vashchenko, D.M. Tsymbarenko, M. Hoffmann, M. Pietraszkiewicz, N.P. Kuzmina, E.S. Information, The development of a new approach toward lanthanide-based OLED fabrication: new host materials for Tb-based emitters, Dalt. Trans. 47 (2018) 16350–16357. doi:10.1039/C8DT02911C.
- [40] A.S. Kalyakina, V. V. Utochnikova, E.Y. Sokolova, A.A. Vaschenko, L.S. Lepnev, R. Van Deun, A.L.A.L. Trigub, Y.V.Y. V. Zubavichus, M. Hoffmann, S. Mühl, N.P. Kuzmina, A.A. Vashchenko, L.S. Lepnev, R. Van Deun, A.L. Trigub, Y. V. Zubavichus, M. Hoffmann, S. Mühl, N.P. Kuzmina, OLED thin film fabrication from poorly soluble terbium o-phenoxybenzoate through soluble mixed-ligand complexes, Org. Electron. Physics, Mater. Appl. 28 (2016) 319–329. doi:http://dx.doi.org/10.1016/j.orgel.2015.11.006.
- [41] Y. Yao, Y. Zhang, Q. Shen, K. Yu, Synthesis, Reactivity, and Structure of Mixed-Ligand Ytterbium Complexes Supported by β-Diketiminate, Organometallics. 21 (2002) 819–824. doi:10.1021/om010803a.
- [42] C. Ram, S. Sivamani, T. Micha Premkumar, V. Hariram, Computational study of leading edge jet impingement cooling with a conical converging hole for blade cooling, ARPN J. Eng. Appl. Sci. 12 (2017) 6397–6406. doi:10.1039/b000000x.
- [43] A. D'Aléo, A. Picot, P.L. Baldeck, C. Andraud, O. Maury, Design of dipicolinic acid ligands for the two-photon sensitized luminescence of europium complexes with optimized cross-sections, Inorg. Chem. 47 (2008) 10269–10279. doi:10.1021/ic8012975.
- [44] A. D'Aléo, A. Picot, A. Beeby, J.A.G. Williams, B. Leguennic, C. Andraud, O. Maury, Efficient sensitization process of europium, ytterbium and neodymium through charge-transfer excited state, Inorg. Chem. 47 (2008) 10258.
- [45] S. V Eliseeva, G. Auböck, F. Van Mourik, A. Cannizzo, B. Song, E. Deiters, A. Chauvin, M. Chergui, J.G. Bünzli, Multiphoton-excited luminescent lanthanide bioprobes : two- and three-photon cross sections of dipicolinates derivatives and binuclear helicates Laboratory of Lanthanide Supramolecular Chemistry, Swiss Federal Institute of Technology, Lausanne S1 S2, (2010) 5–11.
- [46] G.L. Law, K.L. Wong, C.W.Y. Man, W.T. Wong, S.W. Tsao, M.H.W. Lam, P.K.S. Lam, Emissive terbium probe for multiphoton in vitro cell imaging, J. Am. Chem. Soc, 130 (2008) 3714–3715. doi:10.1021/ja710418d.
- [47] Y.A. Belousov, V.V. Utochnikova, S.S. Kuznetsov, M.N. Andreev, V.D. Dolzhenko, A.A. Drozdov, New rare-earth metal acyl pyrazolonates: Synthesis, crystals structures, and luminescence properties, Russ. J. Coord. Chem. 40 (2014) 627–633. doi:10.1134/S1070328414090024.
- [48] J.-C.G. Bünzli, On the design of highly luminescent lanthanide complexes, Coord. Chem. Rev. 293–294 (2015) 19–47. doi:10.1016/j.ccr.2014.10.013.
- [49] I. Clarkson, R. Dickins, A. de Sousa, others, Non-radiative deactivation of the excited states of europium, terbium and ytterbium complexes by proximate energy-matched OH, NH and CH oscillators: an improved luminescence method for establishing solution hydration states, J. Chem. Soc. Perkin Trans. 2. (1999) 493–504.
- [50] S. Lis, Z. Hnatejko, P. Barczynski, M. Elbanowski, Luminescence studies of Eu(III) mixed ligand complexes, J. Alloys Compd. 344 (2002) 70–74. doi:10.1016/S0925-8388(02)00310-9.
- [51] V. V. Utochnikova, N.N. Solodukhin, A.A. Aslandukov, K. V. Zaitsev, A.S. Kalyakina, A.A. Averin, I.A. Ananyev, A. V. Churakov, N.P. Kuzmina, Highly Luminescent, Water-Soluble Lanthanide Fluorobenzoates: Syntheses, Structures and Photophysics. Part II: Luminescence Enhancement by p-Substituent Variation, Eur. J. Inorg. Chem. (2016).
- [52] P. Hänninen, H. Härmä, eds., Lanthanide Luminescence, Springer Berlin Heidelberg, Berlin, Heidelberg, 2011. doi:10.1007/978-3-642-21023-5.
- [53] Y. Zheng, J. Lin, Y. Liang, Y. Yu, Y. Zhou, C. Guo, S. Wang, H. Zhang, A novel way to enhance electroluminescence performance based on soluble binary and ternary europium 1,1,1-trifluoroacetylacetonate complexes, J. Alloys Compd. 336 (2002) 114–118. doi:10.1016/S0925-8388(01)01887-4.
- [54] Y. Lin, C.M. Wal, Supercritical Fluid Extraction of Lanthanides with Fluorinated [beta]-Diketones and Tributyl Phosphate, (2000) 2000.
- [55] V. V. Utochnikova, E. V. Latipov, A.I. Dalinger, Y. V. Nelyubina, A.A. Vashchenko, M. Hoffmann, A.S. Kalyakina, S.Z. Vatsadze, U. Schepers, S. Bräse, N.P. Kuzmina, Lanthanide pyrazolecarboxylates for OLEDs and bioimaging, J. Lumin. 202 (2018) 38–46. doi:10.1016/j.jlumin.2018.05.022.
- [56] S. V. Novikov, A. V. Vannikov, Charge induced energy fluctuations in thin organic films: Effect on charge transport, Synth. Met. 121 (2001) 1387–1388. doi:10.1016/S0379-6779(00)00994-2.
- [57] X. Yu, Q. Su, Photoacoustic and luminescence properties study on energy transfer and relaxation processes of Tb(III) complexes with benzoic acid, J. Photochem. Photobiol. A Chem. 155 (2003) 73–78. doi:10.1016/S1010-6030(02)00362-

# ACCEPTED MANUSCRIPT

3.

- [58] M. Hilder, M. Lezhnina, P.C. Junk, U.H. Kynast, Spectroscopic properties of lanthanoid benzene carboxylates in the solid state: Part 3. N-heteroaromatic benzoates and 2-furanates, Polyhedron. 52 (2013) 804–809. doi:10.1016/j.poly.2012.07.047.
- [59] J.-C.G. Bünzli, Review: Lanthanide coordination chemistry: from old concepts to coordination polymers, J. Coord. Chem. 67 (2014) 3706–3733. doi:10.1080/00958972.2014.957201.
- [60] V. V. Utochnikova, M.S. Abramovich, E. V. Latipov, A.I. Dalinger, A.S. Goloveshkin, A.A. Vashchenko, A.S. Kalyakina, S.Z. Vatsadze, U. Schepers, S. Bräse, N.P. Kuzmina, Brightly luminescent lanthanide pyrazolecarboxylates: Synthesis, luminescent properties and influence of ligand isomerism, J. Lumin. 205 (2019) 429–439. doi:10.1016/J.JLUMIN.2018.09.027.
- [61] P.S.S. Kalsi, K. S.P., P.S.S. Kalsi, Spectroscopy of Organic Compounds, 6th ed., New Age International, Delhi, 2004.
- [62] E. Kusrini, R. Adnan, M.I. Saleh, L.-K. Yan, H.-K. Fun, Synthesis and structure of dimeric anthracene-9-carboxylato bridged dinuclear erbium(III) complex, [Er2(9-AC)6(DMF)2(H2O)2], Spectrochim. Acta Part A Mol. Biomol. Spectrosc. 72 (2009) 884–889. doi:10.1016/j.saa.2008.12.011.
- [63] S. Shuvaev, V. Utochnikova, L. Marciniak, A. Freidzon, I. Sinev, R. Van Deun, R.O. Freire, Y. Zubavichus, W. Gruenert, N. Kuzmina, S. Shuvaev, V. Utochnikova, Ł. Marciniak, A. Freidzon, I. Sinev, R. Van Deun, R.O. Freire, Y. Zubavichus, W. Grunert, N. Kuzmina, Lanthanide complexes with aromatic o-phosphorylated ligands: synthesis, structure elucidation and photophysical properties, Dalt. Trans. 43 (2014) 3121–3136. doi:10.1039/c3dt52600c.
- [64] V.V. Utochnikova, A.D. Kovalenko, A.S. Burlov, L. Marciniak, I.V. Ananyev, A.S. Kalyakina, N.A. Kurchavov, N.P. Kuzmina, Lanthanide complexes with 2-(tosylamino)benzylidene-N-benzoylhydrazone, which exhibit high NIR emission, Dalton Trans. 44 (2015) 12660–12669. doi:10.1039/C5DT01161B.
- [65] V. V. Utochnikova, N.P. Kuzmina, Photoluminescence of lanthanide aromatic carboxylates, Russ. J. Coord. Chem. 42 (2016) 679–694. doi:10.1134/S1070328416090074.
- [66] W. Ferenc, A. Walkow-Dziewulska, Complexes of heavy lanthanides and yttrium with 3,4-dimethoxybenzoic acid, J. Therm. Anal. Calorim. 61 (2000) 923–933. doi:10.1023/A:1010111011794.
- [67] K.P. Zhuravlev, V.I. Tsaryuk, I.S. Pekareva, J. Sokolnicki, Z.S. Klemenkova, Europium and terbium ortho-, meta-, and para-methoxybenzoates: Structural peculiarities, luminescence, and energy transfer, J. Photochem. Photobiol. A Chem. 219 (2011) 139–147. doi:10.1016/j.jphotochem.2011.02.003.
- [68] V.I. Tsaryuk, K.P. Zhuravlev, A. V. Vologzhanina, V. a. Kudryashova, V.F. Zolin, Structural regularities and luminescence properties of dimeric europium and terbium carboxylates with 1,10-phenanthroline (C.N.=9), J. Photochem. Photobiol. A Chem. 211 (2010) 7–19. doi:10.1016/j.jphotochem.2010.01.012.
- [69] N. Arnaud, J. Georges, Comprehensive study of the luminescent properties and lifetimes of Eu3+ and Tb3+ chelated with various ligands in aqueous solutions: influence of the synergic agent, the surfactant and the energy level of the ligand triplet, Spectrochim. Acta Part A Mol. Biomol. Spectrosc. 59 (2003) 1829–1840. doi:10.1016/S1386-1425(02)00414-6.
- [70] M. Hilder, M.M. Lezhnina, P.C. Junk, U.H. Kynast, M.M. Lezhnina, Spectroscopic properties of lanthanoid benzene carboxylates in the solid state: Part 1, J. Photochem. Photobiol. A Chem. 202 (2009) 10–20. doi:10.1016/j.jphotochem.2008.10.026.
- [71] R. Koner, I. Goldberg, A unique two-dimensional coordi-nation network of 1-benzofuran-2,3-di-car- boxyl-ate with lanthanum(III) obtained by solvothermal synthesis, Acta Crystallogr. Sect. C Cryst. Struct. Commun. 65 (2009) 149– 151. doi:10.1107/S0108270109007161.
- [72] V.V. Utochnikova, D.S. Koshelev, A.V. Medvedko, A.S. Kalyakina, I.S. Bushmarinov, A.Y. Grishko, U. Schepers, S. Bräse, S.Z. Vatsadze, Europium 2-benzofuranoate: synthesis and use for bioimaging, Opt. Mater. (Amst). under revi (2017) 191–196. doi:10.1016/j.optmat.2017.05.038.
- [73] E.R. Trivedi, S. V. Eliseeva, J. Jankolovits, M.M. Olmstead, S. Petoud, V.L. Pecoraro, Highly emitting near-infrared lanthanide "encapsulated sandwich" metallacrown complexes with excitation shifted toward lower energy, J. Am. Chem. Soc. 136 (2014) 1526–1534. doi:10.1021/ja4113337.
- [74] G. Ning, X. Lu, W. Gong, J. Ye, H. Gao, Q. Wang, Y. Lin, Effect of auxiliary-ligand on assembly of lanthanide(III) complexes with quinoline-2-carboxylic acid: Synthesis, structure, photoluminescent and magnetic properties, Inorganica Chim. Acta. 384 (2011) 1–7. doi:10.1016/j.ica.2011.11.028.
- [75] W. Xu, Y. Zhou, D. Huang, W. Xiong, M. Su, K. Wang, S. Han, M. Hong, Crystal Structure, Multiplex Photoluminescence, and Magnetic Properties of a Series of Lanthanide Coordination Polymers Based on Quinoline Carboxylate Ligand, Cryst. Growth Des. 13 (2013) 5420–5432. doi:10.1021/cg401391b.
- [76] H. Zhang, R. Fan, P. Wang, X. Wang, S. Gao, Y. Dong, Y. Wang, Y. Yang, Structure variations of a series of lanthanide complexes constructed from quinoline carboxylate ligands: photoluminescent properties and PMMA matrix doping, RSC Adv. 5 (2015) 38254–38263. doi:10.1039/C5RA01796C.
- [77] J.C.G. Bünzli, A.S. Chauvin, H.K. Kim, E. Deiters, S. V. Eliseeva, Lanthanide luminescence efficiency in eight- and nine-coordinate complexes: Role of the radiative lifetime, Coord. Chem. Rev. 254 (2010) 2623–2633.

# doi:10.1016/j.ccr.2010.04.002.

- [78] J.C.G. Bünzli, S. Comby, A.S. Chauvin, C.D.B. Vandevyver, New Opportunities for Lanthanide Luminescence, J. Rare Earths. 25 (2007) 257–274. doi:10.1016/S1002-0721(07)60420-7.
- [79] V.Y. Khudoleeva, V. V. Utochnikova, A.S. Kalyakina, I.M. Deygen, A.A. Shiryaev, Ł. Marciniak, V.A. Lebedev, I. V. Roslyakov, A. V. Garshev, L.S. Lepnev, U. Schepers, S. Bräse, N.P. Kuzmina, Surface modified EuxLa1-xF3 nanoparticles as luminescent biomarkers: Still plenty of room at the bottom, Dye. Pigment. 143 (2017) 348–355. doi:10.1016/j.dyepig.2017.04.058.
- [80] O. V. Dolomanov, L.J. Bourhis, R.J. Gildea, J.A.K. Howard, H. Puschmann, OLEX2: A complete structure solution, refinement and analysis program, J. Appl. Crystallogr. 42 (2009) 339–341. doi:10.1107/S0021889808042726.
- [81] L.J. Bourhis, O. V. Dolomanov, R.J. Gildea, J.A.K. Howard, H. Puschmann, The anatomy of a comprehensive constrained, restrained refinement program for the modern computing environment - Olex2 dissected, Acta Crystallogr. Sect. A Found. Crystallogr. 71 (2015) 59–75. doi:10.1107/S2053273314022207.
- [82] G.M. Sheldrick, Crystal structure refinement with SHELXL, Acta Crystallogr. Sect. C Struct. Chem. 71 (2015) 3–8. doi:10.1107/S2053229614024218.
- [83] A.A. Granovsky, Firefly version 8., (n.d.).
- [84] Stuttgart, Cologne, Stuttgart/Cologne energy-consistent (ab initio) pseudopotentials, (n.d.).
- [85] O. Vechorkin, N. Hirt, X. Hu, Carbon dioxide as the C1 source for direct C-H functionalization of aromatic heterocycles, Org. Lett. 12 (2010) 3567–3569. doi:10.1021/ol101450u.
- [86] J.J.A.G. Kamps, R. Belle, J. Mecinović, Hydroxylamine as an oxygen nucleophile: substitution of sulfonamide by a hydroxyl group in benzothiazole-2-sulfonamides, Org. Biomol. Chem. 11 (2013) 1103–1108. doi:10.1039/C2OB26929E.
- [87] I.I.F. Boogaerts, S.P. Nolan, Carboxylation of C-H bonds using N -heterocyclic carbene gold(I) complexes, J. Am. Chem. Soc. 132 (2010) 8858–8859. doi:10.1021/ja103429q.
- [88] J.H. Musser, T.T. Hudec, K. Bailey, A Simple One-Step Synthesis of Alkyl Benzazol-2-carboxylates, Synth. Commun. 14 (1984) 947–953. doi:10.1080/00397918408063765.
- [89] I. V. Zavarzin, V.N. Yarovenko, E.I. Chernoburova, M.M. Krayushkin, I. Edition, Synthesis of monothiooxamides, Russ. Chem. Bull. 53 (2004) 476–477. doi:10.1023/B:RUCB.0000030819.80699.6e.
- [90] N. Suzuki, T. Goto, Synthesis of 4-thiazolone derivatives related to firefly oxyluciferin, Agric. Biol. Chem. 36 (1972) 2213–2221. doi:10.1080/00021369.1972.10860525.
- [91] B. Bleaney, Nuclear magnetic resonance shifts in solution due to lanthanide ions, J. Magn. Reson. 8 (1972) 91–100. doi:10.1016/0022-2364(72)90027-3.
- [92] H. Friebolin, J.K. Becconsall, Basic one-and two-dimensional NMR spectroscopy, VCH Weinheim, 1993.
- [93] D.M. Corsi, C. Platas-Iglesias, H. van Bekkum, J.A. Peters, Determination of paramagnetic lanthanide (III) concentrations from bulk magnetic susceptibility shifts in NMR spectra, Magn. Reson. Chem. 39 (2001) 723–726.
- [94] V. V. Utochnikova, N.N. Solodukhin, A.A. Aslandukov, K. V. Zaitsev, A.S. Kalyakina, A.A. Averin, I.A. Ananyev, A. V. Churakov, N.P. Kuzmina, Luminescence Enhancement by p -Substituent Variation, Eur. J. Inorg. Chem. 2017 (2017) 107–114. doi:10.1002/ejic.201600843.
- [95] W. Brzyska, A. Kula, Studies on the thermal decomposition of rare earth element complexes with 2-haphtoic acid, Thermodyn. Acta. 44 (1995) 1159–1169.
- [96] J.C.G. Bünzli, Lanthanide luminescence for biomedical analyses and imaging, Chem. Rev. 110 (2010) 2729–2755. doi:10.1021/cr900362e.
- [97] M. Latva, H. Takalo, V.-M. Mukkala, C. Matachescu, J.C. Rodríguez-Ubis, J. Kankare, Correlation between the lowest triplet state energy level of the ligand and lanthanide(III) luminescence quantum yield, J. Lumin. 75 (1997) 149–169. doi:10.1016/S0022-2313(97)00113-0.
- [98] J.H.S.K. Monteiro, A.L.B. Formiga, F.A. Sigoli, The influence of carboxilate, phosphinate and seleninate groups on luminescent properties of lanthanides complexes, J. Lumin. 154 (2014) 22–31. doi:10.1016/j.jlumin.2014.03.071.
- [99] N.N. Solodukhin, V. V. Utochnikova, L.S. Lepnev, N.P. Kuzmina, Mixed-ligand terbium hydroxyaromatic carboxylates with o-phenanthroline: luminescence quenching at 300 and 77K, Mendeleev Commun. 24 (2014) 91–93. doi:10.1016/j.mencom.2014.03.008.
- [100] E.A. Varaksina, I. V. Taydakov, S.A. Ambrozevich, A.S. Selyukov, K.A. Lyssenko, L.T. Jesus, R.O. Freire, Influence of fluorinated chain length on luminescent properties of Eu3+β-diketonate complexes, J. Lumin. 196 (2018) 161–168. doi:10.1016/j.jlumin.2017.12.006.
- [101] G. Stein, Energy gap law in the solvent isotope effect on radiationless transitions of rare earth ions, J. Chem. Phys. 62 (1975) 208. doi:10.1063/1.430264.
- [102] G.A. Chesnokov, M.A. Topchiy, A.F. Asachenko, N. V. Muravyev, L.I. Grishin, A.S. Nikiforova, V. V. Utochnikova, V.B. Rybakov, V.N. Khrustalev, M.S. Nechaev, No Title, Eur. J. Inorg. Chem. 2018 (2018) 805–815. doi:10.1002/ejic.201701154.
- [103] L. Piemontese, G. Carbonara, G. Fracchiolla, A. Laghezza, P. Tortorella, F. Loiodice, Convenient synthesis of some 3-

phenyl-1-benzofuran-2-carboxylic acid derivatives as new potential inhibitors of ClC-Kb channels, Heterocycles. 81 (2010) 2865–2872. doi:10.3987/COM-10-12070.

- [104] Y. Cui, F. Zhu, B. Chen, G. Qian, Metal–organic frameworks for luminescence thermometry, Chem. Commun. 51 (2015) 7420–7431. doi:10.1039/C5CC00718F.
- [105] C.D.S. Brites, A. Millán, L.D. Carlos, Lanthanides in Luminescent Thermometry, in: Handb. Phys. Chem. Rare Earths, 2016: pp. 339–427. doi:10.1016/bs.hpcre.2016.03.005.
- [106] A. Kovalenko, P.O. Rublev, L.O. Tcelykh, A.S. Goloveshkin, L.S. Lepnev, A.S. Burlov, A.A. Vashchenko, L. Marciniak, A.M. Magerramov, N.G. Shikhaliyev, S.Z. Vatsadze, V. V. Utochnikova, Lanthanide complexes with 2-(tosylamino)-benzylidene-N-(aryloyl)hydrazones universal luminescent materials, Chem. Mater. (2019) acs.chemmater.8b03675. doi:10.1021/acs.chemmater.8b03675.
- [107] V. Khudoleeva, L. Tcelykh, A. Kovalenko, A. Kalyakina, A. Goloveshkin, L. Lepnev, V. Utochnikova, Terbiumeuropium fluorides surface modified with benzoate and terephthalate anions for temperature sensing: Does sensitivity depend on the ligand?, J. Lumin. 201 (2018) 500–508. doi:10.1016/j.jlumin.2018.05.002.
- [108] W. Ferenc, A. Walków-Dziewulska, Thermal and spectral properties of 2,3-, 2,4- and 3,4- dimethoxybenzoates of light lanthanides, J. Therm. Anal. Calorim. 70 (2002) 949–958. doi:10.1023/A:1022280909229.
- [109] † Stéphane Petoud, † Seth M. Cohen, ‡ and Jean-Claude G. Bünzli, † Kenneth N. Raymond\*, Stable Lanthanide Luminescence Agents Highly Emissive in Aqueous Solution: Multidentate 2-Hydroxyisophthalamide Complexes of Sm3+, Eu3+, Tb3+, Dy3+, (2003). doi:10.1021/JA0379363.
- [110] T.-Y. Kim, J.-H. Jung, J.-B. Kim, D.-G. Moon, Achieving high efficiency by high temperature annealing of hole transporting polymer layer in solution-processed organic light-emitting devices, Synth. Met. 232 (2017) 167–170. doi:10.1016/j.synthmet.2017.08.004.
- [111] N. Thejo Kalyani, S.J. Dhoble, Organic light emitting diodes: Energy saving lighting technology—A review, Renew. Sustain. Energy Rev. 16 (2012) 2696–2723. doi:10.1016/j.rser.2012.02.021.
- [112] W. Gaynor, S. Hofmann, M.G. Christoforo, C. Sachse, S. Mehra, A. Salleo, M.D. McGehee, M.C. Gather, B. Lüssem, L. Müller-Meskamp, P. Peumans, K. Leo, Color in the corners: ITO-free white OLEDs with angular color stability., Adv. Mater. 25 (2013) 4006–13. doi:10.1002/adma.201300923.
- [113] C.J. Weiss, T.J. Marks, Organo-f-element catalysts for efficient and highly selective hydroalkoxylation and hydrothiolation, Dalt. Trans. 39 (2010) 6576. doi:10.1039/c003089a.
- [114] K. Binnemans, Interpretation of europium(III) spectra, Coord. Chem. Rev. 295 (2015). doi:10.1016/j.ccr.2015.02.015.
- [115] M.H. V. Werts, R.T.F. Jukes, J.W. Verhoeven, V.J.W. Werts M.H. V., Jukes R.T.F., The emission spectrum and the radiative lifetime of Eu3+ in luminescent lanthanide complexes, Phys. Chem. Chem. Phys. 4 (2002) 1542–1548. doi:10.1039/b107770h.

CEP C

New benzoxazolates and benzothiazolates of some lanthanides were obtained.

Complex properties are mainly independent on the second (O or S) heteroatom nature.

Mixed-ligand europium benzothiazolate with batophenanthroline was successfully used in solution-based OLED.

Bimetallic terbium-europium benzothiazolate demonstrates temperature-dependent luminescence with high sensitivity (2.8%/K).