This article was downloaded by: [Memorial University of Newfoundland] On: 15 July 2014, At: 00:13 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



Molecular Crystals and Liquid Crystals Publication details, including instructions for authors and subscription information: http://www.tandfonline.com/loi/gmcl20

Electroluminescence Characteristics of a New Green-Emitting Phenothiazine Derivative with Biphenyl Benzimidazole Substituent

Sun-Hee Lee $^{\rm a}$, Man Su Kim $^{\rm a}$, Yong-Bum Cha $^{\rm b}$, Kwang-Hyun Ahn $^{\rm b}$ & Young Chul Kim $^{\rm a}$

 $^{\rm a}$ Department of Chemical Engineering and MRCID , Kyung Hee University , Yongin-si, Gyeonggi-do, Korea

^b Department of Applied Chemistry and MRCID , Kyung Hee University , Yongin-si, Gyeonggi-do, Korea Published online: 19 Apr 2010.

To cite this article: Sun-Hee Lee, Man Su Kim, Yong-Bum Cha, Kwang-Hyun Ahn & Young Chul Kim (2010) Electroluminescence Characteristics of a New Green-Emitting Phenothiazine Derivative with Biphenyl Benzimidazole Substituent, Molecular Crystals and Liquid Crystals, 520:1, 36/[312]-43/[319], DOI: 10.1080/15421401003608378

To link to this article: http://dx.doi.org/10.1080/15421401003608378

PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms &

Conditions of access and use can be found at <u>http://www.tandfonline.com/page/terms-and-conditions</u>



Electroluminescence Characteristics of a New Green-Emitting Phenothiazine Derivative with Biphenyl Benzimidazole Substituent

SUN-HEE LEE,¹ MAN SU KIM,¹ YONG-BUM CHA,² KWANG-HYUN AHN,² AND YOUNG CHUL KIM¹

¹Department of Chemical Engineering and MRCID, Kyung Hee University, Yongin-si, Gyeonggi-do, Korea ²Department of Applied Chemistry and MRCID, Kyung Hee University, Yongin-si, Gyeonggi-do, Korea

We report on the synthesis and electroluminescence characteristics of a new green-emitting material, 3,7-bis(1-(biphenyl-4-yl)benzimidazol-2-yl)10-methylphenothiazine (PhBBMP) containing the electron-donating phenothiazine core and the electron-accepting biphenyl benzimidazole substituent. An optimized OLED device with the structure of [ITO/NPB (40 nm)/PhBBMP (30 nm)/BCP (10 nm)/TPBI (30 nm)/LiF (1 nm)/Al (100 nm)] exhibited a luminous efficiency of 4.5 cd/A and an external quantum efficiency of 0.9% at 100 mA/cm², and the maximum luminance of 12,000 cd/m² with the CIE 1931 chromaticity coordinates of (0.21, 0.54). A more balanced charge carrier injection and the charge confinement in the emitting layer cooperatively contributed to improve the performance of the device prepared with the PhBBMP emitting layer.

Keywords Biphenyl benzimidazole; green OLED; phenothiazine

Introduction

Organic light-emitting diode (OLED) [1] is attracting increasing interest due to its potential applicability to large area displays and two-dimensional light sources, and small full-color display products are already on the market. Accordingly, tremendous efforts have been made over the recent two decades to improve the emission efficiency of OLEDs by developing either high efficiency materials or efficient device structures. In order to fabricate full-color displays or white light sources, it is also of essential importance to have blue-, green-, and red-emitting materials with high color purity and long-term stability as well as high luminous quantum yield.

 π -conjugated donor-acceptor (D-A) molecules have been successfully employed in OLEDs as high efficiency emitting materials [2–6] because energy transfer and charge carrier recombination can easily occur within the molecular structure to give

Address correspondence to Prof. Young Chul Kim, Department of Chemical Engineering, Kyung Hee University, Yongin-si, Gyeonggi-do 446-701, Korea. E-mail: kimyc@khu.ac.kr

a high emission efficiency. In this work, we synthesized a new green-emitting D-A molecule with a phenothiazine core and two biphenylbenzimidazole substituents. Phenothiazine is a well known electron donor with electron-rich sulfur and nitrogen heteroatoms [7] and its unique non-planar geometry can make the molecule have an amorphous nature with decreased crystallinity, resulting in an enhanced device performance [8,9]. Benzimidazole group was introduced to the material as an electron acceptor due to its high electron affinity [10,11]. We also prepared the OLED devices with three different multilayer structures using the new material as the emitting layer, and characterized their performance to optimize the device structure.

Experimental

Synthesis of PhBBMP

3,7-Bis(1-(biphenyl-4-yl)benzimidazol-2-yl)10-methylphenothiazine (PhBBMP) **4** was prepared according to Scheme 1. 10H-Phenothiazine **1** was alkylated to give 10-methylphenothiazine **2** in an excellent yield (99%). Vilsmeier-Haak reaction of 10-methylphenothiazine **2** by phosphorus(III) oxychloride and DMF in 1,2-dichlor-oethane afforded 10-methylphenothiazine-3,7-dicarbaldehyde **3** (53%). 3,7-Bis(1-(biphenyl-4-yl)benzimidazol-2-yl)10-methylphenothiazine **4** was obtained by the oxidative coupling of N-(biphenyl-4-yl)benzene-1,2-diamine with **3** under the treatment of sodium metabisulfite. The compound was purified by column chromatography using hexane and ethyl acetate (78%).

10-Methylphenothiazine (2), Mp: $101^{\circ}C$. ¹H NMR (300 MHz, CDCl₃): δ 7.15–7.20(m, 4H), 6.87–6.98(m, 4H), 3.41(s, 3H).

¹³C NMR (75 MHz, CDCl₃): δ 145.74, 127.37, 127.08, 123.29, 122.38, 114.01, 35.22.

10-Methylphenothiazine-3,7-dicarbaldehyde (3), Mp: $153^{\circ}C$. ¹H NMR (300 MHz, CDCl₃): δ 9.83(s, 2H), 7.69(dd, J = 8.40, J = 1.80 Hz, 2H), 7.16(d, J = 1.80 Hz, 2H), 6.92(d, J = 8.40 Hz, 2H), 3.49(s, 3H).

¹³C NMR (75 MHz, CDCl₃): δ 189.85, 149.22, 131.88, 130.48, 127.78, 123.27, 114.47, 36.20.



Scheme 1. Reagent and conditions: (a) NaH, CH₃I, THF, 0°C; (b) POCl₃, DMF, ClCH₂CH₂Cl, 90°C; (c) N-(biphenyl-4-yl)benzene-1,2-diamine, Na₂S₂O₅, DMF, 150°C.

3,7-Bis(1-(biphenyl-4-yl)benzimidazol-2-yl)10-methylphenothiazine (4), Mp: 300°C. ¹H NMR (300 MHz, CDCl₃): δ 7.80(d, 2H), 7.56–7.66(dd, 8H), 7.18–7.41(m, 20H), 6.55(d, 2H), 3.20(s, 3H).

¹³C NMR (75 MHz, CDCl₃): δ 151.16, 145.88, 141.55, 139.56, 137.02, 135.73, 128.98, 128.73, 128.49, 127.94, 127.90, 127.62, 127.10, 123.95, 123.93, 123.35, 123.16, 123.08, 119.40, 113.72, 110.40, 35.45.

Fabrication of OLEDs

ITO-coated glass substrates with a surface resistance of 10 Ω /sq were patterned by photholithography and cleaned with trichloroethylene, acetone, deionized water, and isopropyl alcohol in an ultrasonic bath. The cleaned ITO surface was oxygen plasma-treated to improve adhesion with organic materials. OLED devices with three different structures were prepared by using PhBBMP as the emitting layer, as depicted in Figure 1. In the devices, N,N'-bis(1-naphthyl)-N,N'-diphenyl-1,1'-biphenyl-4,4'diamine (NPB) was used as a hole transport layer (HTL), 2,9-dimethyl-4,7diphenyl-1,10-phenanthroline (BCP) as a hole blocking layer (HBL), 1,3,5-tris (N-phenylbenzimidazol-2-yl)benzene (TPBI) and tris-(8-hydroxyquinoline) aluminum (Alq₃) as an electron transport layer (ETL), and the bilayer of lithium fluoride (LiF) and aluminum (Al) as a cathode. All organic and metal layers were deposited by thermal evaporation under ~10⁻⁶ torr on the ITO substrate and the deposition rates were 1.0, 0.1, 3~4Å/s for the organic, LiF, and Al layers, respectively. Active emitting area of the devices was defined to be 3 × 3 mm².

Measurements

UV-vis absorption and photoluminescence (PL) spectra were obtained using an Agilent 8453 UV-visible spectrophotometer and a PTI QuantaMasterTM spectro-fluorometer, respectively. The current-voltage-luminance (J-V-L) characteristics of the devices were measured with a JBS IVL-300 EL characterization system and a Keithley 2400 sourcemeter. The highest occupied molecular orbital (HOMO) energy level of PhBBMP was measured by cyclic voltammetry (CV) and the lowest unoccupied molecular orbital (LUMO) energy level was obtained by adding the optical absorption band gap to the HOMO level.



Figure 1. Structures and energy level diagrams of the OLED devices; (a) device 1, (b) device 2, (c) device 3.

Results and Discussion

Thermal and Optical Properties

The thermal properties of PhBBMP were examined by thermogravimetric analysis (TGA) and differential scanning calorimetry (DSC) as shown in Figure 2. The TGA thermogram of PhBBMP measured at a rate of 5°C/min showed that the material has a fairly high thermal decomposition temperature (T_d) of 394°C. In the DSC thermograms, both melting and recrystallization behavior were not observed when heated up to 300°C and then cooled to room temperature at a scan rate of 5°C/min. On the second heating, however, the thermogram showed a relatively high glass transition temperature (T_g) of 162°C, which is far above the normal operating temperature of OLED. It is considered that the non-planar structure of PhBBMP with biphenyl benzimidazole group prevents close packing of the molecules. Accordingly, the PhBBMP layer can remain homogeneous and amorphous under the joule heating during the device operation.

Figure 3 presents the normalized UV-vis absorption and PL spectra of PhBBMP in dilute toluene solution (10^{-5} M) . When the PhBBMP solution was excited at the two absorption peak wavelengths of 294 and 382 nm, the solution exhibited almost the same PL spectrum centered at 502 nm but the PL intensity was much stronger when excited at 294 nm. This implies that there is a large Stokes shift between absorption and emission. It has been reported that the two biphenyl rings in the benzimidazole substituent have different geometric structures between the ground and the excited states because the twisted phenyl rings transform into planar structure when excited, leading to a large Stokes shift [12–14]. A large Stokes shift sometimes enhances the emission efficiency by preventing the self-absorption of the emitted light.

Electroluminescence Properties of OLED Devices

The current density-voltage-luminance characteristics of the OLED devices are shown in Figure 4. As shown in Figure 4(a), device 1 with the TPBI (30 nm) and



Figure 2. TGA and DSC thermograms of PhBBMP measured at a scan rate of 5° C/min in nitrogen.



Figure 3. UV-vis absorption and photoluminescence spectra of PhBBMP in dilute toluene solution.



Figure 4. (a) Luminance and current density vs. voltage, and (b) luminous efficiency and external quantum efficiency vs. current density characteristics of device 1 (\Box,\blacksquare), device 2 (\triangle,\blacktriangle), and device 3 (\bigcirc,\bullet).



Figure 5. Electroluminescence spectrum of device 3.

Alq₃ (10 nm) layers as ETLs required a high driving voltage of 13 V to give a luminance of 100 cd/m², however, the driving voltage was reduced to 9 V when the TPBI (40 nm) single layer was employed as ETL (device 2). Although device 2 has a higher energy barrier for electron injection (1.2 eV) from cathode to ETL than that of device 1 (1.0 eV), the higher electron mobility in the TPBI layer than in the Alq₃ layer could reduced the driving voltage [15–19]. On the other hand, device 2 gave a lower luminous efficiency than device 1 as shown in Figure 4(b), which can result from a poorly balanced charge carrier injection.

To obtain an OLED device with a higher luminous efficiency as well as a lower driving voltage, we introduced the BCP (10 nm) layer as a hole blocking layer (HBL) between EML (PhBBMP) and ETL (TPBI) (device 3). Device 3 demonstrated a luminous efficiency of 4.5 cd/A at a current density of 100 mA/cm^2 and a driving voltage of 10 V. The luminous efficiency was increased by 1.7 cd/A compared with device 2 and the driving voltage was reduced by 3 V compared with device 1. As illustrated in Figure 1(b), device 2 has a higher energy barrier for electron injection than that for hole injection therefore, without an HBL, a considerable amount of holes can transport across EML to cause current loss. It is possible to confine the injected holes in EML by introducing an HBL such as BCP that has a deep HOMO level of 6.7 eV, as shown in Figure 1(c), and hole confinement in EML can increase the chance of charge carrier recombination in EML to generate more excitons. Accordingly, device 3 with the optimized device structure exhibited the best performance not

	Turn-on voltage		$\eta_L [cd/A]$	$\eta_P [\mathrm{lm/W}]$	η_{ext} [%]	CIE coordinates
Device	[V]	$L_{\rm max} [{\rm cd}/{\rm m}^2]$	$100 \mathrm{mA/cm^2}$	$100 \mathrm{mA/cm^2}$	$100 \mathrm{mA/cm^2}$	[x, y]
1	13	8500	4.2	0.6	0.9	0.22, 0.55
2	9	8800	2.8	0.6	0.6	0.22, 0.56
3	10	12000	4.5	0.9	1.0	0.21, 0.54

Table 1. Electroluminescence characteristics of the OLED devices

only by the efficient electron injection through TPBI but also by a more effective recombination of injected holes and electrons in EML.

Also, device 3 showed a green emission spectrum peaked at 502 nm (Fig. 6) with the CIE 1931 chromaticity coordinates of (0.20, 0.55) at a current density of 100 mA/cm^2 . EL characteristics of devices 1–3 were summarized in Table 1.

Conclusions

We synthesized a new green-emitting material, 3,7-bis(1-(biphenyl-4-yl)-benzimidazol-2-yl)-10-methylphenothiazine (PhBBMP), which contains the electron-donating phenothiazine core and the electron-accepting biphenyl benzimidazole substituent. We also prepared the OLED devices with three different multilayer structures using the new material as the emitting layer, and characterized their performance to optimize the device structure. The optimized device with the configuration of [ITO/NPB (40 nm)/PhBBMP (30 nm)/BCP (10 nm)/TPBI (30 nm)/LiF (1 nm)/Al (100 nm)] exhibited a luminous efficiency of 4.5 cd/A and an external quantum efficiency of 0.9% at 100 mA/cm², and the maximum luminance of 12000 cd/m² with the CIE 1931 chromaticity coordinates of (0.20, 0.55). The TPBI layer acted as an efficient ETL for the device and the BCP layer employed as an HBL successfully confined holes and excitons in EML to enhance the emission efficiency.

Acknowledgement

This research was supported by Basic Science Program through the National Research Foundation of Korea (NRF) funded by the Ministry of Education, Science and Technology (Grant No. 2009-0090177), and the "GRRC" Project of Gyeonggi Provincial Government, ROK.

References

- [1] Tang, C. W. & VanSlyke, S. A. (1987). Appl. Phys. Lett., 51, 913.
- [2] Ge, Z., Hayakawa, T., Ando, S., Ueda, M., Ajiike, T., Miyamoto, H., Kajita, T., & Kakimoto, M. (2008). Adv. Func. Mater., 18, 584.
- [3] Thomas, K. R. J., Lin, J. T., Tao, Y. T., & Chuen, C. H. (2002). Chem. Mater., 14, 3852.
- [4] Kulkarni, A. P., Kong, X., & Jenekhe, S. A. (2006). Adv. Func. Mater., 16, 1057.
- [5] Doi, H., Kinoshita, M., Okumoto, K., & Shirota, Y. (2003). Chem. Mater., 15, 1080.
- [6] Chiang, C. L., Wu, M. F., Dai, D. C., Wen, Y. S., Wang, J. K., & Chen, C. T. (2005). Adv. Func. Mater., 15, 231.
- [7] Spreitzer, H. & Daub, J. (1996). Chem. Eur. J., 2, 1150.
- [8] Kramer, C. S., Zeitler, K., & Muller, T. J. J. (2000). Org. Lett., 2, 3723.
- [9] Ranasinghe, M. I., Varnavski, O. P., Pawlas, J., Hauck, S. I., Louie, J., Hartwig, J. F., & Goodson, T. (2002). J. Am. Chem. Soc., 124, 6520.
- [10] Shirota, Y. & Kageyama, H. (2007). Chem. Rev., 107, 953.
- [11] Chen, C. H., Huang, W. S., Lai, M. Y., Tsao, W. C., Lin, J. T., Wu, Y. H., Ke, T. H., Chen, L. Y., & Wu, C. C. (2009). Adv. Func. Mater., 19, 2661.
- [12] Sakamoto, M., Cai, X., Hara, M., Tojo, S., Fujitsuka, M., & Majima, T. (2004). J. Phys. Chem., 108, 8147.
- [13] Hiratsuka, H., Yamazaki, T., Maekawa, Y., Hikida, T., & Mori, Y. (1986). J. Phys. Chem., 90, 774.
- [14] Wang, B. Ch., Liao, H. R., Yeh, H. Ch., Wu, W. Ch., & Chen, Ch. T. (2005). J. Luminescence., 113, 321.

- [15] Li, Y., Fung, M. K., Xie, Z., Lee, S.-T., Hung, L. S., & Shi, J. (2002). Adv. Mater., 14, 1317.
- [16] Hung, L. S., Tang, C. W., & Mason, M.G. (1997). Appl. Phys. Lett., 70, 152.
- [17] Xie, Z. Y., Hung, L. S., & Lee, S. T. (2001). Appl. Phys. Lett., 79, 1048.
- [18] Xie, Z. Y., Wong, T. C., Hung, L. S., & Lee, S. T. (2002). Appl. Phys. Lett., 80, 1477.
- [19] Wong, T. C., Kovac, J., Lee, C. S., Hung, L. S., & Lee, S. T. (2001). Chem. Phys. Lett., 334, 61.