

View Article Online View Journal

RSC Advances

This article can be cited before page numbers have been issued, to do this please use: R. PVRK, P. K. Jella, K. P. Gangavarapu and A. R. Srivastava, *RSC Adv.*, 2014, DOI: 10.1039/C4RA10249E.



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. This Accepted Manuscript will be replaced by the edited, formatted and paginated article as soon as this is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/advances

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxx

Synthesis, Characterization and Photocatalytic activity of Ag-TiO₂ Nanoparticulate film

P.V.R.K.Ramacharyulu,*^a J. Praveen kumar^a, G.K. Prasad*^a, and A.R.Srivastava^a

Received (in XXX, XXX) Xth XXXXXXXX 20XX, Accepted Xth XXXXXXXX 20XX 5 DOI: 10.1039/b000000x

Ag-TiO₂ nanoparticulate film was synthesized by dip coating followed by adsorption and photoreduction in UVA light, characterized by transmission electron microscopy, scanning electron microscopy, energy dispersive analysis of X-rays, glancing angle X-ray diffractometry, UV-Vis absorption spectrophotometry techniques. The data indicated the presence of TiO₂ particles of anatase phase of size varying from 5-15 nm, Ag nanoparticles of size varying from 10-20 nm, and also indicated the added visible light activity in Ag-TiO₂ nanoparticles film. Photocatalytic degradation of methyl parathion (O,O-dimethyl O-(4nitrophenyl) phosphorothioate), a well known pesticide in aqueous solution was studied using Ag-TiO₂ nanoparticulate film and the data was compared with TiO₂ nanoparticulate film. Photocatalytic degradation reactions demonstrated pseudo first order behaviour. Methyl parathion was found to be degraded initially to paraoxon which further was degraded to p-nitrophenol, trimethyl ester of phosphoric

acid, trimethyl ester of phosphothioic acid, and finally to phosphate ion. Minute amounts of carbon

INTRODUCTION

dioxide and acetaldehyde were also detected.

Published on 26 November 2014. Downloaded by Memorial University of Newfoundland on 27/11/2014 04:07:37.

Organophosphorous compounds (OPC) have been expansively used as insecticides, pesticides, and acaricides to protect the crops. They inhibit acetylcholinesterase enzyme in mammalians and were found to be highly toxic to human beings.¹⁻³ Methyl parathion (MP) is one such OPC which is being used in many 25 countries worldwide as a fumigant and acaricide for protective treatment of a wide variety of crops. It is classified as an acutely

toxic pesticide by the US EPA (2003). It is slowly hydrolyzed to other toxic chemical species in aqueous solution and is quite persistent in environment posing threat to people who get ³⁰ exposed. Therefore, it is important to develop methods to eliminate the OPC like MP from contaminated water streams.⁴⁻⁶

Photocatalysis is one of the advanced oxidation processes that have been used to degrade toxic OPCs in contaminated water streams. When a photocatalyst is irradiated with light whose 35 energy is greater than band gap, charge carriers are generated and react with water and surrounding oxygen species to form highly reactive hydroxyl (\cdot OH) and superoxide anion(O_2^{-1}) radicals.⁷⁻⁹ These species in turn react with pollutant molecules like OPCs and degrade them to innocuous products. Recently, titania 40 materials were used to photocatalytically degrade organophosphorous pesticides such as malathion, diazon, fenitrothion, and parathion.¹⁰ Doong and Chang have studied photocatalytic degradation of organophosphorous pesticides and attributed the decomposition of P-S and C-S bonds as a cause for

⁴⁵ their degradation.¹¹ Zhang has reported the photocatalytic degradation of methamidophos by UV radiation in the presence

of nano TiO₂.¹² More recently, acephate, a well known insecticide was decomposed by photocatalysis treatment assisted by nano TiO₂ and UV light.¹³ Vorontsov has studied the photocatalytic

⁵⁰ oxidation of dimethyl methyl phosphonate, trimethyl phosphate and diethyl phosphoramidate using suspension of TiO₂ particles in aqueous media.¹⁴ Subsequently, Moctezuma *et al.* have studied photocatalytic degradation of MP using aqueous suspension of titania particles. They also have investigated ⁵⁵ pathways of MP degradation along with its reaction products.¹⁵ Evgenidou *et al.* have studied photocatalytic oxidation of MP over TiO₂ and ZnO suspensions.¹⁶ Titanium dioxide was found to be more promising photocatalyst since the degradation of the insecticide was observed to proceed at relatively higher reaction ⁶⁰ rate. Kim *et al.* have explored degradation mechanism of MP using TiO₂ photocatalysis and photolysis.¹⁷

Although TiO₂ photocatalyst exhibited promising activity towards degradation of above OPCs, removal of the catalyst from solutions after use is expensive and technologically difficult. ⁶⁵ TiO₂ thin films have been used for the purpose of solving these technical problems. Compared to powder TiO₂ particles, immobilized TiO₂ films are more promising in practical applications, especially in water treatment.¹⁸⁻²⁰ In this connection, Prasad *et al.* have studied photocatalytic degradation ⁷⁰ of paraoxon-ethyl using titania nanoparticulate film.²¹ On the other hand, modifications of TiO₂ photocatalyst with noble metal such Au, Ag, and Pt was found to enhance its photocatalytic efficiency towards environmental pollutants. These small metal particles were found to accelerate the scavenging of ⁷⁵ photoelectrons and assist the separation of charge carrier species,

RSC Advances Accepted Manuscript

and in turn lead to generation of superoxide anion and hydroxyl radical species. $^{\rm 22\text{-}26}$

Although, many researchers have reported the degradation of MP using titania suspensions, there were scanty of literature on ⁵ the photocatalytic degradation of MP using TiO₂ and Ag-TiO₂ nanoparticulate films which is technologically important. Hence, we have prepared the TiO₂ and Ag-TiO₂ films and characterized them by transmission electron microscopy (TEM), glancing angle X-ray diffractometry (GAXRD), scanning electron microscopy ¹⁰ coupled with energy dispersive analysis of X-rays (SEM-EDAX),

UV-visible spectrophotometry and studied the degradation of MP under photocatalytic conditions.

EXPERIMENTAL

Materials

15

Silver nitrate, titanium tetraisopropoxide (TTIP), and MP of more than 90% purity, 1.27 g/mL density of Aldrich chemicals, USA make were used for photocatalytic degradation experiments.
²⁰ Isopropanol, dichloromethane, acetonitrile, bistrimethyl silyl trifluoroacetamide (BSTFA) were procured from E. Merck India Ltd. Double distilled water having pH 6.0 ± 1.0 was used for making MP solutions.

Fabrication of Ag-TiO₂ nanoparticulate film

- ²⁵ Before the fabrication of Ag-TiO₂ nanoparticulate film, TiO₂ nanoparticle dispersion was synthesized in our laboratory by solgel method followed by hydrothermal treatment at 80°C by a reported method.²¹ 5 mL of titania nanoparticle dispersion (1 mg/mL) was diluted to 149 mL by double distilled water, and ³⁰ 1mL of concentrated hydrochloric acid was added to it. Resulting dispersion was sonicated for 60 min before the preparation of the films. Films were prepared by dip coating technique. Quartz and glass substrates with 50 mm length, 1.3 mm thickness, and 13 mm width were used for fabricating TiO₂ and Ag-TiO₂ ³⁵ nanparticulate films. Substrate was immersed in dispersion for 5 min, and then lifted slowly from the solution with a withdrawal
- speed around 10 cm/min. Subsequently, the coated films were dried in an oven at 100°C for 2 h and this immersion, withdrawal and drying cycle was repeated for 5 times to obtain films. ⁴⁰ Subsequently, the film was immersed in 50 mL of aqueous
- solution of silver nitrate (1 mM) for 30 min and then it was dried at 100°C for 2 h. Followed by this, it was photoreduced under UV irradiation of 0.3 mW/cm² for 30 min to obtain Ag-TiO₂ nanoparticulate film.²⁷

45 Characterization

TEM measurements were done on Tecnai transmission electron microscope of FEI, The Netherlands make. Ag- TiO_2 film was peeled off and the sample was suspended in 30 mL acetone, and the suspension was sonicated for 30 min. After that, suspension

⁵⁰ was placed on carbon coated copper grids of 3 mm dia and dried at room temperature prior to the analysis. Prepared films were characterized by X pert pro diffractometer (Panalytical, Netherlands) using glancing angle X-ray diffraction (GAXRD, angle of incidence 1°, penetration depth <300 nm). Measurements so on scanning electron microscopy coupled with energy dispersive analysis of X-rays (SEM-EDAX) were done on FEI Quanta 400 model equipment of FEI, The Netherlands make at 20 kV operating voltage. Lambda 35 ultraviolet and visible spectrophotometer of Perkin Elmer, USA was used for recording the absorbance of MP at different intervals of time. MP showed the absorption maxima at 274 nm.

The amount of MP remaining in solution at different intervals of time was determined following calibration of the absorption maxima at 274 nm according to Beer-Lambert law. UV-vis 65 spectrometry was also used for recording the absorbance of Ag-TiO₂, TiO₂ nanoparticles immobilized on quartz substrates prepared by dip coating for 5 cycles. The pH of the solution was measured by using cyber Scan pH 1500 Eutech instrument of Thermo Scientific Company, Italy. Reaction products were 70 characterized by gas chromatography-mass spectrometry (GC-MS) system after concentration followed by silvlation with BSTFA. GC (model no. 6890N), MS (5975B) of Agilent technologies, USA was used for this purpose. Temperature program from 50 to 250°C, at a rate of 15°C/min was used for the 75 analysis. DB 5 MS capillary column of 0.25 mm i.d, 0.25 µm film thickness and 30 meters length was used for the purpose of analysis of reaction products.

Photocatalyitc degradation of MP

Stock solution was prepared by adding ~19 μ L of MP in 1000 mL 80 of double distilled water. 50 mL of aqueous solution of MP was taken in guartz round bottom (QRB) flask. Subsequently, Ag-TiO₂ or TiO₂ nanoparticulate film was immersed in ORB flask containing MP solution, and was kept in front of 175 watt xenon illuminator of M/s. Luzchem, Canada having a range of 85 wavelength of 280-800 nm. Intensity of irradiance was adjusted by the regulator provided with xenon illuminator. Intensity for the position of QRB flask was measured by digital light meter (SLM 110 model) of A.W. Sperry Instruments, USA with help of adopters provided. Intensity of UV light was found to be 0.3 ⁹⁰ W/cm². The solution was magnetically stirred to facilitate proper mixing of reactant species. Calibrated equipment based on infrared absorption and electrochemical principle manufactured by Drager, Germany was used to sniff the released CO₂ and acetaldehyde from headspace. GC-MS analysis of reaction ⁹⁵ products extracted from the reaction mixture after silvlation with BSTFA, semi-micro qualitative analysis of concentrated water samples and sniffing the headspace gases by Drager chemical sensor were used to ascertain the reaction pathways of photocatalytic degradation of MP.

100

RESULTS AND DISCUSSION

Characterization of films

¹⁰⁵ Titania nanoparticles of 5-15 nm size range were used for making TiO₂ and Ag-TiO₂ nanoparticulate films. Simple dip coating method was used for making films on glass as well as quartz substrates. SEM image of TiO₂ nanoparticulate film illustrate uniformly deposited titania nanoparticles on the substrate.

Published on 26 November 2014. Downloaded by Memorial University of Newfoundland on 27/11/2014 04:07:37.



Figure 1. TEM image of Ag-TiO₂ nanoparticles (a) peeled off from the film and (b) SEM image of Ag-TiO₂ nanoparticulate film.

- ⁵ TEM image of Ag-TiO₂ nanoparticles peeled off from Ag-TiO₂ nanoparticulate film and SEM image of Ag-TiO₂ film made by dip coating of titania nanoparticles followed by adsorption and photo reduction (UV) of silver ions are shown in Figure 1. The SEM and TEM images of TiO₂ and Ag-TiO₂ nanoparticulate
 ¹⁰ films showed similar morphologies except that in the case of Ag-TiO₂ nanoparticulate film, slightly bigger aggregates of silver nanoparticles were found in addition to the TiO₂ nanoparticles. Relatively brighter particles of nanodimensions shown in SEM image of Ag-TiO₂ film were actually found to be the aggregates
 ¹⁵ of silver nanoparticles. These observations are consistent with
- TEM data of Ag-TiO₂ film which indicated TiO₂ nanparticles of size at around 5-15 nm and silver nanoparticles of size at around 10-20 nm. The aggregation of these particles can be ascribed to vander Waals forces. The EDAX result confirmed the presence of ²⁰ silver on Ag-TiO₂ film. Due to limited resolution power of SEM,
- it could not give exact indication of the size of particles however illustrated the titania and silver particles of nanodimensions.

GAXRD data

GAXRD data of Ag-TiO₂ film depicted the presence of titania $_{25}$ nanoparticles on the substrate as shown in Figure 2.



Figure 2. XRD pattern of Ag-TiO₂ nanoparticulate film.

³⁰ GAXRD pattern showed peaks at $2\theta = 25.2^{\circ}$ (101), $2\theta = 37.8^{\circ}$ (004), $2\theta = 48.0$ (200), $2\theta = 53.8$ (106), $2\theta = 62.7$ (215) and illustrated the presence of titania nanoparticles of anatase phase. Silver nanoparticles did not give any indication of their presence. This can be attributed to the amorphous nature of film. The ³⁵ Scherer formula was used to calculate crystallite size of titania particles present on the substrate. The average crystallite size of titania particles deposited on the substrate was found to be 11 nm. XRD pattern of TiO₂ film was already reported.²¹

TiO₂ nanoparticulate film showed absorption maximum at 40 around 240 nm indicating the presence of TiO₂ nanoparticles. Ag-TiO₂ nanoparticulate film showed two absorption maxima at around 240 nm and 420 nm. Maxima at around 240 nm can be attributed to TiO₂ nanoparticles and the maxima at around 420 nm can be ascribed to the presence of silver nanoparticles (Figure 45 3.). Apparently, Ag-TiO₂ film was found to possess enhanced visible light absorbance when compared to TiO₂ nanoparticulate film due to the presence of silver nanoparticles.



Figure 3. Absorption spectra of TiO₂ and Ag-TiO₂ nanoparticulate films.

Photocatalytic degradation of MP using TiO₂ and Ag-TiO₂ nanoparticulate films

Photocatalytic activity of TiO₂ and Ag-TiO₂ nanoparticulate ⁶⁰ films were evaluated against MP and the data was compared to that obtained under photolytic degradation conditions. MP was observed to decompose slowly by photolysis under sole treatment of light radiation ranging from 280-800 nm. Only 81 % of MP was found to be degraded in 420 min due to photolysis. Whereas, 5 90 % of MP was found to be degraded in the presence of TiO₂ nanoparticulate film due to photocatalysis and 100 % of MP was found to be degraded in the presence of Ag-TiO₂ nanoparticulate film in 420 min. Only 0.7 % of methyl parathion was observed to be degraded in dark reaction in the absence of light when only ¹⁰ TiO₂ or Ag-TiO₂ nanoparticulate film was used (Figure 4).This





Figure 4 Degradation of MP in the presence of only light, in the presence of light along with TiO_2 and Ag- TiO_2 nanoparticulate films.

- ³⁰ Concentration of MP was found to be decreasing exponentially and logarithmic plots were observed to be linear when plotted versus time depicting pseudo first order kinetics. Kinetic analysis of above data indicated the value of rate constant to be 2.3 X10⁻³ min⁻¹ for photolytic degradation of MP in aqueous solution. The ³⁵ rate of degradation reaction was found to be enhanced by the presence of TiO₂ nanoparticulate film and the value of rate constant was calculated to be 4.6 X 10⁻³ min⁻¹. The increase of value of rate constant from 2.3 X10⁻³ to 4.6 X 10⁻³ can be attributed to the additive effect of presence of TiO₂
 ⁴⁰ nanoparticulate film which facilitated the photocatalytic degradation of MP (Figure 5). It further increased to 6.9 X 10⁻³ min⁻¹ when Ag-TiO₂ film was used for photocatalysis. Blank experiments conducted by using TiO₂ or Ag-TiO₂ nanoparticulate film in absence of light indicated negligible degradation of MP.
- ⁴⁵ Data showed that there is no change of MP concentration in the absence of light. When TiO_2 and $Ag-TiO_2$ films were compared, the increase of the value of rate constant from 4.6 $X10^{-3}$ to 6.9 $X10^{-3}$ min⁻¹ can be attributed to the effective separation of photogenerated charge carriers which was found to be promoted by
- $_{50}$ silver nanoparticles present on Ag-TiO₂ film. In addition to this, addition of silver nanoparticles to TiO₂ film extended its absorbance to visible light region which in turn extended the photoactivity of Ag-TiO₂ film into visible light region, where TiO₂ absorb only in UV region. This also could be a reason for
- ss the slightly larger activity of Ag-TiO₂ film when compared to TiO_2 film.



Figure 5 Kinetics of degradation of MP in the presence of only light, TiO_2 and Ag- TiO_2 nanoparticulate films along with R^2 values in brackets.

In order to examine the stability and regenerability of Ag-TiO₂ nanoparticulate film, four successive experiments were conducted under the same experimental conditions using the same film. Film was rinsed with water thoroughly after every cycle of ⁷⁵ photocatalysis experiment. It was observed that, 100 % of methyl parathion (Figure 6) was found to be degraded in each reaction cycle in 420 min of reaction time and in each reaction cycle value of rate constant was found to be same, i.e., 6.9 X 10⁻³ min⁻¹.



 $_{80}$ Figure 6 Regenerability of Ag-TiO₂ nanoparticulate film used for photocatalytic degradation of methyl parathion

This observation clearly demonstrated the stability and regenerability of titania nanoparticulate film. Reaction products formed on surface of the film were found to be removed instantaneously by water molecules which collide the surface, and this way the surface poisoning seemed to be avoided. Perhaps the negligible chemical adsorption of reaction products formed on the surface seemed to have influenced the availability of active ⁹⁰ sites and regeneration of surface. In addition to this, to understand whether any loss of titania nanoparticles was there due to peeling off the film, absorbance of the film was recorded which was reused for 4 cycles. Interestingly there is no significant change in absorbance at 240 nm which further confirmed the stability of

Published on 26 November 2014. Downloaded by Memorial University of Newfoundland on 27/11/2014 04:07:37

titania nanoparticulate film. However, the absorbance at 420 nm decreased after each cycle due to oxidation of silver nanoparticles to silver ions. However, after washing thoroughly and subsequently exposing it to UV irradiance for 30 min regained ⁵ the absorbance value indicating that although silver nanoparticles were oxidized to silver ions after each cycle of the experiment and they were not peeled off from the Ag-TiO₂ film surface.

Compounds	Retention time	Characterstic ions (m/z)
Phosporic acid, trimethyl ester	5.04	140,110,95,79,65,47, 29,15
Phosphorothioic acid O,O,S-trimethyl ester	7.03	156,141,126,110, 109,95,79
Trimethyl silyl phosphate	8.85	314,299,283,211, 133,73
Trimethyl silyl(4- nitrophenoxy)	10.87	213,196,150,73,45
Methyl paraxon	13.29	247,230,170,152,109 93,79,63
Methyl paraxon	13.29	247,230,170,152, 93,79,63

10 Table.1. List of products formed due to the photocatalytic degradation of methyl parathion on Ag-TiO₂ nanoparticulate film as detected by GC-MS.

Short discussion on photocatalytic degradation mechanism

Table 1 shows the main products detected by GC-MS after ¹⁵ silylation during photocatalytic oxidation of MP on TiO₂ and Ag-TiO₂ nanoparticulate film. Carbon dioxide and acetaldehyde were detected by sniffing the head space gas by using a Drager chemical sensor. GC-MS data indicated the presence of paraoxon-methyl, silylated product of p- nitrophenol, and ²⁰ trimethyl silyl phosphate ester in the reaction mixture. In addition to these, trimethyl ester of phosporic acid, and phosphorothioic acid O,O,S-trimethyl ester were also observed in the reaction

Phosphoric acid dimethyl ester further underwent ²⁵ reaction with hydroxyl radical and formed phosphoric acid monomethyl ester, phosphoric acid and then lead to the formation of phosphate ion in final stage. As mentioned above, formation of phosphate ion was confirmed by the presence of trimethyl silyl phosphate in the reaction mixture. It was

mixture.

- ³⁰ understood that, photocatalytic degradation of MP started with cleavage of P-O-C bond. Subsequently, P-O bond, C-C bond etc, and P and C atoms were found to be oxidized gradually and finally lead to the formation of final degradation products such as carbon dioxide and phosphate ion .²⁸
- Based on the above results, reaction mechanism of photocatalytic degradation of MP is presented in Figure 7. In aqueous solution of MP, holes seemed to have reacted with water molecules and hydroxide ions and produced hydroxyl radicals. Electrons observed to have reacted with dissolved oxygen

⁴⁰ molecules and generated super oxide anion radicals. They further reacted with water molecules and facilitated the formation of hydroxyl radicals. These strongly electrophilic 'OH radicals found to have contributed to degradation of MP in aqueous solutions. Formation of phosphate ion was also confirmed by the 45 semi micro qualitative analysis of concentrated water. Water was acidified with nitric acid and then treated with ammonium heptamolybdate solution.



50 Figure 7. Routes of photocatalytic degradation of MP assisted by Ag-TiO₂ nanoparticulate film.

The solution had turned to yellow precipitate due to the formation of ammonium molybdophosphoric acid thus confirming the ⁵⁵ presence of phosphate ions by semi micro qualitative analysis. This observation is consistent with reported results by Vorontsov *et al.*. ²⁹ Subsequently, oxidation of P-O-C and C-H bonds by 'OH radicals observed to have assisted the formation of acetaldehyde, and then finally carbon dioxide.

⁶⁰ Silver nanoparticles seemed to have contributed to enhanced photocatalysis by trapping the charge carriers. Visible light activity of Ag-TiO₂ film aroused due to the presence of silver nanoparticle also seemed to have contributed to enhanced photocatalytic degradation of MP. Collectively, studies on ⁶⁵ photocatalytic degradation of MP, a toxic pesticide using Ag-TiO₂ nanoparticulate film provides a promising technology for purification of water contaminated with toxic OPCs avoiding several logistic problems such as removal of catalysts after treatment when used for water purification.

70 Conclusions

Studies have revealed that $\mathrm{Ag}\text{-}\mathrm{TiO}_2$ film has demonstrated enhanced rate of photocatalytic degradation of MP when

compared to TiO₂ nanoparticulate film. Silver nanoparticles were found to have contributed to photocatalysis by trapping the charge carriers. Oxidation or cleavage of P-O-C was found to be predominant relative to oxidation of C-C or C-H bonds. Some 5 amount of MP was completely mineralized to phosphate ion and the same was confirmed by GC-MS data.

Notes and references

Published on 26 November 2014. Downloaded by Memorial University of Newfoundland on 27/11/2014 04:07:37

^a Defence R & D Establishment, Jhansi Road, Gwalior.Tel: 07512390169 10 E-mail: <u>gkprasad2001@gmail.com</u>, <u>ramamsc2007@gmail.com</u>

- J. Fournier, Chemie des Pesticides, *Editions Cultures et Techniques, Nantes*, 1988.
- 2. J.R. Chambers, H.W. Chambers, in L. Somasundaraman, J.R. Coats, (Eds), Pesticide transformation products, *ACS Symp.Ser*, 1991.
- 3. K. Harada, T. Hisanaga and K. Tanaka, Water Res, 1990, 24, 1415.
- H.D. Burrows, M.L. Canle, J.A. Santaballa and S.Steenken, J Photochem.Photobiol B:Biology, 2002, 67, 71.
- 5. H. Roques, Chemical Treatment:Principles and Practice, VCH, New vork, 1996.
- 6. M. Eto, Organophosphorous pesticides:organic and biological chemistry, *CRC Press, Cleveland*, 1974.
- A. Topalov, D. Molnar-Gabor, B. Abramovic, S. Korom and D. Pericin, *J.Photochem.Photobiol.A:Chem*, 2003, 160, 195.
- 25 8. A. Fujishima, D.A. Tryk and T.N. Rao, J. Photochem. Photobiol. C: Photochemistry reviews, 2000, 1, 1.
- K. Hashimoto, H. Irie and A. Fujishima, *Jpn.J.Appl.Phys.*, 2005, 44, 8269.
- 10. F. Denny, E. Permana, J. Scott, J. Wang, D.Y.H. Pui and R. Amal, *Environ. Sci. Technol.*,2010, **44**, 5558.
- R-a. Doong and W-h. Chang, J.Photochem. Photobiol.A:Chem., 1997, 107, 239.
- L. Zhang, F. Yan and Y. Wang, X.Guo, P.Zhang, *Inorg. Mater.*, 2006, 42, 1379.
- 35 13. S. Han, J. Li, H. Xi, D. Xu, Y. Zuo and J. Zhang, J. Hazard. Mater., 2009, 163, 1165.
 - E.A. Kozlova, P.G. Smirniotis and A.V. Vorontsov, J. Photochem. Photobiol. A: Chem., 2004, 162, 503.
- 15. E. Moctezuma, E. Leyva, G. Palestino and H.D. Lasa, J.Photochem.Photobiol A:Chem., 2007, **186**, 71.
- E. Evgenidou, I. Konstantinou, K. Fytianos, I. Poulios and T. Albanis, *Catal. Tod.*, 2007, **124**, 156.
- T-S. Kim, J-K. Kim, K.Choi, M.K. Stenstrom and K-D. Zoh, Chemosphere, 2006, 62, 926.
- 45 18. Y.Lei, L.D.Zhang and J.C.Fan, Chem. Phys. Lett., 2001, 338, 231.
- K. Esquivel, L.G.Arriaga, F.J. Rodriguez, L.Martinez, and L.A. Godinez, *Water Res.*, 2009, 43, 3593.
- H. Choi, S.R. Al-Abed, D.D. Dionysio, in M. Diallo, J. Duncan, N. Savage, A. Street, R. Sustich, (Eds.), Nanotechnology applications for clean water, *William Andrew Inc., Norwich, NY*, 2009, 39.
- G.K. Prasad, P.V.R.K. Ramacharyulu, J. PraveenKumar, A.R. Srivastava and B. Singh, *Thin Solid Films*, 2012, 520, 5597.
- 22. C. Yogi, K. Kojima, T. Takai and N. Wada, J.Mater.Sci., 2009, 44, 821.
- 55 23. Y. Wu, H. Liu, J. Zhang and F. Chen, J. Phys. Chem. C, 2009, 113, 14689.
- L. Sun, J. Li, C. Wang, S. Li, Y. Lai, H. Chen and C. Lin, J.Haz. Mater., 2009, 171,1045.
- 25. H-Y. Chuang and D-H. Chen, Nanotechn., 2009, 20, 105704.
- 60 26. M. Qamar, Desal., 2010, 254, 108.
- 27. L.C. Courrol, F.R.de Oliveira Silva, L.Gomes, Colloid. &Int. A: Physicochem.& eng. Aspects, 2007, 305(1-3), 54.
- B. Sun, A.V. Vorontsov and P.G. Smirniotis, *J.Hazard.Mater.*, 2011, 186, 1147.
- 65 29. A.V. Vorontsov, Y.C. Chen and P.G. Smirniotis, J.Hazard.Mater., 2004, 113, 89.