

Available online at www.sciencedirect.com



Chinese Chemical Letters 23 (2012) 793-796



www.elsevier.com/locate/cclet

Novel phosphorus–silicon synergistic flame retardants: Synthesis and characterization

Tao Song, Zhi Sheng Li, Jin Gang Liu*, Shi Yong Yang*

Laboratory of Advanced Polymer Materials, Institute of Chemistry, Chinese Academy of Sciences, Beijing 100190, China

Received 13 March 2012 Available online 9 June 2012

Abstract

Three novel flame retardants containing both phosphorus and silicon elements in their structures, including [(1,1,3,3-tetramethyl-1,3-disiloxanediyl)di-2, 1-ethanediyl]bis(diphenylphosphine oxide) (FR-1), [(2,4,6,8-tetramethylcyclotetra-silox-ane-2,4,6,8-tetrayl)tetra-2,1-ethanediyl]tetrakis[diphenylphosphine oxide] (FR-2) and 1,3,5,7,9,11,13,15-octakis(di-phenylphosphine oxide-2,1-ethanediyl)pentacyclo[9.5.1.1^{3,9}.1^{5,15}.1^{7,13}]octasiloxane (FR-3) were synthesized by a convenient pathway from the reaction of diphenylphosphine oxide (DPPO) and vinyl-terminated siloxanes under the catalysis of triethylborane. The chemical structures of the target compounds were confirmed by nuclear magnetic resonance (¹H NMR, ¹³C NMR, ²⁹Si NMR and ³¹P NMR), matrix-assisted laser desorption/ionization time-of-flight mass spectrometry (MALDI-TOF-MS) and Fourier transform infrared (FT IR) measurements. Thermogravimetric analysis (TGA) results indicated that the new flame retardants possessed good thermal stability both in nitrogen and in air. FR-3 containing polyhedral oligosilsesquioxanes (POSS) moiety exhibited the best thermal properties with a 10% weight loss temperature >400 °C and a residual weight ratio >39% at 700 °C. © 2012 Jin Gang Liu. Published by Elsevier B.V. on behalf of Chinese Chemical Society. All rights reserved.

Keywords: Phosphorous-containing siloxanes; POSS; Flame retardant; Synergistic effect

Flame retardants (FRs) are one of the most important components for common engineering polymers, such as engineering plastics, textiles and molding compounds for electronic packaging [1]. In recent rears, various efforts have been performed in order to improve the flame retardant efficiency of the FRs. Among various methodologies, the attempts taking advantage of the synergistic effects of specific elements with flame retardant characteristics, such as boron, silicon, phosphorus, nitrogen, halogen (chlorine, bromine and iodine), antimony and bismuth have gained much attention in recent years [2–4]. Various synergistic couples, for instance, P–N, P–Si, Sb–Cl, Bi–Cl and many other combinations have been incorporated into the structures of high performance FRs [5–7]. In the synergistic systems mentioned above, the P–Si system has been proved to be of great value due to its inherent high flame retardant efficiency, good environmental compatibility and good thermal durability at elevated temperatures [8,9]. Various P–Si synergistic FRs, for instance, those containing 9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO) and POSS components can usually increases the ignition resistance of common polymers significantly while maintaining the thermal stability of polymer matrixes [10,11].

* Corresponding authors.

E-mail addresses: liujg@iccas.ac.cn (J.G. Liu), shiyang@iccas.ac.cn (S.Y. Yang).

^{1001-8417/\$-}see front matter © 2012 Jin Gang Liu. Published by Elsevier B.V. on behalf of Chinese Chemical Society. All rights reserved. http://dx.doi.org/10.1016/j.cclet.2012.04.024

In our previous study, a series of P–Si synergistic FRs have been developed from DOPO and vinyl-terminated linear siloxanes [12]. However, the inferior hydrolysis resistance of the P–O–C bond in the DOPO ring limited their applications in moisture-sensitive areas [13].

In this communication, a class of P–Si synergistic FRs containing P–C bonds instead of P–O–C bonds was developed from diphenylphosphine oxide (DPPO) and vinyl-containing siloxanes. Compared with their DOPO analogues, the P–C bond in the phosphonate moiety in DPPO is less sensitive to moisture and would not hydrolyze in high temperature wet environments. The synthesis and characterization of the new FRs were investigated in detail.

1. Experimental

Triethylborane (as a 1 mol/L solution in hexane) and vinyl-terminated siloxanes, including 1,3-divinyl-1,1,3,3-tetramethyldisiloxane, 1,3,5,7-tetramethyl-1,3,5, 7-tetravinylcyclotetrasiloxane and octavinyl POSS (OVPOSS) were purchased from Sigma–Aldrich and used as received. FT IR spectra were recorded on a PE 2000 FT IR spectrometer. ¹H NMR and ¹³C NMR were conducted on a Bruker AV-400 nuclear magnetic resonance spectrometer with tetramethylsilane (TMS) as the internal standard. ²⁹Si NMR and ³¹P NMR measurements were performed on a Bruker DMX 300 spectrometer. MALDI-TOF-MS spectra were obtained on a Biflex III mass spectrometer. Differential scanning calorimeter (DSC) measurements were performed with a TA Instruments Q100 thermal analysis system.

1,3,5,7,9,11,13,15-Octakis(diphenylphosphine oxide-2,1-ethanediyl)pentacyclo [9.5.1.1^{3,9}.1^{5,15}.1^{7,13}]octa-siloxane (FR-3) was synthesized as follows. Into a 250-mL three-necked bottle equipped with a mechanical stirrer, a dropping funnel and a gas inlet was added diphenylphosphine oxide (DPPO) (16.16 g, 80 mmol), OVPOSS (6.31 g, 10 mmol) and tetrahydrofuran (60 mL). The mixture was stirred at room temperature in nitrogen until all of the reactants dissolved. A stoichiometric triethylborane solution in hexane (16 mL, 16 mmol) was added dropwise. After the addition, the progress of the reaction was monitored by thin layer chromatography (TLC). After the reaction was judged complete (usually after 5–6 h) by TLC, the reaction mixture was evaporated to remove the tetrahydrofuran. The resulting solid was successively washed by diethyl ether and distilled water for three times. Then, the resulting white solid was further purified by recrystallization from tetrahydrofuran to afford FR-3 (20.46 g) with a yield of 91%. Melting point: 259 °C (DSC peak temperature); ¹H NMR (400 MHz, CDCl₃): δ 0.87 (m, 16H, –Si–CH₂–), 2.28 (d, 16H, –CH₂–P), 7.37 (m, 32H), 7.42 (m, 16H), 7.61 (m, 32H); ¹³C NMR (101 MHz, CDCl₃): δ 132.5, 131.8, 131.5, 130.7, 128.8, 22.7; ²⁹Si NMR (60 MHz, CDCl₃): δ –66.72; ³¹P NMR (162 MHz, CDCl₃): δ 32.76; FT IR (KBr): ν 3067, 3026, 2987, 2961, 1946, 1604, 1410, 1276, 1111, 1005, 970 cm⁻¹; MALDI-TOF-MS: *m/z* calcd. for C₁₁₂H₁₁₂O₂₀P₈Si₈ [M+Na]⁺: 2271.4, found 2271.2.

[(1,1,3,3-Tetramethyl-1,3-disiloxanediyl)di-2,1-ethanediyl]bis(diphenylphosphine oxide) (FR-1) and [(2,4,6,8-tetramethylcyclotetrasiloxane-2,4,6,8-tetrayl)tetra-2,1-ethanediyl]tetrakis[diphenylphosphine oxide] (FR-2) were synthesized with a similar procedure as described in the synthesis of FR-3 except that 1,3-divinyl-1,1,3,3-tetramethyldisiloxane was used instead of OVPOSS for FR-1 and 1,3,5,7-tetramethyl-1,3,5,7-tetravinylcyclo-tetrasiloxane was used for FR-2.

FR-1: mp: 169 °C (DSC peak temperature); yield: 89%. ¹H NMR (400 MHz, CDCl₃): δ –0.08 (s, 12H, –Si–CH₃), 0.63 (d, 4H, –Si–CH₂–), 2.05 (d, 4H, –CH₂–P), 7.30 (d, 6H), 7.60 (t, 4H); ¹³C NMR (101 MHz, CDCl₃): δ 133.0, 131.7, 130.9, 128.7, 77.1, 23.4, 8.43, –0.05; ²⁹Si NMR (60 MHz, CDCl₃): δ 8.63; ³¹P NMR (162 MHz, CDCl₃): δ 33.28; FT IR (KBr): ν 3052, 2958, 2899, 1483, 1437, 1410, 1318, 1255, 1183, 1150, 1120, 1091, 999, 842 cm⁻¹; MALDI-TOF-MS: m/z calcd. for C₃₂H₄₀O₃P₂Si₂ [M+Na]⁺: 613.2, found 613.2.

FR-2: yield: 89%. ¹H NMR (400 MHz, CDCl₃): δ –0.06 (s, 12H, –Si–CH₃), 0.59 (d, 8H, –Si–CH₂–), 2.01 (d, 8H, – CH₂–P), 7.22 (m, 24H), 7.61 (m, 16H); ¹³C NMR (101 MHz, CDCl₃): δ 134.9, 133.5, 132.7, 132.5, 131.7, 131.3, 131.2, 130.7, 128.7, 128.1, 23.0, 22.3, 7.1, –1.1; ²⁹Si NMR (60 MHz, CDCl₃): δ –18.69; ³¹P NMR (162 MHz, CDCl₃): δ 33.77; FT IR (KBr): ν 3056, 2959, 2901, 1637, 1591, 1484, 1437, 1408, 1262, 1180, 1160, 1121, 1071, 918 cm⁻¹; MALDI-TOF-MS: *m/z* calcd. for C₆₀H₆₈O₈P₄Si₄ [M+Na]⁺: 1175.3, found 1175.3.

2. Results and discussion

Three P–Si synergistic FRs, FR-1, FR-2 and FR-3 were synthesized with a procedure shown in Scheme 1. This procedure has been proven to be an efficient pathway for the formation of P–C bonds [14]. In our experiments, the triethylborane-induced radical addition of DPPO to vinyl-siloxanes proceeded smoothly giving rise to the



Scheme 1. Synthesis of phosphorus-silicon FRs (FR-1-FR-3).

corresponding phosphorus-containing siloxanes FRs in a yield >85%. FR-1 and FR-3 were obtained as white crystals with a melting point of 169 °C and 259 °C, respectively; while FR-2 was obtained as a white solid without clear melting transition in the DSC measurement. The chemical structures of the FRs were confirmed by FT IR, NMR and MALDI-TOF-MS measurements. For instance, in the ³¹P NMR spectra (not shown), the FRs exhibited clear resonances at 33.28 ppm for FR-1, 33.77 ppm for FR-2 and 32.76 ppm for FR-3. In the ¹H NMR spectra, the characteristic chemical shifts of protons in the terminal vinyl (H₂C=CH–) at about 5.7–5.9 ppm disappeared in the spectra of the final FRs, indicating the successful transition of the reactions. In addition, the measured molecular weights for the three FRs agreed well with the theoretical values. Thus, all the characterizations indicate that we successfully prepared the target FRs.

The effects of the structures of the FRs on their thermal properties were investigated by TGA techniques. Fig. 1 illustrates the TGA decomposition curves of the FRs measured both in air and nitrogen. Table 1 tabulates the thermal data of the FRs. It can be obviously observed that the current FRs possessed good thermal stability up to 300 °C both in air and nitrogen. The 5% ($T_{5\%}$) and 10% ($T_{10\%}$) weight loss temperatures of the FRs increased in the order FR-1 < FR-2 < FR-3.



Fig. 1. Thermal stabilities of FRs in nitrogen and air.

Sample	$T_{5\%}{}^{a}$		$T_{10\%}{}^{\rm b}$		$R_{\rm w}^{\ \ c}$	
	In air	In nitrogen	In air	In nitrogen	In air	In nitrogen
FR-1	312.9	317.8	331.0	336.5	1.2	2.8
FR-2	329.4	331.6	366.5	361.9	31.3	30.3
FR-3	395.5	383.5	411.1	401.2	42.4	39.0

Table 1 Thermal data for FRs.

^a Temperatures at 5% weight loss.

^b Temperatures at 10% weight loss.

^c Residual weight ratio at 700 °C.

For instance, FR-3 exhibited the highest $T_{10\%}$ value of 411.1 °C in air, which is nearly 80 °C and 45 °C higher than those of FR-1 and FR-2, respectively. The residual weight ratios (R_w) of FR-3 at 700 °C were 42.4% in air and 39.0% in nitrogen, respectively. The best thermal stability of FR-3 might be ascribed to its highest phosphorous and silicon contents in the series. In addition, the slightly higher R_w values of FR-3 in air than that in nitrogen might be due to the formation of inert phosphorous or silicon oxide compounds at elevated temperatures in air. These residues increase the weights ratio of the FRs.

The detailed thermal decomposition mechanism of the FRs in air and nitrogen and the effects of their structures on the flame retardancy of epoxy systems would be discussed in our next work.

Acknowledgments

The authors thank the National Natural Science Foundation of China (No. 51173188) for financial support. The authors thank Dr. Xuechao Zhang for his instructive discussion on this work.

References

- [1] C.A. Wilkie, A.B. Morgan, Fire Retardancy of Polymeric Materials, CRC Press, Boca Raton, 2010.
- [2] H.D. Lu, C.A. Wilkie, Polym. Degrad. Stab. 95 (2010) 564.
- [3] M. Dogan, A. Yilmaz, E. Bayramli, Polym. Degrad. Stab. 95 (2010) 2584.
- [4] C. Gerard, G. Fontaine, S. Bourbigot, Polym. Adv. Technol. 22 (2011) 1085.
- [5] Y.M. Yu, S.Y. Fu, P.A. Song, et al. Polym. Degrad. Stab. 97 (2012) 541.
- [6] L. Costa, M.P. Luda, L. Trossarelli, Polym. Degrad. Stab. 68 (2000) 67.
- [7] S. Gaan, G. Sun, K. Hutches, et al. Polym. Degrad. Stab. 93 (2008) 99.
- [8] Z.L. Tang, Y.N. Li, Y.J. Zhang, et al. Polym. Degrad. Stab. 97 (2012) 638.
- [9] X. Wang, Y. Hu, L. Song, et al. J. Polym. Sci. Part B: Polym. Phys. 48 (2010) 693.
- [10] W.C. Zhang, X.M. Li, R.J. Yang, J. Appl. Polym. Sci. 124 (2012) 1848.
- [11] L. Song, S.Y. Xuan, X. Wang, et al. Thermochim. Acta 527 (2012) 1.
- [12] J.P. Ding, Z.Q. Tao, X.B. Zuo, et al. Polym. Bull. 62 (2009) 829.
- [13] M.A. Espinosa, M. Galla, V. Cadiz, J. Polym. Sci. Part A: Polym. Chem. 42 (2004) 3516.
- [14] P. Rey, J. Taillades, J.C. Rossi, et al. Tetrahedron Lett. 44 (2003) 6169.