Synthesis of group 4 complexes that contain the tridentate diamido ligands $[(ArNCH_2CH_2)_2O]^{2-}$ (Ar = C₆H₃-Me₂-2,6 or C₆H₃Prⁱ₂-2,6)

Richard R. Schrock,* Florian Schattenmann, Michael Aizenberg and William M. Davis

Department of Chemistry 6-331, Massachusetts Institute of Technology, 77 Massachusetts Avenue, Cambridge, MA 02139, USA

Complexes of Zr and Hf of the type $[(2,6-R_2C_6H_3NCH_2CH_2)_2O]ZrMe_2$ (R = Me or Prⁱ) can be activated by [PhNMe_2H][B(C_6F_5)_4] or [Ph_3C][B(C_6F_5)_4] in chlorobenzene or bromobenzene to yield catalysts for the polymerization of hex-1-ene, but analogous titanium catalysts are relatively poorly behaved.

Significant advances have been made in the synthesis of 'well defined' alkene polymerization catalysts of the early metals (largely group 4) in the last 15 years, the vast majority of which contain two cyclopentadienyl-like rings.¹⁻³ (See, however, ref. 4, and references therein.) Recently group 4 complexes that contain chelating diamido ligand systems have received increased attention as potential alkene polymerization catalysts.⁵⁻¹³ The most successful so far appear to be dialkyl complexes of Ti that contain diamido ligands such as $[ArNCH_2CH_2CH_2NAr]^{2-}$ (Ar = C₆H₃Prⁱ₂-2,6),^{5,6} and dialkyl complexes of Zr that contain the 'diamido/donor' ligand, $[(o-[^{2}H_{6}]Bu^{t}NC_{6}H_{4})_{2}O]^{2-}$ ([NON]²⁻).¹⁰ Both types can be activated to yield (presumably) cationic catalysts for the living polymerization of hex-1-ene. We report here Ti, Zr and Hf complexes that contain potentially interesting 'diamido/donor' variations of the [NON]²⁻ ligand, ligand, $[(2,6-R_2C_6H_3NCH_2CH_2)_2O]^{2-}$ (R = Me, Prⁱ), and preliminary experiments concerning their use as catalysts for the polymerization of hex-1-ene.

The diamines, $(2,6-Me_2C_6H_3NHCH_2CH_2)_2O$ (H_2L^{1a}) and $(2,6-Pri_2C_6H_3NHCH_2CH_2)_2O$ (H_2L^{1b}), can be prepared readily from (TsOCH_2CH_2)_2O (TsO = tosylate) and 2 equiv. of LiNH(C₆H₃Me₂-2,6) or LiNH(C₆H₃Pri₂-2,6), respectively, in thf.† Compound H₂L^{1a} can be obtained in 60% yield as colorless crystals upon crystallization from pentane.[‡],§ Compound H₂L^{1b} is obtained in 80% yield as an oil that has crystallized in some instances upon standing for several days, and that can be crystallized from pentane in low yield at -30 °C.[‡],[‡] Crude H₂L^{1b} can be used in subsequent reactions.

The reaction between $H_2^2L^{1a}$ or H_2L^{1b} and $Zr(NMe_2)_4$ in pentane at room temp. yields crystalline $ZrL^{1a}(NMe_2)_2$; or $ZrL^{1b}(NMe_2)_2$; readily. The dimethylamido compounds react with excess SiMe₃Cl in ether overnight at room temp. to yield $ZrL^{1a}Cl_2$; and $ZrL^{1b}Cl_2$; as colorless, relatively insoluble crystals. NMR spectra of $ZrL^{1b}(NMe_2)_2$ and $ZrL^{1b}Cl_2$ show two sets of isopropyl methyl groups, but only one methine resonance, consistent with restricted rotation of the aryl ring about the $N-C_{ipso}$ bond, a phenomenon that was also noted by McConville and co-workers^{5–8,14} in complexes containing the $[ArNCH_2CH_2CH_2NAr]^{2-}$ and related ligands. Only a single amido methyl resonance is observed in all dimethylamido compounds at room temp. in C_6D_6 .

Alkylation of ZrL^{1a}Cl₂ with MeMgBr in ether gives ZrL^{1a}Me₂ **1a**⁺ in good yield, while alkylation of ZrL^{1b}Cl₂ with Me or Buⁱ Grignard reagents in ether yields ZrL^{1b}Me₂ **1b**⁺ or ZrL^{1b}(CH₂CHMe₂)₂ **2b**,⁺ respectively, in good yields as colorless cubes. NMR spectra are again consistent with slow rotation around the N–C_{ipso} bond on the NMR timescale. In all dialkyl compounds the alkyl groups are equivalent, consistent either with a pseudotrigonal bipyramidal structure of type **A** or a pseudotrigonal bipyramid of type **B** in which the alkyl groups become equivalent on the NMR timescale *via* a rapid 'flipping' of the ligand backbone through an intermediate with structure **A**.



An X-ray study of ZrL^{1a}Me₂ (Fig. 1)¶ showed it to have structure **A** with 'axial' Zr–N bond distances of 2.084(3) Å and a Zr–O(2) bond length of 2.336(3) Å. The compound has a crystallographic mirror plane defined by Zr, O(2), C(5) and C(6). The planes of the aryl rings are perpendicular to the ZrO(2)N(3)N(4) pseudo-plane. The structure is closely related to that of $[(2,6-Et_2C_6H_3NCH_2)_2NC_5H_3]ZrMe_2$ [N–Zr–N 139.6(2)° and C–Zr–C 102.4(3)°]⁸ and contrasts markedly with that of { $[(o-[^2H_6]Bu^tNC_6H_4)_2O]ZrMe$ }{MeB(C₆F₅)₃,1° in which B(C₆F₅)₃ has partially removed Me_{ax}. The two Me groups are technically inequivalent in the solid state structure of ZrL^{1a}Me₂ [C(8)–O(2)–C(18) 113.7(4)°] as a consequence of C(18) and C(8) not lying in the ZrN₂ plane.

Reactions similar to those employed to prepare Zr compounds can be employed to prepare $HfL^{1a}(NMe_2)_2,\ddagger HfL^{1a}Cl_2,\ddagger$ and $HfL^{1a}Me_2$ **3a**.‡ The Hf compounds are virtually identical to the Zr compounds in physical properties and NMR characteristics.

Addition of Li₂L^{1a} to TiCl₄(thf)₂ in diethyl ether at -30 °C led to formation of a deep red precipitate, which could be recrystallized from CH₂Cl₂ to yield TiL^{1a}Cl₂ in 57% yield. Alkylation of TiL^{1a}Cl₂ in ether with MeMgCl in thf at -30 °C gave TiL^{1a}Me₂ **4a** in 53% yield as a yellow powder from pentane. Red, crystalline TiL^{1a}(CH₂Ph)₂ **5a** was prepared in low yield (*ca*. 15%) *via* the reaction between Ti(CH₂Ph)₄ (2 mmol)



Fig. 1 A view of the structure of $ZrL^{1a}Me_2$ nearly opposite the Zr–O bond in the ZrC₂ plane. Bond lengths (Å) and angles (°): Zr–C(5) 2.253(6); N(4)–Zr–N(3) 139.1(2), C(8)–O(2)–C(18) 113.7(4), Zr–N(3)–C(9) 120.2(2), C(5)–Zr–C(6) 100.0(2)°.

Chem. Commun., 1998 199

(Complex	Activator	$M_{\rm n}$ (theory)	M_{n}^{b}	$M_{\rm w}{}^b$	$M_{\rm w}/M_{\rm n}{}^b$	Yield (%)
2 2 2 2 2	ZrL ^{1b} Me ₂ ZrL ^{1b} Me ₂ ZrL ^{1b} (CH ₂ CHMe ₂) ₂ ZrL ^{1b} Me ₂	$\label{eq:constraint} \begin{split} &[NHMe_2Ph]^+ \\ &[CPh_3]^+ \\ &[NHMe_2Ph]^+ \\ &[CPh_3]^+ \end{split}$	13 440 16 800 16 800 16 800	2 670 2 460 2 650 11 700	3 560 4 220 8 550 18 000	1.33 1.72 3.23 1.55	96 96 94 100

^a Dialkyl complex (44 μ mol), activator (40 μ mol), 200 equiv. hex-1-ene (except first entry = 160 equiv.), 10 ml chlorobenzene.^b Determined by GPC coupled with on-line light scattering (Wyatt Technology).



Fig. 2 A view of the structure of TiL^{1a}(CH₂Ph)₂. Bond lengths (Å) and angles (°): Ti-C(1) 2.129(10), Ti-N(1) 1.962(6), C(2)-Ti-O 169.3(3).

and H_2L^{1a} (2 mmol) in pentane (ca. 15 ml) in 40 h. In 4a and 5a the alkyl groups are equivalent on the NMR timescale at room temp., although several proton and carbon resonances in 5a are broad at 22 °C. The structure of TiL^{1a}(CH₂Ph)₂ (Fig. 2)¶ is best described as type **B** in which O and C(2) are in the apical position and N(1), N(2), and C(1) are in the equatorial positions of a pseudotrigonal bipyramid. Surprisingly, the benzyl groups are bound only in an η^1 fashion; if two Ti–N π bonds can form, the metal should be viewed as having a 14 electron count, an electron deficiency that has led in many situations to η^2 or η^3 binding of benzyl ligands.15

Activation of alkyl complexes 1a,b, 2b and 3a by either [PhNMe₂H][B(C₆F₅)₄] or [Ph₃C][B(C₆F₅)₄] yields initiators for the polymerization of hex-1-ene in chlorobenzene at 0 °C. Polymerization yields are high, but the molecular masses of the polymers were found to be significantly smaller than expected when $ZrL^{1b}Me_2$ and $ZrL^{1b}(CH_2CHMe_2)_2$ were employed (Table 1). These results suggest that chain termination competes with propagation, but that the catalyst remains active thereafter and polymerization of a new chain is initiated. The [PhNMe2H]+ and [Ph₃C]⁺ activators seem to be equally efficient. The number average molecular mass of poly(hex-1-ene) prepared using ZrL^{1a}Me₂ is approximately that expected if no significant chain termination is taking place. In all cases polymerization activity ceases when 2,4-dimethylpyridine is added to the catalyst mixture, consistent with competitive binding of the nitrogen base to a cationic metal center. Analogous experiments employing HfL1aMe2 yielded results similar to those employing $ZrL^{1a}Me_2$, but use of TiL^{1a}Me₂ (activated bv $[PhNMe_2H][B(C_6F_5)_4]$ in $[^2H_5]$ bromobenzene) led to only *ca*. 75% consumption of 25 equiv. of hex-1-ene to give poly(hex-1-ene).

We conclude that [(2,6-R₂C₆H₃NCH₂CH₂)₂O]²⁻ ligands produce stable five-coordinate dialkyl complexes of Ti, Zr and Hf, and that 'cations' formed by protonation or oxidative cleavage of an alkyl group from Zr or Hf are initiators for the polymerization of hex-1-ene. These results should be contrasted with results obtained by McConville and co-workers^{5,6} where Ti is the most successful when the diamido ligand does not contain an additional donor.

R. R. S. thanks the Department of Energy (DEFG02-86ER13564) and Exxon for supporting this research, and M. A. is grateful for a Rueff-Wormser Postdoctoral Fellowship.

Footnotes and References

[†] Solid (TsOCH₂CH₂)₂O (5 g, 12.0 mmol) was added to a chilled (-30 °C) solution of 2,6- $Pr_{2}^{i}C_{6}H_{3}NHLi$ (4.53 g, 24.8 mmol) in thf (30 ml). After 24 h all solvents were removed in vacuo and the residue was extracted with pentane. The pentane was removed in vacuo to yield an orange oil (4.2 g, 82%). An analytically pure sample was obtained by recrystallization from a concentrated pentane solution at -30 °C: ¹H NMR (C₆D₆) δ 7.18–7.14 (m, 6, Haryl), 3.60 (t, 2, NH), 3.48 (spt, 4, CHMe2), 3.35 (t, 4, OCH2), 3.07 (q, 4, CH₂N), 1.06 (d, 24, CHMe₂); (CDCl₃) δ7.18-7.05 (m, 6, H_{aryl}), 3.70 (t, 4, OCH₂), 3.57 (br, 2, NH), 3.36 (spt, 4, CHMe₂), 3.14 (br t, 4, CH₂N), 1.27 (d. 24, CHMe₂).

[‡] Satisfactory elemental analyses have been obtained (C, H, N).

§ ¹H NMR (C_6D_6) δ 3.15 (t, 4, OCH₂), 2.95 (dt, 4, CH₂N), 2.24 (s, 12, ArMe).

¶ Crystallographic data: ZrL1aMe2: Siemens SMART/CCD, orthorhombic, space group *Pnma*, a = 12.741(3), b = 22.663(5), c = 7.518(2) Å, $\hat{U} = 2170.9(8) \text{ Å}^3, Z = 4, D_c = 1.321 \text{ g cm}^{-3}, R = 0.0368, R_w = 0.1009,$ GOF = 1.179. For TiL^{1a}(CH₂Ph)₂: Siemens SMART/CCD, orthorhombic, space group Fdd2, a = 32.803(8), b = 42.342(13), c = 8.547(4) Å, U = 11872(7) Å³, Z = 16, $D_c = 1.210$ g cm⁻³, R = 0.0609, $R_w = 0.1269$, GOF = 1.095. CCDC 182/679.

|| In a typical experiment a chilled (-30 °C) solution of 1b (19 mg, 44 µmol) in chlorobenzene (3 ml) was added to a suspension of [PhNMe₂H][B(C_6F_5)₄] $(32 \text{ mg}, 40 \text{ }\mu\text{mol})$ in chlorobenzene (6 ml) at -30 °C. The reaction mixture was allowed to warm to room temp. and was stirred for 15 min. The reaction mixture was cooled to 0 °C and hex-1-ene (1.0 ml, 8.0 mmol) was added all at once. After stirring for 1 h at 0 °C the reaction was quenched with HCl (1.0 M in ether, 4 ml). In a typical experiment employing $[Ph_3C][B(C_6F_5)_4]$ the reaction mixture was stirred for 2 min at -30 °C and allowed to equilibrate at 0 °C before hex-1-ene (1.0 ml, 8.0 mmol) was added all at once.

- 1 H. H. Brintzinger, D. Fischer, R. Mulhaupt, B. Rieger and R. M. Waymouth, Angew. Chem., Int. Ed. Engl., 1995, 34, 1143.
- W. Kaminsky and M. Ardnt, Adv. Polym. Sci., 1997, 127, 144.
- 3 M. Bochmann, J. Chem. Soc., Dalton Trans., 1996, 255.
- 4 Y.-X. Chen and T. J. Marks, Organometallics, 1997, 16, 3649.
- 5 J. D. Scollard and D. H. McConville, J. Am. Chem. Soc., 1996, 118, 10 008
- 6 J. D. Scollard, D. H. McConville, N. C. Payne and J. J. Vittal, Macromolecules, 1996, 29, 5241.
- 7 J. D. Scollard, D. H. McConville and J. J. Vittal, Organometallics, 1995, 14. 5478.
- 8 F. Guérin, D. H. McConville and J. J. Vittal, Organometallics, 1996, 15, 5586
- 9 K. Aoyagi, P. K. Gantzel, K. Kalai and T. D. Tilley, Organometallics, 1996, 15, 923.
- 10 R. Baumann, W. M. Davis and R. R. Schrock, J. Am. Chem. Soc., 1997. 119.3830
- 11 A. D. Horton, J. de With, A. J. van der Linden and H. van de Weg, Organometallics, 1996, 15, 2672.
- 12 F. G. N. Cloke, T. J. Geldbach, P. B. Hitchcock and J. B. Love, J. Organomet. Chem., 1996, 506, 343.
- 13 T. H. Warren, R. R. Schrock and W. M. Davis, Organometallics, 1996, 15. 562.
- 14 F. Guérin, D. H. McConville and J. J. Vittal, Organometallics, 1995, 14, 3154.
- 15 J. P. Collman, L. S. Hegedus, J. R. Norton and R. G. Finke, Principles and Applications of Organotransition Metal Chemistry, University Science Books, Mill Valley, CA, 2nd edn., 1987.

Received in Bloomington, IN, USA, 3rd September 1997; 7/06452G