

# A Thieno[2,3-b]pyridine-Flanked Diketopyrrolopyrrole Polymer as an n-Type Polymer Semiconductor for All-Polymer Solar Cells and Organic Field-Effect Transistors

Hung-Yang Chen,<sup>\*,†©</sup> Mark Nikolka,<sup>‡</sup> Andrew Wadsworth,<sup>†©</sup> Wan Yue,<sup>†,||</sup> Ada Onwubiko,<sup>†</sup> Mingfei Xiao,<sup>‡</sup> Andrew J. P. White,<sup>†</sup> Derya Baran,<sup>†,§</sup> Henning Sirringhaus,<sup>‡</sup> and Iain McCulloch<sup>†,§</sup>©

<sup>†</sup>Department of Chemistry and Centre for Plastic Electronics, Imperial College London, London SW7 2AZ, U.K.

<sup>‡</sup>Cavendish Laboratory, University of Cambridge, J. J. Thompson Avenue, Cambridge CB3 0HE, U.K.

<sup>§</sup>King Abdullah University of Science and Technology (KAUST), KSC, Thuwal 23955-6900, Saudi Arabia

<sup>II</sup>Key Laboratory for Polymeric Composite and Functional Materials of Ministry of Education, School of Material and Material Engineering, Sun Yat-Sen University, Guangzhou 510275, China

### **S** Supporting Information

**ABSTRACT:** A novel fused heterocycle-flanked diketopyrrolopyrrole (DPP) monomer, thieno[2,3-*b*]pyridine diketopyrrolopyrrole (TPDPP), was designed and synthesized. When copolymerized with 3,4-difluorothiophene using Stille coupling polymerization, the new polymer pTPDPP-TF possesses a highly planar conjugated polymer backbone due to the fused thieno[2,3-*b*]pyridine flanking unit that effectively alleviates the steric hindrance with both the central DPP core and the 3,4-difluorothiophene repeat unit. This new polymer exhibits a high electron affinity (EA) of -4.1 eV and was successfully utilized as an n-type polymer semiconductor for applications in organic field-effect transistors (OFETs) and all polymer solar cells. A promising n-type charge carrier mobility of 0.1 cm<sup>2</sup> V<sup>-1</sup>



s<sup>-1</sup> was obtained in bottom-contact, top-gate OFETs, and a power conversion efficiency (PCE) of 2.72% with a high opencircuit voltage ( $V_{\rm OC}$ ) of 1.04 V was achieved for all polymer solar cells using PTB7-Th as the polymer donor.

## INTRODUCTION

Solution-processable polymer semiconductors are promising candidates to realize next-generation lightweight and flexible electronics, such as organic field-effect transistors (OFETs) and organic solar cells (OSCs), via low cost and large area printing. The past decade has witnessed a tremendous advance in p-type polymer semiconductors with hole mobilities surpassing 10 cm<sup>2</sup> V<sup>-1</sup> s<sup>-1</sup> in OFETs<sup>1,2</sup> and power conversion efficiencies (PCEs) above 11% in OSCs.<sup>3,4</sup> To achieve broad applications of organic electronics such as organic complementary circuits and all polymer solar cells, congruent performances for both p- and n-type polymer semiconductors are desired. However, the progress in n-type polymer semiconductor development is much slower in comparison with its p-type counterparts with few polymers demonstrating electron mobility higher than 5 cm<sup>2</sup>  $V^{-1}$  s<sup>-1</sup> in OFETs<sup>5,6</sup> and PCEs higher than 7% as acceptors in OSCs.<sup>7-11</sup> Moreover, most high performance n-type polymer semiconductors are constructed by rylene diimide-based structure, such as perylene diimide (PDI),<sup>11–13</sup> naphthalene diimide (NDI),<sup>8,10,14</sup> or naphthodithiophene diimide (NDTI).<sup>15,16</sup>

Diketopyrrolopyrrole (DPP)-based small molecules and polymers have shown excellent performance as p-type semiconductors in OFETs and OSCs<sup>17</sup> due to their high structural planarity, small optical gap,<sup>18</sup> and high absorption coefficient.<sup>19</sup> Impressive hole mobility of higher than 1 cm<sup>2</sup>  $V^{-1}\ s^{-1}$  in  $\mbox{OFETs}^{20,21}$  and PCEs above 8% as donors in OSCs<sup>20,22</sup> have been reported in these DPP polymers. High short-circuit current  $(I_{SC})$  of larger than 20 mA cm<sup>-2</sup> in OSCs using DPP polymer donors are also reported.<sup>20,23</sup> The bicyclic DPP core is usually flanked with electron-rich aryl units on both sides at the 3- and 6-positions of DPP, such as phenyl, furan, thiophene, selenophene, and thieno [3,2-b]thiophene.<sup>18,24,25</sup> Although the bis-lactam core DPP unit is electron-deficient, few examples are demonstrated to realize DPP-based polymers as predominantly n-type polymer semiconductors.<sup>26</sup> These examples utilize electron-deficient comonomers, such as benzothiadiazole,<sup>27</sup> fluorinated phenylene,<sup>28</sup>

Received: May 15, 2017

Revised: December 10, 2017

Scheme 1. Fused Heterocycle-Flanked DPP Polymers



Scheme 2. Synthetic Route of Thieno [2,3-b] pyridine – Diketopyrrolopyrrole (TPDPP) and Brominated Thieno [2,3-b] pyridine – Diketopyrrolopyrrole ( $\alpha$ - and  $\beta$ -Brominated TPDPP)<sup>*a*</sup>



<sup>a</sup>Reagents: (a) *m*-CPBA, CHCl<sub>3</sub>; (b) dimethylcarbamyl cloride, trimethylsilyl cyanide, CH<sub>3</sub>CN; (c) Na, cat. FeCl<sub>3</sub>, 2-methyl-2-butanol, diethyl succinate; (d) 9-(bromomethyl)nonadecane, K<sub>2</sub>CO<sub>3</sub>, 18-crown-6, DMF; (e) NBS, DMF; (f) i. "BuLi/THF; ii. CBr<sub>4</sub>/THF; (g) dimethylcarbamyl chloride, trimethylsilyl cyanide, CH<sub>2</sub>Cl<sub>2</sub>.

and thienylcyanovinylene,<sup>29</sup> to increase the electron affinity (EA) and achieve n-type charge transport.

There are, however, very few examples reported with modification by electron-deficient flanking substituents on the DPP core. Replacement of thiophene by thiazole to synthesize a thiazole-flanked DPP unit was successfully employed as a building block for n-type polymer semiconductors. The polymer PDPP2TzT possesses an electron mobility of 0.13 cm<sup>2</sup> V<sup>-1</sup> s<sup>-1</sup> in OFET and was employed as an acceptor in OSC with a PCE around 3%.<sup>30,31</sup> Pyridine was also chosen as the flanking substituent for the DPP core, which is more electron deficient than the commonly used aryl units (thiophene, furan, and benzene) and also possesses a smaller steric hindrance between the N-CH<sub>2</sub> of the alkyl chain and the nitrogen atom at the ortho-position of pyridine.<sup>5</sup> When copolymerized with 2,2'-bithiophene, the polymer PDBPyBT demonstrated ambipolar charge transport compared with its analogous thiophene polymer, PDQT, which showed only ptype charge transport.<sup>3</sup>

A DPP-based repeat unit bearing the fused heterocycle, thieno[3,2-*b*]thiophene, has previously been demonstrated with impressive performances as p-type semiconducting polymers in both OFETs and OSCs.<sup>20,25,33,34</sup> The fused heterocycle substituent with increased intermolecular association through extended polymer coplanarity was shown to

enhance intermolecular charge-carrier hopping. This approach was used to design an n-type semiconducting polymer based on the DPP core with an electron-deficient flanking unit. A fused heterocycle thieno[2,3-b]pyridine was chosen as the flanking unit (Scheme 1). The thieno[3,2-*b*]thiophene-flanked DPP unit has less steric effects than phenyl-flanked units as the five-membered ring of thiophene adjacent to the DPP core does not possess alpha C-H groups which can exhibit torsional twisting, thus increasing the dihedral angle between the linked units. On the other hand, thieno [2,3-b]pyridineflanked DPP monomer also shows a suppressed steric hindrance through the positioning of the less steric nitrogen atom adjacent to the DPP core to improve the coplanarity. Furthermore, thieno [2,3-b] pyridine is more electron deficient than thieno [3,2-b] thiophene which has the benefit of increasing the electron affinity. Besides, we choose thieno-[2,3-b]pyridine as the flanking substituent rather than thieno[3,2-b]pyridine is due to its ability to adopt a quinoid resonance form, which is potential for smaller band gap and better charge transport for the polymer chain. However, a quinoid resonance structure cannot be formed when using thieno[3,2-b]pyridine as the flanking substituent on the DPP core. Additionally, compared with the pyridine-flanked DPP polymer, PDBPyBT, which has a larger steric hindrance between 3,5-positions of hydrogen atoms on the pyridine with



Figure 1. Chemical structure and single crystal structure (front and side view) of 2EH-TPDPP.

linking comonomers, the flanking thiophene on the thieno[2,3-b]pyridine flanked DPP should have reduced backbone twisting with linking comonomers compared with the pyridine-flanked DPP monomer.<sup>5</sup> As shown in Scheme 1, the electron-deficient 3,4-difluorothiophene was chosen as the comonomer to ensure a high coplanarity and high electron affinity (EA) for the polymer.

## RESULTS AND DISCUSSION

Scheme 2 shows the synthetic routes of the brominated thieno[2,3-b]pyridine-diketopyrrolopyrrole (TPDPP) monomer and its derivatives. Initially, the thieno[2,3-*b*]pyridine core was synthesized in one step from commercially available 2nitrothiophene according to the literature procedure.<sup>35</sup> Beyond our expectations, it was tortuous to obtain the TPDPP monomer. First, we started our approach using route I following reactions analogous to those commonly used in the diaryl-DPP. The carbonitrile precursor in preparing DPP, thieno [2,3-b] pyridine-6-carbonitrile 3, can be easily synthesized from thieno [2,3-b] pyridine by two steps in moderate yields. After obtaining the non-alkylated TPDPP 4 from 3 according the literature method, a long and branched 2octyldodecyl chain was anchored on the TPDPP core to obtain C8C10-TPDPP to ensure a good solubility for the polymer. However, the bromination of C8C10-TPDPP using Nbromosuccinimde (NBS) or liquid bromine resulted in a decomposition of the TPDPP core and unidentified side products.

We therefore modified our synthetic route to introduce the bromine atom at the earlier step as presented in route II. Bromination of thieno [2,3-*b*] pyridine-6-carbonitrile 3 using *N*-bromosuccinimide proceeded smoothly in DMF. Surprisingly, it was found afterward that the bromination occurred at the  $\beta$ -position of 3 to afford 5, with the consequence that the UV-

vis absorption spectrum of the polymer obtained from the  $\beta$ position dibrominated TPDPP monomer,  $\beta$ -Br<sub>2</sub>TPDPP, and distannylated thiophene by Stille polymerization having a much higher energy absorption than expected (see Supporting Information, Figure S7). As shown in Figure S7, the absorption of the polymer pTPDPP- $\beta$ -T shows a less bathochromic shift compared with the monomer  $\beta$ -Br<sub>2</sub>TPDPP, which is not in accordance with literature reported DPP polymers using thiophene as the comonomer. This is likely due to crossconjugation and therefore reduced delocalization. Therefore, a single crystal of 3-bromothieno[2,3-b]pyridine-6-carbonitrile 5 was prepared to confirm the position of the bromine atom on the thieno [2,3-b] pyridine-6-carbonitrile. The absolute configuration of the single-crystal structure indeed shows the bromination occurred at the  $\beta$ -position of 3, and crystal data of compound 5 are shown in the Supporting Information (Figure S4). A previous literature has also shown the bromination of thieno[2,3-b] pyridine<sup>35</sup> using liquid bromine can lead to the  $\beta$ -position brominated product. A similar situation also occurred in the case of benzo[b]thiophene.<sup>36</sup> Because of the higher reactivity for the  $\beta$ -position of thieno[2,3-b]pyridine-6-carbonitrile 3 under electrophilic halogenation, we changed our strategy by using *n*-butyllithium to deprotonate the  $\alpha$ -position of thieno [2,3-*b*] pyridine 1. The nucleophilic  $\alpha$ -lithiated thieno [2,3-*b*] pyridine was then reacted with the bromine source tetrabromomethane (CBr<sub>4</sub>) to afford 2-bromothieno[2,3-b]pyridine 7. The carbonitrile precursor, 2bromothieno[2,3-b]pyridine-6-carbonitrile 9, was obtained in two steps analogous to those in route I, in which the structure of compound 9 was also confirmed from its single crystal (Figure S5). Finally, the  $\alpha$ -position dibrominated TPDPP,  $\alpha$ -Br<sub>2</sub>TPDPP, was obtained from 9 as a deep red solid, which is soluble in common organic solvents.

As shown in Scheme 3, the polymer pTPDPP-TF was then synthesized from dibrominated TPDPP monomer,  $\alpha$ -



**Figure 2.** Left: normalized UV–vis absorption spectra of pTPDPP-TF in 1,2-dichlorobenzene and as thin film. Middle: cyclic voltammograms of pTPDPP-TF thin film drop cast on a Pt working electrode (reference electrode: Ag/AgCl, counter electrode: Pt gauze, electrolyte solution: 0.1 M TBAPF<sub>6</sub> in anhydrous acetonitrile). Right: XRD diffractogram of the as cast film on Si wafer for pTPDPP-TF.



Figure 3. Dihedral angles of energy-minimized polymer backbone structure of pTPDPP-TF (front and side view).

Br<sub>2</sub>TPDPP, and 2,5-bis(trimethylstannyl)-3,4-difluorothiophene comonomer using palladium-catalyzed Stille coupling polymerization. The crude polymer was purified by Soxhlet extraction in the sequence of methanol, hexane, ethyl acetate, and chloroform. The purified polymer, soluble in chloroform, chlorobenzene, and 1,2-dichlorobenzene at room temperature, has a weight-average molecular weight ( $M_w$ ) of 125.3 kDa and number-average molecular weight ( $M_n$ ) of 24.4 kDa giving a polydispersity (PDI) of 5.1, likely an overestimate due to aggregating effects in solution.

To confirm the planarity of the new TPDPP monomer, a model TPDPP small molecule anchored with two shorter 2ethylhexyl branched chains (2EH-TPDPP) was synthesized, and the single crystal structure was easily obtained from slow evaporation of a binary solvent system (chloroform and methanol). Detailed crystallographic data are shown in Figure S6. Figure 1 shows the single crystal structure of 2EH-TPDPP, which exhibits a dihedral angle of  $7.1^{\circ}$  between the thieno [2,3b]pyridine ring and the DPP core. Although 2-pyridinylsubstituted DPP block has been reported with a dihedral angle between pyridine and the DPP core being  $0^{\circ}$  from computer simulations,<sup>5</sup> no applicable references of the pyridinyl-DPP crystal structure are available to the best of our knowledge. Moreover, the small dihedral angle of 2EH-TPDPP is similar to thiophene-containing DPP molecules that have dihedral angles ranging from 3° to 9° in several reported crystal structures.<sup>37</sup> This indicates that a highly coplanar structure and  $\pi$ -electron delocalization could be achieved in the polymer backbone when using TPDPP as the building block.

As shown in Figure 2, the UV–vis absorption spectra of pTPDPP-TF in 1,2-dichlorobenzene (1,2-DCB) and as thin film exhibit almost the same absorption profile. This is attributed to small polymer aggregates of pTPDPP-TF in 1,2-DCB solution, showing two vibronic peaks at around 642 and 711 nm. The optical band gap calculated from the onset

absorption of the thin film is 1.66 eV, which is significantly larger than the thieno [3,2-b] thiophene-flanked DPP polymer (1.38 eV).<sup>25</sup> This can be attributed to a lower degree of intramolecular donor-acceptor molecular orbital hybridization among the polymer conjugation backbone of pTPDPP-TF.

Photoelectron spectroscopy in air (PESA) was utilized to measure the ionization potential (IP) of pTPDPP-TF thin films. A large IP of -5.8 eV was measured, and the electron affinity (EA) was subsequently obtained as -4.1 eV by the addition of its optical band gap. The EA of pTPDPP-TF is significantly higher than that of thieno [3,2-b] thiopheneflanked DPP polymer (-3.7 eV).<sup>25</sup> This high EA value would be beneficial in electron injection for n-type OFETs and also to promote charge separation in donor/acceptor blends in bulk-heterojunction OSCs. In considering the ability of pTPDPP-TF to be utilized as an n-type semiconductor, cyclic voltammetry (CV) was used to study its electron affinity and the stability of its negatively charged polaron. As shown clearly in Figure 2, a reversible reduction cycle was observed, suggesting its excellent electron-accepting ability and reversibility. The EA value of pTPDPP-TF calculated from the onset reduction potential is -3.51 eV, which is higher lying than that of  $PC_{71}BM$  (-3.90 eV) measured in the same conditions (see Supporting Information). An improved open-circuit voltage  $(V_{\rm OC})$  relative to PC<sub>71</sub>BM can be expected in the solar cell when using pTPDPP-TF as the acceptor.

pTPDPP-TF adopts a lamellar type packing motif similar to other DPP polymers,<sup>18,20</sup> which can be evident from the (100) and (200) diffraction peaks in its XRD diffractogram (Figure 2, right). The first-order diffraction peak  $2\theta = 4.5^{\circ}$  corresponds to a *d*-spacing of 19.7 Å. Although pTPDPP-TF orients predominantly edge-on relative to the substrate as evident from the stronger intensity of (100) diffraction peak, we assume the broad featureless diffractions from  $2\theta = 15^{\circ}$  to  $30^{\circ}$ 

Article



**Figure 4.** (a) Transistor transfer characteristics and gate-voltage ( $V_G$ ) dependence of saturation mobility for OFETs ( $L = 20 \ \mu m$ ,  $W = 1 \ mm$ ). (b) n-Type output characteristics for pTPDPP-TF gate-voltage ( $V_G$ ).



Figure 5. (a) J-V curves of optimized PTB7-Th:pTPDPP-TF (1:1) solar cell. (b) EQE spectrum (line + symbol) of optimized PTB7-Th:pTPDPP-TF (1:1) solar cell alongside normalized thin film absorption spectra (line) of PTB7-Th and pTPDPP-TF.

likely contain reflections from face-on crystallites and other tilted chain orientations.  $^{\rm 38}$ 

In order to further probe the dihedral angles between adjacent backbone units, a computational modeling study using density functional theory (DFT) at the B3LYP 6-31G level was used to predict energy-minimized polymer backbone structure and study backbone planarity for pTPDPP-TF. As shown in Figure 3, pTPDPP-TF exhibits close to coplanar dihedral angles between the DPP unit and adjacent substituents (thieno [2,3-b] pyridine). This is attributed to the effective suppression of steric hindrance from the 2-pvridinvl groups. However, there is more of a twist in the molecule, as observed from the single crystal structure, than is predicted by DFT. It is possible that the small twist may arise from the longer alkyl chain (2-ethylhexyl) of the model compound than the calculated structure (methyl). Furthermore, pTPDPP-TF is almost completely coplanar along the backbone due to the absence of steric hindrance between TPDPP monomer and 3,4-difluorothiophene monomers. This highly planar polymer backbone is in agreement with its tendency of forming small aggregates in solution due to strong  $\pi - \pi$  interactions between polymer chains.

In Figure 4, representative transfer characteristics of OFET for the investigated polymer pTPDPP-TF are shown. We find that in our device architecture (bottom-contact, top-gate with gold electrodes), after annealing at 100  $^{\circ}$ C, pTPDPP-TF

exhibits ambipolar charge transport characteristics with more pronounced n-type than p-type transport behavior was observed. As evident from the gate-voltage ( $V_{\rm G}$ ) dependence of extracted charge carrier mobilities presented in Figure 4a, we found that the maximum n-type field-effect mobility of pTPDPP-TF was obtained as 0.1 cm<sup>2</sup> V<sup>-1</sup> s<sup>-1</sup> with a corresponding on—off ratio of 10<sup>4</sup>, and the threshold voltage for pTPDPP-TF OFET was 14 V. Fitting of the transfer characteristics with an ideal MOSFET model as described elsewhere<sup>39</sup> results in a conservative mobility of 0.04 cm<sup>2</sup> V<sup>-1</sup> s<sup>-1</sup>. The output characteristics in Figure 4b do not exhibit the typical S-shape associated with an injection barrier, suggesting that the LUMO level is close enough to the electrode Fermi level to provide good injection of electrons.

Polymer–polymer solar cells, using PTB7-Th (also known as PBDTTT-EFT) as the donor and pTPDPP-TF as the acceptor, were fabricated in an inverted device architecture of glass/ITO/ZnO/PTB7-Th:pTPDPP-TF (1:1)/MoO<sub>3</sub>/Ag. PTB7-Th has been reported to have an EA value of -3.66 eV and a IP value of -5.24 eV using ultraviolet photoelectron spectroscopy (UPS);<sup>40</sup> therefore, sufficient energetic offsets between PTB7-Th and pTPDPP-TF were expected for charge separation. The active layer solution was prepared in 1,2-dichlorobenzene, without the use of additives. The best device gave a power conversion efficiency (PCE) of 2.72% with a short-circuit current density ( $I_{SC}$ ) of 6.57 mA cm<sup>-2</sup>. A low fill

factor (FF) of 0.40 was obtained, suggesting poor phase separation in the blend, resulting in significant charge recombination.<sup>30</sup> However, a high open-circuit voltage  $(V_{OC})$ of 1.04 V was obtained, which has a significant improvement compared with the PCE10:PC71BM blend due to the higher EA of pTPDPP-TF (according to our comparison of EA values from cyclic voltammetry).40 The EQE of the best PTB7-Th:pTPDPP-TF device is shown in Figure 5b, alongside the normalized absorption spectra of pristine PTB7-Th and pTPDPP-TF. It can be seen clearly that the EQE around 450 nm is mainly contributed from pTPDPP-TF due to its stronger absorption in this spectral region. This is also evidence of charge generation from "channel II",<sup>41</sup> where the exciton was generated from the acceptor, followed by hole transfer from acceptor to donor. The EQE in the range of 500-800 nm can be attributed to both PTB7-Th and pTPDPP-TF due to their overlapping absorptions and the stronger EQE intensity.

## CONCLUSIONS

A new fused heterocycle-flanked diketopyrrolopyrrole (DPP) monomer possessing a planar and electron-deficient structure was designed and successfully synthesized. The fused thieno-[2,3-b]pyridine flanking unit effectively alleviates the steric hindrance both with the central DPP core and the comonomers due to the less sterically nitrogen atom and thiophene ring on the thieno [2,3-b] pyridine, respectively. When copolymerized with electron-deficient 3,4-difluorothiophene, the resulting polymer pTPDPP-TF features a highly planar conjugated backbone with a high EA and IP values of -4.1 eV and -5.8 eV, respectively. A good and reversible electron-accepting ability was also observed from cyclic voltammetry. A promising n-type charge carrier mobility of 0.1 cm<sup>2</sup> V<sup>-1</sup> s<sup>-1</sup> was obtained in bottom-contact, top-gate OFETs. All polymer solar cells using PTB7-Th as the polymer donor gave a power-conversion efficiency of 2.72% with a high open-circuit voltage of 1.04 V. These results demonstrate that the new DPP monomer TPDPP as a potential building block for the design of n-type semiconducting polymers.

## EXPERIMENTAL SECTION

**Materials.** Thieno [2,3-b] pyridine<sup>35</sup> and 2,5-bis(trimethylstannyl)-3,4-difluorothiophene<sup>42</sup> were synthesized according to literature procedures. All other reagents and solvents were purchased from Sigma-Aldrich, VWR, Fluorochem, and Acros and used as received. Dry solvents for anhydrous reactions were purchased from Sigma-Aldrich, and no further attempt at drying them was made. All reactions were carried out under an inert argon atmosphere unless otherwise stated.

**Thieno**[2,3-*b*]**pyridine** 7-Oxide (2). A stirred solution of thieno[2,3-*b*]**pyridine** (1, 5.4 g, 40.0 mmol) in chloroform (180 mL) at room temperature was treated with *m*-chloroperoxybenzoic acid (*m*-CPBA 77%, 12.4 g, 71.9 mmol) in portions over a period of 30 min. After the reaction mixture was stirred for over 48 h, the solution was washed with 10% aqueous NaOH solution and then water. The organic phase was dried over MgSO<sub>4</sub>, filtered, and concentrated under vacuum to give a white solid (5.83 g, 96% yield). The crude product was used in the next step without any further purification. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 8.35 (d, *J* = 6.2 Hz, 1H), 7.77 (m, *J* = 8.0, 0.4 Hz, 1H), 7.60 (d, *J* = 5.7 Hz, 1H), 7.37–7.30 (m, 2H). <sup>13</sup>C NMR (101 MHz, CDCl<sub>3</sub>)  $\delta$ : 136.88, 134.23, 128.44, 123.08, 121.92, 121.37.

**Thieno[2,3-b]pyridine-6-carbonitrile (3).** To a stirred solution of thieno[2,3-b]pyridine-7-oxide (2, 5.44 g, 36.0 mmol) in acetonitrile (360 mL) at room temperature, dimethyl carbamyl chloride (6.7 mL,

72.0 mmol) was added dropwise under an argon atmosphere, followed by slowly addition of trimethyl cyanide (6.9 mL, 54.0 mmol). The reaction mixture was heated to 100 °C. After being stirred at 100 °C for 4 h, the reaction mixture was cooled to room temperature, and then 10% K<sub>2</sub>CO<sub>3</sub> aqueous solution was added to quench the reaction. The layers were allowed to separate; the organic layer was isolated and dried by MgSO<sub>4</sub>, filtered, and then concentrated. The crude product was purified by column chromatography with petroleum ether/ethyl acetate (9:1) as the eluent to give compound **3** as a white solid (5.6 g, 97% yield). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 8.22 (d, *J* = 8.2 Hz, 1H), 7.85 (d, *J* = 6.0 Hz, 1H), 7.70 (d, *J* = 8.2 Hz, 11H), 7.40 (d, *J* = 6.0 Hz, 1H). <sup>13</sup>C NMR (101 MHz, CDCl<sub>3</sub>)  $\delta$ : 162.23, 134.72, 132.16, 131.54, 129.44, 123.37, 121.46, 117.55.

**3,6-Bis(thieno[2,3-***b***]pyridin-6-yl)-2,5-dihydropyrrolo[3,4-***c***]pyrrole-1,4-dione (4). Sodium (0.69 g, 30.0 mmol) and iron(III) chloride (30 mg) were added to 20 mL of 2-methyl-2-butanol, and the mixture was heated to reflux until full consumption of the sodium was observed (about 3 h). The solution was cooled to 85 °C, and then thieno[2,3-***b***]pyridine-6-carbonitrile (3, 3.2 g, 20.0 mmol) was added, followed by diethyl succinate (1.33 mL, 8.0 mmol). After stirring for 2 h, the reaction was cooled to 50 °C, and methanol (25.0 mL) was added. The reaction was quenched by addition of glacial acetic acid (8.0 mL) and refluxed for 15 min. The reaction mixture was filtered and washed with water (2 × 50 mL), hot methanol (2 × 50 mL), acetone (2 × 25 mL), and hexane (25 mL) to afford the product as a dark purple solid (2.1 g, 52% yield), which was used without further purification.** 

2,5-Bis(2-octyldodecyl)-3,6-bis(thieno[2,3-b]pyridin-6-yl)-2,5-dihydropyrrolo[3,4-c]pyrrole-1,4-dione (C8C10-TPDPP). To a mixture of 3,6-bis(thieno[2,3-b]pyridin-6-yl)-2,5dihydropyrrolo[3,4-c]pyrrole-1,4-dione (4, 0.49 g, 1.22 mmol), potassium carbonate (0.56 g, 4.03 mmol), and 18-crown-6 (6 mg) in DMF (20 mL) was added 9-(bromomethyl)nonadecane (1.46 g, 4.03 mmol). The reaction mixture was stirred at 120 °C for overnight and then cooled to room temperature. Chloroform (50 mL) and water were added (100 mL), and the layers were separated. The organic layer was washed with saturated brine, dried over MgSO4, filtered, and then concentrated under vacuum. Column chromatography on silica gel with petroleum ether/CH<sub>2</sub>Cl<sub>2</sub> (4:1) as the eluent followed by recrystallization from CH2Cl2 and MeOH afforded C8C10-TPDPP as a deep red solid (0.35 g, 30% yield). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 9.10 (d, J = 8.5 Hz, 2H), 8.28 (d, J = 8.5 Hz, 2H), 7.72 (d, J = 6.0 Hz, 2H), 7.39 (d, J = 6.0 Hz, 2H), 4.46 (d, J = 7.2 Hz, 4H), 1.74–1.63 (m, 2H), 1.34–1.06 (m, 64H), 0.87 (dt, J = 8.6, 7.0 Hz, 12H).  $^{13}$ C NMR (101 MHz, CDCl<sub>3</sub>)  $\delta$ : 162.72, 160.92, 145.48, 144.42, 133.12, 131.51, 130.10, 123.11, 121.77, 111.66, 46.44, 38.55, 31.93, 31.89, 31.59, 30.11, 29.66, 29.57, 29.52, 29.37, 29.31, 26.56, 22.70, 14.12.

**3-Bromothieno**[2,3-*b*]**pyridine-6-carbonitrile (5).** To a stirred solution of thieno[2,3-*b*]**pyridine-6-carbonitrile (3,** 0.32 g, 2.0 mmol) in anhydrous DMF was added *N*-bromosuccinimide (0.37 g, 2.1 mmol) at room temperature. The reaction mixture was stirred at room temperature for overnight. The reaction mixture was poured into water and then extracted with ethyl acetate for three times. The organic layers were collected and then washed with water and brine, dried over MgSO<sub>4</sub>, filtered, and then concentrated under vacuum. Column chromatography on silica gel with petroleum ether/ethyl acetate (9:1) as the eluent gave compound **5** as a white solid (0.25 g, 53% yield). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 8.24 (d, *J* = 8.2 Hz, 1H), 7.85 (s, 1H), 7.81 (d, *J* = 8.2 Hz, 1H). <sup>13</sup>C NMR (101 MHz, CDCl<sub>3</sub>)  $\delta$ : 160.36, 133.57, 131.53, 130.68, 129.13, 124.02, 117.03, 105.56.

**3,6-Bis(3-bromothieno[2,3-b]pyridin-6-yl)-2,5dihydropyrrolo[3,4-c]pyrrole-1,4-dione (6).** Sodium (86 mg, 3.75 mmol) and iron(III) chloride (3.5 mg) were added to 2.5 mL of 2-methyl-2-butanol, and the mixture was heated to reflux until full consumption of the sodium was observed (about 3 h). The solution was cooled to 85 °C, and then 3-bromothieno[2,3-b]pyridine-6carbonitrile (5, 0.6 g, 2.5 mmol) was added, followed by diethyl succinate (0.17 mL, 1.0 mmol). After stirring for 2 h, the reaction was cooled to 50 °C, and methanol (3.0 mL) was added. The reaction was quenched by addition of glacial acetic acid (1.0 mL) and refluxed for 15 min. The reaction mixture was filtered and washed with water (2 × 20 mL), hot methanol (2 × 20 mL), acetone (2 × 10 mL), and hexane (10 mL) to afford the product 6 as a dark purple solid (0.35 g, 50% yield), which was used without further purification.

3,6-Bis(3-bromothieno[2,3-b]pyridin-6-yl)-2,5-bis(2-octyldodecyl)-2,5-dihydropyrrolo[3,4-c]pyrrole-1,4-dione ( $\beta$ -Br<sub>2</sub>TPDPP). To a mixture of 3,6-bis(3-bromothieno[2,3-b]pyridin-6-yl)-2,5-dihydropyrrolo[3,4-c]pyrrole-1,4-dione (6, 0.56 g, 1.0 mmol), potassium carbonate (0.42 g, 3.0 mmol), and 18-crown-6 (6.0 mg) in DMF (20 mL) was added 9-(bromomethyl)nonadecane (1.31 g, 3.0 mmol). The reaction mixture was stirred at 120 °C for overnight and then cooled to room temperature. Chloroform and water were added, and the layers were separated. The organic layer was washed with saturated brine, dried over MgSO<sub>4</sub>, filtered, and then concentrated under vacuum. Column chromatography on silica gel with petroleum ether/ $CH_2Cl_2$  (4:1) as the eluent followed by recrystallization from  $CH_2Cl_2$  and MeOH afforded  $\beta$ -Br<sub>2</sub>TPDPP as a deep red solid (90 mg, 8% yield). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 9.18 (d, J = 8.5 Hz, 2H), 8.29 (d, J = 8.5 Hz, 2H), 7.72 (s, 2H), 4.44 (d, J = 7.1 Hz, 4H), 1.71-1.61 (m, 2H), 1.40-1.07 (m, 64H), 0.88(q, J = 7.0 Hz, 12 H).

2-Bromothieno[2,3-b]pyridine (7). To a stirred solution of thieno[2,3-b]pyridine (1, 1.5 g, 11.1 mmol) in anhydrous THF (30 mL) was added n-butyllithium (2.5 M, 4.9 mL, 12.2 mmol) dropwise at -78 °C under an argon atmosphere. After the reaction mixture was stirred for 1 h at -78 °C, a solution of tetrabromomethane (4.0 g, 12.2 mmol) in anhydrous THF (10 mL) was added dropwise. After addition, the reaction mixture was allowed to warm to room temperature and then stirred for overnight. The reaction was quenched with 10% aqueous Na<sub>2</sub>S<sub>2</sub>O<sub>3</sub> solution and then extracted with ethyl acetate for three times. The organic phases were combined, dried over MgSO<sub>4</sub>, filtered, and then concentrated. The crude product was purified by silica gel column chromatography with petroleum/ ethyl acetate (4:1) as the eluent to give compound 7 as a white solid (2.23 g, 94% yield). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 8.60 (dd, J = 4.6, 1.5 Hz, 1H), 8.10 (dd, J = 8.0, 1.6 Hz, 1H), 7.56 (d, J = 6.0 Hz, 1H), 7.36-7.30 (m, 1H).

**2-Bromothieno**[2,3-*b*]**pyridine-7-oxide (8).** A stirred solution of 2-bromothieno[2,3-*b*]**pyridine** (7, 2.4 g, 11.1 mmol) in chloroform (50 mL) at room temperature was treated with *m*-chloroperoxybenzoic acid (*m*-CPBA 77%, 3.11 g, 18.0 mmol) in portions over a period of 30 min. After the reaction mixture was stirred for over 48 h, the solution was washed with 10% aqueous NaOH solution and then water. The organic phase was dried over MgSO<sub>4</sub>, filtered, and concentrated under vacuum to give a light brown solid (1.94 g, 76% yield). The crude product was used in the next step without any further purification. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 8.27 (dd, *J* = 6.3, 0.8 Hz, 1H), 7.63 (dd, *J* = 8.1, 0.9 Hz, 1H), 7.38 (s, 1H), 7.32 (dd, *J* = 8.1, 6.3 Hz, 1H). <sup>13</sup>C NMR (101 MHz, CDCl<sub>3</sub>)  $\delta$ : 149.84, 136.93, 134.28, 125.64, 122.04, 120.89, 118.86.

**2-Bromothieno**[**2**,**3**-*b*]**pyridine-6-carbonitrile** (**9**). To a stirred solution of 2-bromothieno[2,3-*b*]**pyridine-7-oxide** (**8**, 3.0 g, 13.04 mmol) in dichloromethane at room temperature, dimethyl carbamyl chloride (1.4 mL, 15.13 mmol) was added dropwise under an argon atmosphere, followed by slowly addition of trimethyl cyanide (1.9 mL, 15.13 mmol). After the reaction mixture was stirred for 14 days at room temperature, 10% K<sub>2</sub>CO<sub>3</sub> aqueous solution was added to quench the reaction. The layers were allowed to separate; the organic layer was isolated and dried by MgSO<sub>4</sub>, filtered, and then concentrated. The crude product was purified by column chromatography with petroleum ether/ethyl acetate (9:1) as the eluent to give compound 9 as a white solid (1.78 g, 57% yield). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 8.09 (d, *J* = 8.2 Hz, 1H), 7.67 (d, *J* = 8.2 Hz, 1H), 7.44 (s, 1H).

**3,6-Bis(2-bromothieno[2,3-b]pyridin-6-yl)-2,5dihydropyrrolo[3,4-c]pyrrole-1,4-dione (10).** Sodium (0.43 g, 18.7 mmol) and iron(III) chloride (17 mg) were added to 12.5 mL of 2-methyl-2-butanol, and the mixture was heated to reflux until full consumption of the sodium was observed (about 3 h). The solution was cooled to 85 °C, and then 2-bromothieno[2,3-*b*]pyridine-6-carbonitrile 9 (3.0 g, 12.55 mmol) was added, followed by diethyl succinate (0.85 mL, 5.02 mmol). After stirring for 2 h, the reaction was cooled to 50 °C, and methanol (17 mL) was added. The reaction was quenched by addition of glacial acetic acid (5 mL) and refluxed for 15 min. The reaction mixture was filtered and washed with water (2 × 50 mL), hot methanol (2 × 50 mL), acetone (2 × 25 mL), and hexane (25 mL) to afford the product as a black solid (1.4 g, 40% yield), which was used without further purification.

3,6-Bis(2-bromothieno[2,3-b]pyridin-6-yl)-2,5-bis(2-octyldodecyl)-2,5-dihydropyrrolo[3,4-c]pyrrole-1,4-dione ( $\alpha$ -**Br<sub>2</sub>TPDPP).** To a mixture of 3,6-bis(2-bromothieno[2,3-b]pyridin-6-yl)-2,5-dihydropyrrolo[3,4-c]pyrrole-1,4-dione **10** (0.56 g, 1.0 mmol), potassium carbonate (0.42 g, 3.0 mmol), and 18-crown-6 (6 mg) in DMF (20 mL) was added 9-(bromomethyl)nonadecane (1.31 g, 3.0 mmol). The reaction mixture was stirred at 120 °C for overnight and then cooled to room temperature. Chloroform and water were added, and the layers were separated. The organic layer was washed with saturated brine, dried over MgSO<sub>4</sub>, filtered, and then concentrated under vacuum. Column chromatography on silica gel with petroleum ether/ $CH_2Cl_2$  (4:1) as the eluent followed by recrystallization from  $CH_2Cl_2$  and MeOH afforded  $\alpha$ -Br<sub>2</sub>TPDPP as a deep red solid (112 mg, 10% yield). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 9.09 (d, J = 8.5 Hz, 2H), 8.15 (d, J = 8.5 Hz, 2H), 7.42 (s, 2H), 4.41 (d, J = 7.3 Hz, 4H), 1.71–1.61 (m, 2H), 1.36–1.06 (m, 64H), 0.88 (q, J = 6.9 Hz, 12H). MS (MALDI-TOF): m/z calcd for  $C_{60}H_{88}Br_2N_4O_2S_2$  1121.32; found 1121.7 (M + 1).

2,5-Bis(2-ethylhexyl)-3,6-bis(thieno[2,3-b]pyridin-6-yl)-2,5dihydropyrrolo[3,4-c]pyrrole-1,4-dione (2EH-TPDPP). To a mixture of 3,6-bis(thieno[2,3-b]pyridin-6-yl)-2,5-dihydropyrrolo[3,4*c*]pyrrole-1,4-dione 4 (0.8 g, 2.0 mmol), potassium carbonate (0.91 g, 6.6 mmol), and 18-crown-6 (12 mg) in DMF (40 mL) was added 2ethylhexyl bromide (1.2 mL, 6.6 mmol). The reaction mixture was stirred at 120 °C for overnight and then cooled to room temperature. Chloroform and water were added, and the layers were separated. The organic layer was washed with saturated brine, dried over MgSO4, filtered, and then concentrated under vacuum. Column chromatography on silica gel with petroleum ether/CH<sub>2</sub>Cl<sub>2</sub> (3:1) as the eluent to afford 2EH-TPDPP as a deep red solid (0.68 g, 54% yield). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$ : 9.13 (d, J = 8.5 Hz, 2H), 8.29 (d, J = 8.5 Hz, 2H), 7.72 (d, J = 6.0 Hz, 2H), 7.39 (d, J = 6.0 Hz, 2H), 4.56-4.39 (m, 4H), 1.65 (q, J = 6.5 Hz, 2H), 1.45-1.12 (m, 16H), 0.95-0.74 (m, 12H). <sup>13</sup>C NMR (101 MHz, CDCl<sub>3</sub>) δ: 162.78, 160.96, 145.47, 144.39, 133.13, 131.57, 130.16, 123.14, 121.79, 111.72, 46.19, 39.91, 30.66, 28.81, 23.96, 23.16, 14.04, 10.86.

Synthesis of pTPDPP-TF. To a microwave vial was added 3,6bis(2-bromothieno[2,3-b]pyridin-6-yl)-2,5-bis(2-octyldodecyl)-2,5dihydropyrrolo[3,4-*c*]pyrrole-1,4-dione (α-Br<sub>2</sub>TPDPP, 51.5 mg, 0.045 mmol, 1.0 equiv), 2,5-bis(trimethylstannyl)-3,4-difluorothiophene (20.1 mg, 0.045 mmol, 1.0 equiv), P(°Tol)<sub>3</sub> (1.23 mg, 4.05 µmol, 0.09 equiv), and Pd<sub>2</sub>(dba)<sub>3</sub> (0.91 mg, 0.99 µmol, 0.022 equiv). Following further degassing the microwave vial, degassed chlorobenzene (4.5 mL) was added. The microwave vial was sealed, and the reaction mixture was heated at 130 °C for 72 h. After cooling to room temperature, the reaction mixture was poured into vigorously stirring methanol, and the resulting polymeric precipitate was filtered. The polymer was purified by Soxhlet extraction in a sequence of methanol, hexane, ethyl acetate, and finally chloroform. The chloroform fraction was concentrated by rotary evaporation, suspended in methanol, and filtered to afford the polymer pTPDPP-TF as a dark green flake (40 mg, 82%). GPC (chlorobenzene, 80 °C):  $M_n = 24.4 \text{ kDa}$ ,  $M_w = 125.3 \text{ kDa}$ , PDI = 5.1.

#### ASSOCIATED CONTENT

#### **S** Supporting Information

The Supporting Information is available free of charge on the ACS Publications website at DOI: 10.1021/acs.macro-mol.7b00934.

Method and instruments, experimental details for fabrication and characterization of OFET and OSC devices, NMR spectra of intermediates and monomers, DSC curve of the polymer, and crystallographic data (PDF)

### AUTHOR INFORMATION

#### **Corresponding Author**

\*E-mail: h.chen@imperial.ac.uk (H.-Y.C.).

## ORCID <sup>©</sup>

Hung-Yang Chen: 0000-0001-8426-4254 Andrew Wadsworth: 0000-0002-9050-0599 Iain McCulloch: 0000-0002-6340-7217

#### Notes

The authors declare no competing financial interest.

#### ACKNOWLEDGMENTS

The authors thank KAUST for financial support and acknowledge EC FP7 Project SC2 (610115) EC H2020 (643791), and EPSRC Projects EP/G037515/1 and EP/M005143/1. Mingfei Xiao thanks the Cambridge Overseas Trust and Chinese Scholarship Council for PhD funding.

## REFERENCES

(1) Luo, C.; Kyaw, A. K. K.; Perez, L. A.; Patel, S.; Wang, M.; Grimm, B.; Bazan, G. C.; Kramer, E. J.; Heeger, A. J. General Strategy for Self-Assembly of Highly Oriented Nanocrystalline Semiconducting Polymers with High Mobility. *Nano Lett.* **2014**, *14*, 2764–2771.

(2) Tseng, H.-R.; Phan, H.; Luo, C.; Wang, M.; Perez, L. A.; Patel, S. N.; Ying, L.; Kramer, E. J.; Nguyen, T.-Q.; Bazan, G. C.; Heeger, A. J. High-Mobility Field-Effect Transistors Fabricated with Macroscopic Aligned Semiconducting Polymers. *Adv. Mater.* 2014, *26*, 2993–2998.
(3) Zhao, J.; Li, Y.; Yang, G.; Jiang, K.; Lin, H.; Ade, H.; Ma, W. Efficient Organic Solar Cells Processed From Hydrocarbon Solvents. *Nat. Energy* 2016, *1*, 15027.

(4) Yao, H.; Ye, L.; Zhang, H.; Li, S.; Zhang, S.; Hou, J. Molecular Design of Benzodithiophene-Based Organic Photovoltaic Materials. *Chem. Rev.* **2016**, *116*, 7397–7457.

(5) Sun, B.; Hong, W.; Yan, Z.; Aziz, H.; Li, Y. Record High Electron Mobility of 6.3 cm<sup>2</sup>V  $^{-1}s^{-1}$  Achieved for Polymer Semiconductors Using a New Building Block. *Adv. Mater.* **2014**, *26*, 2636–2642.

(6) Bucella, S. G.; Luzio, A.; Gann, E.; Thomsen, L.; McNeill, C.R.; Pace, G.; Perinot, A.; Chen, Z.; Facchetti, A.; Caironi, M. Macroscopic and High-Throughput Printing of Aligned Nanostructured Polymer Semiconductors for MHz Large-Area Electronics. *Nat. Commun.* **2015**, *6*, 8394.

(7) Hwang, Y.-J.; Courtright, B. A. E.; Ferreira, A. S.; Tolbert, S. H.; Jenekhe, S. A. 7.7% Efficient All-Polymer Solar Cells. *Adv. Mater.* **2015**, *27*, 4578–4584.

(8) Li, Z.; Xu, X.; Zhang, W.; Meng, X.; Ma, W.; Yartsev, A.; Inganäs, O.; Andersson, M. R.; Janssen, R. A. J.; Wang, E. High Performance All-Polymer Solar Cells by Synergistic Effects of Fine-Tuned Crystallinity and Solvent Annealing. J. Am. Chem. Soc. 2016, 138, 10935–10944.

(9) Ye, L.; Jiao, X.; Zhao, W.; Zhang, S.; Yao, H.; Li, S.; Ade, H.; Hou, J. Manipulation of Domain Purity and Orientational Ordering in High Performance All-Polymer Solar Cells. *Chem. Mater.* **2016**, *28*, 6178–6185.

(10) Gao, L.; Zhang, Z.-G.; Xue, L.; Min, J.; Zhang, J.; Wei, Z.; Li, Y. All-Polymer Solar Cells Based on Absorption-Complementary Polymer Donor and Acceptor with High Power Conversion Efficiency of 8.27%. *Adv. Mater.* **2016**, *28*, 1884–1890.

(11) Guo, Y.; Li, Y.; Awartani, O.; Han, H.; Zhao, J.; Ade, H.; Yan, H.; Zhao, D. Improved Performance of All-Polymer Solar Cells

Enabled by Naphthodiperylenetetraimide-Based Polymer Acceptor. *Adv. Mater.* **2017**, *29*, 1700309.

(12) Zhan, X.; Tan, Z.; Domercq, B.; An, Z.; Zhang, X.; Barlow, S.; Li, Y.; Zhu, D.; Kippelen, B.; Marder, S. R. A High-Mobility Electron-Transport Polymer with Broad Absorption and Its Use in Field-Effect Transistors and All-Polymer Solar Cells. *J. Am. Chem. Soc.* **2007**, *129*, 7246–7247.

(13) Zhou, E.; Cong, J.; Wei, Q.; Tajima, K.; Yang, C.; Hashimoto, K. All-Polymer Solar Cells From Perylene Diimide Based Copolymers: Material Design and Phase Separation Control. *Angew. Chem., Int. Ed.* **2011**, *50*, 2799–2803.

(14) Zhou, E.; Cong, J.; Hashimoto, K.; Tajima, K. Control of Miscibility and Aggregation via the Material Design and Coating Process for High-Performance Polymer Blend Solar Cells. *Adv. Mater.* **2013**, *25*, 6991–6996.

(15) Zhou, E.; Nakano, M.; Izawa, S.; Cong, J.; Osaka, I.; Takimiya, K.; Tajima, K. All-Polymer Solar Cell with High Near-Infrared Response Based on a Naphthodithiophene Diimide (NDTI) Copolymer. ACS Macro Lett. **2014**, *3*, 872–875.

(16) Yang, J.; Xiao, B.; Tajima, K.; Nakano, M.; Takimiya, K.; Tang, A.; Zhou, E. Comparison Among Perylene Diimide (PDI), Naphthalene Diimide (NDI), and Naphthodithiophene Diimide (NDTI) Based N-Type Polymers for All-Polymer Solar Cells. *Macromolecules* **2017**, *50*, 3179–3185.

(17) Tang, A.; Zhan, C.; Yao, J.; Zhou, E. Design of Diketopyrrolopyrrole (DPP)-Based Small Molecules for Organic-Solar-Cell Applications. *Adv. Mater.* **2017**, *29*, 1600013.

(18) Nielsen, C. B.; Turbiez, M.; McCulloch, I. Recent Advances in the Development of Semiconducting DPP-Containing Polymers for Transistor Applications. *Adv. Mater.* **2013**, *25*, 1859–1880.

(19) Vezie, M. S.; Few, S.; Meager, I.; Pieridou, G.; Dörling, B.; Ashraf, R. S.; Goni, A. R.; Bronstein, H.; McCulloch, I.; Hayes, S. C.; Campoy-Quiles, M.; Nelson, J Exploring the Origin of High Optical Absorption in Conjugated Polymers. *Nat. Mater.* **2016**, *15*, 746–753.

(20) Ashraf, R. S.; Meager, I.; Nikolka, M.; Kirkus, M.; Planells, M.; Schroeder, B. C.; Holliday, S.; Hurhangee, M.; Nielsen, C. B.; Sirringhaus, H.; McCulloch, I. Chalcogenophene Comonomer Comparison in Small Band Gap Diketopyrrolopyrrole-Based Conjugated Polymers for High-Performing Field-Effect Transistors and Organic Solar Cells. J. Am. Chem. Soc. **2015**, *137*, 1314–1321.

(21) Venkateshvaran, D.; Nikolka, M.; Sadhanala, A.; Lemaur, V.; Zelazny, M.; Kepa, M.; Hurhangee, M.; Kronemeijer, A. J.; Pecunia, V.; Nasrallah, I.; Romanov, I.; Broch, K.; McCulloch, I.; Emin, D.; Olivier, Y.; Cornil, J.; Beljonne, D.; Sirringhaus, H. Approaching Disorder-Free Transport in High-Mobility Conjugated Polymers. *Nature* **2014**, *515*, 384–388.

(22) Choi, H.; Ko, S.-J.; Kim, T.; Morin, P.-O.; Walker, B.; Lee, B. H.; Leclerc, M.; Kim, J. Y.; Heeger, A. J. Small-Bandgap Polymer Solar Cells with Unprecedented Short-Circuit Current Density and High Fill Factor. *Adv. Mater.* **2015**, *27*, 3318–3324.

(23) Zhou, E.; Cong, J.; Hashimoto, K.; Tajima, K. Introduction of a Conjugated Side Chain as an Effective Approach to Improving Donor–Acceptor Photovoltaic Polymers. *Energy Environ. Sci.* **2012**, *5*, 9756–9759.

(24) Grzybowski, M.; Gryko, D. T. Diketopyrrolopyrroles: Synthesis, Reactivity, and Optical Properties. *Adv. Opt. Mater.* **2015**, *3*, 280–320.

(25) Bronstein, H.; Chen, Z.; Ashraf, R. S.; Zhang, W.; Du, J.; Durrant, J. R.; Tuladhar, P. S.; Song, K.; Watkins, S. E.; Geerts, Y.; Wienk, M. M.; Janssen, R. A. J.; Anthopoulos, T.; Sirringhaus, H.; Heeney, M; McCulloch, I. Thieno[3,2-b]thiophene-Diketopyrrolopyrrole-Containing Polymers for High-Performance Organic Field-Effect Transistors and Organic Photovoltaic Devices. J. Am. Chem. Soc. 2011, 133, 3272–3275.

(26) Li, Y.; Sonar, P.; Murphy, L.; Hong, W. High Mobility Diketopyrrolopyrrole (DPP)-Based Organic Semiconductor Materials for Organic Thin Film Transistors and Photovoltaics. *Energy Environ. Sci.* **2013**, *6*, 1684–1710.

(27) Sonar, P.; Singh, S. P.; Li, Y.; Soh, M. S.; Dodabalapur, A. A Low-Bandgap Diketopyrrolopyrrole-Benzothiadiazole-Based Copolymer for High-Mobility Ambipolar Organic Thin-Film Transistors. *Adv. Mater.* **2010**, *22*, 5409–5413.

(28) Park, J. H.; Jung, E. H.; Jung, J. W.; Jo, W. H. A Fluorinated Phenylene Unit as a Building Block for High-Performance N-Type Semiconducting Polymer. *Adv. Mater.* **2013**, *25*, 2583–2588.

(29) Yun, H.-J.; Kang, S. J.; Xu, Y.; Kim, S. O.; Kim, Y.-H.; Noh, Y.-Y.; Kwon, S.-K. Dramatic Inversion of Charge Polarity in Diketopyrrolopyrrole-Based Organic Field-Effect Transistors via a Simple Nitrile Group Substitution. *Adv. Mater.* **2014**, *26*, 7300–7307.

(30) Li, W.; Roelofs, W. S. C.; Turbiez, M.; Wienk, M. M.; Janssen, R. A. J. Polymer Solar Cells with Diketopyrrolopyrrole Conjugated Polymers as the Electron Donor and Electron Acceptor. *Adv. Mater.* **2014**, *26*, 3304–3309.

(31) Li, W.; An, Y.; Wienk, M. M.; Janssen, R. A. J. Polymer– Polymer Solar Cells with a Near-Infrared Spectral Response. *J. Mater. Chem. A* 2015, 3, 6756–6760.

(32) Li, Y.; Sonar, P.; Singh, S. P.; Soh, M. S.; van Meurs, M.; Tan, J. Annealing-Free High-Mobility Diketopyrrolopyrrole-Quaterthiophene Copolymer for Solution-Processed Organic Thin Film Transistors. J. Am. Chem. Soc. **2011**, 133, 2198–2204.

(33) Bronstein, H.; Collado-Fregoso, E.; Hadipour, A.; Soon, Y. W.; Huang, Z.; Dimitrov, S. D.; Ashraf, R. S.; Rand, B. P.; Watkins, S. E.; Tuladhar, P. S.; Meager, I.; Durrant, J. R.; McCulloch, I. Thieno[3,2b]thiophene-Diketopyrrolopyrrole Containing Polymers for Inverted Solar Cells Devices with High Short Circuit Currents. *Adv. Funct. Mater.* **2013**, *23*, 5647–5654.

(34) Meager, I.; Ashraf, R. S.; Mollinger, S.; Schroeder, B. C.; Bronstein, H.; Beatrup, D.; Vezie, M. S.; Kirchartz, T.; Salleo, A.; Nelson, J.; McCulloch, I. Photocurrent Enhancement from Diketopyrrolopyrrole Polymer Solar Cells Through Alkyl-Chain Branching Point Manipulation. J. Am. Chem. Soc. 2013, 135, 11537–11540.

(35) Jia, H.; Dai, G.; Weng, J.; Zhang, Z.; Wang, Q.; Zhou, F.; Jiao, L.; Cui, Y.; Ren, Y.; Fan, S.; Zhou, J.; Qing, W.; Gu, Y.; Wang, J.; Sai, Y.; Su, W. Discovery of (S)-1-(1-(Imidazo[1,2-*a*]pyridin-6-yl)ethyl)-6-(1-methyl-1*H*-pyrazol-4-yl)-1*H*-[1,2,3]triazolo[4,5-*b*]pyrazine (Volitinib) as a Highly Potent and Selective Mesenchymal–Epithelial Transition Factor (c-Met) Inhibitor in Clinical Development for Treatment of Cancer. J. Med. Chem. 2014, 57, 7577–7589.

(36) Qi, T.; Guo, Y.; Liu, Y.; Xi, H.; Zhang, H.; Gao, X.; Liu, Y.; Lu, K.; Du, C.; Yu, G.; Zhu, D. Synthesis and Properties of the *anti* and *syn* Isomers of Dibenzothieno[*b*, *d*]Pyrrole. *Chem. Commun.* **2008**, 6227–6229.

(37) Mueller, C. J.; Singh, C. R.; Fried, M.; Huettner, S.; Thelakkat, M. High Bulk Electron Mobility Diketopyrrolopyrrole Copolymers with Perfluorothiophene. *Adv. Funct. Mater.* **2015**, *25*, 2725–2736.

(38) Li, Y.; Sonar, P.; Singh, S. P.; Zeng, W.; Soh, M. S. 3,6-Di(furan-2-yl)Pyrrolo[3,4-c]Pyrrole-1,4(2H,5H)-Dione and Bithiophene Copolymer with Rather Disordered Chain Orientation Showing High Mobility in Organic Thin Film Transistors. *J. Mater. Chem.* **2011**, 21, 10829–10835.

(39) Yue, W.; Nikolka, M.; Xiao, M.; Sadhanala, A.; Nielsen, C. B.; White, A. J. P.; Chen, H.-Y.; Onwubiko, A.; Sirringhaus, H.; McCulloch, I. Azaisoindigo Conjugated Polymers for High Performance N-Type and Ambipolar Thin Film Transistor Applications. *J. Mater. Chem. C* **2016**, *4*, 9704–9710.

(40) Zhang, S.; Ye, L.; Zhao, W.; Liu, D.; Yao, H.; Hou, J. Side Chain Selection for Designing Highly Efficient Photovoltaic Polymers with 2D-Conjugated Structure. *Macromolecules* **2014**, *47*, 4653–4659.

(41) Stoltzfus, D. M.; Donaghey, J. E.; Armin, A.; Shaw, P. E.; Burn, P. L.; Meredith, P. Charge Generation Pathways in Organic Solar Cells: Assessing the Contribution from the Electron Acceptor. *Chem. Rev.* **2016**, *116*, 12920–12955.

(42) Sakamoto, Y.; Komatsu, S.; Suzuki, T. Tetradecafluorosexithiophene: the First Perfluorinated Oligothiophene. *J. Am. Chem. Soc.* **2001**, *123*, 4643–4644.