

Article

Subscriber access provided by UNIV OF CALIFORNIA SAN DIEGO LIBRARIES

Singlet Oxygen-Engaged Selective Photo-oxidation over Pt Nanocrystals/ Porphyrinic MOF: The Roles of Photothermal Effect and Pt Electronic State

Yu-Zhen Chen, Zhiyong U. Wang, Hengwei Wang, Junling Lu, Shu-Hong Yu, and Hai-Long Jiang J. Am. Chem. Soc., Just Accepted Manuscript • DOI: 10.1021/jacs.6b12074 • Publication Date (Web): 20 Jan 2017 Downloaded from http://pubs.acs.org on January 20, 2017

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



Journal of the American Chemical Society is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036 Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

Singlet Oxygen-Engaged Selective Photo-oxidation over Pt Nanocrystals/Porphyrinic MOF: The Roles of Photothermal Effect and Pt Electronic State

Yu-Zhen Chen,[†] Zhiyong U. Wang,[‡] Hengwei Wang,[†] Junling Lu,[†] Shu-Hong Yu,[†] and Hai-Long Jiang^{*,†}

[†]Hefei National Laboratory for Physical Sciences at the Microscale, CAS Key Laboratory of Soft Matter Chemistry, Collaborative Innovation Center of Suzhou Nano Science and Technology, School of Chemistry and Materials Science, University of Science and Technology of China, Hefei, Anhui 230026, P. R. China

[‡]Department of Chemistry and Physics, Troy University, Troy, Alabama 36082, USA

ABSTRACT: The selectivity control toward aldehyde in the aromatic alcohol oxidation remains a grand challenge using molecular oxygen under mild conditions. In this work, we have designed and synthesized Pt/PCN-224(M) composites by integration of Pt nanocrystals and porphyrinic metal-organic frameworks (MOFs), PCN-224(M). The composites exhibit excellent catalytic performance in the photo-oxidation of aromatic alcohols by 1 atm O_2 at ambient temperature, based on synergetic photothermal effect and singlet oxygen production. Additionally, in opposition to the function of Schottky junction, the injection of hot electrons from plasmonic Pt into PCN-224(M) would lower the electron density of Pt surface, which thus is tailorable for the optimized catalytic performance via the competition between Schottky junction and plasmonic effect by altering the light intensity. To the best of our knowledge, this is not only an unprecedented report on singlet oxygen-engaged selective oxidation of aromatic alcohols to aldehydes but also the first report on photothermal effect of MOFs.

INTRODUCTION

Selective oxidation of primary alcohols to aldehydes is an important laboratory and commercial procedure for the production of fine chemicals and intermediates.¹⁻⁸ While the reaction can be traditionally effected with stoichiometric inorganic and organic oxidants, there have been ongoing active efforts to develop new catalytic systems using environmentally benign reagents such as molecular oxygen.9,10 In this regard noble metal nanoparticles (NPs) such as Au NPs supported on metal oxides have been developed as effective catalysts,⁴⁻⁸ although there are still limitations including low selectivity and harsh reaction conditions requiring high temperature or high pressure, organic solvents, strong oxidants or corrosive environment. Molecular oxygen in its ground state exists in triplet state $({}^{3}\Sigma_{g})$, and upon activation it can be turned into two singlet excited states, ${}^{1}\Delta_{g}$ and ${}^{1}\Sigma_{g}$, 95 and 158 kJ/mol above the triplet state, respectively.¹¹ Singlet oxygen (${}^{1}O_{2}$), a mild yet efficient oxidant, has proven to be a versatile reactive oxygen species with applications in multiple organic transformations as well as photodynamic cancer therapy,¹²⁻²¹ but so far it has not been applied to the oxidation of aromatic alcohols.^{22,23} It is assumed that the ${}^{1}O_{2}$ species might be effective in the oxidation of alcohols and its moderate oxidation ability will merit the selectivity to aldehydes against over-oxidation, although this remains unexplored thus far. In this context, the development of efficient photosensitizers and catalysts, which are critical for both ¹O₂ production and the selective alcohol oxidation under mild conditions, is highly desirable.

Various photosensitizers, such as metal NPs, porphyrins and their derivatives, have been reported to effectively generate

 ${}^{1}O_{2}$.²²⁻²⁷ We reason that the integration of the photosensitizers into porous materials, such as metal-organic frameworks (MOFs),²⁸⁻³¹ could result in their synergistic and superior functions. MOFs have captured widespread interests and have found applications in many diverse fields in recent two decades due to their high surface area and great structural tailorability.³²⁻⁵² Recently, porphyrinic MOFs have been reported to be an effective photosensitizer for ${}^{1}O_{2}$ generation and exhibit good catalytic activity for oxidation reactions using ¹O₂ as an oxidant.¹⁶⁻¹⁸ On the other hand, Pt-group metal nanocrystals (NCs) can not only activate O_2 to 1O_2 under light irradiation but also adsorb and activate alcohols in catalytic oxidation of alcohols.^{6,9,26,53,54} Moreover, the photothermal effect converting light into heat has been recently realized on metal NCs based on localized surface plasmon resonance (LSPR) and has been shown to promote the reactivity of metal NCs.⁵⁵⁻⁵⁸ With these facts, Pt NCs could be a promising catalyst for oxidation of alcohols with O₂ under light irradiation. Given that the optimized electronic state of Pt surface, similar to that of Pd,¹³ is critical for O₂ activation and oxidation reaction, for which the formation of heterojunction structure of metal/semiconductor is an effective approach.⁵⁹⁻⁶³ Therefore, the integration of Pt NCs with semiconductor-like porphyrinic MOFs as ¹O₂ generator, could achieve their synergistic effects and provide optimized Pt electronic state and an effective catalytic system for alcohol oxidation.

Based on the aforementioned considerations, we have rationally set out to stabilize Pt NCs by porphyrinic MOFs, namely PCN-224(M) (M represents the metal ion residing in the center of porphyrin ligand),³⁴ to afford composite catalysts, Pt/PCN-224(M). The optimized Pt/PCN-224(Zn) composite combines the advantages of both Pt NCs and PCN-224(Zn), lying in their photothermal effect and ${}^{1}O_{2}$ production ability, and exhibits excellent catalytic activity and selectivity in the oxidation of primary alcohols to aldehydes, via a singlet oxygen-engaged oxidation process by using O₂ under very mild conditions involving visible light irradiation (Scheme 1). To the best of our knowledge, this is the first report on the singlet oxygen-engaged oxidation of aromatic alcohols and also the first finding of photothermal effect by MOFs.

Scheme 1. Schematic illustration showing the singlet oxygen-engaged selective oxidation of alcohols over Pt/PCN-224(M) using molecular oxygen under visible light irradiation



MATERIALS AND METHODS

Materials and equipment. All chemicals were from commercial suppliers without further purification unless otherwise mentioned. Powder X-ray diffraction (XRD) patterns were measured on a Japan Rigaku SmartLabTM rotation anode X-ray diffractometer equipped or Holland X'Pert PRO fixed anode X-ray diffractometer equipped with graphite monochromatized Cu K α radiation ($\lambda = 1.54178$ Å). The UV-Vis absorption spectra were recorded on a UV-Vis spectrophotometer (UV-2700, Shimadzu) in the wavelength range of 200-800 nm. The content (6.3 wt%) of Pt in Pt/PCN-224(Zn) was quantified by an Optima 7300 DV inductively coupled plasma atomic emission spectrometer (ICP-AES). The size, morphology and microstructure of Pt/PCN-224(Zn) were investigated by transmission electron microscopy (TEM) on JEOL-2010 with an electron acceleration energy of 200 kV and a scanning electron microscopy (SEM, Zeiss Supra 40 scanning electron microscope at an acceleration voltage of 5 kV). The X-ray photoelectron spectroscopy (XPS) measurements were conducted by using an ESCALAB 250 high-performance electron spectrometer using monochromated Al K α radiation (hv = 1486.7 eV) as the excitation source. Nitrogen sorption isotherms were measured by an automatic volumetric adsorption equipment (Micromeritics, ASAP 2020). Prior to nitrogen adsorption/desorption measurements, the as-synthesized samples were activated in DMF and acetone, and then dried in vacuum at 60 °C. Following that, the product was dried again by using the "outgas" function for 12 h at 80 °C. Electron spin resonance spectra (ESR) were recorded on JES-FA200 electron paramagnetic resonance spectrometer under visible-light irradiation ($\lambda > 400$ nm). Catalytic oxidation reaction products were analyzed and identified by gas chromatography (GC, Shimadzu 2010 Plus with a 0.25 mm \times 30 m Rtx \mathbb{R} -5 capillary column). GC-MS analysis was performed on an Agilent Technologies 7890B GC System equipped with an Agilent Technologies 5977B MSD Mass Spectrometer. The metal dispersion was measured by CO chemisorption using a fully automated chemisorption analyzer (Micromeritics, Autochem II 2920) at 323 K. Prior to CO titration, the catalysts were treated at 423 K for 60 min under a hydrogen gas flow and then cooled to 323 K under a helium gas atmosphere. The metal dispersion was calculated assuming a stoichiometry of one CO molecule per surface metal atom.

Preparation of ligand. The tetrakis(4-carboxyphenyl)porphy-rin (TCPP) and other metal-involved TCPP (M-TCPP) ligands were synthesized based on previous reports with minor modifications.³⁴

Preparation of PCN-224(M) (M: Zn, Ni, Co, Mn and 2H). PCN-224(M) were prepared based on the reported procedure with minor modifications.³⁴ For PCN-224(M) (M: Zn, Co, and 2H): typically, ZrCl₄ (120 mg), Zn-TCPP or Co-TCPP or H₂TCPP (40 mg), benzoic acid (1.2 g) and 0.5 mL of acetic acid in 7.5 mL of DMF were ultrasonically dissolved in a 20 mL Teflon-lined autoclave and heated in 120 °C oven for 24 h. For PCN-224(Ni): ZrCl₄ (40 mg), Ni-TCPP (40 mg), benzoic acid (1.0 g) and 0.5 mL of acetic acid in 7.5 mL of DMF were ultrasonically dissolved in a 20 mL Teflon-lined autoclave and heated in 120 °C oven for 24 h. For PCN-224(Mn): ZrCl₄ (40 mg), Mn-TCPP (40 mg), benzoic acid (1.8 g) and 0.5 mL of acetic acid in 7.5 mL of DMF were ultrasonically dissolved in a 20 mL Teflon-lined autoclave and heated in 120 °C oven for 24 h. For all samples, dark brown crystals were harvested by filtration and washing.

Preparation of ZIF-8. The synthesis of ZIF-8 powder was based on a previous procedure with some modifications.⁶⁴ Typically, $Zn(NO_3)_2$ · $6H_2O$ (1.68 g) was dissolved in 80 mL of methanol, followed by a mixture of 2-methylimidazole (3.70 g) with 80 mL of methanol was added into above solution with vigorous stirring for 24 h. The white product was separated by centrifugation and washed thoroughly with methanol, and finally dried for 12 h at 50 °C. The ZIF-8 powder was further activated at 200 °C under vacuum prior to use.

Preparation of branched Pt nanocrystals (~10 nm). The branched Pt nanocrystals (NCs) in good dispersion were prepared according to reported procedure with modifications.65 Typically, a volume of 2.5 mL of ethylene glycol (EG) was preheated at 120 °C for 10 min. Then, 94 µL of 0.375 M polyvinylpyrrolidone (PVP, M.W. = 55,000) and 47 μ L of 0.0625 M H₂PtCl₆·6H₂O aqueous solution was added to the EG every 30 s interval over a 16 min period with constant vigorous stirring (total volumes for PVP and H2PtCl6·6H2O solutions are 3 mL and 1.5 mL, respectively). The resulting mixture was kept at 120 °C for an additional 10 min and then cooled down to room temperature. The product was centrifuged at 14,000 rpm for 5 min and washed thoroughly with water for several times to remove excess PVP. The precipitate was collected and redispersed in water to obtain an aqueous solution of Pt NCs (2 mg/mL) with size of ~ 10 nm.

Preparation of Pt/PCN-224(M) and Pt/ZIF-8 composites. The Pt/PCN-224(M) or Pt/ZIF-8 composites were prepared by introducing as-synthesized MOF into the synthetic system of Pt NCs (0.0256 mmol). Typically, the mixture of PCN-224(M) or ZIF-8 (50 mg) in ethylene glycol (EG, 2.5 mL) was ultrasonically dispersed, and then preheated at 120 °C for 10 min. Following that, 94 μ L of 0.375 M polyvinylpyrrolidone (PVP, M.W. = 55,000) and 47 μ L of 17 mM H₂PtCl₆·6H₂O aqueous solution was added to the EG every 30 s interval over a 16min period with constant vigorous stirring (total volumes for PVP and H₂PtCl₆·6H₂O solutions are 3 mL and 1.5 mL, respectively). The resulting mixture was kept at 120 °C for an additional 10 min and then cooled down to room temperature. The obtained product was collected by centrifugation, and washed thoroughly several times with water and ethanol. The synthesized sample was further dried overnight at 323 K under dynamic vacuum for further use. The PVP concentration was changed to 1.125 M for synthesis of ~2.5 nm Pt NCs and no PVP was added for ~14 nm Pt NCs, while other parameters were fixed.

Preparation of Pd octahedron nanocrystals (~15 nm). The Pd octahedron nanocrystals were prepared according to reported procedure.⁶⁶ Typically, 0.105 g of PVP, 0.060 g of citric acid and 0.060 g of L-ascorbic acid were dissolved in 8 mL of deionized water in a 3-neck flask. The mixture was heated in air at 120 °C for 5 min. The Pd stock solution (0.065 g K₂PdCl₄ in 3 mL of deionized water) was then added dropwise into the flask within 30 min. The reaction was kept at 120 °C in air for 3 h. The precipitate was washed with acetone and then with ethanol thoroughly to remove the PVP and other molecules by centrifugation.

Photocurrent measurement. Photocurrent measurements were performed on a work station (Chenhua Instrument, Shanghai, China) in a standard three-electrode system with the photocatalyst-coated FTO as the working electrode, Pt plate as the counter electrode, and Ag/AgCl as the reference electrode. A 300 W Xenon lamp with a visible light cut-off filter (> 400 nm) was used as the light source. A 0.2 M Na₂SO₄ electrolyte was bubbled with nitrogen for 20 min before the measurements. The as-synthesized Pt NCs, PCN-224(Zn), and Pt/PCN-224(Zn) composite (5 mg) were added into 2 µL Nafion and 1 mL ethanol mixed solution, and the working electrodes were prepared by dropping the suspension (100 µL) onto the surface of a FTO plate. The working electrodes were dried at room temperature, and the photoresponsive signals of the samples were measured under chopped light at 0.6 V.

Mott-Schottky plot measurement. Mott-Schottky plots of PCN-224(Zn) were measured on a electrochemical work-station (Zahner Zennium) in a standard three-electrode system with the photocatalyst-coated electrode as the working electrode, Pt plate as the counter electrode, and Ag/AgCl as the reference electrode at frequencies of 1000, 1500, and 2000 Hz, respectively. A 0.5 M Na₂SO₄ solution deoxygenated using N₂ stream was used as the electrolyte. The preparation procedure of working electrode is similar to that for the photocurrent measurement described above.

3,3',5,5'-tetramethylbenzidine (TMB) oxidation. TMB (5 mg) was mixed with 3 mL of HAc/NaAc buffer solution (0.2 M : 0.2 M) and 1 mL of H₂O. Then, an aqueous suspension of 100 μ L of PCN-224(Zn) (3.2 mg/mL), or 10 μ L of Pt nanocrystals (2 mg/mL), or 100 μ L of Pt/PCN-224(Zn) (3.2 mg/mL), was added into the reaction mixture with O₂ bubbling at 20 °C under visible light irradiation. The concentration of Pt NCs was kept the same as that in Pt/PCN-224(Zn). The samples were taken at different time intervals for UV-Vis measurements. The measurements were also performed under other gas environments (N₂ and air). To verify the type of active oxygen species, different scavenger molecules were added into the solution prior to the UV-Vis measurements: (1) carotene (10 mg); (2) mannite (2 mg); (3) catalase (200 unit/mL, 2 mg);

(4) superoxide dismutase (SOD, 1350 unit/mL, 500 μ L), respectively.

The 2,2,6,6-tetramethyl-4-piperidone hydrochloride (4oxo-TMP) oxidation and ESR analysis. A 10 μ L aqueous suspension of PCN-224(Zn) (3.2 mg/mL) or 1 μ L aqueous suspension of Pt nanocrystals (2 mg/mL) or 10 μ L aqueous suspension of Pt/PCN-224(Zn) (3.2 mg/mL) was mixed with 500 μ L of 4-oxo-TMP solution (50 mM). The measurements were conducted at room temperature under incident light irradiation with USHIO Optical Modulex SX-U1501XQ (500 W, $\lambda > 400$ nm) or in dark.

Confirmation experiments for singlet oxygen production. Some classical probe molecules, such as 1,3diphenylisobenzofuran (DPBF),¹⁶ 9,10-dimethylanthracene (DMA),⁶⁷ singlet oxygen sensor green (SOSG, Molecular Probe)⁶⁸ and terpene hydrocarbons (α -terpinene),⁶⁹ have been used to detect singlet oxygen. The test based on DPBF was carried out using a visible light source at room temperature. Typically, 10 mg of DPBF was dissolved in 4 mL of DMF with 10 μ L aqueous suspension of PCN-224(Zn) (3.2 mg/mL). The stock solutions of fluorescent DMA or SOSG were prepared by dissolving 6 mg of DMA in 6 mL of dimethyl formamide or 100 μ g of SOSG in 1 mL of methanol. Then 2 μ L of the sensor solution was mixed with 3 mL of D₂O with or without 10 μ L of aqueous suspension of PCN-224(Zn) (3.2 mg/mL).

The 5,5-dimethyl-1-pyrroline *N*-oxide (DMPO) ring opening reaction and corresponding ESR analysis. A 10 μ L aqueous suspension of Pt/PCN-224(Zn) (3.2 mg/mL) was mixed with 0.5 mL of water. Then 20 μ L of DMPO was added into the solution. The measurements were conducted at room temperature under incident light irradiation with USHIO Optical Modulex SX-U1501XQ (500 W, $\lambda > 400$ nm).

Alcohol oxidation reactions conducted at ambient temperature. In general, a mixture of 1.25 mg of Pt NCs or 20 mg of 6.3 wt% Pt/PCN-224(Zn) (determined by ICP analysis) or PCN-224(M), 20 µmol of alcohol compounds (or toluene) and 10 mL water was placed in a three-neck flask (25 mL). The catalytic oxidation reaction was initiated at ambient temperature (~16 $^{\circ}$ C) with 1 atm O₂ under visible light irradiation with a 300W Xe lamp ($\lambda > 400$ nm, PLS-SXE300, Beijing Philae Technology Co., LTD, China). The solution temperature of the reaction system was monitored throughout the reaction. After the reaction, the catalyst was separated by centrifugation, thoroughly washed with water and ethanol, and then reused in subsequent runs. The yield of the product was analyzed by GC with *n*-dodecane as the internal standard. For comparison, 20 mg of Pt/ZIF-8 as a catalyst was examined for the reaction while all other reaction parameters and processes were kept the same. For the testing of oxidation ability of H₂O₂ for benzyl alcohol, 1.25 mg of Pt NCs, 1 mL of H₂O₂, 9 mL of H₂O and 20 µmol of benzyl alcohol was mixed in the absence of light irradiation.

Alcohol oxidation reactions conducted at a fixed temperature (T = 16 °C). In general, a mixture of 20 mg of 6.3 wt% Pt/PCN-224(M) or PCN-224(M), 20 µmol alcohol and 10 mL water was placed in a photo-catalytic reactor. The temperature of mixture solution was fixed at 16 °C by flowing condensate water. The catalytic oxidation reaction was carried out in the presence of 1 atm O₂ under visible light irradiation with a 300W Xe lamp ($\lambda > 400$ nm). The yield of the product was analyzed by GC with *n*-dodecane as the internal standard. Alcohol oxidation reaction over Pd octahedron nanocrystals. In general, a mixture of 2.5 mg of Pd octahedra, 20 μ mol of benzyl alcohol and 10 mL of water was placed in a three-neck flask (25 mL). The catalytic oxidation reaction was initiated at 80 °C with 1 atm O₂ in the absence of visible light irradiation.

RESULTS AND DISCUSSION

A series of chemically stable PCN-224(M) (M = Zn, Ni, Co, Mn, 2H) were obtained via solvothermal reactions at 120 °C according to previous procedure (Figure S1).³⁴ Their structures contain both channels and cages with sizes as large as ~19 Å (Figure S2). N₂ sorption experiment on the representative PCN-224(Zn) indicates high porosity and a large BET surface area of 2018 m²/g (Figure S3). UV-Vis spectrum of PCN-224(Zn) shows strong adsorption in the range of 300-800 nm (Figure 1a), revealing the photon absorption and electron-hole separation ability upon visible-light irradiation. The positive slopes of Mott-Schottky plots for PCN-224(Zn) at frequencies of 1000, 1500 and 2000 Hz are consistent with the behavior of a typical *n*-type semiconductor (Figure 1b). The flat band position (LUMO) determined from the intersection is ~ -0.80 V vs Ag/AgCl or -0.58 V vs normal hydrogen electrode (NHE). The valence band (HOMO) is then calculated to be 1.25 V vs NHE, considering that the band gap energy of PCN-224(Zn) is estimated to be 1.83 V from Tauc plot (Figure S4).



Figure 1. (a) UV-VIS spectra of PCN-224(Zn), Pt NCS and Pt/PCN-224(Zn). (b) Mott-Schottky plots for PCN-224(Zn) in 0.2 M Na₂SO₄ aqueous solution (pH 6.8); inset: the energy diagram of the HOMO and LUMO levels of PCN-224(Zn). (c) TEM and HRTEM (inset) images for Pt NCs. (d) TEM and enlarged TEM images for Pt/PCN-224(Zn).

Pt NCs were obtained by reacting H₂PtCl₆·6H₂O in ethylene glycol (EG)/H₂O in the presence of polyvinylpyrrolidone (PVP) at 120 °C for 10 min.⁶⁵ Transmission electron microscopy (TEM) and high-resolution TEM (HRTEM) images clearly show the branched Pt NCs in tripod or tetrapod shape with good dispersion, uniform size (~10 nm), and great crystallinity (Figure 1c and S5a). The broad adsorption of Pt NCs in UV-Vis spectrum indicates the SPR property (Figure 1a). The Pt/PCN-224(M) composite was assembled by pre-addition of PCN-224(M) into the synthetic system of Pt NCs. The crystallinity and structure of PCN-224(M) are well maintained upon combination with Pt NCs (Figure S1). The slight decrease of surface area in reference to parent PCN-224(Zn) is ascribed to the mass occupation of Pt NCs (Figure S3). Scanning electron microscopy (SEM) image shows that PCN-224(Zn) has uniform size (~800 nm) and is mostly in octahedral shape (Figure S5b), and Pt NCs are uniformly dispersed on the surface of PCN-224(Zn) in the composite (Figure 1d and S5c,d).

The O₂ activation is a key step in the O₂-involved oxidation reactions. To examine the ability of Pt/PCN-224(M) composites for O₂ activation, TMB was employed as the initial model compound to undergo oxidation over Pt/PCN-224(Zn) as a representative. Upon oxidation by different active oxygen species, the colorless TMB was changed to two colored products with characteristic UV-Vis peaks at 370 and 652 nm (partially oxidized product I, blue), as well as 450 nm (fully oxidized product II, yellow), respectively (Figure S6).⁷⁰ Interestingly, TMB molecules were mainly oxidized into partially oxidized intermediate by Pt NCs, PCN-224(Zn), and Pt/PCN-224(Zn) composite (Figure S6), revealing their moderate oxidation power, which is essential for selective oxidation of primary alcohols into aldehydes but not carboxylic acids. This result prompted us to compare the oxidation of benzyl alcohol with O₂ by Pt/PCN-224(Zn) versus KMnO₄. While excellent selectivity for benzaldehyde was achieved with Pt/PCN-224(Zn), the stronger oxidant KMnO₄ gave benzoic acid as a main product (Figure S7).



Figure 2. UV-Vis peak intensity for the TMB oxidation product vs reaction time (a) over Pt/PCN-224(Zn) in various gas environments, (b) over Pt/PCN-224(Zn) in the presence of different scavengers, and (d) over different catalysts in bubbled O_2 . (c) ESR spectra of the samples after mixing 4-oxo-TMP solution with PCN-224(Zn), Pt NCs, Pt/PCN-224(Zn) in the absence or presence of carotene under visible light irradiation or in dark. A curve for the 4-oxo-TMP solution was collected as the reference.

The dramatically different oxidation rates for TMB in various gas environments (N₂, O₂ and air) suggest that active oxidative species is indeed evolved from O₂ (Figure 2a and S8). To clarify which active oxygen species is actually generated in our system, various scavengers including carotene, mannite, catalase, and superoxide dismutase (SOD) were introduced into reaction system to specifically inhibit the generation of ${}^{1}O_{2}$, •OH, H₂O₂, and O₂^{•-}, respectively.⁷¹ As shown in Figure 2b, only carotene significantly suppresses the oxidation of TMB, indicating that the main active species generated by Pt/PCN-224(Zn) composite is ${}^{1}O_{2}$. The fact that oxidation is not completely inhibited by carotene suggests that some minor oxidation pathways other than ${}^{1}O_{2}$ oxidation might be also in effect. Furthermore, 4-oxo-TMP, a well-known probe molecule for ${}^{1}O_{2}$ due to its ability to trap ${}^{1}O_{2}$ to afford the stable

а

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59 60 nitroxide radical 4-oxo-TEMPO, further confirms the ¹O₂ generation through electron spin resonance (ESR) measurement. ESR spectra display 1:1:1 triplet with a g-value of 2.030 characteristic signals of 4-oxo-TEMPO for all the samples (Figure 2c),⁷² demonstrating the formation of ${}^{1}O_{2}$ or at least a species that displays chemical properties of ¹O₂. Amongst Pt/PCN-224(Zn), its two components, and the simple physical mixture of two components, Pt/PCN-224(Zn) exhibits the strongest UV absorbance for TMB oxidation product (Figure 2d) and the strongest signals of 4-oxo-TEMPO (Figure 2c), confirming the synergy between Pt NCs and the MOF for ${}^{1}O_{2}$ production.^{16,26} The signals are almost completely quenched by carotene or in the dark, again manifesting that they are originated from ${}^{1}O_{2}$ indeed and light is necessary for ${}^{1}O_{2}$ generation. To further confirm the generation of ¹O₂ based on Pt/PCN-224(Zn) by light irradiation, a variety of classical ${}^{1}O_{2}$ probe molecules including DPBF, DMA, and SOSG, have been examined. All obtained results corroborate each other and reveal that active ¹O₂ species is indeed formed in our reaction system (Figure S9-11).

Since oxidative species other than ¹O₂ could be responsible for our observed reactions, we checked whether any of them is formed in significant amount. The radical trapping agent DMPO is particularly useful for identifying O₂⁻⁻ and •OH. The ESR spectra display a 1:1:1 triplet signal consistent with $DMPO/^{1}O_{2}$. Neither 1:1:1:1 quartet signal from $DMPO/^{\bullet}O_{2}H$ nor 1:2:2:1 quartet signal from DMPO/•OH was detected (Figure S12), disqualifying radicals as responsible oxidants in our reaction system.⁷³ α -Terpinene is an excellent probe compound for our system because it will be converted to ascaridole with ${}^{1}O_{2}$ but to other aromatic products with O_{2} and •OOH.⁶⁹ Ascaridole was detected as the nearly exclusive product after 4 h in our reaction conditions, again corroborating ${}^{1}O_{2}$ engagement (Figure S13). Our proposed mechanism is consistent with the generation of ¹O₂ but inhibited conversion of O₂ to O₂⁻ based on PCN-224(Zn) upon light irradiation (Scheme S1).

With the above information in hands, we are in a position to investigate the photo-oxidation of aromatic alcohols by O₂ over Pt/PCN-224(M) or related catalysts under visible light irradiation. The reaction has been conducted with benzyl alcohol in water with 1 atm O_2 at ambient temperature (16 °C). The data for catalytic oxidation of benzyl alcohol in Table 1 indicates that Pt/PCN-224(Zn) exhibits the highest catalytic activity among all catalysts with 100% selectivity for aldehyde production and the reaction is complete in 50 min (entry 1). The reaction does not produce benzoic acid even it is extended to longer reaction time, manifesting the superb selectivity of catalyst (entry 1). Based on the 3.4% of accessible Pt sites from a CO titration experiment (Figure S14), the turnover frequency (TOF) is calculated to be as high as 269 h⁻¹. Under identical conditions, only 56% of benzyl alcohol is oxidized over Pt NCs after 60 min, and negligible activity can be detected with PCN-224(Zn) (entries 2, 3), suggesting that alcohols can be activated on the Pt surface while the MOF has no such ability.⁹ The mere 62% yield for the physical mixture of Pt NCs and PCN-224(Zn) (entry 4), significantly lower than that of the composite, should be ascribed to the absence of interaction between separated Pt NCs and the MOF.

An unusual photothermal effect has been observed for the reaction. Upon visible light irradiation for 30 min, the reaction temperature spontaneously increases from 16 °C to 26 °C for

both Pt NCs and PCN-224(M), and 36 °C for Pt/PCN-224(Zn), evidently higher than the resulting temperature (18 °C) of the reaction system in the absence of catalyst or the presence of ZIF-8 (Table S1). Both Pt NCs and PCN-224(M) obviously have photothemal effect, which is synergistically enhanced in Pt/PCN-224(M). We propose that visible light-responsive porphyrin unit in PCN-224(M) is responsible for converting the light to heat, as other non-porphyrin based MOFs like ZIF-8 cannot. To the best of our knowledge, neither the photothermal effect of MOFs nor the synergistic photothermy between Pt NCs and MOFs has been reported previously.

Table 1. Oxidation of benzyl alcohol by O_2 over different catalysts under visible light irradiation started from ambient temperature $(16 \ ^{\circ}C)^{a}$

Entry	Catalyst	Time	T (⁰ C)	Yield ^b
		(min)	I (°C)	(%)
1	Pt/PCN-224(Zn)	30	34	84
		50	36	>99
		12 h	36	>99
2	Pt NCs	30	26	39
		60	28	56
2	PCN-224(Zn)	30	26	5
3		60	28	5
4	Pt + PCN-224(Zn)	30	28	37
4		60	28	62
۶¢	Pt/PCN-224(Zn)	30	16	52
2		60	16	86
(Pt/PCN-224(Ni)	30	27	59
0		60	27	97
7	Pt/PCN-224(Co)	30	30	52
/		60	28	83
0	Pt/PCN-224(Mn)	30	28	61
8		60	28	81
0	Pt/PCN-224 -	30	30	41
9		60	30	62
10	Pt/ZIF-8	60	26	52
11	Pt/PCN-224(Zn)	30	16-35 ^d	35
12 ^e	Pd NCs	60	80	>99
$13^{\rm f}$	Pt NCs	120	25	23
14	Pt/PCN-224(Zn)	30	34	15
14	+ carotene	60	36	31
15 ^g	Pt/PCN-224(Zn)	12 h	38	>99

^aReaction conditions: catalyst (20 mg, 6.3 µmol Pt), alcohol (20 µmol), 10 mL H₂O, visible light ($\lambda > 400$ nm, 100 mW/cm²), O₂ (1 atm). ^bYield of aldehyde was analyzed by GC, and *n*-dodecane was used as the internal standard. ^cAt a fixed reaction temperature of 16 °C. ^dThe reaction was from 16 to 35 °C within 30 min by external heating in the absence of light irradiation, with the heating speed similar to that by photothermal effect. ^ePd NCs (2.5 mg), 80 °C, in the absence of light. ^fH₂O₂ (1 mL), H₂O (9 mL), alcohol (20 µmol), without O₂ bubbling and visible light irradiation. ^galcohol (1 mmol), catalyst (31.5 µmol Pt).

The synergistic photothemal conversion of Pt/PCN-224(Zn) is an important finding as photo-induced heat is highly desirable for endothermal reactions. When the reaction temperature was fixed at 16 °C to eliminate photo-induced heat, only 52% and 86% yields can be obtained for Pt/PCN-224(Zn) after 30 min and 60 min, respectively (Table 1, entry 5 and Figure 3). Pt/ZIF-8 gave a similar activity to Pt NCs (entries 2, 10),

mainly because of that ZIF-8 cannot convert light into heat. It is noteworthy that the catalytic activities of Pt/PCN-224(M) composites increase with more d electrons of central metals (no metal, Mn, Co, Ni, Zn) in the porphyrin (entries 1, 6-9). To exclude the influence of photothermal effect, reactions with different catalysts were conducted under identical conditions at a fixed temperature (16 °C), and the same activity order was observed (Table S2). It is assumed that the d electron number of the metal centered in metalloporphyrin in MOFs influences the triplet states of porphyrin, which play important roles in both the activation ability of triplet O₂ (Scheme S2) and possibly the energy transfer between MOF and Pt,^{19,22} reasonably explaining the distinct activity in Pt/PCN-224(M).



Figure 3. The oxidation yield of benzyl alcohol *vs* reaction time over Pt/PCN-224(Zn) in the presence or absence of light irradiation or external heating, while other reaction parameters being kept unchanged.

To assess the importance of light, the catalytic oxidation over Pt/PCN-224(Zn) was carried out with all parameters unaltered except changing light irradiation to heating, in which the yield was only 35% after 30 min, far below that under visible light irradiation (entry 11 and Figure 3).

While all experimental evidences point to the conclusion that ${}^{1}O_{2}$ or some other species from it is responsible for our observed alcohol oxidation, which was rarely reported.13,22,23 Pd octahedron nanocrystals was reported to generate ¹O₂ solely and oxidize glucose.¹³ We synthesized Pd NCs according to literature procedures and applied it to benzyl alcohol oxidation (Figure S15). The reaction achieved complete conversion to benzaldehyde after 1 h at 80 °C in water (entry 12). More importantly, when the reaction was performed at ambient temperature, 35% conversion to benzaldehyde was achieved after 12 h (data not shown). This is clear that ${}^{1}O_{2}$ is engaging the selective oxidation of alcohol to aldehyde, albeit in low efficiency with Pd NCs. Moreover, ESR analysis of the radical trapping agent DMPO excludes the formation of the radicals (e.g., O2[•] and •OH), as indicated above (Figure S12). Another possible oxidant that could be formed in our reaction system is hydrogen peroxide. However, the direct introduction of H_2O_2 into the benzyl oxidation reaction to replace ¹O₂ results in much lower activity, indicating that H₂O₂ is not the responsible oxidant in our reaction system (entry 13). To further exclude the formation of other reactive oxygen species (ROS) and/or the conversion of ${}^{1}O_{2}$ into other ROS in the reaction system, four specific scavengers that exclusively inhibit the generation of ¹O₂, •OH, H₂O₂, and O₂⁻ species, respectively, were introduced into the reaction system in varying amounts. While the reaction yield quickly decreased with increasing amount of the ${}^{1}O_{2}$ quencher carotene (only 31% yield was obtained even after 60 min by adding 20 mg of ¹O₂ quencher;

entry 14), it showed no response to varying amounts of other quenchers even at over two orders of magnitude of theoretically consumed amount (Figure S17). These results unambiguously rule out the other three types of ROS and demonstrate the involvement of ${}^{1}O_{2}$ from O₂ activation by Pt/PCN-224(M) in the reaction of benzyl alcohol. The above multiple evidence collectively supports that ¹O₂ is indeed generated (see SI, Section 4) and is truly engaged and responsible in our benzyl alcohol oxidation system. We have proposed a tentative reaction pathway (Scheme S3). However, the exact mechanism, including the specific roles played by ${}^{1}O_{2}$ to boost the reaction, remains to be clarified by more experiments and/or theoretical calculations. Since ${}^{1}O_{2}$ alone is inefficient at oxidizing benzyl alcohol, we propose that visible light, photothermal effect, $^{1}O_{2}$, and the diamagnetism of metal ion residing in porphyrin center synergistically contribute to the excellent activity and selectivity in the oxidation of benzyl alcohol to benzaldehyde using O₂ over the Pt/PCN-224(M) composite.

In consideration of the potential for practical applications, the reaction with increased amount of substrate was also conducted (entry 15). With 1 mmol (~0.10 g) of alcohol the reaction took longer time (12 h) to finish, but it is remarkable that exclusive and quantitative formation of benzaldehyde is still achieved without external heat input. Noteworthily, in addition to the representative Pt/PCN-224(Zn) with ~9 nm Pt NCs described above, the Pt/PCN-224(Zn) with Pt NCs of ~3 and ~14 nm have been synthesized (Figure S16) and they also present 100% selectivity toward benzaldehyde, though lower activity compared to that with ~9 nm Pt NCs, in the oxidation of benzyl alcohol under identical reaction conditions (Table S3).



Figure 4. The oxidation yield of benzyl alcohol over Pt/PCN-224(Zn) at different light intensities under visible light irradiation at (a) spontaneous reaction temperatures, and (b) a fixed reaction temperature ($16 \,^{\circ}$ C).

To further understand the role of visible light and the interaction between Pt and PCN-224(M), the catalytic performance of Pt/PCN-224(Zn) as a representative has been investigated for benzyl alcohol oxidation under varying light intensities (60~140 mW/cm², $\lambda > 400$ nm). The reaction yields increase with enhanced light intensity from 60 to 100 mW/cm², and then decrease when the light intensity is further increased (Figure 4a). The positive relationship between reaction yields and light intensity at the range of 60-100 mW/cm² can be explained by photothermal effect, as stronger light intensity leads to a higher reaction temperature which is favorable for the endothermic process (Figure S18 and Table S4). The drop of reaction yield after the light intensity further increases beyond 100 mW/cm², however, indicate that other factors also control the reaction. Reactions were thus conducted at a constant temperature (16 °C) to exclude photothermal effect, and similar correlation between reaction yield and light intensity was observed (Figure 4b). The results imply the presence of electron transfer between Pt NCs and PCN-224(Zn) under 1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59 60

light irradiation and thus the electron density of Pt surface changes along with light intensity. It has been reported that O₂ activation and oxidation reaction are positively correlated with the electron density on the surface of Pd-group metals.¹³ Meanwhile, the modulation of the charge state of active metal surface has been well documented in the noble metal/semiconductor (M-S) hybrid configuration based on the electron transfer via Schottky junction and/or plasmonic effect.⁵⁹⁻⁶³ In our system, both Pt NCs and PCN-224(Zn) are able to accept photons of visible light and can be excited to produce photoelectrons. Upon visible light irradiation with relatively low intensity (<100 mW/cm²), PCN-224(Zn) is readily photoexcited and electron-hole pairs are separated. The electrons on the conductive band (LUMO) of PCN-224(Zn), with the behavior of an *n*-type semiconductor, flow to the Fermi level of Pt, promoted by the presence of Schottky junction. Higher light intensity would induce the delivery of more electrons to the Pt surface, making it more electron-rich, which is beneficial to the activation of O_2 to 1O_2 and thus improves the catalytic activity. When the light intensity further increases $(>100 \text{ mW/cm}^2)$, the hot electrons of Pt NCs can be generated by the excitation of surface plasmons (plasmonic effect), which is more competitive than Schottky junction for electron transfer between Pt NCs and PCN-224(Zn). As a result, the electrons from Pt NCs are injected into the conductive band (LUMO) of PCN-224(Zn), producing the electron-deficient surface of Pt sites, which is disadvantageous to ¹O₂ generation and lowers catalytic activity. The above results indicate that the electronic density of Pt surface can be flexibly regulated by adjusting light intensity, which holds the key to modulation of ${}^{1}O_{2}$ generation and the catalytic activity of alcohol oxidation (Scheme S4).

Scheme 2. Proposed mechanism for the ${}^{1}O_{2}$ generation and electron transfer between Pt and PCN-224(M) in the oxidation of benzyl alcohol over Pt/PCN-224(M) under visible light irradiation. VB, valence band; CB, conduction band; E_f represents the Fermi level of PCN-224(M) or Pt NCs; E_f' represents the Fermi level of Pt/PCN-224(M) composite



This electron transfer between Pt NCs and PCN-224(Zn) was further studied by transient photocurrent measurement for PCN-224(Zn), Pt NCs and Pt/PCN-224(Zn) (Figure S19). While the current density of separate PCN-224(Zn) or Pt NCs stays positively correlated with light intensity from 60 to 120 mW/cm², the current density of Pt/PCN-224(Zn) composite initially increases with increasing light intensity up to 100 mW/cm² then subsequently decreases when light intensity is further increased. The results corroborate with the trend observed for reaction yield *vs* light intensity and indicate improved charge separation in Pt/PCN-224(Zn) driven by the Schottky barrier at relatively low light intensity (<100 mW/cm²) and the reverse injection of energetic hot electrons

from the plasmonic Pt NCs to reach the M-S interface and enter the LUMO of PCN-224(Zn) at high light intensity (>100 mW/cm²). The flow of electrons in Pt/PCN-224(Zn) composite at different light intensities is well consistent with the catalytic results and the mechanism is illustrated in Scheme 2.

The recycling stability of a heterogeneous catalyst is of great importance for its practical application. Delightedly, the catalytic activity of Pt/PCN-224(Zn) is well retained even after six runs of benzyl alcohol oxidation without any treatment or activation (Figure 5a). No significant loss of crystallinity for PCN-224(Zn) was observed from the PXRD patterns (Figure S21) and aggregation of Pt NCs does not occur from TEM image after reaction (Figure S5b), suggesting excellent recyclability and stability of Pt/PCN-224(Zn). XPS measurements show that the binding energies of Pt 4f_{5/2} and 4f_{7/2} remain well before and after reaction, indicating the unchanged oxidation state of Pt during the reaction and excellent stability of Pt/PCN-224(Zn) (Figure S22).



Figure 5. (a) Recyclability of Pt/PCN-224(Zn) in the oxidation of benzyl alcohol. (b) TEM image of Pt/PCN-224(Zn) after catalytic reaction.

Encouraged by the excellent catalytic performance of Pt/PCN-224(Zn) in the oxidation of benzyl alcohol, we proceeded to investigate the scope of this reaction. Diverse substituted benzyl alcohols and heteroaromatic alcohols were completely oxidized with varying reaction time, but quantitative conversion as well as complete selectivity for aldehyde over carboxylic acid or other oxidizing products was obtained in each case (Table 2). The reactions were completed within 60 min with benzyl alcohol (entry 1) and its substitutions with electron-withdrawing groups (-NO₂, -Cl, -Br) (entries 2-4), while it requires at least 120 min for those bearing electrondonating groups (-CH₃, -NH₂) or furfuryl alcohol (entries 5-7). The 4-methoxybenzyl alcohol is an abnormality here (entry 8). Despite the presence of the electron-donating methoxy group, the reaction rate is not slowed down as compared to benzyl alcohol (entry 1). In addition to electronic effect, steric hindrance also significantly slows down the reaction (entries 4, 9, and 10). In the absence of steric hindrance, the 1,4benzenedimethanol can be quickly converted (entry 11), with a similar catalytic efficiency to that of benzyl alcohol. However, under identical conditions, Pt/PCN-224(Zn) does not present any activity in the oxidation of toluene (entry 12), which generally requires harsh conditions like stronger oxidant or high temperature/pressure.

Table 2. Photo-oxidation of various aromatic alcohols over Pt/PCN-224(Zn)^a



Journal of the American Chemical Society

	Entry	Substrate	Time (min)	Conversion (%) ^b	Selectivity (%) ^b
	1	ОН 1а	50	>99	100
	2	O ₂ N 2a	60	>99	100
	3	Br 3a	50	>99	100
	4	CI 4a	40	>99	100
	5	DH 5a	120	>99	100
	6	H ₂ N 6a	120	>99	100
	7	Ta OH	120	>99	100
	8	OH 8a	50	>99	100
	9	CI OH 9a	300	>99	100
	10	OH 10a	180	>99	100
	11 ^c	HO OH 11a	50	>99	100
-	12	CH ₃ 12a	120	-	-

^aReaction conditions: catalyst (20 mg, 6.3 µmol Pt), alcohol (20 µmol), 10 mL H₂O, visible light ($\lambda > 400$ nm, 100 mW/cm²), O₂ (1 atm), starting temperature: 16 °C. ^bYield of aldehyde was analyzed by GC, and *n*-dodecane was used as the internal standard. ^cSubstrate (10 µmol).

CONCLUSIONS

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20 21

22

23

24 25

26

27 28

29

30

31 32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59 60

In summary, we demonstrate for the first time the superiority of photochemically generated ¹O₂ as a mild oxidant for the selective oxidation of aromatic alcohols into corresponding aldehydes using Pt/PCN-224(M) as the catalysts. The reactions proceed with excellent selectivity and yield within short reaction time under ambient conditions involving visible light irradiation. Neither harsh chemicals nor high pressure is needed, and the catalyst can be recycled at least six times without noticeable loss of activity. We carried out detailed studies and found unusual synergistic effect among photothermal effect, electronic state of Pt surface, and diamagnetism of metal in the MOF. We attribute the excellent performance of Pt/PCN-224(Zn) composite to the combination of the following factors: 1) both Pt NCs and PCN-224(Zn) have strong visible light-harvesting power and they work synergistically in the composite to achieve even more pronounced photothermal effect which promotes the oxidation reaction; 2) Under visible

light irradiation, Pt/PCN-224(Zn), synergizing the ability of its individual component for the ¹O₂ generation, effectively activates O_2 into 1O_2 , a mild and crucial oxidant for the highly selective oxidation of primary alcohols; 3) Among all PCN-224(M) explored, PCN-224(Zn) exhibits the greatest ability of O_2 activation and 1O_2 production due to the strongest diamagnetism with the d¹⁰ configuration of Zn²⁺ among different metals residing in the porphyrin center in the MOF; 4) The electronic state of surface Pt, closely associated with ¹O₂ generation, can be adjusted flexibly by the competition between Schottky junction and plasmonic effect with varying light intensities, to achieve optimized O_2 activation; 5) The moderate oxidation ability of ${}^{1}O_{2}$ effectively prevents the over-oxidation and thus gives 100% selectivity to aldehyde products. This work represents the first report on the acceleration of catalytic organic oxidations by regulating electronic states of metal surface in metal/MOF composites and their photothermal effect under visible light irradiation, which will open up a new door to the development of metal/MOF composites, or even metal/semiconductors, for photocatalytic organic reactions.

ASSOCIATED CONTENT

Supporting Information.

Additional figures mentioned in the text. This material is available free of charge via the ACS Publications website at http://pubs.acs.org.

AUTHOR INFORMATION

Corresponding Author

jianglab@ustc.edu.cn

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENT

We are grateful to the reviewers for their insightful comments and valuable suggestions. This work was supported by the NSFC (21673213, 21371162, and 21521001), the 973 program (2014CB931803), the Recruitment Program of Global Youth Experts, and the Fundamental Research Funds for the Central Universities (WK20160190075).

REFERENCES

(1) Sheldon, R. A.; Arends, I. W. C. E.; Brink, G. J.; Dijksman, A. Acc. Chem. Res. 2002, 35, 774.

(2) Ishida, T.; Nagaoka, M.; Akita, T.; Haruta, M. Chem. Eur. J. 2008, 14, 8456.

(3) Karimi, B.; Khorasani, M.; Vali, H.; Vargas, C.; Luque, R. ACS Catal. 2015, 5, 4189.

(4) Enache, D. I.; Edwards, J. K.; Landon, P.; Solsona-Espriu, B.; Carley, A. F.; Herzing, A. A.; Watanabe, M.; Kiely, C. J.; Knight, D. W.; Hutchings, G. J. *Science* **2006**, *311*, 362.

(5) Sarina, S.; Zhu, H.; Jaatinen, E.; Xiao, Q.; Liu, H.; Jia, J.; Chen, C.; Zhao, J. J. Am. Chem. Soc. **2013**, *135*, 5793.

(6) Guo, Z.; Liu, B.; Zhang, Q.; Deng, W.; Wang, Y.; Yang, Y. Chem. Soc. Rev. 2014, 43, 3480.

(7) Abad, A.; Concepción, P.; Corma A.; García, H. Angew. Chem. Int. Ed. 2005, 44, 4066.

(8) Mori, K.; Hara, T.; Mizugaki, T.; Ebitani, K.; Kaneda, K. J. Am. Chem. Soc. 2004, 126, 10657.

(9) Mallat, T.; Baiker, A. Chem. Rev. 2004, 104, 3037.

(10) Su, F.; Mathew, S. C.; Lipner, G.; Fu, X.; Antonietti, M.; Blechert, S.; Wang, X. J. Am. Chem. Soc. **2010**, *132*, 16299.

59 60 (11) Herzberg, G. Molecular spectra and molecular structure I: spectra of diatomic molecules, 2nd ed., VonNostrand, New York, 1950.
(12) Wahlen L: De Vos D. E: Jacob P. A: Alsters P. I. 4dy.

- (12) Wahlen, J.; De Vos, D. E.; Jacob, P. A.; Alsters, P. L. Adv. Synth. Catal. **2004**, *346*, 152.
- (13) Long, R.; Mao, K.; Ye, X.; Yan, W.; Huang, Y.; Wang, J.; Fu,
- Y.; Wang, X.; Wu, X.; Xie, Y.; Xiong, Y. J. Am. Chem. Soc. 2013, 135, 3200.
- (14) Urakami, H.; Zhang, K.; Vilela, F. Chem. Commun. 2013, 49, 2353.
- (15) Lu, K.; He, C.; Lin, W. J. Am. Chem. Soc. 2014, 136, 16712.
- (16) Park, J.; Feng, D.; Yuan, S.; Zhou, H.-C. Angew. Chem. Int. Ed. 2015, 54, 430.
- (17) Liu, Y.; Howarth, A. J.; Hupp, J. T.; Farha, O. K. Angew. Chem. Int. Ed. 2015, 54, 9001.
- (18) Chen, X.; Addicoat, M.; Jin, E.; Zhai, L.; Xu, H.; Huang, N.; Guo, Z.; Liu, L.; Irle, S.; Jiang, D. J. Am. Chem. Soc. 2015, 137,
- 3241.
- (19) Ding, X.; Han, B.-H. Angew. Chem. Int. Ed. 2015, 54, 6536.
- (20) Liu, Y.; Moon, S.-Y.; Hupp, J. T.; Farha, O. K. ACS Nano **2015**, *9*, 12358.
- (21) Wilkinson, F.; Helman, W. P.; Ross, A. B. J. Phys. Chem. Ref. Data 1995, 24, 663.
- (22) DeRosa, M. C.; Crutchley, R. J. Coord. Chem. Rev. 2002, 233-234, 351.
- (23) Montagnon, T.; Tofi, M.; Vassilikogiannakis, G. Acc. Chem. Res. 2008, 41, 1001.
 - (24) Kovalev, B. D.; Fujii, M. Adv. Mater. 2005, 17, 2531.
 - (25) Ogilby, P. R. Chem. Soc. Rev. 2010, 39, 3181.
- (26) Vankayala, R.; Sagadevan, A.; Vijayaraghavan, P.; Kuo, C.-L.; Hwang, K. C. *Angew. Chem. Int. Ed.* **2011**, *50*, 10640.
- (27) Wang, H.; Yang, X.; Shao, W.; Chen, S.; Xie, J.; Zhang, X.; Wang, J.; Xie, Y. J. Am. Chem. Soc. 2015, 137, 11376.
 - (28) Long, J. R.; Yaghi, O. M. Chem. Soc. Rev. 2009, 38, 1213.
- (29) Zhou, H.-C.; Long, J. R.; Yaghi, O. M. Chem. Rev. 2012, 112, 673.
- (30) Furukawa, H.; Cordova, K. E.; O'Keeffe, M.; Yaghi, O. M. Science **2013**, *341*, 974.
 - (31) Zhou, H.-C.; Kitagawa, S. Chem. Soc. Rev. 2014, 43, 5415.
 - (32) Wang, Z. Q.; Cohen, S. M. Chem. Soc. Rev. 2009, 38, 1315.
- (33) Fu, Y.; Sun, D.; Chen, Y.; Huang, R.; Ding, Z.; Fu, X.; Li, Z. Angew. Chem. Int. Ed. 2012, 51, 3364.
- (34) Feng, D.; Chung, W.-C.; Wei, Z.; Gu, Z.-Y.; Jiang, H.-L.;
- Chen, Y.-P.; Darensbourg, D. J.; Zhou, H.-C. J. Am. Chem. Soc. 2013, 135, 17105.
- (35) Gao, W.-Y.; Chrzanowski, M.; Ma, S. Chem. Soc. Rev. 2014, 43, 5841.
- (36) He, Y.; Zhou, W.; Qian, G.; Chen, B. Chem. Soc. Rev. 2014, 43, 5657.
 - (37) Zhao, M.; Ou, S.; Wu, C.-D. Acc. Chem. Res. 2014, 47, 1199.
- (38) Hermes, S.; Schröter, M.-K.; Schmid, R.; Khodeir, L.; Muhler, M.; Tissler, A.; Fischer, R. W.; Fischer, R. A. Angew. Chem. Int. Ed.
- **2005**, *44*, 6237. (39) Hwang, Y. K.; Hong, D.; Chang, J.-S.; Jhung, S. H.; Seo, Y.-
- K.; Kim, J.; Vimont, A.; Daturi, M.; Serre, C.; Férey, G. Angew. *Chem. Int. Ed.* **2008**, *47*, 4144.
- (40) Jiang, H.-L.; Liu, B.; Akita, T.; Haruta, M.; Sakurai, H.; Xu, Q. J. Am. Chem. Soc. **2009**, *131*, 11302.
- (41) Yuan, B.; Pan, Y.; Li, Y.; Yin, B.; Jiang, H. Angew. Chem. Int. Ed. 2010, 49, 4054.
- (42) Lu, G.; Li, S.; Guo, Z.; Farha, O. K.; Hauser, B. G.; Qi, X.;
- Wang, Y.; Wang, X.; Han, S.; Liu, X.; DuChene, J. S.; Zhang, H.;
- Zhang, Q.; Chen, X.; Ma, J.; Loo, S. C. J.; Wei, W. D.; Yang, Y.;
- Hupp, J. T.; Huo, F. Nat. Chem. 2012, 4, 310.
- (43) Hermannsdörfer, J.; Friedrich, M.; Miyajima, N.; Albuquerque, R. Q.; Kümmel, S.; Kempe, R. *Angew. Chem. Int. Ed.* **2012**, *51*, 11473.
- (44) Dhakshinamoorthy, A.; Garcia, H. Chem. Soc. Rev. 2012, 41, 5262.
- (45) Moon, H. R.; Lim, D. W.; Suh, M. P. Chem. Soc. Rev. 2013, 42, 1807.

- (46) Khaletskaya, K.; Reboul, J.; Meilikhov, M.; Nakahama, M.; Diring, S.; Tsujimoto, M.; Isoda, S.; Kim, F.; Kamei, K. I.; Fischer, R.
- A.; Kitagawa, S.; Furukawa, S. J. Am. Chem. Soc. 2013, 135, 10998.
 (47) Hu, P.; Morabito, J. V.; Tsung, C.-K. ACS Catal. 2014, 4,
- 4409. (48) Liu, X.; He, L.; Zheng, J.; Guo, J.; Bi, F.; Ma, X.; Zhao, K.;
- Liu, Y.; Song, R.; Tang, Z. *Adv. Mater.* **2015**, *27*, 3273.
- (49) Yang, Q.; Xu, Q.; Yu, S.-H.; Jiang, H.-L. Angew. Chem. Int. Ed. 2016, 55, 3685.
- (50) Li, Z.; Yu, R.; Huang, J.; Shi, Y.; Zhang, D.; Zhong, X.; Wang,
- D.; Wu, Y.; Li, Y. Nat. Commun. 2015, 6, 8248.
 - (51) Wang, D.; Wang, M.; Li, Z. ACS Catal. 2015, 5, 6852.
 (52) Deenadayalan, M. S.; Sharma, N.; Verma, P. K.; Nagaraja, C.
- M. Inorg. Chem. 2016, 55, 5320.
 (5) Shiniki V. Sycona V. Tanaka S. Hirai T. Angan Chem.
- (53) Shiraishi, Y.; Sugano, Y.; Tanaka, S.; Hirai, T. Angew. Chem. Int. Ed. 2010, 49, 1656.
- (54) Chiu, C.-Y.; Yao, Z.; Zhou, F.; Zhang, H.; Ozolins, V.; Huang, Y. J. Am. Chem. Soc. 2013, 135, 15489.
- (55) Jain, P. K.; Huang, X.; El-Sayed, I. H.; El-Sayed, M. A., Acc. Chem. Res. 2008, 41, 1578.
- (56) Wang, F.; Li, C.; Chen, H.; Jiang, R.; Sun, L. D.; Li, Q.; Wang, J.; Yu, J. C.; Yan, C. H. J. Am. Chem. Soc. **2013**, *135*, 5588.
- (57) Linic, S.; Aslam, U.; Boerigter, C.; Morabito, M. Nat. Mater. 2015, 14, 567-576.
- (58) Song, S.; Wang, X.; Li, S.; Wang, Z.; Zhu, Q.; Zhang, H. Chem. Sci. 2015, 6, 6420.
- (59) Zhai, W.; Xue, S.; Zhu, A.; Luo, Y.; Tian, Y. *ChemCatChem* **2011**, *3*, 127.
- (60) Kim, J.; Monllor-Satoca, D.; Choi, W. Energy Environ. Sci. 2012, 5, 7647.
- (61) Yang, J.; Wang, D.; Han, H.; Li, C. Acc. Chem. Res. 2013, 46, 1900.
- (62) Long, R.; Mao, K.; Gong, M.; Zhou, S.; Hu, J.; Zhi, M.; You, Y.; Bai, S.; Jiang, J.; Zhang, Q.; Wu, X.; Xiong, Y. Angew. Chem. Int.
- Ed. 2014, 53, 3205.
- (63) Sakamoto, H.; Ohara, T.; Yasumoto, N.; Shiraishi, Y.; Ichikawa, S.; Tanaka, S.; Hirai, T. J. Am. Chem. Soc. 2015, 137, 9324.
- (64) Venna, S. R.; Jasinski, J. B.; Carreon, M. A. J. Am. Chem. Soc. 2010, 132, 18030.
- (65) Song, H.; Kim, F.; Connor, S.; Somorjai, G. A.; Yang, P. J. Phys. Chem. B 2005, 109, 188.
- (66) Li, B.; Long, R.; Zhong, X.; Bai, Y.; Zhu, Z.; Zhang, X.; Zhi, M.; He, J.; Wang, C.; Li, Z.-Y.; Xiong, Y. *Small* **2012**, *8*, 1710.
- (67) Gomes, A.; Fernandes, E.; Lima, J. L. J. Biochem. Biophys. Methods. 2005, 65, 45.
- (68) Gollmer, A.; Arnbjerg, J.; Blaikie, F. H.; Pedersen, B. W.; Breitenbach, T.; Daasbjerg, K.; Glasius, M.; Ogilby, P. R. *Photochem. Photobiol.* **2011**, *87*, 671.
- (69) Zhang, K.; Kopetzki, D.; Seeberger, P. H.; Antonietti, M.; Vilela, F. Angew. Chem. Int. Ed. 2013, 52, 1432.
- (70) Josephy, P. D.; Eling, T.; Mason, R. P. J. Biol. Chem. 1982, 257, 3669.
- (71) Badwey, J. A.; Karnovsky, M. L. Annu. Rev. Biochem. 1980, 49, 695.
- (72) Konaka, R.; Kasahara E.; Dunlap W. C.; Yamamoto, Y.; Chien, K. C.; Inoue M. Free Radical Biol. Med. **1999**, *27*, 294.
- (73) Noda, Y.; Anzai, K.; Mori, A.; Kohno, M.; Shinmei, M.; Packer, L. *Biochem. Mol. Biol. Int.* **1997**, *42*, 35.

Journal of the American Chemical Society

Table of Contents





- 57 58 59
- 60