

Article

Oxygenation of Methylarenes to Benzaldehyde Derivatives by a Polyoxometalate Mediated Electron Transfer-Oxygen Transfer Reaction in Aqueous Sulfuric Acid

Bidyut Bikash Sarma, Irena Efremenko, and Ronny Neumann

J. Am. Chem. Soc., Just Accepted Manuscript • DOI: 10.1021/jacs.5b01745 • Publication Date (Web): 22 Apr 2015 Downloaded from http://pubs.acs.org on April 29, 2015

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



Journal of the American Chemical Society is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036 Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

Oxygenation of Methylarenes to Benzaldehyde Derivatives by a Polyoxometalate Mediated Electron Transfer-Oxygen Transfer Reaction in Aqueous Sulfuric Acid

Bidyut Bikash Sarma, Irena Efremenko and Ronny Neumann*

Department of Organic Chemistry, Weizmann Institute of Science, Rehovot, Israel 76100

Supporting Information Placeholder

ABSTRACT: The synthesis of benzaldehyde derivatives by oxygenation of methylarenes is of significant conceptual and practical interest because these compounds are important chemical intermediates whose synthesis is still carried out by non-sustainable methods with very low atom economy and formation of copious amounts of waste. Now an oxygenation reaction with a 100 % theoretical atom economy using a polyoxometalate oxygen donor has been found. The product yield is typically above 95% with no "over oxidation" to benzoic acids; H₂ is released by electrolysis, enabling additional reaction cycles. An electrocatalytic cycle is also feasible. This reaction is possible through the use of an aqueous sulfuric acid solvent, in an aqueous biphasic reaction mode that also allows to simple catalyst recycle and recovery. The solvent plays a key role in the reaction mechanism by protonating the polyoxometalate thereby enabling the activation of the methylarenes by an electron transfer process. After additional proton transfer and oxygen transfer steps, benzylic alcohols are formed that further react by an electron transfer-proton transfer sequence forming benzaldehyde derivatives.

Introduction

Carbon-hydrogen bond activation of alkanes and related oxygen insertion leading to hydroxylated products remains a highly desirable and important chemical transformation with broad implications in many areas ranging from the energy sector, for example methane to methanol, to transformations in the fine chemical industry. Much of the more recent research in homogeneous phase catalytic hydroxylation has been devoted to enzymatic reactions and the use of related biomimetic analogues as catalysts.^{1,2} Iron based heme and non-heme catalysts have been the most studied compounds.^{3,4} An important sub-class of alkane hydroxylation reactions is the oxygenation of alkylarenes, where the weaker benzylic carbon-hydrogen bond makes such a selective transfor-

mation more probable. Surprisingly, despite the perceived easier oxygenation of alkylarenes, a selective, high yield reaction of methylarenes, ArCH₃, to benzaldehyde derivatives, ArCHO, remains a considerable challenge, especially in the context of green, waste free transformations with a high atom economy, because aerobic and peroxide oxidation strongly tends to yield benzoic acid derivatives as the major product.⁵ A perusal of the literature describing the synthesis of benzaldehyde derivatives shows that there are five major reaction pathways. The first pathway is formylation reactions of arenes by various methods such as the Gatterman-Koch reaction,⁶ the Gatterman reaction,⁷ the Vilsmeier-Haack reaction,⁸ the Reimer-Tiemann reaction,⁹ the use of dichloromethyl methyl ether and aluminum chloride,¹⁰ or formylfluoride/boron trifluoride.11 All these reactions form copious amounts of waste, and often use or produce toxic compounds. They are not general for all substrates and not regioselective, thus requiring product separation. Second, use of molecular halogens X_2 , X =Cl, Br, either through free radical halogenation of methylarenes followed by hydrolysis to yield the required aldehyde,¹² or by halogenation of arenes to the corresponding haloarenes followed by carbonylation with carbon monoxide typically using palladium catalysts.¹³ Obviously these reactions produce large quantities of halide waste. Methylarenes can be oxidized to the corresponding carboxylic acids, by a large variety of methods but also catalytically with O₂ using the classic autooxidation Co/Mn/Br catalysts.⁵ The carboxylic acid can then be reduced, typically via formation of an acylchloride followed by reduction.¹⁴ Single step highly selective catalytic formation of ArCHO from ArCH₃ in high yields with benign oxidants has not been demonstrated, although using stoichiometric reagents such as chromyl chloride,¹⁵ permanganate,¹⁶ manganese diox-ide,¹⁷ hypervalent iodine compounds,¹⁸ and cerium oxidants¹⁹ can be effective. Recently, there have been some reports on new catalysts for the oxidation of ArCH₃ compounds such as Pd-Au nanoparticles supported on

carbon or TiO_2 ,²⁰ Cu-based heterogeneous catalysts,²¹ and thermally treated melamine.²² Conversion and/or selectivity to benzaldehyde is low.

Previous research has shown that phosphovanadomolybdate polyoxometalates, most notably H₅PV₂Mo₁₀O₄₀ is reactive in electron transfer-oxygen transfer (ET-OT) reactions that, for example, can lead insertion of oxygen from $H_5PV_2Mo_{10}O_{40}$ into a C-H bond.²³ For example, an alkylarene with a low oxidation potential, such as xanthene, was shown to react in this manner to yield xanthone as product.²⁴⁻²⁵ However, no reaction occurred with substrates with higher oxidation potential notably toluene and alike. Recently, we have demonstrated that (ET-OT) reactions, active for cleavage of C-C bonds of primary alcohols and vicinal diols,²⁶ can transform carbohydrates to synthesis gas.²⁷ Important in the context of this research, it was observed that such reactions are considerably accelerated using mineral acids as solvents, leading us the proposition that reactions that were not enabled in typical organic solvents may be possible in mineral acids. Indeed, we now demonstrate for the first time the two stage very high yield and selective oxidation of ArCH₃, to ArCHO with a theoretical atom economy of 100%, Scheme 1. First ArCHO is formed in an ET-OT oxygenation reaction and then H₂ as the additional product is released by electrolysis. The reaction can also be carried out electrocatalytically. Cyclic voltammetry and DFT calculations coupled with mechanistic probe reactions shows why mineral acids may be superior solvents for such ET-OT transformations.



Scheme 1. Scheme for the ET-OT oxygenation of ArCH₃ to ArCHO followed by electrolytic release of H₂.

Results and Discussion

Oxygenation of ArCH₃ to ArCHO. As shown in Scheme 1, the oxygenation of ArCH₃ to ArCHO is a four-electron oxidation and since H₅PV₂Mo₁₀O₄₀ is nominally a two-electron oxidant, stoichiometric reactions between H₅PV₂Mo₁₀O₄₀ and ArCH₃ in a 2:1 ratio were found to be optimal for the formation of ArCHO. In such a process it has been shown that an oxygen atom on the surface of the polyoxometalate framework is the oxygen donor.²⁵ Thus, the ET-OT oxygenation of toluene, PhCH₃, and various substituted derivatives, $RC_6H_4CH_3$ with 2 equivalents $H_5PV_2Mo_{10}O_{40}$ was carried out in 50% aqueous H₂SO₄ as solvent. Depending on the substrate, the partially optimized conditions of reaction temperature and time to yield an optimal amount of ArCHO products are summarized in Table 1. The results show highly efficient formation of ArCHO in almost all cases with practically no formation (0-0.1

mol%) of the corresponding carboxylic acid, ArCOOH. Also, no sulfonated products were detected. For toluene and halogen substituted derivatives as electron withdrawing moieties nearly quantitative conversions were observed with very high selectivity to ArCHO.

Table 1. ET-OT oxidation of ArCH₃ compounds to Ar-CHO

R in R-	Time,	Temper-	Conver-	Selectivi-
$C_6H_4CH_3$	h	ature, °C	sion, mol%	ty, mol%
Н	5	70	99	95
4-Me	5	60	99	94
3-Me	5	70	99	94
2-Me	5	60	99	89
2,4-diMe ^[a]	5	50	80	80
1,3,5-	5	50	90	85
unime				
4-OMe	24	5-22 ^[b]	85	75
4- <i>i</i> -Pr	24	5-22 ^[b]	60	30 ^[c]
4- <i>t</i> -Bu	12	30	93	89 ^[d]
4-F	5	70	99	98
4-Cl	7	80	99	97
4-Br	10	80	98	96
4-I	10	80	97	96
3-C1	8	80	98	93
3-Br	7	80	98	94
2,4,-diCl	12	90	90	96
$4-NO_2^{[e]}$	24	90	45	98

Reaction conditions: 0.461 mmol ArCH₃, 0.922 mmol $H_5PV_2Mo_{10}O_{40}$ •32H₂O, 8 mL 50% H_2SO_4 , N₂. The products were quantified by GC-FID and identified by GC-MSD when reference samples were unavailable. Unless otherwise stated the major by-products were dimers, e.g. a mixture of dimethyl substituted biphenyl isomers from toluene. Traces of other compounds, typically less than 0.5% were sometimes formed. No arene sulfonation reactions were observed. [a] Three dimethyl benzaldehyde isomers were formed in similar amounts. [b] The reaction mixture was kept at ~5 °C for 3 h and then left to warm to ambient temperature. [c] The major product, 65-70%, was 4-methylacetophenone. [d] The major byproduct, ~8 %, was benzaldehyde. [e] The substrate tended to sublime from the reaction mixture.

Since the reaction is initiated by electron transfer to yield an electrophilic radical cation, ArCH₃⁺⁺, which can then also yield an electrophilic cation ArCH₂⁺ through further proton and electron transfer, ²⁵ reaction of these plausible intermediate electrophiles with ArCH₃ yields some small amounts of dimeric compounds, typically as the only by-products. 4-Nitrotoluene also reacts, however, in this case sublimation of the substrate leads to its removal from the reaction mixture lowering the yield. For moderately activated toluene derivatives, such as the xylenes, the corresponding tolualdehydes are formed

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35 36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58 59

60

selectively. Similarly, 4-tert-butyltoluene reacts selectively to yield the corresponding 4-tert-butyl benzaldehyde with some formation of benzaldehyde likely because acid catalyzed dealkylation. An interesting substrate is 4-iso-propyltoluene, where the tertiary C-H bond is weaker than the primary C-H bond. Activation at the tertiary positions leads to oxygenation coupled with C-C bond cleavage to give the 4-methylacetophenone as the main product. Still there are significant amounts of 4-iso-propyl benzaldehyde formed, which is clearly the kinetically preferred product since at higher temperatures only 4-methylacetophenone is formed. Similarly, iso-propylbenzene yielded acetophenone (88 % yield) and ethylbenzene also yielded the C-C bond cleaved product benzaldehyde (94 % yield). With more electron donating substituents, for example with 1,2,4trimethylbenzene, dimer formation becomes more pronounced. This dimer formation can be significantly inhibited by reducing the reaction temperature to 5-22 °C and increasing reaction times. This effect is pronounced in the oxidation of 4-methoxytoluene where good yields of 4-methoxy benzaldehyde were achievable. At 50-60 °C there was almost only dimerization and even some formation of oligomers.

After completion of the ET-OT reaction with the formation of ArCHO, the polyoxometalate is reduced. The number of electrons on the polyoxometalate was measured by titration with KMnO₄ on the representative toluene oxidation reaction. About 1.95 electrons per polyoxometalate were found which is commensurate with the yield of benzaldehyde and the reaction stoichiometry. The completion of catalytic cycles in typical organic solvents is possible by use of O_2 , equation 1.

(1) 2 $H_7PV_2^{IV}Mo_{10}O_{40} + O_2 \longrightarrow 2 H_5PV_2^{V}Mo_{10}O_{40} + 2 H_2O$

However, in 50 % H₂SO₄ this reaction is very slow and alternatively the reduced polyoxometalate can be reoxidized by electrolysis with quantitative formation of H_2 .²⁷ A cyclic voltametric measurement of the reaction mixture after the formation of the reduced polyoxometalate shows a reversible redox wave at ~ 1.1 V versus SCE, Figure S1. Therefore, H₇PV^{IV}Mo₁₀O₄₀ was reoxidized with a Pt gauze anode and a platinum wire cathode at a potential of 1.3 V or higher between the anode and cathode to quantitatively release H₂, Figure S2.²⁸ It should be noted that in a two-cell setup with a Nafion membrane, Figure S3, one visually observe that H_2 is being released at the Pt cathode electrode and that the reduced green polyoxometalate was oxidized to the orange $H_5PV^{\nu}Mo_{10}O_{40}$ at the anode. In this vein, five oxygenation - electrolysis cycles were carried out without loss of reactivity on three representative substrates, toluene, 4-chlorotoluene and 4-tert-butyltoluene showing that the catalyst is easily reoxidized and then recovered without its removal from the solvent in a quantitative

transformation. The conversions and product selectivity were within ± 3 % for each cycle.

Alkylarene oxidation can also be carried out electrocatalytically in one step, that is simultaneous substrate oxygenation and polyoxometalatate reoxidation. Thus, 10 mmol substrate, 0.23 mmol H₅PV₂Mo₁₀O₄₀ in 5 mL 50 % H₂SO₄ were reacted using Pt gauze as working electrode, and Pt wire as counter and reference electrode at a cell potential of 1.5 V between the cathode and anode. The higher cell potential was used to accelerate the reoxidation of the polyoxometalate. When the substrate was toluene at 70 °C, approximately a 65 % yield (28 turnovers) of benzaldehvde was obtained after 10 h with >95% selectivity. When *p*-xylene was used as substrate similar results were obtained. Attempts to use a two half cell setup as shown in Figure S3 suffered from the lack of stability of the Nafion membrane at more elevated temperatures. It should be noted that indirect electrocatalytic oxidation of toluene and derivatives is also possible with Mn³⁺ and Co³⁺ salts in concentrated acid, but these catalysts tend to be less selective to benzaldehyde derivatives under high conversion conditions (see discussion below).²⁹ Ce⁴⁺ has been more selective but in order to obtain good results Ag⁺ was added as a catalyst or reactions were carried out in CH₃SO₃H.³⁰

Mechanism of activation of ArCH₃. The key experimental observation that oxygenation of toluene with H₅PV₂Mo₁₀O₄₀ is possible in a mineral acid solvent but not in an organic solvent such as acetonitrile requires detailed explanation. It was hypothesized that the strongly acidic medium lead to the increase in the redox potential of $H_5PV_2Mo_{10}O_{40}$. In Figure 1, we present the cyclic voltammetry measurements that show the changes in the oxidation potential as a function of H₂SO₄ concentration. See Figure S4 for all the cyclic voltammograms. At increasing H₂SO₄ concentrations from 0.1-5% there is a relatively small change in the oxidation potential from ~0.41 to 0.54 V versus SCE. At concentrations between 10-25% it was difficult to observe the redox wave, however at 30% to 50% H₂SO₄ the oxidation potential clearly and very strongly shifted to 1.0-1.1 V versus SCE. This shift in the redox potential is attributed to the formation of a protonated polyoxometalate at higher H₂SO₄ concentrations (see below).



Figure 1. Oxidation potential, $E_{1/2}$, versus SCE of $H_5PV_2Mo_{10}O_{40}$ at various concentrations of aqueous H_2SO_4 . The measurements were carried out at 2 mM $H_5PV_2Mo_{10}O_{40}$ using a glassy carbon working electrode, a platinum wire counter electrode and a calomel reference electrode; scan rate 50 mV/sec. Representative cyclic voltammograms at 1% (insert left) and 50% (insert right) H_2SO_4 are shown.

DFT calculations show that the oxidation of PhCH₃ to PhCHO according to Scheme 1 is thermodynamically favorable with $\Delta G_{298} = -39.0$ and -36.9 kcal/mol in acetonitrile and sulfuric acids, respectively. It is shown above that protonation dramatically increased the oxidation potential and reactivity of $H_5PV_2Mo_{10}O_{40}$. This has also been observed with other oxidants such as manganese and cobalt acetate,³¹ and has been attributed (i) to the lowering of orbital energies including that of the LUMO, (ii) to an increase of electrophilicity through formation of a positively charged species and (iii) specifically for H₅PV₂Mo₁₀O₄₀ by formation of coordinatively unsaturated sites that become available for coordination of a reactant.³² In a non-protic regime, polyoxometalates such as H₅PV₂Mo₁₀O₄₀ are neutral where the negative charge of the polyanion is fully compensated by the corresponding number of protons chemically bound to the bridging oxygen atoms, preferably around vanadium atoms.^{33,34} In sulfuric acid calculations show that further protonation of H₅PV₂Mo₁₀O₄₀ is favorable with $\Delta G_{298} = -2.4$ kcal/mol, equation 2.

(2)
$$H_5PV_2Mo_{10}O_{40} + H_3O^+ \longrightarrow H_6PV_2Mo_{10}O_{40}^+ + H_2O$$

1 2

Moreover, the proton affinity of reduced species is even higher, Table S1. Thus, protonation favors the reduction of this polyoxometalate both kinetically and thermodynamically. As predicted by the calculations, the protonation increases the electron affinity or oxidative "power" of $H_5PV_2^VMo_{10}O_{40}$ and $H_6PV_V^VV^{IV}Mo_{10}O_{40}$ by 10.6 kcal/mol and 9.3 kcal/mol, respectively.

Reaction of Neutral Polyoxometalate

PT [H₆PV^V₂Mo₁₀O₄₀]⁺ + PhCH₂⁻ [H₅PV^V₂Mo₁₀O₄₀] + PhCH₃ ET [H₅PV^{IV}V^VMo₁₀O₄₀]• + PhCH2• [H₅PV^{IV}V^VMo₁₀O₄₀]⁻⁻ + PhCH₃⁺⁺ ΔG_{298}^{AN} ΔG_{298}^{SA} ∆G₂₉₈ga $PT 1 \rightarrow 2$ 181.5 85.8 98.7 77.3 13.3 4.7 ET 1 → 3 PCFT $1 \rightarrow 4$ 214 17.5 18.1 Reaction of Protonated Polyoxometalate 2Mo₁₀O₄₀]+ + PhCH₃ FI [H₇PV^{IV}V^VMo₁₀O₄₀]*+ + PhCH₂* [H₅PV^{IV}V^VMo₁₀O₄₀]' + PhCH₃'+ 5 ∆G₂₉₈0 ΔG_{298}^{AN} ΔG_{298}^{SA} ET $2 \rightarrow 4$ 14.9 5.9 -5.9 -3.8 -6.6 10.1 PCET 2 → 5

Figure 2. Possible initial outer-sphere reactions for the oxidation of toluene and the calculated energetics. AN and SA refer to acetonitrile and sulfuric acid, respectively.

Activation of the reactants through electron transfer (ET) or proton coupled electron transfer (PCET) usually precedes oxygen transfer from the polyoxometalate to a substrate. Figure 2 displays the calculated energetics for the possible initial outer-sphere reactions for the oxidation of toluene. Although ET presents a plausible initial step for a neutral complex 1 in acetonitrile and, especially in sulfuric acid, all the outer sphere reactions of this complex are endergonic at 298 K. The outer-sphere reactions of 2 with toluene are energetically more favorable. Thus, electron transfer becomes exergonic in sulfuric acid. In gas phase as well as in the less polar acetonitrile solution PCET is energetically preferred, although 2 is not experimentally accessible under these conditions; ET is still endergonic. Thus, in contrast to PCET in neutral complexes as observed previously for more reactive alkylarenes such as xanthene,²⁵ toluene activation in sulfuric acid presents a sequential protonation of the polyoxometalate by the solvent followed by electron transfer and then proton transfer from the substrate to the polyoxometalate, Scheme 2.

Scheme 2. Reaction pathways for hydroxylation of xanthene in acetonitrile (top) and toluene (bottom) in aqueous $\rm H_2SO_4$.



Substitution effects. The results from Table 1 clearly show that toluene derivatives with electron donating groups are more reactive than those with electron withdrawing groups. This observation is commensurate with the calculations presented above showing that activation of PhCH₃ by **2** is initiated by ET. Thus, one might expect that the rate of oxidation of a series of substrates $RC_6H_4CH_3$ for various substituents R would be 4-Me > H > 4-Br > 4-Cl > 4-F. Indeed, the vertical ionization energy of these compounds, which represents the driving force for ET, approximated by the HOMO level in sulfuric acid, is appropriate for this order, Table S2. It was, therefore, initially surprising to observe that in the oxidation of 4-RC₆H₄CH₃ to 4-RC₆H₄CHO the relative first order rate constants, Figure S5, were 4-Me (1.24) > H 1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55 56

57

58

59

60

0.02

0.01

0.00

-0.01

-0.02

-0.03

-0.04

-0.05

-2

ARate, mol/min

(1.0) > 4-F (0.88) > 4-Cl (0.43) > 4-Br (0.24); the relative rates of the 4-halogen substituted compounds are very noticeably inverted. Further analysis of calculated data shows that the adiabatic ionization energy, Table S2, which represents the thermodynamic effect of ET shows a trend for the halogen substituted compounds that is proportional to the observed rates. One may rationalize these results by noting that spin delocalization is the main factor that determines the stability of a benzylic radical.³⁵ Thus, spin localization on the electron withdrawing halogen substituents may lead to destabilization of the benzylic radical. Indeed, for the isodesmic reaction, equation 3, we have found that there is a correlation between the experimentally observed substituent induced change in the reaction rate with the computed stabilization or destabilization energies, Figure 3. Thus, the radical cation of *p*-xylene is more stable (less reverse ET) relative to that of toluene leading to a faster rate for p-xylene. On the other hand, the radical cations of 4- $XC_6H_4CH_3$ (X = F, Cl, Br) are less stable (more reverse ET) than that of toluene, Br < Cl < F. Thus, in the range of reversible ET the less stable the intermediate radical cation the slower the rate.

(3) $C_6H_5CH_3 + 4-RC_6H_4CH_3^{+} \longrightarrow C_6H_5CH_3^{+} + 4-RC_6H_4CH_3$

0 🖊 F

R (de)stabilization, kcal/mol

4

2

= 0.019x - 0.012

 $R^2 = 0.994$

Me 🔷

6

8



Therefore, one may suggest that although the ET from all the tested *para* substituted compounds, $4\text{-RC}_6\text{H}_4\text{CH}_3$, is exergonic, radical cation intermediates of low stability as observed for 4-halogen substituted compounds may reverse the ET step and reduce the rate of reaction measured as formation of product. In contrast, for substrates with electron donating groups the benzylic radical is stable enough to slow or inhibit reverse ET reactions and the total rate of oxidation is mainly determined by the energy of the HOMO, the driving force for ET (see also below).

Mechanism of the ET-OT reaction. The proposed calculated mechanism for the ET-OT oxygenation of toluene is presented in Figure 4. As can be seen from the

results and as discussed above, after the initial ET reaction to yield $PhCH_3^{*+}$, the rate determining step is the sequential PT reaction leading to formation of the highest energy intermediates, the benzylic radical PhCH₂ and $[H_7PV^{IV}V^VMo_{10}O_{40}]^{++}$ (5); $\Delta G^{\ddagger}_{298} = 19.7$ kcal/mol. This is quite comparable to the experimental value of $\Delta G^{\ddagger}_{298} = 22.8 \text{ kcal/mol} (\Delta H^{\ddagger}_{298} = 15.8 \text{ kcal/mol}; \Delta S^{\ddagger}_{298}$ = -23.3 cal/mol K) obtained from the Eyring equation, Figure S6. In the transition state (TS) the proton being transferred has short bonds with both the benzylic carbon atom (1.25 Å) and a bridging oxygen atom of the polyoxometalate (1.34 Å). It should be expected that a PT limiting step would be associated with a kinetic isotope effect (KIE). Indeed, such a measurement, Figure S7, showed a KIE = 4.95 in a comparative experiment between the oxidation of C_7H_8 in H_2SO_4/H_2O and C_7D_8 in D₂SO₄/D₂O. A competitive experiment using a 1:1 mixture of C₇H₈ and C₇D₈ also indicated a similar KIE, but the GC-MS analysis was complicated by competing H-D exchange reactions at both the benzylic and ring positions.

After the formation of PhCH₂[•] there is a "rebound" where the $PhCH_2$ is bonded to the bridging atom of the polyoxometalate to form stable triplet and singlet intermediates of similar energy (8T and 8S). Subsequently, proton transfer to the bridging oxygen atom leads to formation of PhCH₂OH still strongly bonded to the polvoxometalate, intermediate 9, although the V-O/Mo-O bonds are considerably elongated to 2.35/2.44 Å from 2.12-2.14/2.04 Å in 8. Benzyl alcohol is released through the formation of defect species with coordinatively unsaturated sites and coordination of water (10), Figure S8, by the scission of a V-O/Mo-O bond. It should be noted that after short reaction times (20-30 min) small amounts of benzyl alcohol are indeed observed in the GC analyses. Furthermore, separate experiments also showed that benzyl alcohol is facilely oxidized to benzaldehyde; relative first order rate constants $PhCH_2OH:PhCH_3 = 4.9.$

Further in the course of the reaction pathway calculations show the feasibility of subsequent oxidative dehydrogenation of PhCH₂OH by another protonated complex **2** initiated by an outer-sphere ET, where the propensity for ET is similar to that of PhCH₃, Table S2. However, since the formation of PhCHO does not require the breaking of M-O bonds in the polyoxometalate, it proceeds with energies that are overall more favorable.

As stated above, contrary to organic solvents where ET-OT oxygenation of toluene does not occur, H_2SO_4 can react with $H_5PV_2^VMo_{10}O_{40}$ to yield a protonated, cationic $[H_6PV_2^VMo_{10}O_{40}]^+$ species. Thus, an ET reaction of $[H_6PV_2^VMo_{10}O_{40}]^+$ with toluene in H_2SO_4 is favored compared to a reaction between $H_5PV_2^VMo_{10}O_{40}$ and toluene in acetonitrile by 19 kcal/mol, in good agreement with the experimentally

observed increase of the oxidation potential of $H_2PV_2Mo_{10}O_{40}$ by ~0.7 eV when moving from diluted to concentrated sulfuric acid, Figure 1. It should be also noted that the protonation of the polyoxometalate and therefore *inter alia* the use of mineral acid solvents leads to more favorable thermodynamics and kinetics throughout the reaction profile. Moreover, the total energy of the reaction is also favored by the protonation of the polyoxometalate, equation 4.

(4) PhCH₃ + 2[H₆PV^V₂Mo₁₀O₄₀]⁺ + H₂O \longrightarrow PhCHO + 2[H₈PV^{IV}₂Mo₁₀O₄₀]⁺ ΔG_{298} = -44.5 kcal/mol PhCH₃ + 2 H₅PV^V₂Mo₁₀O₄₀ + H₂O \longrightarrow PhCHO + 2

 $H_7 P V_2^{IV_2} Mo_{10} O_{40} \quad \Delta G_{298} = -36.9 \text{ kcal/mol}$

 The hallmark of the transformation reported here is the very high selectivity obtained for ArCHO without formation of benzoic acid derivatives, ArCOOH. This is easily explained by the much less favored ionization energies and ΔG_{298} for ET for PhCHO compared to PhCH₃ and PhCH₂OH, Table S2. In this context, it is also worthwhile to discuss the intrinsic differences and advantages of ET-OT oxidation of PhCH₃ with H₅PV₂Mo₁₀O₄₀ compared to (a) ET oxidation catalyzed by Co^{III}(OAc)₃ using O₂ as oxygen donor and on the other hand (b) the use of stoichiometric oxidants such as

Étards reagent, CrO_2Cl_2 ¹⁵ and permanganate.^{16,36} The ET oxidation of ArCH₃ with $Co^{III}(OAc)_3$ is long known,³⁷ but the required use of O_2 as an oxygen donor leads to formation of peroxo radicals, ArCH₂OO', and then alkoxy radicals, ArCH₂O[•]. Especially the latter easily abstracts a hydrogen atom from benzaldehyde to promote a competing autoxidation reaction pathway by a hydrogen atom transfer (HAT) mechanism and formation of ArCOOH. The slow kinetic formation of Co^{III}(OAc)₃ in aerobic reactions has also led to use of promotors, notably bromide typically together with Mn(OAc)₂ which further attenuates ArCOOH formation by autoxidation.³⁸ Thus, it is difficult to obtain high yields of ArCHO using Co^{III}(OAc)₃/O₂. Although, the stoichiometric oxidation of ArCH₃ by CrO₂Cl₂¹⁵ or permanganate^{16,36} is long known, the selectivity to ArCHO is low.^{15,16} Interestingly, however, Mayer and coworkers have convincingly argued that these reactions proceed by a HAT or hydride transfer mechanism concluding that the key feature in these reactions is affinity of the oxidant to H'/H⁻ that represents the thermodynamic driving force for oxygen transfer. The mechanism of oxidation of alkylarenes with CrO₂Cl₂ or KMnO₄ is very different than that observed here with $H_5PV_2Mo_{10}O_{40}$.



Figure 4. A DFT calculation derived mechanism for oxidation of toluene $H_5PV_2Mo_{10}O_{40}$ in 50% sulfuric acid. Green – V; black – Mo; red- O; brown – C; whitish - H.

Conclusions

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36 37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59

60

The transformation of toluene and its derivatives to the corresponding benzaldehyde compounds as presented in Scheme 1, shows both the ET-OT oxidation of the substrate and the formation of H₂ in a second step to form a cyclic repeatable process, for the high yield formation of products with a 100% theoretical atom economy, considering that H₂ has value. The oxidation potential of $H_5PV_2Mo_{10}O_{40}$ in this media, 1.1 V SCE (1.34 V NHE), is higher than the potential for aerobic formation of water (1.23 V NHE), equation 1. This prevents the thermal re-oxidation of the reduced polyoxometalate and precludes an aerobic reaction requiring an electrochemical oxidation of the reduced polyoxometalate. The generally very high reaction yield lends an important practical aspect to such a reaction with potential to replace common non-benign procedures. Notably, the use of aqueous H₂SO₄ as solvent leads to an aqueous biphasic reaction medium,³⁸ and therefore a simple cascade of operations - (i) thermal substrate oxygenation, (ii) phase separation of the organic and catalyst phase and (iii) catalyst recycle and recovery by electrolysis, can be implemented. However, one-stage electrocatalytic reactions are also viable. The stability of the Nafion membrane in a two half-cell configuration at elevated temperatures sometimes needed is a remaining technical issue to be solved.

In summary, the use of strong mineral acids as solvents that allows significantly improved reactivity due to the higher redox potential of $H_5PV_2Mo_{10}O_{40}$. There are also advantages in catalyst recovery that are intrinsic to biphasic media. Together with the unique ET-OT oxygenation reactions that $H_5PV_2Mo_{10}O_{40}$ catalyzes, this research opens up new prospects for selective oxidative transformations, demonstrated here by the selective oxygenation of methylarenes.

Experimental Section

Materials. Alkylarenes were of analytical grade. Deuterated compounds were purchased from Cambridge Isotope Laboratories. $H_5PV_2Mo_{10}O_{40}$ •32H₂O was prepared by a known procedure.

Reactions. Typically the oxidation reactions of ArCH₃ were carried out in 50 mL pressure tubes under N₂ under the conditions given in the tables and figures. The products were decanted and diluted by dichloromethane for analysis by gas chromatography. GC-FID (HP 6890) and GC-MSD (HP 5973) instruments were used equipped with a 5% phenyl methylsilicone 0.32 mm ID, 0.25 mm coating, 30 m column (Restek 5MS) using helium as carrier gas. H₂ was volumetrically quantified by calibration by GC-TCD using a 20' x 1/8" stainless steel column packed with molecular Sieve 5Å in series with a 4' x 1/8" stainless steel column packed with HayeSep T. The carrier gas was Ar, column T = 90 °C.

Electrolysis and cyclic voltammetry experiments. Cyclic voltammetry experiments were performed using a potentiostat (CHI660A) connected to a personal computer. The measurements were performed in a three-

electrode cell configuration consisting of (i) glassy carbon working electrode, (ii) a Pt wire counter electrode, and (iii) a calomel a reference electrode. experiments were performed at room temperature. The scan rate was 50 mV sec^{-1} . Electrolysis in a one cell configuration was carried out using (i) Platinum gauze (working electrode), (ii) a Pt wire (counter electrode), and (iii) Pt (a reference electrode). The experiments were performed at 25-80 °C. Electrolysis in a two half cell configuration was carried out in presence of Pt gauze as working electrode, and Pt wire as counter and reference electrode at different potentials from 1.3 to 1.5 V between the anode and cathode. The higher the potential the faster is the reoxidation reaction. The two half cells were separated by a Nafion 212 membrane washed before use with 5% wt H₂O₂ and 8% H₂SO₄ consecutively.

Computational method. All computations were done using the same methodology previously described by us for calculations involving $H_5PV_2Mo_{10}O_{40}$.³² Bulk solvent effects of the sulfuric acid medium have been calculated at the M06/PC1 level using the continuum solvation model COSMO with a static dielectric constant, $\varepsilon = 100$.⁴¹

ASSOCIATED CONTENT

Supporting Information. Additional experimental information and data. This material is available free of charge via the Internet at http://pubs.acs.org.

AUTHOR INFORMATION

Corresponding Author

Email: Ronny.Neumann@weizmann.ac.il

ACKNOWLEDGMENT

This research was supported by the Israel Science Foundation grants # 1073/10 and 763/14, the Bernice and Peter Cohn Catalysis Research Fund and the Helen and Martin Kimmel Center for Molecular Design. R.N. is the Rebecca and Israel Sieff Professor of Chemistry.

REFERENCES

1. Que Jr, L.; Tolman, W. B. Nature, 2008, 455, 333-340.

2. Bordeaux, M.; Galarneau, A.; Drone, J. Angew. Chem. Int. Ed. 2012, 51, 10712–10723.

3. Poulos, T. L. Chem. Rev. 2014, 114, 3919-3962.

4. Nam, W.; Lee, Y.-M; Fukuzumi, S. Acc. Chem. Res. 2014, 47, 1146-1154.

5. Partenheimer, W. Catal. Today 1995, 23, 69-158.

6. Crounse, N. N. Org. React. 1949, 5, 290-300.

7. Truce, W. E. Org. React. 1957, 9, 37-72.

8. Jones, G.; Stanforth, S. P. Org. React. 2004, 49, 1-330.

9. Wynberg, H.; Meijer, E. W. Org. React. 2005, 28, 1-36.

10. Rieche, A.; Gross, H.; Höft, E. Chem. Ber. 1960, 93, 88-94.

11. Olah, G. A.; Kuhn, S. J. J. Am. Chem. Soc. 1960, 82, 2380–2382.

12. K. Ditrich, Sci. Synth. 2007, 25, 575-584.

13. Klaus, S.; Neumann, H.; Zapf, A.; Strübing, D.; Hübner, S.; Almena, J.; Riermeier, T.; Gross, P.; Sarich, M.; Krahnert, W.-R.; Rossen, K.; Beller, M. *Angew. Chem. Int. Ed.* **2006**, *45*, 154–158. 14. Gutsulyak, D. V.; Nikonov, G. I. Adv. Synth. Catal. 2012, 354, 607–611.

15. Cook, G. A.; Mayer, J. M. J. Am. Chem. Soc. 1995, 117, 7139–7156.

16. Gardner, K. A.; Kuehnert, L. L.; Mayer, J. M. Inorg. Chem. 1997, 36, 2069–2078.

17. Nammalwar, B.; Fortenberry, C.; Bunce, R. A.; Lageshetty, S. K.; Ausman, K. D. *Tetrahedron Lett.* **2013**, *54*, 2010-2013.

18. Nicolaou, K. C.; Baran, P. S.; Zhong, Y.-L. J. Am. Chem. Soc. 2001, 123, 3183-3185.

19. R. P. Kreh, R. P.; Spotnitz, R. M.; Lundquist, J. T. *Tetrahedron Lett.* **1987**, *28*, 1067-1068 (1987).

20. Kesavan, L.; Tiruvalam, R.; Abu Rahim, M. H.; bin Saiman, M. I.; Enache, D. I.; Jenkins, R. L.; Dimitratos, N.; Lopez-Sanchez, J. A.; Taylor, S. H.; Knight, D. W.;. Kiely, C. J; Hutchings, G. J. *Science*, **2011**, *331*, 195-199.

21. Wang, F.; Xu, J.; Li, X.; Gao, J.; Zhou, L.; Ohnishi, R. Adv. Synth. Catal. 2005, 347, 1987-1992.

22. Li, X.-H.; Wang, X.; Antonietti, M. ACS Catal. 2012, 2, 2082–2086.

23. Neumann, R. Inorg. Chem. 2010, 49, 3594-3601.

24. Khenkin, A. M.; Neumann, R. Angew. Chem. Int. Ed. 2000, 39, 4088-4090.

25. Khenkin, A. M.; Weiner, L.; Wang, Y.; Neumann, R. J. Am. Chem. Soc. 2001, 123, 8531-8542.

26. Khenkin, A. M.; Neumann, R. J. Am. Chem. Soc. 2008, 130, 14474-14476.

27. Sarma, B. B.; Neumann, R. Nature Commun. 2014, 5, 4621.

28. The redox reaction $2H^+ + 2e^- \rightarrow H_2$ cannot be observed using a glassy carbon working electrode, calomel reference and Pt counter electrode. This reaction was observed when using Pt as working, counter and reference electrodes at ~0 V (ref 27), how-

ever this is the potential between the working and reference electrode and does not represent the redox potential of the polyoxometalate, which in this case is the potential between the Pt working and counter electrodes (cathode and anode), ~ 1.3 V.

29. (a) Wendt, H.; Schneider, H. J. Appl. Electrochem. **1986**, 16, 134-146. (b) Jow, J.-J.; Lee, A. C.; Chou, T.-C. J. Appl. Electrochem. **1987**, 17, 753-759. (c) Comminellis, C.; Plattner, E.; Javet, P. J. Appl. Electrochem. **1979**, 9, 753-755.

30. (a) Devadoss, V.; Basha, C. A.; Jayaraman, K. Ind. Eng. Chem. Res. 2008, 47, 4607–4616. (b) Jow, J.-J.; Chou, T.-C. J.

Appl. Electrochem. **1988**, *18*, 298-303. (c) Kramer, K.; Robertson, P. M.; Ibl, N. J. Appl. Electrochem. **1980**, *10*, 29-36.

31 Hanotier, J.; Hanotier-Bridoux, M.; de Radzitzky, P. J. Chem. Soc., Perkin Trans. 2, 1973, 381-386.

32. Efremenko, I.; Neumann, R. J. Am. Chem. Soc. 2012, 134, 20669–20680.

33. Efremenko, I.; Neumann, R. J. Phys. Chem. A, 2011, 115, 4811–4826.

34. Macht, J.; Janik, M. J.; Neurock, M.; Iglesia, E. J. Am. Chem. Soc. 2008, 130, 10369–10379.

35. Wu, Y.-D.; Wong, C.-L.; Chan, K. W. K. J. Org. Chem. 1996, 61, 746-750.

36. Gardner, K. A.; Mayer, J. M. Science, 1995, 269, 1849-1851.

37. Sheldon, R. A.; Kochi, J. K. Metal-Catalyzed Oxidations of Organic Compounds. Academic Press, (1981).

38. Jiao, X.-D.; Espenson, J. H. Inorg. Chem. 2000, 39, 1549-1554.

39. Sheldon, R. A. Green Chem. 2005, 7, 267–278.

40. Tsigdinos, G. A.; Hallada, C. J. Inorg. Chem. 1968, 7, 437-441.

41. Gillespie, R. J.; Cole, R. H. Trans. Faraday Soc. 1956, 52, 1325-1331.

