

View Article Online View Journal

RSC Advances

This article can be cited before page numbers have been issued, to do this please use: S. Mallakpour, M. Dinari and M. Hatami, *RSC Adv.*, 2014, DOI: 10.1039/C4RA05754F.



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. This Accepted Manuscript will be replaced by the edited, formatted and paginated article as soon as this is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/advances

Modification of Mg/Al-layered double hydroxide with L-aspartic acid containing dicarboxylic acid and its application in enhancement of thermal stability of chiral poly(amide-imide)

Shadpour Mallakpou,*^{*a,b,c*} Mohammad Dinari^{*a,b*} and Masoud Hatami^{*a*}

s Received (in XXX, XXX) Xth XXXXXXX 20XX, Accepted Xth XXXXXXXX 20XX DOI: 10.1039/b000000x

In this study, Mg/Al-layered double hydroxide (LDH) was intercalated with diacid containing Laspartic acid in one step using ultrasonic method under green conditions. Organic diacid was used as modifier to enhance their compatibility and led to better dispersion of LDH nanoclay in polymer ¹⁰ matrix. An effective intercalation of the examined diacid in LDH was confirmed by increasing in basal spacing of the obtained products in comparison with Mg/Al-CO₃²⁻ LDH precursors using Xray diffraction. An optically active poly(amide-imide) (PAI) was synthesized via polycondensation of *N*,*N*-(pyromellitoyl)-bis-phenylalanine diacid with 4,4-diaminodiphenylsulfone in molten tetrabutylammoniom bromide. The modified LDH (M-LDH) was used as a filler into the PAI ¹⁵ matrix and PAI/M-LDH nanocomposites containing 2, 4 and 8% of M-LDH were fabricated. Thermogravimetric analysis showed improvement in thermal stability and morphology investigations by field emission scanning electron microscopy and transmission electron microscopy displayed that M-LDH is dispersed in the PAI matrix.

20 1. Introduction

Aspartic acid is an α-amino acid with the chemical formula of HOOCCH(NH₂)CH₂COOH.¹ It was classified as an acidic amino acid and can be used in synthesis of polymers with relatively low molecular weight as well as high molecular weight with ²⁵ polycondensation reaction.² There are two enantiomers of aspartic acid and the name aspartic acid can refer to either enantiomer or a mixture of two of these two forms, one L-aspartic acid is a chosen amino acid which has been applied to the synthesize ³⁰ of fresh polymers due to its multifunctionality.³ D-aspartic acid is

- ³⁰ of fresh polymers due to its multifunctionality. D-aspartic acid is an internal amino acid, which has been found in nervous and endocrine texture of both invertebrates and vertebrates. Daspartic acid has a lot of applications in the chicken and rat brain, human and so on.⁴
- Layered double hydroxides (LDHs), known as hydrotalcite like compounds, have attracted attention, because of their layered structure and very high anion-exchange capacity.⁵ The structure of these compounds consists of positively charged brucite-like layers with interlayer space containing charge compensating ⁴⁰ anions and water molecule. The positive charges on the LDH
- surface are balanced by interlayer anions and water molecules.⁵⁻⁷ The general formula of LDHs is $[M^{2+}_{1-x} M^{3+}_{x}(OH)_2] A^{n-}_{x/n} .yH_2O$, where M^{2+} is a divalent metal ions such as Mg^{2+} , Ca^{2+} , Fe^{2+} , Co^{2+} and M^{3+} is a trivalent ions such as Al^{3+} , Fe^{3+} , Cr^{3+} , Mn^{3+} and

- ⁴⁵ Aⁿ⁻ is the exchangeable anion (often carbonate, chloride or nitrate).⁸⁻¹¹ Recently the synthesis, structure and properties of LDHs have been widely studied because of their potential applications in catalysts,¹² drug delivery,¹³ remove harmful oxyanions,¹⁴ adsorption of acid red from dye wastewater,¹⁵
 ⁵⁰ optics,¹⁶ biosensors,¹⁷ synthesis of highly efficient flame retardant nonocomposites (NCs),¹⁸⁻²³ and other areas. LDHs are also naturally abundant, readily synthesized at industrial scale, inexpensive and stable at high temperature (up to 500-600 °C) and pH conditions.²⁴
- ⁵⁵ In the last decade there has been considerable interest in polymer-LDH NCs due to their remarkably enhanced mechanical, thermal, electrical, magnetic and fire retardant properties.²⁵ These enhanced properties are mainly attributed to the dispersion of layered compounds within the polymer matrix. The use of LDHs ⁶⁰ as nanofillers has some limitations. The high charge density of LDH layers and the high content of anionic compounds and water molecules, result in strong interlayer interactions between the sheets and pronounced hydrophilic properties. Thus, monomer and or polymer cannot easily penetrate within the LDH layers and ⁶⁵ the homogeneously dispersed of LDH layers within the hydrophobic polymer matrix is difficult. To facilitate the intercalation of LDH within the polymer matrix and to gain a desirable degree of dispersion, the interlayer space should be modified with suitable and capable organic anions.²⁶⁻²⁸ Among

the numerous types of polymer structure, optically active polymers offer a number of advantages in terms of their thermal stability, chemical resistance and efficiency of binding.²⁹ Poly(amide-imide) (PAI) are known to have the property 5 advantages of both polyamides and polyimides such as high strength, good solubility in polar amide-type solvent, hydrogen bonding interaction and extensive chemical resistant, being a promising matrix candidate for hybrid materials.³⁰⁻³²

In this work, Mg/Al-LDH was modified with dicarboxylic acid 10 containing L-aspartic acid and tetrabromophthalic anhydride under ultrasound irradiation as green and safety technique via coprecipitation method in aqueous media. The product (M-LDH) was applied as filler with different percent's (2, 4 and 8 wt %) in the PAI matrix for the preparation of LDH/PAI NCs. Fourier 15 transform infrared (FT-IR), X-ray diffraction (XRD), field emission scanning electron microscopy (FE-SEM) and transmission electron microscopy (TEM) were used to study the morphological features and the nature of LDH particle dispersion in PAI matrix. The thermal features of the NCs were studied by 20 means of thermogravimetric analysis (TGA) to probe the effects of LDH nanoclay on the thermal stability of the resulting NCs.

2. Experimental section

2.1 Materials

Materials used in the synthesis of LDHs are aluminum nitrate 25 nonahydrate [Al(NO₃)₃. 9H₂O] and magnesium nitrate hexahydrate [Mg(NO₃)₂. 6H₂O] were purchased from Aldrich Chemical CO. (USA). Tetrabromophthalic anhydride (TBPA), tetrabutylammoniom bromide (TBAB), triphenyle phosphite dianhydride (TPP) and pyromellitic (benzene-1,2,4,5-30 tetracarboxylic dianhydride) (PMDA) were purchased from Merck Chemical CO. (Germany). Amino acids L-aspartic acid and L-phenvlalanine were used without more purification. The other solvents and materials were used as gained without further purification.

35 2.2 Apparatus

Jasco-680 (Japan) spectrophotometer was used for FT-IR analyses of the synthesized materials. Spectra of solid samples were obtained with KBr disk. The vibration transition frequencies are described in the range of 400-4000 cm⁻¹. The XRD patterns 40 were accumulated by using a Philips Xpert MPD X-ray diffractometer. The diffractograms were measured for 2θ , in the range of 5-80°, using a voltage of 40 kV and Cu Ka incident light $(\lambda=1.51418 \text{ A}^\circ)$. TGA data were obtained on a STA503 TA apparatus in an argon atmosphere by heating rate of 10 °C/min ⁴⁵ from room temperature to 800 °C. The dispersion morphology of the mixtures was detected using TEM (a Philips CM 120 operated, Netherlands) and FE-SEM (Hitachi, S-4160, Japan). The reaction was happened on a MISONIX ultrasonic liquid processor, XL-2000 series with a wave of frequency 2.25×10^4 Hz 50 and power 100 W.

2.3 Synthesis of biosafe diacid containing aspartic acid

L-aspartic acid containing diacid was synthesized according to the procedure reported by Tagle et al.³³ The mixed solution of 55 0.50 g (1.0 mmol) of TBPA, 0.15 g (1.1 mmol) of aspartic acid and 8 mL of acetic acid were prepared and 1 mL of pyridine was added into this solution. The mixed solution was stirred at room

temperature for 12 h and then the solution was refluxed at 120 °C for 12 h. The solvent was removed under reduced pressure and to 60 the residue, 50 mL of cold mixture of water and hydrochloric acid (10%) was added. The solution was then stirred for 2 h. A white

precipitate was formed, filtered off, and dried to give 0.58 g (89%) of aspartic acid containing diacid. melting point (m.p.) 267–269 °C, (Literature 265-267 °C),²⁷ $[\alpha]^{17}_{589}$ (N,N- $_{65}$ dimethylformamide) = +76 deg⁻¹g⁻¹cm³. FT-IR (KBr, cm⁻¹): 3433 (br), 2939 (m), 1779, 1725 (s, br), 1425 (m), 1389 (s), 1342 (s, m), 1292 (s), 1202 (s, w), 1119 (s), 1027 (w), 950 (s, br), 921 (br), 827 (w), 752 (s, m), 669 (s, m), 640 (s, m), 520 (s, w), 421 (s, w).

70 2.4 Synthesis of M-LDH via ultrasonic method

In this work M-LDH was prepared by the co-precipitation method under ultrasonic irradiation. The mixed solution of 0.50 g (2.0 mmol) of Mg(NO₃)₂. 6H₂O and 0.37 g (1.0 mmol) of Al(NO₃)₃. 9H₂O (molar ratio 2/1) was prepared in the 20 mL of 75 deionized water (solution A). On the other hand, 0.83 g (1.5 mmol) of L-aspartic based diacid and 0.12 g (3.0 mmol) of NaOH was dissolved in the 20 mL deionized water (solution B). Solution A was added into the solution B and stirred at room temperature for 3h. Then the pH of obtained suspension was ⁸⁰ adjusted to 10 by adding 1M NaOH. Finally the resulting product was sonicated for 1h and obtained precipitate filtered and washed by deionized water and then was dried at 60 °C for 24h. The $Mg/Al-CO_3^{2-}$ was synthesized by similar procedure without adding diacid molecule.

85 2.5 Synthesis of L-phenylalanine containing diacid

N,N-(Pyromellitoyl)-bis-L-phenylalanine monomer was prepared according to earlier study.34

2.6 Synthesis of chiral PAI

PAI was prepared according to the reported procedure in the 90 provirus work.³⁵ An optically active L-phenylalanine containing PAI was prepared by the polycondensation reaction of an equimolar mixture of 0.29 mmol of monomer 3 and 0.29 mmol of 4,4-diaminodiphenyle sulfone (diamine 4) in the 1.16 mmol of molten TBAB. After the reagents dissolved completely, 0.28 mL 95 of TPP was added and the reaction mixture was stirred for 12h at the 120 °C. The viscous and yellow solution was poured into 40 mL of methanol and the precipitate solid was filtered using Whatman filter paper. The inherent viscosity of the resulting polymer was 0.34 dL/g and the yield was 88%. The specific ¹⁰⁰ rotation was measured $\left[\alpha\right]_{D}^{25}$ =-134° (at a concentration of 0.5 g/dL in DMF at 25 °C), confirming the optical activity of this polymer.

2.7 Synthesis of PAI/M-LDH NCs

Different NC of PAI/M-LDH (2, 4 and 8 wt.%) were prepared by 105 following method. 0.1g of PAI was dispersed in the 8 mL ethanol and a uniform colloidal dispersion was obtained after sonication for 15 min (solution 1). Different percent's of M-LDH were dispersed in 8 mL of ethanol and was sonicated for 30 min (solution 2). Two solutions were mixed together at room 110 temperature and sonicated for 3h. After irradiation, the ethanol was removed and the obtained solid was dried in the room temperature for 24 h.

3. Result and discussions

Published on 29 August 2014. Downloaded by University of California - San Francisco on 02/09/2014 15:03:35.

3.1 Preparation of chiral diacid and M-LDH

L-Aspartic acid containing diacid was synthesized from the reaction of the TBPA and L-aspartic amino acid in refluxed acetic acid at the presence of pyridine as shown in Scheme 1.³³ This ⁵ diacid was used for organo-modification of Mg/Al-LDH by a simple and green method under ultrasonic irradiation. The

schematic of such an adsorption process between chiral diacid and Mg/Al-LDH is shown in Figure 1. The elementary reason for selecting Mg/Al based LDH is their typical metal hydroxide-like

¹⁰ chemistry and conventional clay-like layered crystalline structure which makes them appropriate for polymer NCs preparation and can progress their dispersion in polymer matrix. Mg/Al-LDH can't be easily dispersed in polymer matrix; this failure is due to the weak interactions between the polymer and the LDH. In fact,

¹⁵ the organic component of the organoclay increases interactions between the polymer and the M-LDH.



Scheme 1. Preparation of diacid from reaction between TBPA and aspartic acid



Figure 1. Intercalation of diacid in the interlayer of LDH

3.2 Synthesis of PAI

20

From a technological point of view, the use of an organic solvent ²⁵ in big scale preparation is not very friendly and highly polar conventional solvents such as *N*,*N*- dimethylformamide, *N*,*N*-dimethylacetamide, pyridine, *N*-methylpyrrolidone and chlorinated solvents which are used in polycondensation polymerizations are volatile and most of them are flammable, ³⁰ toxic, quite hazardous and harmful compared to ionic liquids.^{36,37} in this study, molten TBAB ionic liquid was selected because it proved to be the most valuable among those employed. Due to their nonvolatility, ionic liquid have a little effect on the environment and human health and so, they are known as green

- ³⁵ solvents due to their properties such as chemical stability, low to high viscosity, and high ionic conductivity properties.^{38,39} For the preparation of the polymer, first an optically active and bioactive dicarboxylic acid **3** was synthesized via the reaction of Lphenylalanine and PMDA in refluxing acetic acid solution
- ⁴⁰ (Scheme 2). Then PAI **5** was successfully synthesized by the polycondensation reactions of an equimolar mixture of **3** with aromatic diamines **4** in molten TBAB as an ionic liquid media and TPP which acted as activating agent in good yield and moderated inherent viscosity (Scheme 3). The obtained PAI which actuates a subject of the second state of the second
- ⁴⁵ displayed optical rotation, which showed that the polymer is optically active and chirality was introduced into the backbone of the polymer.



Scheme 2. Synthesis of *N*,*N*-(pyromellitoyl)-bis-L-phenylalanine ⁵⁰ monomer



Scheme 3. Synthesis of chiral PAI

3.3 Preparation of PAI/M-LDH NCs

PAI/M-LDH NCs were synthesized by a solution-intercalation ⁵⁵ method using ultrasound radiation. The organic anions containing the polar groups are intercalated in LDH interlayers and can allow anchoring of the polymeric unit onto LDH. The inorganic nanoparticles (hydroxide nanosheets) are randomly dispersed in the PAI matrix. The adsorption of PAI onto the surfaces of M-⁶⁰ LDH was presumed to occur through hydrogen bonding (Figure 2). Although, van der Waals forces between PAI matrix and M-LDH surface would also play an essential role in the overall adsorption process.



65 Figure 2. Synthesis of NCs of PAI and M-LDH

3.4.1 FT-IR

FT-IR spectroscopy has been mostly employed to study the structural accommodation of interlayer species and hydrogen bond network in LDH. FT-IR spectra of the LDH-CO₃²⁻, L-70 aspartic containing diacid and M-LDH are represented in Figure 3. For LDH-CO₃²⁻, the broad peak in the 3150-3500 cm⁻¹ is ascribed to the water molecules where the hydrogen bonding in the interlayer region between water molecules and the hydroxide sheet is obvious from shoulder at 3050-3100 cm⁻¹. The 75 asymmetric stretching of carbonate in the interlayer space of LDH was shown in the range 1350-1380 cm⁻¹. The strong band at 455 cm⁻¹ and the broad one at 651 cm⁻¹ are ascribed to the vibrations of metal oxides (Mg-O and Al-O), respectively. The FT-IR spectrum of diacid showed a broad and strong peak at $_{\rm 80}\ 2350\text{-}3650\ \text{cm}^{-1},$ which was assigned to the COOH groups and two absorption bands at 1779 and 1725 cm⁻¹, which are corresponding to the unsymmetrical and symmetrical stretching vibrations of imide C=O group. The adsorption peaks showed at 1389 and 752 cm⁻¹ region is related to the presence of the imide 85 heterocycle ring and showed peak in the 1119 cm⁻¹ due to the C-Br. FT-IR spectra for M-LDH shows the adsorption peaks at 1775 and 1720 cm⁻¹ related to the stretching vibration of C=O, at 1124 cm⁻¹ related to the C-Br and 1388 and 752 cm⁻¹ can be related to the imide C=O group in comparison with LDH-CO₃²⁻ 90 which may confirm the presence of diacid in the interlayer of LDH. Peak due to the carbonate anion (1378 cm^{-1}) is also observed, because the process was applied without N₂ atmosphere and CO₂ can be absorbed from the atmosphere during the process.



Figure 3. FT-IR spectra of (a) LDH-CO₃²⁻, (b) diacid and (c) M-LDH

Figure 4 shows the FT-IR spectra of the pure PAI and NCs of PAI with different amount of the M-LDHs. The FT-IR spectrum of PAI showed absorption peaks around 3360 cm⁻¹ (N–H), and ¹⁰ two overlapped carbonyl (amide and imide's C=O) absorptions at 1779, 1725, and 1663 cm⁻¹, respectively. Absorption at 1380 and 727 cm⁻¹ indicate the presence of the imide heterocycle in this polymer structure. Absorptions at 1251 and 1150 cm⁻¹ are due to the sulfone moiety (SO₂ stretching).³⁵ The spectra of the prepared ¹⁵ NCs clearly exhibit the characteristic absorption peaks corresponding to the polymeric groups, although some peak intensity may be changed. The new peaks showed in the range 400-600 cm⁻¹ are correspond to metal oxide (Mg-O and Al-O) in the NCs spectra. This result in sum confirmed the presence of M-²⁰ LDH nanoclay in the PAI matrix.





Figure 4. FT-IR spectra of PAI and NCs of PAI with different amount of ³⁵ the M-LDHs

3.4.2 X-ray diffraction

The XRD patterns are very valuable and main analytical technique for the characterization of LDHs and crystalline phases.⁴⁰ It is also used to determine the interlayer spacing and ⁴⁰ for the determination of the structure of layered samples. The XRD patterns of LDH-CO₃²⁻, M-LDH, NC4 and 8 wt% were shown in Figure 5. Before organic treatment, the basal spacing of the pure LDH, that is, LDH-CO₃²⁻ is 0.75 nm, which corresponds to the (003) diffraction peak with 2θ =11.84°.²⁸ After modified ⁴⁵ LDH with the diacid molecule, the X-ray reflections have been shifted to a lower angle position. The M-LDH displays a (003) diffraction peak at 2θ =7.87° corresponding to an interlayer distance of 1.12 nm. In conclusion, these increases in the interclayer distances show the intercalation of bigger anionic

- ⁵⁰ diacid functionalized between the LDH layers. The size of the guest diacid was estimated and compared to the obtained basal spacing via XRD patterns. Based on previous work, the thickness of LDH-CO₃²⁻ hydroxide sheets is 0.48 nm.¹⁰ The increase of interlayer distance in the M-LDH, calculated from the d003 spacing and thickness of the inorganic layer, is approximately 0.64 nm. This means that the anionic diacid are horizontally
- 0.64 nm. This means that the anionic diacid are horizontally oriented in the interlayer space (Figure 1), which are confirmed by the approximate molecule length diacid which were calculated by gauss view (Scheme 4).
- For PAI/LDH NCs (4% and 8%), the XRD patterns don't showed any peak for M-LDH in the samples. The only new broad and vast diffraction peak that appeared at $2\theta=17.70^{\circ}$ related to the PAI polymer matrix. In PAI/clay NCs, complete exfoliation of LDH results in disappearance of the diffraction maxima in their
- ⁶⁵ XRD patterns. Moreover, this can also happen due to other reasons, such as extremely low concentration of clay materials in the polymer matrix, crystal defects, etc. The high degree of exfoliation of the LDH clay layers in polymer NCs has also been reported using several studies.^{41,42} However, XRD analysis alone 70 is not adequate for proven of the dispersion in the polymer
- ¹ is not adequate for proven of the dispersion in the polymer matrix.

5

25

Published on 29 August 2014. Downloaded by University of California - San Francisco on 02/09/2014 15:03:35.



Figure 5. XRD patterns of LDH, M-LDH and NCs of PAI 4 and 8% of the M-LDHs

3.4.3 Thermal analysis

5 TGA is used to measure variations in the mass of LDH and evaluation of the content of water and anion molecules.³⁰ The TGA curves for LDH and M-LDH are shown in the Figure 6. Three mass-loss steps are noticed for LDH. The weight loss before 200 °C is recognized to the releasing of the physically 10 adsorbed water and water molecules around Mg and Al cations and the about 400 °C removal of water molecules by dehydroxylation process was showed. Third weight loss is related to the removal of the interlayer carbonate anions.¹⁰ For M-LDH the numbers of decomposition stages have enhanced. Diacid 15 modified LDH have similar mass-loss behavior before 400 °C. In comparison to LDH-CO32-, residual weight percent of the diacid intercalated LDH was decreased. Also the presence of a larger weight loss step within 410-540 °C for LDH-dicarboxylate anion compared to the LDH, confirmed the presence of interlayer 20 surfactant anions in LDH, because the presence of organic groups in the interlayer of M-LDH reduced the thermal stability of the



Figure 6. TGA curves for LDH and M-LDH

- Figure 7 shows the thermal decomposition of neat PAI and PAI/M-LDH NCs with different contents of M-LDH and resulting TGA data are summarized in Table 1. The thermal stability of the PAI and PAI/M-LDH NCs was studied on the basis of 5 and 10% weight losses (T_5 and T_{10} , respectively) of the 30 samples and the char yield (residue weight at 800 °C). The initial decomposition temperatures of the NCs with different M-LDH percent (2, 4 and 8 %) were over 315°C, which can be related to the decomposition of pristine polymer matrix.³⁵ According to the Table 1, T₅, T₁₀ and char yield for NCs with different M-LDH 35 content are higher than of pure PAI. It is clear that the PAI/M-LDH materials improved thermal properties due to the incorporation of M-LDH. The improvement of thermal property of PAI/M-LDH NCs can be attributed to the homogeneous dispersion of M-LDH nanoclay in polymer matrix and the strong 40 hydrogen bonding between O-H groups on the surface of M-LDH and nitrogen atoms or carbonyl group of PAI matrix. Char yield can be applied as a crucial factor for estimating limiting oxygen index (LOI) of the polymers based on Van Krevelen and Hoftyzer
 - $_{45}$ LOI = 17.5+ 0.4 CR

equation.43

Where CR = char yield. According to this equation, LOI values calculated based on their CR at 800 °C were higher than 30, showing that such macromolecules can be classified as self-extinguishing polymers.



Figure 7. TGA curve of PAI and NCs of PAI with different amount of the M-LDHs

 Table 1. The data obtained from TGA thermogram of PAI and PAI/M-LDH NCs

Sample	T ₅ (T ₁₀ (^o C) ^a	Char yield (%) ^b	LOI
	°C) ^a			
PAI	289	349	39.00	33.10
PAI/M-LDH 2%	316	379	41.23	33.99
PAI/M-LDH 4%	342	382	42.42	34.46
PAI/M-LDH 8%	342	400	46.46	36.08

55 ^a Temperature at which 5 and 10% weight loss was recorded by TGA at heating rate of 10 °C/min under a nitrogen atmosphere

^b Weight percentage of material left undecomposed after TGA analysis at a temperature of 800 °C under a nitrogen atmosphere

3.4.4 Morphological analysis by electron microscopy

FE-SEM and TEM provide beneficial and crucial images of textural and crystal morphologies of LDH intercalated materials. LDH generally shows a hexagonal platelet morphology.²⁷ The ⁵ FE-SEM images of LDH-CO₃²⁻ and M-LDH with different magnification are showed in the Figure 8. The LDH displayed the nature of LDH particles, which roughly contained of plate-like shapes with lateral dimensions and thickness ranging over few nanometer (Figures 8a and 8b).The FE-SEM images for M-LDH ¹⁰ showed formation of plate-like nanoparticles with regular shape, as commonly observed for the typical organic anionic intercalated LDH compounds. The layer nanoparticles have a diameter over a few hundred nanometers and a thickness over several tens of nanometers (Figures 8c and 8d).



Figure 8. FE-SEM images of (a, b) LDH-CO₃²⁻ and (c, d) M-LDH

The FE-SEM micrograph for neat PAI and NCs with different percent represent in the Figure 9. The morphology of neat PAI seems to be smooth relatively (Figures 9a and 9b). After ²⁰ modification of PAI with M-LDH the surface morphology of the NCs is changed and the micrograph showed uniform distribution and excellent dispersion of M-LDH into the PAI matrix (Figures 9c-9f). These observations are perhaps a result of modification of LDH with diacid. TEM shows a real image of nanoclay platelets ²⁵ to allow identification of internal morphology and hybrid structure of NCs. In Figures 10a and 10b, TEM images of LDH-CO₃²⁻ showed and the synthesized LDH-CO₃²⁻ are smooth, wellshaped in a hexagonal form, crystalline and don't showed any aggregated platelets. After modification of LDH with L-aspartic

³⁰ containing diacid, the expected plate-like nature of the crystallites and hexagonal structure is clearly apparent and there are no signs of aggregation visible in the micrographs (Figures 10c and 10d). Figures 10e and 10f shows the TEM images of PAI/M-LDH NCs with 8 wt% of M-LDH. The TEM image showed that the LDHs ³⁵ are dispersed throughout the polymer matrix. The layers are well shown in this image and the thickness and lateral sizes of the LDH layers can be calculated as being about nanometric size.



Figure 9. FE-SEM images of (a, b) PAI (c, d) PAI/M-LDH NC 2% (e, f) PAI/M-LDH NC 4% and (g, h) PAI/M-LDH NC 8%



Fig. 10. TEM images of LDH-CO $_3^{2-}$ (a, b), M-LDH (c, d) and PAI/M-45 LDH NC 8% (e, f)

4. Conclusions

LDH was modified with diacid containing TBPA and aspartic acid by co-precipitation method through applying the ultrasonic irradiation as green, easy and safety tool. The increase in basal 50 spacing of M-LDH in comparison to the LDH, showed by XRD analyses, indicated an intercalation of bigger organic anions into the LDH interlayer space. Polycondensation reaction of chiral diacid with solfonated diamin furnished a chiral PAI, due to Lphenylalanine amino acid in the polymer structure. LDH 55 nanoclay modified with organic diacid as a bifunctional coupling agent was used to enhance the compatibility between PAI matrix and LDHs. The morphology and textural of NCs was study by FE-SEM and TEM techniques and the results showed well dispersed and formation of intercalated and or exfoliated 60 modified LDH platelets in the PAI matrix. Thermal properties increase for NCs in the presence of M-LDH due to the hydrogen bonding between the M-LDH nanoclay and the PAI matrix.

15

Published on 29 August 2014. Downloaded by University of California - San Francisco on 02/09/2014 15:03:35.

Acknowledgments

We wish to sincerely thank the Research Affairs Division Isfahan University of Technology (IUT), Isfahan, for the financial 5 support of this work. Further financial support from National Elite Foundation (NEF), and Iran Nanotechnology Initiative Council (INIC) is gratefully acknowledged.

Notes and references

- ^aOrganic Polymer Chemistry Research Laboratory, Department of 10 Chemistry, Isfahan University of Technology, Isfahan, 84156-83111, I. R. Iran. FAX: +98-311-391-2350, Tel; +98-311-391-3267; E-mail:
- mallak@cc.iut.ac.ir,mallak777@yahoo.com, mallakpour84@alumni.ufl.edu (Shadpour Mallakpour).
- ^bNanotechnology and Advanced Materials Institute, Isfahan University of 15 Technology, Isfahan, 84156-83111, I. R. Iran. FAX: +98-311-391-2350, +98-311-391-3267; E-mail: Tel: mallak@cc.iut.ac.ir, mallak777@yahoo.com, mallakpour84@alumni.ufl.edu (Shadpour Mallakpour).
- ^cCenter of excellent in sensor and green chemistry, Department of 20 chemistry, Isfahan University of Technology, Isfahan 84156-83111, Islamic Republic of Iran, e-mail: mallak@cc.iut.ac.ir; mallak777@yahoo.com; mallakpour84@alumni.ufl.edu
- C. Liebecq, K. L. Loening, G. P. Moss, J. Reedijk, S. L. Velick and J. 25 F. G. Vliegenthart, Pure Appi. Chem., 1984, 56, 595-624
- 2 M. Tomida, T. Nakato, S. Matsunami and T. Kakuchi, Polymer, 1997, 38, 4733-4736
- 3 M. R. Vakili and N. Rahneshin, Carbohydr. Polym., 2013, 98, 1624-1630
- 30 4 G. Macchia, E. Topo, N. Manganoc, E. D. Aniello and R. Boni, Animal. Reproduction. Sci., 2010, 118, 337-343
 - 5 L. Tammaro, V. Vittoria and V. Bugatti, Eur. Polym. J., 2014, 52, 172-180
- S. Mallakpour and M. Dinari, Prog. Org. Coat., 2014, 77, 583-589. 6
- J. P. Cheng, J.H. Fang, M. Li, W. F. Zhang, F. Liu and X. B. Zhang, 35 7 Electrochim. Acta, 2013, 114, 68-75

P. Guerrero-Urbaneja, C. Garcia-Sancho, R. Moreno-Tost, J. Merida-Robles, J. Santamaria-Gonzalez, A. Jimenez-Lopez and P. Maireles-Torres, Appl. Catal., A, 2014, 470, 199-201

40 9 Z. Huang, P. Wu, B. Gong, Y. Lu, N. Zhu and Z. Hu, Appl. Surf. Sci., 2013 286 371-378

10 S. Mallakpour, M. Dinari and V. Behranvand, RSC Adv., 2013, 3, 23303-23308

11 K. Klemkaite, I. Prosycevas, R. Taraskevicius, A. Khinsky and A. 45 Kareiva. Cent. Eur. J. Chem., 2011, 9, 275-282

12 J. M. Hidalgo, J. S. Cesar and R. R. Jose, Appl. Catal., A, 2014; 470: 311-317

13 L. Alberto de Sousa Rodriguesa, A. Figueiras, F. Veiga, R. Mendes de Freitas, L. C. C. Nunesa, E. Cavalcanti da Silva Filho and C. M. da 50 Silva Leite, Colloids Surf., B, 2013, 103, 642-651

14 K. H. Goh, T. T. Lim and Z. Dong, Water Res., 2008, 42, 1343-1368

15 T. Xue, Y. Gao, Z. Zhong, A. Umar, X. Yan, X. Zhang, Z. Guo and Q. Wang, J. Alloys. Compd., 2014, 587, 99-104

16 S. Y. Ryu, M. Yoon, J. H. Choy, S. H. Hwang, A. Frube, T. Asahi 55 and et al, Bull. Korean Chem. Soc., 2003, 24, 446-452

17 F. T. Zhang, X. Long, D. W. Zhang, Y. L. Sun, Y. L. Zhou, Y. R. Ma, L. M. Qi and X. X. Zhong, Sens. Actuators, B, 2014, 192, 150-156

18 C. Nyambo, P. Songtipya, E. Manias, M. M. Jimenez-Gascoc and C. A. Wilkie, J. Mater. Chem., 2008, 18, 4827-4838

- 60 19 Y. Gao, Q. Wang, J. Wang, L. Huang, X. Yan, X. Zhang, Q. He, Z. Xing and Z. Guo, ACS Appl. Mater. Interface., 2014, 6, 5094-5104
- 20 Q. wang, J. Wu, Y. Gao, Z. Zhang, J. Wang, X. Zhang, A. Umar, Z. Guo and D. O'Hare, RSC Adv., 2013, 3, 26017-26024
- 21 Y. Gao, J. Wu, Z. Zhang, R. Jin, X. Zhang, X. Yan, A. Umar, Z. Guo 65 and Q. Wang, J. Mater. Chem. A, 2013, 1, 9928-9934
- 22 Q. Wang, X. Zhang, J. Zhu, Z. Guo and D. O'Hare, Chem. Comm., 2012, 48, 7450-7452
- 23 Q. Wang, X. Zhang, C. J. Wang, J. Zhu, Z. Guo, and D. O'Hare, j. Mater. Chem., 2012, 22, 19113-19-121
- 70 24 F. L. Theiss, S. J. Couperthwaite, G. A. Ayoko and R. L. Frost, J. Colloid Interface Sci., 2013, 402, 114-121
- 25 N. Muksing, R. Magaraphan, S. Coiai and E. Passaglia, Express Polym. Lett., 2011, 5 428-448
- 26 Z. Matusinovic, H. Lu and C. A. Wilkie, Polym. Degrad. Stab., 2012, 75 97, 1563-1568
- 27 F. Leroux, L. Meddar, B. Mailhot, S. Morlat-Theriasb and J. L. Gardette, Polymer, 2005, 46, 3571-3578
- 28 N. H. Huang and J. Q. Wang, Express Polym. Lett., 2009, 3, 595-604
- 29 S. Mallakpour and M. Hatami, Polym. Plast. Technol. Eng., 2012, 51, 80 1106-1112
 - 30 S. Mallakpour and M. Zarei, J. Reinf. Plast. Compos., 2012, 32, 574-582
 - 31 Z. Hu, S. Li and C. Zhang, J. Appl. Polym. Sci., 2007; 106: 2494-501
- 32 S. Mallakpour, M. Iderli, M. R. Sabzalian, Designed Monomers 85 Polym., 2013, 16, 509-514
 - 33 L. H. Tagle, C. A. Terraza, A. Tundidor-Camba and J. Soto-Salamanca, Polym. Bull., 2014, 71, 287-300

34 S. Mallakpour and M. Dinari, J. Macromol. Sci. Part A: Pure Appl. Chem., 2011, 48, 644-679

- 90 35 S. Mallakpour and M. Dinari, Polymer, 2011, 52, 2514-2523
 - 36 S. Mallakpour, M. Zarei, J. Reinf. Plast. Compos., 2012, 32, 574-582
 - 37 S. Mallakpour and M. Dinari, Iran. Polym. J., 2010, 19, 983-1004
 - 38 S. Mallakpour, M. Dinari, Amino Acids, 2013, 44, 1021-1029
 - 39 S. Mallakpour and M. Dinari, Iran. Polym. J., 2011, 20, 259-279
- 95 40 M. Silion, M. I. Popa, G. Lisa and D. Hritcu, Rev. Roum. Chim., 2008, 53, 827-831.

41 W. Cui, Q. Jiao, Y. Zhao, H. Li, H. Liu and M. Zhou, Express Polym Lett, 2010, 6, 485-493

42 I. Brnardic, Z. Matusinovic, J. Sipusic and J. Macan, Polymeri, 2012, 100 33. 52-57

43 D. W. Van Krevelen and P. J. Hoftyzer, Elsevier Scientific Publishing, New York, 3rd ed., 1976