Facile preparation of $ZnO:g-C_3N_4$ heterostructures and their application in amiloride photodegradation and CO_2 photoreduction

Nailma de Jesus Martins, Isabel C.H. Gomes, Gelson T.S.T. da Silva, Juliana A. Torres, Waldir Avansi, Jr., Caue Ribeiro, Andréa R. Malagutti, Henrique A.J.L. Mourão

PII: S0925-8388(20)33162-5

DOI: https://doi.org/10.1016/j.jallcom.2020.156798

Reference: JALCOM 156798

To appear in: Journal of Alloys and Compounds

Received Date: 13 April 2020

Revised Date: 22 July 2020

Accepted Date: 18 August 2020

Please cite this article as: N. de Jesus Martins, I.C.H. Gomes, G.T.S.T. da Silva, J.A. Torres, W. Avansi Jr., C. Ribeiro, André.R. Malagutti, H.A.J.L. Mourão, Facile preparation of ZnO:g-C₃N₄ heterostructures and their application in amiloride photodegradation and CO₂ photoreduction, *Journal of Alloys and Compounds* (2020), doi: https://doi.org/10.1016/j.jallcom.2020.156798.

This is a PDF file of an article that has undergone enhancements after acceptance, such as the addition of a cover page and metadata, and formatting for readability, but it is not yet the definitive version of record. This version will undergo additional copyediting, typesetting and review before it is published in its final form, but we are providing this version to give early visibility of the article. Please note that, during the production process, errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

© 2020 Published by Elsevier B.V.



CRediT author statement

Nailma de Jesus Martins: Conceptualization, Methodology, Investigation, Writing - Original Draft.

Isabel C. H. Gomes: Methodology, Investigation.

Gelson T. S. T. da Silva: Conceptualization, Methodology, Investigation, Writing - Original Draft.

Juliana A. Torres: Conceptualization, Methodology, Investigation, Writing - Original Draft.

Waldir Avansi, Jr.: Conceptualization, Methodology, Investigation, Resources, Writing - Original Draft.

Caue Ribeiro: Conceptualization, Supervision, Resources, Funding acquisition, Writing - Original Draft.

Andréa R. Malagutti: Conceptualization, Supervision, Resources, Writing - Original Draft.

Henrique A. J. L. Mourão: Conceptualization, Methodology, Resources, Writing - Original Draft, Supervision, Funding acquisition, Project administration.

Facile preparation of ZnO:g-C₃N₄ heterostructures and their application in amiloride photodegradation and CO₂ photoreduction

Nailma de Jesus Martins^{a,b*}; Isabel C. H. Gomes^b; Gelson T. S. T. da Silva^c; Juliana A.

Torres^c; Waldir Avansi Jr.^d; Caue Ribeiro^c; Andréa R. Malagutti^e; Henrique A. J. L.

Mourão^{a,b,**}

^a Chemistry Postgraduate Program (PPGQ), Federal University of Jequitinhonha and Mucuri Valleys (UFVJM), MGT 367 Highway – Km 583, CEP 39100-000, Diamantina, MG, Brazil.

^b Institute of Science and Technology (ICT), Federal University of Jequitinhonha and Mucuri Valleys (UFVJM), MGT 367 Highway – Km 583, CEP 39100-000, Diamantina, MG, Brazil.

^c Nanotechnology National Laboratory for Agriculture (LNNA), Embrapa Instrumentation, Zip Code 13560-970, São Carlos, SP, Brazil.

^d Department of Physics, Federal University of São Carlos (UFSCar), 13565-905, São Carlos, SP, Brazil

^e Department of Pharmacy (DEFAR), Federal University of Jequitinhonha and Mucuri Valleys (UFVJM), MGT 367 Highway – Km 583, CEP 39100-000, Diamantina, MG, Brazil.

* Corresponding author: nailmajanauba@gmail.com

** Corresponding author: henrique.mourao@ict.ufvjm.edu.br

Abstract

Semiconductor heterojunctions are interesting strategies for the development of efficient photocatalysts. In this paper we report the synthesis of ZnO:g-C₃N₄ heterostructures with different percentages of g-C₃N₄ (15%, 50% and 85%) using an easy and new method: precipitation of ZnO by alkaline solution at room temperature on g-C₃N₄ surface. The nucleation of ZnO nanoparticles had effective interaction on the g-C₃N₄ surface, showing good crystallinity and uniformity, which improved the heterostructure stability and the separation of photogenerated charge carriers, consequently increasing the photocatalytic efficiency for both the degradation of the amiloride (AML) drug and the conversion of CO₂ into products such as CO, CH₄ and C₂H₄.

Keywords: Sol-gel synthesis; zinc oxide; graphitic carbon nitride; heterostructure; photodegradation; CO₂ photoreduction.

1. INTRODUCTION

Investigations on photocatalytic materials have been carried out to show their importance in different topics, including environmental remediation (i.e. oxidation of organic compounds) and new energy production (i.e. H₂ evolution from water and CO₂ photoreduction into hydrocarbons) [1,2]. Semiconductors are considered promising materials for such applications since their electronic and structural properties allow the charge transfer and the generation of reactive species responsible for oxidation-reduction reactions in the heterogeneous medium [3]. The conversion efficiency of these processes depends essentially on the light absorption capacity, the generation and separation of photogenerated charge carriers, the adsorption and diffusion of molecules, among others [4,5]. However, a clear understanding of these properties–the oxidative and reductive capacity of semiconductors–and how they influence each process is still a matter of study, essential for the suitable design of future catalysts according to the intended application.

Among several semiconductors, zinc oxide (ZnO) has been widely studied for photocatalysis application due to its several excellent properties [6]. Nevertheless, this oxide is traditionally synthesized by thermal processes, either at high temperatures (above the ambient temperature) or high pressure, in order to obtain the crystalline phase [7–9]. These conditions not only make the synthetic process more complex and costly, but also can decrease the specific surface area that is essential for catalysis. However, to the best of our knowledge, synthetic methods at ambient temperature for the crystalline ZnO is still little explored in the literature.

The use of ZnO as photocatalyst under prolonged light irradiation can promote its photocorrosion. In addition, for being an amphoteric oxide, ZnO can suffer acid-base chemical reactions in drastic values of pH, either under alkaline or acid conditions [10,11]. These two effects can decrease the effectiveness of the reaction due to ZnO dissolution in the reaction medium by chemical or photocorrosion mechanisms. Therefore, these barriers must be overcome to increase its photocatalytic efficiency. In this light, the coupling of ZnO with other semiconductors appears as a promising alternative [12,13].

The graphitic carbon nitride, g-C₃N₄, is an organic semiconductor widely studied in photocatalytic processes due to its good stability and band gap (2.7 eV) [14–17]. However, in most cases it is coupled to another semiconductor because of its high electron/hole recombination rate, forming heterojunctions. This coupling is responsible for the stabilization of the metal or oxide and the increase in the solar radiation absorption, thus favoring a reaction direction. Although heterojunctions between ZnO and g-C₃N₄ are not new [18–20], there is an increasing necessity for more studies related to methods of impregnation under milder reaction conditions, which can provide good migration of photogenerated charges as a result of the efficient nucleation of ZnO nanoparticles without any loss of surface properties, for instance. Futhermore, the development of simple, efficient and low-cost methods for the synthesis of heterostructures with high stability and photocatalytic properties, especially under visible-light or solar irradiation, can contribute to the consolidation of the use of heterogeneous photocatalysis on a large scale.

Therefore, we describe herein a facile method to synthesize $ZnO:g-C_3N_4$ heterostructures with different proportions in mass of $g-C_3N_4$ (15%, 50% and 85%). The synthesized heterostructures were characterized by several techniques and applied for the photodegradation of amiloride and the photoreduction of CO₂.

2. EXPERIMENTAL SECTION

2.1. Materials preparation

The reagents used to prepare the materials were zinc acetate (ISOFAR), melamine (Sigma-Aldrich) and sodium hydroxide (Synth). All reagents were used without further purification.

Firstly, pristine materials were synthesized. The ZnO was prepared by a facile method based on sol-gel hydrolysis as follows: in a typical procedure, a sodium hydroxide solution (1.0 mol L⁻¹) was added to the zinc acetate aqueous solution (0.10 mol L⁻¹) under vigorous stirring until pH=10, resulting in a white precipitate. After that, the as-formed precipitates were filtrated, washed with deionized water and isopropyl alcohol several times and dried in air at 75 °C. The pristine g-C₃N₄, denoted as CN, was obtained by thermal polycondensation of melamine at 550 °C for 2 h in a conventional furnace in the air atmosphere [21].

The ZnO:g-C₃N₄ heterostructures were synthesized by a simple procedure, as subsequently described. The as-synthesized g-C₃N₄ was dispersed in a zinc acetate aqueous solution at about 0.10 mol L⁻¹, and then a hydroxide sodium solution (1.0 mol L⁻¹) was added under vigorous stirring until pH=10. Then, the suspensions were also washed and dried at the same conditions of the pure ZnO to produce the powder samples. To obtain heterostructures with different mass contents of ZnO and g-C₃N₄, the synthetic procedure was performed with 15%, 50% and 85% of g-C₃N₄. These samples were referred to as ZnO:CN_{15%}, ZnO:CN_{50%}, and ZnO:CN_{85%}, respectively.

2.2. Materials characterization

X-ray diffraction (XRD) patterns were obtained with an XRD 6000 diffractometer (CuKa radiation) at a scanning speed of 2°/min in the 20 range from 10° to 90°. The crystallite sizes were calculated using Scherrer's equation [22]. TG-DTA measurements were carried out on a TGA Q500 thermal analyzer (TA Instruments, New Castle, DE) under airflow at a heating rate of 10 °C min⁻¹ at temperatures varying from room temperature to 700 °C. Fourier transform infrared (FTIR) spectra were obtained from 400 to 4000 cm⁻¹ using a VARIAN 640-IR FT_IR Spectrometer in ATR mode. The images of field emission gun scanning electron microscopy (FEG/SEM) were obtained using a JEOL JSM-6701F microscope. Energy dispersive X-ray spectroscopy (EDS) measurements were performed using an EDS Thermo-Noran equipped with a Si detector attached to the JEOL JEM 2010 microscope. Transmission electron microscopy was performed on a FEI Tecnai G2 F20 microscope. The values of specific surface area (SSA) were estimated according to the Brunauer-Emmett-Teller (BET) method, by using N₂ adsorption data obtained in Micromeritics ASAP-2020 equipment. Diffuse reflectance spectrometry (DRS) analyses were performed with a UV-vis Shimadzu UV-2600 spectrophotometer in the range of 300-700 nm. The band gap energy was estimated by using the Tauc equation from the x-axis intercept of the tangent lines of each curve, as described in a previous study [23].

The photocatalytic performances of the synthesized samples were analyzed in a photoreactor equipped with six fluorescent lamps placed on the top of the reactor with emission in the visible range. This photoreactor was connected to a heat exchanger that maintained the temperature at about 20 °C. Aqueous suspensions were obtained by the dispersion of 10 mg of each photocatalyst in 20 mL of aqueous solutions of the drug

amiloride (AML) at 10 mg L⁻¹. Before the photocatalytic test, the suspensions were previously kept in the dark for 12 h to achieve adsorption/desorption equilibrium. The decrease in the AML concentration was analyzed in a Double Beam spectrophotometer (Shimadzu UV 6300PC equipment) at 285 nm in different periods. All measurements were performed in triplicate. The stability of the synthesized photocatalyst (ZnO:CN_{50%}) was evaluated by performing three recycling experiments with cycles of 260 min each under visible-light irradiation, a total of 780 min (13 h) of catalysis process. The main active species in the photocatalytic degradation process was also investigated. The hydroxyl radical (·OH), hole (h^+) and electron (e^-) were trapped with isopropyl alcohol (20 mmol L⁻¹), potassium bromide (10 mmol L⁻¹) and sodium oxalate (10 mmol L⁻¹), respectively.

The CO₂ photoreduction was performed in a cylindrical steel reactor covered with borosilicate glass with a total volume of 240 mL. Briefly, 0.1 g of catalyst was suspended in 100 ml of distilled water. To remove unwanted gases (O₂ and N₂) inside the reactor, CO₂ was bubbled in the reactor for 20 min in the flow of 20 mL min⁻¹. At the top of the reactor, a 5 W UVC lamp (Philips) with maximum length of 254 nm was inserted, protected by a quartz capsule. The photocatalytic performance of all synthesized materials was monitored for 6 h, and after this period the gaseous and liquid products were collected with a syringe and injected into specific chromatograph equipment. The gaseous products were determined by gas chromatography (Varian, CP-3800). Assays without catalyst were performed to evaluate the photolysis effect and correct the total product formation by photocatalysis.

3. RESULTS AND DISCUSSION

3.1. Characterization of the synthesized materials

Fig. 1 shows the X-ray diffraction (XRD) patterns of all synthesized materials: the pristine compounds (ZnO and g-C₃N₄) and the heterostructures with different mass contents of ZnO and g-C₃N₄. All diffraction peaks of the ZnO sample are well defined and intense, suggesting that the treatment with sodium hydroxyl at ambient temperature was sufficient to obtain a material with good crystallinity. Such peaks can be indexed to the hexagonal würtzite phase of ZnO [JCPDS n° 36-1451]. The g-C₃N₄ pattern shows two peaks at 20 equal to 13° and 27°, which can be attributed to the crystallographic (100) and (002) planes of the graphitic carbon nitride phase [JCPDS n° 87-1526]. These observed peaks are related to an in-plane structural packing motif, such as the hole-tohole distance of the nitride pores in the crystal and the planar graphitic interlayer distance of g-C₃N₄, respectively [24]. In the crystallographic pattern of the synthesized compounds with different amounts of ZnO and g-C₃N₄ we can observe peaks with different intensities, indicating that those related to ZnO become more evident when the oxide amount is increased, as expected.

The preferred position for Fig. 1

Table 1 shows the values of the crystallite size of the ZnO phase calculated according to the diffraction peaks of the (100), (002) and (101) planes, and the values of specific surface area (SSA) of the synthesized samples. It seems that ZnO preferably grows in one particular direction since the crystallite sizes perpendicular to the (002) planes were the highest for each sample containing ZnO (ZnO, ZnO:CN_{15%}, ZnO:CN_{50%}, and ZnO:CN_{85%}). In addition, the CN sample and the heterostructures (containing g-C₃N₄ and ZnO) showed higher SSA than the ZnO.

The preferred position for Table 1

The synthesized materials were also characterized by TGA, as shown in Fig. 2 a,b. Thermogravimetric analysis was used to estimate the amount of $g-C_3N_4$ in the heterostructures since this compound is thermally degraded above 500 °C (see Fig. 2b) under air condition and ZnO is practically stable in this range, losing only 5% of its total mass (see Fig. 2a). The thermogravimetric curves reveal that the pristine ZnO has a small weight loss at low temperatures when heat-treated up to 700 °C, which can be associated with the release of water molecules adsorbed on the material surface [25]. The same contribution was expected in the thermogravimetric results of the synthesized heterostructures, whose curves show that the expected amounts of $g-C_3N_4$ were very close to those obtained, demonstrating that the method was efficient to obtain the proportions 85%, 50% and 15%, as seen in Fig. 2a.

On the other hand, in Fig. 2b we can better observe in the derivative weight loss curves that the heterostructures synthesized with $g-C_3N_4$ suffered thermal decomposition of $g-C_3N_4$ at lower temperatures than the pristine $g-C_3N_4$ sample. Our previous studies already demonstrated a worse thermal stability of $g-C_3N_4$ in the presence of metal oxides or their precursors [21]. This effect is possibly related to the influence of Zn sites on the thermal decomposition of $g-C_3N_4$. It is known that metals in thermal reactions with $g-C_3N_4$, or even its precursors, can catalyze its decomposition reactions. Even though this effect can be seen in the ZnO: $CN_{15\%}$ and ZnO: $CN_{85\%}$ samples, it is more intense in the ZnO: $CN_{50\%}$, suggesting that its better distribution (i.e. higher ZnO and $g-C_3N_4$ contact) could increase the degradation to a maximum; such distribution appears to be lower in the ZnO: $CN_{85\%}$ sample due to its low ZnO content. Additionally, the low amount of $g-C_3N_4$ in the ZnO: $CN_{15\%}$ sample might have influenced the reduction of the decomposition temperature.

The preferred position for Fig. 2

Fig. 3 shows the FTIR spectra obtained from all the synthesized samples and precursors (melamine and zinc acetate). The spectrum of the pristine ZnO has few peaks, which are attributed to the hydroxyl groups connected to the ZnO surface (3400 cm⁻¹), the Zn-O vibrations at 450 cm⁻¹ and the precursor (zinc acetate) residues (1565-1438cm⁻¹) [25]. However, it is important to note that the quantity of residues is probably the same in all samples, not compromising future performances. From the melamine spectrum, it is possible to observe the presence of vibrational modes attributed to the CN bond (1500-1430 cm⁻¹), the NH bond of the amine group (-NH₂) (3500-3000 cm⁻¹) and 1650-1600 cm⁻¹) and the deformation of the triazine ring (808 cm⁻¹) [26]. Many of these vibrational modes can be visualized in the g-C₃N₄ (CN sample) spectrum with the appearance of a broadband centered at approximately 3250 cm⁻¹ as a result of the thermal polymerization of triazine rings and the formation of OH groups. The same profile was exhibited for all the synthesized heterostructures, yet with a single difference: the signal at 808 cm⁻¹ decreased as the ZnO amount increased, demonstrating that the presence of g-C₃N₄ or its exposure on the surface of the materials was reduced. Besides this, the intensity of the band in the range between 3600-2750 cm⁻ ¹ refers to O-H and N-H vibrations (convoluted peak). This is better visualized in the ZnO:CN_{85%} sample, where the N-H vibrations are more significant and indicate a slight shift of the sharper peak. Therefore, the higher intensity presented by the $ZnO:CN_{50\%}$ sample can be probably explained by the greater contributions of both shifts, i.e., the O-H vibration is mainly caused by the presence of ZnO, while the N-H vibration mostly appears as a result of the presence of $g-C_3N_4$.

The preferred position for Fig. 3

Fig. 4 shows the UV-vis spectra obtained from DRS measurements of the synthesized materials. Both pristine $g-C_3N_4$ and ZnO have photoabsorption under visible and UV lights, respectively, which is consistent with previous reports [9,27]. On the other hand, all spectra of the synthesized heterostructures showed that the ZnO: $g-C_3N_4$ heterostructures have absorption in the visible-light region. In addition, the band gap values decreased to a value similar to that found in the pristine $g-C_3N_4$, indicating that the presence of ZnO in the structure contributes poorly to the optical properties of the synthesized heterostructures.

The preferred position for Fig. 4

The morphology of the synthesized samples can be seen in Fig. 5. The SEM micrograph of the pristine g-C₃N₄ (Fig. 5a) demonstrates that the synthesized powder has the typical lamellar agglomerate morphology [21]. The SEM image of the ZnO sample (Fig. 5b) shows irregular rod-like particles with micrometric lengths and hexagonal base of approximately 100 nm, as seen in the inset of Fig. 5b. In contrast, the representative image of the ZnO: $CN_{50\%}$ sample (Fig. 5c) reveals the existence of irregular rod-like particles and lamellar materials, indicating the presence of ZnO and g- C_3N_4 , respectively. Besides that, the inset of Fig. 5c also suggests that the synthesis method effectively caused good nucleation of ZnO particles on the g- C_3N_4 surface, producing an intimate contact between them, consequently resulting in the formation of heterojunctions between the semiconductors.

A representative TEM image of the ZnO: $CN_{50\%}$ sample (Fig. 5d) reveals the existence of two distinct morphologies: lamellar and spherical/hexagonal nanomaterials. The HRTEM image (Fig. 5e) confirms that the spherical/hexagonal nanostructures are related to the ZnO hexagonal wurtzite since it showed an interlayer distance of 0.25 nm,

which can be assigned to (101) crystalline plane of this phase. In addition, Fig. S1 brings a representative EDS mapping analysis (b-d) from the region shown in Fig. S1a of the representative ZnO: $CN_{50\%}$ sample, which confirms the presence and coexistence of elements related to ZnO and g-C₃N₄, such as C, N, Zn and O. A good homogeneity in the distribution of g-C₃N₄ and ZnO particles can also be observed.

Therefore, according to our SEM, TEM and EDS results, it was possible to conclude that the ZnO rods consist of agglomerates formed by a large number of smaller ZnO nanoparticles sized between 5-20 nm. This behavior was already observed by different materials, such as BiVO₄, where a larger particle is composed of smaller particles [28]. We could also infer that the ZnO particles are attached to the g-C₃N₄, thus forming the ZnO:C₃N₄ heterostructures.

The preferred position for Fig. 5

3.2. Photocatalytic tests

3.2.1. Photo-oxidation properties

Fig. 6 displays the photodegradation curves of the amiloride (AML) drug under visible light. In addition, Table S1 shows the reaction rate constants (k_p) that were calculated using a pseudo-zero-order model [29]. In the presence of the synthesized materials, there was an improvement in the degradation of the AML solution compared to the photolysis process (negligible degradation), demonstrating that the such materials are promising catalysts in the oxidation of this drug. Also, the pristine semiconductors (ZnO and g-C₃N₄) showed poor activity compared to all synthesized heterostructures, degrading about 15% and 22% of AML, respectively. The low photocatalytic activity exhibited by these pristine materials was already expected as the tests were carried out under visible-light irradiation, and this spectral range is not sufficient to activate ZnO. It is worth mentioning that the g-C₃N₄ is known to have a high rate of recombination of photogenerated charge carriers [30]. Thus, the presence of g-C₃N₄ was crucial for the photoactivation under visible-light irradiation, and the coupling of ZnO with g-C₃N₄ was fundamental to improve the photocatalytic efficiency of the prepared heterostructures compared to the pristine materials. In addition, the ZnO:CN_{50%} sample had the best photocatalytic performance (about 53% of degradation), according to Fig. 6. In this way, these results suggest the formation of heterojunctions between the ZnO and g-C₃N₄ phases, which induces an increase in the separation of the photogenerated charges through charge transfer from g-C₃N₄ to ZnO, since the association of these phases showed a positive synergistic effect for the photodegradation process. In the intermediate proportion of each heterostructure component, i.e. 50% (ZnO:CN_{50%}), the number of heterojunctions is probably greater than in other samples, as the components (g-C₃N₄ and ZnO) tend to be more dispersed and less segregated.

The preferred position for Fig. 6

For being a fundamental characteristic of a good catalyst, especially in largescale processes, the stability of the synthesized photocatalyst with the best performance for AML degradation under visible light, ZnO: $CN_{50\%}$, was analyzed. In Fig. 7, we can see no significant deactivation of the analyzed photocatalyst after successive re-uses, demonstrating that the studied systems (ZnO:CN heterostructures) can be employed to stabilize ZnO in photocatalytic processes. This may be associated with the fact that apparently there was neither photo nor chemical corrosion with oxide, as the materials exhibited good photostability and good performance to degrade amiloride under visiblelight irradiation even after 13 h of use.

The preferred position for Fig. 7

To investigate the active species in the AML photodegradation driven by the ZnO:CN_{50%} heterostructure under visible light, some scavengers were added to the reaction, e.g., isopropyl alcohol (scavenger for the hydroxyl radical, \cdot OH), potassium bromide (scavenger for the electron e^{-}) and sodium oxalate (scavenger for the hole h^{+}) (Fig. 8). In this experiment, we observed that the sequestering agents added to the reactions fulfilled their role and decreased the AML degradation rate caused by the synthesized photocatalyst. With that in mind, it was demonstrated that all the photogenerated species participate in the AML degradation mechanism.

The preferred position for Fig. 8

Based on our results and several important studies regarding heterogeneous photocatalysis [18,20,31,32], we proposed a hypothetical mechanism (Fig. 9a) to illustrate the formation and migration of charges as well as the oxidation and reduction processes in the valence (VB) and conduction (CB) bands, respectively. First, due to the presence of g-C₃N₄ in a conventional type-II heterostructure, the heterostructures are photoactivated under visible-light irradiation–although they could also be activated by solar radiation. In this case, the ZnO is not photoactive because of its high value of band gap, making unfeasible the possibility of direct Z-scheme [33–35]. Second, there is the formation of oxidizing charges in the VB (h^+) and reducers in the CB (e) in the photoactived g-C₃N₄. The VB participates in the oxidation reactions, and the photogenerated electrons are first migrated to the CB of g-C₃N₄, and then transferred to the CB of ZnO. This charge transfer process is essential to decrease the charge carrier recombination and consequently increase the photocatalytic activity; this is the principle of a conventional type-II heterostructure. The charge generated (h^+) in the VB can act as a direct oxidizing agent and degrade the organic molecule, or oxidize water, generating hydroxyl radicals, species with a high oxidizing capacity. In other words, the degradation can occur indirectly by the oxidation of AML molecules through their interaction with the formed species (i.e. \cdot OH), or directly by their interaction with the generated charges, especially the direct oxidation of AML molecules by the holes originating from the BV of g-C₃N₄. This direct oxidation by holes can begin with the formation of AML radicals (\cdot AML⁺), responsible for subsequent reactions of the AML degradation. According to Fig. 8, the holes (h^+) contribute to the degradation of AML more than other species since they can participate in the formation of both \cdot OH and \cdot AML⁺. On the other hand, the electrons transferred to the CB of ZnO can reduce the molecular oxygen, forming the superoxide radical (\cdot O₂⁻), a species with a high oxidizing capacity that later oxidizes the organic molecules, or oxidizes water, also generating hydroxyl radicals.

The preferred position for Fig. 9

3.2.2. CO₂ photoreduction properties

The catalytic capacity of these materials (except the pristine ZnO) was also monitored with respect to the reduction of CO₂, a molecule responsible for several climatic changes. Fig. 10 shows the results of the photocatalytic reduction of CO₂ into CO, CH₄ and C₂H₄. The pristine ZnO did not have satisfactory results in relation to CO₂ conversion, because under experimental conditions this oxide is completely dissolved, as expected. It occurs due to acidic species (HCO₃⁻ and H₂CO₃) formed when CO₂ is dissolved in water, leading to ZnO instability, especially under irradiation. This effect was not observed in the experiments with other prepared samples (g-C₃N₄ and heterostructures), confirming the results observed in Fig. 7, where the use of g-C₃N₄ not only improved the activity of the synthesized materials, but also increased their photochemical stability in photocatalytic processes.

The preferred position for Fig. 10

From Fig. 10, it is possible to observe that the pristing $g-C_3N_4$ showed a moderate selectivity for CO formation after 6 h of reaction despite the fact that the observed CO production was low (0.56 µmol/g) compared to the other samples, demonstrating that the formation of heterojunctions with ZnO makes the materials more efficient due to the improved separation of photogenerated charge carriers [36]. It can also be noted that the ZnO: $CN_{85\%}$ sample (1.64 μ mol/g) exhibited a greater activity than the pristine $g-C_3N_4$, indicating that there is a tendency towards the improvement of such activity as a consequence of the presence of ZnO. This influence can be better observed in the ZnO:CN_{50%} sample, whose production was 12.73 µmol/g. However, when more ZnO (ZnO: $CN_{15\%}$) was added we could notice a drop in the production of CO (1.37 μ mol/g), suggesting that although ZnO is fundamental for the catalytic activity of the material an excessive amount can come to pile up the ZnO rods, agglomerating all of them in the same region. As a result, the interaction with $g-C_3N_4$ was reduced, causing a low sharing of photogenerated charges, consequently decreasing the lifetime of the electron/hole pairs. This decrease in the interaction with g-C₃N₄ can also lead to undesirable photo or chemical corrosion since the g-C₃N₄ surface used as a stabilizing agent will not be available for coupling.

Furthermore, the synthesized heterostructures showed good catalytic performance for the conversion of CO_2 into other products, such as CH_4 and C_2H_4 , as it can be seen in Fig. 10. The results demonstrate that the synthesized heterostructures (ZnO:CN_{15%}, ZnO:CN_{50%}, and ZnO:CN_{85%}) produced low amounts of C_2H_4 , which were

close to the detection limit of the equipment, making it difficult to analyze the results. However, it is possible to observe a trend of the ZnO: $CN_{50\%}$ sample (0.49 µmol/g) to be more effective than other samples (0.15 and 0.16 µmol/g for ZnO: $CN_{15\%}$ and ZnO: $CN_{85\%}$, respectively). The C₂H₄ production involves high energy to promote -CH₂ dimerization, low stability of the formed intermediates and successive number of steps that the specimens must undergo to form such product [37]. On the other hand, the CH₄ production showed that the low exposure of g-C₃N₄ did not affect the performance of the ZnO: $CN_{15\%}$ heterostructures (4.47 µmol/g) compared to 3.99 and 2.94 µmol/g for ZnO: $CN_{50\%}$ and ZnO: $CN_{85\%}$, respectively, indicating a moderate selectivity of the sample to ZnO catalytic sites.

Therefore, the good photocatalytic performance of the analyzed materials during the CO₂ conversion can be mainly attributed to: (i) the stability of ZnO promoted by the coupling with the g-C₃N₄ surface; and (ii) the formation of type-II heterostructures that favored the migration of the photogenerated charges and increased the reduction potential of the photocatalyst. It is important to highlight that the direct Z-scheme would be also possible considering that the CO₂ photoreduction tests were carried out under UV irradiation, which enables the photoativation of both semiconductors (ZnO and g-C₃N₄) [33–35]. This effect could positively influence the reduction potential of the heterostructure since the CO₂ reduction could occur in the CB of the g-C₃N₄ (Fig. 9b), which presents higher reduction potential than the BC of the ZnO.

4. CONCLUSIONS

Highly crystalline ZnO nanoparticles and ZnO: $g-C_3N_4$ heterostructures were successfully prepared by a facile method at controlled pH. The synthesized heterostructures showed distinct properties, such as visible light photoactivation,

chemical and photo stabilities, better separation of the photogenerated electron-hole pairs, among others. In general, the $ZnO:CN_{50\%}$ sample exhibited outstanding performance for both AML photodegradation and CO_2 reduction, especially with regard to CO production, which was attributed to synergetic effects associated with the presence of heterojunctions between the two phases: ZnO and g-C₃N₄.

Acknowledgments

The authors are grateful for the financial support of the funding agencies: CNPq (grants number 454438/2014-1, 311463/2017-7 and 159866/2018-9), FAPESP (grants number 2013/17639-4 and 2016/21515-7) and FAPEMIG. The authors also gratefully thank the support from the LMMA sponsored by FAPEMIG (CEX-112-10), SECTES/MG and RQ-MG (FAPEMIG: CEX-RED-00010-14); the Improvement of Higher Education Personnel (CAPES) (Finance Code 001 and CAPES/Embrapa Call 15/2014 Grant #166); and the Agronano Network (Embrapa Research Network). The authors thank the Laboratory of Structural Characterization (LCE/DEMa/UFSCar) for the TEM facilities. Caue Ribeiro also acknowledges Alexander von Humboldt Foundation and CAPES for the Experienced Research Fellowship (CAPES/Humboldt Agreement – Process 88881.145566/2017-1).

REFERENCES

[1] V.R. de Mendonça, O.F. Lopes, A.E. Nogueira, G.T.S.T. da Silva, C. Ribeiro, Challenges of synthesis and environmental applications of metal-free nano-

heterojunctions, in: Inamuddin, G. Sharma, A. Kumar, E. Lichtfouse, A.M. Asiri (Eds.), Nanophotocatalysis and Environmental Applications, Springer International Publishing, Cham, 2019: pp. 107–138. https://doi.org/10.1007/978-3-030-10609-6_4.

 [2] S. Wang, Y. Wang, S. Zang, X.W. (David) Lou, Hierarchical hollow heterostructures for photocatalytic CO2 reduction and water splitting, Small Methods. 4 (2020) 1900586. https://doi.org/10.1002/smtd.201900586.

[3] R. Bueno, O. Lopes, K. Carvalho, C. Ribeiro, H. Mourão, Heterostructured semiconductors: an approach about the main challenges for obtaining and application on environmental and energy photochemical processes, Química Nova. (2019). https://doi.org/10.21577/0100-4042.20170372.

[4] C. Xu, P. Ravi Anusuyadevi, C. Aymonier, R. Luque, S. Marre, Nanostructured materials for photocatalysis, Chem. Soc. Rev. 48 (2019) 3868–3902. https://doi.org/10.1039/C9CS00102F.

[5] M. Xiao, Z. Wang, M. Lyu, B. Luo, S. Wang, G. Liu, H. Cheng, L. Wang,
Hollow nanostructures for photocatalysis: Advantages and challenges, Adv. Mater. 31
(2019) 1801369. https://doi.org/10.1002/adma.201801369.

[6] S.B.A. Hamid, S.J. Teh, C.W. Lai, Photocatalytic water oxidation on ZnO: A Review, Catalysts. 7 (2017) 93. https://doi.org/10.3390/catal7030093.

[7] G. Byzynski, A.P. Pereira, D.P. Volanti, C. Ribeiro, E. Longo, Highperformance ultraviolet-visible driven ZnO morphologies photocatalyst obtained by microwave-assisted hydrothermal method, Journal of Photochemistry and Photobiology A: Chemistry. 353 (2018) 358–367. https://doi.org/10.1016/j.jphotochem.2017.11.032.

[8] J. Wojnarowicz, T. Chudoba, I. Koltsov, S. Gierlotka, S. Dworakowska, W. Lojkowski, Size control mechanism of ZnO nanoparticles obtained in microwave solvothermal synthesis, Nanotechnology. 29 (2018) 065601. https://doi.org/10.1088/1361-6528/aaa0ef.

[9] G.T.S.T. da Silva, K.T.G. Carvalho, O.F. Lopes, E.S. Gomes, A.R. Malagutti, V.R. Mastelaro, C. Ribeiro, H.A.J.L. Mourão, Synthesis of ZnO nanoparticles assisted by N sources and their application in the photodegradation of organic contaminants, ChemCatChem. 9 (2017) 3795–3804. https://doi.org/10.1002/cctc.201700756.

[10] L. Zhang, H. Cheng, R. Zong, Y. Zhu, Photocorrosion suppression of ZnO nanoparticles via hybridization with graphite-like carbon and enhanced photocatalytic activity, J. Phys. Chem. C. 113 (2009) 2368–2374. https://doi.org/10.1021/jp807778r.

[11] A. Degen, M. Kosec, Effect of pH and impurities on the surface charge of zinc oxide in aqueous solution, Journal of the European Ceramic Society. (2000) 7.

[12] S. Kumar, A. Kumar, A. Kumar, V. Krishnan, Nanoscale zinc oxide based heterojunctions as visible light active photocatalysts for hydrogen energy and environmental remediation, Catalysis Reviews. (2019) 1–60. https://doi.org/10.1080/01614940.2019.1684649.

[13] C.B. Ong, L.Y. Ng, A.W. Mohammad, A review of ZnO nanoparticles as solar photocatalysts: Synthesis, mechanisms and applications, Renewable and Sustainable Energy Reviews. 81 (2018) 536–551. https://doi.org/10.1016/j.rser.2017.08.020.

[14] J. Li, C. Tian, H. Zhao, J. Mei, J. Zhang, S. Yang, Controllable fabrication of a red phosphorus modified g-C3N4 photocatalyst with strong interfacial binding for the efficient removal of organic pollutants, Journal of Alloys and Compounds. 810 (2019) 151885. https://doi.org/10.1016/j.jallcom.2019.151885.

[15] H. Tang, R. Wang, C. Zhao, Z. Chen, X. Yang, D. Bukhvalov, Z. Lin, Q. Liu, Oxamide-modified g-C3N4 nanostructures: Tailoring surface topography for high-performance visible light photocatalysis, Chemical Engineering Journal. 374 (2019) 1064–1075. https://doi.org/10.1016/j.cej.2019.06.029.

[16] C. Zhao, Z. Chen, J. Xu, Q. Liu, H. Xu, H. Tang, G. Li, Y. Jiang, F. Qu, Z. Lin, X. Yang, Probing supramolecular assembly and charge carrier dynamics toward enhanced photocatalytic hydrogen evolution in 2D graphitic carbon nitride nanosheets, Applied Catalysis B: Environmental. 256 (2019) 117867. https://doi.org/10.1016/j.apcatb.2019.117867.

[17] G. Mamba, A.K. Mishra, Graphitic carbon nitride (g-C 3 N 4) nanocomposites: A new and exciting generation of visible light driven photocatalysts for environmental pollution remediation, Applied Catalysis B: Environmental. 198 (2016) 347–377. https://doi.org/10.1016/j.apcatb.2016.05.052.

[18] H. Jung, T.-T. Pham, E.W. Shin, Effect of g-C3N4 precursors on the morphological structures of g-C3N4/ZnO composite photocatalysts, Journal of Alloys and Compounds. 788 (2019) 1084–1092. https://doi.org/10.1016/j.jallcom.2019.03.006.

[19] M. Sun, Z. Chen, X. Jiang, C. Feng, R. Zeng, Optimized preparation of Co-Pi decorated g-C3N4@ZnO shell-core nanorod array for its improved photoelectrochemical performance and stability, Journal of Alloys and Compounds. 780 (2019) 540–551. https://doi.org/10.1016/j.jallcom.2018.12.019.

[20] Y. He, Y. Wang, L. Zhang, B. Teng, M. Fan, High-efficiency conversion of CO2 to fuel over ZnO/g-C3N4 photocatalyst, Applied Catalysis B: Environmental. 168–169 (2015) 1–8. https://doi.org/10.1016/j.apcatb.2014.12.017.

[21] M.A. Ferreira, G.T.S.T. da Silva, O.F. Lopes, V.R. Mastelaro, C. Ribeiro,M.J.M. Pires, A.R. Malagutti, W. Avansi, H.A.J.L. Mourão, Fabrication of SrTiO3/g-

C3N4 heterostructures for visible light-induced photocatalysis, Materials Science in Semiconductor Processing. 108 (2020) 104887. https://doi.org/10.1016/j.mssp.2019.104887.

[22] P. Bindu, S. Thomas, Estimation of lattice strain in ZnO nanoparticles: X-ray peak profile analysis, Journal of Theoretical and Applied Physics. 8 (2014) 123–134. https://doi.org/10.1007/s40094-014-0141-9.

[23] A. Murphy, Band-gap determination from diffuse reflectance measurements of semiconductor films, and application to photoelectrochemical water-splitting, Solar Energy Materials and Solar Cells. 91 (2007) 1326–1337. https://doi.org/10.1016/j.solmat.2007.05.005.

[24] I.F. Teixeira, E.C.M. Barbosa, S.C.E. Tsang, P.H.C. Camargo, Carbon nitrides and metal nanoparticles: from controlled synthesis to design principles for improved photocatalysis, Chem. Soc. Rev. 47 (2018) 7783–7817. https://doi.org/10.1039/C8CS00479J.

[25] T.R. Giraldi, G.V.F. Santos, V.R. Mendonça, C. Ribeiro, I.T. Weber, Annealing effects on the photocatalytic activity of ZnO nanoparticles, J. Nanosci. Nanotech. 11 (2011) 3635–3640. https://doi.org/10.1166/jnn.2011.3801.

[26] N.E. Mircescu, M. Oltean, V. Chiş, N. Leopold, FTIR, FT-Raman, SERS and DFT study on melamine, Vibrational Spectroscopy. 62 (2012) 165–171. https://doi.org/10.1016/j.vibspec.2012.04.008.

[27] S.C. Yan, Z.S. Li, Z.G. Zou, Photodegradation performance of g-C3N4 fabricated by directly heating melamine, Langmuir. 25 (2009) 10397–10401. https://doi.org/10.1021/la900923z.

[28] O.F. Lopes, K.T.G. Carvalho, A.E. Nogueira, W. Avansi, C. Ribeiro, Controlled synthesis of BiVO4 photocatalysts: Evidence of the role of heterojunctions in their catalytic performance driven by visible-light, Applied Catalysis B: Environmental. 188 (2016) 87–97. https://doi.org/10.1016/j.apcatb.2016.01.065.

[29] H.A.J.L. Mourão, C. Ribeiro, TiO2 and SnO2 magnetic nanocomposites: Influence of semiconductors and synthetic methods on photoactivity, J. Nanosci. Nanotech. 11 (2011) 7876–7883. https://doi.org/10.1166/jnn.2011.4712.

[30] P. Niu, L. Zhang, G. Liu, H.-M. Cheng, Graphene-like carbon nitride nanosheets for improved photocatalytic activities, Adv. Funct. Mater. 22 (2012) 4763–4770. https://doi.org/10.1002/adfm.201200922.

[31] O. Legrini, E. Oliveros, A.M. Braun, Photochemical processes for water treatment, Chem. Rev. 93 (1993) 671–698. https://doi.org/10.1021/cr00018a003.

[32] M.R. Hoffmann, S.T. Martin, Wonyong. Choi, D.W. Bahnemann,
Environmental Applications of Semiconductor Photocatalysis, Chem. Rev. 95 (1995)
69–96. https://doi.org/10.1021/cr00033a004.

[33] G. Liu, L. Wang, H.G. Yang, H.-M. Cheng, G.Q. (Max) Lu, Titania-based photocatalysts—crystal growth, doping and heterostructuring, J. Mater. Chem. 20 (2010) 831–843. https://doi.org/10.1039/B909930A.

[34] C. Zhao, L. Tian, Z. Zou, Z. Chen, H. Tang, Q. Liu, Z. Lin, X. Yang, Revealing and accelerating interfacial charge carrier dynamics in Z-scheme heterojunctions for highly efficient photocatalytic oxygen evolution, Applied Catalysis B: Environmental. 268 (2020) 118445. https://doi.org/10.1016/j.apcatb.2019.118445.

[35] X. Yang, L. Tian, X. Zhao, H. Tang, Q. Liu, G. Li, Interfacial optimization of g-C3N4-based Z-scheme heterojunction toward synergistic enhancement of solar-driven photocatalytic oxygen evolution, Applied Catalysis B: Environmental. 244 (2019) 240–249. https://doi.org/10.1016/j.apcatb.2018.11.056.

[36] W. Yu, D. Xu, T. Peng, Enhanced photocatalytic activity of g-C3N4 for selective CO2 reduction to CH3OH via facile coupling of ZnO: a direct Z-scheme mechanism, J. Mater. Chem. A. 3 (2015) 19936–19947. https://doi.org/10.1039/C5TA05503B.

[37] D. Gao, R.M. Arán-Ais, H.S. Jeon, B. Roldan Cuenya, Rational catalyst and electrolyte design for CO2 electroreduction towards multicarbon products, Nat Catal. 2 (2019) 198–210. https://doi.org/10.1038/s41929-019-0235-5.

TABLE

Samples	D _{hkl} (nm)			$SSA (m^2 a^{-1})$
	(100)	(002)	(101)	55A (III-g)
ZnO	39	46	34	6
ZnO:CN _{15%}	35	40	33	15
ZnO:CN _{50%}	38	45	41	11
ZnO:CN _{85%}	33	44	34	21
CN	-	-		19

Table 1. Crystallite size (D_{hkl}) calculated by Scherrer's equation and specific surfacearea (SSA).

ournalpre

FIGURES



Fig. 1. XRD patterns of the synthesized samples. The hkl and symbol (*) identify the main diffraction peaks of the ZnO and $g-C_3N_4$ crystalline phases, respectively.



Fig. 2. (a) TG curves showing the mass percent as a function of temperature. The total mass lost is presented at the end of each TG curve. (b) The first derivative of the mass loss curves ($\%/^{\circ}C$).



Fig. 3. FTIR spectra obtained from the precursors and all the synthesized samples. More conclusive peaks and bands are highlighted in the spectra.



Fig. 4. UV-vis diffuse reflectance spectra and Tauc plot (in the inset) for indirectly allowed transition obtained from UV-vis diffuse reflectance spectra data. The values of band gap (E_{BG}) are also shown in the inset.



Fig. 5. FEG/SEM images of the synthesized samples: a) CN; b) ZnO; c) ZnO: $CN_{50\%}$. The expanded views of 'b' and 'c' reveal rod-like ZnO particles and both materials (ZnO and g-C₃N₄) together, respectively. TEM (d) and HRTEM (e) images of the ZnO: $CN_{50\%}$ sample. The inset in (e): an expanded view of the HRTEM image for a representative ZnO nanoparticle.



Fig. 6. Photodegradation curves of the amiloride (AML) comparing the direct photolysis with its degradation in the presence of the synthesized photocatalysts under visible-light irradiation.



Fig. 7. Stability of the $ZnO:CN_{50\%}$ (green bar) photocatalyst during three cycles of AML photodegradation. AML direct photolysis was also presented for comparison.



Fig. 8. The effects of scavengers on the efficiency of AML degradation with the $ZnO:CN_{50\%}$ photocatalyst under visible-light irradiation.



Fig. 9. Schematic illustration of a) AML photodegradation and b) CO_2 photoreduction using the synthesized heterostructures. *Direct Z-scheme: possible recombination between e⁻ of the ZnO with h⁺ of the g-C₃N₄.



Fig. 10. Catalytic CO₂ photoreduction products after 6 h of reaction.

Jonuly

Highlights

- Synthesis of highly crystalline ZnO at room temperature;
- A new and facile method for the preparation of ZnO:g-C₃N₄ heterostructures;
- Photochemical stabilization of ZnO by association with g-C₃N₄;
- Photodegradation of amiloride under visible light;
- Photocatalytic reduction of CO2 into value-added products.

s.

Declaration of Interest Statement

 \boxtimes The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

boutual