View Article Online

Dalton Transactions

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: Y. Naganawa, Y. Maegawa, H. Guo, S. S. Gholap, S. Tanaka, K. Sato, S. Inagaki and Y. Nakajima, *Dalton Trans.*, 2019, DOI: 10.1039/C9DT00078J.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the **author guidelines**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the ethical guidelines, outlined in our <u>author and reviewer resource centre</u>, still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/dalton



ARTICLE

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

Heterogeneous hydrosilylation reaction catalysed by platinum complexes immobilized on bipyridine-periodic mesoporous organosilicas

Yuki Naganawa,^a Yoshifumi Maegawa, ^b Haiqing Guo,^a Sandeep Suryabhan Gholap,^a Shinji Tanaka,^a Kazuhiko Sato,^a Shinji Inagaki,^{*b} and Yumiko Nakajima^{*a}

The utility of a bipyridine periodic mesoporous organosilica, BPy-PMO, as a support material of a hydrosilylation catalyst was investigated in the hydrosilylation of phenylacetylene with (MeO)₃SiH. [PtMe₂(BPy-PMO)] (1) exhibited a moderate catalytic activity, whereas the reaction was successfully catalysed by [PtMe₂(BPy-PMO-TMS)] (2) bearing end-capped TMS groups on the surface. Spectroscopic analyses of 2 revealed that the porous structure of BPy-PMO-TMS remained almost unchanged through the reaction. The hot filtration test supported the nonleaching property of 2, thereby exhibiting good reusability without the loss of the product yields.

Introduction

Hydrosilylation is one of the most important methods for the synthesis of various organosilicon compounds.¹ Platinum catalysts, such as Speier's catalyst $(H_2PtCl_6)^2$ and Karstedt's catalyst,³ are widely utilized in the silicon industry because they exhibit high catalytic activity, selectivity, and high stability toward oxygen and moisture. As a result, significant amounts of Pt are consumed in the silicon industry (5.6 tons in 2007, ca. 3% of the annual global platinum production),⁴ and the high cost and uncertainty of the long-term supply of precious platinum are becoming a larger issue. In addition, separating the catalyst from the reaction mixture is often problematic in some industrial processes.^{1c} As a result, the development of a hydrosilylation process using immobilized Pt catalysts, which has the advantage of easy catalyst recovery, is attracting great interest.⁵

To prepare immobilized hydrosilylation catalysts, a wide variety of support materials have been used to date, including both organic polymers and inorganic substrates.⁶ The substrates normally possess functional linkages and connect with active metal centers, which sometimes interact with neighboring metals due to the flexible nature of the linkers, leading to a decrease in their catalytic performances. An alternative way to develop novel heterogeneous catalysts from effective homogeneous catalysts is to support them directly on highsurface-area solids without a linker.7 In this context, we focus on a periodic mesoporous organosilica containing a 2,2'bipyridine (bpy) unit within the framework (bipyridine-periodic mesoporous organosilica: BPy-PMO)⁸⁻¹⁶ as a solid chelating ligand (Figure 1). In the structure of BPy-PMO, the 2,2'bipyridine ligands are regularly and densely arranged in the siloxane network and exposed on the pore surface with a large specific surface area (>600 m² g⁻¹). Thus, BPy-PMO enables us to directly immobilize various homogeneous catalysts on the molecularly well-defined pore surface and thus suppress undesired interaction and aggregation of the metal centers. Another notable feature of BPy-PMO is the large pore size (3.8 nm in diameter), which allows the smooth diffusion of reactant molecules in the mesochannel. By utilizing these characteristic properties, we have thus far synthesized various BPy-PMObased metal complexes including Ir,⁸⁻¹⁰ Ru,^{8,11,12} Re,^{8,13} Pd,⁸ Au,¹⁴ Mo,¹⁵ and Rh¹⁶ on the PMO pore surface and demonstrated their utility as heterogeneous catalysts for organic syntheses.^{8,9,13,14}



BPy-PMOs

Figure 1. Bipyridine-periodic mesoporous organosilica (BPy-PMO, X = H) and end-capped BPy-PMO (BPy-PMO-TMS, X = SiMe₃).

^{a.} Interdisciplinary Research Center for Catalytic Chemistry National Institute of Advanced Industrial Science and Technology

Tsukuba, Ibaraki 305-8565, Japan. E-mail: yumiko-nakajima@aist.go.jp

^{b.} Toyota Central R&D Laboratories, Inc. Nagakute, Aichi 480-1192, Japan. E-mail: inagaki@mosk.tytlabs.co.jp

⁺ Footnotes relating to the title and/or authors should appear here.

Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

Published on 07 February 2019. Downloaded by Iowa State University on 2/8/2019 11:13:42 AM

Page 2 of 7

Herein, we synthesized BPy-PMO-based Pt complexes¹⁷ as hydrosilylation catalysts. A carrier support of hydrosilylation catalysts should be thermally and chemically stable during the reaction and must provide good accessibility and dispersion of the active sites to apply the catalyst system for the curing of silicone products. Considering this, we were motivated to examine the utility of BPy-PMO as the support of the hydrosilylation catalyst. In this study, we tested two types of BPy-PMO bearing different siloxane frameworks with silanol groups (X = H; BPy-PMO) or TMS-protected silanol groups (X =SiMe₃; BPy-PMO-TMS) as shown in Figure 1.

Results and Discussion

Formation of Pt complexes on solid supports

First, the formation of bipyridine-based Pt complex¹⁷ was attempted by simply mixing BPy-PMO and Karstedt's catalyst as a precursor complex in solution. However, the reaction was not successful, leading to the formation of the compounds with a small Pt loading amount of ~30 μ mol g⁻¹. This result indicates that BPy-PMO is not a suitable support for the Karstedt's catalysts. Formation of Pt(II) complex was then performed by following the synthetic procedure of [PtMe₂(bpy)],¹⁸ in which $[PtMe_2(\mu-SMe_2)]_2$ was used as a precursor. Rigorous stirring of the powder of BPy-PMOs (X = H and SiMe₃; Figure 1) in a benzene solution containing $[PtMe_2(\mu-SMe_2)]_2$ (0.15 equiv of bpy unit on surface) at 6 °C resulted in the formation of [PtMe₂(BPy-PMO)] (1) (Scheme 1; see the Supporting Information). The white color of BPy-PMO changed to light pink (1) or purple (2), implying the formation of Pt-bipyridine complex on the pore surface of BPy-PMO. Graft-type Ptbipyridine complexes 3a and 3b were also prepared for comparison using TMS-protected mesoporous silica (FSM-16) and silica gel as a support, respectively (Scheme 2; Figures S1 and S2).



Scheme 1. Synthesis of [PtMe₂(BPy-PMO)] (1) and [PtMe₂(BPy-PMO-TMS)] (2).



Scheme 2. Synthesis of [PtMe₂(BPy-C₄-FSM-16)] (**3a**) and [PtMe₂(BPy-C₄-Silica gel)] (**3b**).

Characterization of Pt-complex-immobilized solid supports

The amounts of bipyridine ligand in solid supports and Pt in catalysts **1**, **2**, **3a**, and **3b** were measured by CHN elemental analysis and energy-dispersive X-ray spectrometry (EDX) analysis, respectively. The results are summarized in Table 1. The amounts of bipyridine ligand in BPy-PMO and BPy-PMO-TMS were 3.18 and 2.92 mmol g⁻¹. Pt loading amounts in **1** and **2** were 0.26 and 0.36 mmol g⁻¹. When all Pt ions coordinated with bipyridine ligands in 1:1 ratio, this EDX result indicates that there are large amounts of free bipyridine units (88% for **1** and 82% for **2**) on the pore surface (see, Experimental Section). In contrast, although the loading amounts of Pt in **3a** and **3b** were similar to those of bipyridine ligands in the supports (0.38 mmol g⁻¹ for **3a** and 0.36 mmol g⁻¹ for **3b**), almost no free bipyridine ligands exist in **3a** and **3b**.

To investigate the structural change of solid supports during the immobilization of Pt complex, powder X-ray diffraction (XRD) patterns and nitrogen adsorption/desorption isotherms were measured (Figure S3-S6). The XRD patterns of 1, 2, and 3a showed an intense peak at 2θ values of 1.86°, 1.82°, and 1.88°, respectively, indicating that well-ordered mesostructures of parent solid supports remained (Figures S3-S5). For PMO complexes 1 and 2, four additional peaks were observed at scattering angles of 7.60°, 15.2°, 22.9°, and 30.8° due to the molecular-scale periodicity of the bipyridine groups in the pore walls (Figures S3 and S4). Table 1 summarizes the values of the Brunauer–Emmett–Teller surface area (S_{BET}) and t-plot pore volume (V_{t-plot}), and the density functional theory pore diameter (d_{DFT}) obtained from nitrogen adsorption/desorption isotherms of four solid catalysts and parent solid supports (Figures S7 and S8). For 1, S_{BET} , V_{t-plot} , and d_{DFT} values were decreased compared with those of parent BPy-PMO, indicating the occurrence of partial structural change by immobilization of the Pt complex. In contrast, S_{BET} , V_{t-plot} , d_{DFT} values of **2** and BPy-PMO-TMS were nearly constant, meaning the preservation of uniform mesoporous structure even after the immobilization of the Pt complex. This result is ascribed to improvement in the structural stability of the pore framework by TMS protection. A similar positive effect by the TMS group was also previously reported for BPy-PMO.¹⁵ For **3a** and **3b**, S_{BET} , $V_{\text{t-plot}}$, and d_{DFT} values were slightly reduced compared with those of parent

supports, suggesting the almost complete preservation of original porous structures by TMS protection.

Table 1. Physicochemical properties of PMO complexes 1 and 2,and graft-type complexes 3a and 3b.

sample	bpy unit	Pt amount	S _{BET} [m ² g ⁻¹] ^{c)}	V _{t-pot} [cc g ⁻¹] ^{c)}	<i>d</i> _{DFT} [nm] ^{с)}
	bpy g ⁻¹] ^{a)}	[mmol Pt			
BPy-PMO	3.18		764	0.58	4.4
1	_	0.26	478	0.31	3.9
BPy-PMO- TMS	2.92	_	654	0.45	4.0
2	_	0.36	632	0.42	3.9
BPy-C₄- FSM-16	0.38	_	575	0.44	3.8
3a	_	0.38	528	0.36	3.8
BPy-C ₄ -	0.42	-	402	0.46	5.7
Silica gel					
3b	_	0.36	373	0.37	5.5

^a The amounts of bpy unit in support were determined by CHN elemental analysis. ^b Determined by EDX analysis. ^c Determined from nitrogen adsorption/desorption isotherms at liquid nitrogen temperature and calculated using the BET method (S_{BET}), *t*-plot method (V_{t-plot}), or density functional theory (d_{DFT}).

Complexation of Pt and bipyridine was confirmed by UV-vis diffuse reflectance spectroscopy (Figure S9). The UV-vis absorption spectrum of the model complex [PtMe₂(bpy)] in toluene showed partly structured absorption in the range of 400-600 nm due to the metal-to-ligand charge transfer (MLCT) band of the Pt-bipyridine complex.¹⁹ However, complex 1 showed a weak absorption in the same range. Because the absorption intensity is weak, a small amount of the desired Ptbipyridine complex seems to form on the pore surface. It is also likely that an undesired Pt complex was formed by the reaction of the Pt precursor with the surface silanol groups. In contrast, 2 showed a broad absorption band centered at 540 nm in the range of 450-650 nm, which can be attributed to the Ptbipyridine complex on the pore surface. The red-shift of the absorption band compared with that of [PtMe₂(bpy)] might be due to the changes in electronic state of the Pt-bipyridine complex by direct attachment of silicon atoms at both sides of the bipyridine ligand and end-capping of surface silanol groups with TMS groups. The red-shift of the MLCT band due to the silicon substitution was also reported in other metalimmobilized BPy-PMO.8 Graft-type complexes 3a and 3b showed a broad absorption band centered at ~470 nm, which is similar to that of PtMe₂(bpy) in toluene solution, indicating that Pt complexes in 3a and 3b were located in a hydrophobic environment.

Catalytic activity of Pt catalysts immobilized on BPy-PMO

The catalytic activity of 1 and 2 toward hydrosilylation was examined using phenylacetylene as a model'substrate (Pable 2). Pt-catalyzed hydrosilylation of terminal alkynes has been extensively examined as one of the common preparation methods of a series of vinylsilanes, which are valuable synthetic intermediates in organic chemistry, although the mixture of β trans and α adducts was often obtained in the reactions.²⁰ In the presence of a catalytic amount of 1 (5 mol% Pt), the reaction of phenylacetylene with (MeO)₃SiH proceeded at 60 °C, and the hydrosilylated product was obtained after 15 h as the mixture of β -trans and α adducts (β -trans/ α = 70/30), albeit in a low yield (10%) (Table 2, Entry 1). Complex 2 also catalysed the hydrosilylation reaction to give the hydrosilylated products in higher yield, 82%, with the similar ratio of β -trans/ α = 72/28 (Table 2, entry 2). The yield was improved to 98% after a longer reaction time of 24 h (Table 2, entry 3).

A catalytic activity of a homogeneous catalyst, [PtMe₂(bpy)], was also tested for reference. This reaction afforded the hydrosilylated product in 97% yield with the β -trans/ α ratio of 73/27 (Table 2, entry 4). Thus, no deleterious effect on the catalytic activity was observed after the immobilization on BPy-PMO.

Table 2. H	ydrosil	vlation	of pheny	lacet	lene.	a)

Ph	-H Cat (5 mol% P	rt) Ph		Ph
+	benzene	→	Si(OMe) ₃	(MeO) ₃ Si
(MeO) ₃ SiH	60 °C, Time	β-trans		α
entry	cat (Time)	% conv. ^{b)}	% conv. ^{b)}	% yield ^{b)}
		alkyne	hydrosilane	$[\beta$ -trans/ α]
1	1 (15 h)	80	65	10 [70/30]
2	2 (15 h)	85	82	78 [72/28]
3	2 (24 h)	>99	>99	98 [72/28]
4	[PtMe ₂ (bpy)]	>99	>99	97 [72/28]
	(24 h)			
5	3a (24 h)	97	>99	97 [72/28]
6	3b (24 h)	93	97	93 [71/29]

 $^{\rm a}$ Reaction conditions: catalyst (0.01 mmol Pt), alkyne (0.2 mmol), hydrosilane (0.2 mmol) in benzene (1 mL) at 60 °C. $^{\rm b}$ Determined by ¹H NMR analysis with mesitylene (0.2 mmol) as an internal standard.

It is noteworthy that both phenylacetylene and $(MeO)_3SiH$ were considerably consumed, with 80% and 65% conversion, respectively, in the reaction catalysed by 1, although the reaction gave only 10% yield of the products. We tentatively ascribe this lower product yield to the reactive silanol groups on PMO-siloxane surface, which could react with the hydrosilylated product, (trimethoxysilyl)styrene, to give the end-capped BPy-PMO.²¹ To elucidate this point, the solid-state ²⁹Si MAS NMR analysis was conducted. The ²⁹Si MAS NMR spectrum of 1 displayed two signals at 66.9 ppm and 78.3 ppm assignable to the T² unit and T³ unit of siloxane matrix, respectively (Figure 2(a)). The clear disappearance of the T² unit of 1 after the catalytic reaction suggests the occurrence of a silane-coupling reaction between BPy-PMO and product, which leads to the conversion of the T² unit to the corresponding T³

ARTICLE

unit (Figure 2(b)). Because the signal intensity of the Qⁿ unit was not sufficiently high to be identified under this measurement conditions, it is likely that the dehydrogenative coupling of silanol with (MeO)₃SiH hardly proceeded. The spectrum of **2** shows an additional signal due to the TMS protecting group at 12.9 ppm instead of the T² unit, indicating that the T² unit in **1** was mostly consumed by TMS protection (Figure 2(c)). As expected, there was no significant difference in ²⁹Si NMR spectrum after the hydrosilylation by **2**. Thus, the utility of TMSend-capping to enhance chemical stability of the mesoporous structure was supported (Figure 2(d)).



Figure 2. ²⁹Si MAS NMR analyses of (a) **1**, (b) **1** after hydrosilylation, (c) **2**, and (d) **2** after hydrosilylation.

Complexes 3a and 3b exhibited similar catalytic activity to 2. Thus, under similar reaction conditions, the hydrosilylated products were obtained quantitatively with the β -trans/ α ratio of 72/28 and 71/29, respectively (Table 2, entries 5 and 6). In contrast, hot filtration experiments showed significant differences in the leaching behavior of 2, 3a, and 3b. The reactions catalysed by 2, 3a, and 3b were conducted at 60 °C at the catalyst loading of 5 mol% Pt for 2 and 0.1 mol% Pt for 3a and **3b** and monitored by ¹H NMR spectroscopy. After stirring for 1 h, filtration of the reaction mixture was performed at 60 °C and the filtrate was further stirred at this temperature. The results are summarized in Figure 3. In the reaction catalysed by 2, the yield of the hydrosilylated products was 22% after 1 h and this value remained unchanged for 20 h. Therefore, the possibility of leaching of 2 was excluded. The reactions catalysed by 3a and 3b were conducted similarly. To our surprise, the yields gradually increased after the filtration and then reached 88% (3a) and 44% (3b) after stirring the filtrate for 19 h. These results strongly suggested that the reaction catalysed by **3a** or **3b** was partly promoted by leaching. At species, such as Pt nanoparticles.^{7b,22D} Considering that ***2** possesses many spare bipyridine units (82%) that are densely arranged on the pore surface as determined above, we postulated that the free bipyridine would be helpful for suppression of leaching of Pt species from the pore surface.



Figure 3. Time course in the hot filtration test of hydrosilyllation of phenylacetylene and trimethoxysilane with cat **2** and **3**. Reaction conditions: catalyst (0.01 mmol Pt for **2**, 0.001 mmol Pt for **3**), alkyne (0.2 mmol for **2**, 1.0 mmol for **3**), hydrosilane (0.2 mmol for **2**, 1.0 mmol for **3**) in benzene (1 mL for **2**, 5 mL for **3**) at 60 °C. Determined by ¹H NMR analysis with mesitylene (0.2 mmol for **2**, 1.0 mmol for **3**) as an internal standard.

Recycle experiments of Pt catalyst immobilized on BPy-PMO

Encouraged by the leaching experiments, we next examined the reusability of 1 and 2 (Figure 4). The reaction of phenylacetylene with (MeO)₃SiH was performed for 15 h and the catalyst was recovered by simple filtration. It was found that the recovered 2 maintained good catalytic activity with slight loss of product yields for at least five times, indicating the good recyclability of **2**. Through the whole cycles, the ratio of two regioisomers (β trans/ α) remained almost unchanged. Complex **1** were less active than 2 for each reaction cycle. This is probably because Pt atoms are partially immobilized on the silanol surface in 1. Interestingly, the catalytic activity of **1** was slightly improved after the second cycle. Since the hydrosilylated product reacts with silanol groups on the BPy-PMO surface, as noted above, it is likely that passivation of the surface proceeded during the reaction, and thus the catalytic activity could be somewhat improved after the reaction cycles.

To confirm the preservation of the mesoporous structure after the hydrosilylation, we measured XRD patterns and nitrogen adsorption/desorption isotherms of recovered PMO complex **2** after the fifth reaction. The XRD pattern for recovered **2** showed

strong reflection at low angle of 1.80° and four diffraction peaks at 7.60°, 15.2°, 22.9°, and 30.8°, suggesting the preservation of periodic mesoporous and crystal-like pore wall structures due to the robust covalent siloxane networks (Figure S10). The S_{BET} , $V_{t\text{-plot}}$, and d_{DFT} values of recovered **2** were 625 m² g⁻¹, 0.39 cc g⁻¹ 1, 3.8 nm, respectively, clearly indicating preservation of the periodic mesoporous structure (Figure S11). The TEM images of recovered **2** suggested no formation of Pt particles, indicating that the Pt-bipyridine complex remained without aggregation even after the fifth reaction. (Figure S12)²³



Figure 4. Yields in recycle experiments on hydrosilylation of phenylacetylene and trimethoxysilane with 5 mol% of **1** and **2**. The values in parentheses represent regioselectivity (β -trans/ α). Reaction conditions: catalyst (0.01 mmol Pt), alkyne (0.2 mmol), hydrosilane (0.2 mmol) in benzene (1 mL) at 60 °C for 15 h. Determined by ¹H NMR analysis with mesitylene (0.2 mmol) as an internal standard.

Experimental

Materials

All chemicals were purchased from commercial suppliers (Sigma-Aldrich, Tokyo Chemical Industry Co., Ltd., and Wako Pure Chemical Industries, Ltd.) and used without further purification. BPy-PMO and BPy-PMO end-capped with TMS groups (BPy-PMO-TMS) were prepared according to a previously reported procedure.⁸ BPy-C₄-FSM-16 and BPy-C₄-Silica gel were prepared according to a previously reported procedure to a previously reported procedure.

Characterization of immobilized Pt complexes

²⁹Si dipolar decoupling (DD) MAS NMR measurement was performed at 79.49 MHz at a sample spinning frequency of 4 kHz using a Bruker Avance III 400 spectrometer with a 7 mm zirconia rotor. For the ²⁹Si MAS NMR measurements, the repetition delay was 60 s, and the pulse width was 1.5 µs. Chemical shifts were referenced to hexamethylcyclotrisiloxane at –9.68 ppm as external standard for ²⁹Si NMR. X-ray diffraction (XRD) profiles were recorded by a Rigaku RINT-TTR diffractometer using Cu-Kα radiation (50 kV, 300 mA). Nitrogen adsorption/desorption isotherms were obtained using a Quantachrome Nova3000e sorptometer at liquid nitrogen temperature (-196 °C). Brunauer–Emmett–Teller (BET) surface areas were calculated from the linear sections of BET ($POPP_0$) = 0.1–0.2). Pore-size distributions were calculated using the DFT method (DFT kernel: N₂ at -196 °C on silica, cylindrical pores, nonlinear density functional theory (NLDFT) equilibrium model). Pore volumes were estimated using the *t*-plot method. Energy-dispersive X-ray spectrometry (EDX) was performed using a Hitachi S-3600N instrument. TEM observations were performed using a Jeol JEM-EX2000 operating at 5 kV and 200 kV, respectively. UV-vis diffuse reflectance and absorption spectra were obtained using a Jasco V-670.

Synthesis of PtMe₂(BPy-PMO) (1) and PtMe₂(BPy-PMO-TMS) (2)

A 50 mL Schlenk tube was equipped with a stir bar, BPy-PMO (629 mg, 2.12 mmol BPy/g on the surface) or BPy-PMO-TMS (684 mg, 1.95 mmol BPy/g on the surface), and dry benzene (8 mL). The mixture was stirred at 60 °C. Then, a solution of $[PtMe_2(\mu-SMe_2)]_2$ (57 mg, 0.1 mmol) in dry benzene (20 mL) was added dropwise at 60 °C. After stirring for ca. 5 min at the same temperature, the mixture was cooled to 6 °C and kept stirred for an additional 24 h. The resulting suspension was filtered and then washed with dry benzene. The material was dried under reduced pressure to give PtMe₂(BPy-PMO) (1) and PtMe₂(BPy-BPy-TMS) (2), respectively. The loading amounts of Pt in PMO complexes 1 and 2 were determined from the Pt/Si ratios measured by energy-dispersive X-ray spectroscopy (EDX). The EDX analysis showed that the Pt/Si ratios were 0.041 and 0.037 for PMO complexes 1 and 2, respectively. Because of the Si/BPy molar ratios are 2/1 for BPy-PMO and 10/3 for BPy-PMO-TMS,⁸ the Pt/BPy molar ratios in 1 and 2 were calculated to be 0.082 and 0.12, and thus corresponding to 0.26 and 0.36 mmol Pt g⁻¹, respectively. In the case of 2, Pt complexes should be exclusively formed on the BPy ligands exposed on the surface layer of BPy-PMO pore wall which is composed of three layers of Si-BPy-Si unit. Therefore, the Pt/BPy_{surface} are determined to be 18% for PMO complexes 2 and there are 82% of free bipyridine units on the pore surface.

Synthesis of $PtMe_2(BPy-C_4-FSM-16)$ (3a) and $PtMe_2(BPy-C_4-Silica gel)$ (3b)

A 50 mL Schlenk tube was equipped with a stir bar, BPy-C₄-FSM-16 (500 mg, 0.38 mmol BPy/g) or BPy-C₄-Silica gel (500 mg, 0.42 mmol BPy/g), and dry benzene (5 mL). The mixture was stirred at 60 °C. Then, a solution of $[PtMe_2(\mu-SMe_2)]_2$ (73 mg, 0.127 mmol) in dry benzene (6 mL) was added at 60 °C. The reaction mixture was stirred at 6 °C for 20 h. The resulting suspension was filtered and then washed with dry benzene. The material was dried under reduced pressure to give PtMe₂(BPy-C₄-FSM-16) (**3a**) and PtMe₂(BPy-C₄-Silica gel) (**3b**), respectively.

Typical procedure for hydrosilylation of phenylacetylene and $(\mbox{MeO})_3\mbox{SiH}$

A 20 mL Schlenk tube equipped with a stir bar was charged with phenylacetylene (22 μ L, 0.2 mmol), mesitylene (28 μ L, 0.2 mmol), and PtMe₂(BPy-PMO-TMS) (**2**) (28 mg, 0.01 mmol Pt) in

Published on 07 February 2019. Downloaded by Iowa State University on 2/8/2019 11:13:42 AM

ansactions Accepted Manusc

dry benzene (1 mL). Then, (MeO)₃SiH (25 µL, 0.2 mmol) was added dropwise to the suspension. The reaction mixture was stirred for 15 h at 60 °C. The heterogeneous catalyst was removed by passing through a membrane filter (0.1 µm). The yield of the product was determined by ¹H NMR analysis with mesitylene as an internal standard. ¹H NMR spectra of the products, β -trans- and α -(trimethoxysilyl)styrene, were reported in the literature.²⁴

Conclusions

In this study, we prepared the Pt complex directly immobilized on BPy-PMO, and BPy-PMO-TMS as well as Pt complexes with other silica-based bipyridine ligands possessing functional linkages. The reaction of both BPy-PMO and BPy-PMO-TMS with $[PtMe_2(\mu-SMe_2)]_2$ provided the corresponding Pt complexes 1 and 2, respectively. Complex 1 exhibited moderate catalytic activity in the hydrosilylation of phenylacetylene with (MeO)₃SiH, probably due to the partial formation of undesired Pt complex coordinated with free silanol moieties. It is also to be mentioned that the reaction of silanol moieties with the hydrosilylatd product also lead to the decrease in the apparent production yield. In contrast, complex 2 with BPy-PMO-TMS, which was end-capped with TMS groups on the surface silanol groups, effectively catalysed the hydrosilylation reaction. Hot filtration experiments excluded the occurrence of leaching of 2 during the reactions. In contrast, leaching of the grafted complexes 3a and 3b was observed. We postulated that the utility of free bipyridine units in 2, which are densely arranged on the pore surface, could suppress the leaching behavior. Complex 2 showed good reusability without the loss of the product yield for at least five reuse cycles in hydrosilylation. Overall, the superior utility of BPy-PMO-TMS as a solid-support ligand for Pt-catalysed hydrosilylation was demonstrated.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by the "Development of Innovative Catalytic Processes for Organosilicon Functional Materials" project (Project Leader: K. Sato) from the New Energy and Industrial Technology Development Organization (NEDO). The authors thank Dr. Yasutomo Goto and Dr. Masamichi Ikai (Toyota Central R&D Laboratories, Inc.) for TEM observations and SEM-EDX analysis.

Notes and references

 (a) L. N. Lewis, J. Stein, Y. Gao, R. E. Colborn and G. Hutchins, *Platinum Met. Chem.* 1997, **41**, 66-75; (b) Y. Nakajima and S. Shimada, *RSC ADV*. 2015, **5**, 20603-20616; (c) D. Troegel and J. Stohrer, *Coord. Chem. Rev.* 2011, **255**, 1440-1459; (d) B. G. Marciniec, *Coord. Chem. Rev.* 2005, **249**, 2374-2390: (e) D. Xiaoyong, H. Zheng, *ACS Catal.* 2017, **7**

- 2 (a) J. L. Speier, J. A. Webster and G. H. Barnes, J. Am. Chem. Soc. 1957, **79**, 974-979; (b) J. L. Speier, Adv. Organomet.
- Chem. 1979, 17, 407–447.
 B. D. Karstedt, General Electric Company, US3775452A, 1973.
- A. J. Holwell, *Platinum Met. Rev.* 2008, **52**, 243-266.
- 5 (a) M. Pagliaro, R. Ciriminna, V. Pandarus and F. Béland, *Eur. J. Org. Chem.* 2013, 6227-6235; (b) Y. Bai, J. Peng, J. Li, G. Lai, and X. Li, *Prog. Chem.* 2011, 23, 2466-2477; (c) H. Bai, *Ind. Eng. Chem. Res.* 2014, 53, 1588-1597.
- 6 (a) L. Wang and Y. Jiang, J. Organomet. Chem. 1983, 251, 39-44; (b) C.-Y. Hu, X.-M. Han and Y.-Y. Jiang, J. Mol. Catal. 1986, 35, 329-333; (c) W. R. Cullen and N. F. Han, J. Organomet. Chem. 1987, 333, 269-280; (d) R. Drake, R. Dunn, D. C. Sherrington and S. J. Thomson, Chem. Commun. 2000, 1931-1932; (e) Z. M. Michalska, Ł. Rogalskia, K. Rózga-Wijas, J. Chojnowski, W. Fortuniak and M. Ścibiorek, J. Mol. Catal. A: Chem. 2004, 208, 187-194; (f) J. Li, C. Yang, L. Zhang and T. Ma, J. Organomet. Chem. 2011, 696, 1845-1849.
- 7 (a) Q. J. Miao, Z. Fang and G. P. Cai, *Catal. Commun.* 2003, 4, 637-639; (b) T. Galeandro-Diamant, R. Sayah, M. Zanota, S. Marrot, L. Veyre, C. Thieuleux and V. Meille, *Chem. Commun.* 2017, 53, 2962-2965.
- 8 M. Waki, Y. Maegawa, K. Hara, Y. Goto, S. Shirai, Y. Yamada, N. Mizoshita, T. Tani, W.-J. Chun, S. Muratsugu, M. Tada, A. Fukuoka and S. Inagaki, *J. Am. Chem. Soc.* 2014, **136**, 4003-4011.
- 9 Y. Maegawa and S. Inagaki, *Dalton Trans.* 2015, **44**, 13007-13016.
- 10 X. Liu, Y. Maegawa, Y. Goto, K. Hara and S. Inagaki, Angew. Chem. Int. Ed. 2016, **55**, 7943-7947.
- N. Ishito, H. Kobayashi, K. Nakajima, Y. Maegawa, S. Inagaki, K. Hara and A. Fukuoka, *Chem. Eur. J.* 2015, **21**, 15564-15569.
- 12 Y. Kuramochi, M. Sekine, K. Kitamura, Y. Maegawa, Y. Goto, S. Shirai, S. Inagaki and H. Ishida, *Chem. Eur. J.* 2017, **43**, 10301-10309.
- 13 M. Waki, K.-i. Yamanaka, S. Shirai, Y. Maegawa, Y. Goto, Y. Yamada and S. Inagaki, *Chem. Eur. J.* 2018, **24**, 3846-3853.
- 14 N. Ishito, K. Nakajima, Y. Maegawa, S. Inagaki and A. Fukuoka, Catal. Today 2017, **298**, 258-262.
- 15 S. Ishikawa, Y. Maegawa, M. Waki and S. Inagaki, ACS Catal. 2018, 8, 4160-4169.
- 16 K. Matsui, Y. Maegawa, M. Waki, S. Inagaki and Y. Yamamoto, *Catal. Sci. Technol.* 2018, **8**, 534-539.
- 17 M. Yoshida, K. Saito, H. Matsukawa, S. Yanagida, M. Ebina, Y. Maegawa, S. Inagaki, A. Kobayashi and M. Kato, J. Photochem. Photobiol. A 2018, 358, 334-344.
- (a) J. D. Scott and R. J. Puddephatt, *Organometallics* 1983, 2, 1643-1648;
 (b) P. K. Monaghan and R. J. Puddephatt, *Organometallics* 1984, 3, 444-449;
 (c) D. Minniti, G. Alibrandi, M. L. Tode and R. Romeo, *Inorg. Chem.* 1987, 26, 3956-3958;
 (d) M. Rehdi, Z. Fakhroeian and R. J. Puddephatt, *J. Organomet. Chem.* 1991, 406, 261-267.
- 19 A. Klein, J. van Slageren and S. Záliš, Eur. J. Inorg. Chem., 2003, 1917-1928.
- A review, see: (a) B. M. Trost and Z. T. Ball, *Synthesis*. 2005, 853-887. Pioneering examples of Pt-catalyzed hydrosilylation of alkynes, see: (b) L. N. Lewis, K. G. SyG. L. Bryant, Jr. and P. E. Donahue, *Organometallics* 1991, 10, 3750-3759; (c) M. G. Voronkov, V. B. Pukhnarevich, I. I. Tsykhanskaya, N. I. Ushakova, Y. L. Gaft and I. A. Zakharova, *Inorg. Chim. Acta*. 1983, 68, 103-105; (d) M. Green, J. L. Spencer, F. G. A. Stone and C. A. Tsipis, *J. Chem. Soc., Dalton Trans*. 1977, 1525-1529; (e) C. A. Tsipis, *J. Organomet. Chem*. 1980, 187, 427-446.
- 21 H. Noda, K. Motokura, A. Miyaji and T. Baba, *Angew. Chem. Int. Ed.* 2012, **51**, 8017-8020.

View Article Online DOI: 10.1039/C9DT00078J

Dalton Transactions Accepted Manuscript

- 23 Examples of single atom catalysts (SACs) based on Pt, see: (a) X. Cui, K. Junge, X. Dai, C. Kreyenschulte, M. M. Pohl, S. Wohlrab, F. Shi, A. Brückner and M. Beller, ACS Cent. Sci. 2017, 3, 580-585; (b) J. L. Liu, F. R. Lucci, M. Yang; S. Lee, M. D. Marcinkowski, A. J. Therrien, C. T. Williams, E. C. Sykes and M. Flytzani-Stephanopoulos, J. Am. Chem. Soc. 2016, 138, 6396-6399; (c) F. Dvořák, M. F. Camellone, A. Tovt, N.-D. Tran, F. R. Negreiros, M. Vorokhta, T. Skála, I. Matolínová, J. Mysliveček, V. Matolín and S. Fabris, Nat. Commun. 2016, 7, 10801-10807; (d) B. Qiao, A. Wang, X. Yang, L. F. Allard, Z. Jiang, Y. Cui, J. Liu, J. Li and T. Zhang, Nat. Chem. 2011, 3, 634-641; (e) H. Wei, X. Liu, A. Wang, L. Zhang, B. Qiao, X. Yang, Y. Huang, S. Miao, J. Liu and T. Zhang, Nat. Commun. 2014, 5, 5634-5640; (f) S. Yang, J. Kim, Y. J. Tak, A. Soon and H. Lee, Angew. Chem. Int. Ed. 2016, 55, 2058-2062; (g) B. Zhang, H. Asakura, J. Zhang, J. Zhang, S. De and N. Yan, Angew. Chem. Int. Ed. 2016, 55, 8319-8323; (h) M. Moses-DeBusk, M. Yoon, L. F. Allard, D. R. Mullins, Z. Wu, X. Yang, G. Veith, G. M. Stocks and C. K. Narula, J. Am. Chem. Soc. 2013, 135, 12634-12645; (i) J. Wang, X. Zhao, N. Lei, L. Li, L. Zhang, S. Xu, S. Miao, X. Pan, A. Wang and T. Zhang, ChemSusChem 2016, 9, 784-790.
- 24 C.-H. Jun and R. H. Crabtree, J. Organomet. Chem. 1993, 447, 177-187.

This journal is © The Royal Society of Chemistry 20xx