This article was downloaded by: [The University of British Columbia] On: 10 October 2014, At: 18:12 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information: http://www.tandfonline.com/loi/gmcl20

Synthesis of New Liquid Crystals with 2,3,4,9-Tetrahydro-1H-Fluorene Moiety

R. Ch. Geivandov^a, V. Mezhnev^a & T. Geivandova^a

^a Moscow Fine Organic Synthesis & Liquid Crystal Laboratory "INCORFIN" Ltd. Co , Moscow, Russia Published online: 14 Jun 2011.

To cite this article: R. Ch. Geivandov, V. Mezhnev & T. Geivandova (2011) Synthesis of New Liquid Crystals with 2,3,4,9-Tetrahydro-1H-Fluorene Moiety, Molecular Crystals and Liquid Crystals, 542:1, 141/[663]-148/[670], DOI: <u>10.1080/15421406.2011.570542</u>

To link to this article: http://dx.doi.org/10.1080/15421406.2011.570542

PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms & Conditions of access and use can be found at http://www.tandfonline.com/page/terms-and-conditions



Synthesis of New Liquid Crystals with 2,3,4,9-Tetrahydro-1*H*-Fluorene Moiety

R. CH. GEIVANDOV, V. MEZHNEV, AND T. GEIVANDOVA

Moscow Fine Organic Synthesis & Liquid Crystal Laboratory "INCORFIN" Ltd. Co, Moscow, Russia

A new range of liquid crystals containing the 2,3,4,9-tetrahydro-1H-fluorene system have been prepared and its thermal properties were examined. The mesomorphic properties are compared with those of the fluorene and trans-cyclohexane derivatives. Introduction of 2,3,4,9-tetrahydro-1H-fluorene in typical liquid crystal structure leads to decrease of melting point and the clearing point values. The chemical structures and mesogenic properties for the reported novel compounds are discussed.

Keywords 2,3,4,9-tetrahydro-1*H*-fluorene; cross-coupling reaction; liquid crystals

1. Introduction

The introduction of alicyclic fragment in the mesogenic moiety of potential liquid-crystalline structure leads to a change in the basic properties of mesomorphic compounds (temperature phase transitions, optical and dielectric anisotropy, viscosity, etc.) [1–4]. In continuation of our systematic studies [5–7] in the area of synthesis of mesomorphic structures, containing mono-, bi- and trialicyclic units, we synthesized a new class of liquid crystals – 2,7-disubstituted 2,3,4,9-tetrahydro-1*H*-fluorene derivatives and investigated their temperature phase transitions.

2. Results and Discussion

2.1. Synthesis of Target Intermediates and Liquid Crystal

We thought it was interesting to synthesize an analogue of fluorene, where one of benzene rings is partially hydrogenated. We have concentrated our efforts on the development of convenient synthetic methods for key intermediate products, which provide a new class of liquid crystals – 2,7-disubstituted 2,3,4,9-tetrahydro-1H-fluorene derivatives. The syntheses were carried out according to Schemes 1 and 2.

Address correspondence to R. Ch. Geivandov, Moscow Fine Organic Synthesis & Liquid Crystal Laboratory "INCORFIN" Ltd. Co, 27, Burakova str., 111123 Moscow, Russia. Tel.: +7-916-0518677; E-mail: r.ch.geivandov@gmail.com



Scheme 1. Synthesis of 7-Bromo-2-pentyl-2,3,4,9-tetrahydro-1H-fluorene (6).

The Scheme 1 in included the following basic subsequent steps:

- obtaining the β-chloracroleine 2 using Vilsmeier-Haack-Arnold method [8] by action of POCl₃-DMF complex on ketone 1,
- cross-coupling of β -chloracroleine 2 with 4-bromophenylboronic acid 3,
- reduction of aldehyde group in compound 4 using lithium aluminum hydride to obtain alcohol 5,
- intramolecular dehydration-cyclization of alcohol 5 in the presence of acidic catalysts to obtain compounds 6 with tetrahydrofluorene system.

Although aryl chloride is less reactive due to higher energy barrier for the oxidative insertion of the palladium catalyst into the C-C bond, the Suzuki coupling of vinyl chlorides takes place at a sufficient pace. Moreover, the presence of an electron-accepting group leads to an increase of the reaction rate and allows the use of such derivatives as β -chloracroleine.

The β -chloracroleine **2** easily went into cross-coupling reaction and the compound **4** was produced in 82% yield.

We have conducted wide investigation while searching for the optimal conditions of cyclization of alcohol **5** by trying various acidic catalysts and reaction conditions variants. The best result for cyclization of alcohol **5** into the compound **6** has been achieved under action of polyphosphoric acid (PPA). The yield of compound **6** was approximately 35%.



Scheme 2. Synthesis of liquid crystals (9-12) by cross-coupling reaction.

142/[664]

Phenylboronic acids	Product	Yield, %	Ms: m/z (M ⁺)
(HO) ₂ B-F	C ₅ H ₁₁	68	334
(HO) ₂ B-F	C ₅ H ₁₁	77	352
(HO) ₂ B-CN		44	341
(HO) ₂ B-OCH ₃	C ₅ H ₁₁ OCH ₃	76	346

Table 1. Cross- coupling reaction of 7-bromo-2-pentyl-2,3,4,9-tetrahydro-1*H*-fluorene (6) with substituted phenylboronic acids (8a-d)

Compound 6 have been cyanated using cooper cyanide and yielded nitrile 7. The cross-coupling reaction of compound 6 with 4-substituted phenylboronic acids (8a-d) in the presence of 10% Pd/C lead to liquid crystals 9–12 (Scheme 2, Table 1).

2.2. Liquid Crystalline Properties

The 2,3,4,9-tetrahydro-1H-fluorene is a partially saturated derivative of fluorene. The fluorene moiety differs from a biphenyl unit since it is almost flat and just slightly bent in the plane of the rings. Previous work on fluorene containing mesogens showed them to exhibit mainly smectic phases or very short nematic ranges [9].

Molecule of 2,3,4,9-tetrahydro-1H-fluorene (**A**) in contrast to fluorene (**B**) is not flat at all and has a rigid-flexible configuration; both structures are shown on Figure 1.

In this regard, when comparing properties of LC molecules, we also present data on the temperatures for similar trans-cyclohexane derivatives, whose structures combine a rigid-flexible configuration of the core molecule.



Figure 1. Molecular structures of 2,3,4,9-tetrahydro-1*H*-fluorene (**A**) and fluorene (**B**). (Figure appears in color online.)

As one can see from Table 2, compound 7 and fluorene derivative 7b with terminal nitrile group exhibit monotropic nematic phase, while compound 7a has a normal liquid crystalline temperature range.

We have synthesized three units compounds of 2,3,4,9-tetrahydro-1*H*-fluorene (A). Compounds 9, 10, 11, 12 (Table 2) have, in contrast to described corresponding trans-cyclohexane derivatives (9a, 11a, 12a), lower melting point and give way mainly to thermal stability.

The compounds containing tetrahydro-1H-fluorene units **9–12** were found to have nematic and smectic liquid crystalline phase with relatively low phase transition temperature and wide liquid crystalline temperature range.

Compound	Molecular structure*	Cr	S	Ν	Ι	Ref.
7		52	_		(34)	_
7A		31	_		55	[10]
7B		66	_		(24.5)	[9]
9	R	76	_		141	_
9a	R	100	_		152	[11]
10		64	_		104	_
11		89	110		178	_
11a		96	_	·	222	[12]
11b		128	_		216	[13]
12	R-C-OCH3	110	130		183	_
12a	ROCH3	80	_		165	[14]
$*R = C_5 H_{11}.$						

Table 2. Transition temperatures (°C) for 7-substituted -2-pentyl-2,3,4,9-tetrahydro-1*H*-fluorenes, fluorene and trans-cyclohexane derivatives

The wide liquid crystalline temperature range of compound 11 and fluorene derivative 11b are almost comparable, but compound 11 have lower melting and clearing points as compared to compound 11b.

3. Experimental

All commercially available substances were purchased from Aldrich, Merck, Acros, Fluka or Lancaster and were used without further purification. Solvents were purified and dried if necessary according to standard procedures. All reactions were monitored by thin-layer chromatography on silica gel (Merck, Kieselgel 60, F254). UV-light with wavelength of $\lambda = 254$ nm was used for detection.

3.1. Melting and Clearing Points

The temperatures of phase transitions and liquid crystalline phases were observed with Mettler FP 90 coupled with a polarizing Olympus BH-2 microscope. Measured temperatures from the polarizing microscope have been corrected by calibration with standard materials.

3.2. NMR Spectroscopy

Confirmations of the intermediate and final product structures were accomplished by ¹H, ¹³C, ¹⁹F, NMR spectroscopy (Bruker AM-300 and Bruker Avance II 300 spectrometers) at ambient temperature. Chemical shifts values (δ) are relative to Me₄Si and are given in ppm (references solvents are CDCl₃ and DMSO-d6).

3.3. Mass Spectrometry

Mass-spectra were obtained directly using Finningan MAT INCOS 50 spectrometer (EI, 70 eV).

2-Chloro-5-pentylcyclohex-1-ene-1-carbaldehyde (2). To solution of DMF (10.3 ml) in dry chloroform (25 ml) at 5–10 °C was added phosphoryl chloride (10.1 ml) and the mixture was stirred for 10 minutes. Then the 4-pentylcyclohexanone 1 (16.8 ml, 0.1 mol) in chloroform (25 ml) was added drop wise at 20 °C and the mixture was heated at 55–60 °C for 3 hour. The reaction mixture was poured into an aqueous sodium acetate solution (35 g sodium acetate in 120 ml water), extracted with chloroform (3 × 30 ml), and the combined chloroform extracts were washed successively with water and dried (Na₂SO₄). The solvent was removed *in vacuo* and the residue was distilled to give a colourless liquid.

Yield 82%; bp 92–94 °C at 0.24 mmHg; n_D^{20} 1.4925; ¹H NMR(CDCl₃) δ 0.85 (3H, t, CH₃), 1.2–1.4 (8H, m, C₅H₁₁), 1.45–1.8 (4H, m, cyclohexane), 2.47 (3H, m, cyclohexane), 11,5 (H, s, CHO); ms m/z 214 (M⁺).

2-(4-Bromophenyl)-5-pentylcyclohex-1-ene-1-carbaldehyde (4). A mixture of chloroacroleine 2 (2,59 mmol), 4-bromophenyl boronic acid (3) (2,83 mmol), tetrabutylammonium bromide (2,60 mmol), palladium acetate (0,053 mmol, 2 mol %) and potassium carbonate (6,45 mmol) was added to a 10 mL round-bottom flask. Deionized water (5 ml) was added, and the reaction was stirred vigorously for

3 hours at 45 °C. The reaction mixture became dark and non-homogenous. Then the mixture was diluted with water (15 ml), and the product was extracted with EtOAc $(3 \times 30 \text{ ml})$. The organic phase was stirred over charcoal for 30 min and dried (MgSO₄). After filtration and concentration *in vacuo*, the residue was distilled to give a colourless liquid.

Yield is 68%; bp183–190 °C at 0.120 mm Hg; n_D^{20} 1.5660; mp 28–30 °C; ¹H NMR(CDCl₃) δ 0.9(3H, s, CH₃), 1.2–1.4 (8H, m, C₅H₁₁), 1.45–1.95(4H, m, cyclohexane), 2.5–2.7(3H, m, cyclohexane), 7,1(2H, d, aromatic). 7,5(2H, d, aromatic), 9,48(1H, s, CHO); ms m/z 334 (M⁺).

[2-(4-Bromophenyl)-5-pentylcyclohex-1-en-1-yl]methanol (5). Ether solution (8 ml) of aldehyde 4 (2.1 g, 6.25 mmol) was added to a stirred suspension of lithium aluminum hydride (0.300 g, (7.9 mmol) in dry ether (6 ml) at 0 °C. The temperature was kept at 0 °C for 1 hour. Then reaction mixture was poured into NH₄Cl solution, the product was extracted with ether (3 × 30 mL), combined extracts were washed with water and dried (Na₂SO₄). The solvent was removed *in vacuo* and the residue was purified by column chromatography (silica gel/n-hexane). Yield 90%; m.p. 55–56 °C; ¹H NMR (CDCl₃) δ 0.9(3H, t, CH₃), 1.2–1.45 (8H, m, C₅H₁₁), 1.75–1.92 (4H, m, cyclohexane), 2.22–2.45 (3H, m, cyclohexane), 3.92 (2H, s, CH₂OH), 7,0(2H, d, aromatic). 7,42(2H, d, aromatic); ¹³C NMR (DMSO) δ 141.70(C_{arom}-C=C) 135.64(C=C-C_{arom}), 132.86(C_{arom}), 131.92(C_{arom}), 129.93 (C_{arom}), 120.54(C-Br), 63.94(CH₂OH), 36.57(C_{tret}), 32.80, 34.0, 33.7, 32.3, 29.55, 26.69, 22.75(CH₂), 14.14(CH₃); ms *m*/*z* 337 (M⁺).

7-Bromo-2-pentyl-2,3,4,9-tetrahydro-1H-Fluorene (6). A mixture of (1.5 g, 4.7 mmol) compound 5 and polyphosphoric acid (PPA) (50 g) was heated for 20 minutes at 135–137 °C. The reaction mixture was diluted with water and the product was extracted with ether (3×50 ml). The combined organic extracts were washed with water and dried (Na₂SO₄). The solvent was removed *in vacuo* and the residue was purified by column chromatography (silica gel/n-hexane).

Yield 35%; m.p. 79–80 °C (acetone); ¹H NMR (CDCl₃) δ 0.92(3H, t, CH₃), 1.25–1.48 (8H, m, C₅H₁₁), 1.65–1.8(1H, s, cyclohexane), 1.9–2.1(2H, m, cyclohexane), 2.3–2.55 (3H, m, cyclohexane), 3.2 (2H, s, CH₂), 7,0(1H, d, aromatic). 7,38(1H, d, aromatic), 7,5(1H, d, aromatic); ¹³C-NMR (DMSO) δ 145.06(C_{arom}-C=C) 141.91(C=C-C_{arom}), 135.49(C_{arom}), 129.04 (C_{arom}), 126.61 (C_{arom}), 118.73(C-Br), 117.49(C_{arom}), 40.42(CH₂), 36.41(C_{tret}), 34.44, 32.54, 32.23, 29.03, 26.87, 22.80, 22.00(CH₂), 14.21(CH₃); ms m/z 318 (M⁺).

2-Pentyl -2,3,4,9-tetrahydro-1H-Fluorene-7-carbonitrile (7). A mixture of 7-Bromo-2-pentyl-2,3,4,9-tetrahydro-1H-fluorene **6** (0.175 g, 0.55 mmol), copper (I) cyanide (0.58 g, 0.32 mmol) and N-methyl-2-pyrrolidone (5.5 ml) was refluxed in a three-neck flask for 5 hours. Toluene (5 ml) was added, the mixture was cooled, and a solution consisting of ferric chloride (0.65 g), conc. hydrochloric acid (0.16 ml) and water (7.5 ml) was added and it was stirred for 30 minutes at 60–70 °C. The resulting two layers were separated and the resulting organic layer was washed with dilute hydrochloric acid, then with dilute aqueous sodium hydroxide, and further with water. After a small amount of solid matter was eliminated by filtration, toluene was distilled off *in vacuo*. The residue was purified by column chromatography (silica gel/n-hexane). Yield 65%; transitions (°C) Cr 52 N (34) I; ¹H NMR (CDCl₃) δ 0.92(3H, t, CH₃), 1.25–1.45 (8H, m, C₅H₁₁), 1.65–1.8(1H, s, cyclohexane), 1.9–2.15(2H, m, cyclohexane), 2.3–2.62(3H, m, cyclohexane), 3.3(2H, s, CH₂), 7,0(1H, d, aromatic). 7,22(1H, aromatic), 7,58(1H, aromatic); ms m/z 265 (M⁺).

General procedure for cross- coupling reaction of 7-bromo-2-pentyl-2,3,4,9-tetrahydro-IH-fluorene (5) with substituted phenylboronic acids (**8a-d**). 7-Bromo-2-pentyl-2,3,4,9-tetrahydro-1H-fluorene **6** (4.38 mmol), substituted phenylboronic acid **8a-d** (4.38 mmol), 10% Pd/C (0.01 g), triphenylphosphine (0.18 mmol) and sodium carbonate (8.76 mmol) were heated in a mixture of toluene (1 ml), ethanol (0.5 ml) and water (0.3 ml) for 24 hours at 80 °C. The reaction mixture was diluted with water, the product was extracted with EtOAc and the combined extracts were washed with water, filtered, dried (Na₂SO₄). The solvents were removed *in vacuo* and the residue was purified by column chromatography (silica gel/n-hexane).

7-(4-Fluorophenyl)-2-pentyl-2,3,4,9-tetrahydro-1H-fluorene (9). Yield 68%; transitions (°C) Cr 76 N 141 I; ¹H NMR (CDCl₃) δ 0.91 (3H, t), 1.20–2.7 (15H, m), 3.3 (2H, m), 7.05–7.6 (7H, m, arom). ¹⁹F-NMR (DMSO): δ 138.5.

7-(3,4-Difluorophenyl)-2-pentyl-2,3,4,9-tetrahydro-1H-fluorene (10). Yield 77%; transitions (°C) Cr 64 N 104 I; ¹H NMR (CDCl₃) δ 0.91 (3H, t), 1.20–1.5 (8H, m), 1.75 (1H, s), 1.9–2.2 (2H, m), 2.3–2.65 (3H, m), 3.3 (2H, s, CH₂), 7.1–7.55 (6H, m, arom). ¹⁹F NMR (CDCl₃): δ 138.5 (d, 1 F), 142.45(d, 1 F).

4-(2-Pentyl-2,3,4,9-tetrahydro-1H-fluoren-7-yl)benzonitrile (11). Yield 44%; transitions (°C) Cr 89 S 110 N 178 I;¹H NMR (CDCl₃) δ 0.91 (3H, t), 1.25–2.6 (15H, m), 3.3 (2H, m), 7.25–7.7 (7H, m, arom.).

7-(4-Methoxyphenyl)-2-pentyl-2,3,4,9-tetrahydro-1H-fluorene (12). Yield 76%; transitions (°C) Cr 110 S 130 N 183 I; ¹H NMR (CDCl₃) δ 0.91 (3H, t), 1.25–2.6 (15H, m), 3.29 (2H, m), 3.85 (3H, s, OCH₃), 7.0–7.6 (7H, m, arom.).

4. Conclusions and Perspectives

For the first time a new class of nematic liquid crystal compounds containing 2,3,4,9-tetrahydro-1*H*-fluorene system has been synthesized and characterized.

We can conclude that the replacement of rigid fragments in the typical LC molecules with rigid-flexible fragments changes the whole set of their properties. Molecular factors can be divided into three groups – geometry, dispersion, and polarity. They all have an impact on the mesomorphic behavior of molecules.

The relative importance of each factor depends on the characteristics of chemical, electronic and spatial structure of the molecule. In this regard, sequential



Figure 2. Structures of 2,3,4,4a,9-tetrahydro-2H-fluorene (C) and trans-2,3,4,4a,9,9a-hexahydro-1*H*-fluorene (D) mesogenic moiety.

analysis of each of these factors on the example of the LC classes allows us to estimate the contribution of factor in the total effect of changes in respect of thermal stability and mesophase range.

In future, we plan to synthesize new LC structures, containing 2,3,4,4a,9-tetrahydro-2H-fluorene (**C**) and trans-2,3,4,4a,9,9a-hexahydro-1*H*-fluorene (**D**) systems (Figure 2).

References

- [1] Eidenschink, R., Haas, O., Romer, M., & Scheuble, B. S. (1984). Angew. Chem., 96, 151.
- [2] Eidenschink, R., & Scheuble, B. S. (1986). Mol. Cryst. Liq. Cryst. Lett., 3, 33.
- [3] Gray, G. W., & Kelly, S. M. (1981). Mol. Cryst. Liq. Cryst., 75, 95.
- [4] Petrov, V. F., Torgova, S. I., Karamysheva, L. A., & Takenaka, S. (1999). Liquid Crystals, 26, 1141.
- [5] Geivandov, R. Ch., Goncharova, I. V., & Titov, V. (1989). Mol. Cryst. Liq. Cryst., 166, 101.
- [6] Karamysheva, L. A., Geivandova, T. A., Agafonova, I. F., Roitman, K. V., Torgova, S. I., Geivandov, R. Ch., Petrov, V. F., & Grebyonkin, M. F. (1990). *Mol. Cryst. Liq. Cryst.*, 191, 237.
- [7] Barnik, M. I., Geivandov, R. Ch., Gorina, I. I., & Shtykov, N. M. (1998). Mol. Mat., 2, 1.
- [8] Arnold, Z., & Zemlicka, J. (1959). Collect. Czech. Chem. Commun., 24, 2385.
- [9] Davison, I. R., Hall, D. M., & Sage, I. (1985). Mol. Cryst. Liq. Cryst., 129, 17.
- [10] Eidenschink, R., Erdmann, D., Krause, J., & Pohl, L. (1977). Angew. Chem., 89, 103.
- [11] Eidenschink, R. (1983). Mol. Cryst. liq. Cryst., 94, 119.
- [12] Eidenschink, R., Erdmann, D., Krause, J., & Pohl, L. (1977). Angew. Chem. Int. Ed. Engl., 16, 100.
- [13] Boardman, F. H., Dunmur, D. A., Grossel, M. C., & Luckhurst, G. R. (2002). Chem. Lett., 31, 60.
- [14] Demus, D., Goodby, J. W., Gray, G. W., Spiess, H.-W., & Vill, V. (1997). Handbook of Liquid Crystals, Wiley: New York.