# Reactivity of active oxygen species generated in the EuCl<sub>3</sub> catalytic system for monooxygenation of hydrocarbons



Department of Chemical Engineering, Tokyo Institute of Technology, Ookayama, Meguro-ku, Tokyo 152, Japan

The reactivity of active oxygen species generated from  $O_2$  in the EuCl<sub>3</sub>-Zn-MeCO<sub>2</sub>H catalytic system for the monooxygenation of various hydrocarbons has been studied in detail. In the case of the oxygenation of alkanes, a large difference between the reactivities of primary, secondary and tertiary C-H bonds (1:6:19) is observed. The kinetic isotope effect (KIE) between C-H and C-D (2.6) for the oxidation of cyclohexane, the relative conversion rate of cooxidation of cyclopentane and cyclohexane (C<sub>s</sub>/C<sub>6</sub> = 0.7) and the non-retention of the configuration of tertiary C-H bonds suggest that the cleavage of the C-H bond is a key step in forming the alkyl radical intermediate by H<sup>•</sup> abstraction in the oxidation of alkanes. In the case of epoxidation of *cis*-hex-2-ene and *trans*-hex-2-ene, the *cis*- and *trans*-configurations are not preserved in their epoxides. This suggests that the epoxidation proceeds through alkyl radical intermediates. In the case of the hydroxylation of toluene, the regioselectivity in the formations of cresols (o:m:p, 13:1:16) suggests a strong electrophilicity of active oxygen species. The electrochemical studies for oxidation of cyclohexane mediated by EuCl<sub>3</sub> over a glassy carbon cathode suggest that the formation of Eu<sup>2+</sup> and O<sub>2</sub><sup>-</sup> is important for the cyclohexane oxidation.

### Introduction

We have recently reported that europium salts (*e.g.* EuCl<sub>3</sub>) are active catalysts for the monooxygenation of hydrocarbons with  $O_2$  in the presence of Zn powder, carboxylic acid and solvent at room temperature.<sup>1</sup> Dioxygen, activated reductively with electrons and protons, was postulated to be responsible for the monooxygenation using this EuCl<sub>3</sub> catalytic system [eqn. (1)].

$$C_m H_n + O_2 + 2e^{-}(Zn) + 2H^{+}(MeCO_2H) \longrightarrow \cdots \longrightarrow$$
$$C_m H_n O + H_2 O + [Zn(MeCO_2)_2] \quad (1)$$

Other than  $EuCl_3$ ,  $LaCl_3$  and  $SmCl_3^2$  also exhibited good activities for monooxygenations, although their catalytic activities were 10 times lower than that of  $EuCl_3$ .

We have reported the effects of reaction conditions [temperature,  $P(O_2)$ , solvent, carboxylic acid, *etc.*] on the oxygenation of cyclohexane and the epoxidation of hex-1-ene using these rare earth chloride based catalytic systems.<sup>1</sup> However, the following questions have not yet been answered; (*i*) why is there a large difference in reactivities between the EuCl<sub>3</sub> and LaCl<sub>3</sub> (or SmCl<sub>3</sub>) catalytic systems?; (*ii*) are the catalytic natures and formulae of the active oxygen species different in each system?; and (*iii*) what properties are specific to this EuCl<sub>3</sub> catalytic system compared with the well-known oxygenation systems, such as the metalloporphyrin system,<sup>3-10</sup> the Fenton system<sup>10,11</sup> and the Gif system?<sup>12-14</sup> Therefore, the aim of this paper is to gain information about the nature of the active oxygen species and the reaction mechanism for the monooxygenation of alkanes and alkenes in the EuCl<sub>3</sub> catalytic system.

### **Results and discussion**

### **Oxidation of alkanes**

In order to gain information on the nature of active oxygen species in the rare earth catalytic system, the reactivities for the monooxygenation of some hydrocarbons were investigated for the EuCl<sub>3</sub>, LaCl<sub>3</sub> and SmCl<sub>3</sub> catalytic systems. The active oxygen species in each catalytic system will be expressed as O\*-EuCl<sub>3</sub>, O\*-LaCl<sub>3</sub> and O\*-SmCl<sub>3</sub> hereafter.

As shown in Table 1, the oxygenation of hexane gave hexan-

1-ol, hexanal, hexan-2-ol, hexan-2-one, hexan-3-ol and hexan-3-one for all catalytic systems. The turnover number (TON) of the sum of the products based on  $EuCl_3$  was 6.57 in 1 h corresponding to 2.6% yield based on hexane. The regioselectivity of the active oxygen attacking the terminal and the internal C-H bonds of hexane was evaluated from the yield of oxygenated products. The ratio of the reactivities of primary to secondary (1°:2°) C-H bonds (normalized per C-H bond) for O\*-EuCl<sub>3</sub> was 1:6.0. For O\*-LaCl<sub>3</sub> and O\*-SmCl<sub>3</sub>, the regioselectivities (1°:2°) were 1:14.9 (LaCl<sub>3</sub>) and 1:12.9 (SmCl<sub>3</sub>), which differ appreciably from that observed in the EuCl<sub>3</sub> catalytic system.

The regioselectivity for the secondary: tertiary ratio  $(2^\circ: 3^\circ)$ was obtained from the oxygenation of adamatane. Although the concentration of adamantane used was 21 times lower than that of hexane, the TON for the sum of the products (adamantan-1-ol, adamantan-2-ol and adamantan-2-one) in the EuCl<sub>3</sub> catalytic system was 8.09 in 1 h corresponding to a yield of 66%. The ratio of the reactivity of the secondary and tertiary C-H bonds for the EuCl<sub>3</sub> catalytic system was 1:3.1. This ratio indicates that the nature of the reactivity of O\*-EuCl<sub>3</sub> is quite different from that of Gif chemistry  $(2^\circ: 3^\circ 1:\sim 1)$ .<sup>12-14</sup> In the case of O\*-LaCl<sub>3</sub> and O\*-SmCl<sub>3</sub>, the regioselectivities of secondary: tertiary were 1:6.3 (LaCl<sub>3</sub>) and 1:6.8 (SmCl<sub>3</sub>), though each TON for the sum of products was not over unity. The regioselectivities, primary: secondary: tertiary, estimated from the above results were for the EuCl<sub>3</sub> system, 1:6:19, for the LaCl<sub>3</sub> system, 1:15:94, and for the SmCl<sub>3</sub> system, 1:13:88. These ratios reflect the electrophilicities of the active oxygen species in each system.

The ratio of the initial conversion rates of cooxidation for cyclopentane and cyclohexane per C-H bond  $(C_5/C_6)$  obtained from their cooxidation gives further information about the active oxygen species.<sup>15</sup> It is reported that  $C_5/C_6 \le 0.5$  suggests electrophilic attack on the C-H bond,  $0.6 \le C_5/C_6 \le 1$  and  $C_5/C_6 \ge 1$  indicate H<sup>•</sup> abstraction and H<sup>-</sup> abstraction, respectively.<sup>8,9,15</sup> The results for the parameter of  $C_5/C_6$  for EuCl<sub>3</sub>, LaCl<sub>3</sub> and SmCl<sub>3</sub> catalytic systems obtained at a low conversion of reactants (*ca.* 0.1%) are shown in Table 1. The C<sub>5</sub>/C<sub>6</sub> for EuCl<sub>3</sub> (0.41). This result implies that H<sup>•</sup> abstraction occurs during the

 Table 1
 Oxygenation of alkanes catalysed by EuCl<sub>3</sub>, LaCl<sub>3</sub> and SmCl<sub>3</sub><sup>a</sup>

	TON for product in 1 h							
Hexane	Hexan-1-ol	Hexan-2-ol	Hexan-3-ol	Hexanal	Hexan-2-one	Hexan-3-one	Yield/%	Remarks 1°:2°
EuCl <sub>3</sub> LaCl <sub>3</sub> SmCl <sub>3</sub>	0.24 0.01 0.01	1.55 0.11 0.12	1.65 0.12 0.12	0.49 0.02 0.03	1.51 0.22 0.27	1.13 0.15 0.18	2.57 0.25 0.29	1:6.0 1:14.9 1:12.9
	TON for prod	uct in 1 h					NC 111	
Adamantane <sup>b</sup>	damantane <sup>b</sup> Adamantan-1-ol		Adamantan-2-ol		Adamantan-2-one		Yield/ %	2°:3°
EuCl <sub>3</sub>	3.99 0.55		2.92 0.18		1.18		66.3 6.64	1:3.1
SmCl <sub>3</sub>	0.52		0.11		0.12		6.07	1:6.8
<b>D</b>	TON for products							
c-Pentane + c-Hexane <sup>b</sup>	c-Pentanone	c-Per	ntanol	c-Hexanone	;	-Hexanol		C <sub>5</sub> /C <sub>6</sub>
EuCl <sub>3</sub>	0.028	0.10		0.035	(	).169		0.66
LaCl <sub>3</sub> SmCl <sub>3</sub>	0.032 0.035	0.03	3	0.076 0.075		).116 ).116		0.38 0.41

<sup>a</sup> Standard conditions: T = 40 °C; catalyst (0.03 mmol); Zn (1 g); MeCO<sub>2</sub>H (2 ml); reactant (1 ml); CH<sub>2</sub>Cl<sub>2</sub> (2 ml); O<sub>2</sub> (1 atm). <sup>b</sup> Adamantane (0.05 g) in CH<sub>2</sub>Cl<sub>2</sub> (1 ml). <sup>c</sup> c-Pentane (0.5 ml) + c-hexane (0.5 ml).

 Table 2
 Retention of the configuration of the tertiary C-H bond of alkane during the oxidation<sup>a</sup>

	TON for products in 1 h (trans: cis)					
	1,2-Dimethylcyclo- hexan-1-ol	1,2-Dimethyl- cyclohexane 3-oxygenates	1,2-Dimethyl- cyclohexane 4-oxygenates	2-Methoxymethyl- cytohexane	Yield/%	
cis-1,2-Dimethylcyclohexane						
EuCl <sub>3</sub>	5.66 (48:52)	2.31 (7:93)	3.18 (2:98)	0.59 (20:80)	5.05	
LaCl <sub>3</sub>	1.01 (48:52)	0.02	0.04	0.0	0.46	
trans-1,2-Dimethylcyclohexane EuCl <sub>2</sub>	1.80 (48:52)	1.85 (97:3)	2.27 (99:1)	0.39 (89:11)	2.77	
	Decalin-9-ol	Decalin 1-oxygenates	Decalin 2-oxygenates	Yield/%		
<i>cis</i> -Decalin EuCl <sub>3</sub>	1.54 (80:20)	1.17 (4:96)	1.81 (2:98)		2.09	
trans-Decalin EuCl <sub>3</sub>	1.04 (83:17)	2.45 (97:3)	3.13 (98:2)		3.16	

\* Standard conditions T = 40 °C; reaction time, 1 h; catalyst (0.03 mmol); Zn (1 g); MeCO<sub>2</sub>H (2 ml); reactant (1 ml); CH<sub>2</sub>Cl<sub>2</sub> (2 ml); O<sub>2</sub> (1 atm).

oxidation of alkanes in the EuCl<sub>3</sub> catalytic system, while electrophilic attack on the C-H bond is suggested for the oxidations with O\*-LaCl<sub>3</sub> and O\*-SmCl<sub>3</sub>. The strong electrophilicities of these active oxygen species have already been suggested from the ratios primary: secondary: tertiary described above.

It is suggested from the results of the  $C_5/C_6$  factor that an alkyl radical intermediate may exist during the oxidation of alkanes with O\*-EuCl<sub>3</sub>. If this is true, then the cis- and transconfiguration of the cycloalkanes should not be retained in the products. Table 2 shows the results of the oxidations of cis- and trans-1,2-dimethylcyclohexane with O\*-EuCl<sub>3</sub> and O\*-LaCl<sub>3</sub>. Although several oxygenated products of 1,2-dimethylcyclohexane were obtained, the most important concern was the ratio of *cis*- to *trans*-1,2-dimethylcyclohexan-1-ols. This ratio was 1:1.1 for both the oxidations of cis- and trans-1,2dimethylcyclohexanes. The cis- and trans-isomerization of the dimethylcyclohexanes was not observed during the oxidation. These results indicate that the configuration of the tertiary C-H bonds is not retained in the oxidation with O\*-EuCl<sub>3</sub>. This result supports the hypothesis that an alkyl radical intermediate is produced as a result of H abstraction from the 1,2dimethylcyclohexanes.

In the case of the oxidation of 1,2-dimethylcyclohexane with  $O^*$ -LaCl<sub>3</sub>, the ratio of *cis*- to *trans*-1,2-dimethylcyclohexan-1ols was also 1:1.1, indicating the configuration of tertiary C-H bonds was not retained in this case either. This result may rule out the reaction mechanism suggested from the value of the C<sub>5</sub>/C<sub>6</sub> factor; electrophilic attack at the C-H bond followed by insertion of oxygen between the C-H bond retaining the *cis*- and *trans*-configuration of the substrates in the 1,2dimethylcyclohexan-1-ol. Thus, we believe that H<sup>\*</sup> abstraction is also important during the oxidation with O\*-LaCl<sub>3</sub>.

The original cis- and trans-retention in the products were also examined for the oxidations of cis- and trans-decalin with O<sup>\*</sup>-EuCl<sub>3</sub>. As can be seen from Table 2, the trans-form of decalin-9-ol was the major product for the oxidation of cis-decalin. The product ratio of trans- to cis-decalin-9-ols (80:20) for the oxidation of cis-decalin was close to the ratio obtained in the oxidation of trans-decalin (83:17). The retention of configuration was estimated to be about 3% from these trans- and cisdecalin-9-ol selectivities. This result also indicates that the cis- and trans-configuration of the reactants is not retained in the products, supporting the fact that H<sup>\*</sup> abstraction occurs during the oxidation of decalin.

	TON for	product in 1 l	ı			
Diphenyl sulfide <sup>b</sup>	Ph <sub>2</sub> SO	Ph <sub>2</sub> SO <sub>2</sub>	Total			Yield/%
EuCl <sub>2</sub>	6.80	4.22	11.03			55.2
Diphenyl sulfoxide (		$Ph_2SO_2$				Yield/%
EuCl <sub>3</sub>		6.97				35.0
Benzene	PhOH					Yield/%
EuCl <sub>3</sub>	1.93					0.52
Toluene	Ph-		Cresols			
	СНО	CH₂OH	0-	m-	р-	Yield/%
EuCl <sub>3</sub>	0.33	0.61	1.47	0.11	0.87	1.08

" Standard conditions: T = 40 °C; reaction time, 1 h; EuCl<sub>3</sub> (0.03 mmol), O<sub>2</sub> (1 atm); Zn (1 g); MeCO<sub>2</sub>H (2 ml); reactant (1 ml); CH<sub>2</sub>Cl<sub>2</sub> (2 ml). <sup>b</sup> Ph<sub>2</sub>S (0.112 g) in CH<sub>2</sub>Cl<sub>2</sub> (1 ml). <sup>c</sup> Ph<sub>2</sub>SO (0.121 g) in CH<sub>2</sub>Cl<sub>2</sub> (1 ml).

The H<sup>•</sup> abstraction in the C-H bond activation of alkanes was supported by kinetic isotope effect (KIE) experiments on the conversion rate of cyclohexane using a mixture of  $c-C_6D_{12}$ and  $c-C_6H_{12}$  under the standard conditions. A KIE of 2.6 was observed in the EuCl<sub>3</sub> catalytic system. This value was smaller than those in the LaCl<sub>3</sub> (3.7) and SmCl<sub>3</sub> catalytic systems (3.6). The results of the KIE suggest that either the cleavage of the C-H bond or H<sup>•</sup> abstraction from cyclohexane is the rate determining step in the oxidations by these rare earth catalytic systems. The KIE obtained for O<sup>\*</sup>-EuCl<sub>3</sub>, O<sup>\*</sup>-LaCl<sub>3</sub> and O<sup>\*</sup>-SmCl<sub>3</sub> are different from those of Fenton (1.2),<sup>10,11</sup> Gif (2.3)<sup>12-14</sup> and metalloporphyrin (~5) systems.<sup>3-9</sup>

### Oxidation of sulfur compounds and aromatics

Table 3 shows the reactivities of the EuCl<sub>3</sub> catalytic system for the oxidation of sulfur compounds and the hydroxylation of aromatics. The EuCl<sub>3</sub> catalytic system showed a high catalytic activity in the oxidation of diphenyl sulfide to diphenyl sulfoxide and diphenyl sulfone; total yield of 55% in 1 h based on diphenyl sulfide. Oxidation of Ph<sub>2</sub>SO to Ph<sub>2</sub>SO<sub>2</sub> also proceeded with O\*-EuCl<sub>3</sub>. The rate of oxidation of diphenyl sulfoxide was 37% lower than that of diphenyl sulfide. This result reflects the electrophilicity of O\*-EuCl<sub>3</sub>. Oxidation of diphenyl sulfide does not proceed with the Fenton system (HO<sup>\*</sup>)<sup>16</sup> and the Gif system (Fe<sup>V</sup>=O).<sup>12</sup> This oxidation is usually used as a test reaction of biomimetic systems, such as metalloporphyrin.<sup>7,17</sup> However, the oxidation of Ph<sub>2</sub>SO to Ph<sub>2</sub>SO<sub>2</sub> does not proceed in metalloporphyrin systems. Thus, the nature of O\*-EuCl<sub>3</sub> and O\*-LaCl<sub>3</sub> is different from that in these catalytic systems.

It is well known that the active oxygen species in the Fenton system  $(HO^{-})^{10,11}$  and the metalloporphyrin system  $(P^{++}-Fe^{4+}=O)^3$  initiate the hydroxylation of aromatics, but that in the Gif system  $(Fe^{5+}=O)^{12-14}$  does not. The hydroxylation of benzene to phenol occurred with a TON of 1.93 in 1 h for the EuCl<sub>3</sub> catalytic system. The hydroxylation of toluene was carried out to obtain information on the regioselectivity for C-H bonds of the aromatic ring. The TON of 2.45 in 1 h for the cresols was larger than that for the hydroxylation of benzene. The ratio of regioselectivity for the formations of *o*-, *m*- and *p*-cresols per C-H bond was 13:1:16. A strong preference for the *o*- and *p*-orientations was observed. This result supports the electrophilic nature of O<sup>\*</sup>-EuCl<sub>3</sub> suggested in the oxygenation of alkanes (Table 1).

### **Epoxidation of alkenes**

Table 4 shows the results of the retention of configuration of the C=C bond for the epoxidation of stilbene and hex-2-enes. In the case of the epoxidation of *cis*-stilbene with O\*-EuCl<sub>3</sub>, a mixture of *cis*- and *trans*-stilbene oxide, along with products

resulting from C=C bond cleavage (benzaldehyde and benzyl alcohol), were obtained. The ratio of *cis*- to *trans*-stilbene oxide was 2:98 when *cis*-stilbene was used as a starting material. Isomerization of *cis*-stilbene to *trans*-stilbene was not observed during the oxidation. These results suggest that the configuration of *cis*-stilbene is not retained in the epoxide for the EuCl<sub>3</sub> catalytic system. When the epoxidation of *cis*-stilbene was carried out at lower temperatures, the ratio of *cis* to *trans* increased to 13:87 (20 °C) and to 21:79 (0 °C). A slight increase in the selectivity to the sum of epoxide was observed with decreasing temperature from 43% (40 °C) to 53% (0 °C). These results suggest that part of the configuration of *cis*-stilbene was retained by decreasing the temperature. The epoxidation of *trans*-stilbene did not dissolve in the reaction mixture.

As mentioned above, most of the configuration of cisstilbene was not retained. Therefore, to gain more information on the retention of configuration during the epoxidation, the reaction of cis- and trans-hex-2-enes with O\*-EuCl<sub>3</sub> was studied in detail, as shown in Table 4. When the epoxidation of cishex-2-ene was carried out, trans- and cis-2,3-epoxyhexane, hexan-2-one, hexan-3-one and hexanediols were produced. The TON of 28.8 (10.6% yield) in 1 h for the sum of cis- and transepoxides (selectivity of 90%) was higher than that of 11.7 observed in the hex-1-ene epoxidation.<sup>1</sup> More selective and faster epoxidation of cis-hex-2-ene occurred compared with that of hex-1-ene (selectivity of 81%). The ratio of cis- to trans-2,3-epoxyhexane was 17:83 under the standard conditions. The results for the epoxidation of trans-hex-2-ene showed a TON of 24.1 (9.0% yield) in 1 h for the sum of the epoxides (selectivity of 90%) and the ratio of cis: trans was 9:91. The isomerizations of the reactant between cis- and trans-hex-2enes were not observed during the epoxidation. These results suggest that part of the configuration of hex-2-ene is retained in the EuCl<sub>3</sub> catalytic system under the standard conditions because of the difference between the ratios of the epoxidation of cis-hex-2-ene (17:83) and trans-hex-2-ene (9:91) that was observed. The retention of the configuration was estimated to be about 8%. However, the majority of the configuration of hex-2-ene is not retained during the epoxidation. Influences of solvents (e.g. 1,2-dichloroethane) and carboxylic acids (e.g. propionic acid) on the ratios of cis: trans were studied. However, the ratios were constant, independent of the solvents and the acids. When the reaction temperature was decreased to 10 °C, the ratios of cis: trans did not change. This result seems to conflict with the result observed in the epoxidation of cisstilbene. However, a rotation of the C-C bond of the intermediate from hex-2-enes may be easier than that of stilbene.

Table 4	Epoxidation	of alkenes	catalysed	by the	EuCl <sub>3</sub> system '
---------	-------------	------------	-----------	--------	----------------------------

	TON for product in 1 h							
cis-Stilbene	<i>cis</i> -Stilbene oxide	<i>trans</i> -Stilbene oxide	Benza	ıldehyde	Benzyi alcohol	Yield/%	cis: trans	
40 °C 20 °C 0 °C	0.14 0.34 0.29	6.08 2.30 1.02	7.30 2.24 0.87		1.04 0.80 0.29	7.73 3.02 1.31	2:98 13:87 21:79	
cis-Hex-2-ene	cis-2,3- Epoxyhexane	trans-2,3- Epoxyhexane	Hexan- 2-one	Hexan- 3-one	Hexanediols	Yield/%	cis: trans	
40 °C With EtCO <sub>2</sub> H With (CH <sub>2</sub> Cl) <sub>2</sub> 10 °C	4.83 2.83 4.61 0.96	24.0 14.19 24.2 4.70	0.24 	0.13 0.13 0.07	0.95  0.97 0.26	11.72 6.64 11.72 2.56	17:83 17:83 16:84 17:83	
<i>trans</i> -Hex-2-ene 40 ℃ 10 ℃	2.14 0.39	21.96 4.31	0.09	0.08	0.63 0.16	9.96 2.18	9:91 8:92	

<sup>a</sup> Standard conditions: T = 40 °C; reaction time 1 h; EuCl<sub>3</sub> (0.03 mmol); reactant (1 ml); O<sub>2</sub> (1 atm); Zn powder (1 g); MeCO<sub>2</sub>H (2 ml); CH<sub>2</sub>Cl<sub>2</sub> (2 ml).



Fig. 1 Electrochemical oxidation of cyclohexane to cyclohexanone and cyclohexanol mediated by rare earth chlorides over a glassy carbon (GC) cathode; T = 303 K, GC cathode (5.0 cm<sup>2</sup>), rare earth chlorides ( $2.0 \times 10^{-3}$  mol 1<sup>-1</sup>), Bu'<sub>4</sub>NClO<sub>4</sub> (0.2 mol 1<sup>-1</sup>, MeCO<sub>2</sub>H (7.0 mol 1<sup>-1</sup>), CH<sub>2</sub>Cl<sub>2</sub> (6.2 mol 1<sup>-1</sup>), cyclohexane (1.85 mol 1<sup>-1</sup>), O<sub>2</sub> gas (5 ml min<sup>-1</sup>);  $\bullet = EuCl_3$ ,  $\Box = LaCl_3$ ,  $\Delta = SmCl_3$ 

These results suggest that an alkyl radical intermediate is involved in the epoxidation. Generation of an alkyl radical intermediate may be responsible for the cleavage of the C=C bond of stilbene and styrene during the epoxidation and non-selective epoxidation of cyclohexene.<sup>1</sup>

### Electrochemical study

In order to gain information on the oxidation state of europium, electrochemical studies have been carried out. Fig. 1 shows the oxygenation of cyclohexane as a function of the cathode potential. The oxidation of cyclohexane did not proceed at all in the absence of rare earth catalyst under the potential conditions in Fig. 1. The oxidation of cyclohexane to cyclohexanone and cyclohexanol occurred with addition of



**Fig. 2** Cyclic voltammetry of EuCl<sub>3</sub>, Eu(MeCO<sub>2</sub>)<sub>3</sub> and Eu(ClO<sub>4</sub>)<sub>3</sub>; scan rate 200 mV s<sup>-1</sup>, T = 303 K, GC cathode (0.07 cm<sup>2</sup>), rare earth chloride ( $2.0 \times 10^{-3}$  mol l<sup>-1</sup>), Bu'<sub>4</sub>NClO<sub>4</sub> (0.2 mol l<sup>-1</sup>), MeCO<sub>2</sub>H (7.0 mol l<sup>-1</sup>), CH<sub>2</sub>Cl<sub>2</sub> (8.05 mol l<sup>-1</sup>), atmosphere of Ar; (*a*) (----) EuCl<sub>3</sub>, (*b*) (----) Eu(MeCO<sub>2</sub>)<sub>3</sub> and (*c*) (----) Eu(ClO<sub>4</sub>)<sub>3</sub>

EuCl<sub>3</sub>, LaCl<sub>3</sub> or SmCl<sub>3</sub>. These results prove that EuCl<sub>3</sub>, LaCl<sub>3</sub> and SmCl<sub>3</sub> work as mediators for the electrochemical oxygenation as shown in Fig. 1. In the case of EuCl<sub>3</sub>, the rate of the oxygenation gradually increased with decreasing cathode potential from -0.1 to -0.4 V (vs. Ag/AgCl). When the potential decreased from -0.4 to -0.5 V, the rate of the oxygenation increased abruptly. In the case of LaCl<sub>3</sub> and SmCl<sub>3</sub>, this sudden enhancement in the rate was not observed. The cathode potential for the sudden increase in the rate of oxygenation observed for EuCl<sub>3</sub> in Fig. 1 roughly corresponds to the standard redox potential of Eu<sup>3+</sup>/Eu<sup>2+</sup> (-0.55 V vs. Ag/AgCl). The standard redox potential of Sm<sup>3+</sup>/Sm<sup>2+</sup> (-1.75 V) is far more negative compared to that of Eu<sup>3+</sup>/Eu<sup>2+</sup>, and for La<sup>2+</sup> does not exist. The results in Fig. 1 strongly suggest that the dramatic enhancement in the rate of oxygenation is due to electrochemical reduction of Eu<sup>3+</sup> to Eu<sup>2+</sup>.

To study further the electrochemical redox reactions of europium, we have measured cyclic voltammetry (CV) under similar conditions to those of potentiostatic studies. Fig. 2 shows the electrochemical redox reaction of some Eu salts [EuCl<sub>3</sub>·6H<sub>2</sub>O, Eu(MeCO<sub>2</sub>)·6H<sub>2</sub>O and Eu(ClO<sub>4</sub>)<sub>3</sub>·6H<sub>2</sub>O], in an atmosphere of Ar without addition of cyclohexane. A couple was not observed in the absence of Eu salts. Different CV spectra for the couples of Eu<sup>3+</sup>/Eu<sup>2+</sup> were observed for the three Eu salts. This suggests



**Fig. 3** Cyclic voltammetry of EuCl<sub>3</sub> and O<sub>2</sub>; scan rate 200 mV s<sup>-1</sup>, T = 303 K, GC cathode (0.07 cm<sup>2</sup>), Bu'<sub>4</sub>NClO<sub>4</sub> (0.2 mol 1<sup>-1</sup>), MeCO<sub>2</sub>H (7.0 mol 1<sup>-1</sup>), CH<sub>2</sub>Cl<sub>2</sub> (6.2 mol 1<sup>-1</sup>), cyclohexane (1.85 mol 1<sup>-1</sup>); (a) (-----) presence of EuCl<sub>3</sub> (2.0 × 10<sup>-3</sup> mol 1<sup>-1</sup>) in an atmosphere of Ar, (b) (-----) without EuCl<sub>3</sub> in an atmosphere of O<sub>2</sub>, (c) (---) presence of EuCl<sub>3</sub> (2.0 × 10<sup>-3</sup> mol 1<sup>-1</sup>) in an atmosphere of O<sub>2</sub>

that the counter-anion of Eu salts plays an important role in the active Eu species in the reaction mixture.

In the case of EuCl<sub>3</sub>, a reduction peak of Eu<sup>3+</sup> to Eu<sup>2+</sup> at --0.28 V (vs. Ag/AgCl) and an oxidation peak of Eu<sup>2+</sup> to Eu<sup>3+</sup> at +0.05 V were observed. The difference between these peak potentials for the redox of Eu<sup>3+</sup>/Eu<sup>2+</sup>,  $\Delta E_p = 0.33$  V, was 5.8 fold larger than the value estimated from theory for an electrochemically reversible system (0.0565 V). Thus, the redox reaction of Eu<sup>3+</sup>/Eu<sup>2+</sup> in this system is electrochemically irreversible; the rate of electrochemical reaction of Eu<sup>3+</sup>/Eu<sup>2+</sup> over the GC electrode was slow.

Fig. 3 shows some CV spectra in the presence of cyclohexane. The CV spectrum of (a) was measured for the redox reaction of EuCl<sub>3</sub> in an atmosphere of Ar. The reduction peak of Eu<sup>3+</sup> to Eu<sup>2+</sup> shifted to negative potential. The CV spectrum of (b) was measured in an atmosphere of  $O_2$  without EuCl<sub>3</sub>. Electrochemical reduction of  $O_2$  to  $O_2^-$  over GC was observed (peak at -1.4 V),<sup>19</sup> with  $O_2^-$  being produced below -0.3 V. An oxidation peak of  $O_2^-$  was not observed because of the fast successive protonation and the formation of H<sub>2</sub>O<sub>2</sub> [eqn. (2)].<sup>19</sup> The CV

$$O_2^- + H^+ \longrightarrow HO_2^- \longrightarrow 1/2 H_2O_2 + O_2$$
 (2)

spectrum of (c) was measured in the presence of EuCl<sub>3</sub> in an atmosphere of O<sub>2</sub>. The oxidation peak of Eu<sup>2+</sup> to Eu<sup>3+</sup> was not observed. This suggests that O<sub>2</sub><sup>-</sup> is produced by the chemical reduction of O<sub>2</sub> with Eu<sup>2+</sup> [eqn. (3)]. The reduction of O<sub>2</sub> was

$$Eu^{2+} + O_2 \longrightarrow Eu^{3+} + O_2^{-}$$
(3)

mediated by Eu<sup>3+</sup>/Eu<sup>2+</sup> reaction. In the cathode potential between -0.4 and -0.5 V, where the sudden increase in the oxidation activity was observed, the electrochemical formation of Eu<sup>2+</sup> and O<sub>2</sub><sup>-</sup> was observed.

The standard redox potential of  $Zn^{2+}/Zn^{0}$  is -0.97 V (Ag/AgCl). Therefore, Eu<sup>3+</sup> can be reduced to Eu<sup>2+</sup> by Zn powder which is indispensable in the EuCl<sub>3</sub> system for the monoxy-genations. The redox potential of Sm<sup>3+</sup>/Sm<sup>2+</sup> (-1.75 V) is far more negative than that of Zn<sup>2+</sup>/Zn<sup>0</sup>, and for La<sup>2+</sup> does not exist. Thus, La<sup>2+</sup> and Sm<sup>2+</sup> cannot exist in their catalytic systems. Therefore, La<sup>3+</sup> and Sm<sup>3+</sup> should perform as catalysts in these catalytic systems.

### **Reaction scheme**

A model of the active form of the europium catalyst, complex A, is shown in Scheme 1 and is proposed on the basis that the CV spectrum of  $Eu(MeCO_2)_3$  is very different from that of



EuCl<sub>3</sub> and the catalytic activity of Eu(MeCO<sub>2</sub>)<sub>3</sub> is lower than that of EuCl<sub>3</sub>.<sup>1</sup> The monooxygenation may be initiated by the active oxygen species generated from complex A.

Eu<sup>2+</sup> has an electron shell structure of [Xe]4f<sup>7</sup>. Gd<sup>3+</sup> has the same structure of [Xe]4f<sup>7</sup> but the catalytic activity of GdCl<sub>3</sub> was lower than those of LaCl<sub>3</sub> and SmCl<sub>3</sub>. Therefore, the electronic structure of [Xe]4f<sup>7</sup> is not important and the redox reaction of Eu<sup>3+</sup>/Eu<sup>2+</sup> may be a key factor for the monooxygenation.

It is hypothesized that an  $O_2$  coordinated on the Eu<sup>2+</sup> of A is reductively activated, generating the active oxygen species. The reactivities of O\*-EuCl<sub>3</sub>, O\*-LaCl<sub>3</sub> and O\*-SmCl<sub>3</sub> together with those of well-known systems are summarized in Table 5. Evidently, different reactivities are shown between O\*-EuCl<sub>3</sub> and O\*-LaCl<sub>3</sub> or O\*-SmCl<sub>3</sub>. The electrophilicities of active oxygen species estimated from the ratios of primary: secondary: tertiary are OH (Fenton)<sup>10,11</sup>  $< O^*$ - $EuCl_3 < O^*-LaCl_3, O^*-SmCl_3 < RO_2^{(autooxidation)} > 1.8 < P^{+}-$ Fe<sup>4+</sup>= $O.^{3-9}$  The results of the KIE, the C<sub>5</sub>/C<sub>6</sub> factor and the retention of the substrate configuration in the products suggest that the cleavage of the C-H bond is the rate determining step and an alkyl radical intermediate is formed during the oxidation of alkanes in the rare earth catalytic systems. However, alkyl radical coupling products, such as dicyclohexyl or diadamantyl, were not produced.<sup>1</sup> This fact suggests that the H' abstraction process might not simply be a metalcatalysed autoxidation. In the case of the epoxidation, the formation of the alkyl radical intermediates is proposed because the configuration of the substrate was not preserved during the epoxidation. However, the electrophilicity of O\*-EuCl<sub>3</sub> is proposed for the epoxidation because hex-2-enes are more reactive than hex-1-enes. These experimental facts indicate that the nature of the active oxygen generated in the rare earth catalytic system has both radical character and electrophilicity and is different from those of Fenton,<sup>10,11</sup> Gif<sup>12-14</sup> and metalloporpyrin systems.<sup>3-9</sup> This double character of O\*-EuCl<sub>3</sub> made it possible to oxygenate sulfur compounds and aromatics. It is not certain whether this double character of O\*-EuCl<sub>3</sub> comes from the unique active oxygen or from two independent species.

If the reduction of  $O_2$  is caused by the oxidation of  $Eu^{2+}$ ,  $Eu^{3+} \cdots O_2^{-}(H^+)$  may be produced according to eqn. (4). A free

$$O_2 + Eu^{2+} + (H^+) \longrightarrow Eu^{3+} \cdots O_2^{-}(H^+)$$
(4)

 $O_2^-$  or HO<sub>2</sub><sup>•</sup> is not the active oxygen species for the monooxygenation because the very low reactivity of a free  $O_2^-$  or HO<sub>2</sub><sup>•</sup> was previously reported.<sup>19</sup> It is suggested that the formation of Eu<sup>2+</sup> and  $O_2^-$  over a GC cathode is important for the oxidation. We speculate that  $O_2^-$  or HO<sub>2</sub><sup>•</sup> might be further activated

Table 5 Comparison for the reactivities of some catalytic oxidation systems

A		Alkene			Retention of c	configuration/%	
		1°:2°:3°	KIE	C <sub>5</sub> /C <sub>6</sub>	Alkane ox.	Alkene epox.	
	EuCl <sub>3</sub>	1:6:19	2.6	0.66	0 <sup>h</sup> 3 <sup>i</sup>	8	
	LaCl <sub>3</sub>	1:15:94	3.7	0.38	0*3'	8	
	SmCl <sub>3</sub>	1:13:84	3.6	0.41	j	j	
	OH.ª	1:4.7:10	1.1	1.14	i	k	
	RO <sub>1</sub> ••	1:18:134	1.0		5		
	Gif	1:3:~3	2.0~2.3	0.6~0.85	j	k	
	Fe-TPPC1						
	(PhIO) <sup>4</sup>	1.25.150	6~9	i	90	~100	
	$(O_2, Zn, MeCO_2H)^{\epsilon}$	1.25.150	2.3	0.45	0	j	
	Mn-TPPCl						
	(PhIO) <sup>f</sup>	1:59:600	2~5	j	j	~100	
	$(O_2, Zn, MeCO_2H)^g$	():1:20	2.8	0.7	25%	>90	

<sup>a</sup> From refs. 8, 9, 11 and 12. <sup>b</sup> Refs. 4 and 16. <sup>c</sup> Refs. 11 and 12. <sup>d</sup> Ref. 3. <sup>e</sup> Ref. 7. <sup>f</sup> Refs. 5 and 6. <sup>g</sup> Ref. 6. <sup>h</sup> Obtained from the *cis*- and *trans*-1,2dimethylcyclohexane oxidation. <sup>i</sup> Obtained from the *cis*- and *trans*-decalin oxidation. <sup>j</sup> Not measured. <sup>k</sup> The reaction does not proceed.

through a redox reaction of  $Eu^{3+}/Eu^{2+}$  [eqn. (5)]. However, the

$$Eu^{3*} \cdots O_2^{-}(H^*) + e^{-} \longrightarrow Eu^{2*} \cdots O_2^{-}(H^*) \times (\longrightarrow \longrightarrow O^* - Eu^{3*})$$
 (5)

definitive form of the active oxygen cannot be identified at this moment.

Further investigations are needed to clarify the working state of the Eu species, the nature of the active oxygen species in EuCl<sub>3</sub>, LaCl<sub>3</sub> and SmCl<sub>3</sub> systems and the reaction mechanisms for the monooxygenations.

### Experimental

### General procedure and materials

The standard procedure for the monooxygenation of hydrocarbons was as follows. Rare earth salts were dissolved in a stirred solution of carboxylic acid, as a proton donor, and a solvent in a three-necked flask with a reflux condenser. Then a reactant and Zn powder, as an electron donor, was added to the solution and the reaction was started by stirring the mixture with a magnetic stirrer under a stream of O<sub>2</sub> at 40 °C. The reaction was continued for 1 h. All the reagents were commercial products (Tokyo Kasei, Wako Pure Chemical and Aldrich), used without further purification. The products were analysed by gas chromatography (Shimazu GC-14A) with PEG-20M over OV-1 capillary columns (0.25 mm i.d.  $\times$  25 m).

# Regioselectivity of the primary, secondary and tertiary C-H bonds

The regioselectivities were estimated from the product yields of the oxidations of hexane and adamantane per C-H bond. The oxidations were carried out as below; EuCl<sub>3</sub>·6H<sub>2</sub>O, LaCl<sub>3</sub>·6H<sub>2</sub>O or SmCl<sub>3</sub>·6H<sub>2</sub>O (0.03 mmol,  $6.00 \times 10^{-3}$  mol l<sup>-1</sup>) was dissolved in a solution of MeCO<sub>2</sub>H (2 ml, 7.06 mol l<sup>-1</sup>) and CH<sub>2</sub>Cl<sub>2</sub> (2 ml) in a flask. Then, hexane (1 ml, 1.53 mol l<sup>-1</sup>) or adamantane solution (0.05 g in CH<sub>2</sub>Cl<sub>2</sub> of 1 ml, 7.40 × 10<sup>-2</sup> mol l<sup>-1</sup>) and Zn (1.0 g, 15.3 mmol) was added to the mixture. The reaction was allowed to continue under a stream of O<sub>2</sub> (1 atm, 5 ml min<sup>-1</sup>) at 40 °C for 1 h. The products were analysed by GC. The ratios of primary: secondary and secondary: tertiary were defined as shown in eqns. (6) and (7).

Primary: secondary =

 $\frac{[hexan-1-ol + hexan-1-a]]/6}{[hexan-2-ol + hexan-2-one + hexa-3-nol + hexan-3-one]/8}$ (6)

2516 J. Chem. Soc., Perkin Trans. 2, 1996

Secondary: tertiary =

$$\frac{[adamantan-2-ol + adamantan-2-one]/12}{[adamantan-1-ol]/4}$$
(7)

### The C<sub>5</sub>/C<sub>6</sub> parameter <sup>15</sup>

The parameter of  $C_5/C_6$  was estimated from the initial conversion rates of the cooxidation for cyclopentane and cyclohexane per C-H bond. The cooxidation was carried out as below; EuCl<sub>3</sub>·6H<sub>2</sub>O, LaCl<sub>3</sub>·6H<sub>2</sub>O or SmCl<sub>3</sub>·6H<sub>2</sub>O (0.03 mmol, 6.00 × 10<sup>-3</sup> mol 1<sup>-1</sup>) was dissolved in a solution of MeCO<sub>2</sub>H (2 ml, 7.06 mol 1<sup>-1</sup>) and CH<sub>2</sub>Cl<sub>2</sub> (2 ml) in a flask. Then, a mixture of c- $C_5H_{10}$  (0.5 ml, 1.06 mol 1<sup>-1</sup>) and c- $C_6H_{12}$  (0.5 ml, 0.926 mol 1<sup>-1</sup>) and Zn (1.0 g, 15.3 mmol) were added to the mixture. The reaction continued under a stream of O<sub>2</sub> (1 atm, 5 ml min<sup>-1</sup>) at 40 °C for 1 h. The products were analysed by GC. The parameter of  $C_5/C_6$  was defined as shown in eqn. (8), where

$$C_{5}/C_{6} = \frac{([c-C_{5}H_{9}OH + c-C_{5}H_{8}O]/10)[C_{5}H_{10}]^{0}}{([c-C_{6}H_{11}OH + c-C_{6}H_{10}O]/12)/[C_{6}H_{12}]^{0}}$$
(8)

 $[C_5H_{10}]^0$  and  $[C_6H_{12}]^0$  are the initial concentrations of c-C<sub>5</sub>H<sub>10</sub> and c-C<sub>6</sub>H<sub>12</sub>, respectively.

# Retention of configuration for the alkane oxidation

The retention of configuration for tertiary C-H bonds was studied during the oxidations of *cis*- and *trans*-dimethylcyclohexanes and *cis*- and *trans*-decalins. The oxidations were carried out as detailed below. EuCl<sub>3</sub>·6H<sub>2</sub>O or LaCl<sub>3</sub>·6H<sub>2</sub>O (0.03 mmol,  $6.00 \times 10^{-3} \text{ mol } 1^{-1}$ ) was dissolved in a solution of MeCO<sub>2</sub>H (7.06 mol  $1^{-1}$ ) and CH<sub>2</sub>Cl<sub>2</sub> (2 ml). Then *cis*-dimethylcyclohexane (1 ml, 1.39 mol  $1^{-1}$ ), *trans*-dimethylcyclohexane (1 ml, 1.43 mol  $1^{-1}$ ), *cis*-decalin (1 ml, 1.30 mol  $1^{-1}$ ) or *trans*-decalin (1 ml, 1.26 mol  $1^{-1}$ ) and Zn (1.0 g, 15.3 mmol) were added to the mixture. The reaction continued under a stream of O<sub>2</sub> (1 atm, 5 ml min<sup>-1</sup>) at 40 °C for 1 h. The products were analysed by GC.

### Measurement of kinetic isotope effects

The kinetic isotope effects (K1E) were measured for the oxidation of cyclohexane by GC-mass spectrometry (Shimadzu QP2000A). A detailed experimental procedure has already been reported.<sup>1,2</sup> The oxidations were carried out as detailed below. EuCl<sub>3</sub>·6H<sub>2</sub>O, LaCl<sub>3</sub>·6H<sub>2</sub>O or SmCl<sub>3</sub>·6H<sub>2</sub>O (0.03 mmol,  $6.00 \times 10^{-3}$  mol 1<sup>-1</sup>) was dissolved in a solution of MeCO<sub>2</sub>H (7.06 mol 1<sup>-1</sup>) and CH<sub>2</sub>Cl<sub>2</sub>(2 ml). Then, a mixture of c-C<sub>6</sub>D<sub>12</sub>(0.5 ml, 0.924 mol 1<sup>-1</sup>) and c-C<sub>6</sub>H<sub>12</sub> (0.5 ml, 0.926 mol 1<sup>-1</sup>) and Zn (1.0 g, 15.3 mmol) were added to the mixture. The reaction continued under a stream of O<sub>2</sub> (1 atm, 5 ml min<sup>-1</sup>) at 40 °C for 1 h.

# Oxidation of sulfur compounds

The oxidations of Ph<sub>2</sub>S and Ph<sub>2</sub>SO were carried out as detailed below. EuCl<sub>3</sub>·6H<sub>2</sub>O (0.03 mmol,  $6.00 \times 10^{-3}$  mol 1<sup>-1</sup>) was dissolved in a solution of MeCO<sub>2</sub>H (2 ml, 7.06 mol l<sup>-1</sup>) and CH<sub>2</sub>Cl<sub>2</sub> (2 ml). Then, Ph<sub>2</sub>S solution (0.112 g in 1 ml CH<sub>2</sub>Cl<sub>2</sub>, 0.12 mol  $1^{-1}$ ) or Ph<sub>2</sub>SO solution (0.121 g in 1 ml CH<sub>2</sub>Cl<sub>2</sub>, 0.12 mol  $1^{-1}$ ) and Zn (1.0 g, 15.3 mmol) were added to the mixture. The reaction was allowed to continue under a stream of O2 (1 atm, 5 ml min<sup>-1</sup>) at 40 °C for 1 h. The products were analysed by GC.

### Hydroxylation of benzene and toluene

The hydroxylations were carried out as detailed below. EuCl<sub>3</sub>·6H<sub>2</sub>O (0.03 mmol,  $6.00 \times 10^{-3} \text{ mol } l^{-1}$ ) was dissolved in a solution of MeCO<sub>2</sub>H (2 ml, 7.06 mol l<sup>-1</sup>) and CH<sub>2</sub>Cl<sub>2</sub> (2 ml). Then, benzene  $(1 \text{ ml}, 2.22 \text{ mol } l^{-1})$  or toluene (1 ml, 1.88 mol) $1^{-1}$ ) and Zn (1.0 g, 15.3 mmol) were added to the mixture. The reaction was allowed to continue under a stream of O<sub>2</sub> (1 atm, 5 ml min<sup>-1</sup>) at 40 °C for 1 h. The products were analysed by GC.

### Retention of configuration for epoxidations

The retention of configuration for C=C bonds was studied during the epoxidation of *cis*-stilbene and *cis*- and *trans*-hex-2enes. The oxidations were carried out as detailed below. EuCl<sub>3</sub>·6H<sub>2</sub>O or LaCl<sub>3</sub>·6H<sub>2</sub>O (0.03 mmol,  $6.00 \times 10^{-3} \text{ mol } 1^{-1}$ ) was dissolved in a solution of  $MeCO_2H$  (7.06 mol  $l^{-1}$ ) and CH<sub>2</sub>Cl<sub>2</sub> (2 ml). Then, cis-stilbene (1 ml, 1.13 mol l<sup>-1</sup>), cis-hex-2ene (1 ml, 1.63 mol  $1^{-1}$ ) or *trans*-hex-2-ene (1 ml, 1.61 mol  $1^{-1}$ ) and Zn (1.0 g, 15.3 mmol) were added to the mixture. The reaction was allowed to continue under a stream of  $O_2$  (1 atm, 5 ml min<sup>-1</sup>) at 40 °C for 1 h. The products were analysed by GC.

### Electrochemical oxidation

A conventional electrochemical cell with the cathode and the anode separated by sintered glass was used for the electrochemical oxidation of cyclohexane. A glassy carbon (5 cm<sup>2</sup>) cathode, a Pt-black/Pt-plate anode and a Ag/AgCl [0.197 V vs. normal hydrogen electrode (NHE)] reference electrode were used for these experiments. The composition of the catholyte (25 ml) was  $EuCl_3$  (2.00 × 10<sup>-3</sup> mol 1<sup>-1</sup>),  $Bu'_4NClO_4$  (0.20 mol 1<sup>-1</sup>),  $MeCO_2H$  (7.06 mol 1<sup>-1</sup>),  $CH_2Cl_2$  (6.20 mol 1<sup>-1</sup>) and cyclohexane (1.85 mol  $l^{-1}$ ). O<sub>2</sub> gas (5 ml min<sup>-1</sup>) was bubbled into the catholyte in the cathode. The cathode potential was controlled by a potentiostat (HOKUTO Co., HA-301) and a function generator (HB-104).

### Measurement of cyclic voltammetry (CV)

CV spectra of EuCl<sub>3</sub>, Eu(ClO<sub>4</sub>)<sub>3</sub> and Eu(MeCO<sub>2</sub>)<sub>3</sub> were measured using the same cell with a GC working-electrode (0.07 cm<sup>2</sup>) under similar conditions to those described above. The scan rate was 200 mV  $s^{-1}$ .

## References

- 1 I. Yamanaka, K. Nakagaki and K. Otsuka, J. Chem. Soc., Chem. Commun., 1995, 1185; I. Yamanaka, T. Akimoto, K. Nakagaki and K. Otsuka, Chem. Lett., 1994, 1717; I. Yamanaka, T. Akimoto and K. Otsuka, Chem. Lett., 1994, 1514; I. Yamanaka, T. Akimoto, K. Nakagaki and K. Otsuka, J. Mol. Catal. A., 1996, 110, 119.
- 2 I. Yamanaka and K. Otsuka, J. Mol. Catal. A., 1995, 95, 115; J. Mol. Catal., 1993, 83, L15; J. Chem. Soc., Faraday Trans., 1994, 90, 451.
- 3 B. Meunier, in Metalloporphyrins Catalyzed Oxidations, eds. F. Montanari and L. Casella, Kluwer Academic Publishers, Netherlands, 1994, p. 1.
- 4 J. T. Groves and T. E. Nemo, J. Am. Chem. Soc., 1983, 105, 5786; J. Am. Chem. Soc., 1983, **105**, 6243. 5 M. J. Nappa and C. A. Tolman, *Inorg. Chem.*, 1985, **24**, 4711. 6 B. R. Cook, T. J. Reinert and K. S. Suslick, J. Am. Chem. Soc.,
- 1986, 108, 7281.
- 7 W. Y. Lu, J. F. Bartoli and D. Mansuy, New J. Chem., 1992, 16, 621; P. Battioni, J. P. Renaud, J. F. Bartoli, M. Reina-Artles, M. Fort and D. Mansuy, J. Am. Chem. Soc., 1988, 110, 791.
- 8 E. I. Karasevich, B. L. Anisimova, V. L. Rubailo and A. E. Shilov, Kinet. Catal. Engl. Trans., 1993, 34, 577; Kinet. Catal. Engl. Trans., 1993, 34, 583; E. I. Karasevich, A. M. Khenkin and A. E. Shilov, J. Chem. Soc., Chem. Commun., 1987, 731.
- 9 A. E. Shilov and E. I. Karasevich, in Metalloporphyrins Catalyzed Oxidations, eds. F. Montanari and L. Casella, Kluwer Academic Publishers, Netherlands, 1994, p. 87.
- 10 Trotman-Dickenson, Adv. Free-Radical Chem., 1965, 1, 1; C. Walling, Acc. Chem. Res., 1975, 8, 125; E. S. Rudakov, L. K. Volkava, V. P. Tret'yakov and V. V. Zamashchikov, Kinet. Catal. Engl. Trans., 1982, 23, 18.
- 11 Shilov, Activation of Saturated Hydrocarbons by Transition Metal Complexes, Reidel, Netherlands, 1984.
- 12 D. H. R. Barton, Acc. Chem. Res., 1992, 504; D. H. R. Barton, J. Boivin, M. J. Gastiger, J. Morzycki, R. S. Hay-Motherwell, W. B. Motherwell, N. Ozbalik and K. M. Schwarzentruber, J. Chem. Soc., Perkin Trans. 2, 1986, 947.
- 13 D. H. R. Barton and D. T. Sawyer, in The Activation of Dioxygen and Homogeneous Catalytic Oxidation, ed. D. H. R. Barton et al., Plenum Press, New York, 1993, p. 1.
- 14 G. Balavoine, D. H. R. Barton, Y. V. Geletii and D. R. Hill, in The Activation of Dioxygen and Homogeneous Catalytic Oxidation, ed. D. H. R. Barton et al., Plenum Press, New York, 1993, p. 255
- 15 E. S. Rudakov, Reactions of Alkanes with Oxidants, Metal Complexes, and Radicals in Solutions, Naukova Dumka, Kiev, 1985.
- 16 D. T. Sawyer, L. Spencer and H. Sugimoto, Isr. J. Chem., 1987/88, 28. 3.
- 17 S. Oae, Y. Watanabe and K. Fujimori, Tetrahedron Lett., 1982, 23, 1187; W. Ando, R. Tajima and T. Takata, Tetrahedron Lett., 1982, 23, 1605.
- 18 J. E. Bennett, D. M. Brown and B. Mile, Trans. Faraday Soc., 1970, 66, 386.
- 19 D. T. Sawyer, Oxygen Chemistry, Oxford University Press, New York, 1991.

Paper 6/01373B Received 26th February 1996 Accepted 1st July 1996