PAMAM dendron-stabilised palladium nanoparticles: effect of generation and peripheral groups on particle size and hydrogenation activity[†]

Tomoo Mizugaki,^a Makoto Murata,^a Sayaka Fukubayashi,^a Takato Mitsudome,^a Koichiro Jitsukawa^a and Kiyotomi Kaneda^{*ab}

Received (in Cambridge, UK) 16th July 2007, Accepted 11th October 2007 First published as an Advance Article on the web 24th October 2007 DOI: 10.1039/b710860e

Dendron stabilised Pd nanoparticles were prepared using the self-assembly of dendrons, which could catalyze a highly selective hydrogenation of dienes and acetylenes to monoenes.

Dendrons, wedge-like molecules composed of a core, divergent branching units, and, end groups, have generated interest because of their great potential in tailoring highly ordered structures and functions.^{1,2} Self-assembly of dendrons can afford spherically shaped architectures similar to micelles and vesicles.³ A variety of subunits have been reported to create well-defined and finely tuned capsule structures, which are expected to provide integrated functional nano-materials in combination with metal species such as metal complexes and particles.^{4,5} The dendritic shell can act as a stabilizer for active metal species in organic syntheses, where the internal branch units function as solvents or additives to facilitate catalytic reactions.

Metal nanoparticles have an extremely large surface area to volume ratio, which can be highly tunable to create various nanoscale objects. Applications of these metal nanoparticles are widely expanding in areas such as catalysis, sensor devices, and nanoelectronics.⁶ Since their function strongly depends on the metal particle size, preparation of size-regulated nanoparticles is a crucial yet challenging problem.⁷ In particular, the precise control of particle sizes in the single nanometer (<10 nm) range is of current interest in developing high performance catalysts for organic synthesis. Although there have been many reports on the stabilization of metal nanoparticles such as Pd, Pt and Au using dendrimers⁵ and dendrons,⁸ the range of particle size has been limited to between 1-3 nm. In the present paper, we describe poly(amidoamine) (PAMAM) dendrons having a pyridine core and alkyl end groups assembled into spherical micelle-like structures. The size of Pd nanoparticles prepared in situ by these dendrons can be controlled by chemical reduction. To our knowledge, this is the first example of the controlled synthesis of Pd nanoparticles with a wide size range between 3 to 10 nm using dendron assemblies. The obtained dendritic Pd nanocomposites catalyse selective hydrogenation of dienes and acetylenes, where the dendron units provide multiple functionalities for the Pd nanoparticles, *e.g.*, templates for Pd nanoparticle formation, ligands for active intermediates, and specific interactions with substrates.

PAMAM dendrons with a pyridine core unit were synthesized using a divergent method from the reaction of 4-picolylamine with methyl acrylate and ethylenediamine,^{8b} and their terminal ester moieties were alkylated by *n*-hexylamine [G_n Py–C₆ (n = 1–3), Fig. 1]. Similarly, using dodecylamine instead of hexylamine gave G_n Py–C₁₂. Their structures were characterized using ¹H NMR spectroscopy, dynamic light scattering (DLS) measurements and TEM imaging. After complexation of [PdCl(C₃H₅)]₂ with the above dendrons in dichloromethane, reduction of the palladium complex with addition of 2 equivalents of LiB(Et)₃H gave a homogeneous dark solution. Notably, the obtained palladium nanoparticles [**1a** G₁ Py–C₆ Pd(0), **2a** G₂ Py–C₆ Pd(0), and **3a** G₃ Py–C₆ Pd(0)] were stable for several months due to the encapsulation effect of the globular assemblies of the dendrons.

¹H NMR spectra of G_n Py–C₆ and G_n Py–C₁₂ exhibited broad signals due to the internal methylenes at around δ 3.2 ppm and the pyridyl core at δ 8.4 and 7.3 ppm, suggesting a reversed micelle-like assembly for the dendrons.⁹ DLS and TEM imaging provided information about the size of the dendritic Pd nanoparticles as



Fig. 1 Synthesis of G₁ to G₃ amidoamine dendrons (G_n Py–C_m: n = 1-3, m = 6, 12) and the dendron-assembly encapsulated Pd nanoparticles G_n Py–C_m Pd(0). (i) excess methyl acrylate, (ii) excess alkyl amine (x = 5, 11), (iii) excess ethylenediamine, (iv) [PdCl(C₃H₅)]₂ in CH₂Cl₂, (v) LiBEt₃H in THF.

^aDepartment of Materials Engineering Science, Graduate School of Engineering Science, Osaka University, 1-3 Machikaneyama, Toyonaka, Osaka, 560-8531, Japan. E-mail: kaneda@cheng.es.osaka-u.ac.jp; Fax: +81-6-6850-6260; Tel: +81-6-6850-6260

^bResearch Center for Solar Energy Chemistry, Osaka University, 1-3 Machikaneyama, Toyonaka, Osaka, 560-8531, Japan

[†] Electronic supplementary information (ESI) available: Experimental details. See DOI: 10.1039/b710860e

shown in Table 1 and Fig. 2. DLS measurement of the dendrons revealed the formation of globular assemblies in CH₂Cl₂ with average diameters of 10.8 \pm 1.7, 10.9 \pm 2.0, and 11.8 \pm 1.7 nm for G_1 , G_2 , and G_3 Pv–C₆ (entries 1–3), respectively. Adding the Pd complex to the dendrons did not alter their size distributions, and even after reduction of the Pd complex, the size distributions for 1a, 2a and 3a were similar to those of the parent dendron assemblies (entries 4-6). From TEM images, the average Pd nanoparticle sizes for G_1 , G_2 , and G_3 Py–C₆ dendrons were 6.8 \pm 2.0(1a), 5.3 \pm 1.7(2a), and 5.1 \pm 1.9 nm(3a), respectively. By changing the C₆ alkyl chain to a C₁₂ chain, G₁, G₂, and G₃ Py-C₁₂ dendrons gave smaller Pd nanoparticles of 4.6 \pm 1.9(1b), 3.6 \pm 1.3(2b) and $3.5 \pm 1.3(3b)$, respectively (entries 10–12). Furthermore, the G₂ Py-CO₂Me dendron without an alkyl chain forms a large spherical assembly with an average diameter of 15.6 ± 2.0 nm, where the Pd nanoparticles of 10.6 ± 2.8 nm were accommodated within the dendron assembly (entries 13 and 14). From these results, it is clear that the end group of the dendron strongly influences and controls the size of Pd nanoparticles. Also, increasing the generation of the dendron decreases the size of the Pd nanoparticles. According to the results by DLS and TEM measurements, the size distribution of the dendron assemblies agreed well with the distribution derived from the combination of the Pd nanoparticle and dendron sizes.[‡] These self-assembled dendrons can thus form monolayer capsules with polar voids to act as controllable templates for Pd nanoparticles with the wide size range from 3 to 10 nm.^{8b} This is the first example of the size regulation of Pd nanoparticles by dendron assemblies.

In order to examine the catalytic activity of the dendron Pd nanoparticles, the hydrogenation of olefins and acetylenes was carried out. The dendron Pd catalysts show high selectivity for hydrogenation of conjugated dienes to the corresponding monoenes. For example, using **1a–3a**, 1,3-cyclooctadiene exclusively gave cyclooctene (Table 2). The reactivity toward the monoene was much lower than that toward the diene; cyclohexene was barely hydrogenated compared to 1,3-cyclohexadiene. The initial hydrogenation rates increased with increasing generation of the dendrons: the G_3 dendron catalyst (**3a**) showed the highest catalytic activity among G_1 , G_2 , and G_3 . These findings are interpreted in terms of accessibility of the substrate to the

 Table 1
 Average diameter of dendron assemblies and Pd nanoparticles by DLS and TEM measurements

		Average diameter/nm			
Entry	Dendron	DLS ^a	Pd^b		
1	G ₁ Ру–С ₆	10.8 ± 1.7			
2	$G_2 Py-C_6$	10.9 ± 2.0			
3	$G_3 Py-C_6$	11.8 ± 1.7			
4	G_1 Py– C_6 Pd(0) 1a	10.5 ± 1.6	6.8 ± 2.0		
5	G_2 Py-C ₆ Pd(0) 2a	11.0 ± 1.7	5.3 ± 1.7		
6	G_3 Py-C ₆ Pd(0) 3a	12.5 ± 2.6	5.1 ± 1.9		
7	$G_1 Py-C_{12}$	9.4 ± 1.4			
8	$G_2 Py-C_{12}$	10.1 ± 1.6	_		
9	$G_3 Py-C_{12}$	11.2 ± 1.7			
10	$G_1 Py-C_{12} Pd(0) 1b$	9.5 ± 1.6	4.6 ± 1.9		
11	$G_2 Py-C_{12} Pd(0) 2b$	10.0 ± 1.5	3.6 ± 1.3		
12	$G_3 Py-C_{12} Pd(0) 3b$	11.4 ± 1.8	3.5 ± 1.3		
13	G ₂ Py–COOMe	15.6 ± 2.0			
14	G ₂ Py–COOMe Pd(0)	15.7 ± 3.3	$10.6~\pm~2.8$		
^a Measured in CH ₂ Cl ₂ at 25 °C. ^b Measured by TEM images.					



Fig. 2 TEM images of Pd nanoparticles encapsulated within the G_2 dendrons; (a) G_2 Py–CO₂Me Pd(0), (b) G_2 Py–C₆ Pd(0) (**2a**), (c) G_2 Py–C₁₂ Pd(0) (**2b**). and (d) the size distributions of **2a**.

Table 2 Hydrogenation of conjugated dienes catalysed by dendron-
encapsulated Pd nanoparticle^a

	cat	, H ₂ 1 atm		
	\sim	r.t.	n =	/n 1, 3
	TOF (mol H ₂ /mol Pd min)			
Substrate	Dendron	$\overline{G_1}$	G_2	G ₃
n =1	Gn-C ₆	5.2	6.4	12.5
n = 3	Gn-C ₆	4.3	5.5	12.3
n = 3	Gn-C12	6.0	9.6	20.3
^a Reaction	conditions: subs	trate 1.0 m	mol, Pd 5.0	µmol, dendron

82 μmol, CH₂Cl₂ 3 mL.

palladium active site; the increasing dendron generation provides a less congested particle surface.^{8e} In the case of unimolecular dendrimer encapsulated Pd nanoparticles, the surface active sites were passivated by the highly congested surface and branching units in the higher generation dendrimers.^{5f} The above generation effect of the dendrons was also observed with dendrons having C₁₂ alkyl groups. The C₁₂ dendron Pd nanoparticles of **1b–3b** showed higher catalytic activities than **1a–3a** having C₆ alkyl groups, as shown in Table 2, which might be due to the smaller Pd nanoparticles. The above high monoene selectivities in the hydrogenation of conjugated dienes were similar to the results by PPI dendrimer-encapsulated Pd nanoparticle catalysts.^{5f}

In the hydrogenation of 1-phenyl-1-propyne, catalyst **3a** gave a 96% yield of 1-phenyl-1-propene (E/Z = 2/98) together with 4% of 1-phenylpropane at 100% conversion of the substrate (Scheme 1). The monoene selectivity is much superior to that of the Lindlar catalyst under the same reaction conditions: 54% yield of 1-phenyl-1-propene (E/Z = 8/92) and 46% of propylbenzene were obtained when the conversion of 1-phenyl-1-propyne reached 100% as shown in Scheme 1. Also, cinnamyl alcohol (E/Z = 2/98) was obtained in 97% yield together with 3% of 3-phenyl-1-propanol in the hydrogenation of 3-phenyl-1-propyne-1-ol.¹⁰ The above high selectivity for monoenes using the dendron stabilised Pd nanoparticle is due to the ligand effect of the pyridine core of the dendrons.^{11,12}§

R ₁ ————————————————————————————————————	cat. H ₂ 1 atm,	R_1	~~ ^R 2 + R	R_2
(R ₁ , R ₂)	catalyst	time(min)	yields(%) ^a	
Ph, CH ₃	3a	60	96 (2/98)	4
	Lindlar	30	54 (8/92)	46
Ph, CH ₂ OH	3a	180	97 (2/98)	3
	Lindlar	40	92 (2/97)	8

Scheme 1 Hydrogenation of alkynes using 3a and Lindlar catalyst. Reaction conditions are in similar to those in Table 2. ^a Figures in parentheses are the selectivity of the (*E*)- and (*Z*)-olefins.



Scheme 2 Intermolecular competitive hydrogenation of 3-phenyl-2-propyn-1-ol (ol) and 1-phenyl-1-propyne (yn) catalysed by **2a**. R_{ol} and R_{yn} are the initial hydrogenation rates of ol and yn, respectively.

Furthermore, the effect of the surrounding dendron branches was emphasized in the intermolecular competitive hydrogenation between 3-phenyl-2-propyn-1-ol and 1-phenyl-1-propyne using **2a** as shown in Scheme 2. The initial hydrogenation rate for 3-phenyl-2-propyn-1-ol (R_{ol}) was greater than that for 1-phenyl-1-propyne (R_{yn}) by a factor of 28, although the hydrogenation rate ratio for individual hydrogenations of 3-phenyl-2-propyn-1-ol and 1-phenyl-1-propyne was 2.1. Clearly, the hydrogenation of an acetylenic compound is accelerated by the hydroxyl group of the substrate through hydrogen bonding with the amide groups within the dendron.¹³

In conclusion, we demonstrated the preparation of supramolecular dendritic Pd(0) nanoparticles utilizing self-assembly of dendrons. Fine tuning of the Pd nanoparticle size ranging from 3 nm to 10 nm was achieved by adjusting the alkyl chain length and the generation of the dendrons. The dendron units provide multiple functionalities to the Pd nanoparticles: (1) templates and stabilizing agents for the palladium nanoparticles, (2) ligands of active sites adjusting the catalytic activity and selectivity, and (3) binding hosts by hydrogen bonding between the amido group of the dendron and the oxygen group of the substrate. Further investigations on the size controllability of these dendrons for high performance metal nanoparticle catalysts are underway.

This work was carried out with partial support from the Grantin-Aid for Scientific Research from the Ministry of Education, Culture, Sports, Science, and Technology of Japan (17656263, 18360389), and from the Grant-in-Aid for Scientific Research on Priority Areas (No.18065016, "Chemistry of Concerto Catalysis") from the Ministry of Education, Culture, Sports, Science, and Technology of Japan. TEM experiments were carried out by using a facility in the Research Center for Ultrahigh Voltage Electron Microscopy, Osaka University. We thank the Center of Excellence (21COE) program "Creation of integrated EcoChemistry", Osaka University.

Notes and references

[‡] The molecular sizes of G_1 , G_2 , and G_3 Py–Cn dendrons calculated by Chem 3D are 1.8, 2.5, and 3.2 nm for C_6 and 2.4, 3.1, and 3.8 nm for C_{12} , respectively.

§ The Lindlar catalyst was obtained from N. E. ChemCat.

- Dendrimers and Other Dendritic Polymers, ed. J. M. J. Fréchet and D. A. Tomalia, Wiley & Sons, New York, 2001.
- 2 For excellent reviews on supramolecular dendritic catalysts, see: (a) R. van Heerbeek, P. C. J. Kamer, P. W. N. M. van Leeuwen and J. N. H. Reek, *Chem. Rev.*, 2002, **102**, 3717–3756; (b) S. M. Grayson and J. M. J. Fréchet, *Chem. Rev.*, 2001, **101**, 3819–3868; (c) D. Astruc and F. Chardac, *Chem. Rev.*, 2001, **101**, 2991–3024.
- 3 S. Hecht and J. M. J. Fréchet, Angew. Chem., Int. Ed., 2001, 40, 74-91.
- 4 For recent reports on dendritic metal complex catalysts, see: Pd: (a) T. Iwasawa, M. Tokunaga, Y. Obora and Y. Tsuji, J. Am. Chem. Soc., 2004, **126**, 6554-6555; (b) M. Ooe, M. Murata, T. Mizugaki, K. Ebitani and K. Kaneda, J. Am. Chem. Soc., 2004, **126**, 1604–1605; (c) K. Heuzé, D. Méy, D. Gauss and D. Astruc, Chem. Commun., 2003, **18**, 2274–2275Rh; (d) M. Q. Slagt, S.-E. Stiriba, H. Kautz, R. J. M. K. Gebbink, H. Frey and G. van Koten, Organometallics, 2004, **23**, 1525–1532Rh; (e) B. Yi, Q.-H. Fan, G.-J. Deng, Y.-Mi. Li, L.-Q. Qiu and A. S. C. Chan, Org. Lett., 2004, **6**, 1361–1364; (f) J. P. K. Reynhardt and H. Alper, J. Org. Chem., 2003, **68**, 8353–8360.
- Recent examples of dendritic metal nanoparticle catalysts, see: (a) L. Wu, B.-L. Li, Y.-Y. Huang, H.-F. Zhou, Y.-M. He and Q.-H. Fan, Org. Lett., 2006, 8, 3605–3608; (b) Y. Jiang and Q. Guo, J. Am. Chem. Soc., 2006, 128, 716–717; (c) H. Ye, R. W. J. Scott and R. M. Crooks, Langmuir, 2004, 20, 2915–2920; (d) K. Esumi, R. Isono and T. Yoshimura, Langmuir, 2004, 20, 237–243; (e) R. W. J. Scott, H. Ye, R. R. Henriquez and R. M. Crooks, Chem. Mater., 2003, 15, 3873–3878; (f) M. Ooe, M. Murata, T. Mizugaki, K. Ebitani and K. Kaneda, Nano Lett., 2002, 2, 999–1002.
- Recent reviews on metal nanoparticles, see: (a) C. Burda, X. Chen, R. Narayana and M. A. El-Sayed, *Chem. Rev.*, 2005, **105**, 1025–1102; (b) M.-C. Daniel and D. Astruc, *Chem. Rev.*, 2004, **104**, 293–346; (c) H. Bönnemann and R. M. Richards, *Eur. J. Inorg. Chem.*, 2001, 2455–2480; (d) G. Schmid, M. Bäumle, M. Geerkens, I. Heim, C. Osemann and T. Sawitowski, *Chem. Soc. Rev.*, 1999, **28**, 179–185.
- 7 O. M. Wilson, M. R. Knecht, J. C. Garcia-Martinez and R. M. Crooks, J. Am. Chem. Soc., 2006, 128, 4510–4511.
- 8 Typical examples of dendron protected metal nanopartcles: (a) R. C. Advincula, *Dalton Trans.*, 2006, 2778–2784; (b) M. Murata, Y. Tanaka, T. Mizugaki, K. Ebitani and K. Kaneda, *Chem. Lett.*, 2005, 34, 272–273; (c) G. Jiang, L. Wang, T. Chen, H. Yu and J. Wang, *Nanotechnology*, 2004, 15, 1716–1719; (d) C. S. Love, V. Chechik, D. K. Smith and C. Brennan, *J. Mater. Chem.*, 2004, 14, 919–923; (e) K. R. Gopidas, J. K. Whitesell and M. A. Fox, *J. Am. Chem. Soc.*, 2003, 125, 6491–6502.
- 9 I. Gistov and J. M. J. Frechet, Macromolecules, 1993, 26, 6536-6546.
- 10 Highly selective hydrogenation of alkynes to monoenes was achieved using nitrogen additives such as quinolines: R. L. Augustine, in Heterogeneous Catalysis for the Synthetic Chemists, Marcel Dekker, New York, 1996, ch. 16, p. 387.
- 11 The phosphine dendron-stabilized Pd nanoparticle catalyst gave quantitative formation of alkanes from alkynes. See ref. 5a.
- 12 The dendron catalyst is stable and no precipitation was observed after complete conversion of the alkynes.
- 13 Dendrimer-encapsulated Pd nanoparticles showed similar selectivity through an attractive hydrogen bonding interaction between the dendrimers and the functional group of the substrate. See ref. 5f.