

Article

## Photocatalytic Cross-coupling of Methanol and Formaldehyde on a Rutile TiO2(110) Surface

Qing Yuan, Zongfang Wu, Yuekang Jin, Lingshun Xu, Feng Xiong, Yunsheng Ma, and Weixin Huang J. Am. Chem. Soc., Just Accepted Manuscript • DOI: 10.1021/ja400978r • Publication Date (Web): 14 Mar 2013 Downloaded from http://pubs.acs.org on March 15, 2013

### Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



Journal of the American Chemical Society is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036

Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

# Photocatalytic Cross-coupling of Methanol and Formaldehyde on a Rutile $TiO_2(110)$ Surface

Qing Yuan, Zongfang Wu, Yuekang Jin, Lingshun Xu, Feng Xiong, Yunsheng Ma, Weixin Huang\*

Hefei National Laboratory for Physical Sciences at the Microscale, CAS Key Laboratory of Materials for Energy Conversion, and Department of Chemical Physics, University of Science and Technology of China, Hefei 230026, China.

**ABSTRACT**: The photocatalytic oxidation of methanol on a rutile  $TiO_2(110)$  surface was studied by means of thermal desorption spectroscopy (TDS) and x-ray photoelectron spectroscopy (XPS). The combined TDS and XPS results unambiguously identify methyl formate as the product in addition to formaldehyde. By monitoring the evolution of various surface species during the photocatalytic oxidation of methanol on  $TiO_2(110)$ , XPS results give direct spectroscopic evidence for the formation of methyl formate as the product of photocatalytic cross-coupling of chemisorbed formaldehyde with chemisorbed methoxy species and clearly demonstrate that the photocatalytic dissociation of chemisorbed methanol to methoxy species occurs and contributes to the photocatalytic oxidation of methanol. These results not only greatly broaden and deepen the fundamental understanding of photochemistry of methanol on the TiO<sub>2</sub> surface but also demonstrate a novel green and benign photocatalytic route for the synthesis of esters directly from alcohols or from alcohols and aldehydes.

#### **1. INTRODUCTION**

Photocatalysis has received remarkable interest as a green and sustainable solution for the energy and environmental issues since Fujishima and Honda's first reports of UV-light-induced redox chemistry on TiO<sub>2</sub>.<sup>1</sup> Among various photocatalytic reactions, the photocatalytic conversion of methanol is of particular importance. Methanol as a hole scavenger greatly enhances the activity of photocatalysts in photocatalytic splitting of water to hydrogen.<sup>2</sup> The photocatalysis of methanol is also prominent in environmental photocatalysis,<sup>3</sup> photocatalytic selective oxidation<sup>4</sup> and photocatalytic reforming reactions.<sup>5</sup> Meanwhile, as a simple prototype for many organic compounds, methanol is adopted as the probe molecule for the fundamental studies of complex photocatalytic reactions on oxide surfaces.

Many experimental and theoretical studies have been performed to study the chemistry and photochemistry of methanol on the rutile  $TiO_2(110)$  surface, a typical model catalyst of  $TiO_2$ .<sup>6-10</sup> Methanol dissociates primarily on oxygen vacancies and steps of  $TiO_2(110)$  surface; on the ideal  $TiO_2(110)$  surface methanol molecularly chemisorbs but arguments still exist on whether methanol can dissociate on the  $Ti^{4+}$  sites or not.<sup>11-26</sup> Recently, the photochemistry of methanol on the  $TiO_2(110)$  surface has been explored.<sup>24,27-32</sup> Methanol can be photocatalyzed into formaldehyde and chemisorbed methoxy species was identified to be the active species. Henderson et al. proposed that chemisorbed methoxy species is formed only by the thermal dissociation of methanol on  $TiO_2(110)$ .<sup>27,30,31</sup> Yang et al. proposed that molecularly chemisorbed methoxy species the photocatalytic dissociation to form chemisorbed methoxy species.<sup>24,29,32</sup> However, by far, only formaldehyde has been observed as the product of methanol photocatalytic oxidation on  $TiO_2(110)$  surface, which is in the dramatic contrast to the rich photochemistry of methanol on  $TiO_2-based$  catalysts. Meanwhile, only very

 few spectroscopic studies have been reported on the photochemistry of methanol on rutile  $TiO_2(110)$  surface.<sup>33,34</sup>

In a just appeared work Phillips et al.<sup>35</sup> firstly reported the sequential photooxidation of methanol to methyl formate on  $TiO_2(110)$  covered with O adatoms by means of thermal desorption spectroscopy (TDS), scanning tunneling microscopy (STM) and theoretical calculations. Very recently Guo et al.<sup>36</sup> also reported the formation of methyl formate as the product of photooxidation of methanol on bare  $TiO_2(110)$  by means of TDS. Here we report our combined TDS and x-ray photoelectron spectroscopy (XPS) study of methanol photocatalytic oxidation on the bare  $TiO_2(110)$  surface in which methyl formate was observed as the product in addition to formaldehyde. By monitoring the evolution of various surfaces species during the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface, our XPS results for the first time give direct spectroscopic evidence for the formation of methyl formate as the product of photocatalytic cross-coupling of chemisorbed formaldehyde with chemisorbed methanol to methoxy species and clearly demonstrate that the photocatalytic dissociation of methanol.

#### 2. EXPERIMENTAL SECTION

All experiments were performed in a Leybold stainless-steel ultrahigh vacuum (UHV) chamber with a base pressure of  $1.2 \times 10^{-10}$  mbar. The UHV chamber was equipped with facilities for x-ray photoelectron spectroscopy with the newly-installed XR 50 x-ray source (SPECS GmbH) and PHBIOS 100 MCD hemispherical energy analyzer (SPECS GmbH), ultraviolet photoelectron spectroscopy, low energy electron diffraction, and differential-pumped thermal desorption spectroscopy. The rutile TiO<sub>2</sub>(110) single crystal purchased from MaTeck was mounted onto a Ta support plate (1 mm thick and of the same dimensions as the crystal)

with a high temperature alumina-based inorganic adhesive (Aremco 503) and graphite powder (99.9995%, Alfa Aesar China Co., Ltd.). The Ta support was cooled and resistively heated by two Ta wires spot-welded to its back side. The sample temperature could be controlled between 100 and 1273 K and was measured by a chromel-alumel thermocouple spot-welded to the backside of the sample. Prior to experiments, the  $TiO_2(110)$  sample was cleaned by repeated cycles of Ar ion sputtering and annealing at 1000 K for 10min until LEED giving a sharp (1×1) diffraction pattern and no contaminants could be detected by XPS.

Methanol (99.8%, Sinopharm Chemical) was purified by repeated freeze-pump-thaw cycles. Formaldehyde was generated via thermal decomposition of paraformaldehyde (95%, Sinopharm Chemical) in a glass tube connected to the UHV apparatus. Prior to experiments, paraformaldehyde was thoroughly degassed by the overnight pumping at 60 °C. The purity of all reactants was checked by QMS prior to experiments. A line-of-sight stainless steel doser (diameter: 8 mm) positioned ~ 2 cm in front of the TiO<sub>2</sub>(110) surface was used for the exposures of methanol and formaldehyde to keep the chamber pressure below  $5\times10^{-10}$  torr. The doser could be retracted 50 mm after the exposure. All exposures were reported in Langmuir (1 L =  $1.0\times10^{-6}$  Torr·s) without corrections for the gauge sensitivity. During the TDS measurements, the sample was positioned ~1 mm away from a collecting tube of a differential-pumped QMS and the heating rate was 2 K/s. XPS spectra were recorded using the Mg K $\alpha$  radiation (hv = 1253.6 eV) with a pass energy of 20 eV. The C 1s XPS spectrum was peak-fitted with the XPSPEAK software (Version 4.1) and the line shape (%Gaussian-Lorentzian = 80%) and full-width at the half-maximum (1.50 eV) were fixed during the peak-fitting process.

The UV irradiation was accomplished using a 100 W high-pressure Hg arc lamp (Oriel 6281) which provides a pressure-broadened emission spectrum from gaseous Hg in the UV-light region.

When the light wavelength is below 250 nm, the light irradiance of this source decreases rapidly and is only 0.05 mW/m<sup>2</sup> for the 200 nm light at a distance of 0.5 m.<sup>37</sup> The absorption of methanol in the UV region below 200 nm can thus be neglected under our experimental condition. A water filter was used to remove the IR portion of the emission spectrum. The UVlight was focused onto the tip of a single strand, 0.6 mm diameter fused silica fiber optic cable that directed the light through a UHV-compatible feedthrough onto the TiO<sub>2</sub>(110) face without exposure to extraneous surfaces. An exposure of TiO<sub>2</sub>(110) crystal at 110 K to the UV-light resulted in the rising of crystal temperature no more than 3 K.

#### **3. RESULTS AND DISCUSSION**

Figure 1A shows CH<sub>3</sub>OH TDS spectra from TiO<sub>2</sub>(110) surfaces covered with 1.80, 0.97, 0.42 and 0.15 ML (1 ML =  $5.2 \times 10^{14}$  sites-cm<sup>-2</sup>) adsorbed methanol that could be reproducibly prepared by a 0.014 L CH<sub>3</sub>OH exposure at 110 K, a 0.014 L CH<sub>3</sub>OH exposure at 110 K followed by the flash to 160, 230 and 300 K, respectively. Agreeing with previous results,<sup>15-18</sup> four CH<sub>3</sub>OH desorption features were observed at ~154, ~210, ~330 and ~495 K, respectively corresponding to the molecular desorption of physisorbed CH<sub>3</sub>OH, CH<sub>3</sub>OH(a) chemisorbed on the bridging-bonded O sites, CH<sub>3</sub>OH(a) chemisorbed on the Ti<sup>4+</sup> sites, and the recombinative desorption of methoxy species (CH<sub>3</sub>O(a)). The saturating coverage of CH<sub>3</sub>OH(a) chemisorbed on the Ti<sup>4+</sup> sites was herein defined as 0.77 ML.<sup>15,26</sup> Figure 1B shows C 1s XPS spectra after the TiO<sub>2</sub>(110) surface covered with 1.80 ML adsorbed methanol was flashed to elevated temperatures. The TiO<sub>2</sub>(110) surface covered with 1.80 ML adsorbed methanol gives an intense and broad C 1s peak with the binding energy at 287.5 eV, corresponding to adsorbed CH<sub>3</sub>OH(a).<sup>18</sup> Flashing the surface to elevated temperatures desorbs adsorbed CH<sub>3</sub>OH(a) from the surface and results in the weakening of C 1s XPS feature at 287.5 eV; meanwhile, the existence of additional C 1s feature becomes evident. For examples, the C 1s XPS spectrum of the surface flashed to 300 K is broadened and asymmetric, and that of the surface flashed to 350 K exhibits a weak peak centering at 286.9 eV. Thus we performed the peak-fitting analysis of the C 1s XPS spectra of surfaces flashed to elevated temperatures and found that these C 1s XPS spectrum could be well fitted with two components with the binding energy at 287.5 and 286.9 eV. The C 1s feature at 286.9 eV can be assigned to be  $CH_3O(a)$  species on  $TiO_2(110)$ .<sup>18</sup> These XPS results agree with previous reports of the formation of methoxy species upon methanol adsorption on TiO<sub>2</sub>(110). Estimated from the integrated peak areas of C 1s features, the coverages of CH<sub>3</sub>OH(a) and CH<sub>3</sub>O(a) are respectively 1.73 and 0.07 ML on TiO<sub>2</sub>(110) surface exposed to 0.014 L CH<sub>3</sub>OH at 110 K. The coverage of CH<sub>3</sub>OH(a) decreases to 0.90, 0.35, 0.08, and 0 ML after the surface was flashed to 160, 230, 300, and 350 K, respectively; correspondingly, the coverage of CH<sub>3</sub>O(a) initially does not vary, then decreases to 0.05 ML after the flash at 350 K and disappears after the flash at 750 K, corresponding to the recombinative desorption of methanol. As shown in Figure 2A, adsorbed CH<sub>3</sub>OH(a) gives the O 1s binding energy at 534.0 eV. Due to the strong interference arising from TiO<sub>2</sub> surface, the O 1s binding energy of chemisorbed CH<sub>3</sub>O(a) species could not be unambiguously identified, but is likely located at ~532.3 eV indicated from the O 1s XPS difference spectra (Figure 2B).

Figure 3 shows TDS spectra of m/z=31, 29 and 60 signals after the TiO<sub>2</sub>(110) surface covered with 0.42 ML adsorbed methanol was irradiated by the UV-light for different times. After a 30s' irradiation, the methanol desorption peak at ~330 K weakens (Figure 3A & 3B), meanwhile, a new desorption feature appears at ~270 K in the TDS spectrum of m/z=29 signal (Figure 3B) that can be assigned to desorption of formaldehyde. This suggests the UV-light-induced photocatalytic oxidation of chemisorbed methanol to chemisorbed formaldehyde on the TiO<sub>2</sub>(110) surface, agreeing with previous reports.<sup>27,32</sup> With the prolonging of irradiation time,

the methanol desorption peak keeps decreasing, and the formaldehyde desorption feature reaches the maximum after a 1min's irradiation but then keeps decreasing. The decrease of formaldehyde desorption feature is accompanied by the appearance and growth of a new desorption feature at ~230 K in the TDS spectra of both m/z=29 and m/z=31 signals. We have thus performed a careful scan of likely species by mass spectroscopy and found the desorption of the m/z=60 signal that is also located at ~230 K (Figure 4). As shown in Figure 3C, the desorption feature of m/z=60 signal is neglectable after a 30s' irradiation but then keep growing with the prolonging of the irradiation time. As shown in Figure 4, the desorption features of m/z=60, 31, 29 signals at ~230 K vary in the same trend under all investigated experimental conditions, demonstrating that these signals arise from the same species. Thus the TDS results demonstrate the formation of another product as well as formaldehyde that exhibits m/z signals of 60, 31, 29 in its mass spectrum.

The photocatalytic oxidation of 0.42 ML adsorbed methanol on the  $TiO_2(110)$  surface was further studied with XPS (Figure 5A). The C 1s features of chemisorbed CH<sub>3</sub>OH(a) and CH<sub>3</sub>O(a) were observed respectively at 287.5 and 286.9 eV on the surface prior to the irradiation. After irradiation, a new C 1s feature with the binding energy at 288.4 eV evolves. The adsorption of formaldehyde on the  $TiO_2(110)$  surface was comparatively studied by XPS and the C 1s binding energy of adsorbed formaldehyde on the  $TiO_2(110)$  surface was determined to be 288.5 eV (Figure 6A). Figure 5B compares the intensity variation of different C 1s features as a function of the irradiation time. With the prolonging of the irradiation time the total intensity does not vary much, but the C 1s feature at 287.5 eV keeps weakening while that at 288.4 eV keeps growing; the C 1s feature at 286.9 eV weakens after a 1min's irradiation, then does not change much, and grows a bit after a 20min's irradiation. Figure 5C shows C 1s XPS spectra after the TiO<sub>2</sub>(110) surface covered with 0.42 ML adsorbed methanol was irradiated for 20min and then flashed to elevated temperatures. The corresponding intensity variation of different C 1s features as a function of the flashing temperature is displayed in Figure 5D. Three C 1s features at 286.9, 287.5 and 288.4 eV are present on the surface subjected to a 20min's irradiation. After flashing to 240 K, the features at 286.9 and 288.4 eV weaken simultaneously, corresponding to the desorption peak of m/e=60, 31 and 29 signals at ~230 K in the TDS spectra; the further flashing to 290 K results in the disappearance of the feature at 288.4 eV and the weakening of the feature at 287.5 eV, corresponding to the desorption peak of formaldehyde at ~270 K and the partial desorption of chemisorbed CH<sub>3</sub>OH(a), respectively; the feature at 287.5 eV disappears and the feature at 286.9 eV weakens after the flash at 450 K and the surface restores to the clean one after flashing to 750 K, corresponding to the desorption of chemisorbed CH<sub>3</sub>OH(a) and the recombinative desorption of chemisorbed CH<sub>3</sub>O(a). It could be seen that the coverages of various surface species estimated from XPS measurement of the  $TiO_2(110)$  surface covered with 0.42 ML adsorbed methanol directly irradiated for 20min (Figure 5D) differ from those estimated from XPS measurement of the same starting surface with the same total irradiation time whose irradiation and subsequent XPS measurement were divided into four sequences (the last data in Figure 5B). This indicates that the efficiency of photocatalytic reaction should be sensitive to the employed experimental procedure.

Above TDS and XPS results clearly demonstrate that in addition to previously reported formaldehyde, a new product is formed during the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface under our investigated conditions. This product gives m/z=60, 31, 29 signals in the mass spectroscopy and gives two C 1s features with the binding energy at 286.9 and 288.4 eV in the XPS spectrum. We thus identified the product to be methyl formate (HCOOCH<sub>3</sub>). Kominami et al. observed the selective oxidation of methanol to methyl formate over powder TiO<sub>2</sub> photocatalysts irradiated by UV-light and heated at elevated temperatures <sup>38</sup> and our results

clearly demonstrate the formation of methyl formation during the photocatalytic oxidation of methanol on TiO<sub>2</sub>(110) surface under UHV conditions. Chemisorbed formaldehyde formed by the photocatalytic oxidation of methanol on  $TiO_2(110)$  surface participates the reaction forming methyl formate and likely surface reactions include (i) the thermally-activated cross-coupling of formaldehyde and methanol as reported on Au surfaces,<sup>39</sup> (ii) the photocatalytic cross coupling of formaldehyde and methanol, (iii) the esterification of formic acid intermediate formed by oxidation of formaldehyde with methanol, and (iv) the dimerization of formaldehyde via Tishchenko-type reaction.<sup>40</sup> Kominami et al. proposed that the photocatalytic oxidation of methanol to methyl formate mainly proceeds through the intermediate of formaldehyde followed by its thermal-activated dimerization.<sup>38</sup> We performed controlled experiments of adsorption and (thermal/photocatalytic) reaction of formaldehyde and coadsorption and (thermal/photocatalytic) reaction of formaldehyde and methanol on the  $TiO_2(110)$  surface. Figure 6B shows TDS spectra after the TiO<sub>2</sub>(110) surface was exposed to 0.01 L HCHO at 110 K. Besides the molecular desorption of formaldehyde at 288 K, only a weak desorption trace of C<sub>2</sub>H<sub>4</sub> was observed at 690 K that arises from the subsurface Ti interstitials or surface oxygen vacancies-mediated coupling reaction of formaldehyde on TiO<sub>2</sub>(110) surface.<sup>41,42</sup> Figure 6C shows TDS spectra after the TiO<sub>2</sub>(110) surface was exposed to 0.01 L HCHO at 110 K followed by a UV-light irradiation for 20 min. Comparing with Figure 6B, the desorption trace of m/z=27 grows and broadens, demonstrating that the UV-light irradiation can induce surface reactions of formaldehyde on the TiO<sub>2</sub>(110) surface which will be discussed elsewhere. No formation of formic acid and methyl formate was observed during the adsorption and (thermal/photocatalytic) reaction of formaldehyde on the TiO<sub>2</sub>(110) surface at 110 K. Figure 7A shows TDS spectra after the TiO<sub>2</sub>(110) surface was exposed to 0.42 ML methanol and subsequently to 0.01 L HCHO at 110 K. The desorption traces of methanol and formaldehyde dominate the TDS spectra and the

formation of methyl formate (m/z=60) was not observed. Figure 7B shows TDS spectra after the TiO<sub>2</sub>(110) surface was exposed to 0.42 ML methanol and subsequently to 0.01 L HCHO at 110 K followed by a UV-light irradiation for 5 min. Besides the desorption traces of methanol and formaldehyde, the desorption trace of methyl formate (m/z=60) was clearly observed at ~220 K. The results of these controlled experiments unambiguously prove that methyl formate is formed on the TiO<sub>2</sub>(110) surface at 110 K by the photocatalytic cross coupling of formaldehyde and methanol instead of dimerization of formaldehyde proposed by Kominami et al.<sup>38</sup> Therefore, the formation of methyl formate during the photocatalytic oxidation of methanol on the  $TiO_2(110)$ surface consists of two sequential photocatalytic reactions (Figure 8): the photocatalytic oxidation of methanol to formaldehyde followed by the photocatalytic cross coupling of formaldehyde and methanol. Concerning the photocatalytic cross coupling mechanism, Phillips et al.<sup>35</sup> proposed the involvement of a transient HCO intermediate made photochemically from formaldehyde but Guo et al.<sup>36</sup> argued that such a transient HCO intermediate was not necessary. Since all the photocatalytic oxidation reactions occur on the  $TiO_2(110)$  surface at 110 K, the photocatalytic cross coupling between aldehydes and alcohols catalyzed by TiO<sub>2</sub> should be facile and might be developed to a novel green and benign route to synthesize esters directly from alcohols or from alcohols and aldehydes.

Our TDS results (Figure 3) demonstrate the photocatalytic oxidation of methanol to formaldehyde dominates the initial 1min's photocatalytic oxidation of methanol on the TiO<sub>2</sub>(110) surface, thus the decrease of the C 1s peak at 286.9 eV and the appearance and growth of the C 1s peak at 288.4 eV in the corresponding XPS results (Figure 5A & 5B) suggest the formation of formaldehyde by the photocatalytic oxidation of methoxy species on the surface. These observations agree with previous reports<sup>27,30</sup> that chemisorbed methoxy species on the Ti<sup>4+</sup> sites of TiO<sub>2</sub>(110) surface is the active species in the photocatalytic oxidation of methanol to

formaldehyde. Beyond 1min, both photocatalytic oxidation of methanol to formaldehyde and photocatalytic cross-coupling of methanol and formaldehyde occur on the surface, the C 1s peak at 288.4 eV in the XPS spectra contributed by both formaldehyde and methyl formate reasonably keeps growing but the C 1s peak at 286.9 eV in the XPS spectra contributed by both methoxy species and methyl formate does not decreases as expected since the methoxy species continuously gets supplied by the dissociation of chemisorbed methanol (Figure 5A & 5B). The dissociation of chemisorbed methanol on the  $Ti^{4+}$  sites of  $TiO_2(110)$  surface to the methoxy species during the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface occurs via two likely mechanisms: one is that the photocatalytic oxidation of methoxy species shifts the thermal equilibrium between chemisorbed methanol and methoxy species toward the formation of methoxy species, as proposed by Henderson et al.;<sup>27,30,31</sup> the other is the photocatalytic dissociation of chemisorbed methanol to the methoxy species as proposed by Yang et al.<sup>24,29,32</sup> Since our XPS results provide the relative surface coverage variation of different surface species during the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface (Figure 5B), we performed the following preliminary reaction kinetic analysis to elucidate the mechanism of the dissociation of chemisorbed methanol the  $Ti^{4+}$  sites of  $TiO_2(110)$  surface to methoxy species.

Model I: Assuming that the dissociation of chemisorbed methanol to methoxy species is only thermally controlled at 110 K, it is plausible that the activation energy of the thermal dissociation reaction is low and the chemisorbed methanol and methoxy species are in the thermal equilibrium.<sup>27,30,31</sup> Thus the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface can be described as the following (O<sub>br</sub> means the bridging-bonded O sites of  $TiO_2(110)$  surface):

$$CH_{3}OH(a) + O_{br} \xleftarrow{K} CH_{3}O(a) + O_{br}H$$

$$CH_{3}O(a) + O_{br} \xrightarrow{hv, r_{2}} HCHO(a) + O_{br}H$$

$$CH_{3}O(a) + HCHO(a) + O_{br} \xrightarrow{hv, r_{3}} HCOOCH_{3}(a) + O_{br}H$$

And the surface coverage change of different surface species can be expressed as the following:

$$\frac{d[CH_3O(a)]}{dt} = 0$$
$$\frac{d[HCHO(a)]}{dt} = r_2 - r_3$$
$$\frac{d[HCOOCH_3(a)]}{dt} = r_3$$

And the peak intensity change of different C 1s features can be expressed as the following:

$$\frac{dI(288.4eV)}{dt} = \frac{d[HCHO(a)]}{dt} + \frac{d[HCOOCH_3(a)]}{dt} = r_2$$
$$\frac{dI(286.9eV)}{dt} = \frac{d[CH_3O(a)]}{dt} + \frac{d[HCOOCH_3(a)]}{dt} = r_3$$

Model II: Assuming that the dissociation of chemisorbed methanol to the methoxy species is photocatalytic, the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface can be described as the following:

$$CH_{3}OH(a) + O_{br} \xrightarrow{hv, r_{1}} CH_{3}O(a) + O_{br}H$$

$$CH_{3}O(a) + O_{br} \xrightarrow{hv, r_{2}} HCHO(a) + O_{br}H$$

$$CH_{3}O(a) + HCHO(a) + O_{br} \xrightarrow{hv, r_{3}} HCOOCH_{3}(a) + O_{br}H$$

And the surface coverage change of different surface species can be expressed as the following:

$$\frac{d[CH_3O(a)]}{dt} = r_1 - r_2 - r_3$$
$$\frac{d[HCHO(a)]}{dt} = r_2 - r_3$$
$$\frac{d[HCOOCH_3(a)]}{dt} = r_3$$

And the peak intensity change of different C 1s features can be expressed as the following:

$$\frac{dI(288.4eV)}{dt} = \frac{d[HCHO(a)]}{dt} + \frac{d[HCOOCH_3(a)]}{dt} = r_2$$
  
$$\frac{dI(286.9eV)}{dt} = \frac{d[CH_3O(a)]}{dt} + \frac{d[HCOOCH_3(a)]}{dt} = r_1 - r_2$$

The reaction kinetics following model I suggests that both the C 1s feature at 286.9 eV and the C 1s feature at 288.4 eV should increase with the prolonging of the irradiation time while that following model II suggests that with the prolonging of the irradiation time, the C 1s feature at 288.4 eV should increase and the peak intensity of the C 1s feature at 286.9 eV should depend on the reaction rates  $r_1$  and  $r_2$ . Comparing with the results shown in Figure 5B, particularly with the peak intensity change of the C 1s feature at 286.9 eV, model II is reasonable but model I is not. Therefore, our results clearly demonstrate that the photocatalytic dissociation of chemisorbed methanol on the Ti<sup>4+</sup> sites of TiO<sub>2</sub>(110) surface to the methoxy species occurs and contributes to the photocatalytic oxidation of methanol on TiO<sub>2</sub>(110) surface, although the thermal dissociation mechanism can not be excluded.

Phillips et al.<sup>35</sup> have just reported the sequential photooxidation of methanol to methyl formate on  $TiO_2(110)$  covered with O adatoms by means of thermal desorption spectroscopy (TDS), scanning tunneling microscopy (STM) and theoretical calculations. Very recently Guo et al.<sup>36</sup> reported the formation of methyl formate as the product of photooxidation of methanol on bare  $TiO_2(110)$  by means of TDS. Comparing with their work <sup>35,36</sup> in which the sequential photooxidation of methanol to methyl formate on the  $TiO_2(110)$  surface was evidenced by means

of TDS, our results are still of great significance and novelty. Firstly, our XPS results clearly demonstrate the evolution of various surfaces species during the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface and thus provide direct and unambiguous spectroscopic evidence for the formation of methyl formate as the product of photocatalytic cross-coupling of chemisorbed formaldehyde with chemisorbed methoxy species. Secondly, in Phillips et al.'s work  $^{35}$  the exposure of the employed TiO<sub>2</sub>(110) surface to O<sub>2</sub> was needed for the occurrence of the photooxidation of methanol to methyl formate but in both Guo et al.'s work<sup>36</sup> and our case such a pretreatment of TiO<sub>2</sub>(110) surface is not required. Phillips et al. proposed that the exposure of the TiO<sub>2</sub>(110) surface to O<sub>2</sub> acts to heal the TiO<sub>2</sub>(110) surface and that the O adatoms formed on TiO<sub>2</sub>(110) surface by O<sub>2</sub> exposure are not required for the photocatalytic reactions. As evidenced by the formation of CH<sub>3</sub>O(a) upon methanol adsorption and the formation of ethylene upon formaldehyde adsorption, our rutile  $TiO_2(110)$  sample is also with certain amounts of bulk defects and surface oxygen vacancies, however, the photooxidation of methanol to formaldehyde and methyl formate could occur without pretreatment. Thus it seems that the density of bulk defects in  $TiO_2(110)$  surface strongly affects the efficiency of the photocatalytic oxidation reactions of methanol. The light absorption and photo-excitation processes mainly occur in the bulk of  $TiO_2(110)$  sample, thus the bulk defects can serve as hole traps that severely suppress the participation of the holes into the photooxidation reaction occurring on the  $TiO_2(110)$  surface. Thirdly, our results clearly demonstrate that the photocatalytic dissociation of chemisorbed methanol on the  $Ti^{4+}$  sites of  $TiO_2(110)$  surface to the methoxy species occurs and contributes to the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface.

We have also compared the yield of methyl formate in the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surfaces covered with different amounts of adsorbed methanol

(Figure 9). The yield increases as the coverage of adsorbed methanol increases from 0.15 ML to 0.42 ML, thus the increase of methanol chemisorbed on the  $Ti^{4+}$  of  $TiO_2(110)$  is beneficial to the photocatalytic oxidation of methanol, supporting that methanol chemisorbed on the  $Ti^{4+}$  of  $TiO_2(110)$  is the photocatalytic active species. However, further increase of the coverage of adsorbed methanol from 0.42 ML to 0.97 ML results in the reduction of the yield of methyl formate, suggesting that the presence of  $CH_3OH(a)$  chemisorbed on the bridging-bonded O sites of  $TiO_2(110)$  surface should suppress the photocatalytic oxidation of methanol. A likely reason is that the adsorption of methanol on the bridging-bonded O sites of  $TiO_2(110)$  surface reduces the number of vacant bridging-bonded O sites available for the formation of surface hydroxyl, another surface intermediate formed in both the photocatalytic oxidation of methoxy species to formaldehyde and the photocatalytic cross-coupling of methoxy groups and formaldehyde. The desorption temperature of methyl formate from the surface was found to shift to the low temperature with the increase of methanol coverage, which could be attributed to the increasing repulsive interaction among surface adsorbates.

#### 4. Conclusions

In summary, we have successfully identified methyl formate as well as formaldehyde to be the products of the photocatalytic oxidation of methanol on the rutile  $TiO_2(110)$  surface. Direct spectroscopic evidence has been provided for the first time to unambiguously prove the formation of methyl formate as the product of the photocatalytic cross-coupling of chemisorbed formaldehyde with chemisorbed methoxy species and to clearly demonstrate that the photocatalytic dissociation of chemisorbed methanol to methoxy species on the  $Ti^{4+}$  sites of  $TiO_2(110)$  surface occurs and contributes to the photocatalytic oxidation of methanol on the  $TiO_2(110)$  surface. Our findings are valuable not only in the molecular-level understanding of

photocatalytic reactions over  $TiO_2$ -based photocatalysts but also in the development of green and benign photocatalytic route for the synthesis of esters directly from alcohols or from alcohols and aldehydes.

#### AUTHOR INFORMATION

#### **Corresponding Author**

huangwx@ustc.edu.cn (W.H.)

#### Notes

The authors declare no competing financial interest.

#### ACKNOWLEDGMENTS

This work was financially supported by National Basic Research Program of China (2013CB933104, 2010CB923301), National Natural Science Foundation of China (21173204), Chinese Academy of Sciences, MOE Fundamental Research Funds for the Central Universities.

#### REFERENCES

- (1) Fujishima, A.; Honda, K. Nature 1972, 238, 37.
- (2) Kawai, T.; Sakata, T. J. Chem. Soc. Chem. Commun. 1980, 5, 694.
- (3) Muggli, D.S.; Odland, M. J.; Schmidt, L. R. J. Catal. 2001, 203, 51.
- (4) Palmisano, G.; Augugliaro, V.; Pagliaro, M.; Palmisano, L. Chem Commun. 2007, 3425.
- (5) Chiarello, G. L.; Augirre, M. H.; Selli, E. J. Catal. 2010, 273, 182.
- (6) Linsebigler, A. L.; Lu, G.; Yates, J. T., Jr. Chem. Rev. 1995, 95, 735.
- (7) Diebold, U. Surf. Sci. Rep. 2003, 48, 53.
- (8) Thompson, T. L.; Yates, J. T., Jr. Chem. Rev. 2006, 106, 4428.

3
Δ
-
5
6
7
8
q
10
10
11
12
13
14
15
10
16
17
18
19
20
20
21
22
23
24
27 25
25
26
27
28
20
29
30
31
32
33
33
34
35
36
37
38
20
39
40
41
42
43
11
44
45
46
47
48
40
50
51
52
53
51
54
55
56
57
58
50
. 1.71

- (9) Pang, C. L.; Lindsay, R.; Thornton, G. Chem. Soc. Rev. 2008, 37, 2328.
- (10) Henderson, M. A. Surf. Sci. Rep. 2011, 66, 185.
- (11) Henderson, M. A.; Otero-Tapia, S.; Castro, M. E. Surf. Sci. 1998, 412/413, 252.
- (12) Bates, S. P.; Kresse, G.; Gillan, M. J. Surf. Sci. 1998, 409, 336.
- (13)Wang, L.-Q.; Ferris, K. F.; Winokur, J. P.; Shultz, A. N.; Baer, D. R.; Engelhard, M. H. J. Vac. Sci. Technol. A **1998**, *16*, 3034.
- (14) Bates, S. P.; Gillan, M. J.; Kresse, G. J. Phys. Chem. B 1998, 102, 2017.
- (15) Henderson, M. A.; Otero-Tapia, S.; Castro, M. E. Faraday Discuss. 1999, 114, 313.
- (16) Wong, G. S.; Kragten, D. D.; Vohs, J. M. J. Phys. Chem. B 2001, 105, 1366.
- (17) Farfan-Arribas, E.; Madix, R. J. J. Phys. Chem. B 2002, 106, 10680.
- (18) Farfan-Arribas, E.; Madix, R. J. Surf. Sci. 2003, 544, 241.
- (19)Onda, K.; Li, B.; Zhao, J.; Petek, H. Surf. Sci. 2005, 593, 32.
- (20)Zhang, Z.; Bondarchuk, O.; White, J. M.; Kay, B. D.; Dohnálek, Z. J. Am. Chem. Soc.
  2006, 128, 4198.
- (21)Sánchez de Armas, R.; Oviedo, J.; San Miguel, M. A.; Sanz, J. F. J. Phys. Chem. C 2007, 111, 10023.
- (22)Oviedo, R.; Sánchez de Armas, J.; San Miguel, M. A.; Sanz, J. F. J. Phys. Chem. C 2008, 112, 17737.
- (23) Zhao, J.; Yang, J.; Petek, H. Phys. Rev. B 2009, 80, 235416.
- (24)Zhou, C.; Ren, Z.; Tan, S.; Ma, Z.; Mao, X.; Dai, D.; Fan, H.; Yang, X.; Larue, J.; Cooper,
  R.; Wodtke, A. M.; Wang, Z.; Li, Z.; Wang, B.; Hou, J. *Chem. Sci.* 2010, *1*, 575.
- (25)Martinez, U.; Vilhelmsen, L. B.; Kristoffersen, H. H.; Stausholm-Møller, J.; Hammer, B. *Phys. Rev. B* **2011**, *84*, 205434.
- (26)Li, Z.; Scott, R. S.; Kay, B. D.; Dohnálek, Z. J. Phys. Chem. C 2011, 115, 22534.

- (27) Shen, M.; Henderson, M. A. J. Phys. Chem. Lett. 2011, 2, 2707.
- (28) Ahmed, A. Y.; Kandiel, T. A.; Oekermann, T.; Bahnemann, D. J. Phys. Chem. Lett. 2011, 2, 2461.
- (29)Zhou, C.; Ma, Z.; Ren, Z.; Mao, X.; Dai, D.; Yang, X. Chem. Sci. 2011, 2, 1980.
- (30) Shen, M.; Henderson, M. A. J. Phys. Chem. C 2012, 116, 18788.
- (31)Shen, M.; Acharya, D. P.; Dohnálek, Z.; Henderson, M. A. J. Phys. Chem. C 2012, 116, 25465.
- (32)Guo, Q.;Xu, C.; Ren, Z.; Yang, W.; Ma, Z.; Dai, D.; Fan, H.; Minton, T. K.; Yang, X. J. *Am. Chem. Soc.* **2012**, *134*, 13366.
- (33)Li, B.; Zhao, J.; Onda, K.; Jordan, K. D.; Yang, J.; Petek, H. Science 2006, 311, 1436.
- (34) Petek, H.; Zhao, J. Chem. Rev. 2010, 110, 7082.
- (35)Phillips, K. R.; Jensen, S. C.; Baron, M.; Li, S.-C.; Friend, C. M. J. Am. Chem. Soc. 2013, 135, 574.
- (36)Guo, Q.; Xu, C.; Yang, W.; Ren, Z.; Ma, Z.; Dai, D.; Minton, T. K.; Yang, X. J. Phys. Chem. C, DOI: 10.1021/jp401613s.
- (37) http://search.newport.com/?q=\*&x2=sku&q2=6281.
- (38) Kominami, H.; Sugahara, H.; Hashimoto, K. Catal. Commun. 2010, 11, 426.
- (39)Xu, B.; Liu, X.; Haubrich, J.; Friend, C. M. Nat. Chem. 2010, 2, 61.
- (40)Lichtenberger, J.; Lee, D.; Iglesia, E. Phys. Chem. Chem. Phys. 2007, 9, 4902.
- (41)Qiu, H.; Idriss, H.; Wang, Y.; Wöll, C. J. Phys. Chem. C 2008, 112, 9828.
- (42) Haubrich, J.; Kaxiras, E.; Friend, C. M. Chem. Eur. J. 2011, 17, 4496.

#### **Figure Captions**

**Figure 1.** (A) TDS spectra of m/z=31 (methanol) after the TiO<sub>2</sub>(110) surface was exposed to 0.15, 0.42, 0.97 and 1.80 ML methanol at 110 K. (B) C 1s XPS spectra after the TiO<sub>2</sub>(110) surface was exposed 1.80 ML methanol at 110 K and flashed to the indicated temperatures.

**Figure 2.** (A) O 1s XPS spectra after the  $TiO_2(110)$  surface was exposed 1.80 ML methanol at 110 K followed and flashed to the indicated temperatures. (B) O 1s difference spectra obtained from Figure 2A.

**Figure 3.** TDS spectra of (**A**) m/z=31 (methanol and methyl formate), (**B**) m/z=29 (methanol, formaldehyde and methyl formate) and (**C**) m/z=60 (methyl formate) after the TiO<sub>2</sub>(110) surface was exposed to 0.42 ML methanol at 110 K followed by the UV-light irradiation for 0 s (a), 30 s (b), 1 min (c), 5 min (d), 10 min (e) and 20 min (f).

**Figure 4.** TDS spectra after the  $TiO_2(110)$  surface was exposed to 0.42 ML methanol at 110 K followed by the UV-light irradiation for the indicated times.

**Figure 5.** (**A**) C 1s XPS spectra and (**B**) the integrated C 1s peak area of each component after the TiO<sub>2</sub>(110) surface was exposed to 0.42 ML methanol at 110 K followed by the UV-light irradiation for the indicated times. Note that these data were obtained in one experiment in which the UV-light irradiation and the XPS data measurement were performed in sequences. The time in the bracket indicates the total irradiation time. (**C**) C 1s XPS spectra and (**D**) the integrated C 1s peak area of each component after the TiO<sub>2</sub>(110) surface was exposed to 0.42 ML methanol at 110 K and irradiated for 20 min followed by flashing to the indicated temperatures.

**Figure 6.** (**A**) C 1s XPS spectra after the TiO<sub>2</sub>(110) surface was exposed to 0.01 L HCHO at 110 K. (**B**) TDS spectra after the TiO<sub>2</sub>(110) surface was exposed to 0.01 L HCHO at 110 K. (**C**) TDS

spectra after the  $TiO_2(110)$  surface was exposed to 0.01 L HCHO at 110 K followed by a UVlight irradiation for 20 min.

**Figure 7.** (A) TDS spectra after the  $TiO_2(110)$  surface was exposed to 0.42 ML methanol and then to 0.01 L HCHO at 110 K. (B) TDS spectra after the  $TiO_2(110)$  surface was exposed to 0.42 ML methanol and then to 0.01 L HCHO at 110 K followed by a UV-light irradiation for 5 min.

**Figure 8.** Schematic illustration of the photocatalytic oxidation of methoxy species to formaldehyde and the subsequent photocatalytic cross-coupling of methoxy species and formaldehyde to methyl formate on the  $TiO_2(110)$  surface covered with methanol. The red, green, yellow and purple spheres represent O, Ti, C and H atoms, respectively.

**Figure 9.** TDS spectra of methyl formate (m/z=60) after the  $TiO_2(110)$  surfaces covered with 0.15, 0.42 and 0.97 ML methanol were irradiated by a UV-light for 20 min.



Figure 1. (A) TDS spectra of m/z=31 (methanol) after the TiO<sub>2</sub>(110) surface was exposed to 0.15, 0.42, 0.97 and 1.80 ML methanol at 110 K. (B) C 1s XPS spectra after the TiO<sub>2</sub>(110) surface was exposed 1.80 ML methanol at 110 K and flashed to the indicated temperatures.



Figure 2. (A) O 1s XPS spectra after the  $TiO_2(110)$  surface was exposed 1.80 ML methanol at 110 K and flashed to the indicated temperatures. (B) O 1s difference spectra obtained from Figure 2A.



**Figure 3.** TDS spectra of (**A**) m/z=31 (methanol and methyl formate), (**B**) m/z=29 (methanol, formaldehyde and methyl formate) and (**C**) m/z=60 (methyl formate) after the  $TiO_2(110)$  surface was exposed to 0.42 ML methanol at 110 K followed by the UV-light irradiation for 0 s (a), 30 s (b), 1 min (c), 5 min (d), 10 min (e) and 20 min (f).



**Figure 4.** TDS spectra after the  $TiO_2(110)$  surface was exposed to 0.42 ML methanol at 110 K followed by the UV-light irradiation for the indicated times.



**Figure 5.** (**A**) C 1s XPS spectra and (**B**) the integrated C 1s peak area of each component after the TiO<sub>2</sub>(110) surface was exposed to 0.42 ML methanol at 110 K followed by the UV-light irradiation for the indicated times. Note that these data were obtained in one experiment in which the UV-light irradiation and the XPS data measurement were performed in sequences. The time in the bracket indicates the total irradiation time. (**C**) C 1s XPS spectra and (**D**) the integrated C 1s peak area of each component after the TiO<sub>2</sub>(110) surface was exposed to 0.42 ML methanol at 110 K and irradiated for 20 min followed by flashing to the indicated temperatures.



**Figure 6.** (A) C 1s XPS spectra after the  $TiO_2(110)$  surface was exposed to 0.01 L HCHO at 110 K. (B) TDS spectra after the  $TiO_2(110)$  surface was exposed to 0.01 L HCHO at 110 K. (C) TDS spectra after the  $TiO_2(110)$  surface was exposed to 0.01 L HCHO at 110 K followed by a UV-light irradiation for 20 min.



**Figure 7.** (A) TDS spectra after the  $TiO_2(110)$  surface was exposed to 0.42 ML methanol and then to 0.01 L HCHO at 110 K. (B) TDS spectra after the  $TiO_2(110)$  surface was exposed to 0.42 ML methanol and then to 0.01 L HCHO at 110 K followed by a UV-light irradiation for 5 min.



**Figure 8.** Schematic illustration of the photocatalytic oxidation of methoxy species to formaldehyde and the subsequent photocatalytic cross-coupling of methoxy species and formaldehyde to methyl formate on the  $TiO_2(110)$  surface covered with methanol. The red, green, yellow and purple spheres represent O, Ti, C and H atoms, respectively.



**Figure 9.** TDS spectra of methyl formate (m/z=60) after the  $TiO_2(110)$  surfaces covered with 0.15, 0.42 and 0.97 ML methanol were irradiated by a UV-light for 20 min.

SYNOPSIS

