## Artificial photochemical nitrogen cycle to produce nitrogen and hydrogen from ammonia by platinized $TiO_2$ and its application to a photofuel cell

M. Kaneko,\*<sup>a</sup> N. Gokan,<sup>a</sup> N. Katakura,<sup>a</sup> Y. Takei<sup>a</sup> and M. Hoshino<sup>b</sup>

Received (in Cambridge, UK) 10th December 2004, Accepted 20th January 2005 First published as an Advance Article on the web 1st February 2005 DOI: 10.1039/b418580c

Photochemical artificial nitrogen cycle was reported to produce dinitrogen and dihydrogen by photodecomposing ammonia with platinized  $TiO_2$ , and its application to a photofuel cell with a nanoporous  $TiO_2$  film electrode, a new concept of a fuel cell to photochemically produce electricity and  $H_2$  from ammonia, was proposed.

The treatment of livestock waste is becoming more and more a serious problem. Especially, the excess amount of nitrogen compounds in the waste are difficult to treat or decompose for the purpose of discarding into the environment or recycling as useful compounds. In Nature the carbon/nitrogen cycle maintains material balance. Carbon waste can be converted into methane (fuel) by methane fermentation, which is regarded as one of the promising methods to create renewable energy from biomass waste. However, nitrogen compounds contained in the livestock waste are now becoming a serious pollutant for the environment, which should be solved urgently. Since nitrogen compounds can be converted finally to ammonia by enzymes such as urease in livestock wastes, if ammonia is converted to harmless or useful compounds, it can solve the livestock waste problem. In addition to this, ammonia is now attracting a great deal of attention as an energy storage material for H2 fuel cells instead of H2 that requires high pressure and large volume for storage.

TiO<sub>2</sub> photoanode was found to photoelectrochemically decompose water under UV light irradiation,<sup>1</sup> and since then many organic and inorganic compounds have been decomposed by this photocatalyst.<sup>2-4</sup> Photodecomposition of ammonia has also been reported, but the products were not N<sub>2</sub>/H<sub>2</sub>. The photodecomposition of ammonia in neutral water has been reported by using TiO<sub>2</sub>-supported Pt or Pd catalyst, but only N<sub>2</sub> and nitrogen oxides were obtained.<sup>5</sup> TiO<sub>2</sub>/Pt decomposed aqueous ammonia into N<sub>2</sub>, while pure TiO<sub>2</sub> decomposed NH<sub>3</sub> into nitrite and nitrate.<sup>6</sup> In these reports hydrogen formation was not reported. Some reports are found on photodecomposition of ammonia with TiO<sub>2</sub> in a gas phase.<sup>7,8</sup> However, to our knowledge, photochemical conversion of aqueous ammonia into N2/H2 has not been reported yet. The present authors have found that an aqueous solution of ammonia can be photochemically converted into N<sub>2</sub>/H<sub>2</sub> if reacted under alkaline conditions and in a stoichiometric 1:3 (N2:H2) molar ratio by using platinized titanium dioxide (TiO<sub>2</sub>) suspension. This could lead to a future artificial nitrogen cycle driven by solar irradiation. Very interestingly, our further investigation showed that the system can lead to a new concept of a photofuel cell in which ammonia

\*mkaneko@mx.ibaraki.ac.jp

serves as a fuel, the light irradiation induces decomposition of the fuel, and so photocurrent is produced in addition to the  $N_2/H_2$  production. The first fundamental results are reported in this paper.

TiO<sub>2</sub> (ST-01, average size 7 nm, from Ishihara Sangyo Co.Ltd.) was platinized by photochemially reducing tetrachloroplatinate in a TiO<sub>2</sub>-water suspension in the presence of 2 wt% methanol. The platinized TiO<sub>2</sub> powders (TiO<sub>2</sub>-Pt) (10 mg) with 1 wt% Pt were suspended in a 5 ml aqueous solution of 1 wt% ammonia (pH 12.3) in a 10 ml cylindrical cell. The cell was sealed after bubbling argon gas into the water for 30 min, and then the suspension was irradiated with a 500 W xenon lamp (intensity 102 or 469 mW cm<sup>-2</sup>). The products were analyzed by a gas chromatograph (Shimadzu, GC4C-PT) with a 13X-D molecular sieve column at 80 °C using argon carrier gas. N2 and H2 were produced by irradiation with nearly in the stoichiometric 3:1 ratio  $(H_2/N_2 = 3.4/1 \text{ molar ratio})$  with a slight excess of  $H_2$ . The slight excess of H<sub>2</sub> formation would be ascribable to photochemical proton reduction to generate H<sub>2</sub> by the TiO<sub>2</sub>-Pt that has been reported earlier.<sup>9</sup> The effect of pH is shown in Table 1.

The decrease of the solution pH to 9.18, 6.93 and 0.97 by adding HNO<sub>3</sub> remarkably reduced the photodecomposition rate. Since the  $pK_a$  value for the dissociation of  $NH_4^+$  to  $NH_3(+H^+)$  is 9.24, the trend of  $N_2$  formation on pH should show that the dissociated NH<sub>3</sub> is more effective for the photodecomposition than  $NH_4^+$ . However, the trend for H<sub>2</sub> formation is not simple; at pH 6.93 the amount H<sub>2</sub> formed increased slightly, which should be investigated in more detail in future. The TiO<sub>2</sub> powders without deposited Pt did not show any appreciable activity.

The photodecomposition yield (%) of NH<sub>3</sub> was examined by changing its concentration (1, 0.1 and 0.01 wt%), and the results are shown in Table 2. When the concentration was decreased, the decomposition yield (%) increased (85.4% for 0.01 wt% NH<sub>3</sub> after 20 h). After prolonged irradiation this value approached nearly 100% decomposition.

**Table 1** N<sub>2</sub> and H<sub>2</sub> evolution by photochemical decomposition of 1 wt%NH<sub>3</sub> aqueous solution (5 ml) in the presence of suspended TiO<sub>2</sub>– Pt (0.01 g) in 3 h. Light intensity, 102 mW cm<sup>-2</sup>

pН	$H_2$ (µl)	$N_2$ (µl)	Mol. ratio (H <sub>2</sub> /N <sub>2</sub> )
12.3	47.8	13.9	3.4
9.18 <sup>a</sup>	Trace	10.3	0
6.93 <sup>a</sup>	3.6	6.6	0.6
$0.97^{a}$	Trace	6.8	0
<sup>a</sup> pH was a	djusted by adding	g HNO <sub>3</sub> .	

NH <sub>3</sub> conc. (wt%)	pH	H <sub>2</sub> (μl)	N <sub>2</sub> (μl)	Mol. ratio (H <sub>2</sub> /N <sub>2</sub> )	Decom. yield (%)
1	11.9	2111	663	3.2	7.5
0.1	12.2	979	296	3.3	33.7
0.01	12.1	409	75	5.4	85.4
<sup>a</sup> pH was adjusted by ad	lding NaOH.				

**Table 2** N<sub>2</sub>/H<sub>2</sub> evolution and ammonia photodecomposition yield (%) of different concentrations NH<sub>3</sub> aqueous solution (5 ml) in the presence of suspended TiO<sub>2</sub>-Pt (0.02 g) in 20 h. Light intensity, 469 mW cm<sup>-2</sup>

A nanoporous TiO2 fim was prepared that was reported to fabricate a dye-sensitized solar cell.<sup>10</sup> 12 g TiO<sub>2</sub> (P-25, received from Japan Aerosil Co.Ltd.) and acetylacetone (0.4 ml) were mixed well in a mortar while adding 4 ml water slowly during 2 h. Triton X-100 (0.2 ml) was added and further mixed well with the TiO<sub>2</sub> slurry, and then the mixture was sonicated. This mixture was spin-coated (2000 rpm) on a FTO glass (2 cm × 1 cm) for about 10 s to obtain 1 cm  $\times$  1 cm area of a nanoporous TiO<sub>2</sub> film, and the film was dried at 100 °C for 30 min. This procedure was repeated until the film thickness reached 10 µm, and then the film was calcinated at 450 °C for 30 min. The quality of the TiO<sub>2</sub> nanoporous film was proved by using this film for a dye-sensitized solar cell<sup>10</sup> by using the well-known *cis*-bis(isothiocyanato)bis(4,4'-dicarboxyl-2,2'-bipyridine)- ruthenium(II), Ru(dcbpy)2-(NCS)<sub>2</sub> (called N3) dye with a conventional  $I_3^{-}/I^{-}$  redox electrolyte solution giving the light-to-electrical power conversion efficiency of around 7%.11

A cyclic voltammogram was measured with this TiO<sub>2</sub> film as working electrode, Ag–AgCl as a reference electrode, and a platinum foil as a counter electrode in a pH 14.1 aqueous solution of 10 M NH<sub>3</sub> containing 0.1 M KNO<sub>3</sub> electrolyte. The CVs under dark and under illumination in an Ar atmosphere are shown in Fig. 1. Clear photoanodic currents were observed showing that the TiO<sub>2</sub> works as a photoanode in the presence of NH<sub>3</sub>. This system induced photoanodic currents also in the absence of NH<sub>3</sub> under the same pH conditions, but the photocurrent density was less than 1/40 in comparison with the Fig. 1 showing evidently that NH<sub>3</sub> works as a donor for the photoelectrochemical event.

Although the photocurrents in Fig. 1 tended to decrease with repeated scanning, it approached a saturated value of around  $0.5 \text{ mA cm}^{-2}$  after 3 to 4 hours. The generated H<sub>2</sub> and N<sub>2</sub> after repeated scanning for 2 hours are shown in Table 3.

The obtained H<sub>2</sub>/N<sub>2</sub> ratio was 2.6/1 under Ar. The smaller amount of H<sub>2</sub> than the 3:1 ratio could be ascribable to the consumption of the photogenerated electrons by the leaked O<sub>2</sub> from air since for this three electrodes system the cell was not tight enough against air leakage. This was supported by the remarkable smaller  $H_2/N_2$  ratio (0.6) obtained under  $O_2$  atmosphere as shown in Table 3. The use of K<sub>2</sub>SO<sub>4</sub> instead of KNO<sub>3</sub> as an electrolyte gave almost the same results as Table 3, indicating that NO<sub>3</sub><sup>-</sup> anion is not involved in the photoelectrochemical reaction. By using the nanoporous TiO<sub>2</sub> film electrode and a Pt foil counter electrode, photoelectrochemical reaction was carried out (10 M NH<sub>3</sub> at pH 14.1 and 0.1 M KNO<sub>3</sub>) under short circuit conditions without any bias potential. For this system the cell was tight enough against air leakage as the cell used for the TiO2-Pt suspension systems. This system produced 150  $\mu$ A cm<sup>-2</sup> photocurrent, and the  $H_2$  and N  $_2$  produced in 2 h were 194  $\mu$ l and 63  $\mu$ l, respectively, with the  $H_2/N_2$  ratio of 3.08/1 nearly in the theoretical



Fig. 1 Repeated cyclic voltammograms under dark and irradiation at a  $TiO_2$  nanoporous electrode soaked in an aqueous solution of  $NH_3$  (10 M) and  $KNO_3$  (0.1 M) at pH = 14.1, with a Pt foil as a counter and a Ag/AgCl as a reference electrode, measured at the scan rate of 20 mV s<sup>-1</sup> under Ar atmosphere. Light intensity, 505 mW cm<sup>-2</sup>.

3/1 ratio. The use of a TiO<sub>2</sub> nanoporous film with deposited Pt did not show activity for the NH<sub>3</sub> photodecomposition. These results show that irradiation of the TiO<sub>2</sub> film by UVlight created electrons and holes, the ammonia is oxidized by the holes to N<sub>2</sub> and protons, and then the electrons in the conduction band of the TiO<sub>2</sub> moved to the counter Pt electrode to reduce protons to H<sub>2</sub>.

Ammonia was thus photochemically decomposed into  $H_2$  and  $N_2$  by using  $TiO_2$ -Pt in an aqueous solution, and this photocatalytic system was successfully applied to fabricate a photofuel cell, a new concept of fuel cell, by which  $NH_3$  is used as a fuel assisted by photocatalysis to generate photocurrent as well as  $H_2$  and  $N_2$ . The present photolysis of ammonia would not only lead to a future artificial solar nitrogen cycle, but also could lead to a future photofuel cell energy system using ammonia as an energy transporting and storing material.

Table 3  $H_2$  and  $N_2$  generated during irradiation for 2 hours under similar conditions to those in Fig. 1 using 10 M NH<sub>3</sub> and 0.1 M KNO<sub>3</sub> aqueous solution (pH 14.1) under Ar or O<sub>2</sub> atmosphere. Light intensity, 505 mW cm<sup>-2</sup>

Atmosphere	$H_2$ (µl)	N2 (µl)	H <sub>2</sub> /N <sub>2</sub> Molar ratio
Ar	568	220	2.6
O <sub>2</sub>	143	225	0.6

M. Kaneko,\*<sup>a</sup> N. Gokan,<sup>a</sup> N. Katakura,<sup>a</sup> Y. Takei<sup>a</sup> and M. Hoshino<sup>b</sup> <sup>a</sup>Faculty of Science, Ibaraki University, Bunkyo, Mito, 310-8512, Japan. E-mail: mkaneko@mx.ibaraki.ac.jp

<sup>b</sup>Nanomaterial Processing Laboratory, The Institute of Physical and Chemical Research, Hirosawa, Wako, 351-0198, Japan

## Notes and references

- 1 A. Fujishima and K. Honda, Nature, 1972, 238, 37.
- 2 A. Fujishima, K. Hashimoto and T. Watanabe, *TiO<sub>2</sub> Photocatalysis Fundamental and Applications*, BKC Inc., Tokyo, 1999.
- 3 K. Kalyanasundaram and M. Graetzel, eds., *Photosensitization and Photocatalysis Using Inorganic and Organometallic Comounds*, Kluwer Academic Publishers, Dordrecht, 1993.

- 4 M. Kaneko and I Okura, eds., *Photocatalysis Science and Technology*, Kodansha/Springer, 2002.
- 5 J. Taguchi and T. Okuhara, Appl. Cat. A: General, 2000, 194-195, 89.
- 6 W. Choi, J. Lee, S. Kim, S. Hwang, M. C. Lee and T. K. Lee, J. Ind. Eng. Chem., 2003, 9, 96.
- 7 M. Nazir, J. Takasaki and H. Kumazawa, *Chem. Eng. Commun.*, 2003, **190**, 322.
- 8 H. D. Jang, S. K. Kim and S. J. Kim, J. Nanoparticle Res., 2001, 3, 141.
- 9 T. Abe, E. Suzuki, K. Nagoshi, K. Miyashita and M. Kaneko, *J. Phys. Chem.*, *B*, 1999, **103**, 1119.
- 10 B. O. Regan and M. Graetzel, Nature, 1991, 353, 737.
- 11 M. Kaneko, T. Hoshi, Y. Kaburagi and H. Ueno, J. Eloectroanal. Chem., 2004, 572, 21–27.