This article was downloaded by: [Dalhousie University] On: 16 July 2014, At: 03:27 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



Molecular Crystals and Liquid Crystals Science and Technology. Section A. Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information: http://www.tandfonline.com/loi/gmcl19

Synthesis and Physical Properties of Thioester Liquid Crystals that Exhibit an Anti-Ferro-Anti Phase Sequencing

Larissa Nassif^a, Antal Jakli^b & Alexander J. Seed^a ^a Department of chemistry, Kent State University, Kent, OH, 44242-0001, USA

^b Liquid Crystal Institute, Kent State University , Kent, OH, 44242-0001, USA Published online: 27 Oct 2006.

To cite this article: Larissa Nassif, Antal Jakli & Alexander J. Seed (2001) Synthesis and Physical Properties of Thioester Liquid Crystals that Exhibit an Anti-Ferro-Anti Phase Sequencing, Molecular Crystals and Liquid Crystals Science and Technology. Section A. Molecular Crystals and Liquid Crystals, 365:1, 171-179, DOI: 10.1080/10587250108025293

To link to this article: http://dx.doi.org/10.1080/10587250108025293

PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness,

or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms & Conditions of access and use can be found at http://www.tandfonline.com/page/terms-and-conditions Mol. Cryst. and Liq. Cryst., 2001, Vol. 365, pp. 171-179 Reprints available directly from the publisher Photocopying permitted by license only

Synthesis and Physical Properties of Thioester Liquid Crystals that Exhibit an Anti-Ferro-Anti Phase Sequencing

LARISSA NASSIF^a, ANTAL JAKLI^b and ALEXANDER J. SEED^a

^aDepartment of chemistry, Kent State University, Kent, OH 44242–0001, USA and ^bLiquid Crystal Institute, Kent State University, Kent OH 44242–0001, USA

Keywords: ferroelectric; antiferroelectric; thioester; electrooptics

INTRODUCTION

In an ongoing program concerned with the synthesis of ferroelectric liquid crystals with high dielectric biaxiality, we have synthesized a homologous series of thioester-containing materials with the thiophene unit as a principal core substituent. The heterocycle imparts a large lateral dipole without the extra molecular breadth that so severely reduces mesophase thermal stability and phase range in materials that contain for example, lateral cyano, nitro and trifluoromethyl substituents. A 2,5-disubstitution pattern of the heterocycle was chosen in order to give the highest linearity of the molecular structure and hence the widest mesophase range and stability^[1].

The incorporation of the thioester unit was expected to give rise to enhanced phase ranges and mesophase thermal stabilities when compared to the analogous carboxylates synthesized by Byron^[2, 3] and Seed^[4]. These trends were indeed observed and are attributed to a combination of both the enhanced molecular polarizability and the increase in the aspect ratio of the thioester materials.

SYNTHESIS

A typical synthetic pathway used in obtaining the desired thioester materials is given in SCHEME 1. Alkoxybromobenzenes (2) were synthesized using Williamson's etherification^[5] in near-quantitative yields. Boronic acids (3) were obtained through halogen metal exchange, reaction with trimethyl borate and subsequent hydrolysis of the borate ester (quantitative yields)^[1, 6]. Palladium-catalyzed cross-coupling^[7] of 3 and 4 gave compounds 5 in yields of between 39 and 65%. Subsequent carboxylation and conversion into the acid chlorides under standard conditions gave compounds 6. 6 and 7 were esterified in the presence of triethylamine to give compounds 8^[8]. The Mitsunobu reaction^[9] was finally used to effect clean esterification of the carboxylic acids (8) with (R)-(-)-octan-2-ol.



SCHEME 1 The synthesis of the (S)-(+)-1-Methylheptyl 4-[2-(4-alkoxyphenyl)thiophene-5-carbonylthiooxy]benzoates

RESULTS AND DISCUSSION

Optical Microscopy

The transition temperatures for the final products are given in TABLE 1. All of the reported transition temperatures were obtained using polarized optical microscopy (plain slide and cover slip) and confirmed by DSC.



 $9\pi...R = C_8H_{17}...Cryst 67.8 S_{C*ANT1} 103.4 S_{C*FERRI} 105.9 S_{C*FERRO} 111.6 S_A 128.5 I$

9b...R = C₉H₁₉...Cryst 67.1 S_{C^{*}ANTI} 80.4 S_{C^{*}FERRI} 87.5 S_{C^{*}FERRO} 114.0 S_A 123.9 I

 $9c...R = C_{10}H_{21}...Cryst 60.6 S_{C}^{*}ANTI 97.8 S_{C}^{*}FERRI 100.5 S_{C}^{*}FERRO 112.5 S_{A} 121.7 I$

9d...R = $C_{11}H_{23}$...Cryst 66.4 ($S_C^*_{ANTI}$ 62.8) $S_C^*_{FERRO}$ 112.2 S_A 119.0 I

9e...R = $C_{12}H_{25}$...Cryst 64.5 $S_{C}^{*}_{ANTI}$ 77.5 $S_{C}^{*}_{FERRI}$ 83.2 $S_{C}^{*}_{FERRO}$ 110.3 S_{A} 116.9 I

 TABLE 1
 Transition temperatures (°C) of the (S)-(+)-1-methylheptyl 4-[2-(4-alkoxyphenyl)thiophene-5-carbonylthiooxy]benzoates

The transition temperatures for the analogous carboxylate derivatives are given in TABLE 2.



10a...R =
$$C_8H_{17}$$
...Cryst 87.5 (S_C*_{ANT1} 83.0 S_C*_{FERRI} 85.4 S_C*_{FERRO} 87.2) S_A 107.3 I
10b...R = C_9H_{19} ...Cryst 76.8 (S_C*_{ANT1} 65.7 S_C*_{FERRI} 69.2) S_C*_{FERRO} 90.1 S_A 103.9 I
10c...R = $C_{10}H_{21}$...Cryst 65.5 S_C*_{ANT1} 78.6 S_C*_{FERRI} 81.4 S_C*_{FERRO} 92.2 S_A 97.4 I
10d...R = $C_{12}H_{25}$...Cryst 64.2 S_C*_{ANT1} 80.2 S_C*_{FERRI} 82.8 S_C*_{FERRO} 92.6 S_A 97.9 I

TABLE 2 Transition temperatures (°C) of the (S)-(+)-1-methylheptyl 4-[2-(4-alkoxyphenyl)thiophene-5-carbonyloxy]benzoates

In looking at tables 1 and 2 it is clear that there are a number of trends in the mesomorphic behavior. The thioesters exhibit smectic A, smectic C*_{FERRO} and C*_{ANTI} phases; the C*_{FERRI} phase is observed in all compounds except 9d. The clearing points decrease regularly with increasing chain length. In comparing the thioester compounds to the carboxylate series it is seen that the thioester link has resulted in a decrease in the melting points for 9a, 9b, and 9c by 19.7 °C, 9.7 °C, and 4.9 °C respectively, but has raised it 0.3 °C in compound 9e. The clearing points for 9a, 9b, 9c, and 9e have increased by 21.2 °C, 20.0 °C, 24.3 °C and 19.0 °C respectively. The S_C*_{FERRO}-S_A transition temperatures have also increased by 24.4 °C, 23.9 °C, 20.3 °C, and 17.7 °C for compounds 9a, 9b, 9c, and 9e respectively. The ferroelectric phase range has increased by 3.9 °C, 5.6 °C, 1.2 °C, and 17.3 °C for 9a, 9b, 9c, and 9e respectively. In comparing the Sc*ANTI-Sc*FERRI transitions, we see an increase in thermal stability for 9a, 9b, and 9c of 20.4 °C, 14.7 °C, and 19.2 °C respectively, and a decrease of 2.7 °C for 9e. The S_C*_{FERRI}- S_C*_{FERRO} phase stabilities show increases of 20.5 °C, 18.3 °C, 19.1 °C and 0.4 °C for 9a, 9b, 9c, and 9e respectively.

Physical measurements of 9a

Optical microscopy indicated that we had a single antiferroelectric phase. However, textures of frustrated phases such as those exhibited by our compounds are often difficult to assign and electrooptic evaluation is an excellent supplementary tool. In addition, the synthesis of the racemic mixtures can also shed light on the existence of the antiferroelectric phase through the observation of two-brush dispirations^[10] which confirm the antiferroelectric structure.

9a was subjected to a number of physical tests in a $15\mu m$ cell. Our initial studies concentrated on optical scanning spectroscopy with the results being shown in FIGURE 1. These observations show characteristic textural changes at 103 °C, 110 °C and 116 °C. In addition there is a slightly less pronounced changed at ~113 °C.



FIGURE 1 Textural variations of 9a with temperature

The threshold for switching polarization was subsequently examined and an unexpected threshold voltage was observed between 110 °C and 116 °C (see FIGURE 2).



FIGURE 2 Temperature dependence of the threshold voltage of 9a

The temperature dependence of the threshold voltage indicates that the material is antiferroelectric below ~103 °C and above 110 °C, contrary to our microscopy evaluation.

The value of the polarization was measured as a function of voltage and the saturated values were taken for the spontaneous polarization. The voltage dependence of the polarization also confirms that two different regimes of antiferroelectric phases exist: one below and one above the ferroelectric state.



FIGURE 3 Temperature dependence of the spontaneous polarization (saturated) for 9a.

178/[1134]

The temperature dependence of the spontaneous polarization (see FIGURE 3) also shows pronounced changes at 103°C, 110°C and 116°C, corresponding to the SmC*_A - SmC*-AF2-SmA phase sequences suggested by Figures 1 and 2. The drastic decrease of the polarization at 113°C coincides with the pronounced textural change observed in FIGURE 1.



FIGURE 4 Temperature variation of the optical tilt angle for 11a

The temperature dependence of the tilt-angle (see FIGURE 4) also reflects the transition to the SmA phase above 116°C, and the ferroelectric range between 103 °C and 110 °C. Here the low-temperature antiferroelectric to ferroelectric transition seems to be preceded by another transition. Considering the measurement errors and the fluctuation effects, we think that it is only pre-transitional effect.

CONCLUSIONS

We have synthesized a series of thioester derivatives. Standard microscopic evaluation indicated that all of the materials (except 9d) had an anti-ferri-ferro phase sequencing. The octyloxy derivative has undergone extensive electrooptical evaluation and appears to have a anti-ferro-anti phase morphology when confined within a 15 μ m cell. In thinner films the antiferroelectric character of AF2 replaces the ferrielectric-type behavior, probably due to the surface forces imposed

by the thin cell. Confirmation of the high temperature antiferroelectric phase may be additionally sought by synthesis of the enantiomerically pure racemic mixture, and the observation of a two-brush dispiration. This phase sequence is the first example of a ferroelectric phase flanked by two antiferroelectric phases.

Acknowledgements

The authors wish to thank Dr. Avtar Matharu for information pertaining to compounds **10a–10c**, and to Kent State University for financial assistance.

References

- [1] A. J. Seed, K. J. Toyne, and J. W. Goodby, J. Mater. Chem., 5, 653-661, (1995).
- [2] D. J. Byron, L. Komitov, A. S. Matharu, I. McSherry, and R. C. Wilson, J. Mater. Chem., 6, 1871-1878, (1996).
- [3] A. S. Matharu, Personal Communication.
- [4] A. J. Seed, M. Hird, P. Styring, H. F. Gleeson, and J. T. Mills, *Mol. Cryst. Liq. Cryst.*, 299, 19–25, (1997).
- [5] A. W. Williamson, J. Chem. Soc., 229-239, (1851).
- [6] L. Brandsma and H. Verkruijsse, Preparative Polar Organometallic Chemistry, vol. 1. (Berlin: Springer-Verlag), (1987).
- [7] M. Hird, G. W. Gray, and K. J. Toyne, Mol. Cryst. Liq. Cryst., 206, 187-204, (1991).
- [8] R. J. Twieg, K. Betterton, W. Hinsberg, P. Wong, W. Tang, and H.-T. Nguyen, Ferroelectrics, 114, 295–308, (1991).
- [9] O. Mitsunobu, Synthesis, 1–28, (1981).
- [10] Y. Takanishi, H. Takezoe, A. Fukuda, H. Komura, and J. Watanabe, J. Mater. Chem., 2, 71-73, (1992).