

View Article Online

Dalton Transactions

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: M. Ibrahim, R. Poreddy, K. Philippot, A. Riisager and E. J. García-Suárez, *Dalton Trans.*, 2016, DOI: 10.1039/C6DT03668F.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the **author guidelines**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the ethical guidelines, outlined in our <u>author and reviewer resource centre</u>, still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/dalton

Chemoselective hydrogenation of arenes by PVP supported Rh nanoparticles

Mahmoud Ibrahim^{a,b}, Raju Poreddy^c, Karine Philippot^{*,a,b}, Anders Riisager^{*,c}, Eduardo J. Garcia-Suarez^{*,c}

^a CNRS, LCC (Laboratoire de Chimie de Coordination), 205 Route de Narbonne, BP44099, 31077 Toulouse Cedex 4, France

^b Université de Toulouse, UPS, INPT, 31077 Toulouse Cedex 4, France

^c Centre for Catalysis and Sustainable Chemistry, Department of Chemistry, Technical University of Denmark, DK-2800 Kgs. Lyngby, Denmark

* Corresponding authors (edgar@kemi.dtu.dk; karine.philippot@lcc-toulouse.fr)

Abstract

Published on 09 November 2016. Downloaded by University of Toronto on 18/11/2016 15:43:18.

Polyvinyl pyrrolidone-stabilized Rh nanoparticles (RhNPs/PVP) of *ca.* 2.2 nm in size were prepared by hydrogenation of the organometallic complex [Rh(η^3 -C₃H₅)₃]) in the presence of PVP and evaluated as catalyst in the hydrogenation of a series of arene substrates as well as levulinic acid and methyl levulinate. The catalyst showed excellent activity and selectivity towards aromatic ring hydrogenation compared to other reported transition metal-based catalysts under mild reaction conditions (room temperature and 1 bar H₂). Furthermore, it showed to be a highly promising catalyst for the hydrogenation of levulinic acid and methyl levulinate in water leading to quantitative formation of the fuel additive γ -valerolactone under moderate reaction conditions compared to previously reported catalytic systems.

Keywords

rhodium, nanoparticle, catalysis, hydrogenation, biomass, levulinic acid, methyl levulinate

Introduction

The hydrogenation of aromatic C-C double bonds to form cyclohexane derivatives is one of the most important reactions in both petrochemical and pharmaceutical industries. For instance, the chemoselective hydrogenation of benzoic acid to cyclohexane carboxylic acid ¹ is a crucial step in the fiber industry for the synthesis of ε -caprolactam from toluene in the Snia Viscosa process (developed by SNIA S.p.A., Italy).² Furthermore, cyclohexane carboxylic acid is a key intermediate in the synthesis of high demanding pharmaceuticals such as praziquantel and ansatrienin (Figure 1).^{3,4,5}



Figure 1. Praziquantel (left) and Ansatrienin (right)

The high relevance of benzoic acid hydrogenation in both bulk and fine chemistry industries has attracted a lot of attention from the scientific community to develop catalysts for the chemoselective hydrogenation of benzoic acid to cyclohexane carboxylic acid. However, hydrogenation of aromatic C-C double bonds, compared to olefinic C-C double bonds, is a very challenging transformation since it generally requires severe reaction conditions. Moreover, a selective catalyst is needed which only hydrogenates the aromatic ring while keeping other functional groups present in the molecule intact. Noble transition metal catalysts, either homogeneous or heterogeneous systems, including Ru-Pt, Rh/C, Pd/C, Pd-Ru have been extensively studied for arene hydrogenation and generally found to exhibit high activities.^{2,6,7,8,9} Among them, Rh/AC (AC = activated carbon) and Pd/AC catalysts show superior catalytic activity compared to other supported transition metal catalysts.¹⁰ Pd/AC are traditionally used for ε -caprolactam production in the chemical fiber industry¹¹ and for terephthalic acid refining in the polyester industry.¹²

It is worth to point out that the process for benzoic acid to cyclohexane carboxylic acid hydrogenation with Pd/AC catalysts suffers from a number of limitations, i.e. high temperature (150 $^{\circ}$ C) and high H₂

Published on 09 November 2016. Downloaded by University of Toronto on 18/11/2016 15:43:18.

Dalton Transactions

pressure (150 bar) conditions as well as excessive catalyst consumption due to its fast deactivation.¹³ Tsung *et al.* have recently reported that Pt nanocrystals are catalytically active in the hydrogenation of pyrrole to *n*-butylamine and that both the activity and the selectivity strongly depend on the shape and size of Pt nanocrystals.¹⁴ A similar behavior was observed by Hu et al. using Pd nanocrystals in citral and cyclohexene hydrogenation.¹⁵ Yoon et al. investigated a bimetallic Rh-Pd/CNT (CNT = carbon nanotube) catalyst for benzene hydrogenation which displayed a much higher activity compared to Rh/CNT or Pd/CNT monometallic catalysts alone. The superior activity was attributed to a synergistic effect between Rh and Pd, but the reaction system required elevated pressure (10 bar) in order to observe sufficient activity.¹⁶

Metal nanoparticle catalysis has progressed significantly during the last 25 years.¹⁷ However, a major drawback often reported when using nanoparticles in solution catalysis is drop in catalytic activity and selectivity associated to particle agglomeration due to a lack of stability with time and/or reaction conditions. Accordingly, intensive research has been focused on developing approaches to increase particle stability and improve catalytic performance. In particular, numerous supports and/or stabilizers (polymers or ligands) that could limit nanoparticle evolution during their application as catalysts in solution are studied. Among polymers employed as stabilizers of metal nanoparticles, polyvinyl pyrrolidone (PVP) efficiently controls the particle growth and contributes to obtain an uniform metal nanoparticle dispersion in the polymer matrix. For these reasons, PVP-stabilized Rh nanoparticles (RhNPs) have attracted attention for arene hydrogenation in both ionic liquids and water as reaction media at relatively low temperatures.^{18,19}

In this work, we report results on the mild hydrogenation of benzoic acid and its derivative benzamide to cyclohexane carboxylic acid and cyclohexane carboxamide at room temperature and atmospheric H_2 pressure with a RhNPs/PVP nanocatalyst using water as a green and eco-friendly solvent. Furthermore, the RhNPs/PVP nanocatalyst has been evaluated in aqueous phase hydrogenation of levulinic acid and its methyl ester to γ -valerolactone.

Experimental part

Materials

All manipulations were carried out under inert atmosphere using standard Schlenk techniques or in glove-box if not otherwise stated. Tetrahydrofuran (THF) and *n*-pentane were purchased from Sigma-

Dalton Transactions

Dalton Transactions Accepted Manuscript

Aldrich purified by column-filtration and degassed by means of three freeze-pump-thaw cycles before use. Other solvents and/or reagents were purchased from Sigma-Aldrich and used without further purification except for PVP that was dried under vacuum over P₂O₅ at 80 °C for 3 days prior to use. The rhodium precursor [Rh(η^3 -C₃H₅)₃] was synthesized from RhCl₃.3H₂O (Johnson Matthey) and CH₂=CHCH₂MgCl (Sigma-Aldrich; solution 2.0 M in THF) following a published preparation method.²⁰ Hydrogen gas (Alphagaz) was purchased from Air liquid.

Synthesis of RhNPs/PVP

 $[Rh(\eta^3-C_3H_5)_3]$ metal precursor (150 mg, 0.663 mmol) was placed in a Fisher-Porter bottle and left under vacuum for 30 min. The Fisher-Porter bottle was then cooled to -80 °C and a THF solution (150 mL) containing 680 mg of PVP ($M_W = 40000$ g/mol) was added to the rhodium complex leading to a yellow solution. The reaction mixture was then let to warm up to room temperature before pressurization with H₂ (3 bar). After 10 min, the yellow solution turned into a black colloidal solution indicating the formation of NPs. The solution was left for stirring under H₂ atmosphere for additional 16 h to ensure complete decomposition of the metal precursor. Then excess of H₂ was removed under vacuum and the colloidal solution concentrated to 10 mL before addition of *n*-pentane in order to precipitate the RhNPs. The resulting RhNPs/PVP solid was washed twice with *n*-pentane, filtered and dried under vacuum overnight allowing obtaining a crystalline dark grey powder (~600 mg) that was kept under inert atmosphere until use.

Characterization of RhNPs/PVP

TEM and HR-TEM analyses

Samples for transmission electron microscopy (TEM) and high resolution HR-TEM analyses were prepared by slow evaporation of a drop of the crude colloidal solution deposited onto a holey carbon-covered copper grid under argon (in glove-box). TEM and HR-TEM analyses were performed on a MET JEOL JEM 1400 microscope operating at 120 kV and a JEOL JEM 2010 microscope working at 200 kV with a resolution point of 2.5 Å and equipped for Energy-Dispersive X-ray spectroscopy (EDX; Noran), respectively. Enlarged micrographs were used for treatment with ImageJ software to obtain a

statistical size distribution and the nanoparticle mean diameter. FFT treatments were carried out with Digital Micrograph Version 1.80.70 to determine NPs crystalline structure.

ICP-AES analyses

The Rh content of the RhNPs/PVP catalyst was quantified by inductively coupled plasma atomic emission spectroscopy (ICP-AES) using a Thermo Scientific iCAP 6300 DUO spectrometer with a 3-channel, 12-roller pump and a 27.12 MHz solid state RF plasma generator. Mineralization of the RhNPs/PVP sample was performed in *aqua regia* solution.

XPS analyses

X-ray photoelectron spectroscopy (XPS) data were acquired with a ThermoScientific system at room temperature using Al-K α radiation (1484.6 eV) as the excitation X-ray source. During analysis the pressure in the chamber was maintained at 2·10⁻¹⁰ mbar. The XPS measurements were then performed in the electron binding energy ranges corresponding to Rh 3d excitations and C, N and O 1s excitations. All samples were measured twice and the reported values are the average of the two analyses.

General hydrogenation procedure

All reactions were performed in a 300 mL stainless steel high pressure autoclave equiped with an electrically heated jacket, a turbine stirrer with a variable speed magnetic driver and a liquid sampling line. In a typical reaction, the reactor was loaded with the substrate (0.5 mmol), water (50 mL) and catalyst (10 mg). Afterwards, the reactor was pressurized with H₂ (4 bar) three times followed by evacuation to displace residual air in the reactor. The autoclave was then filled with H₂ (1 or 10 bar), heated to the desired temperature and the reaction initiated by stirring the mixture at 320 rpm. After the selected reaction time the autoclave was cooled down to room temperature. An aliquot of the reaction mixture was subsequently analyzed by gas chromatography (GC-FID) using a chromatograph (Agilent 6890N) equiped with an HP-5 capillary column (Agilent, J&W, 30 m x 320 µm). Gas chromatography coupled to mass spectrometry (GC-MS) was also performed on Agilent 6850N equipment fitted with the same capillary column.

Results and Discussions

Characterization of RhNPs/PVP

Rhodium nanoparticles stabilized by PVP polymer (RhNPs/PVP) were synthesized following the socalled "organometallic approach" previously developed by some of the authors.^{21,22} This method allows to prepare well-controlled NPs that display interesting catalytic properties.²³ The organometallic complex [Rh(η^3 -C₃H₅)₃] was used as the rhodium source, and decomposed in THF solution at room temperature under H₂ atmosphere at mild conditions (3 bar H₂).²⁴ The main advantage of this method is the formation of propane as the only by-product, which is inert towards the metallic surface and easily removed, thus allowing to get uncoordinated metal NPs in the PVP stabilizing matrix. The PVP matrix permits to have NPs that are both soluble in organic solvents and water.

The RhNPs/PVP were characterized by electron microscopy at low (TEM) and high resolution (HR-TEM) coupled with energy-dispersive X-ray spectroscopy (EDX) techniques to determine the dispersion of the particles inside the PVP polymer and their mean diameter as well as crystalline structure. TEM analysis performed on the crude colloidal solution confirmed the presence of small, spherical, and very well-dispersed Rh NPs with a mean size of *ca.* 2.2 (\pm 0.9) nm. The particles were found to be homogeneous in shape with a quite narrow size distribution (Figures 2a and 2c). HR-TEM analysis (Figure 2b; [011] atomic planes) revealed well-crystallized NPs with a face centered cubic (fcc) packed structure as expected for metallic Rh(0). The EDX analysis showed a clear signal for elemental Rh as well as well-identified signals for C and N atoms from the PVP polymer that embeds the particles (Figure 2d). Published on 09 November 2016. Downloaded by University of Toronto on 18/11/2016 15:43:18.



Figure 2. (a) TEM and (b) HR-TEM images of the as-prepared RhNPs/PVP; (c) NPs size distribution histogram; (d) EDX analysis spectrum.

The oxidation state and the surrounding chemical environment of RhNPs/PVP were examined by X-ray photoelectron spectroscopy (XPS). Figure 3a show XPS spectra with the signals corresponding to C, N and O from the PVP used as stabilizer and Rh (elemental survey). A signal found at about 200.5 eV (inset Figure 3b) is attributed to contamination of Cl from the organometallic precursor. However, it is quite insignificant since it is only about 0.13% of the corresponding intensity compared to the C1s level signal. Figure 3c shows the 3d core level XPS spectra for RhNPs/PVP. The lower binding energy signals at 307.8 eV (3d_{5/2}) and at about 311.9 eV (3d_{3/2}) confirm the metallic state of the Rh NPs. The higher binding energy peak at 313-315 eV (3d_{3/2}) suggests the presence of rhodium oxide species, and comparison with earlier investigations are in agreement with Rh³⁺ species in Rh₂O₃.²⁵ The presence of such species can be attributed to partial oxidation during sample preparation and/or sample introduction to the spectrometer. However, even if such rhodium oxide species are present, they are likely to be reduced under the hydrogenation reaction conditions to Rh(0). A small signal is further detected at 304

Dalton Transactions

eV and attributed to the 3d level with different chemical environment on the surface. The Rh metal content in the RhNPs/PVP was determined by ICP-AES to be equal to 7.37 wt%.



Figure 3. (a) XPS spectra of the RhNPs/PVP; (b) Enlarged area of the Cl (2p) level; (c) 3d core level XPS of the RhNPs/PVP.

Selective hydrogenation of arenes with RhNPs/PVP



Figure 4. Arene substrates examined for the selective hydrogenation with RhNPs/PVP.

Benzamide (**3** in Figure 4) was chosen as a first substrate for the optimization of the selective hydrogenation reaction conditions, because of its low price compared to benzoic acid. As the nature of the solvent (protic, aprotic, polar or apolar) is a well-known parameter influencing catalyst activity and selectivity in hydrogenation reactions,²⁶ three different solvents were initially tested; *n*-hexane, methanol and water, for the benzamide hydrogenation to cyclohexane carboxamide under mild reaction

Dalton Transactions Accepted Manuscrip

conditions (80 °C, 1 bar H₂, 2 h reaction time). Both conversion and selectivity were determined by GC and GC-MS analysis and are reported in Table 1. Water, which has the least solubility of H₂, gave a full conversion of benzamide and 100% selectivity towards the formation of cyclohexane carboxamide (Table 1, entry 3), whereas *n*-hexane, and methanol with relative high solubility of H₂, were found to be much less effective; no more than 39 and 71% conversion were achieved for *n*-hexane and methanol, respectively (Table 1, entries 1-2). The study was then pursued with water as the reaction solvent to analyze the influence of temperature. At 40 and 25 °C (Table 1 entries 4 and 5) the Rh nanocatalyst displays the same high activity as at 80°C, yielding full conversion of benzamide with 100% selectivity towards the desired cyclohexane carboxamide product. Furthermore, a control experiment with no catalyst was performed in order to ensure the indispensability of the catalyst for benzamide hydrogenation to cyclohexane carboxamide. As expected, no reaction product was achieved under the selected reaction conditions (Table 1, entry 6).

Entry	Solvent	Temperature	Conversion	Selectivity ^b	TOF ^c
		(°C)	(%)	(%)	(h ⁻¹)
1	<i>n</i> -hexane	80	39	>99	13.9
2	methanol	80	71	>99	25.4
3	water	80	100	>99	35.7
4	water	40	100	>99	35.7
5	water	25	100	>99	35.7
6 ^d	water	80	0	0	0

Table 1. Hydrogenation of benzamide^a

^a Reaction conditions: 0.5 mmol substrate, 10 mg RhNPs/PVP catalyst (7.36 wt% Rh), 1.4 mol% substrate, 50 mL solvent, 2 h, 320 rpm, 1 bar H₂. ^b Selectivity to cyclohexane carboxamide. ^c Calculated as mol cyclohexane carboxamide per mol Rh per hour. ^d No catalyst.

After choosing the preferred reaction conditions regarding solvent and temperature (water and 25 °C) the catalytic performance of the RhNPs/PVP catalyst was evaluated for hydrogenation of alternative substrates. A series of eight other arene substrates containing diverse electron donating (EDG) or electron withdrawing (EWG) groups were selected (Figure 4), and the obtained results are collected in Table 2.

Dalton Transactions Accepted Manuscrip

Entry	Substrate	Conversion	Yield	Selectivity ^b	TOF ^c
		(%)	(%)	(%)	(h ⁻¹)
1	1	74	73	>98	26.4
2	2	100	99	>99	35.7
3	3	100	97	>97	35.7
4	4	100	99	>99	35.7
5	5	93	92	>98	33.2
6	6	86	85	>98	30.6
7	7	100	99	>99	35.7
8	8	100	99	>99	35.7
9	9	100	20	20	35.7

 Table 2. Hydrogenation of alternative arenes^a

^a Reaction conditions: 0.5 mmol substrate, 10 mg RhNPs/PVP (7.36 wt% Rh), 1.4 mol%, 50 mL solvent, 25 °C, 2 h, 320 rpm, 1 bar H₂. ^b Selectivity to ring hydrogenation product. ^c Calculated as mol cyclohexane carboxamide per mol Rh per hour.

The RhNPs/PVP catalyst showed excellent activity with all of the tested arene substrates resulting in conversions in the range 74-100 % and selectivity >97 % to the desired ring hydrogenated products except for acetophenone **9** (Table 2, entries 1-9). Instead, the product selectivity of cyclohexyl methyl ketone from **9** was only 20 % and 1-phenylethanol (keto group hydrogenation) was observed as the major product, thus indicating preferential reduction of the carbonyl group, instead of ring hydrogenation, for this substrate.²⁷ Notably, the oxo group contained in benzamide **3** and benzoic acid **4** were not reduced under the applied reaction conditions. These observations corroborate with previously reported results with Rh NPs stabilized on carbon nanofibers (CNF) under similar reaction conditions.²⁸ As shown in Table 2, no clear differences were found at the applied reaction conditions in the catalytic hydrogenation of the arene substrates despite their different EDG or EWG. It has been proposed that EDG can facilitate faster hydrogenation as the result of a much stronger adsorption of the substrates on the metal surface. However, stronger adsorption can also be detrimental because of an increase of the hydrogenation energy barrier due to π -complexation of the aromatic ring.^{28,29} Thus, these opposing effects probably make the effect of EDG or EWG unclear.³⁰ In terms of TOF the catalytic performance

of the prepared RhNPs/PVP catalyst is similar to the results obtained by Barbaro and co-workers with resin-supported RhNP catalysts under mild reaction conditions (1 bar and RT).³¹ Other RhNPs-based catalytic systems have been reported to be more active in the hydrogenation of arenes than the one presented in this work, but usually the reaction conditions are more harsh in terms of temperature (> 60 °C) and H₂ pressure (> 10 bar). Moreover, the present work use water as the solvent making the overall process greener than other reported catalytic systems.³¹⁻³³

Encouraged by the good performance of the RhNPs/PVP catalyst in the selective hydrogenation of arenes, the hydrogenation of levulinic acid and methyl levulinate was further explored as a plausible route to obtain γ -valerolactone from biomass (Scheme 1). The reaction conditions were selected on the basis of our recently developed catalytic system with Au core and Pt shell NPs stabilized on graphitized carbon black (Au@Pt/G-CB).^{28,34} Thus, the reactions were performed at 120 °C under 20 bar of H₂ for 20 h in water as solvent.



Scheme 1. Hydrogenation of levulinic acid and methyl levulinate.

In both of the examined reactions 100 % conversion and selectivity >99 % to γ -valerolactone were achieved with the RhNPs/PVP catalyst. These initial results are highly promising since significantly more harsh reaction conditions (200 °C, 30-40 bar H₂) are generally reported in literature for these reactions to achieve similar yields of γ -valerolactone with catalysts containing transition metals like Pt, Ru and Rh.^{29,30,35,36} More detailed exploration of the γ -valerolactone formation from methyl levulinate and derivatives will be the subject of future work.

Conclusions

Well-defined PVP-stabilized Rh nanoparticles of *ca*. 2.2 nm in size were obtained via the organometallic method, namely by hydrogenation of the organometallic complex [Rh(η^3 -C₃H₅)₃]) in the presence of PVP, and then evaluated as catalyst in the hydrogenation of a series of arene substrates.

Dalton Transactions

The RhNPs/PVP catalyst showed excellent activity and selectivity towards aromatic ring hydrogenation compared to other reported transition metal-based catalysts at room temperature and 1 bar H₂, except for acetophenone where 1-phenylethanol was formed as the major product. In addition, the prepared RhNPs/PVP nanomaterial showed to be a highly promising catalyst for the hydrogenation of levulinic acid and methyl levulinate in water, leading to quantitative formation of the fuel additive γ -valerolactone under moderate reaction conditions in opposite to previously reported catalytic systems. Recycling tests of the RhNPs/PVP catalyst are currently under investigation to validate its long-term stability.

Acknowledgements

The authors thank V. Collière at the "Centre de microcaractérisation Raymond Castaing - UMS 3623 in Toulouse" for HR-TEM analysis. CNRS and UPS-Université de Toulouse are acknowledged for financial support and a MESR PhD fellowship (M. Ibrahim). The UNIK research initiative Catalysis for Sustainable Energy is also acknowledged for financial support of a PhD fellowship (R. Poreddy).

References

- ¹Temkin, M. I.; Konyukhov, V. Y.; Kul'kova, N. V., J. Res. Inst. Catal. 1980, 28, 363-370.
- ²Weissermel, H; Arpe, H. J. Industrial organic chemistry. 3rd ed.Weinheim: VCH: **1997**:256-257
- ³Patton, S.M.; Cropp, T.A; Reynolds, K., *Biochemistry* **2000**, *39*, 7595-7604.
- ⁴Shinkai, H.; Nishikawa, M.; Sato, Y.; Toi, K.; Kumashiro, I.; Seto, Y.; Fukuma, M.; Dan, K.; Toyoshima, S., *J. Med. Chem.* **1989**, *32*, 1436-1441.
- ⁵Moore, B. S.; Cho, H.; Casati, R.; Kennedy, E.; Reynolds, K. A.; Mocek, U.; Beale, J. M.; Floss, H. G., *J. Am. Chem. Soc.* **1993**, *115*, 5254-5266.
- ⁶Thomas, J. M.; Johnson, B. F.; Raja, R.; Sankar, G.; Midgley, P. A., *Acc. Chem. Res.* **2003**, *36*, 20-30. ⁷Wang, H. J.; Zhao, F. Y., *Int. J. Mol. Sci.* **2007**, *8*, 628-634.
- ⁸Zong, B. N.; Zhang, X. X.; Qiao, M. H., AIChE J. **2009**, 55, 192-197.
- ⁹Raja, R.; Khimyak, T.; Thomas, J. M.; Hermans, S.; Johnson, B. F., *Angew. Chem., Int. Ed.* **2001**, *40*, 4638-4642.
- ¹⁰Augustine, R. L., Heterogeneous Catalysis for the Synthetic Chemist; Marcel Dekker: New York, **1996**.

Dalton Transactions Accepted Manuscrip

- ¹¹Kou, J. C.; Zhang, X. X.; Zong B. N., Chem Ind Eng Prog. 2002, 21,741-744.
- ¹²Pernicone, N.; Cerboni, M.; Prelazzi, G.; Pinna, F.; Fagherazzi, G., Catal. Today. 1998, 44,129-135.
- ¹³a)SNIA VISCOSA. Italy Patent, IE 967918, **1964**; b)SNIA VISCOSA. Italy Patent, IE 1019795, **1966**; c)SNIA VISCOSA. Italy Patent, IE 1122162, **1968**.
- ¹⁴Tsung, C.-K.; Kuhn, J. N.; Huang, W.; Aliaga, C.; Hung, L.-I.; Somorjai, G. A.; Yang, P., *J. Am. Chem. Soc.*, **2009**, *131*, 5816-5822.
- ¹⁵Hu, B.; Ding, K.; Wu, T.; Zhou,X.; Fan, H.; Jiang, T.; , Q.; Han, B., *Chem. Commun.*, **2010**, *46*, 8552-8554.
- ¹⁶Yoon, B.; Pan, H.-B.; Wai, C.-M., J. Phys. Chem. C,2009, 113, 1520-1525.
- ¹⁷a) Astruc, D. *Nanoparticles and Catalysis*. Wiley-VCH, **2008**; b) Polshettiwar, V., *Nanomaterials in Catalysis*. Edited by Philippe Serp and Karine Philippot, **2013**;c) Kemnitz, E.; Parvulescu, V., *New Materials for Catalytic Applications*, Elsevier, **2016**.
- ¹⁸Yang, X.; Yan, N.; Fei, Z.; Crespo-Quesada, R. M.; Laurenczy, G.; Kiwi-Minsker, L.; Kou, Y.; Li,
 Y.; Dyson, P. J., *Inorganic Chemistry*, **2008**, *47*, 7444–7446.
- ¹⁹Yan, N.; Yuan, Y.; Dyson; P. J., *Chem. Commun.*, **2011**, *47*, 2529-2531.
- ²⁰Powell, J.; Shaw, B. L., Chem. Commun., **1966**, 323-325.
- ²¹Amiens, C.; Chaudret, B.; Ciuculescu-Pradines, D.; Collière, V.; Fajerwerg, K.; Fau, P.; Kahn, M.; Maisonnat, A.; Philippot, K., *New J. Chem.*, **2013**, *37*, 3374-3401.
- ²²Amiens, C.; Ciuculescu-Pradines, D.; Philippot, K., Coord. Chem. Rev., 2016, 308, 409-432.
- ²³Kinayyigit, S.; Philippot, K., Organometallic Approach for the Synthesis of Noble Metal Nanoparticles: Towards Application in Colloidal and Supported Nanocatalysis. in *Metal Nanoparticles for Catalysis: Advances and Applications*, T. Tao (Ed.), RSC, **2014**, Chapter 4, 47-82.
- ²⁴Ibrahim, M. Functionalization of Metal Nanoparticles for Application in Catalysis. *PhD Thesis*, UPS-Toulouse, **2016**.
- ²⁵a) Peuckert, M., Surf. SCI., **1984**, 141, 500-514; b) Barr, T. L., J. Phys. Chem., **1978**, 82, 1801-1810.
- ²⁶Takagi, H.; Isoda, T.; Kusakabe, K.; Morooka; S., *Energy & Fuels*, **1999**, *13*, 1191-1196.
- ²⁷Castelbou, J. L.; Bres-Femenia, E.; Blondeau, P.; Chaudret, B.; Castillon, S.; Claver, C.; Godard, C., *ChemCatChem*, **2014**, *6*, 3160-3168.
- ²⁸Anderson, J. A.; Athawale, A.; Imrie, F.E.; Kenna, F.-M.; McMcCue, A.; Molyneux, D.; Power, K.; Shand, M.; Wells, R.P.K., *Journal of Catalysis*, **2010**, *270*, 9-15.

²⁸Schulz, J.; Roucoux, A.; Patin, H., Chem.-Eur. J., 2000, 6, 618-624.

²⁹Zahmakiran, M.; Roman-Leshkov, Y.; Zhang, Y., *Langmuir*, **2012**, 28, 60-64.

³⁰Lu, F.; Liu, J.; Xu, J.; J. Mol. Catal. A: Chem., 2007, 271, 6-13.

³¹Moreno-Madorran, C.; Liguori, F.; Mercade, E.; Godard, C.; Claver, C.; Barbaro, P., *Catal. Sci. Technol.*, **2015**, *5*, 3762-3772.

³²Sanchez, A.; Fang, M.; Ahmed, A.; Sanchez-Delgado, R.A., *Applied Catalysis A: General*, **2014**, 477, 117-124.

³³Huang, L.; Luo, P.; Pei, W.; Liu, X.; Wang, Y.: Wang, J.; Xing, W.; Huan, J., *Adv. Synth. Catal.*, **2012**, *354*, 2689-2694.

³⁴Engelbrekt, C.; Seselj, N., Poreddy, R. Riisager, A.; Ulstrup, J.; Zhnag, J.; *J. Mater. Chem. A.*, **2016**, 4, 3278-3286.

³⁵Kon, K.; Onodera, W.; Shimizu, K-I., Catal. Sci. Technol., 2014, 4, 3227-3234.

³⁶Hengne, M. A.; Biradar, N. S.; Rode, C. V., Catal. Lett. 2012, 142, 779-787.



 \mathbf{R}^1 = H, C(O)H, OH, C(O)NH₂, C(O)OH, CH₂OH, CH₃, OCH₃, \mathbf{R}^2 = H, CH₃, \mathbf{Z} = N, C