HETEROCYCLES, Vol. 88, No. 1, 2014, pp. -. © 2014 The Japan Institute of Heterocyclic Chemistry Received, 24th April, 2013, Accepted, 23rd May, 2013, Published online, 24th May, 2013 DOI: 10.3987/COM-13-S(S)8

TWO-STEP SYNTHESIS OF 3,4-ETHYLENEDIOXYTHIOPHENE (EDOT) FROM 2,3-BUTANEDIONE

Iwao Hachiya,^a Toshihiro Yamamoto,^a Tatsuhiko Inagaki,^a Tomohiro Matsumoto,^a Atsushi Takahashi,^{a,b} Isao Mizota,^a and Makoto Shimizu^{a,*}

^a Department of Chemistry for Materials, Graduate School of Engineering, Mie University, Tsu, Mie 514-8507, Japan. E-mail: mshimizu@chem.mie-u.ac.jp
^b Takemoto Oil & Fat Co., Ltd., Gamagori, Aichi 443-0036, Japan

This paper is dedicated to Professor Victor Snieckus on the occasion of his 77th birthday.

Abstract – 3,4-Ethylenedioxythiophene (EDOT) was synthesized from commercially available 2,3-butanedione in only a two-step procedure including ketalization and thiophene formation.

Poly(3,4-ethylenedioxythiophene) (PEDOT) prepared by polymerization of 3,4-ethylenedioxythiophene (EDOT (1)) and its derivatives are one of the most successful electron-conducting polymers and widely used as antistatic treatment of plastics and electrode materials for solid state electrolyte capacitors.¹ Several methods for the synthesis of EDOT (1) have been reported using the double Williamson etherification, ² Mitsunobu reaction, ³ transetherification, ⁴ and zirconocene dichloride mediated reaction.⁵ We have already reported a synthetic route toward EDOT (1) from commercially available (*Z*)-but-2-ene-1,4-diol (2) or but-2-yne-1,4-diol (3) using epoxidation, etherification, and thiophene formation.⁶ The characteristics of the synthetic route were relatively mild reaction conditions such as without use of carcinogenic reagents and heavy metals. However, it needed eight or nine steps for the synthesis of EDOT (1) from each starting material (Scheme 1).



Scheme 1. Synthesis of EDOT (1) from (Z)-But-2-ene-1,4-diol (2) or But-2-yne-1,4-diol (3)

In the course of our efforts for the efficient synthesis of EDOT (1), we focused on commercially available 2,3-butanedione (4) as a starting material. Herein, we describe a two-step synthesis of EDOT (1) from commercially available 2,3-butanedione (4).

Scheme 2 shows a retrosynthetic analysis of EDOT (1): EDOT (1) could be synthesized by thiophene formation of 2,3-dimethylene-1,4-dioxane (5), which could be obtained by dienol bisetherification of commercially available 2,3-butanedione (4).



Scheme 2. Retrosynthetic Analysis of EDOT (1)

We first examined the synthesis of 2,3-dimethylene-1,4-dioxane (5) using 1,2-dibromoethane (6). The reactions of 2,3-butanedione (4) with 1,2-dibromoethane (6) were carried out in the presence of p-toluenesulfonic acid, NaHMDS, or triethylamine; however, 2,3-dimethylene-1,4-dioxane (5) was not obtained (Eq. 1).



We next examined the synthesis of 2,3-dimethylene-1,4-dioxane (**5**) using ethylene glycol (**7**) instead of 1,2-dibromoethane (**6**). The reaction of 2,3-butanedione (**4**) with ethylene glycol (**7**) and trimethyl orthoformate (**8**) in MeOH was carried out in the presence of a catalytic amount of camphorsulfonic acid (CSA) under reflux to give 2,3-dimethoxy-2,3-dimethyl-1,4-dioxane (**9**) in 95% yield instead of the desired 2,3-dimethylene-1,4-dioxane (**5**) (Eq. 2).⁷



We therefore planned the synthesis of EDOT (1) by trapping of 2,3-dimethylene-1,4-dioxane (5) generated in situ from 2,3-dimethoxy-2,3-dimethyl-1,4-dioxane (9) with a sulfur source (Scheme 3).



Scheme 3. Retrosynthetic Analysis of EDOT (1) via 2,3-Dimethoxy-2,3-dimethyl-1,4-dioxane (9)

Komatsu reported that a facile [4+1] type synthetic route to thiophene (11) from dienol bissilyl ether (10) and elemental sulfur (Eq. 3).⁸ Therefore, we chose S_8 as a sulfur source for the synthesis of EDOT (1).



The reactions of 2,3-dimethoxy-2,3-dimethyl-1,4-dioxane (9) with S_8 were carried out in the presence of several additives such as CSA, Pd/C, palladium black, palladium salts, copper salts, and molecular sieves 4A (MS 4A); however, EDOT (1) was obtained in yields ranging from 0 to 15% (Eq. 4).



We next examined the synthesis of EDOT (1) under microwave irradiation to improve the yield. Table 1 summarizes the results. When the reaction was carried out under microwave irradiation in toluene at 180 °C, EDOT (1) was not obtained (entry 1). Several additives were examined. Among additives tested, CuI was found to be efficient (entries 2-12). Effects of concentration, temperature, and reaction time were next investigated. When the reaction was carried out in the presence of CuI (0.1 equiv) at 180 °C for 6 h, EDOT (1) was obtained in 37% yield (entry 12).

A plausible reaction mechanism for the formation of EDOT (1) is shown in Scheme 4 which refers to that Komatsu.⁸ 2,3-Dimethylene-1,4-dioxane (5) reported by would be generated from 2,3-dimethoxy-2,3-dimethyl-1,4-dioxane (9) along with elimination of MeOH. Nucleophilic reaction of 2,3-dimethylene-1,4-dioxane (5) to S_8 would occur to give the ring-opening intermediate (12). Intramolecular cyclization of the intermediate (12) would give the 1,2-dithiine intermediate (13) along with elimination of S_6 , and the subsequent elimination of H_2S gives EDOT (1). Although the role of CuI as an additive is not yet clear, we presume that it acts as a mild Lewis acid catalyst for the elimination of MeOH and ring-opening of S_8 .

	C		3 (5 equiv) additive		
	MeO $^{/}$ OMe toluene, MW, temp., time		s		
		9		1: EDOT	
Entry	Additive (equiv)	Concentration (M)	Temp. (°C)	Time (h)	Yield (%)
1	None	0.2	180	1	0
2	DBU (2.0)	0.2	180	1	0
3	NaOAc (2.0)	0.2	180	1	0
4	CSA (2.0)	0.2	180	1	Many spots
5	CSA (0.1)	0.2	180	1	0
6	CuI (0.1)	0.2	180	1	14
7	CuI (0.1)	0.2	160	1	0
8	CuI (0.1)	0.2	160	2	0
9	CuI (0.1)	0.2	160	4	6
10	CuI (0.1)	0.2	160	6	32
11	CuI (0.1)	0.1	160	6	11
12	CuI (0.1)	0.1	180	6	37

Table 1. Microwave-assisted Synthesis of EDOT (1)^a

^aConditions: S_8 (2.5 mmol), 2,3-dimethoxy-2,3-dimethyl-1,4-dioxane (9) (0.50 mmol), and CuI (0.050 mmol) in toluene (2.5 or 5.0 mL).



Scheme 4. Plausible Reaction Mechanism for the Synthesis of EDOT (1) from 2,3-Dimethoxy-2,3-dimethyl-1,4-dioxane (9) with S_8

In conclusion, we have developed a two-step synthesis of EDOT (1) from commercially available 2,3-butanedione (4). Although the yield of EDOT (1) was moderate, the present method provides a very short-step and easy access to several EDOT derivatives using substituted 1,2-diols instead of ethylene glycol (7), and the overall yield is good. Furthermore, the application of the process to the industrial synthesis of EDOT (1) may be possible by an efficient heating device.

EXPERIMENTAL

General. Reactions under microwave irradiation were carried out using a Biotage Initiator. Infrared spectra were recorded on a JASCO FT/IR-460 Plus spectrometer. ¹H NMR spectra were recorded on a JEOL JNM α -500 spectrometer (500 MHz) with tetramethylsilane as an internal standard. ¹³C NMR spectra were recorded on a JEOL JNM α -500 spectrometer (126 MHz). Chemical sifts are reported in δ units, parts per million from the central peak of CDCl₃ (δ 77.0) as an internal reference. High resolution mass spectra (EI) were recorded on a JEOL JMS-700D mass spectrometer. MeOH was distilled from magnesium methoxide and stored over molecular sieves 3A. Toluene was pre-dried with CaCl₂, distilled, and stored over molecular sieves 4A. Purification of products was performed by column chromatography on silica gel (Kanto Chemical Co. Inc., Silica Gel 60 N (spherical, neutral)) and/or preparative TLC on silica gel (Merck Kiesel Gel GF254).

Synthesis of 2,3-Dimethoxy-2,3-dimethyl-1,4-dioxane (9):

To a solution of ethylene glycol (7) (7.88 g, 127 mmol) in MeOH (63 mL) was added 2,3-butanedione (4) (10.0 g, 116 mmol), trimethyl orthoformate (8) (29.6 g, 279 mmol), and camphorsulfonic acid (2.93 g, 12.6 mmol) at room temperature under an argon atmosphere. The mixture was stirred at reflux for 24 h. Triethylamine (1.9 mL) was added to the reaction mixture to quench the reaction. The mixture was diluted with Et_2O and washed with water, sat. aqueous NaHCO₃, and brine, dried over anhydrous Na₂SO₄, and filtered. The solvents were evaporated in vacuo and then the residue was purified by chromatography on silica gel (*n*-Hex/EtOAc = 1/1, as an eluent) to give 2,3-dimethoxy-2,3-dimethyl-1,4-dioxane (9) (19.4 g, 95%) as a yellow oil.

¹H NMR (500 MHz, CDCl₃) δ = 3.95 (dd, *J* = 12.2, 19.5 Hz, 2H), 3.43 (dd, *J* = 12.2, 19.5 Hz, 2H), 3.31 (s, 6H), 1.29 (s, 6H). ¹³C NMR (126 MHz, CDCl₃) δ = 98.5, 58.9, 48.1, 17.8. IR (neat) 2954, 2831, 1449, 1373, 1308, 1264, 1269, 1141, 1084, 1037, 941, 918, 871, 829 cm⁻¹. HRMS (EI): Calculated for C₈H₁₆O₄ (M)⁺ 176.1049, found 176.1050.

Synthesis of EDOT (1)⁹ (Table 1, entry 12):

S₈ (640 mg, 2.5 mmol), 2,3-dimethoxy-2,3-dimethyl-1,4-dioxane (**9**) (88 mg, 0.50 mmol), toluene (5.0 mL), CuI (9.5 mg, 0.050 mmol), and a magnetic stirring bar were placed in a microwave reactor vial. The vial was capped, placed in the microwave reactor, and irradiated at 180 °C for 6 h. The mixture was cooled to room temperature, diluted with EtOAc, and filtered through a Celite pad. The solvents were evaporated in vacuo and then the residue was purified by preparative TLC on silica gel (developed twice with *n*-Hex and once with *n*-Hex/EtOAc = 8/1) to give EDOT (**1**) (26.0 mg, 37%) as a yellow oil. ¹H NMR (500 MHz, CDCl₃) δ = 6.32 (s, 2H), 4.20 (s, 4H). ¹³C NMR (126 MHz, CDCl₃) δ = 141.8, 99.6, 64.7. IR (neat) 3111, 2974, 2924, 2872, 1488, 1449, 1422, 1236, 1274, 1186, 1057, 932, 893, 761 cm⁻¹.

REFERENCES AND NOTES

- For a review, see: L. Groenendaal, F. Jonas, D. Freitag, H. Pielartzik, and J. R. Reynolds, *Adv. Mater.*, 2000, 12, 481 and references therein.
- 2. Q. Pei, G. Zuccarello, M. Ahlskog, and O. Inganäs, *Polymer*, 1994, **35**, 1347.
- (a) K. Zong, L. Madrigal, L. Groenendaal, and J. R. Reynolds, *Chem. Commun.*, 2002, 2498; (b) D. Caras-Quintero and P. Bäuerle, *Chem. Commun.*, 2002, 2690.
- Short step synthesis of EDOT via *p*-TsOH catalyzed transetherification of 3,4-dimethoxythiophene with ethylene glycol, see: (a) F. von Kieseritzky, F. Allared, E. Dahlstedt, and J. Hellberg, *Tetrahedron Lett.*, 2004, 45, 6049; (b) S. Chen, B. Lu, X. Duan, and J. Xu, *J. Polym. Sci. Part A: Polym. Chem.*, 2012, 50, 1967.
- 5. S. Das, P. K. Dutta, S. Panda, and S. S. Zade, J. Org. Chem., 2010, 75, 4868.
- 6. I. Hachiya, T. Matsumoto, T. Inagaki, A. Takahashi, and M. Shimizu, *Heterocycles*, 2010, 82, 449.
- For a review on 1,2-diacetals, see: S. V. Ley, D. K. Baeschlin, D. J. Dixon, A. C. Foster, S. J. Ince, H. W. M. Priepke, and D. J. Reynolds, *Chem. Rev.*, 2001, **101**, 53. For examples, see: (b) N. Mariet, M. Ibrahim-Ouali, and M. Santelli, *Tetrahedron Lett.*, 2003, **44**, 5315; (c) S. V. Ley, E. Diez, D. J. Dixon, R. T. Guy, P. Michel, G. L. Nattrass, and T. D. Sheppard, *Org. Biomol. Chem.*, 2004, **2**, 3608.
- 8. Y. Kasano, A. Okada, D. Hiratsuka, Y. Oderaotoshi, S. Minakata, and M. Komatsu, *Tetrahedron*, 2006, **62**, 537.
- 9. ¹H NMR, ¹³C NMR, and IR spectra of the synthetic and the commercially available EDOT (1) were identical.