



Subscriber access provided by University of Sunderland

# Article

# Screening Libraries of Amphiphilic Janus Dendrimers Based on Natural Phenolic Acids to Discover Monodisperse Unilamellar Dendrimersomes

Irene Buzzacchera, Qi Xiao, Hong Han, Khosrow Rahimi, Shangda Li, Nina Yu. Kostina, B. Jelle Toebes, Samantha E Wilner, Martin Moeller, Cesar Rodriguez-Emmenegger, Tobias Baumgart, Daniela A. Wilson, Christopher James Wilson, Michael L. Klein, and Virgil Percec

Biomacromolecules, Just Accepted Manuscript • Publication Date (Web): 25 Oct 2018 Downloaded from http://pubs.acs.org on October 25, 2018

# **Just Accepted**

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036

Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

# Screening Libraries of Amphiphilic Janus Dendrimers Based on Natural Phenolic

# Acids to Discover Monodisperse Unilamellar Dendrimersomes

Irene Buzzacchera,<sup>†,‡,I</sup> Qi Xiao,<sup>†,§</sup> Hong Han,<sup>†</sup> Khosrow Rahimi,<sup>‡,⊥</sup> Shangda Li,<sup>†</sup> Nina Yu. Kostina,<sup>‡,⊥</sup> B. Jelle Toebes,<sup>#</sup> Samantha E Wilner,<sup>†</sup> Martin Möller,<sup>‡,⊥</sup> Cesar Rodriguez-Emmenegger,<sup>‡,⊥</sup> Tobias Baumgart,<sup>†</sup> Daniela A. Wilson,<sup>#</sup> Christopher J. Wilson,<sup>I</sup> Michael L. Klein<sup>§</sup> and Virgil Percec<sup>†,\*</sup>

<sup>†</sup>Roy & Diana Vagelos Laboratories, Department of Chemistry, University of Pennsylvania, Philadelphia, Pennsylvania 19104-6323, United States

<sup>‡</sup>DWI–Leibniz Institute for Interactive Materials, RWTH Aachen University, 52074 Aachen, Germany <sup>†</sup>NovioSense B.V., Transistorweg 5, 6534 AT Nijmegen, The Netherlands

<sup>§</sup>Institute of Computational Molecular Science, Temple University, Philadelphia, Pennsylvania 19122, United States

<sup>1</sup>Institute of Technical and Macromolecular Chemistry, RWTH Aachen University, 52074 Aachen, Germany <sup>#</sup>Institute of Molecules and Materials, Radboud University, Heyendaalseweg 135, 6525 AJ Nijmegen, The Netherlands

\*E-mail: percec@sas.upenn.edu

ABSTRACT: Natural, including plant, and synthetic phenolic acids are employed as building blocks for the synthesis of constitutional isomeric libraries of self-assembling dendrons and dendrimers that are the simplest examples of programmed synthetic macromolecules. Amphiphilic Janus dendrimers are synthesized from a diversity of building blocks including natural phenolic acids. They self-assemble in water or buffer into vesicular dendrimersomes employed as biological membrane mimics, hybrid and synthetic cells. These dendrimersomes are predominantly unilamellar or multilamellar vesicles with size and polydispersity that is predicted by their primary structure. However, in numerous cases unilamellar dendrimersomes completely free of multilamellar assemblies are desirable. Here we report the synthesis and structural analysis of a library containing 13 amphiphilic Janus dendrimers containing linear and branched alkyl chains on their hydrophobic part. They were prepared by an optimized iterative modular synthesis starting from natural phenolic acids. Monodisperse dendrimersomes were prepared by injection and giant polydisperse by hydration. Both were structurally characterized to select the molecular design principles that provide unilamellar dendrimersomes in higher yields

and shorter reaction times than under previously used reaction conditions. These dendrimersomes are expected to provide important tools for synthetic cell biology, encapsulation and delivery.

## **INTRODUCTION**

Natural including plant AB<sub>n</sub> phenolic acids are the building blocks employed by our laboratory for the iterative synthesis of constitutional isomeric self-assembling dendrons and dendrimers as the simplest class of Programmed Synthetic Macromolecules.<sup>1-12</sup> Phenolic acids are naturally occurring aromatic compounds having phenol and carboxylic acid functionalities.<sup>1-7</sup> Our laboratory elaborated the concept of Programmed Synthetic Macromolecules, which employs biological principles to achieve a function. Specifically, the first biological principles that involve primary-secondary-tertiary-quaternary structure were employed to create a desired function. Programmed Synthetic Macromolecules are monodisperse self-assembling macromolecules with precise primary structure that includes composition, sequence and stereochemistry. They undergo, when desired, folding into secondary and tertiary structures and self-organization into quaternary structures that are responsible for the creation of a defined function. When the periodic and quasi-periodic assemblies studied exhibit internal order, their structural and retro-structural analysis allows the elucidation of their structure and the elucidation of the mechanism of hierarchical supramolecular structure formation by a combination of methods including X-ray diffraction together with simulation of oriented fiber diffractograms via molecular models, reconstructed electron-density maps, electron diffraction, transmission electron microscopy (TEM), cryo-TEM, circular dichroism, and molecular dynamics simulations (Figure 1).



**Figure 1.** Accelerated synthesis of constitutional isomeric libraries of quasi-equivalent self-assembling dendrons and dendrimers and the analysis of their quaternary, tertiary, and secondary structures *via* structural and retrostructural analysis of their periodic and quasi-periodic assemblies with internal order.<sup>8,9,11,29</sup> Adapted with permission from ref 29. Copyright 2009 American Chemical Society.

The methodologies elaborated in our laboratory for structural and retrostructural analysis were inspired by the pioneering work of Watson, Crick, Klug and others<sup>13–15</sup> in the field of structural biology and transplanted into the field of macromolecular self-assembly<sup>16–18</sup> Many of the classic problems from structural biology were solved with this combination of diffraction tools. In the same way by investigating nine generational<sup>17–32</sup> and one deconstruction<sup>33</sup> libraries, our laboratory discovered soft matter quasicrystals and Frank-Kasper phases of supramolecular dendrons and dendrimers,<sup>17,18,34–38</sup> mediated changes in the chemical reactivity and chemoselectivity,<sup>20,39–42</sup> discovered self-repairing supramolecular electronics,<sup>43–45</sup> mimics of transmembrane protein channels analogous to aquaporin,<sup>46–54</sup> molecular machines,<sup>55–59</sup> chiral supramolecular columns and chiral supramolecular spheres.<sup>60–63</sup>

thermodynamically controlled crystallization,<sup>64–66</sup> deracemization in the crystal state,<sup>67</sup> a double helix that disregards chirality,<sup>68</sup> as well as a solid-state orientational memory effects.<sup>69–71</sup>

However, the entire machinery of life including nucleic acids, proteins, photosynthesis, etc., is compartmentalized, assembled and functions inside a cell, the membrane of which is the least understood biological system. The main reason for this limited understanding is that cells and cell membranes are dynamic fluid assemblies that cannot be investigated by the diffraction methodology elaborated as described above.<sup>72-76</sup> Therefore, a fundamental question is how can one generate Programmed Synthetic Macromolecules that produce biological membrane mimics without the help of diffraction methods? A typical biological membrane is a fluidic bilayer structure co-assembled from phospholipids, cholesterol, transmembrane proteins, glycolipids, glycoproteins, and other components. Once the components of a biological membranes are removed, the host phospholipids alone form vesicles named liposomes that are unstable for long time (Figure 2).<sup>77</sup> Stealth liposomes, containing some phospholipids conjugated to polyethylene glycol or other water-soluble polymers,<sup>78–80</sup> and amphiphilic block copolymers (their vesicles are named polymersomes)<sup>81</sup> have been used to overcome the stability problem of phospholipid liposomes (Figure 2). However, both Stealth liposomes and polymersomes are prepared by complex methods, are polydisperse and cannot be conjugated with multiple functional groups. In addition, polymersomes have a thicker bilayer than either liposomes or biological membranes.



**Figure 2.** Structures of liposomes, stealth liposomes, polymersomes, dendrimersomes, glycopolymers, glycodendrimers, glycoliposomes, glycodendrimersomes, sequence-defined glycodendrimersomes. Reprinted with permission from ref 84. Copyright 2014 National Academy of Sciences USA; from Springer Nature, ref 12. Copyright 2013 Springer-Verlag Berlin Heidelberg; from ref 96. Copyright 2016 National Academy of Sciences USA.

Our laboratory entered the field of biological membrane mimics by discovering that amphiphilic Janus Dendrimers (JDs) made from constitutional isomeric AB<sub>2</sub> and AB<sub>3</sub> natural phenolic acids self-assemble, by injection from ethanol into water or buffer, in stable and monodisperse unilamellar and multilamellar onion-like (Figure 3) vesicles named dendrimersomes (DSs).<sup>83–99</sup>



**Figure 3.** Multilayer onion-like dendrimersomes and glycodendrimersomes.<sup>84,90</sup> Reprinted with permission from ref 84. Copyright 2014 National Academy of Sciences USA.

The dimensions and physical properties of DSs can be predicted when they are prepared by injection but not when they are assembled by hydration.<sup>85</sup> Their bilayer is similar in thickness to that of biological membranes,<sup>85</sup> and unlike phospholipids and block copolymer amphiphiles, they can be functionalized with multiple components. Our laboratory next provided models for glycan-decorated cell-membranes. Previously, glycopolymers, glycodendrimers, and glycoliposomes obtained by complex coassembly, were the only models for biological glycans (Figure 2). Screening libraries of amphiphilic Janus glycodendrimers (JGDs) with various primary structures containing plant, bacterial, and human carbohydrates that bind to sugar-binding proteins (lectins and galectins) led to the discovery of JGDs, which self-assemble into monodisperse unilamellar and multilamellar (Figure 3) vesicles named glycodendrimersomes (GDSs) (Figure 2).<sup>87</sup> Subsequently, twin-twin, single-single and sequence-defined

Page 7 of 55

### Biomacromolecules

JGDs and their corresponding GDSs were synthesized. The next step was to design monodisperse sequence-defined oligomers containing carbohydrates and inert oligooxyethylene-hydrophilic fragments in their structure (Figure 4). These sequence-defined oligomers self-assemble into biological membrane mimics containing various concentrations of carbohydrates (Figure 4).<sup>88–95</sup> With these new systems we could ask the trivial question: What is the minimum concentration of surface carbohydrate that would allow the glycodendrimer to recognize sugar binding proteins? The shocking finding was that the ability to bind proteins increased by decreasing the concentration of carbohydrate.<sup>89,90</sup> These findings indicated that as the concentration of carbohydrate decreased, the rate constant of the recognition process increased! This observation could only be explained with a different rate constant of binding that is mediated by different carbohydrate morphologies determined by distinct supramolecular arrangements of carbohydrates on the surface of these biological membrane mimics. However, structure determination requires diffraction experiments that cannot be performed on fluid vesicles. Fluorescence microscopy is also not available since the size of dendrimersomes is below the resolution of optical microscopy. While the methodology to answer this question is being developed we decided to address some other fundamental problems of biological cell membrane mimics.



**Figure 4.** Sequence-defined Janus glycodendrimers self-assemble in glycodendrimersomes and their agglutination with human galectins (absorbance and rate constant k).<sup>89</sup> Reprinted with permission from ref 89. Copyright 2015 American Chemical Society.

In previous studies, JDs with 3,5-substituted dodecyl chains were extensively used including for hybrids with DSs and bacterial membranes.<sup>96</sup> Models for cell fusion and fission were also elaborated.<sup>97–99</sup> Dodecyloxy chains on phenolic acids units in the hydrophobic part of the Janus dendrimers were chosen in these studies as the cell membrane mimics with similar bilayer width to the natural phospholipids which have 16 or 18 carbons in their alkyl groups. This bilayer width demonstrates that the phenolic acid fragments are part of the hydrophobic part of the bilayer. The self-assemblies from JDs containing 3,5-substituted dodecyl chains, one of the routinely employed Janus dendrimers, form mixtures of unilamellar and multilamellar onion-like DSs. The aim of this report is to deepen the knowledge on the size and stability of unilamellar DSs self-assembled by JDs synthesized from a fixed hydropholic dendron and a variable hydrophobic dendron made from a phenolic acid core substituted with a diversity of alkyl chains of different length and degree of branching. To understand the effect of

Page 9 of 55

the number of carbon atoms of the linear alkyl chains or branched alkyl chain, a library containing 13 JDs was synthesized and the factors affecting the self-assembled monodisperse unilamellar DSs were investigated and are reported here.

## **EXPERIMENTAL SECTION**

# Materials

All reagents were obtained from commercial sources and were used without purification unless otherwise stated.  $CH_2Cl_2$  (DCM) was dried over  $CaH_2$  and freshly distilled before use. Tetrahydrofuran (THF) for preparation of DSs was distilled with NaHSO<sub>3</sub> and 3,5-di-*tert*-butyl-4-hydroxytoluene (BHT) and restored in dark. Solvents and reagents were deoxygenated when necessary by purging with N<sub>2</sub>. Milli-Q water obtained from Milli-Q UV plus with the resistivity 18.2 M $\Omega$ ·cm was used for the preparation of phosphate-buffered saline (PBS). PBS (1×) was obtained by dissolving 8 g of NaCl, 0.2 g of KCl, 1.44 g of Na<sub>2</sub>HPO<sub>4</sub> and 0.24 g of KH<sub>2</sub>PO<sub>4</sub> in 800 mL of Milli-Q water, adjusted to pH = 7.4 and diluted to 1,000 mL.

## Techniques

<sup>1</sup>H and <sup>13</sup>C NMR spectra were recorded at 500 MHz and 126 MHz respectively, on a Bruker DRX (500 MHz) NMR spectrometer. All NMR spectra were measured at 23 °C in CDCl<sub>3</sub>. Chemical shifts ( $\delta$ ) are reported in ppm and coupling constants (*J*) are reported in Hertz (Hz). The resonance multiplicities in

the <sup>1</sup>H NMR spectra are described as "s" (singlet), "d" (doublet), "t" (triplet), and "m" (multiplet). Residual protic solvent of CDCl<sub>3</sub> (<sup>1</sup>H,  $\delta$  7.26 ppm; <sup>13</sup>C,  $\delta$  77.16 ppm), or tetramethylsilane (TMS) were used as the internal reference in the <sup>1</sup>H- and <sup>13</sup>C-NMR spectra. Evolution of the reaction was monitored by thin-layer chromatography (TLC) using silica gel 60 F<sub>254</sub> precoated plates (E. Merck) and compounds were visualized by UV light with a wavelength of 254 nm. Purifications by flash column chromatography were performed using flash silica gel from Silicycle (60 Å, 40-63 µm) with the indicated eluent. The purity of the products was determined by a combination of TLC and high-pressure liquid chromatography (HPLC) was carried out using Shimadzu LC-20AD high-performance liquid chromatograph pump, a PE Nelson Analytical 900 Series integration data station, a Shimadzu RID-10A refractive index (RI) detector, a Shimadzu SPD-10A VP (UV-vis) and three AM gel columns (a guard column, two 500 Å, 10 µm columns). THF was used as solvent at the oven temperature of 23 °C. Detection was done by UV absorbance at 254 nm. MALDI-TOF mass spectra were performed on a PerSeptive Biosystem-Voyager-DE (Framingham, MA) mass spectrometer equipped with nitrogen laser (337 nm) and operating in linear mode. Internal calibration was performed using Angiotensin II and Bombesin as standards. The analytical samples were obtained by mixing the THF solution of the sample (5-10 mg/mL) with the THF solution of the matrix (2,5-dihydroxybenzoic acid, 10 mg/mL) in a 1/5 (v/v) ratio. The prepared solution f sample and matrix (0.5  $\mu$ L) was loaded on the MALDI plate and allowed to dry at 23 °C before the plate was inserted into the vacuum chamber of the MALDI instrument. The

#### **Biomacromolecules**

laser steps and voltages applied were adjusted depending on both the molecular weight and the nature of each analyzed compound.

**Preparation of Monodisperse Dendrimersomes by Injection.** A stock solution was prepared by dissolving the required amount of amphiphilic JD in THF. DSs were then generated by injection of 50  $\mu$ L of the stock THF solution of JD into 1.00 mL Milli-Q water or PBS, followed by 5 s vortexing. Eppendorf Research Plus Single Channel Pipette (10  $\mu$ L–100  $\mu$ L) and VWR Signature Ergonomic High Performance Single-Channel Variable Volume Pipettor (100  $\mu$ L–1000  $\mu$ L) were used for injection into Milli-Q water or PBS.

**Preparation of Polydisperse Giant Dendrimersomes by Hydration.** A 200  $\mu$ L (0.2 mL) solution of JD (10 mg·mL<sup>-1</sup>) in THF was deposited on the top surface of a roughened Teflon sheet (1 cm<sup>2</sup>), placed in a 20 mL flat-bottom vial, followed by evaporation of the solvent for 2 h. The Teflon sheet was dried *in vacuo* for an additional 12 h. Milli-Q water or PBS (2.0 mL) was added to submerge the film on the Teflon sheet, and the vial was placed in a 60 °C oven for 12 h for hydration. The sample vial containing the Teflon sheet was then mixed using a vortex mixer for 30 s. The final concentration of JD <del>of</del> in Milli-Q water is 1 mg·mL<sup>-1</sup>.

**Dynamic Light Scattering (DLS).** DLS for the monodisperse vesicles was performed in PBS and in Milli-Q water with a Malvern Instruments particle sizer (Zetasizer® Nano S, Malvern Instruments, UK) equipped with 4 mW He-Ne laser 633 nm and avalanche photodiode positioned at 175° to the beam and

temperature-controlled cuvette holder. Instrument parameters were determined automatically along with measurement times. Experiments were performed in triplicate.

**Cryogenic Transmission Electron Microscopy (cryo-TEM).** Cryo-TEM micrographs were taken on a Carl Zeiss Libra 120 Microscope (Oberkochen, Germany). Cryo-TEM samples were prepared by plunge freezing of aqueous dispersion on plasma-treated lacey grids. The vitrified specimens were transferred to a Gatan-910 cryo-holder. The images were recorded at a temperature of -170 °C with an acceleration voltage of 120 kV.

**Confocal Fluorescence Microscopy.** An imaging chamber (5–10 µl) containing DSs was formed between two coverslips ( $25 \times 25$  mm, Fisher Scientific) sealed with vacuum grease. DSs were imaged by confocal fluorescence microscopy (FluoView 300 scanning system configured on an IX81 inverted microscope platform) with a 60 × 1.2 NA water immersion lens (Olympus, Center Valley, PA). DSs containing **3,5-C12-RhB** were excited at a wavelength of  $\lambda = 543$  nm. **3,5-C12-RhB** is a JD with 3,5-bis(dodecyloxy)benzoate hydrophobic dendrons conjugated to Rhodamine B (RhB) that was previously reported to co-assemble with JD with red fluorescense.<sup>97</sup> Laser intensities were adjusted so that fluorescence signal was not oversaturated. Image processing and analysis were completed with ImageJ 1.50 software.

**Synthesis of Amphiphilic Janus Dendrimers.** Accelerated modular synthesis of a library of Janus dendrimers is shown in Scheme 1. Compounds 1–6 and **3,5-C12-RhB** were synthesized as previously reported.<sup>82,97</sup> These alkylation conditions will be later called conventional reaction conditions.



Synthesis of Methyl 3,5-bis(octyloxy)benzoate at Conventional Reaction Temperature and Time.<sup>30,32,82</sup> 1-Bromooctane (5.0 g, 26.2 mmol), 3,5-dihydroxybenzoate (2.0 g, 11.9 mmol, and K<sub>2</sub>CO<sub>3</sub> (8.2 g, 60 mmol) were added in a 250 mL round-bottom flask and dissolved in 50 mL of N,N-dimethylformamide (DMF). The reaction was allowed to stir at 80 °C under N<sub>2</sub> for 15 h. The mixture was cooled at room temperature and 100 mL of water were added. The aqueous layer was extracted with DCM for 4 times. The organic phase was dried with Na<sub>2</sub>SO<sub>4</sub> and the solvent was

ACS Paragon Plus Environment

removed. The product was purified by column chromatography on silica gel with a mobile phase (hexane: DCM = 3:1) to obtain the target ester 4.6 g, Yield: 98%.

# General Optimized Procedure for Alkylation at Higher Reaction Temperature and Shorter

**Reaction Time.** Alkyl bromide and methyl 3,5-dihydroxybenzoate or methyl 3,4,5-trihydroxybenzoate (~400 mg), and  $K_2CO_3$  were added in a 50 mL round-bottom flask. DMF 5 mL was also added. The reaction was allowed to stir at 600 rpm and 120 °C under N<sub>2</sub> for 3.5 to 6.5 h while monitored by conversion by TLC. The mixture was cooled at room temperature and 30 mL of water were added. The aqueous layer was extracted with DCM 4 times. The organic phase was dried with Na<sub>2</sub>SO<sub>4</sub> and the solvent was removed. The product was purified by column chromatography on silica gel with hexane/ethyl acetate as mobile phase to obtain the target ester.

**Methyl 3,5-bis(hexyloxy)benzoate.** Reagents: 1-bromohexane (825 mg, 5.0 mmol), methyl 3,5-dihydroxybenzoate (400 mg, 2.4 mmol),  $K_2CO_3$  (2.0 g, 14.4 mmol) for 4 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 600 mg, Yield: 74%.

**Methyl 3,5-bis(heptyloxy)benzoate.** Reagents: 1-bromoheptane (752 mg, 4.2 mmol), methyl 3,5-dihydroxybenzoate (336 mg, 2.0 mmol),  $K_2CO_3$  (1.6 g, 12 mmol) for 3.5 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 576 mg, Yield: 80%.

#### Biomacromolecules

**Methyl 3,5-bis(nonyloxy)benzoate.** Reagents: 1-bromononane (1.0 g, 5 mmol), methyl 3,5-dihydroxybenzoate (400 mg, 2.4 mmol),  $K_2CO_3$  (2.0 g, 14.4 mmol) for 3.5 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 760 mg, Yield: 75%.

Methyl 3,5-bis(decyloxy)benzoate. Reagents: 1-bromodecane (930 mg, 4.2 mmol), methyl 3,5-dihydroxybenzoate (336 mg, 2.0 mmol),  $K_2CO_3$  (1.66 g, 12 mmol) for 3 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 710 mg, Yield: 80%.

**Methyl 3,5-bis(undecyloxy)benzoate.** Reagents: 1-bromoundecane (920 mg, 3.9 mmol), methyl 3,5-dihydroxybenzoate (312 mg, 1.85 mmol),  $K_2CO_3$  (1.54 g, 11.1 mmol) for 4.5 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 819 mg, Yield: 93%.

**Methyl 3,5-bis(dodecyloxy)benzoate.** Reagents: 1-bromododecane (933 mg, 3.8 mmol), methyl 3,5-dihydroxybenzoate (300 mg, 1.8 mmol),  $K_2CO_3$  (1.54 g, 10.6 mmol) for 4.5 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 820 mg, Yield: 91%.

**Methyl 3,5-bis(2-ethylhexyloxy)benzoate.** Reagents: 2-ethylhexyl bromide (811 mg, 4.2 mmol), methyl 3,5-dihydroxybenzoate (336 mg, 2.0 mmol),  $K_2CO_3$  (1.66 g, 12 mmol) for 4.5 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 410 mg, Yield: 50%.

Methyl 3,5-bis(3*S*,7-dimethyloctyloxy)benzoate. Reagents: 1-bromo-3*S*,7-dimethyloctane (840 mg, 3.8 mmol),<sup>68</sup> methyl 3,5-dihydroxybenzoate (300 mg, 1.8 mmol),  $K_2CO_3$  (1.66 g, 12 mmol) for 4.5 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 690 mg, Yield: 85%.

Methyl 3,5-bis(3,7-dimethyloctyloxy)benzoate. Reagents: 1-bromo-3,7-dimethyloctane (racemic) (840 mg, 3.8 mmol),<sup>68</sup> methyl 3,5-dihydroxybenzoate (300 mg, 1.8 mmol), K<sub>2</sub>CO<sub>3</sub> (1.66 g, 12 mmol) for 4.5 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 600 mg, Yield: 74%.

Methyl 3,4,5-tris(octyloxy)benzoate. Reagents: 1-bromooctane (1.0 g, 5.2 mmol), methyl 3,4,5-trihydroxybenzoate (300 mg, 1.6 mmol),  $K_2CO_3$  (1.8 g, 13.2 mmol) for 6.5 h. Eluent for silica column: hexane:ethyl acetate = 30:1. Product: 510 mg, Yield: 61%.

Methyl 3,4,5-tris(2-ethylhexyloxy)benzoate. Reagents: 2-ethylhexyl bromide (1.4 g, 7.2 mmol), methyl 3,4,5-trihydroxybenzoate (400 mg, 2.2 mmol),  $K_2CO_3$  (1.8 g, 13.2 mmol) for 6.5 h. Eluent for silica column: hexane:ethyl acetate = 40:1. Product: 510 mg, Yield: 45%.

Methyl 3,4,5-tris(3,7-dimethyloctyloxy)benzoate. Reagents: 1-bromo-3,7-dimethyloctane (racemic) (1.6 g, 7.2 mmol), methyl 3,4,5-trihydroxybenzoate (400 mg, 2.2 mmol), K<sub>2</sub>CO<sub>3</sub> (1.8 g, 13.2 mmol) for 6.5 h. Eluent for silica column: hexane:ethyl acetate = 60:1. Product: 640 mg, Yield: 48%.

General Procedure for the Hydrolysis of Esters. The ester and KOH were added in a 50 mL round-bottom flask together with 10 mL ethanol. The reaction was allowed to stir at 100 °C for 2 h. The mixture was evaporated under vacuum. 30 mL of Water (30 mL) was added, and the remaining mixture was cooled at 0 °C. Hydrochloride acid (2M) was added dropwise until pH < 2. The aqueous layer was extracted with DCM for 4 times. The organic phase was dried with Na<sub>2</sub>SO<sub>4</sub> and the solvent was

#### Biomacromolecules

removed to obtain the target 3,5-bis(alkyloxy)benzoic acid or 3,4,5-tris(alkyloxy)benzoic acid without further purification in quantitative yield.

General Procedure for Esterification for Janus Dendrimers (JDs). Compound 6. 3,5-bis(alkyloxy)benzoic acid or 3,4,5-tris(alkyloxy)benzoic acid, and 4-(dimethylamino)pyridinium 4-toluenesulfonate (DPTS)<sup>100</sup> dissolved (10)were mixed and in DCM mL). N,N-Dicyclohexylcarbodiimide (DCC) was added to the reaction mixture. The mixture was then allowed to stir at 23 °C for 12 h. The precipitate was then filtered, and the filtrate was concentrated to dryness. The crude product was further purified by column chromatography on silica gel with a mobile phase of (DCM/methanol) to to yield he target JD as a colorless oily liquid.

**3,5-C6.** Reagents: Compound **6** (200 mg, 0.15 mmol), 3,5-bis(hexyloxy)benzoic acid (103 mg, 0.32 mmol), DPTS (88 mg, 0.30 mmol), DCC (124 mg, 0.60 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 260 mg, Yield: 89%.

**3,5-C7.** Reagents: Compound **6** (290 mg, 0.20 mmol), 3,5-bis(heptyloxy)benzoic acid (308 mg, 0.80 mmol), DPTS (260 mg, 0.80 mmol), DCC (272 mg, 1.3 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 410 mg, Yield: 94%.

**3,5-C8.** Reagents: Compound **6** (200 mg, 0.15 mmol), 3,5-bis(otcyloxy)benzoic acid (144 mg, 0.38 mmol), DPTS (112 mg, 0.38 mol), DCC (124 mg, 0.60 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: mg, Yield: 83%.

**3,5-C9.** Reagents: Compound **6** (200 mg, 0.15 mmol), 3,5-bis(nonyloxy)benzoic acid (146 mg, 0.36 mmol), DPTS (132 mg, 0.45 mmol), DCC (155 mg, 0.75 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 278 mg, Yield: 89%.

**3,5-C10.** Reagents: Compound **6** (220 mg, 0.17 mmol), 3,5-bis(decyloxy)benzoic acid (304 mg, 0.70 mmol), DPTS (206 mg, 0.70 mmol), DCC (210 mg, 1.0 mmol). Eluent for silica column: DCM:methanol = 40:1. Product: 322 mg, Yield: 88%.

**3,5-C11.** Reagents: Compound **6** (225 mg, 0.17 mmol), 3,5-bis(undecyloxy)benzoic acid (199 mg, 0.43 mmol), DPTS (151 mg, 0.51 mmol), DCC (177 mg, 0.86 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 347 mg, Yield: 92 %.

**3,5-C12.** Reagents: Compound **6** (370 mg, 0.28 mmol), 3,5-bis(hexyloxy)benzoic acid (274 mg, 0.56 mmol), DPTS (164 mg, 0.56 mmol), DCC (206 mg, 1.0 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 530 mg, Yield: 84%.

3,5-EH. Reagents: Compound 6 (171 mg, 0.13 mmol), 3,5-bis(2-ethylhexyloxy)benzoic acid (200 mg, 0.53 mmol), DPTS (156 mg, 0.53 mmol), DCC (161 mg, 0.78 mmol). Eluent for silica column: DCM:methanol = 40:1. Product: 172 mg, Yield: 85%.

#### **Biomacromolecules**

**3,5-dm(S).** Reagents: Compound **6** (200 mg, 0.20 mmol), 3,5-bis(3S,7-dimethyloctyloxy)benzoic acid (261 mg, 0.6 mmol), DPTS (117 mg, 0,6 mmol), DCC (186 mg, 0,9 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 310 mg, Yield: 96%.

3,5-dm(rac). Reagents: Compound 6 (200 mg, 0.20 mmol), 3,5-bis(3,7-dimethyloctyloxy)benzoic acid
(261 mg, 0.6 mmol), DPTS (117 mg, 0,6 mmol), DCC (186 mg, 0,9 mmol). Eluent for silica column:
DCM:methanol = 20:1. Product: 305 mg, Yield: 95%.

**3,4,5-C8.** Reagents: Compound **6** (100 mg, 0.08 mmol), 3,5-bis(otcyloxy)benzoic acid (131 mg, 0.26 mmol), DPTS (68 mg, 0.23 mmol), DCC (78 mg, 0.38 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 162 mg, Yield: 93%.

**3,4,5-EH.** Reagents: Compound **6** (200 mg, 0.15 mmol), 3,4,5-tris(2-ethylhexyloxy)benzoic acid (193 mg, 0,83 mmol), DPTS (132 mg, 0.45 mmol), DCC (155 mg, 0.75 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 326 mg, Yield: 95%.

**3,4,5-dm(rac).** Reagents: Compound **6** (200 mg, 0.15 mmol), 3,4,5-tris(3,7-dimethyloctyloxy)benzoic acid (225 mg, 0.38 mmol), DPTS (132 mg, 0.45 mmol), DCC (155 mg, 0.75 mmol). Eluent for silica column: DCM:methanol = 20:1. Product: 365 mg, Yield: 93 %.

## Purity by HPLC, <sup>1</sup>H NMR, <sup>13</sup>C NMR, and MALDI-TOF for Previously Unreported Compounds

**3,5-C7.** Purity (HPLC): 99%+. <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>)  $\delta$  = 7.24 (s, 4 H), 7.09 (d, *J* = 2.3 Hz, 4 H), 6.61 (t, *J* = 2.3 Hz, 2 H), 4.61 (s, 4 H), 4.58 (s, 4 H), 4.22 (m, 4 H), 4.16 (m, 8 H), 3.93 (t, *J* = 6.5 Hz, 8 H), 3.86 (m, 8 H), 3.79 (m, 4H), 3.71 (m, 12 H), 3.64 (m, 24 H), 3.53 (m, 12 H), 3.36 (s, 6 H), 3.35 (s, 12 H), 1.76 (m, 8 H), 1.44 (m, 8 H), 1.38-1.25 (m, 24 H), 0.88 (t, *J* = 6.9 Hz, 12 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>)  $\delta$  = 165.9, 165.5, 160.3, 152.5, 143.1, 131.1, 124.3, 109.1, 107.8, 106.7, 72.6, 72.0, 70.9, 70.8, 70.6, 69.7, 69.0, 68.4, 63.1, 63.0, 59.1, 43.4, 31.9, 29.3, 29.2, 26.1, 22.7, 14.2. MALDI-TOF (m/z): [M+Na]<sup>+</sup> calcd for C<sub>103</sub>H<sub>168</sub>O<sub>36</sub>Na, 2004; found, 2006.

3,5-C9. Purity (HPLC): 99%+. <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>) δ = 7.24 (s, 4 H), 7.09 (d, J = 2.3 Hz, 4 H),
6.61 (t, J = 2.3 Hz, 2 H), 4.61 (s, 4 H), 4.58 (s, 4 H), 4.22 (m, 4 H), 4.17 (m, 8 H), 3.93 (t, J = 6.5 Hz, 8 H), 3.86 (m, 8 H), 3.79 (m, 4H), 3.72 (m, 12 H), 3.64 (m, 24 H), 3.53 (m, 12 H); 3.36 (s, 6 H), 3.35 (s, 12 H), 1.76 (m, 8 H), 1.44 (m, 8 H), 1.36–1.26 (m, 40 H), 0.88 (t, J = 6.9 Hz, 12 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>) δ = 165.8, 165.4, 160.2, 152.4, 143.0, 131.0, 124.1, 109.0, 107.7, 106.6, 77.4, 77.2, 76.9, 72.4, 71.9, 70.8, 70.6, 70.5, 70.5, 69.6, 68.9, 68.3, 63.1, 62.9, 58.9, 43.3, 31.8, 29.5, 29.4, 29.2, 29.2, 26.0, 22.6, 14.1. MALDI-TOF (m/z): [M+Na]<sup>+</sup> calcd for C<sub>111</sub>H<sub>184</sub>O<sub>36</sub>Na, 2116; found, 2116.

3,5-C10. Purity (HPLC): 98%+. <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>) δ = 7.24 (s, 4 H); 7.08 (d, J = 2.3 Hz, 4 H);
6.61 (t, J = 2.3 Hz, 2 H); 4.61 (s, 4 H); 4.58 (s, 4 H); 4.21 (m, 4 H), 4.16 (m, 8 H), 3.92 (t, J = 6.5 Hz, 8 H), 3.85 (m, 8 H), 3.79 (m, 4H), 3.72 (m, 12 H), 3.63 (m, 24 H), 3.53 (m, 12 H); 3.36 (s, 6 H), 3.35 (s, 6 H), 3.53 (s, 6 H), 3.53 (s, 6 H), 3.53 (s, 6 H), 3.55 (s

12 H), 1.76 (m, 8 H), 1.44 (m, 8 H), 1.35–1.27 (m, 48 H), 0.88 (t, J = 6.9 Hz, 12 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>)  $\delta = 165.7$ , 165.3, 160.2, 152.3, 142.9, 130.9, 124.1, 109.0, 107.6, 106.5, 72.4, 71.8, 70.2, 70.6, 70.5, 70.4, 69.5, 68.9, 68.2, 63.0, 62.8, 58.9, 43.3, 31.8, 29.5, 29.3, 29.2, 29.1, 26.0, 22.6, 14.0. MALDI-TOF (m/z): [M+Na]<sup>+</sup> calcd for C<sub>115</sub>H<sub>192</sub>O<sub>36</sub>Na, 2172; found, 2172.

**3,5-C11.** Purity (HPLC): 99%+. H NMR (500 MHz, CDCl<sub>3</sub>)  $\delta$  = 7.24 (s, 4 H); 7.08 (d, *J* = 2.3 Hz, 4 H); 6.61 (t, *J* = 2.3 Hz, 2 H); 4.61 (s, 4 H); 4.58 (s, 4 H); 4.22 (t, *J* = 4.5 Hz, 4 H), 4.16 (t, *J* = 4.5 Hz, 8 H), 3.92 (t, *J* = 6.5 Hz, 8 H), 3.85 (m, 8 H), 3.79 (m, 4H), 3.72 (m, 12 H), 3.65 (m, 24 H), 3.52 (m, 12 H); 3.36 (s, 6 H), 3.35 (s, 12 H), 1.76 (m, 8 H), 1.42 (m, 8 H), 1.25 (m, 48 H), 0.87 (t, *J* = 6.9 Hz, 12 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>)  $\delta$  = 166.0, 165.6, 160.4, 152.6, 143.2, 131.2, 124.3, 109.2, 107.9, 106.8, 72.6, 72.1, 71.0, 70.9, 70.7, 70.7, 69.8, 69.1, 68.5, 63.2, 63.2, 59.2, 43.5, 32.1, 29.8, 29.8, 29.6, 29.5, 29.4, 26.2, 22.9, 14.3. MALDI-TOF (m/z): [M+K]<sup>+</sup> calcd for C<sub>119</sub>H<sub>200</sub>O<sub>36</sub>K, 2244; found, 2245.

3,5-EH. Purity (HPLC): 99%+. <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>) δ = 7.25 (s, 4 H); 7.11 (d, J = 2.3 Hz, 4 H);
6.63 (t, J = 2.3 Hz, 2 H); 4.61 (s, 4 H); 4.59 (s, 4 H); 4.22 (m, 4 H), 4.17 (m, 8 H), 3.87–3.82 (m, 16 H),
3.79 (m, 4H), 3.72 (m, 12 H), 3.63 (m, 24 H), 3.53 (m, 12 H); 3.36 (s, 6 H), 3.35 (s, 12 H), 1.69 (m, 12 H), 1.54–1.30 (m, 24 H), 0.94–0.88 (m, 24 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>) δ = 165.9, 165.5, 160.5,
152.4, 143.0, 131.0, 124.2, 109.1, 107.8, 106.7, 72.5, 72.0, 70.8, 70.7, 70.6, 70.6, 69.7, 69.0, 62.9, 62.8,

59.0, 43.4, 39.4, 30.5, 29.1, 23.8, 23.1, 14.1, 11.2. MALDI-TOF (m/z): [M+Na]<sup>+</sup> calcd for C<sub>107</sub>H<sub>176</sub>O<sub>36</sub>Na, 2160; found, 2162.

**3,5-dm(S).** Purity (HPLC): 99%+. H NMR (500 MHz, CDCl<sub>3</sub>)  $\delta$  = 7.24 (s, 4 H); 7.10 (d, *J* = 2.3 Hz, 4 H); 6.62 (t, *J* = 2.2 Hz, 2 H); 4.61 (s, 4 H); 4.59 (s, 4 H); 4.21 (m, 4 H), 4.17 (m, 8 H), 3.97 (m, 8 H), 3.86 (m, 8 H), 3.79 (m, 4H), 3.72 (m, 12 H), 3.64 (m, 24 H), 3.53 (m, 12 H); 3.36 (s, 6 H), 3.35 (s, 12 H), 1.85–1.62 (m, 12 H), 1.60–1.48 (m, 8 H), 1.36–1.12 (m, 20 H), 0.93 (d, *J* = 6.6 Hz, 12 H), 0.86 (d, *J* = 6.6 Hz, 24 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>)  $\delta$  = 165.9, 165.5, 160.3, 152.4, 143.0, 131.1, 124.2, 109.1, 107.8, 106.6, 72.5, 72.0, 70.8, 70.7, 70.6, 69.7, 69.0, 66.7, 62.8, 59.0, 43.4, 39.3, 37.3, 36.1, 29.8, 28.0, 24.7, 22.7, 22.6, 19.6. MALDI-TOF (m/z): [M+Na]<sup>+</sup> calcd for C<sub>115</sub>H<sub>192</sub>O<sub>36</sub>Na, 2172; found, 2172.

**3,5-dm(rac).** Purity (HPLC): 99%+. <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>)  $\delta$  = 7.25 (s, 4 H); 7.10 (d, *J* = 2.3 Hz, 4 H); 6.62 (t, *J* = 2.3 Hz, 2 H); 4.61 (s, 4 H); 4.59 (s, 4 H); 4.21 (m, 4 H), 4.17 (m, 8 H), 3.97 (m, 8 H), 3.86 (m, 8 H), 3.79 (m, 4H), 3.72 (m, 12 H), 3.66–3.62 (m, 24 H), 3.52 (m, 12 H); 3.36 (s, 6 H), 3.35 (s, 12 H), 1.85–1.64 (m, 12 H), 1.60–1.48 (m, 8 H), 1.36–1.11 (m, 20 H), 0.93 (d, J=6.6 Hz, 12 H), 0.86 (d, J=6.6 Hz, 24 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>)  $\delta$  = 165.9, 165.5, 160.3, 152.5, 143.1, 131.1, 124.3, 109.2, 107.9, 106.7, 72.6, 72.0, 70.9, 70.8, 70.6, 69.7, 69.0, 66.8, 63.0, 59.1, 43.4, 39.3, 37.4, 36.2, 29.9, 28.0, 24.7, 22.8, 22.7, 19.7. MALDI-TOF (m/z): [M+Na]<sup>+</sup> calcd for C<sub>115</sub>H<sub>192</sub>O<sub>36</sub>Na, 2172; found, 2172.

**3,4,5-EH.** Purity (HPLC): 99%+. <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>) *δ* = 7.25 (s, 4 H); 7.20 (s, 4 H); 4.59 (s, 4 H); 4.57 (s, 4 H); 4.22 (m, 4 H), 4.17 (m, 8 H), 3.97 (m, 12 H), 3.86 (m, 8 H), 3.79 (m, 4 H), 3.72 (m, 12 H), 3.66–3.62 (m, 24 H); 3.54–3.51 (m, 12 H), 3.36 (s, 6 H), 3.35 (s, 12 H), 1.80 (m, 8 H), 1.73 (m, 4 H), 1.47 (m, 12 H), 1.28 (m, 48 H), 0.89–0.86 (m, 18 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>) *δ* = 165.9, 165.5, 153.2, 152.5, 143.2, 142.9, 124.3, 123.8, 109.2, 107.6, 76.1, 72.6, 72.0, 71.4, 70.9, 70.8, 70.6 69.7, 69.1, 62.7, 59.1, 43.6, 40.7, 39.7, 30.6, 30.5, 29.4, 29.2, 23.9, 23.7, 23.2, 23.2, 14.2, 14.2, 11.3. [M+Na]<sup>+</sup> calcd for C<sub>123</sub>H<sub>208</sub>O<sub>36</sub>Na, 2316; found, 2315.

**3,4,5-dm(rac).** Purity (HPLC): 99%+. <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>)  $\delta$  = 7.26 (s, 4 H); 7.23 (s, 4 H); 4.59 (s, 4 H); 4.58 (s, 4 H); 4.22 (m, 4 H), 4.17 (m, 8 H), 4.08–3.98 (m, 12 H), 3.86 (m, 8 H), 3.79 (m, 4 H), 3.72 (m, 12 H), 3.66–3.62 (m, 24 H); 3.54–3.51 (m, 12 H), 3.36 (s, 6 H), 3.35 (s, 12 H), 1.90–1.78 (m, 6 H), 1.70 (m, 6 H), 1.60–1.48 (m, 12 H), 1.37–1.23 (m, 18 H), 1.19–0.11 (m, 18 H), 0.95–0.91 (m, 18 H), 0.86 (m, 36 H). <sup>13</sup>C NMR (126 MHz, CDCl<sub>3</sub>)  $\delta$  = 165.8, 165.5, 153.0, 152.5, 143.2, 143.0, 124.3, 124.0, 109.2, 108.2, 72.6, 72.0, 71.9, 70.9, 70.8, 70.6, 69.7, 69.1, 67.6, 62.7, 62.6, 59.1, 43.6, 39.5, 39.4, 37.6, 37.6, 37.5, 37.5, 36.5, 29.9, 29.8, 28.1, 24.8, 24.8, 22.8, 22.7, 19.6, 19.6. [M+Na]<sup>+</sup> calcd for C<sub>135</sub>H<sub>232</sub>O<sub>36</sub>Na, 2484; found, 2484.

## **RESULTS and DISCUSSION**

Natural Polyphenols and Phenolic acids as Building Blocks for Programmed Synthetic Macromolecules. Natural phenols, resorcinol, pyrocatechols, pyrogallols, and phenolic acids including  $\alpha$ -resorcylic acid, protocatechuic acid, and gallic acid (Figure 5) are present in a variety of unrelated types of fruits, vegetables, cereals, legumes and their derivatives such as coffee, wine and chocolate.<sup>1–7</sup>



Figure 5. Natural plant phenols, polyphenols and constitutional isomeric AB<sub>2</sub> and AB<sub>3</sub> phenolic acids.

Polyphenols and phenolic acids are generated as secondary metabolites during photosynthesis and they are stored in plant and spice leaves. Their role in plant metabolism is still under investigation. It has been reported that phenolic acids act as signaling molecules, defense agents, preservatives and are responsible for the color and taste of fruits and vegetables. They have been intensively studied for their therapeutic effect on human health. Their main natural function utilizes the antioxidant and free radical scavenger activities of these molecules (Figure 6).<sup>1–7</sup>



Figure 6. Functions and applications of natural including plant phenolic acids.

#### Biomacromolecules

Even at low concentration they can prevent proteins and other macromolecules from undergoing oxidative damage by direct quenching of active oxygen species, inhibition of enzymes and chelation of metal ions. Thanks to their antioxidant activity, a diet rich in phenolic acids has beneficial effects on ageing and stress-induced disorders, but they are also used as natural additives and preservatives in the food industry. They find therapeutic use for the treatment of diseases where oxidative processes play an important role, such as heart diseases, arteriosclerosis, neurodegenerative diseases and some types of cancer. Lately, they have also been employed in the treatment of Diabetes Mellitus and microbial infections (Figure 7). Furthermore, the phosphoprotein mussel foot protein Mefp-5 found in mussels exhibited very strong adhesion to surfaces due to polyphenols. Dopamine building blocks which mimic Mefp-5 protein containing polyphenols are extensively employed to design mussel-inspired surface coating materials (Figure 7).<sup>101–104</sup>



**Figure 7.** Schematic illustration of Mefp-5 protein from mussels, and dopamine containing amine and catechol functional groups (broken red square) used to design mussel-inspired surface coatings.<sup>100</sup>

# Synthetic Phenolic Acids as Building Blocks for Programmed Synthetic Macromolecules. In addition

to the natural phenolic acids shown in Figure 5, four additional libraries of constitutional isomeric AB<sub>2</sub>

and AB<sub>3</sub>, AB<sub>4</sub>, and AB<sub>5</sub> phenolic acids were designed and investigated in our laboratory for the synthesis of *Programmed Synthetic Macromolecules*.<sup>25–27,29</sup> Their structures are shown in Figure 8.



**Figure 8.** Synthetic constitutional isomeric  $AB_2$ ,  $AB_3$ ,  $AB_4$ , and  $AB_5$  phenolic acids<sup>25–27,29</sup> designed and employed in the Percec laboratory for the synthesis of libraries of self-assembling dendrons and dendrimers.

**Synthesis of the Amphiphilic Janus Dendrimer Library.** The unique properties of DSs, the facile and versatile synthesis of amphiphilic JDs, and their self-assembly has been reported previously.<sup>82–86</sup> The formation of biomimetic vesicles from amphiphilic building blocks follows a complex mechanism that requires additional experiments. The modular design of many different libraries of molecular building blocks will contribute to the elucidation of their mechanism of self-assembly. Size, morphology and mechanical properties of the self-assembled DSs can be predicted based on the molecular structure of JDs.<sup>85</sup> During the formation of DSs in polar media, the substitution pattern in the first generation (G1) dendron in the hydrophobic part of JDs is determinant for the interactions between the medium and the hydrophilic part of the molecule and for the degree of interdigitation in-the hydrophobic bilayer of the

### Biomacromolecules

vesicles. In order to maximize stability and size of DSs it has been shown that the (3,4,5)-G1 substitution in the hydrophilic part containing triethylene glycol of JDs results in a better solvation of the new-formed vesicles, and the (3,5)-G1 pattern in the hydrophobic side allows more efficient interdigitation of the alkyl chains as well as tight packing, resulting in tougher membranes compared to the (3,4)-G1 and (3,4,5)-G1 patterns. A systematic synthesis of JDs with different lengths and degree of branching of the alkyl chains in the hydrophobic dendron and screening of the effects on size and stability of DSs have not been performed yet. With this in mind, a new library of 13 amphiphilic JDs has been prepared by an accelerated iterative modular synthetic approach.





\*Conventional reaction temperature (80 °C) and time (15 hours).

Scheme 3. Synthesis of 3,4,5-Substituted Phenolic Acids



The convergent synthesis of the JDs has been performed by diversifying the structure the alkyl chains of the (3,5)- and (3,4,5)-substituted hydrophobic dendrons from phenolic esters, as shown in Schemes 2 and 3. The alkylation of methyl 3,4,5-trihydroxybenzoate and methyl 3,5-bihydroxybenzoate was performed with 10 different alkyl bromides. The conventional conditions for the alkylation (Scheme 2, asterisk) is 80 °C and 15 hours, which was adopted from the synthesis of libraries of dendrons, dendrimers, and Janus dendrimers with the phenolic acid building blocks.<sup>9,82</sup> The alkylation reaction has been optimized according to a previous study.<sup>105</sup> The most influential parameters affecting yield and

Page 29 of 55

#### Biomacromolecules

reaction time for the alkylation of 3,4,5-trihydroxybenzoate were found to be temperature, equivalents of the base and stirring rate. Based on this evaluation, an improved synthetic design has been obtained by ielevating the reaction temperature from 80 °C to 120 °C, increasing the concentration of reagents by 50% and the amount of base by 20%. By using these optimized conditions, smaller amounts of alkyl bromides could be used, but more importantly a reduction of about 70% of the reaction time was obtained. The yield of the newly optimized alkylation reactions ranged between 50 and 90%. The subsequent hydrolysis of the alkyl-substituted benzoates gave the alkyl-substituted phenolic acids that were coupled to the (3,4,5)-substituted hydrophilic dendron (compound 6) as shown in Scheme 1. The length of the linear alkyl chains was varied from 6 to 12 carbons. Three branched molecules were

also employed, two of which being pure enantiomers and one a racemic mixture. As discussed previously, interdigitation of the alkyl chains is fundamental for the formation of robust membranes and it is intuitive to think that the longer the chain the more stable the hydrophobic bilayer. The modulation of chain length was carried out to test the minimum number of carbons required to form stable vesicles. Furthermore, the introduction of branching points on the alkyl chains helps in understanding what happens when we introduce a degree of disruption in the packing. Biological membranes are made of phospholipids that are packed with each other by their hydrophobic chains. The presence of unsaturated bonds, stereocenters and branching does not destabilize the membranes but are utilized in stabilization and modulation of the crystallization of the membrane for adaptation to lower temperature environments,

resulting in the diversity of structures we find in Nature.<sup>105</sup> The creation of this library of JDs is an attempt to mimic the diversity of biological membranes and to elucidate structure-property requirements needed to approach the diversity of Natural membranes in JDs.

Self-assembly of Janus Dendrimers by Injection and Screening of Dendrimersomes Size and Size **Distribution vs Janus Dendrimer Concentration.** The preparation of DSs by injection is by far the easiest technique to obtain stable monodisperse nanoscale vesicles.<sup>82,83</sup> The interplay between solvation of the hydrophilic part of the JDs and the hydrophobic interactions of the alkyl chains with each other results in the formation of supramolecular assemblies whose properties depend on the molecular structure of JDs. There is an inverse proportionality between the thickness of the membrane (i.e. the interdigitation degree of the hydrophobic part of the JDs) and the size and stability of the DSs.<sup>85</sup> The newly synthesized library of JDs was used to prepare vesicles by injection at increasing concentrations, from 0.05 mM until the stability of the DSs was compromised resulting in bimodal molecular size distribution. This bimolecular size distribution sets the maximum concentration that allows preparation of monodisperse DSs by injection. The formation of bimodal distributions in the DLS measurements of DSs at high concentrations is an indication of the instability of vesicles, and the result is the formation of polydisperse vesicles or large aggregates. Size and polydispersity index (PDI) of the DSs in water and buffer was monitored by DLS measurements. The effect of alkyl chain length and branching on the size and stability of DSs is shown in Figures 9 and 10 and Tables 1 and 2. The increase in length of linear alkyl chains has the effect of stabilizing the DS membrane, enabling the formation of larger vesicles at

Page 31 of 55

#### Biomacromolecules

high concentrations. The self-assembly of 3,5-C6 and 3,5-C7 result in the formation of small objects that are most likely micelles rather than lamellar vesicles, suggesting that the length of the C6 and C7 chains are not enough for the stabilization of a membrane structure. There is a substantial difference in the self-assembly of **3.5-C8** and JDs having longer alkyl chains (C8 to C12). The complete screening of DS size made from JDs with linear alkyl chains is reported in Table 1. The minimum chain length required to form vesicles at increasing JD concentration is C8. However, C8 generates relatively flexible and unstable vesicles. The DSs prepared from **3.5-C8**, **3.5-C9**, and **3.5-C10** have similar size trends and critical concentrations toward formation of polydisperse vesicles. The introduction of one more alkyl substituent in **3,4,5-C8** is not compromising the formation of DSs even at high concentrations. However, the interdigitation of the alkyl chains becomes less efficient as evidenced by the smaller size of the vesicles compared to the DSs made from the 3,5-substituted JDs. The series of DSs made from JDs with branched alkyl chains show a different size and stability trend (Table 2). The introduction of one branching point in **3,5-EH** has the effect of increasing the stabilization of the vesicles compared to linear **3,5-C6** and **3,5-C8** (Table 1). The substantial difference observed between **3,5-C6** and **3,5-EH** may arise as a result of the increased interdigitation ability and stability of the 2-ethylhexyl compared to the hexyl chain in the hydrophobic bilayer of the vesicles. The size and stability increase observed in **3,5-EH** is diminished when longer branched chains are used, as in **3,5-dm(S)** and **3,5-dm(rac)**. The introduction of three branched alkyl chains in 3,4,5-EH is importantly impairing the stability of vesicles at increasing JDs concentrations, due to the loss in interdigitation efficiency of the alkyl chains (Figure 9





Figure 9. Representative concentration-dependent dynamic light scattering data.





### Biomacromolecules

Figure 10. Contour color plots of the effect of JD concentrations and the size with the function of the chain lengths.

Table 1. Dimensions of Self-Assembled Particles from Janus Dendrimers with Linear Alkyl Chains

	3,5-C6		3,5-C6 3,5-C7 3,5-C8		3,5-C9		3,5-C10		3,5-C11		3,5-C12		3,4,5-C8			
Conc.	Size	PDI	Size	PDI	Size	PDI	Size	PDI	Size	PDI	Size	PDI	Size	PDI	Size	PDI
(mM)	(nm)		(nm)		(nm)		(nm)		(nm)		(nm)		(nm)		(nm)	
0.05	22	0.20	46	0.32	87	0.09	136	0.08	125	0.17	113	0.11	135	0.14	124	0.07
0.1	26	0.17	47	0.24	134	0.13	151	0.09	173	0.06	144	0.10	168	0.15	141	0.08
0.2	Bim	odal	Bim	odal	215	0.12	189	0.14	188	0.24	183	0.12	215	0.18	187	0.1
0.3		Non-v	esicles		242	0.21	197	0.17	212	0.23	192	0.21	241	0.27	221	0.18
0.4					309	0.24	202	0.2	240	0.22	201	0.23	205	0.22	223	0.22
0.5					274	0.28	227	0.36	295	0.25	228	0.27	289	0.37	220	0.22
0.6					277	0.42	246	0.21	303	0.29	267	0.33	277	0.24	230	0.22
0.7					Bim	odal	Bim	odal	Bim	odal	Bime	odal	282	0.29	Bime	odal
													Bime	odal		

	3,5-ЕН		3,5-dm(8)		3,5-dm(rac)		3,4,5-EH		3,4,5-dm(rac)	
Concentration (mM)	Size (nm)	PDI	Size (nm)	PDI	Size (nm)	PDI	Size (nm)	PDI	Size (nm)	PDI
0.05	94	0.09	121	0.12	130	0.18	109	0.10	149	0.15
0.1	164	0.07	163	0.14	160	0.17	127	0.11	175	0.16
0.2	186	0.13	186	0.25	183	0.24	160	0.13	156	0.4
0.3	249	0.14	208	0.19	207	0.22	268	0.26	Bimod	al
0.4	250	0.15	191	0.23	190	0.19	Bimod	al		
0.5	280	0.19	236	0.25	242	0.29				
0.6	292	0.28	Bimod	al	240	0.28				
0.7	302	0.31			Bimod	al				
0.8	Bimoc	lal								

Table 2. Dimensions of Self-assembled Particles from Janus Dendrimers with Branched Alkyl Chains

**Visualization of Dendrimersome Morphology.** The visualization of DS morphology was performed by cryo-TEM on DSs prepared by injection and by film hydration. Representative visualizations of monodisperse DSs prepared by injection are shown in Figure 11. Multilayer onion-like vesicles are formed from **3,4,5-EH** while mostly unilamellar vesicles are formed from **3,5-C12**.



Figure 11. Representative cryo-TEM images of self-assembled structures by injection.



Figure 12. Representative cryo-TEM images of self-assembled structures by film hydration.

Film hydration is a slower procedure used to make giant DSs<sup>82,96–99</sup> which allows JDs to pre-assemble into two dimensionally organized bilayers on a dry Teflon surface before being hydrated with buffer solutions. It is used to prepare giant vesicles (a few microns), however are generally polydisperse, as shown in Figure 12. Most of the giant vesicles prepared and visualized by cryo-TEM show a monolayer structure, sometimes having an elongated or irregular shape. The bilayer thicknesses were also analyzed by cryo-TEM images<sup>82,87</sup> and summarized in Table 3. **3,5-C8** prepared by hydration resulted in vesicles that seem to have a thicker membrane (11.5 nm) or a non-perfect bilayer (Figure 12). This is due to their high flexibility and dynamic instability. An increasing thickness starts from the JDs with C9 to C12 linear chains. For more than C8 linear chains and branched chains forms stable vesicles, the bilayer structures with clear boundaries showed thicknesses between 3.5 nm to maximum 9.8 nm (Table 3).

	Average bilayer	Standard
	thickness (nm)	deviation (nm)
3,5-C6	N/A	
3,5-C7	N/A	
3,5-C8	11.5	2.1
3,5-C9	3.5	0.4
3,5-C10	5.6	0.7
3,5-C12	5.8	1.0
3,4,5-C8	5.5	0.2
3,5-EH	7.7	1.3
3,5-dm(S)	9.8	0.5
3,5-dm(rac)	7.7	0.2
3,4,5 EH	4.9	0.3
3,4,5 (dm)-rac	6.0	0.5

 Table 3. Average Bilayer Thickness Calculated from Cryo-TEM Images

Giant DSs were prepared by film hydration from **3,5-C10** and 1% of rhodamine B-labeled JD **3,5-C12-RhB**<sup>97</sup> and visualized by confocal fluorescence microscopy (Figure 13). A large population of uniform giant unilamellar vesicles were observed, compared to the observation on **3,5-C12** in previous publications.<sup>98,99</sup> This encourages us to utilized **3,5-C10** for further investigations on confocal microscopy.

3,5-C10

3,5-C12-RhB

50 µm



**Figure 13.** Representative confocal images of self-assembled structures by co-assembly of **3,5-C10** with 1% of rhodamine B labeled JD **3,5-C12-RhB** by film hydration in PBS.

# CONCLUSIONS

Natural and synthetic polyphenols and phenolic acids are building blocks for self-assembling dendrons and dendrimers. The discovery of self-assembling dendrons and dendrimers and their assembly into very complex structures such as Frank-Kasper phases evolved in additionally similar supramolecular nanostructures from block copolymers,<sup>111</sup> surfactants,<sup>112–115</sup> and other systems.<sup>116–119</sup> Here, a library of 13 amphiphilic JDs derived from natural phenolic acids and functionalized with a variety of alkyl chains of different length and branching has been successfully synthesized by accelerated iterative methods. The alkylation of the phenolic acid derivatives methyl 3,4,5-trihydroxybenzoate and methyl

ACS Paragon Plus Environment

#### Biomacromolecules

3,5-dihydroxybenzoate has been optimized resulting in a decrease of about 70% of the reaction time without affecting negatively the yield. A systematic study on the size, structure, stability and polydispersity of the self-assembled DSs was conducted at different concentrations by injection and monitored by dynamic light scattering, crvo-TEM and confocal microscopy. The length of linear alkyl chains is fundamental for an efficient formation of vesicles. For JDs substituted with linear alkyl chains in the 3,5-positions on the phenolic acid part, there is a clear trend of increased size and stability of DSs above C8, with minor differences between 3.5-C9 up to 3.5-C12. C8 forms very flexible vesicle with dynamic bilayers. Amphiphilic Janus dendrimers based on C9 to C12 chains in the hydrophobic part of the JDs, assemble into stable DSs in water. Their stability is predicted by the interdigitation of their alkyl chains.<sup>85</sup> In contrast, C6 and C7 chains may not be long enough for the formation of stable vesicles based on DLS analysis and cryo-TEM measurements. These much smaller assemblies formed by 3,5-C6 and **3.5-C7** are probably micellar,<sup>82</sup> Therefore, **3.5-C8** self-assembled into thick dynamic membrane-like structures as intermediates between micelles (C6 and C7) and vesicles (more than C8). Branched alkyl chains including 2-ethylhexyl and 3,7-dimethyloctyl chains on both 3,5- and 3,4,5substituted phenolic acids presented stable self-assembled DSs comparable to those containing linear chains. DSs from chiral 3,5-dm(S) and racemic 3,5-dm(rac) exhibited similar size, but no onion-like assemblies were observed for **3.5-dm(S)** and the critical concentration of chiral **3.5-dm(S)** is lower than that of **3,5-dm(rac)** (Table 2). The self-assembled chiral/racemic DSs from **3,5-dm(S)** and **3,5-dm(rac)** will be investigated for the role of chirality in the assembly of biological and synthetic membranes.

Among these 13 JD molecules, **3,5-C6** and **3,5-C7** form micelles, **3,5-C9**, **3,5-C10**, and **3,5-dm(S)** form only unilamellar and stable DSs, while the other JDs showed mixtures of unilamellar and multilamellar onion-like DSs. Therefore, **3,5-C9**, **3,5-C10**, and **3,5-dm(S)** are recommended for experiments which require only unilamellar vesicles. With this new library of JDs and their self-assembled stable DSs, encapsulation, delivery, change in structure during encapsulation and release are currently under investigation and will be reported in a different publication. Therefore, these JDs are expected to be utilized as important tools for or nanomedicine<sup>120-135</sup> and synthetic cell biology.

**Supporting Information.** The Supporting Information is available free of charge on the ACS Publications website at DOI: 10.1021/acs.biomac.XXXXXXX. <sup>1</sup>H NMR, <sup>13</sup>C NMR, and MALDI-TOF spectra of newly synthesized Janus dendrimers, and the DLS traces.

## **AUTHOR INFORMATION**

**Corresponding Author.** \*percec@sas.upenn.edu

Notes. The authors declare no competing financial interest.

### ACKNOWLEDGEMENTS

This work was supported by National Science Foundation Grants DMR-1066116, DMR-1807127 (to V.P.), the P. Roy Vagelos Chair at the University of Pennsylvania (to V.P.), the Alexander von

Humboldt Foundation (to N.Y.K. and V.P.), National Science Foundation Grant DMR-1120901 (to M.L.K. and V.P.), the European Union's Horizon 2020 research and innovation programme under the Marie Skłodowska-Curie Grant Agreement 642687 (to I.B.), and financial support from Nankai University (to H.H.).

### REFERENCES

(1) Rice-Evans, C. A.; Miller, N. J.; Paganga, G. Structure-Antioxidant Activity Relationships of Flavonoids and Phenolic Acids. *Free Radic. Biol. Med.* **1996**, *20*, 933–956.

(2) Saibabu, V.; Fatima, Z.; Khan, L. A.; Hameed, S. Therapeutic Potential of Dietary Phenolic Acids. *Adv. Pharmacol. Sci.* **2015**, *2015*, 823539.

(3) Pandey, K. B.; Rizvi, S. I. Plant Polyphenols as Dietary Antioxidants in Human Health and Disease. *Oxid. Med. Cell Longev.* **2009**, *2*, 270–278.

(4) Natella, F.; Nardini, M.; Di Felice, M.; Scaccini, C. Benzoic and Cinnamic Acid Derivatives as Antioxidants: Structure-Activity Relation. *J. Agric. Food Chem.* **1999**, *47*, 1453–1459.

(5) Mattila, P.; Hellström, J.; Törrönen, R. Phenolic Acids in Berries, Fruits, and Beverages. *J. Agric. Food Chem.* **2006**, *54*, 7193–7199.

(6) Haminiuk, C. W. I.; Maciel, G. M.; Plata-Oviedo, M. S. V.; Peralta, R. M. Phenolic Compounds in Fruits – an Overview. *Int. J Food Sci. Technol.* **2012**, *47*, 2023–2044.

(7) Quideau, S.; Deffieux, D.; Douat-Casassus, C.; Pouységu, L. Plant Polyphenols: Chemical Properties, Biological Activities, and Synthesis. *Angew. Chem. Int. Ed.* **2011**, *50*, 586–621.

(8) Rudick, J. G.; Percec, V. Induced Helical Backbone Conformations of Self-Organizable Dendronized Polymers. *Acc. Chem. Res.* 2008, *41*, 1641–1652.

#### Biomacromolecules

1
2
3
4
5
6
7
, 0
0
9
10
11
12
13
14
15
16
17
18
10
20
∠∪ 21
21
22
23
24
25
26
27
28
20
29
20
31
32
33
34
35
36
37
38
39
40
40
41
42
43
44
45
46
47
48
49
50
51
57
5Z 52
53
54
55
56
57
58
59

60

(9) Rosen, B. M.; Wilson, C. J.; Wilson, D. A.; Peterca, M.; Imam, M. R.; Percec, V. Dendron-Mediated Self-Assembly, Disassembly, and Self-Organization of Complex Systems. *Chem. Rev.* **2009**, *109*, 6275–6540.

- (10) Roche, C.; Percec, V. Complex Adaptable Systems Based on Self-Assembling Dendrimers and Dendrons: Toward Dynamic Materials. *Israel J. Chem.* **2013**, *53*, 30–44.
- (11) Sun, H.-J.; Zhang, S.; Percec, V. From Structure to Function *via* Complex Supramolecular Dendrimer Systems. *Chem. Soc. Rev.* **2015**, *44*, 3900–3923.
  - (12) Percec, V. From Synthetic Macromolecules to Biological-Like Complex Systems. *Adv. Polym. Sci.* **2013**, *261*, 173–198.
  - (13) Cochran, W.; Crick, F. H.; Vand, V. The Structure of Synthetic Polypeptides. I. The Transform of Atoms on a Helix. *Acta. Crystallogr* .1952, *5*, 581–586.
  - (14) Watson, J. D.; Crick, F. H. C. Molecular Structure of Nucleic Acids: A Structure for Deoxyribose Nucleic Acid. *Nature* **1953**, *171*, 737–738.
  - (15) Klug, A. From Macromolecules to Biological Assemblies (Nobel Lecture). *Angew. Chem. Int. Ed. Engl.***1983**, *22*, 565–582.
  - (16) Peterca, M.; Percec, V.; Imam, M. R.; Leowanawat, P.; Morimitsu, K.; Heiney, P. A. Molecular Structure of Helical Supramolecular Dendrimers. *J. Am. Chem. Soc.* 2008, *130*, 14840–14852.
  - (17) Balagurusamy, V. S. K.; Ungar, G.; Percec, V.; Johansson, G. Rational Design of the First Spherical Supramolecular Dendrimers Self-Organized in a Novel Thermotropic Cubic Liquid-Crystalline Phase and the Determination of Their Shape by X-Ray Analysis. *J. Am. Chem. Soc.* 1997, *119*, 1539–1555.
  - (18) Hudson, S. D.; Jung, H.-T.; Percec, V.; Cho, W.-D.; Johansson, G.; Ungar, G.; Balagurusamy, V. S.
    K. Direct Visualization of Individual Cylindrical and Spherical Supramolecular Dendrimers. *Science* 1997, *278*, 449–452.

(19) Percec, V.; Cho, W.-D.; Mosier, P. E.; Ungar, G.; Yeardley, D. J. P. Structural Analysis of Cylindrical and Spherical Supramolecular Dendrimers Quantifies the Concept of Monodendron Shape Control by Generation Number. *J. Am. Chem. Soc.* **1998**, *120*, 11061–11070.

(20) Percec, V.; Cho, W.-D.; Möller, M.; Prokhorova, S. A.; Ungar, G.; Yeardley, D. J. P. Design and Structural Analysis of the First Spherical Monodendron Self-Organizable in a Cubic Lattice. *J. Am. Chem. Soc.* **2000**, *122*, 4249–4250.

(21) Percec, V.; Cho, W.-D.; Ungar, G. Increasing the Diameter of Cylindrical and Spherical Supramolecular Dendrimers by Decreasing the Solid Angle of Their Monodendrons *via* Periphery Functionalization. *J. Am. Chem. Soc.* **2000**, *122*, 10273–10281.

(22) Percec, V.; Cho, W.-D.; Ungar, G.; Yeardley, D. J. P. Synthesis and Structural Analysis of Two Constitutional Isomeric Libraries of AB<sub>2</sub>-Based Monodendrons and Supramolecular Dendrimers. *J. Am. Chem. Soc.* **2001**, *123*, 1302–1315.

(23) Percec, V.; Mitchell, C. M.; Cho, W.-D.; Uchida, S.; Glodde, M.; Ungar, G.; Zeng, X.; Liu, Y.; Balagurusamy, V. S. K.; Heiney, P. A. Designing Libraries of First Generation AB<sub>3</sub> and AB<sub>2</sub> Self-Assembling Dendrons *via* the Primary Structure Generated from Combinations of (AB)<sub>Y</sub>–AB<sub>3</sub> and (AB)<sub>Y</sub>–AB<sub>2</sub> Building Blocks. *J. Am. Chem. Soc.* 2004, *126*, 6078–6094.

(24) Percec, V.; Smidrkal, J.; Peterca, M.; Mitchell, C. M.; Nummelin, S.; Dulcey, A. E.; Sienkowska, M. J.; Heiney, P. A. Self-Assembly of Hybrid Dendrons with Complex Primary Structure Into Functional Helical Pores. *Chem. – Eur. J.* 2007, *13* 3989–4007.

(25) Percec, V.; Holerca, M. N.; Nummelin, S.; Morrison, J. J.; Glodde, M.; Smidrkal, J.; Peterca, M.;
Rosen, B. M.; Uchida, S.; Balagurusamy, V. S. K.; Sienkowska, M. J.; Heiney, P. A. Exploring and
Expanding the Structural Diversity of Self-Assembling Dendrons through Combinations of AB,
Constitutional Isomeric AB<sub>2</sub>, and AB<sub>3</sub> Biphenyl-4-Methyl Ether Building Blocks. *Chem. – Eur. J.* 2006, *12*, 6216–6241.

#### **Biomacromolecules**

(26) Percec, V.; Peterca, M.; Sienkowska, M. J.; Ilies, M. A.; Aqad, E.; Smidrkal, J.; Heiney, P. A. Synthesis and Retrostructural Analysis of Libraries of AB<sub>3</sub> and Constitutional Isomeric AB<sub>2</sub> Phenylpropyl Ether-Based Supramolecular Dendrimers. *J. Am. Chem. Soc.* **2006**, *128*, 3324–3334.

(27) Percec, V.; Won, B. C.; Peterca, M.; Heiney, P. A. Expanding the Structural Diversity of Self-Assembling Dendrons and Supramolecular Dendrimers *via* Complex Building Blocks. *J. Am. Chem. Soc.* **2007**, *129*, 11265–11278.

(28) Percec, V.; Holerca, M. N.; Uchida, S.; Cho, W.-D.; Ungar, G.; Lee, Y.; Yeardley, D. J. P. Exploring and Expanding the Three-Dimensional Structural Diversity of Supramolecular Dendrimers with the Aid of Libraries of Alkali Metals of Their AB<sub>3</sub> Minidendritic Carboxylates. *Chem. – Eur. J.* 2002, *8*, 1106–1117.

(29) Rosen, B. M.; Wilson, D. A.; Wilson, C. J.; Peterca, M.; Won, B. C.; Huang, C.; Lipski, L. R.; Zeng, X.; Ungar, G.; Heiney, P. A.; Percec, V. Predicting the Structure of Supramolecular Dendrimers *via* the Analysis of Libraries of AB<sub>3</sub> and Constitutional Isomeric AB<sub>2</sub> Biphenylpropyl Ether Self-Assembling Dendrons. *J. Am. Chem. Soc.* **2009**, *131*, 17500–17521.

(30) Percec, V.; Ahn, C.-H.; Bera, T. K.; Ungar, G.; Yeardley, D. J. P. Coassembly of a Hexagonal Columnar Liquid Crystalline Superlattice from Polymer(s) Coated with a Three-Cylindrical Bundle Supramolecular Dendrimer. *Chem. – Eur. J.* 1999, *5*, 1070–1083.

(31) Percec, V.; Bera, T. K.; Glodde, M.; Fu, Q.; Balagurusamy, V. S. K.; Heiney, P. A. Hierarchical Self-Assembly, Coassembly, and Self-Organization of Novel Liquid Crystalline Lattices and Superlattices from a Twin-Tapered Dendritic Benzamide and Its Four-Cylinder-Bundle Supramolecular Polymer. *Chem. – Eur. J.* **2003**, *9*, 921–935.

(32) Percec, V.; Ahn, C.-H.; Cho, W.-D.; Jamieson, A. M.; Kim, J.; Leman, T.; Schmidt, M.; Gerle, M.;
Möller, M.; Prokhorova, S. A.; Sheiko, S. S.; Cheng, S. Z. D.; Zhang, A.; Ungar, G.; Yeardley, D. J. P.
Visualizable Cylindrical Macromolecules with Controlled Stiffness from Backbones Containing
Libraries of Self-Assembling Dendritic Side Groups. *J. Am. Chem. Soc.* 1998, *120*, 8619–8631.

(33) Rosen, B. M.; Peterca, M.; Huang, C.; Zeng, X.; Ungar, G.; Percec, V. Deconstruction as a Strategy for the Design of Libraries of Self-Assembling Dendrons. *Angew. Chem. Int. Ed.* **2010**, *49*, 7002–7005.

(34) Dukeson, D. R.; Ungar, G.; Balagurusamy, V. S. K.; Percec, V.; Johansson, G. A.; Glodde, M. Application of Isomorphous Replacement in the Structure Determination of a Cubic Liquid Crystal Phase and Location of Counterions. *J. Am. Chem. Soc.* **2003**, *125*, 15974–15980.

(35) Ungar, G.; Liu, Y.; Zeng, X.; Percec, V.; Cho, W.-D. Giant Supramolecular Liquid Crystal Lattice. *Science* **2003**, 299, 1208–1211.

(36) Zeng, X.; Ungar, G.; Liu, Y.; Percec, V.; Dulcey, A. E.; Hobbs, J. K. Supramolecular Dendritic Liquid Quasicrystals. *Nature* **2004**, 428, 157–160.

(37) Peterca, M.; Percec, V. Recasting Metal Alloy Phases with Block Copolymers. *Science* **2010**, *330*, 333–334.

(38) Ungar, G.; Percec, V.; Zeng, X.; Leowanawat, P. Liquid Quasicrystals. *Israel J. Chem.* 2011, 51, 1206–1215.

(39) Percec, V.; Ahn, C.-H.; Barboiu, B. Self-Encapsulation, Acceleration and Control in the Radical Polymerization of Monodendritic Monomers *via* Self-Assembly. *J. Am. Chem. Soc.* **1997**, *119*, 12978–12979.

(40) Percec, V.; Ahn, C.-H.; Ungar, G.; Yeardley, D. J. P.; Möller, M.; Sheiko, S. S. Controlling Polymer Shape Through the Self-Assembly of Dendritic Side-Groups. *Nature* **1998**, *391*, 161–164.

(41) Percec, V.; Rudick, J. G.; Peterca, M.; Wagner, M.; Obata, M.; Mitchell, C. M.; Cho, W.-D.;
Balagurusamy, V. S. K.; Heiney, P. A. Thermoreversible Cis–Cisoidal to Cis–Transoidal Isomerization
of Helical Dendronized Polyphenylacetylenes. *J. Am. Chem. Soc.* 2005, *127*, 15257–15264.

(42) Jishkariani, D.; MacDermaid, C. M.; Timsina, Y. N.; Grama, S.; Gillani, S. S.; Divar, M.; Yadavalli,
S. S.; Moussodia, R.-O.; Leowanawat, P.; Camacho, A. M. B.; Walter, R.; Goulian, M.; Klein, M. L.;
Percec, V. Self-Interrupted Synthesis of Sterically Hindered Aliphatic Polyamide Dendrimers. *Proc. Natl. Acad. Sci. U.S.A.* 2017, *114*, E2275–E2284.

#### **Biomacromolecules**

(43). Percec, V.; Glodde, M.; Bera, T. K.; Miura, Y.; Shiyanovskaya, I.; Singer, K. D.; Balagurusamy, V. S. K.; Heiney, P. A.; Schnell, I.; Rapp, A.; Spiess, H.-W.; Hudson, S. D.; Duan, H. Self-organization of Supramolecular Helical Dendrimers into Complex Electronic Materials. *Nature* 2002, *419*, 384–387.

(44) Percec, V.; Glodde, M.; Peterca, M.; Rapp, A.; Schnell, I.; Spiess, H. W.; Bera, T. K.; Miura, Y.; Balagurusamy, V. S. K.; Aqad, E.; Heiney, P. A. Self-Assembly of Semifluorinated Dendrons Attached to Electron-Donor Groups Mediates Their  $\pi$ -Stacking *via* a Helical Pyramidal Column. *Chem–Eur. J.* **2006**, *12*, 6298–6314.

(45) Percec, V.; Aqad, E.; Peterca, M.; Imam, M. R.; Glodde, M.; Bera, T. K.; Miura, Y.; Balagurusamy,
V. S. K.; Ewbank, P. C.; Würthner, F.; Heiney, P. A. Self-Assembly of Semifluorinated Minidendrons
Attached to Electron-Acceptor Groups into Pyramidal Columns. *Chem–Eur. J.* 2007, *13*, 3330–3345.

(46). Percec, V.; Dulcey, A. E.; Balagurusamy, V. S. K.; Miura, Y.; Smidrkal, J.; Peterca, M.; Nummelin, S.; Edlund, U.; Hudson, S. D.; Heiney, P. A.; Duan, H.; Magonov, S. N.; Vinogradov, S. A. Self-assembly of Amphiphilic Dendritic Dpeptides into Helical Pores. *Nature* 2004, *430*, 764–768.

(47) Percec, V.; Dulcey, A. E.; Peterca, M.; Ilies, M.; Ladislaw, J.; Rosen, B. M.; Edlund, U.; Heiney, P.
A. The Internal Structure of Helical Pores Self-Assembled from Dendritic Dipeptides Is
Stereochemically Programmed and Allosterically Regulated. *Angew. Chem. Int. Ed.* 2005, *44*, 6516–6521.

(48) Percec, V.; Dulcey, A. E.; Peterca, M.; Ilies, M.; Sienkowska, M. J.; Heiney, P. A. Programming the Internal Structure and Stability of Helical Pores Self-Assembled from Dendritic Dipeptides *via* the Protective Groups of the Peptide. *J. Am. Chem. Soc.* **2005**, *127*, 17902–17909.

(49) Percec, V.; Dulcey, A. E.; Peterca, M.; Ilies, M.; Nummelin, S.; Sienkowska, M. J.; Heiney, P. A.
Principles of Self-Assembly of Helical Pores from Dendritic Dipeptides. *Proc. Natl. Acad. Sci. U.S.A.*2006, *103*, 2518–2523.

(50) Peterca, M.; Percec, V.; Dulcey, A. E.; Nummelin, S.; Korey, S.; Ilies, M.; Heiney, P. A. Self-Assembly, Structural, and Retrostructural Analysis of Dendritic Dipeptide Pores Undergoing Reversible Circular to Elliptical Shape Change. *J. Am. Chem. Soc.* **2006**, *128*, 6713–6720.

(51) Percec, V.; Dulcey, A. E.; Peterca, M.; Adelman, P.; Samant, R.; Balagurusamy, V. S. K.; Heiney,
P. A. Helical Pores Self-Assembled from Homochiral Dendritic Dipeptides Based on L-Tyr and
Nonpolar Alpha-Amino Acids. J. Am. Chem. Soc. 2007, 129, 5992–6002.

(52) Kaucher, M. S.; Peterca, M.; Dulcey, A. E.; Kim, A. J.; Vinogradov, S. A.; Hammer, D. A.; Heiney,

P. A.; Percec, V. Selective Transport of Water Mediated by Porous Dendritic Dipeptides. J. Am. Chem. Soc. 2007, 129, 11698–11699.

(53) Rosen, B. M.; Peterca, M.; Morimitsu, K.; Dulcey, A. E.; Leowanawat, P.; Resmerita, A.-M.; Imam,

M. R.; Percec, V. Programming the Supramolecular Helical Polymerization of Dendritic Dipeptides *via* the Stereochemical Information of the Dipeptide. *J. Am. Chem. Soc.* **2011**, *133*, 5135–5151.

(54) Rosen, B. M.; Roche, C.; Percec, V. Self-Assembly of Dendritic Dipeptides as a Model of Chiral Selection in Primitive Biological Systems. *Top. Curr. Chem.* **2013**, *333*, 213–253.

(55) Rudick, J. G.; Percec, V. Helical Chirality in Dendronized Polyarylacetylenes. *New J. Chem.* 2007, *31*, 1083–1096.

(56) Percec, V.; Rudick, J. G.; Peterca, M.; Heiney, P. A. Nanomechanical Function from Self-Organizable Dendronized Helical Polyphenylacetylenes. *J. Am. Chem. Soc.* **2008**, *130*, 7503–7508.

(57) Feringa, B. L.; Browne, W. R. Nanomechanics: Macromolecules Flex their Muscles. *Nat. Nanotechnol.* 2008, *3*, 383.

(58) Rudick, J. G.; Percec, V. Nanomechanical Function Made Possible by Suppressing Structural Transformations of Polyarylacetylenes. *Macromol. Chem. Phys.***2008**, *209*, 1759–1768.

(59) Andreopoulou, K. A.; Peterca, M.; Wilson, D. A.; Partridge, B. E.; Heiney, P. A.; Percec, V.
Demonstrating the 8<sub>1</sub>-Helicity and Nanomechanical Function of Self-Organizable Dendronized
Polymethacrylates and Polyacrylates. *Macromolecules* 2017, *50*, 5271–5284.

(60) Percec, V.; Peterca, M.; Dulcey, A. E.; Imam, M. R.; Hudson, S. D.; Nummelin, S.; Adelman, P.; Heiney, P. A. Hollow Spherical Supramolecular Dendrimers. *J. Am. Chem. Soc.* **2008**, *130*, 13079–13094.

#### Biomacromolecules

(61) Percec, V.; Imam, M. R.; Peterca, M.; Wilson, D. A.; Graf, R.; Spiess, H. W.; Balagurusamy, V. S.
K.; Heiney, P. A. Self-Assembly of Dendronized Triphenylenes into Helical Pyramidal Columns and Chiral Spheres. *J. Am. Chem. Soc.* 2009, *131*, 7662–7677.

(62) Percec, V.; Imam, M. R.; Peterca, M.; Wilson, D. A.; Heiney, P. A. Self-Assembly of Dendritic Crowns into Chiral Supramolecular Spheres. *J. Am. Chem. Soc.* **2009**, *131*, 1294–1304.

(63) Sahoo, D.; Peterca, M.; Aqad, E.; Partridge, B. E.; Heiney, P. A.; Graf, R.; Spiess, H. W.; Zeng, X.;

Percec, V. Hierarchical Self-Organization of Perylene Bisimides into Supramolecular Spheres and Periodic Arrays Thereof. *J. Am. Chem. Soc.* **2016**, *138*, 14798–14807.

(64) Percec, V.; Peterca, M.; Tadjiev, T.; Zeng, X.; Ungar, G.; Leowanawat, P.; Aqad, E.; Imam, M. R.;

Rosen, B. M.; Akbey, U.; Graf, R.; Sekharan, S.; Sebastiani, D.; Spiess, H. W.; Heiney, P. A.; Hudson,
S. D. Self-Assembly of Dendronized Perylene Bisimides into Complex Helical Columns. *J. Am. Chem. Soc.* 2011, *133*, 12197–12219.

(65) Percec, V.; Hudson, S. D.; Peterca, M.; Leowanawat, P.; Aqad, E.; Graf, R.; Spiess, H. W.; Zeng, X.; Ungar, G.; Heiney, P. A. Self-Repairing Complex Helical Columns Generated *via* Kinetically Controlled Self-Assembly of Dendronized Perylene Bisimides. *J. Am. Chem. Soc.* 2011, *133*, 18479–18494.

(66) Percec, V.; Sun, H.-J.; Leowanawat, P.; Peterca, M.; Graf, R.; Spiess, H. W.; Zeng, X.; Ungar, G.; Heiney, P. A. Transformation from Kinetically into Thermodynamically Controlled Self-Organization of Complex Helical Columns with 3D Periodicity Assembled from Dendronized Perylene Bisimides. *J. Am. Chem. Soc.* 2013, *135*, 4129–4148.

(67) Roche, C.; Sun, H.-J.; Prendergast, M. E.; Leowanawat, P.; Partridge, B. E.; Heiney, P. A.; Araoka,
F.; Graf, R.; Spiess, H. W.; Zeng, X.; Spies, H. W.; Zeng, X.; Ungar, G.; Percec, V. Homochiral
Columns Constructed by Chiral Self-Sorting During Supramolecular Helical Organization of
Hat-Shaped Molecules. J. Am. Chem. Soc. 2014, 136, 7169–7185.

(68) Roche, C.; Sun, H.-J.; Leowanawat, P.; Araoka, F.; Partridge, B. E.; Peterca, M.; Wilson, D. A.;
Prendergast, M. E.; Heiney, P. A.; Graf, R.; Spies, H. W.; Zeng, X.; Ungar, G.; Percec, V. A
Supramolecular Helix That Disregards Chirality. *Nat. Chem.* 2016, *8*, 80–89.

(69) Peterca, M.; Imam, M. R.; Hudson, S. D.; Partridge, B. E.; Sahoo, D.; Heiney, P. A.; Klein, M. L.;
Percec, V. Complex Arrangement of Orthogonal Nanoscale Columns *via* a Supramolecular
Orientational Memory Effect. *ACS Nano* 2016, *10*, 10480–10488.

(70) Sahoo, D.; Peterca, M.; Aqad, E.; Partridge, B. E.; Heiney, P. A.; Graf, R.; Spiess, H. W.; Zeng, X.;
Percec, V. Tetrahedral Arrangements of Perylene Bisimide Columns *via* Supramolecular Orientational Memory. *ACS Nano* 2017, *11*, 983–991.

(71) Sahoo, D.; Peterca, M.; Aqad, E.; Partridge, B. E.; Klein, M. L.; Percec, V. Losing Supramolecular Orientational Memory *via* Self-Organization of a Misfolded Secondary Structure. *Polym. Chem.* **2018**, *9*, 2370–2381.

(72) Singer, S. J.; Nicolson, G.; L. The Fluid Mosaic Model of the Structure of Cell Membranes. *Science*, **1972**, *175*, 720-731.

(73) Simons, K.; Ikonen, E. Functional Rafts in Cell Membraneds. *Nature*, **1997**, *387*, 569-572.

(74) Lingwood, D.; Simons, K. Lipid Rafts as a Membrane-Organizing Principle. *Science*, **2010**, *327*, 46–50.

(75) Eggeling, C.; Ringemann, C.; Medda, R.; Schwarzmann, G.; Sandhoff, K.; Polyakova, S.; Belov, V.
N.; Hein, B.; von Middendorff, C.; Schönle, A.; Hell, S.; W. Direct Observation of the Nanoscale Dynamics of Membrane Lipids in a Living Cell. *Nature*, 2009, 457, 1159-1162.

(76) Sezgin, E.; Levental, I.; Mayor, S.; Eggeling C. The Mystery of Membrane Organization: Composition, Regulation and Roles of Lipid Rafts. *Nat. Rev. Mol. Cell Biol.* 2017, *18*, 361-374.

(77) Bangham, A. D.; Standish, M. M.; Watkins, J. C. Diffusion of Univalent Ions Across the Lamellae of Swollen Phospholipids. *J. Mol. Biol.* **1965**, *13*, 238–252.

(78) Allen, T. M.; Chonn, A. Large Unilamellar Liposomes with Low Uptake into the Reticuloendothelial System. *FEBS Lett.* **1987**, *223*, 42–46.

#### Biomacromolecules

(79) Allen, T. M.; Cullis, P. R. Drug Delivery Systems: Entering the Mainstream. *Science* 2004, *303*, 1818–1822.

(80) Torchilin, V. P. Recent Advances with Liposomes as Pharmaceutical Carriers. *Nat. Rev. Drug Discov.* **2005**, *4*, 145–160.

(81) Discher, B. M.; Won, Y.-Y.; Ege, D. S.; Lee, J. C.-M.; Bates, F. S.; Discher, D. E.; Hammer, D. A.

Polymersomes: Tough Vesicles Made from Diblock Copolymers. Science 1999, 284, 1143–1146.

(82) Percec, V.; Wilson, D. A.; Leowanawat, P.; Wilson, C. J.; Hughes, A. D.; Kaucher, M. S.; Hammer,

D. A.; Levine, D. H.; Kim, A. J.; Bates, F. S.; Davis, K. P.; Lodge, T. P.; Klein, M. L.; DeVane, R. H.;

Aqad, E.; Rosen, B. M.; Argintaru, A. O.; Sienkowska, M. J.; Rissanen, K.; Nummelin, S.; Ropponen, J. Self-assembly of Janus Dendrimers into Uniform Dendrimersomes and other Complex Architectures. *Science* **2010**, *328*, 1009–1014.

(83) Sherman, S. E.; Xiao, Q.; Percec, V. Mimicking Complex Biological Membranes and Their Programmable Glycan Ligands with Dendrimersomes and Glycodendrimersomes. *Chem. Rev.* 2017, *117*, 6538–6631.

(84) Zhang, S.; Sun, H.-J.; Hughes, A. D.; Moussodia, R.-O.; Bertin, A.; Chen, Y.; Pochan, D. J.;
Heiney, P. A.; Klein, M. L.; Percec, V. Self-Assembly of Amphiphilic Janus Dendrimers into Uniform
Onion-like Dendrimersomes with Predictable Size and Number of Bilayers. *Proc. Natl. Acad. Sci. U.S.A.*2014, *111*, 9058–9063.

(85) Peterca, M.; Percec, V.; Leowanawat, P.; Bertin, A. Predicting the Size and Properties of Dendrimersomes from the Lamellar Structure of Their Amphiphilic Janus Dendrimers. *J. Am. Chem. Soc.* **2011**, *133*, 20507–20520.

(86) Zhang, S.; Sun, H.-J.; Hughes, A. D.; Draghici, B.; Lejnieks, J.; Leowanawat, P.; Bertin, A.; Otero De Leon, L.; Kulikov, O. V.; Chen, Y.; Pochan, D.J.; Heiney, P. A.; Percec, V. "Single–Single" Amphiphilic Janus Dendrimers Self-Assemble into Uniform Dendrimersomes with Predictable Size. *ACS Nano* 2014, *8*, 1554–1565.

(87) Percec, V.; Leowanawat, P.; Sun, H.-J.; Kulikov, O.; Nusbaum, C. D.; Tran, T. M.; Bertin, A.; Wilson, D. A.; Peterca, M.; Zhang, S.; Kamat, N. P.; Vargo, K.; Moock, D.; Johnston, E. D.; Hammer, D. A.; Pochan, D. J.; Chen, Y.; Chabre, Y. M.; Shiao, T. C.; Bergeron-Brlek, M.; André, S.; Roy, R.; Gabius, H.-J.; Heiney, P. A. Modular Synthesis of Amphiphilic Janus Glycodendrimers and Their Self-Assembly into Glycodendrimersomes and Other Complex Architectures with Bioactivity to Biomedically Relevant Lectins. *J. Am. Chem. Soc.* 2013, *135*, 9055–9077.

(88) Zhang, S.; Moussodia, R.-O.; Sun, H.-J.; Leowanawat, P.; Muncan, A.; Nusbaum, C. D.; Chelling,
K. M.; Heiney, P. A.; Klein, M. L.; André, S.; Roy, R.; Gabius, H.-J.; Percec V. Mimicking Biological Membranes with Programmable Glycan Ligands Self-Assembled from Amphiphilic Janus Glycodendrimers. *Angew. Chem. Int. Ed.* 2014, *53*, 10899–10903.

(89) Zhang, S.; Xiao, Q.; Sherman, S. E.; Muncan, A.; Ramos Vicente, A. D. M.; Wang, Z.; Hammer, D. A.; Williams, D.; Chen, Y.; Pochan, D. J.; Vértesy, S., André, S.; Klein, M. L.; Gabius, H.-J.; Percec, V. Glycodendrimersomes from Sequence-Defined Janus Glycodendrimers Reveal High Activity and Sensor Capacity for the Agglutination by Natural Variants of Human Lectins. *J. Am. Chem. Soc.* 2015, *137*, 13334–13344.

(90) Xiao, Q.; Zhang, S.; Wang, Z.; Sherman, S. E.; Moussodia, R.-O.; Peterca, M.; Muncan, A.; Williams, D. R.; Hammer, D. A.; Vértesy, S.; André, S.; Gabius, H.-J.; Klein, M. L.; Percec, V. Onion-Like Glycodendrimersomes from Sequence-Defined Janus Glycodendrimers and Influence of Architecture on Reactivity to a Lectin. *Proc. Natl. Acad. Sci. U.S.A.* 2016, *113*, 1162–1167.

(91) Zhang, S.; Moussodia, R.-O.; Murzeau, C.; Sun, H.-J.; Klein, M. L.; Vértesy, S.; André, S.; Roy, R.;
Gabius, H.-J.; Percec, V. Dissecting Molecular Aspects of Cell Interactions Using
Glycodendrimersomes with Programmable Glycan Presentation and Engineered Human Lectins. *Angew. Chem. Int. Ed.* 2015, *54*, 4036–4040.

(92) Zhang, S.; Moussodia, R.-O.; Vértesy, S.; André, S.; Klein, M. L.; Gabius, H.-J.; Percec, V. Unraveling Functional Significance of Natural Variations of a Human Galectin by

#### Biomacromolecules

Glycodendrimersomes with Programmable Glycan Surface. *Proc. Natl. Acad. Sci. U.S.A.* 2015, *112*, 5585–5590.

(93) Xiao, Q.; Wang, Z.; Williams, D.; Leowanawat, P.; Peterca, M.; Sherman, S. E.; Zhang, S.; Hammer, D. A.; Heiney, P. A.; King, S. R.; Markovitz, D. M.; André, S.; Gabius, H.-J.; Klein, M. L.;

Percec, V. Why Do Membranes of Some Unhealthy Cells Adopt a Cubic Architecture? *ACS Cent. Sci.* **2016**, *2*, 943–953.

(94) Kopitz. J.; Xiao, Q.; Ludwig, A.-K.; Romero, A.; Michalak, M.; Sherman, S. E.; Zhou, X.; Dazen, C.; Vértesy, S.; Kaltner, H.; Klein, M.L., Gabius, H.-J.; Percec, V. Reaction of a Programmable Glycan Presentation of Glycodendrimersomes and Cells with Engineered Human Lectins To Show the Sugar Functionality of the Cell Surface. *Angew. Chem. Int. Ed.* 2017, *56*, 14677–14681.

(95) Xiao, Q.; Ludwig, A.-K.; Romanò, C.; Buzzacchera, I.; Sherman, S. E.; Vetro, M.; Kaltner, K.; Reed, E. H.; Möller, M.; Wilson, C. J.; Hammer, D. A.; Oscarson, S.; Klein, M. L.; Gabius, H.-J.; Percec, V.; Exploring Functional Pairing Between Surface Glycoconjugates and Human Galectins using Programmable Glycodendrimersomes. *Proc. Natl. Acad. Sci. U.S.A.*, **2018**, *115*, E2509–E2518.

(96) Xiao, Q.; Yadavalli, S.S.; Zhang, S.D.; Sherman, S.E.; Fiorin, E.; da Silva, L.; Wislon, D.A.;
Hammer, D.A.; Andre, S.; Gabius, H.J.; Klein, M.L.; Goulian, M.; Percec, V. Bioactive Cell-Like
Hybrids Coassembled from (Glyco)Dendrimersomes with Bacterial Membranes. *Proc. Natl. Acad. Sci.*U.S.A. 2016, 113, E1134–E1141.

(97) Xiao, Q.; Rubien, J. D.; Wang, Z.; Reed, E. H.; Hammer, D. A.; Sahoo, D.; Heiney, P. A.; Yadavalli, S. S.; Goulian, M.; Wilner, S. E.; Baumgart, T.; Vinogradov, S. A.; Klein, M. L.; Percec, V. Self-Sorting and Coassembly of Fluorinated, Hydrogenated, and Hybrid Janus Dendrimers into Dendrimersomes. *J. Am. Chem. Soc.* 2016, *138*, 12655–12663.

(98) Xiao, Q.; Sherman, S. E.; Wilner, S. E.; Zhou, X.; Dazen, C.; Baumgart, T.; Reed, E. H.; Hammer, D. A.; Shinoda, W.; Klein, M. L.; Percec V. Janus Dendrimersomes Coassembled from Fluorinated, Hydrogenated, and Hybrid Janus Dendrimers as Models for Cell Fusion and Fission. *Proc. Natl. Acad. Sci. U.S.A.* 2017, *114*, E7045–E7053.

2
3
Δ
-
2
6
7
8
9
10
10
11
12
13
14
15
16
17
17
18
19
20
21
22
25
20
24
25
26
27
28
20
29
30
31
32
33
34
25
22
36
37
38
39
40
<u>Λ</u> 1
40 71
42
43
44
45
46
47
ло Л
40
49
50
51
52
53
51
54 55
55
56
57
58
50

1

(99) Wilner, S. E.; Xiao, Q.; Graber, Z. T.; Sherman, S. E.; Percec, V.; Baumgart, T. Dendrimersomes Exhibit Lamellar-to-Sponge Phase Transitions. *Langmuir* **2018**, *34*, 5527–5534.

(100) Moore, J. S.; Stupp, S. I. Room Temperature Polyesterification. *Macromolecules* 1990, 23, 65–70.

- (101) Lee, H.; Dellatore, S. M.; Miller, W. M.; Messersmith, P. B. Mussel-Inspired Surface Chemistry for Multifunctional Coatings. *Science* **2007**, *318*, 426–430.
- (102) Lee, H.; Lee, B. P.; Messersmith, P. B. A Reversible Wet/Dry Adhesive Inspired by Mussels and Geckos. *Nature* **2007**, *448*, 338–341.

(103) Lee, H.; Rho, J.; Messersmith, P. B. Facile Conjugation of Biomolecules onto Surfaces *via* Mussel Adhesive Protein Inspired Coatings. *Adv. Mater.* **2009**, *21*, 431–434.

(104) Lee, B. P.; Messersmith, P. B.; Israelachvili, J. N.; Waite, J. H. Mussel-Inspired Adhesives and Coatings. *Annu. Rev. Mater. Res.* **2011**, *41*, 99–132.

- (105) Hersmis, M. C.; Spiering, A. J. H.; Waterval, R. J. M.; Meuldijk, J.; Vekemans, J. A. J. M.;
  Hulshof, L. A. 3,4,5-Tri-dodecyloxybenzoic Acid: Optimisation and Scale-Up of the Synthesis. *Org. Proc. Res. Dev.* 2001, *5*, 54–60.
- (106) Tu, Y.; Peng, F.; Adawy, A.; Men, Y.; Abdelmohsen, L. K. E. A.; Wilson, D. A. Mimicking the
- Cell: Bio-Inspired Functions of Supramolecular Assemblies. Chem. Rev. 2016, 116, 2023–2078.
- (107) Lee, S.; Bluemle, M. J.; Bates, F. S. Discovery of a Frank-Kasper σ-Phase in Sphere-Forming Block Copolymer Melts. *Science* 2010, *330*, 349–353.
- (108) Bates, F. S.; Hillmyer, M. A.; Lodge, T. P.; Bates, C. M.; Delaney, K. T.; Fredrickson, G. H.
  Multiblock Polymers: Panacea or Pandora's Box? *Science* 2012, *336*, 434–440.
- (109) Gillard, T. M.; Lee, S.; & Bates, F. S. Dodecagonal Quasicrystalline order in a Diblock Copolymer melt. *Proc. Natl Acad. Sci. U.S.A.* **2016**, *113*, 5167–5172.
- (110) Chanpuriya, S.; Kim, K.; Zhang, J.; Lee, S.; Arora, A.; Dorfman, K. D.; Delaney, K. T.;
  Fredrickson, G. H.; Bates, F. S. Cornucopia of Nanoscale Ordered Phases in Sphere-Forming Tetrablock
  Terpolymers. *ACS Nano* 2016, *10*, 4961–4972.

#### **Biomacromolecules**

(111) Kim, K.; Schulze, M. W.; Arora, A.; Lewis III, R. M.; Hillmyer, M. A.; Dorfman, K. D.; Bates, F.
S. Thermal Processing of Diblock Copolymer Melts Mimics Metallurgy. *Science* 2017, *356*, 520–523.

(112) Perroni, D. V.; Mahanthappa, M. K. Inverse *Pm3n* Cubic Micellar Lyotropic Phases from Zwitterionic Triazolium Gemini Surfactants. *Soft Matter* **2013**, *9*, 7919–7922.

(113) Yue, K.; Huang, M.; Marson, R. L.; He, J.; Huang, J.; Zhou, Z.; Wang, J.; Liu, C.; Yan, X.; Wu, K.; Guo, Z.; Liu, H.; Zhang, W.; Ni, P.; Wesdemiotis, C.; Zhang, W.-B.; Glotzer, S. C.; Cheng, S. Z. D. Geometry Induced Sequence of Nanoscale Frank–Kasper and Quasicrystal Mesophases in Giant Surfactants. *Proc. Natl. Acad. Sci. U.S.A.* 2016, *113*, 14195–14200.

(114) Kim, S. A.; Jeong, K.-J.; Yethiraj, A.; Mahanthappa, M. K. Low-Symmetry Sphere Packings of Simple Surfactant Micelles Induced by Ionic Sphericity. *Proc. Natl. Acad. Sci. U.S.A.* **2017**, *114*, 4072–4077.

(115) Baez-Cotto, C. M.; Mahanthappa, M. K. Micellar Mimicry of Intermetallic C14 and C15 Laves Phases by Aqueous Lyotropic Self-Assembly. *ACS Nano* **2018**, *12*, 3226–3234.

(116) Huang, M.; Hsu, C.-H.; Wang, J.; Mei, S.; Dong, X.; Li, Y.; Li, M.; Liu, H.; Zhang, W.; Aida, T.;
Zhang, W.-B.; Yue, K.; Cheng, S. Z. D. Selective Assemblies of Giant Tetrahedra *via* Precisely
Controlled Positional Interactions. *Science* 2015, *348*, 424–428.

(117) Zhang, W.; Huang, M.; Su, H.; Zhang, S.; Yue, K.; Dong, X.-H.; Li, X.; Liu, H.; Zhang, S.; Wesdemiotis, C.; Lotz, B.; Zhang, W.-B.; Li, Y.; Cheng, S. Z. D. Toward Controlled Hierarchical Heterogeneities in Giant Molecules with Precisely Arranged Nano Building Blocks. *ACS Cent. Sci.* 2016, *2*, 48–54.

(118) Zhang, W.; Lu, X.; Mao, J.; Hsu, C.-H.; Mu, G.; Huang, M.; Guo, Q.; Liu, H.; Wesdemiotis, C.;
Li, T.; Zhang, W.-B.; Li, Y.; Cheng, S. Z. D. Sequence-Mandated, Distinct Assembly of Giant Molecules. *Angew. Chem. Int. Ed.* 2017, *56*, 15014–15019.

(119) Ye, X.; Chen, J.; Irrgang, M. E.; Engel, M.; Dong, A.; Glotzer, S. C.; Murray, C. B. Quasicrystalline Nanocrystal Superlattice with Partial Matching Rules. *Nat. Mater.* **2016**, *16*, 214–219.

(120) Guo, X.; Szoka, F. C. Chemical Approaches to Triggerable Lipid Vesicles for Drug and Gene Delivery. *Acc. Chem. Res.* 2003, *36*, 335–341.

(121) Lee, C. C.; MacKay, J. A.; Fréchet, J. M. J.; Szoka, F. C. Designing Dendrimers for Biological Applications. *Nat. Biotechnol.* **2005**, *23*, 1517–1526.

(122) Farokhzad, O. C.; Langer, R. Impact of Nanotechnology on Drug Delivery. *ACS Nano* 2009, *3*, 16–20.

(123) Menjoge, A. R.; Kannan, R. M.; Tomalia, D. A. Drug Discovery Today 2010, 15, 171–185.

(124) Deming, T. J. Preparation and Development of Block Copolypeptide Vesicles and Hydrogels for Biological and Medical Applications. *WIREs Nanomed. Nanobiotechnol.* **2014**, *6*, 283–297.

(125) Yu, T.; Liu, X.; Bolcato-Bellemin, A.-L.; Wang, Y.; Liu, C.; Erbacher, P.; Qu, F.; Rocchi, P.;
Behr, J.-P.; Peng, L.Anamphiphilic dendrimer for effective delivery of small interfering RNA and gene silencing in vitro and in vivo, *Angew. Chem. Int. Ed.* 2012, *51*, 8478–8484.

(126) Liu, X.; Zhou, J.; Yu, T.; Chen, C.; Cheng, Q.; Sengupta, K.; Huang, Y.; Li, H.; Liu, C.; Wang, Y.;

Posocco, P.; Wang, M.; Cui, Q.; Giorgio, S.; Fermeglia, M.; Qu, F.; Pricl, S.; Shi, Y.; Liang, Z.; Rocchi,

P.; Rossi, J.; Peng, L. Adaptive amphiphilic dendrimer-based nanoassemblies as robust and versatile siRNA delivery systems, *Angew. Chem. Int. Ed.* **2014**, *53*, 11822–11827.

(127) Wei, T.; Chen, C.; Liu, J.; Liu, C.; Posocco, P.; Liu, X.; Cheng, Q.; Huo, S.; Liang, Z.; Fermeglia, M.; Pricl, S.; Liang, X.-J.; Rocchi, P.; Peng, L. Anticancer Drug Nanomicelles Formed by Self-Assembling Amphiphilic Dendrimer to Combat Cancer Drug Resistance. *Proc. Natl. Acad. Sci. U. S. A.* 2015, *112*, 2978–2983.

(128) Thota, B. N.S.; Urner, L. H.; Haag, R. Supramolecular Architectures of Dendritic Amphiphiles in Water. *Chem. Rev.* **2016**, *116*, 2079–2102.

(129) Filippi, M.; Catanzaro, V.; Patrucco, D.; Botta, M.; Tei, L.; Terreno, E. First in Vivo MRI Study on Theranostic Dendrimersomes. *J. Controlled Release* **2017**, *248*, 45–52.

(130) Nummelin, S.; Selin, M.; Legrand, S.; Ropponen, J.; Seitsonen, J.; Nykanen, A.; Koivisto, J.; Hirvonen, J.; Kostiainen, M. A.; Bimbo, L. M. Modular Synthesis of Self-Assembling

#### Biomacromolecules

Janus-Dendrimers and Facile Preparation of Drug-Loaded Dendrimersomes. *Nanoscale* 2017, *9*, 7189–7198.

(131) Selin, M.; Nummelin, S.; Deleu, J.; Ropponen, J.; Viitala, T.; Lahtinen, M.; Koivisto, J.; Hirvonen,

J.; Peltonen, L.; Kostiainen, M. A.; Bimbo, L. M. High-Generation Amphiphilic Janus-Dendrimers as Stabilizing Agents for Drug Suspensions. *Biomacromolecules* **2018**, *19*, 3983–3993.

(132) Yang, Y.-L.; Sheng, Y.-J.; Tsao, H.-K. Branching Pattern Effect and Co-Assembly with Lipids of Amphiphilic Janus Dendrimersomes. *Phys. Chem. Chem. Phys.* **2018**. DOI: 10.1039/C8CP05268A.

(133) Elizondo-García, M.; Márquez-Miranda, V.; Araya-Durán, I.; Valencia-Gallegos, J.;

González-Nilo, F.; Elizondo-García, M. E.; Márquez-Miranda, V.; Araya-Durán, I.; Valencia-Gallegos,

J. A.; González-Nilo, F. D. Self-Assembly Behavior of Amphiphilic Janus Dendrimers in Water: A Combined Experimental and Coarse-Grained Molecular Dynamics Simulation Approach. *Molecules* **2018**, *23*, 969.

(134) Liu, X.; Gitsov, I. Thermosensitive Amphiphilic Janus Dendrimers with Embedded Metal Binding Sites. Synthesis and Self-Assembly. *Macromolecules* **2018**, *51*, 5085–5100.

(135) Taabache, S.; Bertin, A.; Taabache, S.; Bertin, A. Vesicles from Amphiphilic Dumbbells and Janus Dendrimers: Bioinspired Self-Assembled Structures for Biomedical Applications. *Polymers* 2017, *9*, 280.

## **TOC Graphic**

Janus Dendrimers for Unilamellar Dendrimersomes

Linear Alkyl Chains: carbon number > 8 Branched Alkyl Chains: 2-Ethylhexyl, 3,7-Dimethyloctyl

ACS Paragon Plus Environment