

Catalytic Addition of Hydrogen Cyanide to Non-activated Olefins

By E. S. BROWN* and E. A. RICK

(Research and Development Department, Union Carbide Corporation, Chemicals and Plastics, South Charleston, West Virginia 25303)

ALTHOUGH soluble transition-metal complexes are used as catalysts for the synthesis of nitriles from non-activated olefins and hydrogen cyanide, their use is limited by the large amount of catalyst required.¹⁻³ We report the first useful homogeneous process for the addition of hydrogen cyanide to non-activated olefins.

Zerovallent palladium and nickel complexes act as efficient catalysts for the addition of hydrogen cyanide to olefins under certain conditions. Reaction of hydrogen cyanide with bicyclo[2,2,1]heptene in the presence of catalytic quantities of tetrakis(triphenylphosphite)palladium[0] gives only poor yields of 2-cyanobicyclo[2,2,1]heptane. However, in the presence of triphenylphosphite

bicyclo[2,2,1]heptene, the product is almost exclusively the *exo*-isomer of 2-cyanobicyclo[2,2,1]heptane.

When the reactants are charged simultaneously, optimum results are obtained when the phosphite concentration approximates the hydrogen cyanide concentration. This large phosphite requirement, however, can be greatly reduced if hydrogen cyanide is added continuously to the reaction mixture at such a rate that the concentration of hydrogen cyanide remains close to that of the phosphite.

We suggest that the initial reaction is formation of the hydride (II) by oxidative addition of hydrogen cyanide. This is reasonable since Pd⁰ complexes add oxidatively to a variety of molecules.⁴ Co-ordinated olefin may then

Catalyst, (M)	Bicyclo[2,2,1]heptene, (M)	HCN , (M)	P(OPh) ₃ , (M)	2-Cyanobicyclo[2,2,1]heptane yield % (on HCN)	Catalyst turnover	
Pd[P(OPh) ₃] ₄	0.01	1.24	0.66	0.0	5.9	4
	0.01	1.24	0.66	0.32	70.0	47
	0.01	1.24	0.66	1.1	83.0	55
	0.01	1.24	0.66	1.9	68.6	45
	0.0005*	3.0	1.05	1.0	59	1260

* 190°, 6 hr., in benzene. All other reactions shown, 120°, 8 hr., in benzene.

(Table) the yield of product and, more importantly, the catalyst turnover is increased (see last example). With

"insert" into the H-Pd bond of (II) to form (III). Formation of product may occur either by a collapse of (III) or

