

Stereocontrolled Synthesis and Optical Properties of All-cis Poly(phenylene vinylenes) (PPVs): A Method for Direct Patterning of PPVs

Hiroyuki Katayama,*,† Masato Nagao,† Tatsuro Nishimura,† Yukio Matsui,† Kazutoshi Umeda,[†] Kensuke Akamatsu,[‡] Takaaki Tsuruoka,[‡] Hidemi Nawafune,[‡] and Fumiyuki Ozawa*,[†]

Contribution from the International Research Center for Elements Science (IRCELS), Institute for Chemical Research, Kyoto University, Uji, Kyoto 611-0011, Japan, and Faculty of Science and Engineering, Konan University, Higashinada-ku, Kobe 658-8501, Japan

Received November 27, 2004; Revised Manuscript Received January 14, 2005; E-mail: hiroyuki@scl.kyoto-u.ac.jp; ozawa@scl.kyoto-u.ac.jp

Abstract: Geometrically pure, all-cis poly(phenylene vinylenes) (PPVs) are synthesized by Suzuki-Mivauratype polycondensation of 2,5-dioctyloxy-1,4-benzenediboronic acid with (Z,Z)-bis(2-bromoethenyl)benzenes, which are prepared by ruthenium-catalyzed (Z)-selective double hydrosilylation of diethynylbenzenes, followed by bromodesilylation of the resulting (Z,Z)-bis(2-silylethenyl)benzenes with N-bromosuccinimide. The all-cis PPVs thus obtained undergo one-way photoisomerization to the corresponding trans-PPVs both in solution and in the solid. This phenomenon is applied to direct microscale patterning of PPVs onto a quartz substrate.

Poly(phenylene vinylenes) (PPVs) belong to the group of π -conjugated polymers that have applications in light-emitting diodes (LEDs),^{1,2} lasers,³ and solar cells.⁴ Considerable efforts have been made to improve their emission color and efficiency in LEDs by introducing substituents to the polymer skeletons. On the other hand, although stereoregularity of vinylene linkages in the polymer backbone is also known to profoundly affect the optical properties of PPVs,⁵ efficient ways of regulating the geometries of vinylene linkages have remained almost unexplored. It is particularly difficult to prepare geometrically pure

all-cis PPVs using previous polymerization methods based on Gilch, Heck, and Wittig reactions.

We recently examined a stereocontrolled synthesis of transand cis-PPVs using Hiyama-type polycondensations of 2,5-dioctyloxy-1,4-diiodobenzene with (E,E)- and (Z,Z)-1,4bis(2-silylethenyl)benzenes.⁶ All-trans PPV was successfully prepared by this method, but stereoregularity for cis-PPV was limited to 66%. Herein, we report that all-cis PPVs are synthesized by Suzuki-Miyaura coupling.⁷ The resulting polymers exhibit a rather unique photochemical property that allows the direct microscale patterning of PPVs onto a quartz substrate.

Results and Discussion

The PPV synthesis was performed with p- and m-isomers of (Z,Z)-bis(2-bromoethenyl)benzene (4a,b) as monomers, which were prepared by a two-step procedure given in Scheme 1.8 The first step is (Z)-selective double hydrosilylation of 1,4- and

Kyoto University. [‡] Konan University.

 ⁽a) Burroughes, J. H.; Bradley, D. D. C.; Brown, A. R.; Marks, R. N.; Mackay, K.; Friend, R. H.; Burn, P. L.; Holmes, A. B. *Nature* 1990, 347, 539. (b) Burn, P. L.; Holmes, A. B.; Kraft, A.; Bradley, D. D. C.; Brown, A. R.; Friend, R. H.; Gymer, R. W. *Nature* 1992, 356, 47. (c) Greenham, N. C.; Moratti, S. C.; Bradley, D. D. C.; Friend, R. H.; Burn, P. L.; Holmes, N. C., Molatti, S. C., Bladey, D. D. C., Fleid, K. H., Bull, F. L., Holmes,
 A. B. *Nature* 1993, 365, 628. (d) Gustafsson, G.; Cao, Y.; Treacy, G. M.;
 Klavetter, F.; Colaneri, N.; Heeger, A. J. *Nature* 1992, 357, 477.
 (e) Hoofman, R. J. O. M.; de Haas, M. P.; Siebbeles, L. D. A.; Warman,
 J. M. *Nature* 1998, 392, 54. (f) Welter, S.; Brunner, K.; Hofstraat, J. W.;
 De Cola, L. *Nature* 2003, 421, 54.

<sup>De Cola, L. Nature 2003, 421, 54.
(2) For reviews, see: (a) Kraft, A.; Grimsdale, A. C.; Holmes, A. B. Angew. Chem., Int. Ed. 1998, 37, 402. (b) Friend, R. H.; Gymer, R. W.; Holmes, A. B.; Burroughes, J. H.; Marks, R. N.; Taliani, C.; Bradley, D. D. C.; Dos Santos, D. A.; Brédas, J. L.; Lögdlund, M.; Salaneck, W. R. Nature 1999, 397, 121. (c) Scherf, U. Top. Curr. Chem. 1999, 201, 163. (d) Akcelrud, L. Prog. Polym. Sci. 2003, 28, 875.
(3) (a) Tessler, N.; Denton, G. J.; Friend, R. H. Nature 1996, 382, 695. (b) Hide, F.; Diaz-Garcia, M. A.; Schwartz, B. J.; Andersson, M. R.; Pei, Q.; Heeger, A. J. Science 1996, 273, 1833. (c) McGehee, M. D.; Heeger, A. J. Adv. Mater. 2000, 12, 1655. (d) Nguyen, T.-Q.; Martini, I. B.; Liu, J.; Schwartz, B. J. J. Phys. Chem. B 2000, 104, 237.
(4) (a) Yu, G.; Gao, J.; Hummelen, J. C.; Wudl, F.; Heeger, A. J. Science 1995, 270, 1789. (b) Dittmer, J. J.; Petritsch, K.; Marseglia, E. A.; Friend,</sup>

D.; Brabec, C. J.; Padinger, F.; Fromherz, T.; Hummelen, J. C.; Badt, D.; Schindler, H.; Sariciftci, N. S. Synth. Met. 2001, 118, 1. (d) Martens, T.; D'Haen, J.; Munters, T.; Beelen, Z.; Goris, L.; Manca, J.; D'Olieslaeger, M.; Vanderzande, D.; De Schepper, L.; Manca, J.; D'Olieslaeger, M.; Vanderzande, D.; De Schepper, L.; Andriessen, R. Synth. Met. 2003, 138, 243.

⁽a) Son, S.; Dodabalapur, A.; Lovinger, A. J.; Galvin, M. E. Science **1995**, 269, 376. (b) Liao, L.; Ding, L.; Karasz, F. E. Pang, Y. J. Polym. Sci., Part A: Polym. Chem. **2004**, 42, 303. (c) Liao, L.; Pang, Y.; Ding, L.; Karasz, F. E. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. E. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; Pang, Y.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; Pang, Y.; C. F. Macromolecules **2001**, 34, 6756. (d) Pang, Y.; Li, J.; Hu, B.; Pang, Y.; Pang, Y (5) Karasz, F. E. *Macromolecules* 2001, *94*, 6150. (d) Fang, F., Li, J., Hu, B.,
 Karasz, F. E. *Macromolecules* 1999, *32*, 3946. (e) Sarker, A. M.; Gürel,
 E. E.; Ding, L.; Styche, E.; Lahti, P. M.; Karasz, F. E. *Synth. Met.* 2003, *132*, 227. (f) Drury, A.; Maier, S.; Rüther, M.; Blau, W. J. J. Mater. Chem.
 2003, *13*, 485. (g) Cassano, T.; Tommasi, R.; Babudri, F.; Cardone, A.;
 Farinola, G. M.; Naso, F. *Synth. Met.* 2003, *139*, 827. (h) Ronchi, A.; Cassano, T.; Tommasi, R.; Babudri, F.; Cardone, A.; Farinola, G. M.; Naso, Cassano, L., Tohmasi, K., Baoduli, F., Cattolie, A., Parliola, U. M., Naso, F. Synth. Met. 2003, 139, 831. (i) Dalton, A. B.; Coleman, J. N.; in het Panhuis, M.; McCarthy, B.; Drury, A.; Blau, W. J.; Paci, B.; Nunzi, J.-M.; Byrne, H. J. J. Photochem. Photobiol., A 2001, 144, 31.
(6) Katayama, H.; Nagao, M.; Moriguchi, R.; Ozawa, F. J. Organomet. Chem.

^{2003, 676, 49}

^{(7) (}a) Miyaura, N.; Suzuki, A. Chem. Rev. 1995, 95, 2457. (b) Miyaura, N. In Metal-Catalyzed Cross-Coupling Reactions, 2nd ed.; de Meijere, A., Diederich, F., Eds.; Wiley-VCH: Weinheim, Germany, 2004; Chapter 2.

⁽⁸⁾ Compound 4a has been prepared from 1,4-benzenedicarboxaldehyde in moderate yield (42%) by a double Wittig reaction: Romero, M. A.; Fallis, A. G. *Tetrahedron Lett.* **1994**, *35*, 4711.

Scheme 1



1,3-diethynylbenzenes (2a,b) with HSiMe₂An (An = 4-methoxyphenyl) to give (Z,Z)-1,4- and (Z,Z)-1,3-bis(2-silylethenyl)benzenes (3a,b), respectively. While this reaction was previously carried out with RuCl₂(CO)(PPrⁱ₃)₂ (10 mol %) as a catalyst in 91-92% selectivities,6 it was found that a newly prepared ruthenium complex 1 bearing an sp²-hybridized phosphorus ligand (DPCB-OMe)9 serves as a more efficient catalyst with higher reactivity and selectivity.¹⁰⁻¹² Thus, the reaction of **2a** with HSiMe₂An (1.9 equiv) in toluene, in the presence of 0.5 mol % of 1, was complete in 1 h at room temperature to give (Z,Z)-3a in over 99% regio- and stereoselectivities. Treatment of the product with N-bromosuccinimide (NBS) in acetonitrile at 0 °C formed (Z,Z)-4a in 65% yield (two steps).¹³ The *m*-isomer (Z,Z)-4b was similarly prepared from 2b in 56% yield. Complex 1 was prepared in 49% yield by treatment of $Ru(\eta^3-allyl)Cl(CO)_3^{14}$ with DPCB-OMe in toluene, followed by treatment with dry HCl in ether (see Supporting Information).

Polycondensation of (Z,Z)-4a with 1 equiv of 2,5-dioctyloxy-1,4-benzenediboronic acid (5) was performed in toluene at 80 °C for 24 h in the presence of Pd(PPh₃)₄ (1.5 mol %), Bu₄-

- (9) DPCB-OMe = 1,2-bis(4-methoxyphenyl)-3,4-bis[(2,4,6-tri-*tert*-butylphe-nyl)phosphinidene]cyclobutene: Minami, T.; Okamoto, H.; Ikeda, S.; Tanaka, R.; Ozawa, F.; Yoshifuji, M. Angew. Chem., Int. Ed. 2001, 40, 4501.
- (10) The (Z)-selective hydrosilylation of terminal alkynes has been rationalized by the modified Chalk–Harrod mechanism involving a silylruthenium(II) complex as a key intermediate, ^{11,12} which may be effectively stabilized by strong π -accepting ability of DPCB-OMe ligand,⁹ leading to the high catalytic reactivity and selectivity.
- (11) (a) Šeitz, F.; Wrighton, M. S. Angew. Chem., Int. Ed. 1988, 27, 289. (b) Randolph, C. L.; Wrighton, M. S. J. Am. Chem. Soc. 1986, 108, 3366. (c) Fernández, M. J.; Esteruelas, M. A.; Jiménez, M. S.; Oro, L. A (c) Fernandez, M. J., Esterueras, M. A., Jintenez, M. S., Olo, E. A. Organometallics 1986, 5, 1519. (d) Ojima, I.; Fuchikami, T.; Yatabe, M. J. Organomet. Chem. 1984, 260, 335. (e) Onopchenko, A.; Sabourin, E. T.; Beach, D. L. J. Org. Chem. 1983, 48, 5101. (f) Schroeder, M. A.; Wrighton, M. S. J. Organomet. Chem. 1977, 128, 345.
- (12) (a) Maruyama, Y.; Yamamura, K.; Nakayama, I.; Yoshiuchi, K.; Ozawa, F. J. Am. Chem. Soc. **1998**, *120*, 1421. (b) Maruyama, Y.; Yamamura, K.; Sagawa, T.; Katayama, H.; Ozawa, F. Organometallics **2000**, *19*, 1308. (c) Katavama, H.; Taniguchi, K.; Kobavashi, M.; Sagawa, T.; Minami, T.; Ozawa, F. J. Organomet. Chem. 2002, 645, 192.
- (13) (a) Tamao, K.; Akita, M.; Maeda, K.; Kumada, M. J. Org. Chem. 1987, 52, 1100. (b) Stamos, D. P.; Taylor, A. G.; Kishi, Y. Tetrahedron Lett. **1996**, *37*, 8647.
- (14) Sbrana, G.; Braca, G.; Piacenti, F.; Pino, P. J. Organomet. Chem. 1968, 13. 240.



Figure 1. ¹H NMR spectra of all-cis **6a** ($M_n = 2700$) (A), (Z,Z)-**7** (B), and all-trans 6a obtained by photoisomerization (C).

NBr (1 equiv), and aqueous K_3PO_4 (3 equiv). The reaction solution was then poured into excess MeOH to precipitate an orange solid of all-cis PPV **6a** ($M_n = 4700$, PDI = 1.92, 95% yield).¹⁵ Similarly, all-cis **6b** ($M_n = 5100$, PDI = 2.13) was obtained in 99% yield, starting from (Z,Z)-4b and 5. All procedures must be performed in the dark to avoid cis-to-trans isomerization of PPVs (vide infra). The use of KOH instead of K₃PO₄ as a base provided comparable results. On the other hand, the molecular weight of **6a** lowered ($M_n = 2700$, PDI = 1.79) in the absence of Bu₄NBr as a phase-transfer catalyst.

An all-cis arrangement of vinylene linkages was confirmed by NMR spectroscopy. Figure 1 shows the ¹H NMR spectrum of **6a** ($M_n = 2700$), together with the spectrum of (Z,Z)-2,5dioctyloxy-4'-(2-bromoethenyl)stilbene (7), which was prepared as a minimum model of an all-cis PPV. As already shown by Pang et al.,^{5c} the signal at δ 3.54 is due to OCH₂ protons of octyloxy groups adjacent to (Z)-vinylene units. On the other hand, the corresponding signal for the trans-PPV structure $(\delta 4.08)$ was not detected. The small signals observed at δ 3.95 (a) and 3.65 (b) with the same intensities are assignable to a 2,5-dioctyloxyphenyl group at a polymer end by comparison with the spectrum of 7.1^{16} Furthermore, vinylic proton signals at δ 7.00 (c) and 6.38 (d) are ascribed to the presence of a BrCH=CH group at the other end of the polymer.

All-cis PPVs thus prepared were isomerized to all-trans PPVs under photoirradiation. Figure 2A shows a change of the UV-vis spectrum of 6a during the isomerization. When a dilute solution of all-cis **6a** ($M_n = 4700$) in benzene was irradiated

⁽¹⁵⁾ GPC data based on polystyrene standards.

^{(16) 2,5-}Dioctyloxyphenyl groups may be generated by hydrolytic deboronation.



Figure 2. Changes of UV–vis absorption spectra of all-cis **6a** ($M_n = 4700$) under photoirradiation in benzene (A) and in a film (B).

with a high-pressure Xe lamp (2.1 mW cm⁻²) at room temperature, the $\pi - \pi^*$ transition at 382 nm decreased rapidly, to be replaced with a strong absorption at 463 nm ($\epsilon = 38200 \text{ M}^{-1} \text{ cm}^{-1}$), which was almost identical to that of all-trans **6a** ($M_n = 5000$). The spectroscopic change occurred within a few minutes, maintaining isosbestic points at 334 and 388 nm. The formation of all-trans **6a** was also confirmed by ¹H NMR spectroscopy (Figure 1C).⁶ Thus, the PPV **6a** was found to undergo a clean "one-way" photoisomerization¹⁷ from the all-cis isomer to the all-trans isomer, and this behavior is in contrast to the reversible isomerization of stilbene- and azobenzene-containing polymers.¹⁸

The cis-to-trans isomerization of PPVs also took place in the solid state. A thin film of all-cis PPV **6a** (ca. 90 nm thick), which was prepared from a CHCl₃ solution by spin-coating on a quartz plate, was irradiated with strong UV light (35.5 mW cm⁻²) at room temperature under a nitrogen



Figure 3. IR-RAS spectra of a film of all-cis **6a** before (solid line) and after (dotted line) photoirradiation.



Figure 4. Fluorescent images of micropatterned 6a (A) and 6b (B).

atmosphere. The color of the film gradually changed from pale yellow to orange and became unchanged after 45 min (Figure 2B). The UV-vis spectrum at this stage was consistent with the formation of trans-PPV, and IR-RAS analysis of the film supported this conclusion (Figure 3). Interestingly, the PPV film thus prepared was much less soluble than that before irradiation. Accordingly, a very simple method for direct patterning of trans-PPV on a micrometer scale was developed. Thus, UV light was irradiated for 45 min through a photomask onto a film of allcis **6a** coated on a quartz plate. The plate was rinsed with CHCl₃ to remove those parts of the PPV film that were not irradiated. Figure 4A shows an optical image of the resulting plate, which was photographed under UV light. A well-resolved pattern is observed with yellowish green emission. In a similar procedure, a micropattern with blue-light emission was developed from all-cis **6b** with *m*-phenylene units (Figure 4B).

⁽¹⁷⁾ Arai, T.; Tokumaru, K. Chem. Rev. 1993, 93, 23.

^{(18) (}a) Momotake, A.; Arai, T. J. Photochem. Photobiol., C 2004, 5, 1.
(b) Macromol. Symp. (Azobenzene-Containing Materials); Natansohn, A., Ed.; Wiley-VCH: Weinheim, Germany, 1999; Vol. 139.

In conclusion, a highly stereocontrolled synthesis of all-cis PPVs has been successfully accomplished using the Suzuki– Miyaura-type polycondensation. (*Z*,*Z*)-Bis(2-bromoethenyl)benzenes, used as starting monomers, were readily prepared by using complex **1** bearing an sp²-hybridized phosphorus ligand as a (*Z*)-selective double hydrosilylation catalyst for diethynylbenzenes. The all-cis PPVs thus prepared undergo one-way photoisomerization to the corresponding PPVs with (*E*)-vinylene linkages under photoirradiation. This property is applicable to direct patterning of PPVs on a micrometer scale. The method is extremely simple and should be useful for constructing functional materials used in optoelectronics.^{19,20}

(19) For a review, see: Holdcroft, S. Adv. Mater. 2001, 13, 1753.

Acknowledgment. We thank Prof. T. Arai (University of Tsukuba) for helpful discussions. This work was supported by a Grant-in-Aid for Scientific Research from the Ministry of Education, Culture, Sports, Science and Technology, Japan.

Supporting Information Available: Experimental details (PDF). This material is available free of charge via the Internet at http://pubs.acs.org.

JA042853N

(20) (a) Renak, M. L.; Bazan, G. C.; Roitman, D. Adv. Mater. 1997, 9, 392.
(b) Gigli, G.; Rinaldi, R.; Turco, C.; Visconti, P.; Cingolani, R.; Cacialli, F. Appl. Phys. Lett. 1998, 73, 3926. (c) DeAro, J. A.; Gupta, R.; Heeger, A. J.; Burato, S. K. Synth. Met. 1999, 102, 865. (d) Kobayashi, H.; Kanbe, S.; Seki, S.; Kigchi, H.; Kimura, M.; Yudasaka, I.; Miyashita, S.; Shimoda, T.; Towns, C. R.; Burroughes, J. H.; Friend, R. H. Synth. Met. 2000, 111, 125. (e) Liang, Z. Q.; Li, K.; Wang, Q. Langmuir 2003, 19, 5555. (f) Pogantsch, A.; Trattnig, G.; Zojer, E.; Tillmann, H.; Horhold, H. H.; Scherf, U.; Langer, G.; Kern, W. Synth. Met. 2003, 138, 85.