

Molecular Crystals and Liquid Crystals Science and Technology. Section A. Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information:

<http://www.tandfonline.com/loi/gmcl19>

Synthesis of Metal Complexes Chelated with N-Naphthalenyl Aminomethyl Phenol and Their Application to OLED

Sung Min Kim^a, Jin-Soon Kim^a, Sung-Jae Lee^a, Young Kwan Kim^a & Yunkyoung Ha^a

^a Department of Science and Chemical Engineering ,
Research Institute for Science and Technology, Hong-Ik
University , Mapo-gu, Sangsu-dong 72-1, Seoul, 121-791,
Korea

Published online: 24 Sep 2006.

To cite this article: Sung Min Kim , Jin-Soon Kim , Sung-Jae Lee , Young Kwan Kim & Yunkyoung Ha (2001) Synthesis of Metal Complexes Chelated with N-Naphthalenyl Aminomethyl Phenol and Their Application to OLED, Molecular Crystals and Liquid Crystals Science and Technology. Section A. Molecular Crystals and Liquid Crystals, 370:1, 57-60, DOI: [10.1080/10587250108030038](https://doi.org/10.1080/10587250108030038)

To link to this article: <http://dx.doi.org/10.1080/10587250108030038>

PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable

for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms & Conditions of access and use can be found at <http://www.tandfonline.com/page/terms-and-conditions>

Synthesis of Metal Complexes Chelated with N-Naphthalenyl Aminomethyl Phenol and Their Application to OLED

SUNG MIN KIM, JIN-SOON KIM, SUNG-JAE LEE,
YOUNG KWAN KIM and YUNKYOUNG HA*

*Department of Science and Chemical Engineering, Research Institute for
Science and Technology, Hong-Ik University, Mapo-gu, Sangsu-dong 72-1,
Seoul 121-791, Korea*

The metal complexes chelated with N-naphthalenyl aminomethyl phenol were synthesized and the beryllium complex was applied to the organic electroluminescent devices as a blue light-emitting layer. Emission wavelength was observed at 406nm in luminescence spectra for this complex. Its ionization potential (IP), electron affinity (EA) and band gap were investigated with cyclic voltammetry and found to be consistent with their UV-vis absorption spectral data.

Keywords N-naphthalenyl aminomethyl phenol; organic electroluminescent device; blue light-emitting layer; band gap; cyclic voltammetry

INTRODUCTION

Organic electroluminescent devices (OLED) have been actively developed in recent years and now these devices are in the stage of practical application. While highly efficient green light emission has been achieved with a device containing AlQ_3 as an emitting layer^[1], red and blue light-emitting materials with high efficiency, good color purity

and long-term stability remain yet to be developed for the commercial full color display.

Recently, several boron^[2] or aluminum centered complexes^[3] have been reported as an efficient blue light-emitting layer in OLED. Parallel to these developments, we would like to report herein that bis-(2-(naphthalen-2-yl-aminomethyl)phenolato) beryllium ($\text{Be}(\beta\text{-nap})_2$) is synthesized and applied to OLED as a blue-light emitting layer. Naphthylamine is known to exhibit strong blue fluorescence upon irradiation and thus was employed in this study as a part of the chelating ligand, 2-(naphthalen-2-yl-aminomethyl)phenol ($\beta\text{-napH}$).




FIGURE 1. Synthesis of bis-(2-(naphthalen-2-yl-aminomethyl)-phenolato) beryllium ($\text{Be}(\beta\text{-nap})_2$)

EXPERIMENTAL

The $\beta\text{-napH}$ (mp 150-152 °C) was prepared from condensation reaction of 2-naphthylamine with salicylaldehyde, followed by reduction of the resulting imine with sodium borohydride. $\text{Be}(\beta\text{-nap})_2$ (mp 204-206 °C) was then prepared from reaction of BeSO_4 (4.4mmol) in 100mL water with $\beta\text{-napH}$ (7.3mmol) in 50mL methanol (Figure 1). The resulting precipitate was filtered and washed with water and cold methanol to

yield $\text{Be}(\beta\text{-nap})_2$ in a 75% yield. $\text{Zn}(\beta\text{-nap})_2$ was prepared by the similar procedure described above. The free ligand and the beryllium complex were characterized with UV-vis, ^1H NMR, MS/FAB, photoluminescence (PL) and EL.

RESULTS AND DISCUSSION

Beryllium and zinc complexes were prepared herein from the reaction of Be(II) or Zn(II) ion and $\beta\text{-napH}$. $\text{Be}(\beta\text{-nap})_2$, but not $\text{Zn}(\beta\text{-nap})_2$, was possible to be sublimed and thus subject to vacuum deposition. The UV-vis absorption and photoluminescence(PL) spectra of $\text{Be}(\beta\text{-nap})_2$ were investigated with its thin film on a quartz substrate.

The maximum PL peak of $\text{Be}(\beta\text{-nap})_2$ was observed at 406nm, being close to the PL peak of the free ligand (Figure 2). It was inferred that the naphthylamine moiety which was known to have strong blue fluorescence greatly contributed to blue light emission displayed by the complex and the free ligand. The bandwidth of the complex was found to be narrower than that of the free ligand.




FIGURE 2. UV-vis (dotted line) and PL (solid line) Spectra : (a) $\beta\text{-napH}$, (b) $\text{Be}(\beta\text{-nap})_2$

Cyclic voltammetry of $\text{Be}(\beta\text{-nap})_2$ was also performed with the vacuum deposited sample on glass. This method revealed the IP, EA, and electrochemical gap of $\text{Be}(\beta\text{-nap})_2$, which correspond to its HOMO, LUMO, and band gap, respectively. From these UV-vis absorption edge and cyclic voltammetry results, we found that the optical band gap is in good agreement with the electrochemical gap (Figure 3).

Further studies on fabrication of the electroluminescent device using $\text{Be}(\beta\text{-nap})_2$ as emitting layer are in progress in our laboratory.




FIGURE 3. Cyclic voltammogram of $\text{Be}(\beta\text{-nap})_2$

ACKNOWLEDGEMENT

This work was supported by Korea Research Foundation Grant (KRF-99-005-E00018).

REFERENCES

- [1]. C. W. Tang, S. A. Van Slyke, *Appl. Phys. Lett.*, **51**, 913 (1987).
- [2]. X. T. Tao, H. Suzuki, T. Wada, S. Miyata, H. Sasabe, *J. Am. Chem. Soc.*, **121**, 9447 (1999).
- [3]. L. M. Leung, W. Y. Lo, S. K. So, K. M. Lee, W. K. Choi, *J. Am. Chem. Soc.*, **122**, 5640 (2000).