This article was downloaded by: [University of Kent] On: 14 December 2014, At: 14:08 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



# Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information: <u>http://www.tandfonline.com/loi/gmcl20</u>

# New Liquid Crystalline Stilbene Derivatives Containing 1,2-Dienylalkoxy Chains

Giuseppe Chidichimo <sup>a</sup> , Giovanni De Filpo <sup>a</sup> , Giuseppe Salerno <sup>a</sup> , Lucia Veltri <sup>a</sup> , Bartolo Gabriele <sup>b</sup> & Fiore Pasquale Nicoletta <sup>b</sup>

<sup>a</sup> Dipartimento di Chimica , Università della Calabria , Arcavacata di Rende, Cosenza, Italy

<sup>b</sup> Dipartimento di Scienze Farmaceutiche, Università della Calabria, Arcavacata di Rende, Cosenza, Italy Published online: 22 Sep 2010.

To cite this article: Giuseppe Chidichimo, Giovanni De Filpo, Giuseppe Salerno, Lucia Veltri, Bartolo Gabriele & Fiore Pasquale Nicoletta (2007) New Liquid Crystalline Stilbene Derivatives Containing 1,2-Dienylalkoxy Chains, Molecular Crystals and Liquid Crystals, 465:1, 165-174, DOI: <u>10.1080/15421400701205784</u>

To link to this article: http://dx.doi.org/10.1080/15421400701205784

# PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with

primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms & Conditions of access and use can be found at <u>http://www.tandfonline.com/page/terms-and-conditions</u>



# New Liquid Crystalline Stilbene Derivatives Containing 1,2-Dienylalkoxy Chains

Giuseppe Chidichimo Giovanni De Filpo Giuseppe Salerno Lucia Veltri

Dipartimento di Chimica, Università della Calabria, Arcavacata di Rende, Cosenza, Italy

## Bartolo Gabriele Fiore Pasquale Nicoletta

Dipartimento di Scienze Farmaceutiche, Università della Calabria, Arcavacata di Rende, Cosenza, Italy

New liquid crystalline stilbene derivatives containing 1,2-dienylalkoxy chains 1 (n = 7, 9, 11) have been synthesized and their mesomorphic properties have been measured by polarizing optical microscopy, differential scanning calorimetry, and absorption spectroscopy. The effect of terminal alkoxy chain length and polimerisable function on the mesomorphic behaviour is discussed.

Keywords: electro-optical devices; liquid crystals; stilbenes

## INTRODUCTION

Liquid crystals represent an interesting class of materials for their applications in optics and electro-optics [1,2]. The anisotropic properties of liquid crystals allow them to be easily aligned by an electric or magnetic field, a mechanical action (e.g. shear flow), an alignment agent. The most common alignments are homeotropic and homogeneous, i.e. the liquid crystal directors form, respectively, a  $0^{\circ}$  and  $90^{\circ}$  angle with the normal to the cell substrates. Generally, a preferential direction is obtained by

MIUR, the Italian Ministry for Research and University is acknowledged for financial supports (grants PRIN 2005 and EX-60%).

Address correspondence to Giuseppe Chidichimo, Dipartimento di Chimica, Università della Calabria, Arcavacata di Rende, Cosenza, 87036, Italy. E-mail: chidichi@unical.it

mean of an alignment agent (inorganic layers, Langmuir-Blodgett films, surface gratings, surfactants, lecithins, polyimides, which are coated onto cell substrates) and then it is changed by an electric field with a consequent change of the optical properties of the cell. Recently, it has been investigated the effect of UV or visible light on alignment layers doped with dyes [3] and on the agents bearing chemical groups, which can undergo a *trans* $\rightarrow$ *cis* isomerization [4], a photo-dimerization [4], or UV photo-polymerization [5]. The importance of such an investigation is that the illuminated regions can change their preferential alignment by a light beam and the original alignment can be gained by a subsequent illumination. This light induced alignment change has been attributed to a different dye orientation or to a change of molecular shape. More recently, a great interest has aroused on polymers bearing both liquid crystalline and photo-responsive units [6]. These molecules can be homogeneously oriented by alignment agents owing to the presence of liquid crystalline units. This preferential alignment can be changed via irradiation of photo-responsive groups with a suitable frequency light beam [7]. Such technique has allowed the development of devices with a response time of some microseconds [7]. The synthesis of such interesting polymers has been carried out starting from a polymerizable mixture, which showed mesomorphic behaviour. The mixture in its nematic state was aligned by agents coated on glass supports and then thermopolymerized. The application of UV light allowed a phase transition for the azobenzene pendants from a homogeneous state (characteristic of trans isomers) to an isotropic state (or disordered state, characteristic of *cis* isomers). However, it is known that *cis* isomers of azobenzenes are unstable, so after irradiation they tend to relax to the *trans* form. Another disadvantage in the use of azobenzenes is related to their thermal and photo-chemical degradation with a consequent formation of free radicals, which can destroy the device [8]. On the contrary, it is known that stilbenes are thermally and photochemically more stable than molecules bearing azobenzene groups. In fact, their relaxation back to the original *trans* form can be achieved only by irradiating the cells with a light beam at a different frequency [9]. In the framework of our continous interest for the development of high quality liquid crystalline



FIGURE 1 Molecular structures of synthesized molecules.

monomers bearing photo-responsive units, we have recently reported the synthesis of new liquid crystalline monomers for cationic polymerization, consisting of stilbene derivatives containing vinyloxyalkoxy chains [10]. We now wish to report the synthesis and the study of mesomorphic properties of a novel class of liquid crystalline stilbene derivatives **1** (see Fig. 1), bearing a dienyl function suitable for radical polymerization. This kind of polymerization may result more indicated than others for the growth of aligned polymer as thin films.

#### **EXPERIMENTAL**

#### Methods

The transition temperatures and phase assignments were determined with a Leitz Laborlux 12 POL polarizing optical microscope in conjunction with a Linkam TH600 hot stage. The observed textures were compared with those reported in the literature [11]. The enthalpies of transitions were measured by differential scanning calorimetry using a Netzsch 2000-T4 calorimeter with a heating-cooling rate of  $10^{\circ}$ C min<sup>-1</sup>.

An evaluation of the homogeneous alignment of compounds 1 and 2 (Fig. 2) was performed by filling glass cells (5  $\mu$ m thick, anti-parallel polyimide coating, Linkam) with compounds 1 and 2 in their nematic state and measuring the transmittance of the polarized probing He-Ne beam as a function of the rotational angle  $\phi$  for the cross configuration of the polarizer and analyzer (see Fig. 3).

Photo-isomerisation of compounds **1** was monitored by UV-VIS absorption spectroscopy with a Yasco 550 V spectrometer as a function of energy supplied at 340 nm and 260 nm by a 200 W high-pressure mercury lamp.



FIGURE 2 Synthesis of compounds 1.



LIGHT BEAM IN

**FIGURE 3** Experimental set up. **P**, polarizer; **A**, analyzer, **n**, easy axis for homogeneous alignment;  $\phi$ , tilt angle.

#### Synthesis

All compounds **1** were synthesized according to the general route shown in Figure 2, involving the following steps: (a) Wittig reaction between (4-cyanobenzyl)triphenylarsonium bromide and *O*-protected 4-hydroxybenzaldehyde, followed by deprotection to give 4-[2-(4-hydroxyphenyl)vinyl]benzonitrile; (b) Williamson reaction between the latter and the appropriate bromoalcohol to give alcohols **2**; (c) Swern oxidation [12] of **2** to aldehydes **3**; (d) Wittig reaction between the latter and allyltriphenylarsonium bromide. We have already reported the synthesis of compounds **2** with n = 7, 9, and 11, which showed liquid crystalline behaviour [10]. In the present work, we have also synthesized compound **2** with n = 6, which also shows a liquid crystalline phase.

All reactions were analyzed by TLC on silica gel 60  $F_{254}$  or by GLC using a Shimadzu GC-14A gas chromatograph and capillary columns with polymethylsilicone + 5% phenylsilicone as the stationary phase (HP-5). Column chromatography was performed on silica gel 60 (Merck, 70–230 mesh). Starting triphenylarsine, 4-cyanobenzyl bromide, 4-hydroxybenzaldehyde, 3,4-dihydro-2*H*-pyran, hexane-1,6-diol, heptane-1,7-diol, nonane-1,9-diol, 11-bromoundecan-1-ol, oxalyl chloride, allyl bromide were commercially available and were used without further purification. 4-(Tetrahydropyran-2-yloxy)benzaldehyde [13], 6-bromohexan-1-ol [14], 7-bromoheptan-1-ol [14], 9-bromononan-1-ol [14], (4-cyanobenzyl)triphenylarsonium bromide [10], 4-[2-(4-hydroxyphenyl)vinyl]benzonitrile [10], (*E*)-4-{2-[4-( $\omega$ -hydroxyalkyloxy)) phenyl]vinyl}benzonitrile derivatives **2** (n = 7, 9, 11) [10], and allyltriphenylarsonium bromide [15] were prepared according to

literature procedures. (*E*)-4-{2-[4-(6-hydroxyhexyloxy)phenyl]vinyl}benzonitrile (n = 6, 70%) was prepared according to the general procedure reported in ref. 10, and purified by column chromatography on silica gel using  $CH_2Cl_2$  as eluent.

#### General Procedure for Swern Oxidation of Derivatives 2 to 4-{2-[4-( $\omega$ -Oxoalkyloxy)Phenyl]Vinyl}Benzonitrile Derivatives 3

A solution of DMSO (5.8 mL) in anhydrous  $CH_2Cl_2$  (97 mL) was added drop wise under nitrogen to a cooled ( $-78^{\circ}C$ ), mechanically stirred solution of oxalyl chloride (3.5 mL) in anhydrous  $CH_2Cl_2$  (97 mL). After a few minutes, a solution of **2** (20.5 mmol) in anhydrous  $CH_2Cl_2$  (70 mL) was added drop wise and the mixture was allowed to stir for additional 40 min. at  $-78^{\circ}C$ . After the addition of Et<sub>3</sub>N (14.3 mL), the mixture was allowed to warm to rt, water was added and phases were separated. The aqueous layer was extracted with  $CH_2Cl_2$ , and the collected organic phases were washed several times with water and brine and eventually dried over  $Na_2SO_4$ . After elimination of the solvent by rotary evaporation, crude products were purified by column chromatography on silica gel using as eluent 9:1  $CHCl_3/hexane$  (n = 6, 82%), 9:1  $CH_2Cl_2/hexane$  (n = 7, 75%); 9:1  $CHCl_3/hexane$  (n = 9, 72%); 9:1  $CHCl_3/hexane$  (n = 11, 87%).

#### General Procedure for the Preparation of 4-{2-[4-(Dienylalkoxy)Phenyl]Vinyl}Benzonitrile Derivatives 1

The method of Tewari [16] was employed. To a stirred suspension of NaOH (32 mg, 1.3 mmol) in anhydrous THF (30 mL) was added under nitrogen allyltriphenylarsonium bromide (555 mg, 1.3 mmol). After additional stirring at rt for 0.5 h, **3** (1.3 mmol) was added and the resulting mixture was allowed to stir at rt for 48 h. After acidification with 0.1 N HCl (7 mL), CHCl<sub>3</sub> was added and phases were separated. The aqueous layer was extracted with CHCl<sub>3</sub>, and the collected organic phases were dried over CaCl<sub>2</sub>. After elimination of the solvent by rotary evaporation, crude products were purified by column chromatography on silica gel using as eluent 9:1 CHCl<sub>3</sub>/hexane (n = 6, 35%); 8:2 CHCl<sub>3</sub>/hexane (n = 7, 42%); 7:3 CHCl<sub>3</sub>/hexane (n = 9, 53%); 6:4 CHCl<sub>3</sub>/hexane (n = 11, 49%).

#### Chemical Characterization of Representative Products

All products were fully characterized by spectroscopic techniques and elemental analysis. Here we report data for compounds 1, and 3 with n = 9.

Melting points were determined on a Reichert Thermovar melting point apparatus and are uncorrected. Elemental analyses were carried out with a Carlo Erba Elemental Analyzer Mod. 1106. <sup>1</sup>H NMR and <sup>13</sup>C NMR spectra were taken on a Bruker AC300 spectrometer and run on CDCl<sub>3</sub> solutions with Me<sub>4</sub>Si as internal standard and recorded at 300 MHz and 75 MHz, respectively. Chemical shifts and coupling constants (*J*) are given in ppm ( $\delta$ ) and in Hz, respectively. IR spectra were taken on a Perkin-Elmer Paragon 1000 PC FT-IR spectrometer.

# 4-[2*E*-(Dodeca-9*E*,11-Dienyloxyphenyl)Vinyl]Benzonitrile 1 (n = 9)

Colourless solid. IR (KBr) 2925 (m), 2853 (m), 2224 (m), 1598 (s), 1513 (m), 1251 (s), 1173 (m), 833 (m), 757 (m), 556 (m) cm<sup>-1; 1</sup>H NMR (CDCl<sub>3</sub>)  $\delta$ 7.64–7.59 (m, 2 H aromatic), 7.57–7.52 (m, 2 H aromatic), 7.49–7.43 (m, 2 H aromatic), 7.17 (distorted d, J 16.1, 1 H, =CHAr), 6.99–6.87 (m, 3 H, aromatic + =CHAr), 6.31 (dt, J 17.1, 10.3, 1 H dienic), 6.11–5.99 (m, 1 H dienic), 5.77–5.65 (m, 1 H dienic), 5.08 (dd, J 17.1, 1.5, 1 H, =CHH), 4.98–4.92 (m, 1 H, =CHH), 3.98 (t, J 6.6, 2 H, OCH<sub>2</sub>), 2.13–2.03 (m, 2 H, CH<sub>2</sub>), 1.85–1.74 (m, 2 H, CH<sub>2</sub>), 1.52–1.24 (m, 10 H, 5 CH<sub>2</sub>); <sup>13</sup>C NMR (CDCl<sub>3</sub>)  $\delta$ 159.7, 142.3, 137.3, 135.5, 132.5, 132.1, 130.9, 129.2, 128.9, 128.2, 126.5, 124.4, 119.1, 114.9, 114.6, 68.1, 32.5, 29.4, 29.3, 29.22, 29.16, 29.12, 26.0. Anal. Calcd for C<sub>27</sub>H<sub>31</sub>NO: C, 84.11; H, 8.10; N, 3.63. Found C, 84.02; H, 8.12; N, 3.61.

### 4-{2E-[4-(9-Oxononyloxy)Phenyl]Vinyl}Benzonitrile 3 (n = 9)

Colourless solid, mp 128–129°C. IR (KBr) 2927 (m), 2859 (m), 2225 (m), 1709 (s), 1598 (s), 1513 (s), 1467 (w), 1255 (s), 1215 (s), 1174 (s), 1023 (w), 839 (s), 555 (m) cm<sup>-1; 1</sup>H NMR (CDCl<sub>3</sub>)  $\delta$ 9.76 (t, J 2.0, 1 H, CHO), 7.61–7.56 (m, 2 H aromatic), 7.55–7.49 (m, 2 H aromatic), 7.48–7.41 (m, 2 H aromatic), 7.15 (distorted d, J 16.1, 1 H, =CH), 6.93–6.86 (m, 2 H aromatic), 6.92 (distorted d, J 16.1, 1 H, =CH), 3.96 (t, J 6.6, 2 H, OCH<sub>2</sub>), 2.42 (td, J 7.3, 2.0, 2 H, CH<sub>2</sub>CHO), 1.85–1.72 (m, 2 H, CH<sub>2</sub>), 1.69–1.57 (m, 2 H, CH<sub>2</sub>), 1.52–1.29 (m, 8 H, 4 CH<sub>2</sub>); <sup>13</sup>C NMR (CDCl<sub>3</sub>)  $\delta$ 202.8, 159.7, 142.3, 132.4, 132.0, 128.9, 128.3, 126.5, 124.4, 119.1, 114.8, 110.0, 68.0, 43.9, 29.26, 29.18, 29.14, 29.07, 26.0, 22.0. Anal. Calcd for C<sub>24</sub>H<sub>27</sub>NO<sub>2</sub>: C, 79.74; H, 7.53; N, 3.87. Found C, 79.85; H, 7.51; N, 3.88.

#### **RESULTS AND DISCUSSION**

We have synthesized compounds 1 with n = 6, 7, 9, 11. The transition temperatures and enthalpy changes of compounds 1 are reported in

**TABLE 1** Transition Temperatures/°C and Enthalpy Changes  $()/Jg^{-1}$  for Compounds 1 with different Alkoxy chain length, n. Cr, Crystal; Sm A, Smectic A phase; N, nematic phase; I, isotropic phase

6	Cr 107.2 (100.6) I
7	Cr 47.7 (17.9) N 50.9 (14.6) I
9	Cr 48.8 (24.2) N 74.8 (10.1) I
11	Cr 81.0 (15.8) SmA 127.8 (42.5) N 134.7 (21.1) I

Table 1. All compounds 1 with an alkoxy chain length larger than 6 exhibit a nematic phase. The absence of mesomorphism for n = 6 can be attributed to the fact that a short chain length does not give enough lateral cohesion. Compounds with a long alkoxy chain length (n = 9, n = 11) show a large mesomorphic range. This is because the lateral intermolecular cohesions increase with increasing alkoxy chain lengths stabilising in such a way the mesophases. A long chain length (n = 11) stabilizes a smectic A phase, too. It is important to note that even precursors 2 show liquid crystalline behaviour. The transition temperatures and enthalpy changes of compounds 2 with n = 5, 7, 9, and 11 have already been reported [10]. The transition temperatures and enthalpy changes of compounds 2 with n = 2, 3 and 6 are shown in Table 2 (results for n = 5, 7, 9, and 11 are included for completeness). All compounds 2 show a nematic phase. Compound 2 with n = 5 also shows a smectic A phase.

The evaluation of the homogeneous alignment of **1** gave a repeated pattern of valleys and peaks with a typical separation of 90° (see Fig. 4). This confirms that cells are well homogeneously aligned. It is known that stilbenes show appreciable absorption in the solar spectral region. UV spectra and changes induced by the indicated periods of irradiation at 340 nm are shown in Figure 5 for  $n = 11 (0.1 \text{ M in CHCl}_3 \text{ at } 25^{\circ}\text{C}$ , quantum yield 0.21).

Before illumination all samples consisted of only the *trans* form of the stilbene derivative, because this isomer is thermodynamically

**TABLE 2** Transition Temperatures/°C and Enthalpy Changes  $()/Jg^{-1}$  for compounds 2 with different Alkoxy Chain Length, n. Cr, crystal; Sm A, smectic A phase; N, nematic phase; I, isotropic phase

2	Cr 166.1 (68.7) N 170.5 (50.1) I
3	Cr 86.9 (49.6) N 100.3 (17.3) I
5	Cr 88.8 (40.4) SmA 94.9 (53) N 104.8 (17.7) I
6	Cr 127.9 (20.0) N 131.0 (84.7) I
7	Cr 83.4 (46.4) N 91.3 (28.7) I
9	Cr 91.0 (79.2) N 98.4 (33.0) I
11	Cr 98.2 (36.3) N 101.2 (67.5) I



**FIGURE 4** Repeated pattern of valleys and peaks in homogeneously aligned compound 1 (n = 11).



**FIGURE 5** Changes in the UV spectra for compound 1 (n = 11) induced by irradiation at 340 nm for different time intervals. Dotted line represents the UV spectra of compound after 5 minutes of irradiation at 260 nm.

more stable than its *cis* form. Upon illumination with UV light (340 nm), all compounds **1** clearly undergo a photo-transformation to the *cis* isomer in an almost complete manner. No by-products were formed in this process, as confirmed by TLC and NMR (CDCl<sub>3</sub>) analysis. The photo-transformation is manifest by the decreasing intensities of  $\pi \rightarrow \pi^*$  absorptions at 340 nm. No thermal back reaction to *trans* isomers was found in agreement with literature [14]. Upon irradiation with UV light at 260 nm for 5 minutes, we observed the relaxation back to the initial state as shown by the dotted curve in Figure 5.

The photo-isomerization was also confirmed by photo-irradiation of aligned thin cells. In fact, if a UV beam (340 nm) impinged on a homogeneously aligned sample in its nematic phase we observed, by using the experimental set up described in Figure 3, a phase transition to the isotropic state, due to the fact that the *cis* isomers are no longer liquid crystalline. As shown in Figure 6, the depolarized light intensity decreases a lot as a function of irradiation time. If such a cell is afterwards irradiated with a 260 nm light beam, one can induce a relaxation back to the *trans* form with a consequent increase of scattered light.

These experiments confirm the potential use of stilbene molecules as information processing and data storage materials.



**FIGURE 6** Depolarized light scattering behaviour for compound 1 (n = 11) as a function of UV irradiation at 340 nm and 260 nm.

### CONCLUSIONS

We have successfully synthesised a novel type of liquid crystalline stilbene molecules having a dienyl function suitable for radical polymerization. All compounds with a rather long alkoxy chain (n > 6) show a nematic phase. The temperature range of mesomorphism is rather large for long alkoxy chain lengths. Further investigation is now in progress to polymerize the obtained homogeneously aligned films and to study their optical response to a light beam.

#### REFERENCES

- Chandrasekar, S. (1992). Liquid Crystals, 2nd edition, Cambridge University Press: New York, USA.
- [2] De Gennes, P. G. & Prost, J. (1993). The Physics of Liquid Crystals, 2nd edition, Clarendon: Oxford, UK.
- [3] Gibbons, W. M., Shannon, P. J., Sun, S.-T., & Swetlin, B. J. (1991). Nature, 351, 49.
- [4] Ichimura, K., Suzuki, Y., Seki, T., Hosoki, A., & Aoki, K. (1988). Langmuir, 4, 1214;
  Ichimura, K. (2000). Chem. Rev., 100, 1847; Matsunaga, D., Tamaki, T., &
  Ichimura, K. (2003). J. Mater. Chem., 13, 1558.
- [5] Li, Z. (1995). Liq. Crystals, 19, 307.
- [6] Ikeda, T., Kurihara, S., Karanjit, D. B., & Tazuke, S. (1990). Macromolecules, 23, 3938; Hasegawa, M., Yamamoto, T., Kanazawa, A., Spiono, T., & Ikeda, T. (1999). Chem. Mater., 361, 428.
- Kurihara, S., Sakamoto, A., & Nonaka, T. (1998). Macromolecules, 31, 4648;
  Kurihara, S., Sakamoto, A., Yoneyama, D., & Nonaka, T. (1999). Macromolecules, 32, 6493;
  Kurihara, S., Yoneyama, D., & Nonaka, T. (2001). Chem. Mater., 13, 2807.
- [8] Barton, D., Hodgett, M., Skirving, P., Whelton, M., Winter, K., & Vardy, C. (1983). Can. J. Chem., 61, 1712.
- [9] Zaplo, O., Stumpe, J., Seeboth, A., & Hermel, H. (1992). Mol. Cryst. Liq. Cryst., 213, 153; Ichimura, K., Tommita, H., & Kudo, K. (1995). Mol. Cryst. Liq. Cryst., 267, 381; Ichimura, K., Tommita, H., & Kudo, K. (1996). Liq. Crystals, 20, 161.
- [10] Chidichimo, G., Gabriele, B., Nicoletta, F. P., Salerno, G., & Veltri, L. (2004). Liq. Crystals, 31, 733.
- [11] Demus, D. & Richter, R. (1978). Textures of Liquid Crystals, Verlag Chemie: Weinheim, Germany; Gray, G.W. & Goodby, J. W. (1984). Smectic Liquid Crystals: Textures and Structures, Heyden: Philadelphia, USA.
- [12] Clyne, D. S. & Weiler, L. (1999). Tetrahedron, 55, 13659.
- [13] Artico, M., Di Santo, R., Costi, R., Novellino, E., Greco, G., Massa, S., Tramontano, E., Marongiu, M. E., De Montis, A., & La Colla, D. (1998). J. Med. Chem., 41, 3948.
- [14] Baldwin, J. E., Adlington, R. M., & Ramcharitar, S. H. (1992). *Tetrahedron*, 48, 3413.
- [15] Ousset, B., Mioskowski, C., & Solladie, G. (1983). Tetrahedron Lett., 24, 4419.
- [16] Kumari, N., Kendurkar, P. S., & Tewari, R. S. (1975). J. Organomet. Chem., 96, 237.