ORIGINAL PAPER



A domino electro-oxidative synthesis of 3,3'-bis(indolyl)methane nanoparticles

Kobra Nikoofar¹ · Khadijeh Ghanbari¹

Received: 16 January 2015/Accepted: 11 May 2015 © Springer-Verlag Wien 2015

Abstract An effective route for electro-oxidative synthesis of 3,3'-bis(indolyl)methane nanoparticles has been described via a domino multi-component reaction between various alcohols and indole derivatives in an undivided cell under constant potential conditions in CH₃CN at room temperature. The mechanistic aspect of this electro-oxidative condensation has also been studied by UV–Vis spectra and cyclic voltammograms. The nanostructure of the products has been confirmed by scanning electron microscopy.

Graphical abstract



Keywords Alcohols · Electrosynthesis · Electro-oxidation · Indole · Condensation

Electronic supplementary material The online version of this article (doi:10.1007/s00706-015-1496-6) contains supplementary material, which is available to authorized users.

Kobra Nikoofar kobranikoofar@yahoo.com

> Khadijeh Ghanbari kh_ghanb@yahoo.com

Introduction

Indole and its derivatives have attracted so much interest in the recent century owing to their extensive biological activities [1]. Bis(indolyl)methanes (BIMs) are one of the most important groups of indole derivatives that are found in cruciferous plants and marine sources [2]. These compounds have shown different pharmaceutical activities such as anticancer [3], antihyperglycemic, antiviral, and antimicrobial [4], and antioxidant [5] properties. They are also known as a promoter of estrogen metabolism [6] and induce apoptosis in human cancer cells [7]. Therefore, the synthesis of these moieties has received much attention during the last years.

A simple and direct method for the synthesis of BIMs is the condensation of indole with the carbonyl groups. In this manner, the reaction of indole with aldehydes or ketones produces azafulvenium salts that react further with a second indole molecule to form bis(indolyl)methanes [8]. On the basis of this general protocol, various Bronsted acids [9, 10], protic acids [11–13], Lewis acids [14–19], heterogeneous acidic catalysts [20–23], ionic liquids [24– 26], and *N*-haloorganocatalysts [27, 28] have been applied for this synthesis. Although a vast range of procedures has been utilized for BIM preparation via the condensation of indoles with carbonyls, reports of oxidative condensation of alcohols with indoles are rare [29, 30].

In spite of the applicability of the reported protocols, most of them suffer from one or more drawbacks including long reaction times, low yields of products, harsh reaction conditions, and use of expensive and/or toxic catalysts and solvents. Therefore, there is still a strong demand for a mild, clean, and highly efficient procedure for one-pot multi-component transformations for BIM synthesis.

Electrochemical organo-synthetic methods have received significant attention because of their benefit to the

¹ Chemistry Department, School of Physics and Chemistry, Alzahra University, Vanak, Tehran, Iran





environment. In these procedures, cleanly generated electricity acts as a "green" catalyst. Among electrochemical synthesis of various organic compounds reported in the literature [31-36], few are dependent on electro-catalytic multi-component condensations [37–39].

1a-1i

Nanosized organic compounds have been prepared through different methods in which organic compounds are first synthesized and then can be transformed into nanosized particles using modern high technology such as ultrahigh pressure rapid expansion of supercritical solutions (RESS) system [40] and hydrocortisone using supercritical antisolvent with enhanced mass transfer [41]. Direct synthesis of nanosized organic compounds is a rarely used method.

On the basis of our research activity about indole derivatives [42-47], we herein report a mild and efficient procedure for the one-pot domino electro-oxidative condensation of alcohols 1a-1i and indoles 2a, 2b via controlled-potential coulometry in an undivided cell, in the presence of LiClO₄ as electrolyte in CH₃CN at room temperature to yield the nanoparticles of the corresponding 3,3'-di(indolyl)methanes 3a-3k (Scheme 1).

Results and discussion

The electrochemical study of 1 mmol solution of 4-chlorobenzyl alcohol (1e) in CH₃CN containing 0.05 g LiClO₄ at a glassy carbon electrode was performed by cyclic voltammetry (Fig. 1). The voltammogram shows one anodic peak (A_1) and one cathodic peak (C_1) at 2.0 and -0.6 V versus SCE which correspond to the oxidation of 4-chlorobenzyl alcohol (1e) to 4-chlorobenzaldehyde (Scheme 2A) and the reduction of anodically generated 4-chlorobenzaldehyde from 4-chlorobenzyl alcohol (1e), respectively.

Controlled-potential coulometry was applied in a solution containing 1 mmol of 4-chlorobenzyl alcohol (1e) at the potential of peak A_1 . Monitoring of the electrolysis progress was carried out by TLC and cyclic voltammetry (Fig. 2). It was observed that, proportional to the advancement of coulometry, the height of A_1 decreases. The anodic peak A1 disappears when the charge



Fig. 1 Cyclic voltammogram of 1 mmol of 4-chlorobenzyl alcohol (1e) at the glassy carbon electrode, in CH₃CN (40 cm³) containing 0.05 g LiClO₄ at the scan rate of 100 mV s⁻

consumption reaches about 2e⁻ per molecule of 1e (Fig. 2, inset). This number of electrons confirms the oxidation of 4-chlorobenzyl alcohol (1e) to 4-chlorobenzaldehyde.

In the next step, electro-condensation was followed by the addition of indoles 2a, 2b to the reaction cell alternatively. Voltammetric behaviors of 1 mmol 4-chlorobenzaldehyde (curve 3a), 2 mmol indole (2a) (curve 3b), and 1 mmol 4-chlorobenzyl aldehyde in the presence of 2 mmol indole (2a) (curve 3c), are shown in Fig. 3. The cyclic voltammogram observed for indole indicated one anodic peak (A_1) and one cathodic peak (C_1) at 1.25 and -0.87 V, respectively (curve 3b), that are related to the oxidation and reduction of indole, respectively. The voltammogram for 4-chlorobenzaldehyde in the presence of indole (2a) (curve 3c) shows two anodic peaks (A_2, A_3) and one cathodic peak (C_3) . The new peak couple (A_3/C_3) corresponds to the reaction between 4-chlorobenzaldehyde in the presence of indole (2a). The negative shift of peak A_2 in the presence of 4-chlorobenzaldehyde is due to the reactivity of the electrochemically generated product 3e which has formed a thin film on the surface of the electrode.

Controlled-potential coulometry was performed in a CH₃CN solution (40 cm³) containing 4-chlorobenzaldehyde (1 mmol) in the presence of indole (2a, 2 mmol) at -0.9 V versus SCE. Electrolysis progress was monitored









Fig. 2 Cyclic voltammograms of 1 mmol 4-chlorobenzyl alcohol (**1e**) at the glassy carbon electrode, in CH₃CN (40 cm³) containing 0.05 g LiClO₄, during controlled-potential coulometry at 2.0 V versus SCE. After consumption of: *a* 0, *b* 10, *c* 25, *d* 45, *e* 65, and *f* 80 C. *Inset* variation of peak current I_p versus charge consumed at the scan rate 100 mVs⁻¹

by cyclic voltammetry and TLC (Fig. 4). As Fig. 4 shows, proportional to the advancement of coulometry, the cathodic peak (C_1) decreases and disappears when the charge consumption reaches about $1e^-$ per molecule of



Fig. 3 Cyclic voltammograms of: *a* 4-chlorobenzaldehyde (1 mmol), *b* indole (2 mmol), *c* a mixture of 4-chlorobenzaldehyde/indole (1/ 2 mol ratio) at the glassy carbon electrode in acetonitrile (40 cm³) containing 0.05 g LiClO₄ with the scan rate of 100 mV s⁻¹

indole. These observations allow us to propose the mechanism illustrated in Scheme 2.

Additionally, the effect of the scan rate on the electrochemical behavior of 4-chlorobenzaldehyde in the presence of indole (**2a**) was investigated (Fig. 5). It can be observed that proportional to the augmentation of potential sweep rate, the height of peak C₃ increases. On the other hand, the current function for peak A₂ $(I_p^{A_2}/v^{1/2})$, changes only



Fig. 4 Cyclic voltammograms of 2 mmol indole (**2a**) at the glassy carbon electrode, in CH₃CN (40 cm³) containing 0.05 g LiClO₄, during controlled-potential coulometry at -0.9 V versus SCE, after consumption of: *a* 0, *b* 20, *c* 40, *d* 70, *e* 95, *f* 120, *g* 150, and *h* 180 C. *Inset* variation of peak current $I_p^{C_1}$ versus charge consumed at the scan rate 100 mVs⁻¹



Fig. 5 Typical voltammograms of a mixture of 4-chlorobenzaldehyde (1 mmol) in the presence of indole (**2a**) (2 mmol) at the glassy carbon electrode, in CH₃CN (40 cm³) containing 0.05 g LiClO₄, at different scan rates ($a \rightarrow i$): 25, 50, 75, 100, 125, 150, 200, 250, 300 mV s⁻¹. *Inset* variation of peak current function ($I_p^{A_2}/v^{1/2}$) vs. scan rate

slightly with the increase in scan rate (Fig. 5, inset). Such behavior is taken as indicative of an EC mechanism [48, 49].

Subsequently, oxidative condensation reaction between various alcohols and indole derivatives was performed. All the tests were carried out in a domino condition in which, at the first step, alcohols were added to the cell where they electro-oxidized to their corresponding aldehyde. Electrocondensation was followed by the addition of indoles to the reaction cell alternatively. The prepared products and reaction conditions are summarized in Table 1.

According to Table 1, benzvl alcohol (1a) and its electron-donating derivatives p-methyl-, p-methoxy-, and ohydroxybenzyl alcohols (1b-1d) and also electron-deficient *p*-chloro-, *p*-nitro-, and *o*-nitro derivatives (**1e**-**1g**) react with indole (2a) in high yields. The results confirmed the regioselectivity in electro-oxidation; as in the case of o-hydroxybenzyl alcohol (1d), any oxidation of its hydroxyl moiety was observed (Table 1, entry 4). In order to survey the efficacy of the method, the domino electro-oxidative condensation of 1-propanol (1h) as an aliphatic alcohol model and cinnamyl alcohol (1i) as an example of an allylic derivative were also performed with indole successfully (Table 1, entries 8, 9). The study also revealed the slower condensation of aliphatic alcohol with indole rather than this reaction between allylic alcohol and indole. It may depend on the greater reactivity of allylic alcohols. 2-Methylindole (2b), as another indolic alternative was also utilized for the domino electro-oxidative condensation with p-methyl and pchlorobenzyl alcohols. The results (Table 1, entries 10, 11) obtaining the 3.3'-di(inconfirm corresponding dolyl)methanes successfully. The high yields of the reactions present the domino-cascaded electro-oxidative condensation method as an efficient and eco-friendly protocol as a multicomponent condensation reaction.

The SEM image of 3,3'-bis(1*H*-indol-3-yl)-(4-chlorophenyl)methane (**3e**) shown in Fig. 6, reveals that the nanoparticle morphology has been created. The average diameter of the nanoparticles of **3e** is 35–50 nm.

Coulometry, voltammetry, and structural observations allow us to propose the pathway shown in Scheme 2 for the electrochemical synthesis of di(indolyl)methane derivatives 3a-3k.

Although the comprehensive mechanism of the reaction is not known, the following rationalization may be worthwhile to explain the product (**3a**) formation (Scheme 2). In the first step of the domino reaction (Scheme 2A), the oxidation of benzyl alcohol (**1a**) at the anode yields benzaldehyde (**4**). By the further addition of indole (**2a**) to the reaction medium (Scheme 2B), indole anion **5** was created via cathodic electron absorbance. Nucleophilic attacks of **5** to the carbonyl moiety of **4** yield intermediate **6**. This intermediate stabilizes with an H-shift and converts to intermediates **7a** and **7b**. Releasing the hydroxyl anion, along with a nucleophilic attack of another indole anion **5**, gives rise to intermediate **8**. Finally, the protonation of **8** by the in situ produced H⁺ form hydroxyl oxidation at the anode followed by rearrangement creates product **3a**.

In order to further survey the illustrated mechanism, timedependent absorption spectra of a mixture of 4-chlorobenzaldehyde (1 mmol) and indole (**2a**) (2 mmol) in CH₃CN (40 cm³) containing 0.05 g LiClO₄ were collected during a controlled-potential coulometry experiment (Fig. 7). These spectra show that, as the coulometry experiment proceeds, absorption peaks with a λ_{max} at 500 nm appears and its height

Entry	R^1	\mathbb{R}^2	Product	Yield ^a /%	Observed m.p./°C	Lit. m.p./°C
1	C ₆ H ₅	Н	3 a	90	121–123	123–125 [19]
2	<i>p</i> -MeC ₆ H ₄	Н	3b	90	97–99	95–97 [23]
3	<i>p</i> -MeOC ₆ H ₄	Н	3c	85	190–192	190–192 [<mark>19</mark>]
4	o-HOC ₆ H ₄	Н	3d	70	256-258	259-261 [20]
5	p-ClC ₆ H ₄	Н	3e	85	74–76	78-80 [21]
6	$p-NO_2C_6H_4$	Н	3f	75	229-231	229–223 [19]
7	o-NO ₂ C ₆ H ₄	Н	3g	60	106-108	112–114 [20]
8	C_3H_7	Н	3h	60	78–79	77–79 [42]
9	C ₆ H ₅ CH=CH	Н	3i	90	96–98	92–94 [42]
10	<i>p</i> -MeC ₆ H ₄	CH ₃	3ј	85	173–175	174–176 [<mark>24</mark>]
11	p-ClC ₆ H ₄	CH ₃	3k	90	146–147	145–147 [42]

Table 1 Electro-oxidative synthesis of di(indolyl)methane derivatives 3a-3k via the reaction of alcohols 1a-1i with indoles 2a, 2b

^a Isolated yields



Fig. 6 The SEM image of 3,3'-bis(1H-indol-3-yl)(4-chlorophenyl)-methane (3e)

increases. This peak belongs to $n \to \pi^*$ absorption of product **3e**. The bands between 300 and 400 nm also relate to $\pi \to \pi^*$ transitions of the highly conjugated BIM **3e**. Growth of the peak intensity during the time interval, which is a proof of the product formation, could be a confirmation for the proposed mechanism depicted in Scheme 2.

According to the above observations, the presented mechanism is quite substantive. The CV spectra affirm the key role of the electrosynthetic protocol for BIM preparation under the above-mentioned conditions.

Conclusion

In conclusion, the cascaded electro-oxidative domino condensation of alcohols and indoles to afford the corresponding 3,3'-bis(indolyl)methanes has been performed. This direct environmentally friendly electrosynthesis of nanosized 3,3'-bis(indolyl)methanes via multi-component condensation shows highlighted advantages over



Fig. 7 Absorption spectra of the mixture of 4-chlorobenzaldehyde and indole (2a) during controlled-potential coulometry at -0.9 V vs. SCE in CH₃CN containing 0.05 g LiClO₄. After consumption of: 0, 20, 40, 70, 95, 120, and 150 C. *Inset* absorption spectra of 1 mmol/CH₃CN (40 cm³) of (I) 4-chlorobenzaldehyde, (II) indole (2a), and (III) 3,3'-bis(1*H*-indol-3-yl)(4-chlorophenyl)methane (3a)

conventional chemistry, such as (a) in situ generation of the nano-sized products without further preparation procedures; (b) avoidance of using a Lewis, Bronsted, and/or protic acid catalyst; (c) a one-pot domino MCR affording excellent yields under mild conditions, and (d) avoiding the use of polluting or hazardous chemicals and toxic reagents. These noteworthy points make the method a green, convenient, and efficient method in organic transformations.

Experimental

Electrochemical measurements were performed by an electrochemical system analyzer (Sama Instruments, Iran). The working electrode used in the voltammetry

experiments was a glassy carbon disc $(1.8 \text{ mm}^2 \text{ area})$ and platinum wire was used as a counter electrode. The working electrode used in controlled-potential coulometry and macroscale electrolysis was an assembly of three carbon rods (8 mm diameter and 4 cm length) and a large platinum gauze $(3 \times 3 \text{ cm}^2)$ constituted the counter electrode. The working potentials have been measured versus standard calomel electrode (SCE) as a reference electrode (all electrodes were obtained from Azar Electrode, Urmia, Iran). Melting points were determined using a Stuart Scientific SMP2 capillary apparatus. IR spectra were recorded from KBr discs on Shimadzu IR-435. ¹H NMR spectra were recorded with a Bruker DRX-500 spectrometer. Mass spectra were obtained on Platform II spectrometer from Micromass; EI mode at 70 eV. Preparative layer chromatography (PLC) carried out on $20 \times 20 \text{ cm}^2$ plates, coated with a 1 mm layer of Merck silica gel PF₂₅₄, prepared by applying the silica as slurry and drying in air. The scanning electron microscope (SEM, model Σ -IJMA) was used to characterize the nano-structures. The alcohols, indoles, and solvents were purchased from Merck, Aldrich, and Alfa Aesar and used without further purification.

General procedure for the domino electro-oxidative condensation of indoles with alcohols

А 40 cm³ acetonitrile solution of alcohols **1a–1i** (1 mmol) in LiClO₄ (0.05 g) was electrolyzed at the 2.0 V versus SCE. After completion of the electro-oxidation of alcohols to their corresponding aldehydes, indoles 2a, 2b (2 mmol) were added and electrolyzed at -0.9 V versus SCE. In the two mentioned stages, electrosynthesis reactions were done in an undivided cell equipped with graphite rods as the cathode and Pt-anode at room temperature. The electrolysis was terminated when the current decreased by more than 95 %. A magnetic stirrer was employed during the electrolysis. The process was interrupted several times during the electrolysis and the graphite rod was washed in acetone in order to reactivate it. After completion of the electrocondensation, the solvent was evaporated and the resulting crude product was purified by preparative thinlayer chromatography on silica gel (eluent: n-hexane-EtOAc, 4:1) to afford 3,3'-di(indolyl)methanes **3a**-**3k**. All the products were characterized by comparison of their melting points and also spectroscopic data (IR, ¹H NMR and mass spectra) with those of the authentic samples in literature.

Acknowledgments The authors express their gratitude for financial support from Alzahra University.

References

- 1. Sundberg RJ (1996) The chemistry of indole. Academic Press, New York, p 113
- 2. Bell R, Carmeli S, Sar N, Vibrindole A (1994) J Nat Prod 57:1587
- Hong C, Firestone GL, Bjeldance LF (2002) Biochem Pharmacol 63:1085
- 4. Hibino S, Choshi T (2001) Nat Prod Rep 18:66
- Shirinzadeh H, Eren B, Gurer-Orhan H, Suzen S, Özden S (2010) Molecules 15:2187
- 6. Zeligs MA (1998) J Med Food 1:67
- 7. Ge X, Yannai S, Rennert G, Gruener N, Fares FA (1996) Biochem Biophys Res Commun 228:153
- Remers WA (1972) In: Houlihan WJ (ed) Heterocyclic compounds. Interscience Publishers, New York, p 1
- 9. Hazarika P, Sharma SD, Konwar D (2008) Synth Commun 38:2870
- Ekbote SS, Deshmukh KM, Qureshi ZS, Bhanage BM (2011) Green Chem Lett Rev 4:177
- 11. Kamal A, Qureshi AA (1963) Tetrahedron 19:513
- 12. Li WJ, Lin XF, Wang J, Li GL, Wang YG (2005) Synth Commun 35:2765
- Yadav JS, Gupta MK, Jain R, Yadav NN, Reddy BVS (2010) Monatsh Chem 141:1001
- 14. Nagarajan R, Perumal P (2002) Tetrahedron 58:1229
- 15. Mi X, Luo S, He J, Cheng JP (2004) Tetrahedron Lett 45:4567 16. Wang L, Han J, Tian H, Sheng J, Fan Z, Tang X (2005) Synlett
- 337
- 17. Qu HE, Xiao C, Wang N, Yu KH, Hu QS, Liu LX (2011) Molecules 16:3855
- Xu XF, Xiong Y, Ling XG, Xie XM, Yuan J, Zhang Sh, Song ZR (2014) Chin Chem Lett 25:406
- 19. Nagawade RR, Shinde DB (2006) Acta Chim Slov 53:210
- 20. Zhang Y, Chen X, Liang J, Shang Zh (2011) Synth Commun 41:2446
- Naik MA, Sachdev D, Dubey A (2010) Catal Commun 11:1148
 Mendes SR, Thurow S, Fortes MP, Penteado F, Lenardão EJ,
- Alves D, Perin G, Jacob RG (2012) Tetrahedron Lett 53:5402
 23. Hasaninejad A, Zare A, Sharghi H, Niknam Kh, Shekouhy M (2007) Arkivoc xiv:39
- 24. Shiri M (2013) J Iran Chem Soc 10:1019
- 25. Khaksar S, Ostad SM (2011) J Fluorine Chem 132:937
- 26. Kalantari M (2012) Arab J Chem 5:319
- 27. Hojati SF, Zeinali T, Nematdoust Z (2013) Bull Korean Chem Soc 34:117
- Sharma GVM, Reddy JJ, Lakshim PS, Krishna PR (2004) Tetrahedron Lett 45:7729
- 29. Khosropour AR, Mohammadpoor-Baltork I, Khodaei MM, Ghanbary P (2007) Z Naturforsch 62b:537
- Zhang S, Fan W, Qu H, Xiao C, Wang N, Shu L, Hu Q, Liu L (2012) Curr Org Chem 16:942
- 31. Weinberg NL, Weinberg HR (1968) Chem Rev 68:449
- 32. Nematollahi D, Dehdashtian S, Niazi A (2008) J Electroanal Chem 616:79
- Souza RFM, Souza CA, Areias MCC, Cachet-Vivier C, Laurent M, Barhdadi R, Léonel E, Navarro M, Bieber LW (2010) Electrochim Acta 56:575
- Guirado A, Andreu R, Gálvez J, Jones PG (2002) Tetrahedron 58:9853
- Jouikov V, Salaheev RG, Souza FM, Souza CA, Areias MCC, Cachet-Vivier C, Laurent M, Barhdadi R, Léonel E, Navarro M, Bieber LW (1996) Electrochim Acta 41:2623
- Li CH, Song XZ, Tao LM, Li QJ, Xie JQ, Peng MN, Pan L, Jiang C, Peng ZY, Xu MF (2014) Tetrahedron 70:1855

- Makarem S, Fakhari AR, Alimohammadi AA (2008) Tetrahedron Lett 49:7194
- Shestopalov AM, Niazimbetova ZI, Evans DH, Niyazymbetov ME (1999) Heterocycles 51:1101
- Vafajoo Z, Veisi H, Maghsoodlou MT, Ahmadian H (2014) C R Chimie 17:301
- 40. Cortopassi AC, Ferrara PJ, Wawiernia TM, Essel JT (2008) Int J Energetic Materials Chem Prop 7:39
- 41. Thakur R, Gupta RB (2006) Chem Eng Commun 193:293
- 42. Mohammadpoor-Baltork I, Memarian HR, Khosropour AR, Nikoofar K (2006) Lett Org Chem 3:768
- Mohammadpoor-Baltork I, Memarian HR, Khosropour AR, Nikoofar K (2006) Heterocycles 68:1837

- Khodaei MM, Mohammadpoor-Baltork I, Memarian HR, Khosropour AR, Nikoofar K, Ghanbary P (2008) J Heterocycl Chem 45:377
- 45. Memarian HR, Mohammadpoor-Baltork I, Nikoofar K (2008) Ultrason Sonochem 15:456
- 46. Memarian HR, Mohammadpoor-Baltork I, Nikoofar K (2007) Can J Chem 85:930
- 47. Fotouhi L, Nikoofar K (2013) Tetrahedron Lett 54:2903
- Bard AJ, Faulkner LR (2001) Electrochemical Methods, 2nd edn. Wiley, New York, p 497
- Greef R, Peat R, Peter LM, Pletcher D, Robinson J (1990) Instrumental Methods in Electrochemistry. Ellis Horwood Limited, New York, p 195