Organic & Biomolecular Chemistry

www.rsc.org/obc



ISSN 1477-0520



PAPERDaniel T. Gryko et al.Quadrupolar, emission-tunable π -expanded 1,4-dihydropyrrolo[3,2-b]-pyrroles – synthesis and optical properties

Organic & Biomolecular Chemistry

PAPER

Cite this: Org. Biomol. Chem., 2014, **12**, 2874

Received 19th January 2014, Accepted 18th February 2014 DOI: 10.1039/c4ob00143e

www.rsc.org/obc

Introduction

Heteropentalenes¹ are a class of 10π -electron aromatic compounds and 1,4-dihydropyrrolo[3,2-*b*]pyrrole is the least studied member of this family.² In contrast to the well explored thieno[3,2-*b*]thiophene, the 1,4-dihydropyrrolo[3,2-*b*]pyrrole core is the strongest electron-donor among 10π -electron systems. The lack of an efficient synthetic method for the preparation of this skeleton has recently been overcome by the discovery of one-pot domino reaction between aldehydes, primary amines and butane-2,3-dione.³ The superb optical properties, including intrinsically high fluorescence quantum yields, combined with the straightforward character of the synthesis, make 1,4-dihydropyrrolo[3,2-*b*]pyrrole the core unit of choice for application in various areas of photonics, in

Quadrupolar, emission-tunable π -expanded 1,4-dihydropyrrolo[3,2-b]pyrroles – synthesis and optical properties[†]

Anita Janiga,^a Dominika Bednarska,^a Bjarne Thorsted,^b Jonathan Brewer^b and Daniel T. Gryko^{*a,c}

The synthesis and optical characterization of six novel heteroaromatic-based chromophores is described. The new dyes present mostly an A–D–A general framework, where A is an electron-deficient aromatic ring and D is an electron-rich pyrrolo[3,2-*b*]pyrrole moiety, linked *via* triple bonds. It was demonstrated that the increase in the molecular length of the chromophore effectively extends π -conjugation. The effect of structural variations on photophysical properties was studied in detail for these compounds and the relationship between the structure and photophysical properties was thoroughly elucidated by comparison with simpler tetraaryl-analogues. The strong charge-transfer characteristic of these functional dyes can be illustrated by large Stokes shifts (4100–7100 cm⁻¹) for A–D–A architectures. The replacement of phenyl rings at positions 2 and 5 with the arylethynylaryl substituents bathochromically shifts both absorption and emission at *ca*. 50–150 nm. The clear dependence of fluorescence maxima on the electron-accepting property of the peripheral arylethynyl substituent emphasizes strong π -conjugation in these molecules. The donor–acceptor interactions were also found to influence the two-photon absorption properties.

particular in fluorescence microscopy. Although classical fluorescent microscopy still plays a critical role, two-photon excited fluorescence (TPEF) microscopy can provide better contrast, brighter images and greater detail compared to classical fluorescent microscopy.^{4,5} This originates from the fact that the two-photon absorption (2PA) scales quadratically with the intensity of the incident laser radiation, which leads to much higher spatial resolution than could be achieved by one-photon absorption.

Very recently, it has become clear that, for the two-photon technology to realize its full potential, the development of more two-photon-active chromophores that also possess other useful optical or chemical properties, such as high fluorescence quantum yields, easy processability, good photostability, and durability, will play a vital role.^{4–8} The breakthrough study by Brédas, Marder, Perry and co-workers⁹ has revealed that molecules possessing the quadrupolar structure (D-A-D, A-D-A) usually possess higher 2PA cross-sections (σ_2) than their dipolar analogs. This is due to the fact that the presence of a donor as the core induces charge transfer from the center to the periphery of the molecule, and hence enables the molecule to display large σ_2 values. Needless to say, the stronger the donor/acceptor ability of the corresponding moieties, the higher the values of σ_2 .^{4,5} We envisioned that the conjugated π -system could be enlarged by two arylethynyl

View Article Online

^aInstitute of Organic Chemistry, Polish Academy of Sciences, Kasprzaka, 44/52 01-224, Warsaw, Poland. E-mail: dtgryko@icho.edu.pl; Fax: +48 22 632 66 81; Tel: +48 22 343 30 63

^bDepartment of Biochemistry and Molecular Biology, University of Southern Denmark, Odense 200-701, Denmark. Tel: +45 6550 3505

^cWarsaw University of Technology, Faculty of Chemistry, Noakowskiego 3, 00-664 Warsaw, Poland. Fax: +48 22 628 27 41; Tel: +48 22 234 58 01

[†]Electronic supplementary information (ESI) available: ¹H NMR, ¹³C NMR, absorption and emission spectra of compounds **4–9**. See DOI: 10.1039/c4ob00143e

units at each side of the 1,4-dihydropyrrolo[3,2-*b*]pyrrole core. The intrinsically high electron-donating ability of the pyrrolo-[3,2-*b*]pyrrole core prompted us to perform the study oriented towards the synthesis of A–D–A molecules based on this skeleton.

Results and discussion

Our design implied decoration of the pyrrolo[3,2-b]pyrrole skeleton with electron-withdrawing groups linked through C-C triple bonds. Moreover, synthesis of a derivative with terminal methoxy groups was planned as to allow for the direct comparison between the influence of electron-rich and electronpoor substituents on optical properties of the chromophore. We reasoned that due to the small dihedral angles between the phenyl ring and the core in analogous to 2-phenylindoles $(\sim 30^{\circ})^{10}$ the conjugation between the three parts of the desired dyes will be strong. 1,4-Di(4-methylphenyl)-2,5-di(alkynylphenyl)-1,4-dihydropyrrolo[3,2-b]pyrrole (3) was prepared in two steps (Scheme 1). Since the Sonogashira coupling is the preferred method leading to derivatives of diarylacetylenes¹¹ to obtain the designed compounds we decided to synthesize an electron-rich heterocycle bearing two terminal acetylenes and subsequently react it with a range of aryl bromides and aryl iodides. The three component condensation of 4-trimethylsilylethynylbenzaldehyde (1),¹² 4-methylaniline and butane-2,3dione in boiling glacial acetic acid produced the derivative 1,4dihydropyrrolo[3,2-b]pyrrole (2) with 15% yield. Deprotection of the TMS group by reaction with tetrabutylammonium fluoride (TBAF) gave product 3, which served as a platform for planned modifications. The Sonogashira coupling between alkyne 3 and 4-bromobenzonitrile or 4-iodobenzonitrile has

Table 1 Optimisation of the Sonogashira reaction leading to compound 4

Entry	Reaction conditions	% Yield	
1	Pd(PPh ₃) ₄ , CuI, Et ₃ N THF, 70 °C, 16 h	24	
2	Pd(PhCN) ₂ Cl ₂ , P(<i>t</i> -Bu) ₃ , CuI, HN(i-Pr) ₂ , dioxane, rt, 16 h	0	
3	Pd ₂ dba ₃ , AsPh ₃ , Et ₃ N, toluene, rt/80 °C, 24 h	20	
4	Cs ₂ CO ₃ , CuI, DABCO, dioxane, 135 °C, 16 h	0	
5	Pd ₂ (dba) ₃ , P(<i>t</i> -Bu) ₃ , Et ₃ N, THF, rt, 16 h	9	
6	Cs ₂ CO ₃ , CuI, phenanthroline, dioxane, 135 °C, 16 h	10	

been chosen as a model system for the optimization studies (Scheme 1, Table 1). In spite of using diverse and modern protocols¹³ we could not reach a higher yield of product 4 than 24%.

Looking for new strategies we directed our research efforts towards the sila-Sonogashira coupling.¹⁴ The combination of both deprotection and coupling in one step, under conditions described by Henze *et al.*¹⁵ allowed us to obtain compound **4** in higher yield with concomitant shortening of the whole procedure (Table 2). Encouraged by this finding, we subsequently investigated whether this synthetic route is applicable for other iodoarenes and bromoarenes.

Subjecting the mixture of 2,6-di(4-(trimethylsilylethynyl)phenyl)-1,5-di(4-methylphenyl)-1,4-dihydropyrrolo[3,2-*b*]pyrrole (2) and aryl halides bearing various substituents to the sila-Sonogashira coupling conditions gave products **4–8** in yields ranging from 15 to 56%. It is noteworthy that although reaction proceeds for both electron-poor and electron-rich halides, 4-bromobenzonitrile was the most efficient substrate in this reaction. Still, compound **8** could only be obtained when the process was performed with 4-iodoanisole rather









Entry	Aryl halide	Product no.	Yield (%)	
1	NC-Br	4	56	
2	F ₅ S-Br	5	21	
3	F ₃ C	6	15	
4	F ₃ C F ₃ C	7	33	
5	MeO-Br	8	0	
6	MeO-	8	30	
7	OHC Br	9	Traces ^a	

^{*a*} Due to the unsatisfactory result we decided to change reaction conditions and employ the standard Sonogashira reaction conditions (see Table 1, entry 1) which increased the yield of the product 9 to 56%.



Fig. 1 Structures of pyrrolo[3,2-*b*]pyrroles 10 and 11.



Fig. 2 Absorption (–) and normalized fluorescence (- - -) spectra of 4 in $\mathsf{CH}_2\mathsf{Cl}_2.$

than 4-bromoanisole (entries 5 and 6, Table 2). Interestingly, reaction of 4-bromobenzaldehyde with compound 2 led to a broad range of side products which impeded the purification process and caused a loss in the overall yield of derivative 9. This unsatisfactory result prompted us to change the reaction conditions and employ the standard Sonogashira coupling (see Table 1, entry 1); this increased the yield of the product 9 to 56%. Spectral characteristics of products **4–9** were then examined and compared to those of parent compounds **10** and **11**³ (Fig. 1–3, Table 3). The absorption spectra of these dyes have broad bands located between 350 and 500 nm (Fig. 2 and 3). The molar absorption coefficients are in the range 50 000–70 000 regardless of the electronic character of the substituents, *i.e.* they are significantly higher than for previously reported tetraaryl-1,4-dihydropyrrolo[3,2-*b*]pyrroles.³ The characteristic feature



Fig. 3 Absorption spectra of 5 (–), 7 (- - -), and 8 (- \cdot -) in CH_2Cl_2

Table 3Photophysical data for 4-11 in CH_2Cl_2

Product no.	$\lambda_{ m abs}/$ nm	$\lambda_{\rm em}/$ nm	${\Phi_{\mathrm{fl}}}^a_{(\%)}$	σ _{2 (720 nm)} (GM)	Stokes shift (cm ⁻¹)
4	428	549	22	250	5200
5	418	523	16	5	4800
6	414	511	42	800	4600
7	421	522	37	500	4600
8	401	479	53	100	4100
9	434	629	2	300	7100
10 ^b	406	461	88	260	2900
11 ^b	368	462	17	25	5500

 a Determined with quinine sulphate in $\rm H_2SO_4$ (0.5 M) as a standard. b Ref. 3.

was the bathochromic shift of absorption when going from compounds **10–11** to dyes **4–9** (~50 nm). This strong bathochromic shift proves the existence of electronic communication in the ground state throughout the whole molecule. In typical low viscosity solvents such as CH_2Cl_2 , the rotation of the benzene ring along the linker is not disturbed, and the coplanarity between the substituted phenyl ring and the pyrrolo[3,2-*b*]pyrrole core is attained.

All of the π -expanded pyrrolo[3,2-*b*]pyrroles are fluorescent. The color of fluorescence of 4-9 ranges from blue, turquoise to orange. Fluorescence maxima, except for compound 8, are shifted above 500 nm. The fluorescence maxima $(\lambda_{\text{max}}^{\text{fl}})$ of the series 4-9 are gradually red-shifted upon increasing the strength of the electron-withdrawing group. The strong relationship between the electron-withdrawing strength of the substituent and the λ_{\max}^{fl} supports the existence of strong electronic communication in these molecules in the excited state. Fluorescence quantum yields of products 4-8 were found to be moderate to good ($\Phi_{\rm fl}$ = 16–53%) and the highest fluorescence quantum yield (53%) was measured for 8. Product 9 had the lowest quantum yield (2%), which is quite typical for aldehydes. The fluorescence quantum yield and Stokes shift of 6 are similar to those of compound 7, while dialdehyde 9 possesses very high Stokes shift (7000 cm⁻¹). The stronger electron-withdrawing substituents in 9 (CHO) and 4 (CN) compared to those in 6 and 7 (CF_3) confer a further



Fig. 4 Two-photon absorption spectra of 4 (black dots), 6 (black diamonds), 7 (red squares), and 10 (green triangles) in CH_2Cl_2 .



Fig. 5 Two-photon absorption spectra of 8 (black dots), 9 (red squares), 5 (open triangles) and 11 (black triangles) in CH_2Cl_2 .

bathochromic shift of absorption and emission as expected for push–pull chromophores.¹⁶ The large Stokes shift corresponds to a significant change of geometry between ground and excited states. Dyes **4–9** compare very favorably with quadrupolar dyes of similar complexity.¹⁷

Two-photon absorption has been measured using TPEF and results are shown in Table 3 and in Fig. 4 and 5. The measurements were conducted in the 700–1020 nm range (corresponding to the relevant biological spectral window). In the spectral range of interest, two-photon absorption cross-sections are not strongly dependent on the magnitude of charge-transfer. Indeed, the strongly electron-donating 4-methoxyphenyl substituent gave relatively intense 2PA signal. Interestingly two-photon absorption of these quadrupolar molecules is typically within 100–800 GM at 720 nm.

Indeed the highest value in the NIR region of the spectrum can be attributed to compound 6 possessing two 4-trifluoromethyl substituents while strongly electron-withdrawing 4 and 9 have lower σ_2 (Table 3, Fig. 4). On the other hand, it is clear

Paper

that tetraaryl-derivative **10** possessing two 4-cyanophenyl substituents at positions 2 and 5 also behaves like the A–D–A system ($\sigma_2 \sim 300$ GM). Eventually, the critical figure of merit *i.e.* two-photon brightness is the highest for dye **6** (~ 340 GM). As illustrated in Fig. 4 and 5 for compounds **4–11**, the lowest (strongly one-photon allowed) excited state is moderately intensive, and the higher (only weakly one-photon allowed) state, responsible for the large 2PA response, is located below 700 nm. This feature is reminiscent of the behavior of symmetrical quadrupolar derivatives.¹⁸

Conclusions

In summary, the first examples of π -expanded pyrrolo[3,2-*b*]pyrroles have been described.²² It has been proven that only 'sila version' of the Sonogashira coupling is an efficient method to assemble these molecules. The proposed synthetic method is operationally simple and leads to new functional dyes possessing strong absorption in the violet-blue region combined with reasonably intensive blue-green fluorescence. In sharp contrast to previously described tetraaryl-pyrrolo[3,2-b]pyrroles both absorption and emission are bathochromically shifted. Thus, it can be reasonably concluded that the connection with arylethynylaryl groups at the 2,5-positions of pyrrolo-[3,2-*b*]pyrroles extends π -conjugation effectively relative to that of 1,2,4,5-tetraarylpyrrolo[3,2-b]pyrroles. The most promising dye bearing two 4-(CF₃)C₆H₄ groups possesses appreciable two-photon brightness (~340 GM) while its calculated Stokes shift remains relatively large (4600 cm⁻¹). A new and efficient turquoise fluorescence emitter, that is a compound possessing two 4-methoxyphenylethynylphenyl substituents, was identified. Our studies illustrate the effect of different substituents on the electronic properties of the pyrrolo[3,2-b]pyrroles and reveal that both absorption and emission can be tuned by straightforward structural manipulations. These results are not only of theoretical significance in that they provide insight into factors influencing the electronic structure of extended π -systems, but they may also open doors to practical applications in such diverse areas as molecular electronics and fluorescence imaging.

Experimental section

All chemicals were used as received unless otherwise noted. Reagent grade solvents (CH_2Cl_2 , hexanes) were distilled prior to use. All reported NMR spectra were recorded on 400 MHz, 500 MHz and 600 MHz spectrometers. UV-vis absorption and fluorescent spectra were recorded in CH_2Cl_2 . Chromatography was performed on silica (200–400 mesh) and dry column vacuum chromatography (DCVC) was performed on preparative thin layer chromatography silica (Merck 107747). Mass spectra were obtained *via* EI-MS and FD-MS.

Synthesis

1,4-Di-(4-methylphenyl)-2,5-bis(4((trimethylsilyl)ethynyl)phenyl)-1,4-dihydropyrrolo[3,2-b]pyrrole (2). 4-Methylaniline (1.27 g, 12 mmol) and 4-(trimethylsilylethynyl)benzaldehyde (2.4 g, 12 mmol) were stirred in glacial acetic acid (10 mL) at 100 °C for 30 min. Then butane-2,3-dione (519 µl, 6 mmol) was added and the resulting mixture was stirred at 100 °C for 3 h. After cooling the precipitate was filtered off and washed with glacial acetic acid. Recrystallization from EtOAc afforded the pure product as a yellow solid in 15% yield (567 mg). $R_{\rm f} = 0.78$ (SiO₂, hexane-CH₂Cl₂, 1:1). Mp 314.0-314.3 °C (decomposition). ¹H NMR (500 MHz, CDCl₃) δ 7.26 (AA'XX', 4H), 7.14 (m, 12H), 6.36 (s, 2H), 2.37 (s, 6H), 0.23 (s, 18H); ¹³C NMR (125 MHz, CDCl₃) δ 137.0, 135.9, 132.0 (2), 130.0, 129.4, 129.1, 128.2, 127.8 (2), 125.3, 106.6, 94.9, 21.2, 0.14. HRMS (EI+) calcd for C₄₂H₄₂N₂Si₂: 630.2905 [M⁺], found: 630.2905. λ_{abs} (CH₂Cl₂, $\varepsilon \times 10^{-3}$) 393 (60) nm.

2,5-Bis(4-ethynylphenyl)-1,4-di-(4-methylphenyl)-1,4-dihydropyrrolo[**3,2-***b***]pyrrole** (**3**). TMS protected derivative **2** (567 mg, 0.90 mmol) was dissolved in THF (5 ml) and TBAF (588 mg, 2.25 mmol) was added. The reaction mixture was stirred for 3 h at rt. The solvent was evaporated and the crude product was recrystallized from EtOAc. The pure product was obtained as a yellow solid in 96% yield (420 mg). $R_{\rm f}$ = 0.67 (SiO₂, hexane–CH₂Cl₂, 1 : 1). Mp 290.0–290.3 °C (decomposition). ¹H NMR (500 MHz, CDCl₃) δ 7.33 (AA'XX', 4H), 7.16 (m, 8H), 7.14 (AA'XX', 4H), 6.39 (s, 2H), 3.07 (s, 2H), 2.38 (s, 6H); ¹³C NMR (125 MHz, CDCl₃) δ 137.4, 135.9, 135.6, 134.2, 132.6, 132.1, 130.0, 127.8, 125.3, 119.5, 95.0, 84.0, 77.6, 21.2. HRMS (EI+) calcd for C₃₆H₂₆N₂: 486.2096 [M⁺], found: 486.2100. Anal. calcd for C₃₆H₂₆N₂: C, 88.86; H, 5.39; N, 5.76; found: C, 88.70; H, 5.31; N, 5.77. λ_{abs} (CH₂Cl₂, ε × 10⁻³) 387 (53) nm.

Representative procedure for the sila-Sonogashira coupling

2,5-Di(4-(4-cyanophenylethynyl)phenyl)-1,4-di(4-methylphenyl)-1,4-dihydropyrrolo[3,2-b]pyrrole (4). The mixture of 1,4-di-(4methylphenyl)-2,5-bis(4-((trimethylsilyl)ethynyl)phenyl)-1,4dihydropyrrolo[3,2-*b*]pyrrole (2, 1.20 mg, 3.17×10^{-5} mol), $PdCl_2(PPh_3)_2$ (2.2 mg, 3.17 × 10⁻⁶ mol), CuI (0.6 mg, 3.17 × 10^{-6} mol) and 4-bromobenzonitrile (12 mg, 6.317 × 10^{-5} mol) in dry THF (0.5 ml) with Et₃N (0.5 ml, 3.6 mmol) was deoxygenated by freeze-pump-thaw cycles and purged with argon gas in an oven dried Schlenk flask. TBAF (21 mg, 7.92×10^{-6} mol) was added, and the reaction mixture was stirred for 16 h at rt under an argon atmosphere. The crude mixture was filtered through celite and the solvent was distilled off. Purification using the DCVC method (SiO₂, hexane-CH₂Cl₂, 4:1) afforded the pure product as a yellow solid in 56% yield (12 mg). $R_{\rm f}$ = 0.27 (SiO₂, hexane-CH₂Cl₂, 1:1). Mp 313.2-313.5 °C (decomposition). ¹H NMR (500 MHz, CDCl₃) δ 7.61 (AA'XX', 4H), 7.57 (AA'XX', 4H), 7.38 (AA'XX', 4H), 7.21 (AA'XX', 4H), 7.19 (m, 8H), 6.42 (s, 2H), 2.39 (s, 6H); ¹³C NMR (125 MHz, $CDCl_3$) δ 137.5, 136.1, 135.7, 134.5, 132.9, 132.2, 132.1, 131.8, 130.1, 128.5, 127.9, 125.4, 119.6, 118.6, 111.5, 95.2, 88.5, 21.2.

HRMS (EI+) calcd for $C_{50}H_{32}N_4$: 688.2627 [M⁺], found: 688.2596. λ_{abs} (CH₂Cl₂, $\varepsilon \times 10^{-3}$) 428 (70) nm.

2,5-Di(4-(4-pentafluorothiophenyl)ethynylphenyl)-1,4-di-(**4-methylphenyl)-1,4-dihydropyrrolo**[**3,2-***b*]**pyrrole** (5). Purification using the DCVC method (SiO₂, hexane–CH₂Cl₂, 4:1) afforded the pure product as a yellow solid in 21% yield (6 mg). $R_{\rm f} = 0.72$ (SiO₂, hexane–CH₂Cl₂, 1:1). Mp 207.0–207.3 °C. ¹H NMR (500 MHz, CDCl₃) δ 7.65 (AA'XX', 4H), 7.48 (AA'XX', 4H), 7.33 (AA'XX', 4H), 7.14 (AA'XX', 4H), 7.14-7.08 (m, 8H), 6.36 (s, 2H), 2.32 (s, 6H); ¹³C NMR (125 MHz, CDCl₃) δ 137.3, 135.9, 135.5, 134.2, 132.6, 131.6, 131.5, 129.9, 127.7, 127.1, 126.0, 125.2, 119.5, 95.0, 92.7, 87.9, 29.7, 21.0. HRMS (EI+) calcd for C₄₈H₃₂F₁₀N₂S₂: 890.1847 [M⁺], found: 890.1843. $\lambda_{\rm abs}$ (CH₂Cl₂, $\varepsilon \times 10^{-3}$) 418 (45) nm.

2,5-Di(4-(4-trifluoromethyl)ethynylphenyl)-1,4-di(4-methylphenyl)-1,4-dihydropyrrolo[3,2-*b***]pyrrole** (6). Purification using the DCVC method (SiO₂, hexane–CH₂Cl₂, 6:1) afforded the pure product as an orange solid in 15% yield (4 mg). $R_{\rm f}$ = 0.76 (SiO₂, hexane–CH₂Cl₂, 1:1). Mp 346.9–347.2 °C (decomposition). ¹H NMR (400 MHz, CDCl₃) δ 7.59 (s, 8H), 7.39 (AA'XX', 4H), 7.19 (m, 12H), 6.42 (s, 2H), 2.38 (s, 6H); ¹³C NMR (125 MHz, CDCl₃) δ 137.5, 136.0, 131.9 (2), 131.7, 130.1, 129.8, 127.9 (2), 127.3 (2), 125.5 (2), 125.4, 125.4, 123.1, 112.6, 95.1, 21.2. HRMS (EI+) calcd for C₅₀H₃₂F₆N₂: 774.2470 [M⁺], found: 774.2461. $\lambda_{\rm abs}$ (CH₂Cl₂, $\varepsilon \times 10^{-3}$) 414 (62) nm.

2,5-Di(4-(3,5-di(trifluoromethyl))ethynylphenyl)-1,4-di-(4-methylphenyl)-1,4-dihydropyrrolo[3,2-*b*]pyrrole (7). Purification using the DCVC method (SiO₂, hexane–CH₂Cl₂, 8:1) afforded the pure product as a yellow solid in 33% yield (10 mg). $R_{\rm f}$ = 0.78 (SiO₂, hexane–CH₂Cl₂, 1:1). Mp 316.6–316.9 °C. ¹H NMR (500 MHz, CDCl₃) δ 7.92 (s, 4H), 7.80 (s, 2H), 7.40 (AA'XX', 4H), 7.23 (AA'XX', 4H), 7.20 (m, 8H), 6.45 (s, 2H), 2.39 (s, 6H); ¹³C NMR (125 MHz, CDCl₃) δ 137.4, 136.1, 134.6, 132.9, 132.2, 132.0, 131.8, 131.4, 130.1, 127.9, 125.9, 125.3, 124.2, 122.0, 119.1, 95.2, 93.3, 87.0, 21.2. HRMS (EI+) calcd for C₅₂H₃₀F₁₂N₂: 910.2215 [M⁺], found: 910.2188. $\lambda_{\rm abs}$ (CH₂Cl₂, $\varepsilon \times 10^{-3}$) 421 (67) nm.

2,5-Di(4-(methoxy)ethynylphenyl)-1,4-di(4-methylphenyl)-1,4dihydropyrrolo[3,2-*b*]pyrrole (8). Purification using the DCVC method (SiO₂, hexane–CH₂Cl₂, 3 : 1) afforded the pure product as a yellow solid in 30% yield (7 mg). $R_{\rm f}$ = 0.44 (silica, hexane– CH₂Cl₂, 1 : 1). Mp 315.3–315.6 °C. ¹H NMR (500 MHz, CDCl₃) δ 7.44 (AA'XX', 4H), 7.35 (AA'XX', 4H), 7.18 (s, 12H), 6.87 (AA' XX', 4H), 6.40 (s, 2H), 3.82 (s, 6H), 2.38 (s, 6H); ¹³C NMR (125 MHz, CDCl₃) δ 159.7, 137.5, 135.8, 133.1, 133.0, 131.3 (2), 130.0, 129.2, 128.4, 127.8 (2), 125.8, 125.3, 114.1, 95.0, 55.5, 21.6, 21.2. HRMS (EI+) calcd for C₅₀H₃₈N₂O₂: 698.2933 [M⁺], found: 698.2955. $\lambda_{\rm abs}$ (CH₂Cl₂, $\varepsilon \times 10^{-3}$) 401 (71) nm.

2,5-Di(4-(formylethynyl)phenyl)-1,4-di(4-methylphenyl)-1,4-dihydropyrrolo[3,2-*b*]pyrrole (9). The mixture of 4-bromobenzaldehyde (50 mg, 2.71×10^{-4} mol), 2,5-bis(4-ethynylphenyl)-1,4-di-(4-methylphenyl)-1,4-dihydropyrrolo[3,2-*b*]pyrrole (3, 66 mg, 1.36×10^{-4} mol), Pd(PPh₃)₄ (7 mg, 6.06×10^{-6} mol), and CuI (2 mg, 1.06×10^{-5} mol) in THF (2 ml) with Et₃N (120 µl, 0.86 mmol) was deoxygenated by freeze-pump-thaw cycles in a Schlenk flask and stirred at 70 °C for 16 h. The crude mixture was filtered through celite and the solvent was distilled off. Purification using the DCVC method (SiO₂, hexane-CH₂Cl₂, 1:1) afforded the pure product as an orange solid in 56% yield (31 mg). $R_{\rm f}$ = 0.16 (SiO₂, hexane-CH₂Cl₂, 1:1). Mp 283.3–283.6 °C (decomposition). ¹H NMR (500 MHz, CDCl₃) δ 10.01 (s, 2H), 7.85 (AA'XX', 4H), 7.64 (AA'XX', 4H), 7.40 (AA'XX', 4H), 7.19 (s, 12H), 6.43 (s, 2H), 2.39 (s, 6H); ¹³C NMR (125 MHz, CDCl₃) δ 191.5, 137.4, 136.0, 135.5, 132.1, 131.8 (2), 130.1, 129.7, 127.8 (2), 125.3, 120.0, 110.1, 94.9, 93.9, 89.5, 29.7, 21.2. HRMS (EI+) calcd for C₅₀H₃₄N₂O₂: 694.2580 [M⁺], found: 694.2585. $\lambda_{\rm abs}$ (CHCl₃, $\varepsilon \times 103$) 434 (30) nm.

Two photon fluorescence intensity measurements

Dichloromethane (CHROMASOLV®, for HPLC, \geq 99.9%), methanol (CHROMASOLV®, for HPLC, ≥99.9), 5-carboxyfluorescein (99% (HPLC)), Rhodamine B and Rhodamine 6G were purchased from Sigma-Aldrich, Denmark. The samples were dissolved in dichloromethane; Rh B and Rh 6G were dissolved in methanol. The fluorescein was dissolved in a CAPS buffer (N-cyclohexyl-3-aminopropanesulfonic acid) of pH 11. The concentrations of the samples and references were determined by a dilution series in a spectrophotometer (Perkin Elmer lambda 35) using quartz cuvettes. The single photon fluorescence emission spectra were measured using a spectrofluorometer (ChronosFD from ISS, Champaign, IL, USA). The two photon excited emission spectra were collected using a custom built multiphoton excitation spectrofluorometer similar to the previously used one.¹⁹ Briefly, the excitation source was a Ti:Sa laser (HPeMaiTai DeepSee, Spectra Physics, Mountain View, CA). The laser power was controlled using a motorized halfwave plate together with a polarizer. The excitation light was focused onto the sample using a 60× super long working objective (Nikon). The emission was collected through the objective and passed through a Multiphoton-Emitter HC 680/ SP (AHF analysentechnik AG, Tuebingen, Germany) to a multimode optical fiber (M200L02S-A, Thorlabs Sweden AB Goteborg, Sweden). The emission was then sent through a monochromator (ARC-SP2155, BFi OPTiLAS, Sweden) and the spectra were imaged using a cooled CCD camera (PIXIS 400B, Princeton Instruments, New Jersey, USA). A motorized XY microscope stage (Nikon) was used as a sample holder. The laser, laser power, camera and XY stage were controlled using ImageJ²⁰ and custom scripts. The relative laser power was monitored using a power meter (PM100D with a S142C head, Thorlabs Sweden AB Goteborg, Sweden). Calculations were done using the custom Matlab code (MathWorks, Natick, USA). The 2-photon absorption spectra were measured relative to standard fluorophores, with well characterized spectra.²¹ The measurement of the sample and standard under the same conditions allows for correction of changes of the temporal pulse profile and spatial beam profile of the laser at different wavelengths. To eliminate possible artifacts, due to photobleaching or linear absorption, we checked that the fluorescence signal increased as the square of the excitation intensity at different excitation wavelengths for the different samples. The absolute 2-photon absorption cross-sections were calculated using a relative fluorescence intensity technique as described previously.²¹ Fluorescein in a CAPS buffer (pH 11) and Rh 6G and Rh B in methanol were used to calibrate the system. The measurements for the two photon crosssections were carried out at least five times for the different samples at excitation wavelengths from 700 nm to 1020 nm.

Acknowledgements

Financial support of our work from the Foundation for Polish Science (grant number TEAM/2009-4/3) is gratefully acknowledged. The research leading to these results has received partial funding from the European Community's Seventh Framework Programme under the TOPBIO project – grant agreement no. 264362. JB gratefully acknowledges support from the Danish Molecular Biomedical Imaging Center (DaMBIC), and the Carlsberg Foundation.

Notes and references

- 1 (a) L. S. Fuller, B. Iddon and K. A. Smith, J. Chem. Soc., Perkin Trans. 1, 1997, 3465-3470; (b) H. Behringer and E. Meinetsberger, Liebigs Ann. Chem., 1981, 1729-1750; (c) H. Behringer and E. Meinetsberger, Tetrahedron Lett., 1973, 22, 1915-1918; (d) M. Kuhn, F. C. Falk and J. Paradies, Org. Lett., 2011, 13, 4100-4103; (e) V. G. Nenajdenko, V. V. Sumerin, K. Y. Chernichenko and E. S. Balenkova, Org. Lett., 2004, 6, 3437-3439; (f) J. T. Henssler, X. Zhang and A. J. Matzger, J. Org. Chem., 2009, 74, 9112-9119; (g) A. Capan, H. Vaisi, A. C. Goren and T. Ozturk, Macromolecules, 2012, 45, 8228-8236; J. Kim, A.-R. Han, J.-H. Seo, J. H. Oh and C. Yang, Chem. Mater., 2012, 24, 346-3472; (h) J. T. Henssler and A. J. Matzger, Org. Lett., 2009, 11, 3144-3147; (i) K. Koh, A. G. Wong-Foy and A. J. Matzger, J. Am. Chem. Soc., 2009, 131, 4184–4185; (*j*) A. G. Wong-Foy, A. J. Matzger and O. M. Yaghi, J. Am. Chem. Soc., 2006, 128, 3494-3495; McCulloch, M. Heeney, M. L. Chabinyc, (k)I. D. DeLongchamp, R. J. Kline, M. Coelle, W. Duffy, D. Fischer, D. Cundloch, B. Hamadani, R. Hamilton, L. Richter, A. Salleo, M. Shkunov, D. Sporrowe, S. Tierney and W. Zhong, Adv. Mater., 2009, 21, 1091-1109; Roncali, Chem. Rev., 1992, 92, 711-738; (l)J. (m) C. Westerlund and A.-B. Hörnfeldt, Acta Chem. Scand., 1976, B30, 391-396; (n) H. R. Snyder, L. A. Carpino, J. F. Zack and J. F. Mills, J. Am. Chem. Soc., 1956, 79, 2556-2559; (o) D. S. Matteson and H. R. Snyder, J. Org. Chem., 1957, 22, 1500-1504; (p) S. Srinivarsan and G. B. Schuster, *Org. Lett.*, 2008, **10**, 3657–3660; (q) I. Alkorta, F. Blanco and J. Elguero, J. Mol. Struct., 2008, 851, 75-83; (r) M. Welch and R. S. Phillips, Heterocycl. Commun., 1999, 5, 305-310; (s) F. Garcia and C. Galvez, Synthesis, 1985, 143-156.
- 2 (*a*) H. Hemetsberger and D. Knittel, *Monatsh. Chem.*, 1972, **103**, 194–204; (*b*) T. Aratani, H. Yoshihara and

G. Suzukamo, Tetrahedron Lett., 1989, 30, 1655-1656; (c) S. Lotz, M. Landman, H. Goerls, C. Crause, H. Nienaber and A. Olivier, Z. Naturforsch., B: Chem. Sci., 2007, 62, 419-426; (d) B. J. Stokes, H. Dong, B. E. Leslie, A. L. Pumphrey and T. G. Driver, J. Am. Chem. Soc., 2007, 129, 7500-7501; (e) T. Kumagai, K. Satake, K. Kidoura and T. Mukai, Tetrahedron Lett., 1983, 24, 2275-2278; (f) T. Mukai, A. Konno, T. Kumagai and K. Satake, Chem. Lett., 1985, 1809-1812; (g) K. Satake, T. Kumagai and T. Mukai, Chem. Lett., 1984, 2033-2036; (h) T. Kumagai, S. Tanaka and T. Mukai, Tetrahedron Lett., 1984, 25, 5669-5672; (i) K. Satake, K. Yano, M. Fujiwara and M. Kimura, Heterocycles, 1996, 43, 2361-2365; (j) K. Satake, D. Nakoge and M. Kimura, Heterocycles, 1998, 48, 433-436; (k) B. P. Murphy, R. W. Glenn, M. Lim, J. M. Gardlik, S. D. Jones, W. D. Laidig and J. D. Shaffer, WO, 2005077324 A1 20050825, 2005; (l) M. L. R. Heffernan, J. M. Dorsey, Q. K. Fang, R. J. Foglesong, S. C. Hopkins, M. L. Jones, S. W. Jones, C. O. Ogbu, J. B. Perales and Soukri, US, 20080058395 A1 20080306, 2008; M. (m) T. A. Hembrough, G. E. Agoston, A. M. Treston and A. D. Hanson, WO, 2007076055 A2 20070705, 2007; (n) H. T. Dieck, U. Verfürth, K. Diblitz, J. Ehlers and G. Fendesak, Chem. Ber., 1989, 122, 129–131; (o) B. Waltenberger, K. Wiechmann, J. Bauer, P. Markt, S. M. Noha, G. Wolber, J. M. Rollinger, O. Werz, D. Schuster and H. Stuppner, J. Med. Chem., 2011, 54, 3163-3174; (p) F. Rörsch, I. Wobst, H. Zettl, M. Schubert-Zsilavecz, S. Grösch, G. Geisslinger, G. Schneider and Proschak, J. Med. Chem., 2010, 53, 911-915; Е. (q) S. Tanaka, T. Kumagai, T. Mukai and T. Kobayashi, Bull. Chem. Soc. Jpn., 1987, 60, 1981-1983.

- 3 (a) A. Janiga, E. Głodkowska-Mrówka, T. Stokłosa and D. T. Gryko, Asian J. Org. Chem., 2013, 2, 411-415;
 (b) D. T. Gryko and A. Janiga, Novel, strongly fluorescent heterocyclic functional dyes and the method of their preparation. Polish Pat., Appl. P.401473, 2012.
- 4 For recent reviews, see: (a) M. Pawlicki, H. A. Collins, R. G. Denning and H. L. Anderson, Angew. Chem., Int. Ed., 2009, 48, 3244–3266; (b) H. M. Kim and B. R. Cho, Chem. Commun., 2009, 153–164; (c) H. Meier, Angew. Chem., Int. Ed., 2005, 44, 2482–2506; (d) G. S. He, L.-S. Tan, Q. Zheng and P. N. Prasad, Chem. Rev., 2008, 108, 1245– 1330; (e) H. M. Kim and B. R. Cho, Acc. Chem. Res., 2009, 42, 863–872; (f) F. Terenziani, C. Katan, E. Badaeva, S. Tretiak and M. Blanchard-Desce, Adv. Mater., 2008, 20, 4641–4678.
- 5 (a) S. Yao, H.-Y. Ahn, X. Wang, J. Fu, E. W. Van Stryland, D. J. Hagan and K. D. Belfield, J. Org. Chem., 2010, 75, 3965–3974; (b) M. A. Ramirez, R. Custodio, A. M. Cuadro, J. Alvarez-Builla, K. Clays, I. Assselberghs, F. Mendicuti, O. Castaño, J. L. Andrés and J. J. Vaquuero, Org. Biomol. Chem., 2013, 11, 7145–7154; (c) D. R. Larson, W. R. Zipfel, R. M. Williams, S. W. Clark, M. P. Bruchez, F. W. Wise and W. W. Webb, Science, 2003, 300, 1434–1437; (d) L. Ventelon, S. Charier, L. Moreaux, J. Mertz and M. Blanchard-Desce, Angew. Chem., Int. Ed., 2001, 40, 2098–2101; (e) E. Maçôas,

G. Marcelo, S. Pinto, T. Cañeque, A. M. Cuadro, J. J. Vaquero and J. M. G. Martinho, *Chem. Commun.*, 2011, 47, 7374–7376.

- 6 (a) D. A. Parthenopoulos and P. M. Renzepis, *Science*, 1989, 245, 843–845; (b) C. Tang, Q. Zheng, H. Zhu, L. Wang, S.-C. Chen, E. Ma and X. Chen, *J. Mater. Chem. C*, 2013, 1, 1771–1780.
- 7 (a) S. Kim, T. Y. Ohulchanskyy, H. E. Pudavar, R. K. Pandey and P. N. Prasad, J. Am. Chem. Soc., 2007, 129, 2669-2675; (b) M. Tasior, V. Hugues, M. Blanchard-Desce and D. T. Gryko, Asian J. Org. Chem., 2013, 2, 669-673; (c) C. B. Nielsen, J. Arnbjerg, M. Johnsen, M. Jrrgensen and P. R. Ogilby, J. Org. Chem., 2009, 74, 9094-9104; (d) J. R. Starkey, A. K. Rebane, M. A. Drobizhev, F. Q. Meng, A. J. Gong, A. Elliott, K. McInnerney and C. W. Spangler, Clin. Cancer Res., 2008, 14, 6564-6573; (e) H. A. Collins, Khurana, E. H. Moriyama, A. Mariampillai, M. E. Dahlstedt, M. Balaz, M. K. Kuimova, M. Drobizhev, V. X. D. Yang, D. Phillips, A. Rebane, B. C. Wilson and H. L. Anderson, Nat. Photonics, 2008, 2, 420-424; (f) M. Gary-Bobo, Y. Mir, C. Rouxel, D. Brevet, I. Basile, M. Maynadier, O. Mongin, M. Blanchard-Desce, A. Morere, M. Garcia, J.-O. Durand and L. Raehm, Angew. Chem., Int. Ed., 2011, 50, 11425-11429.
- 8 (a) O. Zheng, G. S. He and P. N. Prasad, Chem. Phys. Lett., 2009, 475, 250-255; (b) I. Kim, D. Kim, S. Sambasivan and K. Ahn, Asian J. Org. Chem., 2012, 1, 60-64; (c) G. S. He, G. C. Xu, P. N. Prasad, B. A. Reinhardt, J. C. Bhatt, R. McKellar and A. G. Dillard, Opt. Lett., 1995, 20, 435-437; (d) J. E. Ehrlich, X. L. Wu, I. Y. S. Lee, Z. Y. Hu, H. Rçckel, S. R. Marder and J. W. Perry, Opt. Lett., 1997, 22, 1843-1845; (e) M. Charlot, N. Izard, O. Mongin, D. Riehl and M. Blanchard-Desce, Chem. Phys. Lett., 2006, 417, 297-302; (f) G. Lemercier, J.-C. Mulatier, C. Martineau, R. Anemian, C. Andraud, I. Wang, O. Stephan, N. Amari and P. Baldeck, C. R. Chim., 2005, 8, 1308-1316; (g) A. Nowak-Król, M. Grzybowski, J. Romiszewski, M. Drobizhev, G. Wicks, M. Chotkowski, A. Rebane, E. Górecka and D. T. Gryko, Chem. Commun., 2013, 49, 8368-8370; (h) K. D. Belfield, M. V. Bondar, A. R. Morales, X. Yue, G. Luchita and O. V. Przhonska, J. Phys. Chem. C, 2012, 116, 11261-11271.
- 9 M. Albota, D. Beljonne, J. L. Brédas, J. E. Ehrlich, J. Y. Fu,
 A. A. Heikal, S. E. Hess, T. Kogej, M. D. Levin, S. R. Marder,
 D. McCord-Maughon, J. W. Perry, H. Rockel, M. Rumi,
 C. Subramaniam, W. W. Webb, X. L. Wu and C. Xu, *Science*,
 1998, 281, 1653–1656.
- 10 T. Yin and R. Hua, Chem. Lett., 2013, 42, 836-837.
- 11 (a) K. Sonogashira, Y. Tohda and N. Hagihara, *Tetrahedron Lett.*, 1975, 16, 4467–4470; (b) R. Chinchilla and C. Najera, *Chem. Rev.*, 2007, 107, 874–922.
- 12 Synthesized according to the previously published procedure: W. J. Sommer and M. Weck, *Adv. Synth. Catal.*, 2006, 348, 2101–2113.

- 13 (a) J.-F. Nierengarten, S. Zhang, A. Gegout, M. Urbani, N. Armaroli, G. Marconi and Y. Rio, J. Org. Chem., 2005, 70, 7550–7557; (b) T. Hundertmark, A. F. Littke, S. L. Buchwald and G. C. Fu, Org. Lett., 2000, 2, 1729–1731; (c) R. W. Wagner, Y. Ciringh, C. Clausen and J. S. Lindsey, Chem. Mater., 1999, 11, 2974–2983; (d) J.-H. Li, J.-L. Li, D.-P. Wang, S.-F. Pi, Y.-X. Xie, M.-B. Zhang and X.-C. Hu, J. Org. Chem., 2007, 72, 2053–2057; (e) V. P. W. Böhm and W. A. Herrmann, Eur. J. Org. Chem., 2000, 3679–3681; (f) D. Chen, G. Shena and W. Bao, Org. Biomol. Chem., 2009, 7, 4067–4073.
- 14 (a) Y. Nishihara, K. Ikegashira, A. Mori and T. Hiyama, *Chem. Lett.*, 1997, 1233–1234; (b) Y. Nishihara, K. Ikegashira, K. Hirabayashi, J. Ando, A. Mori and T. Hiyama, *J. Org. Chem.*, 2000, 65, 1780–1787; (c) C. Yang and S. P. Nolan, *Organometallics*, 2002, 21, 1020–1022; (d) M. Livecchi, G. Calvet and F. Schmidt, *J. Org. Chem.*, 2012, 77, 5006–5016.
- 15 Z.-L. Zhou, L. Zhao, S. Zhang, K. Vincent, S. Lam and D. Henze, *Synth. Commun.*, 2012, 42, 1622–1631.
- 16 (a) F. Würthner, S. Ahmed, C. Thalacker and T. Debaerdemaeker, *Chem.-Eur. J.*, 2002, 8, 4742-4750;
 (b) J. C. Collings, S.-Y. Poon, C. L. Droumaguet, M. Charlot, C. Katan, L. O. Palsson, A. Beeby, J. A. Mosely, H. M. Kaiser, D. Kaufmann, W.-Y. Wong, M. Blanchard-Desce and T. B. Marder, *Chem.-Eur. J.*, 2009, 15, 198-208;
 (c) A. J. Zucchero, P. L. McGrier and U. H. F. Bunz, *Acc. Chem. Res.*, 2010, 43, 397-408.
- 17 (a) A. R. Morales, A. Frazer, A. W. Woodward, H.-Y. Ahn-White, A. Fonari, P. Tongwa, T. Timofeeva and K. D. Belfield, J. Org. Chem., 2013, 78, 1014–1025; (b) S. K. Das, C. S. Lim, S. Y. Yang, J. H. Han and B. R. Cho, Chem. Commun., 2012, 48, 8395–8397; (c) S. K. Bae, C. H. Heo, D. J. Choi, D. Sen, E.-H. Joe, B. R. Cho and H. M. Kim, J. Am. Chem. Soc., 2013, 135, 9915–9923; (d) D. Firmansyah, A. I. Ciuciu, V. Hugues, M. Blanchard-Desce, L. Flamigni and D. T. Gryko, Chem.–Asian J., 2013, 8, 1279–1294; (e) O. Mongin, L. Porres, M. Charlot, C. Katan and M. Blanchard-Desce, Chem.–Eur. J., 2007, 13, 1481–1498.
- 18 (a) H. M. Kim and B. R. Cho, *Chem.-Asian J.*, 2011, 6, 58–69; (b) M. Barzoukas and M. Blanchard-Desce, *J. Chem. Phys.*, 2000, 113, 3951–3959.
- 19 J. R. Brewer, M. Schiek, I. Wallmann, H.-G. Rubahn, M. Schiek, I. Wallmann and H.-G. Rubahn, *Opt. Commun.*, 2008, 281, 3892–3896.
- 20 C. A. Schneider, W. S. Rasband and K. W. Eliceiri, *Nat. Methods*, 2012, **9**, 671–675.
- 21 N. S. Makarov, M. Drobizhev and A. Rebane, *Opt. Express*, 2008, **16**, 4029–4047.
- 22 D. T. Gryko, A. Janiga and M. Krzeszewski, *New, strongly fluorescent heterocycles and a method of their preparation*, PCT/PL2013/050025, 2013.