Contents lists available at SciVerse ScienceDirect

Chinese Chemical Letters



journal homepage: www.elsevier.com/locate/cclet

Original article

Supported *N*-propylsulfamic acid on magnetic nanoparticles used as recoverable and recyclable catalyst for the synthesis of 2,3-dihydroquinazolin-4(1H)-ones in water

Amin Rostami ^{a,*}, Bahman Tahmasbi ^b, Hoshyar Gholami ^b, Hajir Taymorian ^b

^a Young Researchers and Elites Club, Sanandaj Branch, Islamic Azad University, Sanandaj, Iran

^b Department of Chemistry, Faculty of Science, University of Kurdistan, Zip Code 66177-15175, Sanandaj, Iran

ARTICLE INFO

Article history: Received 7 September 2012 Received in revised form 5 December 2012 Accepted 10 December 2012

Keywords: Magnetic nanoparticles N-Propylsulfamic acid Nanocatalyst 2,3-Dihydroquinazolin-4(1H)-ones Cyclocondensation Anthranilamide

ABSTRACT

An efficient and eco-friendly method is reported for the synthesis of 2-substituted-2,3-dihydroquinazolin-4(1*H*)-ones from direct cyclocondensation of anthranilamide with aldehydes and ketones using *N*-propylsulfamic acid supported onto magnetic Fe₃O₄ nanoparticles (MNPs-PSA) as a recoverable and recyclable nanocatalyst in good to excellent yields in water at 70 °C. The catalyst was readily separated using an external magnet and reusable without significant loss of their catalytic efficiency.

© 2013 Amin Rostami. Published by Elsevier B.V. on behalf of Chinese Chemical Society. All rights reserved.

1. Introduction

Magnetic nanoparticles are efficient, readily available, highsurface-area resulting in high catalyst loading capacity and outstanding stability heterogeneous supports for catalysts [1]. More importantly, magnetic separation of the magnetic nanoparticles is more effective than filtration or centrifugation [2], simple, economical and promising for industrial applications [3]. Among the various magnetic nanoparticles used as the core magnetic support, Fe_3O_4 nanoparticles are arguably the most extensively studied [4] because of their simple synthesis, low cost, and relatively large magnetic susceptibility [5]. Recently, preparation and application of several supported catalysts on magnetic Fe_3O_4 nanoparticles have been reported [6–11].

2,3-Dihydroquinazolin-4(1*H*)-ones are an important class of fused heterocycles with a wide range of pharmaceutical and biological activities [12]. These compounds can easily be oxidized to their quinazolin-4(3*H*)-one analogues [13], which also include important pharmacologically active compounds [14]. Various methods have already been proposed for the synthesis of these compounds [15]. A general procedure for the synthesis of

2,3-dihydroquinazolin-4(1*H*)-ones involves the condensation reaction of anthranilamide with aldehyde or ketone in the presence of various promoting agents [16–23]. Although reported methods produce good results in many instances, the development of efficient, simple, easy work-up and environmentally benign protocols using recyclable catalysts and green solvents for the synthesis of these important compounds is still desirable and in demand.

Sulfamic acid (H₂NSO₃H, SA), a common inorganic acid, is nonvolatile, noncorrosive, stable, water resistance and incapable of forming complexes, making it an outstanding alternative to metal catalysts in different areas of organic synthesis as an efficient and green reagent [24,25]. The main drawback of SA just like any heterogeneous or homogeneous catalyst is its separation from the reaction mixture by filtration or liquid–liquid techniques which cause the loss of catalyst in many reactions. To overcome this drawback, SA can be immobilized on magnetic nanoparticles. In recent years, organic reactions in aqueous media have received high priority in view of green methodology [26].

2. Experimental

* Corresponding author. E-mail address: a.rostamir@uok.ac.ir (A. Rostami). General procedure for the synthesis of 2,3-dihydroquinazolin-4(1H)-ones: The MNPs-PSA (10 mg) was added to a mixture of anthranilamide (1 mmol, 0.136 g) and aldehyde or ketone

1001-8417/\$ – see front matter © 2013 Amin Rostami. Published by Elsevier B.V. on behalf of Chinese Chemical Society. All rights reserved. http://dx.doi.org/10.1016/j.cclet.2013.01.032





Scheme 1. MNPs-PSA catalyzes the synthesis of 2,3-dihydroquinazolin-4(1*H*)-ones in water.



Scheme 2. Synthesis of MNPs-PSA: (a) 3-aminopropyltriethoxysilane, ethanol/ water, rt, 8 h and (b) chlorosulfuric acid, dichloromethane, rt, 2 h.

(1 mmol) in water (2 mL). Then the mixture was stirred for the appropriate time at 70 °C. The progress was monitored by TLC. After completion of the reaction, the reaction mixture was cooled to room temperature. CH_2Cl_2 (2 × 5 mL) was added and the catalyst was separated by an external magnet. The resulting mixture was washed with brine (10 mL) and dried over anhydrous Na₂SO₄. CH_2Cl_2 was evaporated under reduced pressure to afford the essentially pure products. In some cases, the product was recrystalized from ethanol for further purification.

3. Results and discussion

In continuation of our efforts in the development of green synthetic methodologies [27–30], herein we report catalytic application of MNPs-PSA as magnetically heterogeneous nanocatalysts for the synthesis of 2-substituted-2,3-dihydroquinazolin-4(1H)-ones from direct cyclocondensation of anthranilamide with aldehydes or ketones in water at 70 °C (Scheme 1).

Initially, the MNPs-PSA was synthesized according to the method reported recently with some modifications as shown in Scheme 2 [31]. Magnetite (Fe_3O_4) nanoparticles were prepared by coprecipitation of iron (II) and iron (III) ions in basic solution at 85 °C using the method described [32].

The catalyst has been characterized by scanning electron microscopy (SEM), Fourier transform infrared spectroscopy (FT-IR), X-ray diffraction (XRD) and by comparisons with authentic sample. A SEM image of MNPs-PSA is shown in Fig. 1A. It was confirmed that the catalyst was made up of nanometer-sized particles. The IR spectrum of MNPs-PSA shows peaks that are characteristic of a functionalized SA group, which clearly



Fig. 2. Image showing MNPs-PSA can be separated by applied magnetic field. A reaction mixture in the absence (right) or presence of a magnetic field (left).

differentiates from that of the unfunctionalized Fe_3O_4 nanomagnets and aminopropyl-functionalized magnetic nanoparticles (Fig. 1B). XRD pattern of MNPs-PSA is shown in Fig. 1C, the position and relative intensities of all peaks confirm well. To determine the acid amount on the surface, the prepared catalyst (100 mg) was added to an aqueous NaCl solution (1 mol/L, 10 mL) with an initial pH 5.93. The mixture was stirred for 0.5 h after which the pH of solution decreased to 1.72, indicating an ion exchange between sulfamic acid protons and sodium ions, this is equal to a loading of 1.9 mmol/g of sulfamic acid group. This result confirmed by backtitration of the catalyst.

Subsequently, in order to optimize the reaction conditions, we evaluated the influence of different amounts of catalyst on the model cyclocondensation reaction of anthranilamide (1 mmol) and 4-methoxybenzaldehyde (1 mmol) in water at 70 °C on reaction time and yield of product (Table 1). When adding catalyst, the reaction times were reduced, however 10 mg of MNPs-PSA was chosen as the desired condition.

In order to extend the scope of this cyclocondensation reaction, the various benzaldehyde derivatives, including electron-donating and electron-withdrawing groups on aromatic ring, terephthaldehyde and aliphatic ketones were investigated in the presence of the catalytic amount of MNPs-PSA in water at 70 °C, the results are summarized in Table 2.

As shown in Table 2, aromatic aldehydes electron-donating group yielded corresponding 2-substituted-2,3-dihydroquinazolin-4(1*H*)-ones in shorter reaction time and higher yield, whereas aromatic aldehydes with electron-withdrawing groups gave longer reaction times. For aliphatic ketones such as acetone and cyclohexanone, relatively slower reactions were observed (Table 2, entries 15 and 16). We have developed this synthetic method for the preparation of bis-2,3-dihydroquinazolin-4(1*H*)-one in a 2:1



Fig. 1. (A) SEM images of MNPs-PSA, (B) the comparative FT-IR spectra for (a) MNPs, (b) MNPs-APTMs and (c) MNPs-PSA, and (C) the XRD pattern of MNPs-PSA.

Table 1

Optimization of the amounts of MNPs-PSA for cyclocondensation reaction of anthranilamide (1 mmol) and 4-methoxybenzaldehyde (1 mmol) in water at 70 $^\circ C$.

| Entry | Catalyst (mg) | Time (min) | Yield (%) | | |
|-------|---------------|------------|-----------|--|--|
| 1 | 5 | 60 | 89 | | |
| 2 | 7 | 45 | 96 | | |
| 3 | 10 | 25 | 97 | | |
| 4 | 20 | 20 | 95 | | |
| 5 | 30 | 17 | 97 | | |

Table 2

MNPs-PSA catalyzed the synthesis of 2,3-dihydroquinazolin-4(1H)-ones in water at 70 $^\circ\text{C.}^a$

| Entry | Aldehyde | Time (min) | Yields (%) ^b | Mp (°C) [Ref.] |
|-------|--|---------------|----------------------------|----------------|
| 1 | C ₆ H₅CHO | 35 | 97 | 220-222 [17] |
| 2 | 4-OH-C ₆ H ₄ CHO | 50 | 95 | 275-277 [17] |
| 3 | 4-CH ₃ OC ₆ H ₄ CHO | 25 | 97 | 191-193 [17] |
| 4 | 2,4-(CH ₃ O) ₂ C ₆ H ₄ CHO | 50 | 94 | 187-189 [17] |
| 5 | 3,4-(CH ₃ O) ₂ C ₆ H ₄ CHO | 30 | 95 | 214-216 [18] |
| 6 | 4-CH ₃ C ₆ H ₄ CHO | 30 | 93 | 231-233 [17] |
| 7 | 4-Br C ₆ H ₄ CHO | 60 | 91 | 198-200 [19] |
| 8 | 4-Cl C ₆ H ₄ CHO | 25 | 90 | 204-206 [17] |
| 9 | 2-Cl C ₆ H ₄ CHO | 35 | 91 | 210-211 [23] |
| 10 | 4-FC ₆ H ₄ CHO | 30 | 87 | 199-200 [17] |
| 11 | 2-NO ₂ C ₆ H ₄ CHO | 170 | 86 | 190–193 [17] |
| 12 | 3-NO ₂ C ₆ H ₄ CHO | 130 | 88 | 204-206 [17] |
| 13 | 2-naphthaldehyde | 140 | 86 | 222-224 [20] |
| 14 | terephthaldehyde | 80 | 89 | 245-247 [16] |
| 15 | acetone | 160 | 71 | 184-186 [21] |
| 16 | cyclohexanone | 110 | 79 | 223-225 [22] |

^a All the products are known and were characterized by IR, ¹H NMR and by melting point comparisons with those of authentic samples.

^b Isolated yields.

Table 3

Recycling of MNPs-PSA for cyclocondensation reaction of anthranilamide and 4-methoxylbenzaldehyde in water at 70 °C for 25 min.

| Cycle | 1st | 2nd | 3rd | 4th | 5th | 6th | 7th | 8th | 9th | 10th |
|---------------------------|-----|-----|-----|-----|-----|-----|-----|-----|-----|------|
| Recovered catalyst (%) | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 |
| Converted yield (%) | 97 | 97 | 97 | 97 | 95 | 95 | 91 | 87 | 84 | 80 |

molar ratio of anthranilamide and terephthaldehyde (Table 2, entry 14).

In order to show activity of MNPs-PSA, we subject the condensation of 2-nitrobenzaldehyde with anthranilamide in the absence of catalyst, in which the reaction did not occur even after prolonged reaction time.

Finally, the feasibility of re-use of MNPs-PSA was also investigated for cyclocondensation reaction of anthranilamide and 4-methoxylbenzaldehyde. We found that this catalyst demonstrated excellent recyclability, after each round, the mixture was dark brown in colour. The catalyst can be efficiently recovered from the product by exposing it to an external magnet, wherein the solution became very clear (Fig. 2).

The reaction solution was decanted. The remaining magnetic nanoparticles were further washed with CH_2Cl_2 to remove residual product, air-dried and used directly for next round of reaction without further treatment. The recycled catalyst was used for 10 times with little loss of activity (Table 3).

When the recycled catalyst (100 mg) was placed in aqueous NaCl solution (1mol/L, 10 mL), the pH of solution was 3.4 and a loading of 0.04 mmol/g was obtained. This analysis showed the activity of the catalyst was decreased after 10 runs.

4. Conclusion

In summary, MNPs-PSA as a eco-friendly, efficient and magnetically recoverable catalyst was used in synthesis of 2,3dihydroquinazolin-4(1*H*)-ones by direct cyclocondensation of anthranilamide and aryl aldehydes or ketones with good to high yields in water. The characteristic advantages of this catalyst are rapid, simple and efficient separation by using an appropriate external magnet, which minimizes the loss of catalyst during separation, and reusable without significant loss of activity up to 10 cycles. In addition, MNPs-PSA couples the advantages of heterogeneous and homogeneous SA-based systems, which make it as a promising material for industry.

References

- C.O. Dalaigh, S.A. Corr, Y.G. Ko, S.J. Connon, A magnetic-nanoparticle-supported 4-N,N-dialkylaminopyridine catalyst: excellent reactivity combined with facile catalyst recovery and recyclability, Angew. Chem. Int. Ed. 46 (2007) 4329–4332.
- [2] D. Guin, B. Baruwati, S.V. Manorama, Pd on surface-modified NiFe₂O₄ nanoparticles: a magnetically recoverable catalyst for Suzuki and Heck reactions, Org. Lett. 9 (2007) 1419–1421.
- [3] S. Laurent, D. Forge, M. Port, et al., Magnetic iron oxide nanoparticles: synthesis, stabilization, vectorization, physicochemical characterizations, and biological applications, Chem. Rev. 108 (2008) 2064–2110.
- [4] C.T. Yavuz, J.T. Mayo, W.W. Yu, et al., Low-field magnetic separation of monodisperse Fe₃O₄ nanocrystals, Science 314 (2006) 964–967.
- [5] K.T.S. Alexander, L.G. Robin, Simple preparation and application of TEMPO-coated Fe₃O₄ superparamagnetic nanoparticles for selective oxidation of alcohols, Chem. Eur. J. 16 (2010) 12718–12726.
- [6] R. Abu-Reziq, H. Alper, D. Wang, M.L. Post, Metal supported on dendronized magnetic nanoparticles: highly selective hydroformylation catalysts, J. Am. Chem. Soc. 128 (2006) 5279–5282.
- [7] V. Polshettiwar, R. Luque, A. Fihri, et al., Magnetically recoverable nanocatalysts, Chem. Rev. 111 (2011) 3036–3075.
- [8] B. Karimi, E. Farhangi, Highly recyclable magnetic core-shell nanoparticle-supported TEMPO catalyst for efficient metal- and halogen-free aerobic oxidation of alcohols in water, Chem. Eur. J. 17 (2011) 6056–6060.
- [9] Y.H. Liu, J. Deng, J.W. Gao, Z.H. Zhange, Triflic acid-functionalized silica-coated magnetic nanoparticles as a magnetically separable catalyst for synthesis of gemdihydroperoxides, Adv. Synth. Catal. 354 (2012) 441–447.
- [10] H. Yang, G. Li, Z. Ma, Magnetic core-shell-structured nanoporous organosilica microspheres for the Suzuki-Miyaura coupling of aryl chlorides: improved catalytic activity and facile catalyst recovery, J. Mater. Chem. 22 (2012) 6639-6648.
- [11] H. Yang, Y. Wang, Y. Qin, et al., One-pot preparation of magnetic N-heterocyclic carbene-functionalized silica nanoparticles for the Suzuki–Miyaura coupling of aryl chlorides: improved activity and facile catalyst recovery, Green Chem. 13 (2011) 1352–1361.
- [12] Y. Xia, Z.N. Yang, M. Hour, et al., Antitumor agents. Part 204: synthesis and biological evaluation of substituted 2-aryl quinazolinones, Bioorg. Med. Chem. Lett. 11 (2001) 1193–1196.
- [13] R.J. Abdel-Jalil, W. Volter, M.A. Saeed, Novel method for the synthesis of 4(3H)quinazolinones, Tetrahedron Lett. 45 (2004) 3475–3476.
- [14] J.F. Liu, J. Lee, A.M. Dalton, et al., Microwave-assisted one-pot synthesis of 2,3-disubstituted 3H-quinazolin-4-ones, Tetrahedron Lett. 46 (2005) 1241– 1244.
- [15] D.J. Connolly, D. Cusack, T.P. O'Sullivan, P.J. Guiry, Synthesis of quinazolinones and quinazolines, Tetrahedron 61 (2005) 10153–10202, and references therein.
- [16] M. Baghbanzadeh, P. Salehi, M. Dabiri, G. Kozehgary, Water-accelerated synthesis of novel bis-2,3-dihydroquinazolin-4-(1H)-one derivatives, Synthesis (2006) 344–3448.
- [17] J.X. Chen, D.Z. Wu, F. He, et al., Gallium(III) triflate-catalyzed one-pot selective synthesis of 2,3-dihydroquinazolin-4(1H)-ones and quinazolin-4(3H)-ones, Tetrahedron Lett. 49 (2008) 3814–3818.
- [18] M. Dabiri, P. Salehi, S. Otokesh, G. Kozehgary, A.A. Mohammadi, Efficient synthesis of mono- and disubstituted 2,3-dihydroquinazolin-4(1H)-ones using KAl(SO₄)₂·12H₂O as a reusable catalyst in water and ethanol, Tetrahedron Lett. 46 (2005) 6123-6126.
- [19] A. Davoodnia, S. Allameh, A.R. Fakhari, N. Tavakoli-Hoseini, Highly efficient solvent-free synthesis of quinazolin-4(3H)-ones and 2,3-dihydroquinazolin-4(1H)-ones using tetrabutylammonium bromide as novel ionic liquid catalyst, Chin. Chem. Lett. 21 (2010) 550–553.
- [20] A. Rostami, A. Tavakoli, Sulfamic acid as a reusable and green catalyst for efficient and simple synthesis of 2-substituted-2,3-dihydroquinazolin-4(1H)-ones in water or methanol, Chin. Chem. Lett. 22 (2011) 1317–1320.
- [21] R.Z. Qiao, B.L. Xu, Y.H. Wang, A facile synthesis of 2-substituted-2,3-dihydro-4(1H)-quinazolinones in 2,2,2-trifluoroethanol, Chin. Chem. Lett. 18 (2007) 656–658.

- [22] H.R. Shaterian, A.R. Oveisi, PPA-SiO₂ as a heterogeneous catalyst for efficient synthesis of 2-substituted-1,2,3,4-tetrahydro-4-quinazolinones under solventfree conditions, Chin. J. Chem. 27 (2009) 2418–2422.
- [23] M. Wang, T.T. Zhang, Y. Liang, J.J. Gao, Strontium chloride-catalyzed one-pot synthesis of 2,3-dihydroquinazolin-4(1H)-ones in protic media, Chin. Chem. Lett. 22 (2011) 1423–1426.
- [24] M.M. Heravi, B. Baghernejad, H.A. Oskooie, Application of sulfamic acid in organic synthesis, Curr. Org. Chem. 13 (2009) 1002–1014.
- [25] A. Santra, G. Guchhait, A.K. Misra, Efficient acylation and sulfation of carbohydrates using sulfamic acid, a mild, eco-friendly catalyst under organic solventfree conditions, Green Chem. 13 (2011) 1345–1351.
- [26] N. Shapiro, A. Vigalok, Highly efficient organic reactions "on water", "in water", and both, Angew. Chem. Int. Ed. 120 (2008) 2891–2894.
- [27] A. Rostami, J. Akradi, A highly efficient, green, rapid, and chemoselective oxidation of sulfides using hydrogen peroxide and boric acid as the catalyst under solventfree conditions, Tetrahedron Lett. 51 (2010) 3501–3503.

- [28] A. Rostami, F. Ahamad-Jangi, Sulfamic acid: an efficient, cost-effective and green catalyst for crossed-aldol condensation of ketones with aromatic aldehydes under solvent-free, Chin. Chem. Lett. 22 (2011) 1029–1032.
- [29] A. Khazaei, A. Rostami, F. Mantashlo, p-Toluenesulfonyl chloride as a new and effective catalyst for acetylation and formylation of hydroxyl compounds under mild conditions, Chin. Chem. Lett. 21 (2010) 14–30.
- [30] A. Rostami, A. Khazaei, H.A. Alavi-Nik, Z. Toodeh-Roosta, Formylation of alcohol with Formic acid under solvent-free and neutral conditions catalyzed by free I₂ or I₂ generated, in situ from Fe(NO₃)₃·9H₂O/Nal, Chin. J. Catal. 32 (2011) 60–64.
- [31] M.Z. Kassaee, H. Masrouri, F. Movahedi, Sulfamic acid-functionalized magnetic Fe₃O₄ nanoparticles as an efficient and reusable catalyst for one-pot synthesis of α -amino nitriles in water, Appl. Catal. A: Gen. 395 (2011) 28–30.
- [32] X. Liu, Z. Ma, J. Xing, H.J. Liu, Preparation and characterization of amino-silane modified superparamagnetic silica nanospheres, Magn. Magn. Mater. 270 (2004) 1–6.