

View Article Online View Journal

# ChemComm

## Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: Z. Xu, C. Cao, X. Liu, Q. Qiao, M. Zhao, W. Yin, D. Mao and H. Zhang, *Chem. Commun.*, 2014, DOI: 10.1039/C4CC08010F.



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/chemcomm

### ChemComm

# Journal Name

Cite this: DOI: 10.1039/x0xx00000x

Received 00th January 2012,

Accepted 00th January 2012

DOI: 10.1039/x0xx00000x

www.rsc.org/

### COMMUNICATION

**RSCPublishing** 

View Article Online DOI: 10.1039/C4CC08010F

# Published on 29 October 2014. Downloaded by State University of New York at Stony Brook on 30/10/2014 11:51:08.

# A twisted-intramolecular-charge-transfer (TICT) based ratiometric fluorescent thermometer with a mega-Stokes shift and a positive temperature coefficient

Cheng Cao,<sup>*ab*</sup> Xiaogang Liu,\*<sup>*bc*</sup> Qinglong Qiao,<sup>*b*</sup> Miao Zhao,<sup>*b*</sup> Wenting Yin,<sup>*b*</sup> Deqi Mao,<sup>*b*</sup> Hui Zhang\*<sup>*a*</sup> and Zhaochao Xu\*<sup>*b*</sup>

The fluorescence intensity of *N*,*N*-dimethyl-4-((2methylquinolin-6-yl)ethynyl)aniline, exhibits an unusual intensification with increasing temperature, by activating more vibrational bands and leading to stronger TICT emissions upon heating in dimethyl sulfoxide. Based on the different temperature dependence at various wavelengths of the TICT fluorescence spectrum, this dye can be employed to ratiometrically detect temperature.

Fluorescent thermometers have been actively investigated for visualizing temperature distribution in micro-environment with high spatial and temporal resolutions, i.e., in cells and micro-fluidic devices.<sup>1-8</sup> Most of such thermometers are based on temperature-sensitive organic dyes (such as rhodamine B) or inorganic complexes of ruthenium or europium, whilst their emission intensities/lifetimes decrease with rising temperature (owing to the thermal activation of nonradiative deexcitation pathways), and this correlation affords temperature information.<sup>9-13</sup> Recently, CdSe quantum dots<sup>14</sup> and ZnO microcrystals<sup>15</sup> have also been reported as nano-thermometers, which, however, still possess a negative temperature coefficient. In contrast, fluorescent probes with a positive temperature coefficient, whose emission intensities increase with temperature, are particularly desirable, because they can effectively suppress background interference at high temperature; they can also work in conjunction with one fluorophore with a negative temperature coefficient, where ratiometric measurements of their emission intensities provide a built-in correction and allow quantitative detection of temperature with a high sensitivity.<sup>2,16-19</sup> To this end, a number of polymer-based fluorescent thermometers, which consist of a thermo-responsive polymer and a polarity-sensitive fluorophore fragment (such as benzofurazan), have been reported with positive temperature coefficients,<sup>20-22</sup> because polymers offer a decreasing micro-environmental polarity around the fluorophore with a rise in temperature. Unfortunately, these polymer-based thermometers require complicated synthesis procedures; their temperature sensing functionality only operates around the polymer phase transition point (where significant micro-polarity changes occur) and the corresponding working range is thus limited (*i.e.*, < 10 °C). A fluorophore with

a positive temperature coefficient has also been reported based on the thermally activated delayed fluorescence of fullerene  $C_{70}$ , whilst increasing temperature facilitates the back-forth transitions between the excited states  $S_1$  (singlet) and  $T_1$ (triplet).<sup>23</sup> Nevertheless, such an effect is vulnerable to oxygen quenching, posing a significant limitation to its application environment. Consequently, the development of new fluorescent thermometers, preferably with positive temperature coefficients, ratiometric measurements and a wide working range becomes an important research target.

In this work, we propose and demonstrate a new design concept to achieve a positive temperature coefficient in a fluorescent thermometer, employing the twistedintramolecular-charge-transfer (TICT) emission of N.Ndimethyl-4-((2-methylquinolin-6-yl)ethynyl)aniline (1; Scheme 1) in dimethyl sulfoxide (DMSO). TICT emission is typically weak, because emission from the zero vibrational level of TICT state is forbidden; in contrast, the radiative transitions from TICT to ground states are feasible via the assistance of higher and non-totally symmetrical vibrational bands of TICT state.<sup>24</sup> These vibrational bands become activated upon heating. Consequently, the TICT emission intensity will become intensified with increasing temperature, provided that the increase in TICT emission rate exceeds that of non-emissive deexcitation



Compound 1 was synthesized in good yield as shown in Scheme 1 (Supporting Information; Fig. S1—S3). The UV—vis absorption solvatochromism of 1 is very weak (Fig. 1a). For example, the peak UV—vis absorption wavelength ( $\lambda_{abs}$ ) of 1 changes from 332 nm in *n*-hexane to 338 nm in DMSO, by only

Published on 29 October 2014. Downloaded by State University of New York at Stony Brook on 30/10/2014 11:51:08.

6 nm. In contrast, the peak emission wavelength ( $\lambda_{em}$ ) of 1 in solution varies considerably from non-polar to polar solvents (Fig. 1b). For instance, peak  $\lambda_{em}$  is registered at 380 nm in *n*hexane and ~550 nm in DMSO, with a change of ~170 nm. The substantial bathochromic shift in peak  $\lambda_{em}$  results in a mega-Stokes shift of ~210 nm in DMSO. A mega-Stokes shift is beneficial for reducing the overlap between the UV—vis absorption and emission spectra of a fluorophore and minimizing the re-absorption of the emitted photons (*via* the so called "inner-filter" effect), and thus improves the signal-tonoise ratio of fluorescent imaging.<sup>25</sup>



Fig. 1 (a) The UV—vis absorption and (b) fluorescence spectra of **1** in various solvents. (c) The Lippert-Mataga plot for the fluorescence transition energies of **1**. [**1**] = 10  $\mu$ M; the fluorescence spectra were obtained by exciting the samples at their respective peak UV—vis absorption wavelengths. Note that the scales in (b) is arbitrary, owing to varied slit sizes in use; please refer to Table S1 for exact fluorescence quantum yields in various solvents.

It is worth noting that the emission spectrum of 1 in *n*-hexane exhibits a clear shoulder; however, the fluorescence spectra become featureless with large Stokes shifts, as solvent polarity increases (Fig. 1b). Moreover, the transition energies of the fluorescence  $(v_{em})$  and  $\Delta f$ , the orientation polarisability (eq. 1), demonstrate an approximate linear relationship in most solvents, except that in *n*-hexane in a Lippert-Mataga plot (correlation coefficient, r = 0.9287; Fig. 1c; Table S1). Interestingly, by re-plotting  $v_{em}$  against  $\Delta f'$  (eq. 2; which is applicable when TICT state is formed upon the photoexcitation of a dye), an even higher correlation coefficient of 0.9507 is obtained (excluding data in *n*-hexane; Fig. S4).<sup>26</sup> These unusual spectral characteristics indicate the formation of TICT state in the excited state of 1.

$$\Delta f = \frac{\varepsilon - 1}{2\varepsilon + 1} - \frac{n^2 - 1}{2n^2 + 1}$$
(eq. 1)

$$\Delta f' = \frac{\varepsilon - 1}{\varepsilon + 2} - \frac{n^2 - 1}{2n^2 + 4}$$
Vie(eqti2)Online
DOI: 10.1039/C4CC08010

where  $\varepsilon$  and *n* refer to the relative dielectric constant and refractive index of a solvent, respectively.

The formation of TICT state in 1 can be further rationalised via both viscosity-dependent emission measurements and density functional theory (DFT) based calculations. In the mixtures of ethanol and glycerol at various ratios, the UV-vis absorption spectra of 1 remain little changed (Fig. 2a). In contrast, as more glycerol is added into the mixture, affording a higher viscosity, the corresponding emission intensity of 1 is significantly enhanced, *i.e.*, by approximately three times from pure ethanol to pure glycerol (Fig. 2b). Such viscositydependent fluorescence intensification is a typical characteristic of TICT emission.<sup>24, 27</sup> Furthermore, DFT calculations show that the photo-excitation of 1 from the  $S_0$  to  $S_1$  state mainly involves electron transitions from the highest occupied molecular orbital (HOMO) to both the lowest occupied molecular orbital (LUMO) and LUMO+1 (Fig. 2c). Such transitions result in substantial intramolecular charge transfer (ICT) from the phenyl ring to the quinolone ring of 1. The large extent of ICT is accompanied by significant molecular geometry relaxation and drives the formation of TICT state at the excited state of 1, via the rotation of the dimethyl-amino group. The substantial geometry relaxation in conjunction with the greatly increased polarity of 1 in the TICT state is responsible for the mega-Stokes shift of 1 and its large fluorescence solvatochromism.25,28



Fig. 2 (a) The UV—vis absorption and (b) fluorescence spectra of 1 in ethanolglycerol mixtures. [1] = 5  $\mu$ M; the fluorescence spectra were obtained by exciting the samples at 380 nm. (c) The frontier molecular orbitals of 1 in DMSO, obtained via DFT calculations.

The emission intensities of 1 between ~450 and ~600 nm exhibit an *unusual* positive temperature coefficient, with a temperature coefficient of 0.5% per °C, while that in the long wavelength region (> 600 nm) decreases slightly with increasing temperature in DMSO (Fig. 3a). Accordingly, the fluorescence quantum yield of 1 increases as temperature rises in DMSO (Table S2). This extraordinary effect can be rationalised considering the nature of TICT emissions. As temperature rises, more vibrational bands at higher energy levels in TICT state become active, which boosts the probability of radiative electron transitions from TICT to ground states. Not surprisingly, the associated peak emission wavelength of 1 also displays a blue-shift from 551 nm at 25 °C to 538 nm at 65 °C, because TICT emissions associated with Published on 29 October 2014. Downloaded by State University of New York at Stony Brook on 30/10/2014 11:51:08.

**Journal Name** 

higher vibrational bands contribute relatively more as temperature increases (Fig. 3a).<sup>24</sup>

It should be pointed out the overall temperature dependence of fluorescence intensity depends on two competing factors, the rates of radiative TICT emission and non-emissive deexcitation. Both rates increase with rising temperature. While the former is relatively more significant, such as in DMSO, **1** demonstrates a positive temperature coefficient (Fig. 3a); in contrast, an inverse trend is found in other solvents, such as ethyl acetate (EA; Fig. 3b), owing to more substantial non-emissive deexcitation at high temperature. Consequently, the emission quantum yield of 1 drops with increasing temperature (Table S2). In fact, the fluorescence intensities of most TICT dyes decrease at high temperature.<sup>11</sup>



**Fig. 3** Temperature dependence of the fluorescence spectra of (a) **1** in DMSO excited at 360 nm ([**1**] = 5  $\mu$ M); (b) **1** in EA excited at 360 nm ([**1**] = 1  $\mu$ M); (c) the mixture of **1** and rhodamine 6G in DMSO excited at 330 and 540 nm, respectively; [**1**] = 5  $\mu$ M; [rhodamine 6G] = 1  $\mu$ M. Temperature was varied from 25 to 65 °C at a step change of 10 °C. The corresponding temperature dependence of emission intensity ratios and the associated best-fit equations of (d) **1** in DMSO at 500 and 600 nm; (e) **1** in EA at 440 and 520 nm; (f) **1** and rhodamine 6G mixture in DMSO at 500 at 500 and 563 nm.

The different temperature dependence of TICT emissions at varied wavelengths can be employed for ratiometric temperature measurements (Fig. 3). The ratios of emission intensities at 500 and 600 nm in DMSO ([1] = 5  $\mu$ M;  $\lambda_{ex}$  = 360 nm) affords an excellent linear correlation with temperature changes, which demonstrates the potential of using 1 as a thermometer (Fig. 3d). A similar temperature calibration curve has also been constructed in other solvents, *i.e.*, EA, although the overall emission intensity of 1 drops as temperature increases in this case (Fig. 3e). The reversibility of this fluorescence system was also investigated by heating and cooling it between 25 °C and 65 °C at a step change of 10 °C for 10 cycles in DMSO. The fluorescence intensities at different temperatures remain consistent among all cycles, demonstrating an excellent reversibility.

Compound **1** can also work in conjunction with a temperature sensitive fluorophore, *i.e.*, rhodamine 6G with a negative temperature coefficient, to ratiometrically detect temperature in DMSO (Fig. 3c, f). It is interesting to note that Förster resonance energy transfer (FRET) from **1** to rhodamine 6G occurs in this mixture, because the UV—vis absorption

spectrum of rhodamine 6G (represented by the grey shadowed area in Fig. 3c) matches the emission spectrum of **1** very well. As a result, an emission peak at 567 nm<sub>D</sub> wing 59 checkman 6G, became apparent even when the mixture was excited at 330 nm.

The TICT based thermometer of 1 circumvents several limitations of existing fluorescence temperature sensors. Fluorescence lifetime based thermometers require relatively long measurement time and sophisticated equipment.<sup>11</sup> Fluorescence intensity based measurements are more straightforward. However, the emission intensity also depends on dye concentration and illumination intensity. Careful initial calibration is thus unavoidable when a single type of dyes is employed in a thermometer. While a ratiometric thermometer using two types of dyes with distinct temperature coefficients provides a built-in correction, these two types of dyes may photo-bleach at different rates, thus compromising the reliability of the thermometer.<sup>4</sup> Moreover, the inhomogeneous distribution of dyes (or concentration ratios) in a complex system is a major concern for accurate interpretations of emission intensity signals for both the one-dye and two-dye thermometers. In contrast, the thermometer based on 1 offers a ratiometric temperature sensing mechanism, while only one type of dyes is employed. This self-calibration effect makes the thermometer insensitive to dye concentration variations and photo-bleaching effects, thus greatly improving measurement accuracy. In addition, although the emission brightness of TICT dyes is normally low, the quantum yields of 1 are good, measured to be 55.2% and 18.9% at 25 °C in EA and DMSO, respectively (Table S2). Since the temperature calibration curve of 1 is solvent-dependent and viscosity-dependent, this thermometer is most suitable for a system with minimal solvent and viscosity variations. It can also serve as a calibration reference for existing one-dye and two-dye thermometers to further gauge their accuracies, i.e., in cells where the environment mostly consists of water.

In conclusion, we have demonstrated a TICT induced emission system with a positive temperature coefficient and a mega-Stokes shift based on 1. This unusual positive temperature coefficient is realised by significantly activating vibrational bands of TICT state, which greatly facilitates TICT emissions with respect to non-emissive deexcitation with a rise in temperature. Owing to different temperature dependence of TICT fluorescence at various wavelengths, the intensity ratios of these emissions can be used to ratiometrically detect temperature. It is expected that this new sensor design strategy will have a significant impact on the development of ratiometric fluorescent thermometers. However, 1 has poor solubility in aqueous solution and relatively short absorption wavelengths. Developing water-soluble and bathochromically shifted TICT dyes is the subject of our future work, for measuring temperature in biological systems. The molecular origins of the unusually high quantum yields and positive temperature coefficients associated with the TICT emission of 1 are also currently under investigation.

Z.X. thank financial supports from the National Natural Science Foundation of China (21276251; 21422606), Ministry of Human Resources and Social Security of PRC, the 100 talents program funded by Chinese Academy of Sciences. X.L. thanks National Research Foundation of Singapore for the SMART Scholar Postdoctoral Scholarship.

### Notes and references

Published on 29 October 2014. Downloaded by State University of New York at Stony Brook on 30/10/2014 11:51:08.

<sup>a</sup>The School Pharmaceutical Engineering, Shenyang Pharmaceutical University, Shenyang 110016, China. E-mail: zh19683@163.com

<sup>b</sup>Key Laboratory of Separation Science for Analytical Chemistry, Dalian Institute of Chemical Physics, Chinese Academy of Sciences, Dalian 116023, China. E-mail: zcxu@dicp.ac.cn

<sup>c</sup>Singapore-MIT Alliance for Research and Technology (SMART) Centre, 1 CREATE Way, Singapore 138602, Singapore. E-mail: xgliu83@gmail.com

Electronic Supplementary Information (ESI) available: synthesis, characterization, experimental and computational details.

- C. Gosse, C. Bergaud and P. Low, in *Thermal Nanosystems and Nanomaterials*, ed. S. Volz, 2009, vol. 118, 301-341.
- 2. E. J. McLaurin, L. R. Bradshaw and D. R. Gamelin, *Chem. Mater.*, 2013, **25**, 1283-1292.
- T. Ozawa, H. Yoshimura and S. B. Kim, Anal. Chem., 2013, 85, 590-609.
- X. D. Wang, O. S. Wolfbeis and R. J. Meier, *Chem. Soc. Rev.*, 2013, 42, 7834-7869.
- Z. Yang, J. Cao, Y. He, J. H. Yang, T. Kim, X. Peng and J. S. Kim, *Chem. Soc. Rev.*, 2014, 43, 4563-4601.
- K. Okabe, N. Inada, C. Gota, Y. Harada, T. Funatsu and S. Uchiyama, Nat. Commun., 2012, 3, 705.
- S. Kiyonaka, T. Kajimoto, R. Sakaguchi, D. Shinmi, M. Omatsu-Kanbe, H. Matsuura, H. Imamura, T. Yoshizaki, I. Hamachi, T. Morii and Y. Mori, *Nat. Methods*, 2013, 10, 1232-1238.
- T. J. Johnson, D. Ross and L. E. Locascio, Anal. Chem., 2001, 74, 45-51.
- N. Chandrasekharan and L. A. Kelly, J. Am. Chem. Soc., 2001, 123, 9898-9899.
- S. Ryu, I. Yoo, S. Song, B. Yoon and J. M. Kim, J. Am. Chem. Soc., 2009, 131, 3800-3801.
- J. Feng, K. Tian, D. Hu, S. Wang, S. Li, Y. Zeng, Y. Li and G. Yang, Angew. Chem., Int. Ed., 2011, 50, 8072-8076.
- Y. Jiang, X. Yang, C. Ma, C. Wang, Y. Chen, F. Dong, B. Yang, K. Yu and Q. Lin, *ACS Appl Mater Interfaces*, 2014, 6, 4650-4657.
- V. F. Pais, J. M. Lassaletta, R. Fernandez, H. S. El-Sheshtawy, A. Ros and U. Pischel, *Chemistry (Weinheim an der Bergstrasse, Germany)*, 2014, 20, 7638-7645.
- L. M. Maestro, E. M. Rodriguez, F. S. Rodriguez, M. C. la Cruz, A. Juarranz, R. Naccache, F. Vetrone, D. Jaque, J. A. Capobianco and J. G. Sole, *Nano Lett.*, 2010, **10**, 5109-5115.
- S. L. Shinde and K. K. Nanda, Angew. Chem., Int. Ed., 2013, 52, 11325-11328.
- Y. Takei, S. Arai, A. Murata, M. Takabayashi, K. Oyama, S. Ishiwata, S. Takeoka and M. Suzuki, ACS Nano, 2014, 8, 198-206.
- T. Kan, H. Aoki, N. Binh-Khiem, K. Matsumoto and I. Shimoyama, Sensors (Basel, Switzerland), 2013, 13, 4138-4145.
- A. E. Albers, E. M. Chan, P. M. McBride, C. M. Ajo-Franklin, B. E. Cohen and B. A. Helms, *J. Am. Chem. Soc.*, 2012, **134**, 9565-9568.
- F. Ye, C. Wu, Y. Jin, Y. H. Chan, X. Zhang and D. T. Chiu, J. Am. Chem. Soc., 2011, 133, 8146-8149.
- C. Gota, K. Okabe, T. Funatsu, Y. Harada and S. Uchiyama, J. Am. Chem. Soc., 2009, 131, 2766-2767.

- S. Uchiyama, Y. Matsumura, A. P. de Silva and K. Iwai, *Anal. Chem.*, 2004, **76**, 1793-1798.
- S. Uchiyama, N. Kawai, A. P. de Silva and K. J. Wats / CARE OR MARK Soc., 2004, 126, 3032-3033.
- C. Baleizão, S. Nagl, S. M. Borisov, M. Schäferling, O. S. Wolfbeis and M. N. Berberan - Santos, *Chemistry-A European Journal*, 2007, 13, 3643-3651.
- 24. Z. R. Grabowski, K. Rotkiewicz and W. Rettig, *Chem. Rev.* (*Washington, DC, U. S.*), 2003, **103**, 3899-4032.
- 25. X. Liu, Z. Xu and J. M. Cole, J. Phys. Chem. C, 2013, 117, 16584– 16595.
- B. Valeur, Molecular Fluorescence: Principles and Applications, John Wiley & Sons, 2013.
- 27. M. K. Kuimova, G. Yahioglu, J. A. Levitt and K. Suhling, J. Am. Chem. Soc., 2008, **130**, 6672-6673.
- X. Liu, J. M. Cole and K. S. Low, J. Phys. Chem. C, 2013, 117, 14731-14740.

4 | J. Name., 2012, 00, 1-3