This article was downloaded by: [Northeastern University] On: 08 January 2015, At: 13:49 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



## Molecular Crystals and Liquid Crystals Publication details, including instructions for authors and subscription information:

http://www.tandfonline.com/loi/gmcl20

# Structures in Langmuir-Blodgett Films of Amphiphilic Tetrathiafulvalenes and Tetrafluorotetracyanoquinodimethane CT Complex

Yoko Tatewaki <sup>a</sup> , Shuji Okada <sup>a</sup> , Junko Takizawa <sup>b</sup> , Tatsuya Hatanaka <sup>c</sup> , Mutsumi Kimura <sup>b c</sup> & Hirofusa Shirai <sup>b c</sup>

<sup>a</sup> Department of Polymer Science and Engineering , Graduate School of Science and Engineering, Yamagata University , Yonezawa, Japan

<sup>b</sup> Collaborative Innovation Center for Nanotech FIBER, Shinshu University, Ueda, Japan

<sup>c</sup> Department of Functional Polymer Science , Faculty of Textile Science and Technology, Shinshu University , Ueda, Japan Published online: 19 Apr 2010.

To cite this article: Yoko Tatewaki , Shuji Okada , Junko Takizawa , Tatsuya Hatanaka , Mutsumi Kimura & Hirofusa Shirai (2010) Structures in Langmuir-Blodgett Films of Amphiphilic Tetrathiafulvalenes and Tetrafluorotetracyanoquinodimethane CT Complex, Molecular Crystals and Liquid Crystals, 519:1, 157-162, DOI: <u>10.1080/15421401003613584</u>

To link to this article: http://dx.doi.org/10.1080/15421401003613584

## PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms &

Conditions of access and use can be found at <u>http://www.tandfonline.com/page/terms-and-conditions</u>



*Mol. Cryst. Liq. Cryst.*, Vol. 519: pp. 157–162, 2010 Copyright © Taylor & Francis Group, LLC ISSN: 1542-1406 print/1563-5287 online DOI: 10.1080/15421401003613584

# Structures in Langmuir-Blodgett Films of Amphiphilic Tetrathiafulvalenes and Tetrafluorotetracyanoquinodimethane CT Complex

## YOKO TATEWAKI,<sup>1</sup> SHUJI OKADA,<sup>1</sup> JUNKO TAKIZAWA,<sup>2</sup> TATSUYA HATANAKA,<sup>3</sup> MUTSUMI KIMURA,<sup>2,3</sup> AND HIROFUSA SHIRAI<sup>2,3</sup>

<sup>1</sup>Department of Polymer Science and Engineering, Graduate School of Science and Engineering, Yamagata University, Yonezawa, Japan
<sup>2</sup>Collaborative Innovation Center for Nanotech FIBER, Shinshu University, Ueda, Japan
<sup>3</sup>Department of Functional Polymer Science, Faculty of Textile Science and Technology, Shinshu University, Ueda, Japan

An asymmetric TTF derivative 1 having two arms substituted by amide and chiral groups was synthesized and its CT complex with 2,3,5,6-tetrafluoro-7,7',8,8'tetracyano-p-quinodimethane  $(1-F_4TCNQ)$  were also prepared. Thin film formation at the air-water interface and the film deposition on substrates of 1 and  $1-F_4TCNQ$ were investigated. When we deposited the film of  $1-F_4TCNQ$  prepared on pure water onto a mica surface by a single upstroke withdrawal, curved nanowire structures were observed on the thin films. On the contrary, 1 without  $F_4TCNQ$  showed threedimensional dome structures on the thin films, and the morphologies of the Langmuir-Blodgett (LB) films depended on the existence of  $F_4TCNQ$ . An average dimension of nanowire was 6.0 (height)  $\times$  500 (width)  $\times$  10000 (length) nm<sup>3</sup>.

Keywords Charge transfer; chirality; helical structures; hydrogen bonds; nanostructures

### 1. Introduction

Molecular-assembly nanostructures are interesting for the future technologies since they can be used as basic parts of electronic devices in a nanometer scale. Generally, such nanostructures are constructed by the combination of intermolecular interactions such as electrostatic, charge-transfer (CT), hydrogen-bonding and van der Waals interactions. For example, supramolecular approaches, which have a structural flexibility to form nanostructures with a variety of sizes and shapes [1], are effective methods to obtain novel low-dimensional molecular-assembly

Address correspondence to Yoko Tatewaki, Department of Polymer Science and Engineering, Graduate School of Science and Engineering, Yamagata University, Yonezawa, Yamagata 992-8510, Japan. E-mail: ytatewa@yz.yamagata-u.ac.jp



Scheme 1. TTF derivative 1.

nanostructures such as nanodots and nanowires [2]. The other approach is utilization of the LB technique. This technique provides a way of arranging the molecules by the orientational effect at the air-water interface as well as surface pressure applied. These characteristics of the LB method can give rise to well ordered monolayer packing in a two-dimensional (2D) layer [3]. In addition, the LB method using amphiphilic conducting molecules is promising for building conduction paths [4–8]. In the previous study, we have reported gel formation originated from molecular-assembly nanostructures composed of tetrathiafulvalene (TTF) derivatives, which have four arms substituted by amide and chiral groups, and 2,3,5,6-tetrafluoro-7,7',8,8'tetracyano-*p*-quinodimethane (F<sub>4</sub>TCNQ) [7]. The intermolecular hydrogen bonding among chiral amide end-groups and the formation of CT complexes result in a long one-dimensional supramolecular stacking, and the chirality of the end-groups affects the molecular orientation of TTF cores within the stacks.

In the present study, we synthesized an asymmetric TTF derivative 1 having two arms substituted by amide and chiral groups as shown in Scheme 1. Its organization into supramolecular assemblies were investigated for 1 and its CT complex with  $F_4TCNQ$  (1- $F_4TCNQ$ ) by using the LB technique.

#### 2. Experimental

Compound 1 was prepared by referring the procedure for the similar compounds described in the literature 7.  $F_4TCNQ$  was purchased from Tokyo Chemical Industry Co., Ltd. The solution of the CT complex 1- $F_4TCNQ$  was prepared by mixing the same amount of solutions of 1 in CHCl<sub>3</sub> (1 mM) and  $F_4TCNQ$  in CH<sub>3</sub>CN (1 mM). A conventional LB trough (USI, USI-3-22) was used for formation of the films and their depositions. Solution of 1 or 1- $F_4TCNQ$  was spread on the pure water as a subphase. The floating layer at the air-water interface was maintained for 20 min after spreading the solution. Surface pressure-area per molecule ( $\pi$ -A) isothermes were recorded at 291 K. Deposition surface pressures of 1 and the CT complex were 20 mNm<sup>-1</sup> and 13 mNm<sup>-1</sup>, respectively. For atomic force microscopy (AFM) observation, the films at the air-water interface were transferred onto a freshly-cleaved mica surface by the LB method with a single up-stroke withdrawal. AFM images were taken by a JSPM-5400 (JEOL) operating in a tapping mode by using microcantilevers of spring constant of 0.2 Nm<sup>-1</sup>. For UV-Vis spectral measurements, 20 layers of the films were transferred by the horizontal

lifting method on to quartz substrates  $(30 \times 10 \times 1 \text{ mm}^3)$ , which were treated by hexamethyldisilazane (HMDS) vapour to be hydrophobic. UV-Vis spectra were recorded on a Hitachi U-4100. Column chromatography was performed with activated alumina (Wako, 200 mesh) or Wakogel C-200. Recycling preparative gel permeation chromatography was carried out by a JAI recycling preparative HPLC using CHCl<sub>3</sub>. Analytical thin-layer chromatography was performed with commercial Merck plates coated with silica gel 60 F254 or aluminum oxide 60 F254.

Compound 1: A solution of  $CsOH \cdot H_2O$  (700 mg, 4.2 mmol) in methanol (10 mL) was added to a solution of 4,5-bis(2'-cyanoethylthio)-1,3-dithiole-2-thione (931 mg, 2.0 mmol) in acetonitrile (50 mL) over 10 min with stirring at room temperature. After stirring for 30 min, hexylbromide having (S)-methylbenzylamide endgroup (3.0 g, 10.1 mmol) was added, and the reaction mixture was stirred for 24 h. The reaction mixture was concentrated in vacuo, and water (50 mL) was added. The aqueous solution was extracted with CH<sub>2</sub>Cl<sub>2</sub> and the combined organic layer was washed with water. After drying with NaSO<sub>4</sub>, the solvent was evaporated, and the residue was purified by column chromatography (silica, CHCl<sub>3</sub>), to afford 1 as an orange powder (0.84 g, 53%). <sup>1</sup>H NMR (400.13 MHz, CDCl<sub>3</sub>):  $\delta$  = 7.28 (m, 10H, Ar-H), 5.90 (q, J = 8.0 Hz, 2H, N-H), 5.10 (m, 2H, -COCNHCHCH<sub>3</sub>), 2.81 (t, 4H, J = 6.60 Hz, -SCH<sub>2</sub>), 2.42 (t, 4H, J = 7.20 Hz, -CH<sub>2</sub>CONH-), 2.15 (m, 6H, -CH<sub>3</sub>), 1.62 (m, 10H, -SCH<sub>2</sub>CH<sub>2</sub>), -CONHCHCHCH<sub>3</sub>), 1.52 ppm (m, 8H, -SCH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>).

#### 3. Result and Discussion

Figure 1 shows  $\pi$ -A isotherms of the Langmuir film of neutral donor 1 and the CT complex 1-F<sub>4</sub>TCNQ. Formations of stable floating layers were confirmed by sharp increases of the surface pressure during compression. The surface area extrapolated at 0 mNm<sup>-1</sup> of 1-F<sub>4</sub>TCNQ monolayer was  $A_0 = 0.8$  nm<sup>2</sup>. A kink of the  $\pi$ -A isotherm was observed at around 20 mNm<sup>-1</sup>. Compound 1 showed the same behavior on the



Figure 1.  $\pi$ -A isotherms of 1 and 1-F<sub>4</sub>TCNQ on pure water at 291 K.



Figure 2. Surface morphologies of transferred films of (a) 1 and (b) 1-F<sub>4</sub>TCNQ by a single withdrawal from pure water.

 $\pi$ -A isotherm as 1-F<sub>4</sub>TCNQ although the film of 1 formed the hard film and the surface pressure arose over 30 mNm<sup>-1</sup>. The area per molecule at the deposition surface pressure of 1 was 0.18 nm<sup>2</sup> at 20 mNm<sup>-1</sup> ( $A_{20}$ ) and that of 1-F<sub>4</sub>TCNQ was 0.22 nm<sup>2</sup> at  $\pi = 13$  mNm<sup>-1</sup> ( $A_{13}$ ). Given that the  $A_{13}$  and  $A_{20}$  values are same as the areas of one close-packed alkyl chains (0.20 nm<sup>2</sup>). The area per molecule of neutral donor 1 should be 0.4 nm<sup>2</sup>, because this compound has two alkyl chains (0.20 nm<sup>2</sup> × 2). Our results indicate that the floating layers of 1 and 1-F<sub>4</sub>TCNQ didn't create the monolayers.

Figure 2 shows AFM images of LB film composed of 1 and 1-F<sub>4</sub>TCNQ transferred onto mica by a single withdrawal. The AFM image of 1 showed the thin films



Figure 3. UV-Vis spectra of 20-layer multilayer films of 1 and 1-F<sub>4</sub>TCNQ transferred from pure water.

with thickness of about 4 nm and the three-dimensional (3D) dome-type aggregates with a typical dimension of  $\sim 1.2 \times 1.2 \,\mu\text{m}^2$  (Fig. 2a). The formation of nanowires wasn't observed for neutral donor 1, the neutral 1 was assembled together and aggregated. On the other hand, 1-F<sub>4</sub>TCNQ formed the thin films with thickness of about 6 nm and the curved nanowires with an average dimension of 6.0 (height)  $\times$  500 (width)  $\times$  10000 (length) nm<sup>3</sup> were observed on the thin films (Fig. 2b). The nanowires were distributed randomly on the substrate. From these results, we can conclude that the molecular organization of synthesized TTF molecules is a combination of the formation of one-dimensional charge transfer stacks and hydrogen bonding among chiral amide groups.

UV-vis spectra of multilayer films (20 layers) of 1 and 1-F<sub>4</sub>TCNQ were measured from 200 to 600 nm (Fig. 3). The complex 1-F<sub>4</sub>TCNQ showed larger absorbance in the whole range measured than 1. In particular, the shoulder band at 391 nm of 1-F<sub>4</sub>TCNQ is originated from the intramolecular charge transfer between TTF and TCNQ [9,10]. The absorption band at 320 nm for the LB film of the complex 1-F<sub>4</sub>TCNQ are assigned to the neutral TTF of 1 indicating the partial CT state.

#### 4. Conclusion

Thin films of 1 and 1-F<sub>4</sub>TCNQ were formed on a pure water subphase and deposited on substrate surfaces by LB technique. The LB techniques were useful for arrangement of molecules. Both films deposited on to the mica surfaces showed 2D thin films. However, in addition to the thin films, 1 showed the 3D dome-type aggregates and 1-F<sub>4</sub>TCNQ showed the molecular-assembly curved nanowires. Large network structures of conductive nanowires will open new possibilities for the construction of soft electronic nanocircuits like neuronal networks, and 1-F<sub>4</sub>TCNQ and its derivatives may be used for such applications. Finally, large network structures of conductive nanowires will open new possibilities for the construction of soft electronic nano-circuits such as neuronal networks.

### Acknowledgment

This work was partly supported by a Grant-in-Aid for Science Research from the Ministry of Education, Culture, Sports, Science and Technology of Japan.

#### References

- Hamley, I. W. (2000). Introduction to Soft Matter Polymers, Colloids, Amphiphiles and Liquid Crystals, John Wiley & Sons: Weinheim.
- [2] Klabunde, K. L. Ed. (2001). Nanoscale Materials in Chemistry, Wiley & Sons: NY.
- [3] Bryce, M. R. & Petty, M. C. (1995). Nature, 374, 771.
- [4] Akutagawa, T., Ohta, T., Hasegawa, T., Nakamura, T., & Christensen, C. A. (2002). J. Becher, Proc. Nat. Acad. Sci., 99, 5028.
- [5] Miyata, H., Tatewaki, Y., Akutagawa, T., Hasegawa, T., Nakamura, T., Christensen, C. A., & Becher, J. (2003). *Thin Solid Films*, 438–439, 1.
- [6] Tatewaki, Y., Akutagawa, T., Hasegawa, T., Nakamura, T., & Becher, J. (2003). Synthetic Metals, 137, 933.
- [7] (a) Akutagawa, T., Kakiuchi, K., Hasegawa, T., Nakamura, T., & Christensen, C. A. (2004). J. Becher, Langmuir, 20, 4187; (b) Tatewaki, Y., Hatanaka, T., Tsunashima, R., Nakamura, T., Kimura, M., & Shirai, H. (2009). Chem. Asian J., 4, 1474.

- [8] (a) Nielsen, M. B., Lomholt, C., & Becher, J. (2000). *Chem. Soc. Rev.*, 29, 153; (b) Nielsen, M. B. & Becher, J. (1997). *Liebigs Ann. Recueil*, 2177; (c) Simonsen, K. B., Svenstrup, N., Lau, J., Simonsen, O., Mork, P., Kristensen, C. J., & Becher, J. (1996). *Synthesis*, 407.
- [9] Torrance, J. P., Mayerle, J. J., & Bechgaard, K. (1980). Phys. Rev. B., 22, 4960.
- [10] Jacobsen, C. S. (1988). Optical Properties in Semiconductor and Semimetals. In: *High Conducting Quasi-One-Dimensional Organic Crystals*, Conwell, E. (Ed.), Academic Press: NY.