Ionic liquid crystal as a hole transport layer of dye-sensitized solar cells

Noriyo Yamanaka,^a Ryuji Kawano,^b Wataru Kubo,^a Takayuki Kitamura,^a Yuji Wada,^a Masayoshi Watanabe^b and Shozo Yanagida^{*c}

Received (in Cambridge, UK) 19th November 2004, Accepted 20th December 2004 First published as an Advance Article on the web 12th January 2005 DOI: 10.1039/b417610c

Use of a new ionic liquid crystal, 1-dodecyl-3-methylimidazolium iodide, and iodine as an electrolyte of dye-sensitized solar cells leads to a high short circuit photocurrent density and a high light-to-electricity conversion efficiency, due to a selfassembled structure of the imidazolium cations, resulting in high conductivity of the electrolyte.

Dye-sensitized solar cells (DSSC), constructed by using dye molecules, nanocrystalline metal oxides and liquid electrolytes, have attractive features in terms of the high light-to-electricity conversion efficiency, and the low production cost and energy.¹ The electrolytes, usually composed of an I^-/I_3^- redox couple in organic solvents, are sealed between two electrodes. These organic solvents cause a serious problem of low durability due to evaporation.² It has been reported that DSSC using ionic liquids as a non-volatile solvent achieves high temperature stability.^{3,4} However, the conversion efficiency of the cells using ionic liquids is lower than that using organic solvents, because the high viscosity of the ionic liquids retards the physical diffusion of I^- and I_3^- . Many attempts to reduce the viscosity have not yet been successful.⁵ For enhancing the conductivity of ionic liquids leading to the high light-to-electricity conversion efficiency of DSSC, it seems to be necessary to arrange a pathway for fast charge transport.

Previously, we reported that the charge transport rate at high concentration of an I^{-/I₃⁻ redox couple in ionic liquids can be} attributed to the exchange reaction of $I^- + I_3^- \rightarrow I_3^- + I^{-.4,6}$ For enhancing the short circuit photocurrent density (J_{SC}) of DSSC using ionic liquids with a high concentration of an I^-/I_3^- redox couple, the exchange reaction in the ionic liquids needs to be promoted. In this study, we report a new strategy for enhancing the conductivity of ionic liquid electrolytes; employing an ionic liquid crystal (ILC) as a constituent of an electrolyte, which forms a self-assembled structure and promotes the exchange reaction by the locally increased concentrations of I^- and I_3^- . We have selected 1-dodecyl-3-methylimidazolium iodide (C12MImI) as an ILC. This provides a self-assembled structure of the imidazolium cations like a solid, while maintaining the molecular dynamics like a liquid. The ILC with the smectic A phase (SA) has a bilayer structure of interdigitated alkyl chains of the imidazolium cations, and I^- and I_3^- would be localized between the S_A layers. The locally high concentration would promote the exchange reaction. So, the ILC with the SA phase would be suitable for the electrolyte of DSSC when aiming at the high light-to-electricity conversion efficiency.

Imidazolium iodides with long alkyl chains were synthesized by the quaternization reaction of 1-methylimidazole with an equimolar amount of the corresponding alkyl iodide for 72 h under N₂ atmosphere at room temperature. The products were washed with n-hexane to remove the remaining starting materials and dried under vacuum at 40 °C for 4 h, and finally identified by ¹H NMR in CDCl₃ and differential scanning calorimetry (DSC). Imidazolium iodides with alkyl chains longer than C₁₂ showed a liquid crystalline phase. C₁₂MImI showed the lowest melting point and viscosity among them and these properties were suitable for the hole transport layer in DSSC. In this study, we selected C12MImI and applied it with 0.65 M iodine (C12MImI/I2) as the hole transport layer in DSSC. We have compared the properties of C12MImI/I2 with an ionic liquid electrolyte; 1-undecyl-3-methylimidazolium iodide with 0.65 M iodine (C₁₁MImI/I₂).

 $C_{12}MImI$ showed a phase transition from a liquid to a liquid crystal at 80 °C, although $C_{11}MImI$ did not show a liquid crystalline phase. The ionic liquid crystalline phase of $C_{12}MImI$ was confirmed by polarized optical microscopy (POM). The characteristic focal conic domains observed during the cooling process suggested that the liquid crystalline phase of $C_{12}MImI$ was a $S_{\rm A}$ phase.⁷

Photoelectrochemical cells were fabricated as previously described.⁹ $C_{11}MImI/I_2$ and $C_{12}MImI/I_2$ were used as the hole transport layer, respectively. $C_{12}MImI/I_2$ maintained the S_A phase ranging from 27 to 45 °C on heating. On the other hand, $C_{11}MImI/I_2$ showed a liquid phase above 37 °C.

The light-to-electricity conversion efficiencies of DSSC using $C_{12}MImI/I_2$ and $C_{11}MImI/I_2$ were evaluated at 40 °C under AM 1.5 irradiation from a solar simulator, adaptable for amorphous silicon solar cells according to the Japanese Industrial Standard.¹⁰ Each value for cell performance was taken as an average of at least 3 samples.

Fig. 1 shows photocurrent–voltage curves of the DSSC using $C_{12}MImI/I_2$ and $C_{11}MImI/I_2$. J_{SC} of the DSSC using $C_{12}MImI/I_2$ was higher than that using $C_{11}MImI/I_2$, while the open circuit voltage (V_{OC}) and fill factor (FF) were the almost same values as

A few examples of the ILC with the S_A phase, such as imidazolium salts consisting of cations with alkyl chains of C_{12} – C_{18} and anions of hexafluorophosphate or bromide, have been reported.^{7,8} Iodide is indispensable in a DSSC electrolyte, because the I^-/I_3^- redox couple functions as a hole transport agent. However, an imidazolium salt with iodide as the counter anion has not been reported to be an ILC with a S_A phase. Here, we show for the first time that imidazolium iodides with alkyl chains longer than C_{12} exhibit a S_A phase and that the liquid crystalline nature is preferable in terms of the hole transport layer in DSSC.

^{*}yanagida@mls.eng.osaka-u.ac.jp



Fig. 1 Photocurrent–voltage curves of the cells using $C_{12}MImI/I_2$ (bold solid curve) and $C_{11}MImI/I_2$ (solid curve) under AM 1.5 irradiation.

for C₁₁MImI/I₂. This result suggests that the higher conductivity of C₁₂MImI/I₂ than C₁₁MImI/I₂ could lead to a high J_{SC} .^{11,12}

To examine the conductivities of $C_{12}MImI/I_2$ and $C_{11}MImI/I_2$, the diffusion-limited currents (I_{lim}) corresponding to the reaction of $I_3^- + 2e^- \rightarrow 3I^-$ were measured. The measurements were carried out at 40 °C by using a microelectrode and the diffusion coefficients (*D*) of I_3^- were calculated using the values of I_{lim} as previously described.⁶ According to this study, the *D* value calculated from I_{lim} intrinsically includes not only the simple physical diffusion coefficient but also the diffusion coefficient based on the exchange reaction.

The observed D value of $C_{12}MImI/I_2$ (4.2 × 10⁻⁸ cm² s⁻¹) was 1.3 times as large as that of $C_{11}MImI/I_2$ (3.2 \times 10⁻⁸ cm² s⁻¹), while the viscosity of C12MImI/I2 was 2.5 times larger than that of $C_{11}MImI/I_2$. The simple physical diffusion coefficient of $C_{12}MImI/I_2$ I_2 should be smaller than $C_{11}MImI/I_2$. This result would lead to the idea that the diffusion coefficient based on the exchange reaction is increased in C12MImI/I2. It has been reported that anisotropic long-range conductive pathways between the SA layers are formed in liquid crystals with a SA phase.¹³ In C₁₂MImI/I₂, these pathways should be formed, and I^- and I_3^- should be located between the SA layers consisting of the imidazolium cations. If a locally high concentration of I^- and I_3^- is achieved in the pathways, the exchange reaction should be promoted in C12MImI/I2, since the diffusion coefficient value based on the exchange reaction is proportional to the concentrations of I⁻ and I_3^- . So, $C_{12}MImI/I_2$ could show a higher D value than $C_{11}MImI/I_2$ I_2 in which the cations should exist at random.

To prove that the exchange reaction was promoted in the pathways between the S_A layers of $C_{12}MImI/I_2$, we measured the ionic conductivities along the direction parallel ($\sigma_{i\parallel}$) and perpendicular ($\sigma_{i\perp}$) to the S_A layer plane¹³ at temperatures ranging from 32.5 to 57.5 °C. A glass plate with comb-shaped platinum electrodes (cell A) and a pair of indium tin oxide (ITO) electrodes (cell B) were employed for the measurements of $\sigma_{i\parallel}$ and $\sigma_{i\perp}$, respectively. The conoscopic image at 40 °C for $C_{12}MImI/I_2$ revealed that the self-assemblies of the cations formed a homeotropic alignment in the S_A phase on the glass surface.

Fig. 2 shows anisotropic ionic conductivities of $C_{12}MImI/I_2$ and isotropic ionic conductivities of $C_{11}MImI/I_2$ as a function of temperature. It was reported that the ionic conductivities of isotropic ionic liquids gradually increased with the increase in temperature as shown in the insert of Fig. 2.¹⁴ In contrast, for $C_{12}MImI/I_2$, the discontinuous changes of ionic conductivities



Fig. 2 Ionic conductivities for the samples of $C_{12}MImI/I_2$ and $C_{11}MImI/I_2$ (insert) along with the direction parallel $\sigma_{i\parallel}$ (filled circles) and perpendicular $\sigma_{i\perp}$ (open triangles) to the S_A layer plane of the homeotropically aligned ionic liquid crystal.

were observed. The ionic conductivities parallel ($\sigma_{i\parallel}$) to the S_A layer of $C_{12}MImI/I_2$ decreased and those perpendicular ($\sigma_{i\perp}$) increased at 45 °C on heating. When the liquid crystalline phase-order disappeared above the phase transition temperature, the ionic conductivities measured in both cell A and cell B were on the same line within the limits of error. Taking into account that $C_{11}MImI/I_2$ did not show any discontinuous changes in $\sigma_{i\parallel}$ and $\sigma_{i\perp}$ over the whole temperature range, the discontinuous changes of $C_{12}MImI/I_2$ should be attributed to the conductive pathways formed between the S_A layers. The observed $\sigma_{i\parallel}$ values of $C_{12}MImI/I_2$ below 45 °C, which showed ionic conductivities along the direction of the conductive pathways, were enhanced because the exchange reaction would be promoted at the conductive pathways.

In the DSSC using $C_{12}MImI/I_2$, although the long-range order of ILC was not necessarily achieved in the mesoporous TiO₂ electrode, the localization of I⁻ and I₃⁻ between the S_A layers of each domain should result in the promotion of the exchange reaction in a hole transport layer and the enhancement in J_{SC} .

In conclusion, we have demonstrated a new strategy for enhancing the conductivity of the ionic liquid electrolytes containing an I^-/I_3^- redox couple. This strategy is based on the promotion of the exchange reaction between I^- and I_3^- by the locally increased concentrations of I^- and I_3^- . As a means of demonstrating this strategy, a new ionic liquid crystalline $C_{12}MImI/I_2$ with a self-assembled structure of the imidazolium cations was introduced. $C_{12}MImI/I_2$ showed a high ionic conductivity in spite of its high viscosity. The ionic liquid crystalline hole transport layer ($C_{12}MImI/I_2$) was applied to DSSC, which showed a higher J_{SC} and a higher light-to-electricity conversion efficiency than that using the ionic liquid hole transport layer ($C_{11}MImI/I_2$).

This research was supported in part by the New Energy and Industrial Technology Development Organization (NEDO) under the Ministry of Economy, Trade and Industry.

Noriyo Yamanaka,^a Ryuji Kawano,^b Wataru Kubo,^a Takayuki Kitamura,^a Yuji Wada,^a Masayoshi Watanabe^b and Shozo Yanagida^{*c}

^aMaterial and Life Science, Graduate School of Engineering, Osaka

University, 2-1 Yamadaoka Suita, 565-0871, Japan.

E-mail: ywada@mls.eng.osaka-u.ac.jp

^bDepartment of Chemistry and Biotechnology, Yokohama National

University, 79-5 Tokiwadai, Hodogaya-ku, Yokohama, 240-8501,

Japan. E-mail: mwatanab@ynu.ac.jp

^cCenter for Advance Science and Innovation Osaka University, Japan. E-mail: yanagida@mls.eng.osaka-u.ac.jp

Notes and references

- M. K. Nazeeruddin, A. Kay, I. Rodicio, R. H. Baker, E. Mueller, P. Liska, N. Vlachopoulos and M. Grätzel, *J. Am. Chem. Soc.*, 1993, 115, 6382.
- 2 A. Kay and M. Grätzel, Sol. Energy Mater. Sol. Cells., 1996, 44, 99.
- 3 W. Kubo, T. Kitamura, K. Hanabusa, Y. Wada and S. Yanagida, *Chem. Comun.*, 2002, 374.

- 4 W. Kubo, K. Murakoshi, T. Kitamura, S. Yoshida, M. Haruki, K. Hanabusa, H. Shirai, Y. Wada and S. Yanagida, *J. Phys. Chem. B.*, 2001, **105**, 1280.
- 5 H. Matsumoto and T. Matsuda., *Electrochemistry*, 2002, 70, 190.
- 6 R. Kawano and M. Watanabe, Chem. Commun., 2003, 330.
- 7 C. M. Gordon, J. D. Holbrey, A. R. Kennedy and K. R. Seddon, J. Mater. Chem., 1998, 8, 2627.
- 8 A. E. Bradley, C. Hardacre, J. D. Holbrey and M. Nieuwenhuyzen., *Chem. Mater.*, 2002, 14, 629.
- 9 S. Nakade, S. Kambe, T. Kitamura, Y. Wada and S. Yanagida, J. Phys. Chem. B., 2001, 105, 9150.
- 10 Japanese Industrial Standard Committee, Japanese Industrial Standard, Solar simulators for amorphous solar cells and modules, JIS C 8933, Japanese Standards Association, Tokyo, 1995.
- 11 F. Pichot and B. A. Gregg, J. Phys. Chem. B., 2000, 104, 6.
- 12 W. Kubo, S. Kambe, S. Nakade, T. Kitamura, Y. Wada and S. Yanagida, J. Phys. Chem. B., 2003, 107, 4374.
- 13 M. Yoshio, T. Mukai, K. Kanie, M. Yoshizawa, H. Ohno and T. Kato, Adv. Mater., 2002, 14, 35.
- 14 A. B. McEwen, H. L. Ngo, K. LeCompte and J. L. Goldman, J. Electrochem. Soc., 1999, 146, 1687.