LANGMUIR

Subscriber access provided by Bethel University

Interfaces: Adsorption, Reactions, Films, Forces, Measurement Techniques, Charge Transfer, Electrochemistry, Electrocatalysis, Energy Production and Storage

Improving the Electropolymerization Properties of Fluorene-Bridged Dicarbazole Monomers through Polyfluoroalkyl Side Chains

Ilir Pecnikaj, Simonetta Orlandi, Gianluca Pozzi, Maria Victoria Cappellari, Gabriela Marzari, Luciana Fernandez, Maximiliano Andrés Zensich, Laura Hernandez, and Fernando Fungo

Langmuir, Just Accepted Manuscript • DOI: 10.1021/acs.langmuir.9b01141 • Publication Date (Web): 04 Jun 2019

Downloaded from http://pubs.acs.org on June 7, 2019

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.

is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036

Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

Langmuir

Improving the Electropolymerization Properties of Fluorene-Bridged Dicarbazole Monomers through Polyfluoroalkyl Side Chains

Ilir Pecnikaj, Simonetta Orlandi and Gianluca Pozzi *

Istituto di Scienze e Tecnologie Molecolari del Consiglio Nazionale delle

Ricerche, ISTM-CNR, Via Golgi 19, 20133 Milano, Italy

María Victoria Cappellari, Gabriela Marzari, Luciana Fernández, Maximiliano Andrés Zensich, Laura Hernandez, and Fernando Fungo^{*}

Departamento de Química, Universidad Nacional de Río Cuarto, Agencia Postal 3 (X5804BYA), Río Cuarto, Argentina.

ABSTRACT: The facile functionalization of the fluorene scaffold at the 2,7-positions was utilized to provide access to two soluble carbazole- π -carbazole derivatives **CFC-H1** and **CFC-F1** featuring fully hydrogenated- and polyfluorinated alkyl chains at the 9-position of the fluorene π -bridging unit, respectively. The optical and electrochemical properties of the new dicarbazoles were investigated. Their electrochemical polymerization over Pt and indium tin oxide electrodes allowed the generation of electro-active polymeric films, which physicochemical characteristics were strongly dependent on the kind of alkyl chain present on the fluorene bridge. In particular, the electropolymerization of the polyfluorinated monomer allowed the fabrication of thin films with good electrical conductivity, reversible electrochemical processes, electrochromic properties and enhanced water repellency with respect to its non-fluorinated analog.

Keywords: Polymers, Electrodeposition, Optoelectronic materials, Electrochromism

For Table of Contents only



INTRODUCTION

Considerable research efforts are currently devoted to the development of organic macromolecules and polymeric compounds for application in the production of electronic and optoelectronic devices.¹⁻⁴ Actually, a wealth of multifunctional materials with tailored physical characteristics can be obtained from a relatively restricted pool of unsaturated building blocks, thanks to ingenious organic synthesis techniques.^{5,6} It is thus possible to create organic conducting materials with adequate optical and electronic properties, which utilization can make a great contribution to the advancement of optoelectronic devices such as electrochromic windows,^{7,8} solar cells,^{9–12} and lighting systems.¹³ Inexpensive fluorene and carbazole derivatives are fit to this purpose. Indeed, conjugated materials featuring carbazole units either in the π -conjugated backbone or as pendant groups display excellent thermal and photochemical stabilities and possess high charge carrier mobility, making them attractive materials for a variety of applications.^{14–} ¹⁶ In an analogous way, fluorene and 9,9'-spirobifluorene derivatives showing high photoluminescence (PL) quantum yields and electroluminescence (EL) efficiencies, as well as high thermal stabilities, have drawn much attention.^{3,11,17–22} Finally, fluorene and carbazole units can be combined in the same molecular structure leading to a variety of compounds with interesting hole transporting and electroluminescence properties.^{23–27}

The materials used in the fabrication of optoelectronic devices must provide certain essential characteristics, such as: charge transport, strong interaction with light (absorption and/or emission), chemical stability that avoids material degradation when the device is operating, and a right relative position in the energy scale of the valence bands (VB)-conduction band (CB) regarding the devices contacts work function, which ensures the flow of charges in the correct directions. However, for a material to be useful, it must be apt to the formation and deposition of thin films (thicknesses in the order of

Langmuir

nanometers), which is a central aspect in the construction of optoelectronic devices. In this context, the electrodeposition of electroactive compounds is an attractive and promising technique for the production of organic material films, since it has the advantage to produce the film in one-step at room temperature, which requires that the monomer is soluble, polymerizable, and that the solubility of the generated polymer is low enough to induce its precipitation on the working electrode. It also has other advantages, such as permitting a fine control of the film thickness, variations of its morphology (e.g. porosity or roughness), an excellent adhesion of the electrodeposited film to the electrode, and the formation of patterns on the film.²⁸ In addition, the electropolymerization approach offers unique opportunities to tune the wettability properties of the obtained film by just using judicious chemical modifications of the monomer, although this strategy has been so far applied to a restricted number of monomer cores, such as thiophene and pyrrole derivatives.^{29–40} All these features are important parameters in the manufacture of optoelectronic devices.

In this context, the development of fluorene/carbazole hybrid monomers that can give rise to electrodeposited coatings is particularly appealing.^{41–45} In fact, carbazole and N-substituted carbazoles undergo electrochemical oxidative coupling under relatively low oxidation potential to give nitrogen- and ring-coupled dimers, respectively.⁴⁶ These characteristics enable the deposition of polymeric films over conductive substrates by electrochemical oxidation of monomers bearing at least two carbazole substituents.^{47–49} Thus, electropolymerizable fluorene-based monomers were designed in which the sp³ carbon atom of fluorene (9-position) is connected to the N atoms of two electroactive carbazole units through flexible alkyl linkers.^{44,45} In this case, efficient polymerization processes could be observed only for monomers containing at least two functionalized fluorene units.⁴⁴ The use of simple D- π -D conjugated monomers where two carbazoles

Page 5 of 34

Langmuir

donor groups D are directly linked to the phenyl rings of the π -bridging fluorene represents another viable option,⁴³ as also shown by early examples of electropolymerizable bipolar 9,9'-spirobifluorene derivatives.^{41,42} Besides ease of synthesis, this approach offers the opportunity to introduce tailored substituents at the 9-position of fluorene, in particular long alkyl- or polyfluoroalkyl chains, which could be used to facilitate the electropolymerization process and to tune the final properties of the electrodeposited material, as previously shown in the case of simple thiophene or pyrrole derivatives.²⁹⁻⁴⁰

It is well known that the introduction of highly fluorinated moieties in polymeric structures induces valuable features such as improved thermal stability, chemical and oxidative resistance, low dielectric constants and low refractive index, and oil and water repellency.⁵⁰ This last property is crucial for the long-term durability of optoelectronic devices, which is seriously challenged by the deleterious effects of moisture on the charged organic materials produced when the devices are operating.⁵¹ The optoelectronic characteristics of these fluorinated polymers are also very interesting. As an example, the replacement of hydrogen atoms with fluorine results in lower LUMO and HOMO energy states, producing enhanced EL efficiency, while the lower HOMO energies are responsible for increased oxidation potentials and enhanced stability against photooxidation.⁵² A limited number of conjugated poly- and oligofluorenes bearing poly- or perfluoroalkyl chains at the 9-position have been thus studied, focusing on their PL, EL and charge transport properties.^{53–58} The surface properties of these compounds, obtained by transition metal-catalyzed cross-coupling reactions preceded by cumbersome multistep syntheses of properly functionalized monomers, were not investigated. It should be also noted that the attempted electropolymerization of fluorene derivatives bearing a

single semifluorinated chain at the 9-position failed to give the corresponding polyfluorenes.⁵⁶

Based on these premises, we here report a facile electrochemical polymerization approach to the fabrication of conductive films starting from simple D- π -D conjugated carbazole-fluorene-carbazole (CFC) monomers bearing at the 9-position either alkyl- or polyfluoroalkyl chains of similar length (**Figure 1**). It will be shown that the nature of these substituents significantly improves the film formation and affects the morphology, water repellency and electrochromic behavior of the resulting materials.



Figure 1. Monomers structure.

EXPERIMENTAL SECTION

Synthesis procedures.

 General remarks. All available reagents were purchased from commercial sources and were used without any further purification. Solvents were purified by standard methods and dried if necessary. 2,7-Diiodo-9*H*-fluorene 1,⁵⁹ and 9,9-bis(*1H*,*1H*,*2H*,*2H*perfluorodecyl)-9*H*-fluorene 3^{57} were prepared as described in the literature. Reactions were monitored by thin layer chromatography (TLC) that was conducted on plates precoated with silica gel Si 60-F254 (Merck, Germany). Column chromatography was carried out on silica gel SI 60 (Merck, Germany), mesh size 0.063 – 0.200 mm (gravimetric) or 0.040 – 0.063 mm (flash). ¹H NMR and ¹³C NMR were recorded on a Bruker Avance 400 spectrometer (400 and 100.6 MHz, respectively); ¹⁹F NMR spectra

Langmuir

were recorded on a Bruker AC 300 spectrometer (282 MHz). Elemental analyses were carried out by the Departmental Service of Microanalysis (University of Milano).

*9,9-Didecyl-2,7-diiodo-9*H-*fluorene* (**2**). Powder KOH (1.00 g, 17.9 mmol) was added to a stirred solution of 2,7-diiodo-9*H*-fluorene **1** (1.67 g, 4.0 mmol) in DMSO (15 mL) under nitrogen atmosphere. After 5 min, KI (0.12 g, 0.7 mmol) was added, followed by 1-bromodecane (2.65 g, 12.0 mmol. The reaction mixture was stirred under nitrogen for 15 h at RT, then it was poured into H₂O (100 mL). The aqueous phase was extracted with Et₂O (3 x 30 mL). The combined organic phases were dried over MgSO₄ and evaporated under reduced pressure. The residue was purified by column chromatography (silica gel, petroleum ether) to give the bis alkylated fluorene **2** as a pale yellow oil (1.90 g, 68%.). ¹H NMR (400 MHz, CDCl₃) δ 7.67 – 7.60 (m, 4H), 7.40 (d, *J* = 8.4 Hz, 2H), 1.91-1.86 (m, 4H), 1.29-1.05 (m, 28H), 0.86 (t, *J* = 6.6 Hz, 6H), 0.63-0.52 (m, 4H); ¹³C NMR (101 MHz, CDCl₃) δ 152.51, 139.77, 136.03, 132.03, 121.52, 93.16, 55.56, 40.10, 31.91, 29.88, 29.55 (2CH2), 29.32, 29.21, 23.65, 22.71, 14.17. Anal. calcd for C₃₃H₄₈I₂: C, 56.74; H, 6.93; found: C, 56.81; H, 7.03.

9,9-Bis(3,3,4,4,5,5,6,6,7,7,8,8,9,9,10,10,10-heptadecafluorodecyl)-2,7-diiodo-9H-fluorene (**4**). A 25 mL round-bottom flask equipped with a magnetic stir bar and a reflux condenser was charged with fluorene derivative **3** (1.06 g, 1.0 mmol), iodine (0.19 g, 0.75 mmol), iodic acid (0.09 g, 0.5 mmol), water (0.3 mL), acetic acid (7 mL) and 98% H₂SO₄ (0.06 mL). The mixture was heated under reflux for 4h under vigorous stirring, then it was cooled to RT. The white precipitate formed was filtered off, washed with water and dried under vacuum. It was then dissolved in the minimal amount of CH₂Cl₂ and reprecipitated by adding dry ethanol. The crude compound was further purified by column chromatography (silica gel, hexane) to give the title compound as a white solid (1.02 g, 78% yield). mp 117–118 °C; ¹H NMR (400 MHz, CDCl₃) δ 7.77 (d, *J* = 8.0 Hz, 2H), 7.69

(s, 2H), 7.47 (d, J = 8.0 Hz, 2H), 2.41 – 2.17 (m, 4H), 1.36 – 1.18 (m, 4H); ¹³C NMR (101 MHz, CDCl₃) δ 148.01, 139.76, 137.12, 131.73, 122.05, 120.57 – 107.19 (m, C₈F₁₇), 93.52, 54.93, 30.15, 26.14 (t, $J_{CF} = 22$ Hz); ¹⁹F NMR (377 MHz, CDCl₃) δ -81.73 (t, J = 9.6 Hz, 6F), -115.36 (s, 4F), -122.60 – -123.10 (m, 12F), -123.71 (s, 4F), -124.76 (s, 4F), -127.10 (s, 4F). Anal. calcd for C₃₃H₁₄F₃₄I₂: C, 30.25; H, 1.08; found: C, 30.13; H, 1.12.

9,9'-(9,9-didecyl-9H-fluorene-2,7-diyl)bis(9H-carbazole) (CFC-H1) A flamedried Schlenk tube equipped with a stir bar was charged with fluorene 2 (1.40 g, 2.0 mmol), carbazole (1.00 g, 6.0 mmol), dry K_2CO_3 (1.24 g, 9.0 mmol), copper bronze (0.77 g, 12.0 mmol), 18-crown-6 (0.16 g, 0.6 mmol) and dry 1,2-dichlorobenzene (15 mL) under nitrogen atmosphere. The reaction mixture was deaerated by freeze-pump-thaw cycles (3 times), purged with nitrogen and heated at 180 °C under stirring for 48h. The mixture was cooled to RT, diluted with DCM (30 mL) and filtered through a short pad of Celite. The organic solvents were removed by evaporation under vacuum and the residue was purified by flash column chromatography (silica gel, petroleum ether/DCM 10/1). The title compound was obtained as an off-white glassy solid (1.46 g, 94% yield). ¹H NMR (400 MHz, CDCl₃) δ 8.19 (d, J = 7.8 Hz, 4H), 7.99 (d, J = 7.8 Hz, 2H), 7.65 – 7.57 (m, 4H), 7.51 - 7.42 (m, 8H), 7.33 (ddd, J = 7.9, 6.5, 1.7 Hz, 4H), 2.08 - 1.99 (m, 4H), 1.36 - 1.05 (m, 28H), 0.91 - 0.96 (m, 4H), 0.83 (t, J = 6.9 Hz, 6H); ¹³C NMR (101 MHz, CDCl₃) & 152.89, 140.99, 139.55, 136.70, 125.96 (2 CH), 123.41, 121.86, 121.03, 120.42, 119.95, 109.77, 55.72, 40.23, 31.88, 30.03, 29.61, 29.56, 29.42, 29.28, 24.18, 22.65, 14.11. Anal. calcd for C₅₇H₆₄N₂: C, 88.09; H, 8.30; N, 3..60; found: C, 88.15; H, 8.46; N, 3.49.

9,9'-(9,9-bis(3,3,4,4,5,5,6,6,7,7,8,8,9,9,10,10,10-heptadecafluorodecyl)-9Hfluorene-2,7-diyl)bis(9H-carbazole) (CFC-F1). A flame-dried Schlenk tube equipped with a magnetic stir bar was charged with fluorene 4 (1.31 g, 1.0 mmol), carbazole

Langmuir

(0.50 g, 3.0 mmol), dry K₂CO₃ (1.07 g, 5.0 mmol), copper bronze (0.38 g, 6.0 mmol), 18crown-6 (79 mg, 0.3 mmol) and dry 1,2-dichlorobenzene (10 mL) under nitrogen atmosphere. The reaction mixture was deaerated by freeze-pump-thaw cycles (3 times), purged with nitrogen and heated at 180 °C under stirring for 60h. The mixture was cooled to RT, diluted with DCM (30 mL) and filtered through a short pad of Celite. The organic solvents were removed by evaporation under vacuum and the crude product was purified by flash column chromatography (silica gel, petroleum ether/DCM 6/1). The fractions containing the products were collected, evaporated to dryness and the residue was recrystallized from hexane to give the title compound as a white solid (0.87 g, 63% yield). mp 89–90 °C; ¹H NMR (400 MHz, CD₂Cl₂) δ 8.20 (d, J = 7.8 Hz, 4H), 8.11 (d, J = 8.0 Hz, 2H), 7.76 (dd, J = 8.0, 1.8 Hz, 2H), 7.72 (d, J = 1.7 Hz, 2H), 7.48 - 7.43 (m, 8H), 7.37 – 7.30 (m, 4H), 2.57 – 2.36 (m, 4H), 1.77 – 1.54 (m, 4H).¹³C NMR (101 MHz, CD₂Cl₂) δ 148.98, 141.37, 140.14, 138.45, 128.17, 126.64, 124.07, 122.71, 122.01, $120.94, 120.82, 110.11, 120.91 - 107.51 \text{ (m, } C_8F_{17}\text{)}, 55.86, 30.85, 26.80 \text{ (d, } J_{CF}\text{ = } 22 \text{ Hz}\text{)};$ ¹⁹F NMR (377 MHz, CDCl₃) δ -81.71 (t, J = 9.6 Hz, 6F), -115.42 (s, 4F), -122.60 - -123.04 (m, 12F), -123.69 (s, 4F), -124.60 (s, 4F), -127.08 (s, 4F). Anal. calcd for C₅₇H₃₀F₃₄N₂: C, 49.29; H, 2.18, N, 2.02; found: C, 49.18; H, 2.22, N, 1.96.

Optical and electrochemical characterization of monomers and polymers films.

For the optical characterization a diode array HP 8452 spectrometer and a Spex FluoroMax fluorometer were used to measure the absorption and fluorescence spectra, respectively. Spectra in 1,2-dichloroethane (DCE) solution were acquired at room temperature using 1 cm path length quartz cells.

The voltammetric characterization of the redox processes and electropolymerization of the monomers was performed with a CH Instrument 700 E

 pontentiostat using a silver wire quasi-reference electrode and a loop Pt as counter electrode in a conventional three-electrode cell. Pt disk, (2 mm in diameter) polished on a felt pad with 0.3 µm alumina and sequentially sonicated in water and absolute ethanol, was used as working electrode for the voltammetric characterization of the redox processes and indium tin oxide (ITO) electrodes (Delta Technologies) were used for the electropolymerization.

Electrochemical studies of monomers were carried out in DCE with 0.10 M tetra*n*-butylammonium hexafluorophosphate (TBAPF₆) as supporting electrolyte. All the electrochemical responses of the electropolymerized films were obtained in DCE solution with 0.10 M TBAPF₆ as supporting electrolyte. A silver wire quasi-reference electrode was calibrated using ferrocenium/ferrocene (Fc⁺/Fc) couple with potential Fc⁺/Fc taken as 0.4 V vs. saturated calomel electrode (SCE).⁶⁰

Spectroelectrochemical experiments were carried out in a homemade cell built from a commercial UV–visible cuvette. The ITO-coated glass was used as working electrode; a Pt wire was used as counter electrode, and an Ag wire was used as the reference electrode. These experiments were carried out in DCE with 0.10 M TBAPF₆ supporting electrolyte. The cell was placed in the optical path of the sample light beam. The background correction was obtained by taking an UV–vis spectrum of a blank cell (an electrochemical cell with an ITO working electrode without the polymer film) with conditions and parameters identical to those of the polymer experiment.

SEM micrographs were collected using Carl Zeiss EVO MA 10 SEM, with electron beam energy of 18 KeV.

AFM characterization of the polymer films on ITO electrodes was performed using an Agilent 5500 SPM microscope (Agilent Technologies, Inc.) working in Acoustic AC Mode. Commercial silicon cantilever probes, with aluminum backside coating and

Langmuir

nominal tip radius of 10 nm (MikroMasch, NSC15/Al BS/15, spring constant ranging 20– 75 N/m), were employed just under their fundamental resonance frequencies of about 325 kHz. The experiments were performed in stationary dry-air atmosphere. Images were treated and analyzed using Gwyddion, an open source software for the visualization and analysis of scanning probe microscopy data.

Contact angle measurements were performed using an optical contact angle meter (Attension Theta Optical Tensiometer) at room temperature and humidity. A milli Q water droplet (droplet size: 5 μ l) was placed with a Hamilton syringe (25 μ l) on the surface of the electrodeposited films. The contact angles reported values are the averages of at least three consecutive measurements (3 water droplets). Samples for contact angle measurements were prepared using the same procedure as those used for spectroelectrochemistry onto an ITO and they were washed with solvent to eliminate the electrolyte that could remain on the electrode.

RESULTS AND DISCUSSION

Synthesis of CFC monomers.

The polyfluorinated monomer CFC-F1 and its fully hydrogenated analog CFC-H1 were synthesized starting from 2,7-diodofluorene 1 and 9,9-bis(*1H*,*1H*,*2H*,*2H*perfluorodecyl)-9*H*-fluorene 3, respectively, according to the straightforward two steps sequences outlined in Scheme 1. The introduction of two *n*-decyl chains at the 9position of 1 to give the CFC-H1 precursor 2 was easily achieved by nucleophilic substitution reaction with 1-bromodecane in the presence of a substoichiometric amount of KI. An excess of KOH was used to generate the nucleophilic 9-fluorenyl anions. A slightly different route had to be employed in order to get good yields of the desired

Langmuir

polyfluorinated intermediate **4**. In that case, the fluorene derivative **3** was first synthesized, followed by iodination of the 2,7-positions of the fluorene scaffold.



Scheme 1. Synthesis of CFC monomers.

Indeed, attempts at introducing two $C_8F_{17}(CH_2)_2$ - chains at the 9-position of 1 were frustrated by the massive occurrence of side reactions favored by the strong electron withdrawing character of the $-C_8F_{17}$ group.⁵⁷ Bis *N*-arylation of intermediates 2 and 3 with carbazole was then performed under mild Ullmann-type conditions, affording CFC-H1 and CFC-F1, respectively, in excellent yields.

Optical Properties of CFC Monomers:

The electronic transitions of **CFC-H1** and **CFC-F1** were investigated by measuring their absorption and emission spectra in diluted DCE solutions. The obtained results are shown in **Figure 2** and the main photophysical parameters are summarized in **Table I**. A comparison of both spectra shows almost identical optical transition features, which indicates that the insertion of fluorinated alkyl chains at the 9 position of fluorene does not affect the conjugated core of the chromophore system. **CFC** monomers exhibit two clear absorptions bands at ~290 nm and ~340 nm. The light absorption at 290 nm is due to π - π * electron transition of carbazole moiety, while the lower energy transition is

Langmuir

assigned to electron transfer from nitrogen lone pairs to the π^* orbital of fluorene.^{20,24,43,61–64} As reported in **Table I**, the π - π^* electron transition occurs at the same wavelength for both dyes, as the torsion that allows the σ -bonding between the carbazole and fluorene moieties minimizes the extension of the conjugation length between the two aromatic centers. On the other hand, the band assigned to the electron transfer processes between carbazole and fluorene is 4 nm shifted towards lower energy for **CFC-F1** with respect to **CFC-H1**, which indicates the existence of a residual inductive effect exerted by the polyfluorinated alkyl chains.



Figure 2. Absorption (solid line) and emission (dot line) spectra of **CFC-H1** (red) and **CFC-F1** (blue), recorded in DCE solution. The emissions were taken with excitation at 338 nm for **CFC-H1** and 342 nm for **CFC-F1**.

The photoluminescence properties of **CFC-H1** and **CFC-F1** were studied in DCE solution by exciting the monomers at the wavelength maximum of the lower energy light absorption band. As shown in the dyes emission spectra reported in **Figure 2**, **CFC-H1** and **CFC-F1** emit light at 363 and 370 nm with quantum yields 0.77 and 0.69,

> respectively. On the other hand, it was observed that the CFCs dyes fluorescence excitation spectra at different excitation energies were superimposable to their absorption spectra and in addition, a unique fluorescence emission spectrum was obtained irrespective of the excitation wavelength. These results support the absence of light emitting impurities in the CFCs dyes solution.

Table 1. Thotophysical and electrochemical parameters of the compounds.										
	Absorption		Emission		Oxidation		Energy Levels ^f			
	-				Potentials					
Compd	λ_{Mono}	λ_{Film}^{Onset}	λ_{Mono}	ϕ_{Em}^{c}	E_{Mono}	E _{Film}	HOMO	LUMO	E_g	
	(nm) ^a	$(nm)^b$	$(nm)^a$		$(V)^d$	(V) ^e	(eV)	(eV)	(eV)	
CFC-H1	292	397	363	0.77	0.81	0.43	-5.53	-2.41	3.12	
	338				0.96					
					1.06					
CFC-F1	292	404	370	0.69	0.84	0.44	-5.54	-2.47	3.07	
	342				0.95					
					1.02					

 Table 1. Photophysical and electrochemical parameters of the compounds.

^{*a*}Spectra measured in DCE. The emission spectra were measured by excitation at the maximum wavelength of the lower energy absorption bands. ^{*b*}Low energy optical onset of the electrodeposited films, as determined from the intersection between the projection of the corresponding spectrum in the reduced state and the base line. ^{*c*}Emission quantum yield obtained in DCE. Standard used were 9,10-diphenylanthracene. ϕ_{FL} (9,10-diphenylanthracene) = 1 in cyclohexane.⁶⁵ dPeak potential. ^{*c*}Onset potentials of the electrodeposited films determined from intersection between the baseline and the current signal. The potentials values are expressed in volt vs. Fc/Fc⁺. ^{*f*}Calculated HOMO and LUMO energies of the films in the absolute scale (eV) as obtained using the following equations: $HOMO = -(E_{Film} + 5.1), LUMO = -(E_g - HOMO)$ and $E_g = 1240/\lambda_{Film}^{Onset}$.

Electrochemical Properties of CFC Monomers: Electropolymerization and Film

Formation

Cyclic voltammetry experiments were carried out to obtain information about the electrochemical processes of the monomers and their capability to form electropolymers. The results obtained are shown in **Figure 3**. It is interesting to note that **CFC** molecular structures are similar, the only difference being the nature of the saturated chains ($C_{10}H_{21}$ -

Page 15 of 34

Langmuir

or $C_8F_{17}(CH_2)_2$) in the 9-position of the fluorene moiety, (Figure 1). Since the fluorinated chain in CFC-F1 is linked to the fluorene conjugated center of the system by a nonconjugated bridge, therefore, a small influence by inductive effect on the electrochemical behavior of the dye was expected, similarly to what was observed in photophysical studies. However, a general inspection of the CFCs cyclic voltamperograms shapes presented in Figures 3aI and 3bI shows remarkable differences in the behavior of the two monomers, which indicates that the introduction of fluorinated chains notably affects the CFCs redox properties. The cyclic voltammograms of CFCs dves measured on freshly polished Pt electrode show three oxidation processes in the first scan to positive potentials (red line) around 0.85 V, 0.95 V and 1.00 V. Where, in the case of CFC-H1, the detected first and second oxidation processes are manifested as a shoulder of a wave with a maximum at 1.06 V (see arrows in Figure 3aI), while for CFC-F1, those redox processes are not so well defined as in the case of CFC-H1 and they overlap in a wave with a maximum at 0.88 V (see arrows in Figure 3bI). Then, when the potential scan direction is inverted, complementary reduction waves to the previous oxidation processes are detected: at 0.78 V and 0.91 V for CFC-H1, at 0.81 V for CFC-F1), and another at 0.54 V for both CFCs dyes (see Figures 3aI and 3bI). During the second cycle a new oxidation peak at 0.62 V is identified regarding the first potential swept, which is complementary to the reduction process observed at 0.54 V in the first cathodic sweep (see black line in Figures 3aI and 3bI). Finally, when the electrode potential is continually cycled (see the black line in Figures 3aI and 3bI) in both molecular systems all the voltamperogram current waves show a progressive growth, but with a different rate. Clearly, the CFC-F1 current growth rate is bigger than CFC-H1. This behavior can be ascribed to the development of a conductive and electroactive film on the working electrode surface. In concordance, when the electrodes were removed from the

electrochemical cell, washed with fresh solvent to eliminate any rest of monomer, and then transferred to a monomer-free supporting electrolyte solution, electrochemical signals characteristic of redox active modified electrodes were observed (Error! Reference source not found.all and 3bII).



Figure 3. First (red) and 2nd-10th (black) cyclic voltammograms of CFC-H1 (aI) and CFC-F1 (bI). Electrochemical response of the CFC-H1 (aII) and CFC-F1 (bII) electrodeposited films. Conditions: Pt working electrode, electrolyte TBAPF₆ 0.1 M solution in DCE, v=0.1 V/s.

The cyclic voltammograms of the CFC-H1 and CFC-F1 electrodeposited films show two oxidation waves with peak potentials at 0.57 V / 0.93 V and 0.62 V / 0.85 V, respectively. However, as previously pointed out, CFC-F1 is much more efficient than CFC-H1 in terms of film electrodeposition rate. This is clearly shown in Figure 3, where applying ten potential scan cycles in equal experimental conditions, CFC-F1 presents a bigger current increment between successive voltamperometric cycles producing four

Langmuir

times more film oxidation current than **CFC-H1**, which can be associated with a greater amount of electrodeposited material on the electrode surface.

For both CFC monomers, the first oxidation signal observed in the first potential scan (see the red line and inserted arrows in Figure 3aI and 3bI) can be assigned to the oxidation of the fluorene ring; while the second and third electrochemical signals are the oxidation of each carbazole units. The oxidation of the second carbazole moiety occurs at a more anodic potential, because a higher coulombic attraction must be overcome in order to remove a third electron from the dicationic charged species formed in the previous oxidation steps.²⁰ The reactive 2,7 positions of the fluorene core in the CFCs dyes are blocked by two nitrogen atoms, which stabilize the cation radical. In fact, when the potential is swept until the beginning of the first oxidation wave, where the carbazole units are not oxidized, the current growth with the number of potential sweep cycles is not observed. In addition, it is observed that the CFC-F1 first oxidation process is 30 mV shifted to more anodic potentials with respect to CFC-H1 (See Table I) evidencing a fluorinated chain effect on the fluorene ring. On the other hand, as it is shown in Figures 3aI and 3bI, when the scan potential reaches the second oxidation process, the typical electrodeposition process stimulated by coupling of two carbazole cation radicals starts.^{41,42,48,49} Indeed, the oxidation of one carbazole center leads to the formation of a radical cation that undergoes a dimerization reaction to produce less soluble dicarbazole, which precipitates on the electrode surface forming a polymeric film.^{46,47}

It is known that the carbazole dimer structural motif allows the extension of the conjugation length compared to the single carbazole unit, which makes the dimer obtained in the first step of the electropolymerization process more easily oxidizable than the starting monomer.^{24,41,42,46,48,49} Thus, the carbazole dimer produces new voltamperometric signals in the second potential scan cycle around 0.62 V and 0.90 V corresponding to its

Langmuir

radical cation and dication, respectively (See **Figure 3**). Consequently, the oxidation wave of the dimer dication overlaps with the ones corresponding to the starting **CFC** monomers, masking their electrochemical signals. For **CFC-F1**, which shows a higher electrodeposition rate, this effect is manifest, producing changes in the current magnitude of the monomer oxidation peaks, and therefore, changes in the voltammograms shape in the first potential scan regarding **CFC-H1** (see red line in **Figure 3aI** and **3bI**).

The CFC films showed high stability when they were subjected to several oxidation-reduction cycles, and their redox behavior is comparable to that observed with other carbazole derivatives.41,42,48 However, the comparative analysis of the electrochemical data clearly demonstrates the unexpected role played by the pendant polyfluoroalkyl chains, which improves enormously the film electro-formation in case of CFC-F1. This effect cannot be ascribed to any electronic effect, but rather to the wellknown deviation of the solubility properties of compounds featuring polyfluoroalkyl chains from those of their non-fluorinated analogs.^{66,67} In general, the higher the number of polyfluoroalkyl substituents, the lower the affinity of the compound for standard organic solvents. So, the presence of four C₈F₁₇(CH₂)₂- chains in the dimeric form of CFC-F1 produced in the first scan favors the separation of this product from the organic solvent and the precipitation on the electrode, which is not the case for the fully soluble dimeric form of CFC-H1. The same happens for the oligomeric forms of CFC-F1 generated in the subsequent scans, with the result of an increased rate of formation of the polymeric film on the electrode. Rigidity of the terminal C_8F_{17} groups might also play a role, by enhancing the microstructural ordering of the fluorinated polymer.⁶⁸

Morphological and Surface Properties of Electrodeposited Films

Langmuir

The morphology characteristics of the film surface are a significant parameter associated to the possible use of organic materials as active layers in optoelectronic and electronic devices.^{25,67} Figure 4 shows SEM images of the surfaces of CFC-H1 and CFC-F1 electropolymer films obtained under the same experimental conditions used in the electrochemical studies described above. Despite the identical deposition method used, the different surface characteristics of the two films are blatant.



Figure 4. From up to down, scanning electron and atomic force microscopy images and digital camera photographs of a water droplet on the film surface obtained by applied 10 growth cycles. Left **CFC-H1** and right **CFC-F1**.

Langmuir

 The CFC-H1 film is uneven and it does not cover the ITO electrode surface showing unfilled spaces. On the contrary, the CFC-F1 polymeric structure shows a granulate aspect and homogeneously full coats the outside of the ITO electrode. The morphology of the CFC-F1 film surface shows that its formation goes through a nucleation and growth process that ends up in the formation of a continuous film with globular-shaped features. Thus, the observed films surfaces differences between the two modified electrodes are in agreement with the highest CFC-F1 electrodeposition rate regarding CFC-H1, which allows to electrodeposit, in homogenous way, a greater amount of material on the electrode surface. Moreover, as seen in Figure 4, the aspect of the CFCs electrodes surfaces morphologies images obtained by AFM corroborates their surface characteristic found in the SEM study. The AFM imagens exhibit that CFC-H1 modified ITO electrode has a non-uniform and crannied surface, while CFC-F1 shows smooth surface formed by globular-shaped mosaics. From the AFM data were calculated the films thickness of 196 nm for CFC-F1 and 72 nm for CFC-F1, which also is in agreement with the better film formation capability of CFC-F1 molecular system.

The creation of active layers endowed with intrinsic water repellency, which relieves the negative effects of moisture on the charged species produced under exercise conditions,⁵¹ has been recognized as an effective strategy for the enhancement of the long-term durability of optoelectronic devices.⁶⁹ The static contact angle formed by a water drop standing on the film surface provides a direct estimate of the hydrophilic/hydrophobic properties of the surface, with water repellency increasing with the measured contact angle.⁷⁰ Thus, a surface is commonly defined as hydrophilic if the value of the contact angle is less than 90°, as hydrophobic if the value of the contact angle is greater than 90°.⁷¹ Comparison of the water contact angle values for the two **CFC** electropolymer films (**Figure 4**

Langmuir

and **Table 1**) clearly shows that the introduction of polyfluoroalkyl chain on the fluorene ring leads to a dramatic increase, from 82° for **CFC-H1** to 127° for **CFC-F1**. The contact angle measured in the case of the **CFC-H1** film is surprisingly low for an organic material that holds long hydrophobic alkyl chains in its chemical composition. This is due to an incomplete coverage of the ITO electrode, as evidenced in **Figure 4**. Thus, the electrodeposited **CFC-H1** film does not efficiently shelter the substrate and the observed water contact angle is closer to that of the clean ITO surface, which corresponds to 75°. On the other hand, the superficial hydrophobic properties of the defect-free **CFC-F1** film are typical of a polymeric material characterized by the presence of polyfluoroalkyl residues.^{50,72,73} These results show that the introduction of polyfluoroalkyl side chains in fluorene/carbazole hybrid monomers allows to form by electrochemical techniques thin film materials with good morphological and water repellency characteristics, which are highly desirable for the fabrication of optoelectronic devices.

Spectrolectrochemical Properties of Electrodeposited Films.

To get information about the optoelectronic proprieties of the CFC electrodeposited films, spectroelectrochemical experiments were carried out on polymer films electrochemically generated over ITO electrodes applying the same experimental conditions used in the electrochemical studies described above. Nevertheless, for these spectroelectrochemical experiments the films growth was adjusted by the applied number of potential cycles in order to optimize the film light absorption. The absorption spectra of the CFC films at different applied potentials are shown **Figure 5**. The potential applied to each spectrum corresponds to the one identified with a dot of the same color in the corresponding films voltamperograms showed in **Figure 3aII** and **3bII**. Both films

Langmuir

 present three redox states being these neutral (partly transparent in the visible region of the electromagnetic spectrum), semioxidized (yellow), and fully oxidized (green). The pictures inserted in **Figure 5** showed the **CFC** polymer films colorations at different oxidation states.



Figure 5. Spectroelectrochemical measurements of a) **CFC-H1** film (20 growth cycles) and b) **CFC-F1** film (5 growth cycles), at different applied potentials. The potentials applied to obtain the different traces were the same for both monomers. The inset photographs show the electrodes coloration at different redox states and the color frame indicates the corresponding spectrum.

The electro-optical properties of the CFC film have origin mainly in the carbazole dimer. The light absorption onset of the CFC-H1 and CFC-F1 films in their neutral state (light absorption spectra in black in Figure 5) is located at ~404 nm, as determined by the intersection between the projection of the light absorption band tail and the baseline. This UV-band is due to the π - π * transition in the conjugated system and it has a maximum in the UV-region at λ ~340 nm close to the ITO optical cut and therefore, it is not shown in Figure 5. However, both films in their neutral state shown a light absorption in the zone of 430 nm, which can be assigned to the bicarbazole radicals cation. This would indicate that after to the electrochemical films formation, some positively charged traps remain. When the applied potential to the modified electrode reaches higher values than

Page 23 of 34

Langmuir

the films oxidation onset (See **Table I**), two new electronic transitions are observed, one with peak maximum at 422 nm and another broader at ~950 nm (see the green, blue and magenta traces). In addition, when the potential advances through the second oxidation process of **CFC** films (see cyan and red dots and traces in **Figure 3** and **Figure 5**, respectively) the higher energy absorption band starts to decrease in absorbance intensity; while a new broad band at 800 nm is developed. This behavior is typical of electrodeposited carbazole derivative materials and these bands can be assigned to the formation of bicarbazole radicals cation and dications by oxidation of the polymeric film.^{23,48,61}

SUMMARY AND CONCLUSIONS

We have developed two easily accessible electropolymerizable molecules that feature fluorene, bearing either alkyl or polyfluoroalkyl chains in the 9-position, as a bridge between two carbazole moieties. Adequate conditions for the growth of conductive polymers over platinum electrodes and over semitransparent ITO have been established. The proposed electropolymerization mechanism involves the reaction between two carbazole radical cations to form dicarbazole linkages between fluorene units. The morphology characteristics and the rate of deposition of the electropolymerized films generated in this process are heavily dependent on the nature of the pendant saturated chains on the fluorene bridge. In the case of polyfluoroalkyl chains (monomer **CFC-F1**) the film is homogeneous and very stable, with good adherence to the electrode surface. The nature of the pendant chains has also a deep impact on the water affinity of the films, which exhibit clear hydrophobic characteristics in the case of **CFC-F1**, as proved by static contact angle measurements. In addition, the materials obtained show electrochromic properties, with the coloration of the films switching from uncolored to green upon

oxidation due to the applied potential. These findings open perspectives for application in the field of damp- or waterproofing optical coatings and the manufacturing of intelligent windows.

ACKNOWLEDGMENTS

We thank the CNR/Regione Lombardia project "Integrated Zero Emission Buildings", Consejo Nacional de Investigaciones Científicas y Tecnicas (CONICET-Argentina), Agencia Nacional de Promoción Científica y Tecnológica (ANPCYT Argentina), Universidad Nacional de Río Cuarto. M.V.C., G.M, M.Z, L.F, and F.F. are scientific members of CONICET.

AUTHOR INFORMATION

Corresponding Authors

* ffungo@exa.unrc.edu.ar; gianluca.pozzi@istm.cnr.it

REFERENCES

- Park, Y. W. Editorial for the Conducting Polymers for Carbon Electronics Themed Issue. *Chem. Soc. Rev.* 2010, *39*, 2337–2732.
- Bujak, P.; Kulszewicz-Bajer, I.; Zagorska, M.; Maurel, V.; Wielgus, I.; Pron, A.
 Polymers for Electronics and Spintronics. *Chem. Soc. Rev.* 2013, *42*, 8895–8999.
- Xie, L.-H.; Yang, S.-H.; Lin, J.-Y.; Yi, M.-D.; Huang, W. Fluorene-Based Macromolecular Nanostructures and Nanomaterials for Organic (Opto)Electronics. *Philos. Trans. R. Soc. A Math. Phys. Eng. Sci.* 2013, 371, 1–34.
- (4) Kiriy, R.; Poetzsch, Q.; Wei, B. A. Voit, High-Tech Functional Polymers Designed

Langmuir

for Applications in Organic Electronics, Polym. Degrad. Stab. . *Polym. Degrad. Stab.* **2017**, *145*, 150–156.

- (5) Marrocchi, A.; Facchetti, A.; Lanari, D.; Petrucci, C.; Vaccaro, L. Current Methodologies for a Sustainable Approach to π -Conjugated Organic Semiconductors, Energy Environ. *Energy Environ. Sci.* **2016**, *9*, 763–786.
- Schroot, R.; Jäger, M.; Schubert, U. S. Synthetic Approaches towards Structurally-Defined Electrochemically and (Photo)Redox-Active Polymer Architectures. *Chem. Soc. Rev.* 2017, *46*, 2754–2798.
- (7) Ahmad, S.; Ikeda, T. Electroactive Coatings: For Electrically Controlled on Demand Power Windows. *Nanosci. Nanotechnol. Lett.* 2013, *5*, 3–12.
- Wang, Y.; Runnerstrom, E. L.; Milliron, D. J. Switchable Materials for Smart Windows. *Annu. Rev. Chem. Biomol. Eng.* 2016, 7, 283–304.
- (9) Li, R.; Zhu, Y.; Yang, G. Polymer Solar Cells. *Nat. Photon.* **2012**, *6*, 153–161.
- (10) Gendron, D.; Leclerc, M. New Conjugated Polymers for Plastic Solar Cells.
 Energy Environ. Sci. 2011, 4, 1225–1237.
- (11) Facchetti, A. π-Conjugated Polymers for Organic Electronics and Photovoltaic.
 Chem. Mater. 2011, 23, 733–758.
- (12) Xiao, S.; Zhang, Q.; You, W. Molecular Engineering of Conjugated Polymers for Solar Cells: An Updated Report. *Adv. Mater.* 2017, *29*, 1601391.
- (13) Park, M.-H.; Han, T.-H.; Kim, Y.-H.; Jeong, S.-H.; Lee, Y.; Seo, H.-K.; Cho, H.;
 Lee, T.-W. Flexible Organic Light-Emitting Diodes for Solid-State Lighting. J. *Photon. Energy* 2015, 5, 1–21.

(14) Boudreault, P. L. T.; Beaupré, S.; Leclerc, M. Polycarbazoles for Plastic Electronics. *Polym. Chem.* 2010, *1*, 127–136.

- (15) Dumur, F. Carbazole-Based Polymers as Hosts for Solution-Processed Organic Light-Emitting Diodes: Simplicity, Efficacy, Org. Electron. Org. Electron. 2015, 25, 345–361.
- (16) Sathiyan, G.; Sivakumar, E. K. T.; Ganesamoorthy, R.; Thangamuthu, R.;
 Sakthivel, P. Review of Carbazole Based Conjugated Molecules for Highly
 Efficient Organic Solar Cell Application. *Tetrahedron Lett.* 2016, *57*, 243–252.
- (17) Heredia, D.; Natera, J.; Gervaldo, M.; Otero, L.; Fungo, F.; Lin, C.-Y.; Wong, K.-T. Spirobifluorene-Bridged Donor/Acceptor Dye for Organic Dye-Sensitized Solar Cells. *Org. Lett.* 2009, *12*, 12–15.
- (18) Abbel, A. P. H.; Schenning, E. W.; Meijer, R. J. Fluorene-Based Materials and Their Supramolecular Properties. J. Polym. Sci., Part A Polym. Chem. 2009, 47, 4215–4233.
- (19) Yu, M.; Ou, C.; Liu, B.; Lin, D.; Liu, Y.; Xue, W.; Lin, Z.; Lin, J.; Qian, Y.; Wang,
 S.; et al. Progress in Fluorene-Based Wide-Bandgap Steric Semiconductors. *Chinese J. Polym. Sci.* 2017, 35, 155–170.
- (20) Fungo, F.; Wong, K.-T.; Ku, S.-Y.; Hung, Y.-Y.; Bard, A. J. Electrogenerated Chemiluminescence. 81. Influence of Donor and Acceptor Substituents on the ECL of a Spirobifluorene-Bridged Bipolar System. *J. Phys. Chem. B* 2005, *109*, 3984– 3989.
- (21) Heredia, D.; Fernandez, L.; Otero, L.; Ichikawa, M.; Lin, C. Y.; Liao, Y. L.; Wang,S. A.; Wong, K. T.; Fungo, F. Electrochemical Tuning of Morphological and

Langmuir

2
3
4
5
6
7
8
9
10
11
17
12
13
14
15
16
17
18
19
20
21
22
22
23
24
25
26
27
28
29
30
31
21
32
33
34
35
36
37
38
39
40
/1
יד ⊿ר
42
43
44
45
46
47
48
49
50
51
51
52
53
54
55
56
57
58
59

60

Optoelectronic Characteristics of Donor-Acceptor Spiro-Fluorene Polymer Film. Application in the Building of an Electroluminescent Device. *J. Phys. Chem. C* **2011**, *115*, 21907–21914.

- (22) Zabel, P.; Dittrich, T.; Liao, Y.-L.; Lin, C.-Y.; Wong, K.-T.; Fungo, F.; Fernandez, L.; Otero, L. Engineering of Gold Surface Work Function by Electrodeposition of Spirobifluorene Donor–Acceptor Bipolar Systems. *Org. Electron.* 2009, *10*, 1307–1313.
- (23) Promarak, S.; Saengsuwan, S.; Jungsuttiwong, T.; Sudyoadsuk, T.; Keawin, V. Synthesis and Characterization of N-Carbazole End-Capped Oligofluorenes. *Tetrahedron Lett.* 2007, 48, 89–93.
- (24) Usluer, O.; Demic, S.; Egbe, D. A. M.; Birckner, E.; Tozlu, C.; Pivrikas, A.; Ramil,
 A. M.; Sariciftci, N. S. Fluorene-Carbazole Dendrimers: Synthesis, Thermal,
 Photophysical and Electroluminescent Device Properties. *Adv. Funct. Mater.*2010, 20, 4152–4161.
- (25) Koyuncu, S.; Usluer, O.; Can, M.; Demic, S.; Icli, S.; Sariciftci, N. S. Electrochromic and Electroluminescent Devices Based on a Novel Branched Quasi-Dendric Fluorene-Carbazole-2,5-Bis(2-Thienyl)-1H-Pyrrole System. J. Mater. Chem. 2011, 21, 2684–2693.
- Meunmart, D.; Prachumrak, N.; Keawin, T.; Jungsuttiwong, S.; Sudyoadsuk, T.;
 Promarak, V. Bis(4-Diphenylaminophenyl)Carbazole End-Capped Fluorene as
 Solution-Processed Deep-Blue Light-Emitting and Hole-Transporting Materials
 for Electroluminescent Devices, Tetrahedron Lett. *Tetrahedron Lett.* 2012, *53*, 3615–3618.

- (27) Sangchart, T.; Niroram, A.; Kaewpuang, T.; Prachumrak, N.; Namuangruk, S.
 Synthesis, Physical and Electroluminescence Properties of 3,6-Dipyrenylcarbazole
 End Capped Oligofluorenes. *RSC* 2015, *5*, 26569–26579.
- (28) Sarac, A. S. Electropolymerization. In *Encyclopedia of Polymer Science and Technology*; John Wiley & Sons, Inc.: Hoboken, NJ, USA, 2004.
- (29) Yan, H.; Kurogi, K.; Mayama, H.; Tsujii, K. Environmentally Stable Super Water-Repellent Poly(Alkylpyrrole) Films. *Angew. Chemie Int. Ed.* 2005, 44, 3453–3456.
- (30) Mael, N.; Guittard, F.; Geribaldi, S. Stable Superhydrophobic and Lipophobic Conjugated Polymers Films. *Langmuir* 2006, *22*, 3081–3088.
- (31) Mortier, C.; Darmanin, T.; Guittard, F. 3,4-Dialkoxypyrrole for the Formation of Bioinspired Rose Petal-like Substrates with High Water Adhesion. *Langmuir* 2016, 32, 12476–12487.
- (32) Mortier, C.; Darmanin, T.; Guittard, F. Direct Electrodeposition of Superhydrophobic and Highly Oleophobic Poly(3,4-Ethylenedioxypyrrole) (PEDOP) and Poly(3,4-Propylenedioxypyrrole) (PProDOP) Nanofibers. *ChemNanoMat* 2017, *3*, 885–894.
- (33) Darmanin, T.; Taffin de Givenchy, E.; Amigoni, S.; Guittard, F. Hydrocarbon versus Fluorocarbon in the Electrodeposition of Superhydrophobic Polymer Films. *Langmuir* 2010, *26*, 17596–17602.
- (34) Darmanin, T.; Taffin de Givenchy, E.; Guittard, F. Superhydrophobic Surfaces of Electrodeposited Polypyrroles Bearing Fluorinated Liquid Crystalline Segments. *Macromolecules* 2010, *43*, 9365–9370.

- (35) Darmanin, T.; Guittard, F. Superhydrophobic Fiber Mats by Electrodeposition of Fluorinated Poly(3,4-Ethyleneoxythiathiophene). J. Am. Chem. Soc. 2011, 133, 15627–15634.
- (36) Bellanger, H.; Darmanin, T.; Guittard, F. Surface Structuration (Micro and/or Nano) Governed by the Fluorinated Tail Lengths toward Superoleophobic Surfaces. *Langmuir* 2012, 28, 186–192.
- (37) Sulaiman, Y.; Kataky, R. Effect of Monomer Modifications on the Physical Properties of Electropolymerised PEDOT Films. J. Electrochem. Soc. 2011, 159, F1–F9.
- (38) Bellanger, H.; Darmanin, T.; de Givenchy, E. T.; Guittard, F. Influence of Long Alkyl Spacers in the Elaboration of Superoleophobic Surfaces with Short Fluorinated Chains. *RSC Adv.* 2013, *3*, 5556–5562.
- (39) Mortier, C.; Darmanin, T.; Guittard, F. The Major Influences of Substituent Size and Position of 3,4-Propylenedioxythiophene on the Formation of Highly Hydrophobic Nanofibers. *Chempluschem* 2014, 79, 1434–1439.
- (40) Darmanin, T.; Guittard, F. Highly Polar Linkers (Urea, Carbamate, Thiocarbamate) for Superoleophobic/Superhydrophobic or Oleophobic/Hydrophilic Properties. *Adv. Mater. Interfaces* 2015, *2*, 1500081/1-150081/7.
- (41) Natera, J.; Otero, L.; Sereno, L.; Fungo, F.; Wang, N.-S.; Tsai, Y.-M.; Hwu, T.-Y.;
 Wong, K.-T. A Novel Electrochromic Polymer Synthesized through Electropolymerization of a New Donor– Acceptor Bipolar System. *Macromolecules* 2007, 40, 4456–4463.

- (42) Natera, J.; Otero, L.; D'Eramo, F.; Sereno, L.; Fungo, F.; Wang, N.-S.; Tsai, Y.-M.; Wong, K.-T. Synthesis and Properties of a Novel Cross-Linked Electroactive Polymer Formed from a Bipolar Starburst Monomer. *Macromolecules* 2009, *42*, 626–635.
- (43) Usluer, O.; Koyuncu, S.; Demic, S.; Raj, J. A Novel High-contrast Ratio Electrochromic Material from Spiro[Cyclododecane-1,9'-fluorene]Bicarbazole. J. Polym. Sci. Part B Polym. Phys. 2011, 49, 333–341.
- (44) Lv, L.; Yao, C.; Gu, Y.; Xu, Y.; Zhang, Z.; Xie, L.; Liu, L.; Ma, Y. Cross-Linked Luminescent Films via Electropolymerization of Multifunctional Precursors for Highly Efficient Electroluminescence. *Polym Chem* 2013, *4*, 2090–2096.
- (45) Yu, T.; Wu, X.; Lv, Y.; Liu, L.; Du, L.; Zhou, J.; Xie, Z.; Ma, Y. An Electrochemically Deposited Film as an Interface Layer to Improve the Performance of Polymer Light-Emitting Diodes. J. Mater. Chem. C 2014, 2, 4117–4120.
- (46) Ambrose, J. F.; Nelson, R. F. Anodic Oxidation Pathways of Carbazoles: I. Carbazole and N-Substituted Derivatives. J. Electrochem. Soc. 1968, 115, 1159–1164.
- (47) Morin, J.-F.; Leclerc, M.; Adès, D.; Siove, A. Polycarbazoles: 25 Years of Progress. *Macromol. Rapid Commun.* 2005, 26, 761–778.
- (48) Mangione, M. I.; Spanevello, R. A.; Minudri, D.; Heredia, D.; Fernandez, L.;
 Otero, L.; Fungo, F. Electropolimerization of Functionalizaed Carbazole End-Capped Dendrimers. Formation of Conductive Films. *Electrochim. Acta* 2016, 207, 143–151.

(49)	Mangione, M. I.; Spanevello, R. A.; Minudri, D.; Cavallo, P.; Otero, L.; Fungo, F
	Electrochemical Films Deposition and Electro-Optical Properties of Bis-Carbazol-
	Triphenylamine End-Caped Dendrimeric Polymers. Electrochim. Acta 2018, 263
	585–595.

- (50) Améduri, B.; Boutevin, B. Well-Architectured Fluoropolymers: Synthesis, Properties and Applications; Elsevier: Amsterdam, 2004.
- (51) So, F.; Kondakov, D. Degradation Mechanisms in Small-Molecule and Polymer Organic Light-Emitting Diodes. *Adv. Mater.* 2010, *22*, 3762–3777.
- (52) Babudri, F.; Farinola, G. M.; Naso, F.; Ragni, R. Fluorinated Organic Materials for Electronic and Optoelectronic Applications: The Role of the Fluorine Atom. *Chem. Commun.* 2007, *10*, 1003–1022.
- (53) Kameshima, H.; Nemoto, N.; Endo, T. Synthesis and Properties of Fluorene-based Fluorinated Polymers. *J. Polym. Sci. Part A Polym. Chem.* **2001**, *39*, 3143–3150.
- (54) Amara, T. M.; Swager, J. P. Conjugated Polymers with Geminal Trifluoromethyl Substituents Derived from Hexafluoroacetone, Macromolecules. *Macromolecules* 2006, *39*, 5753–5759.
- (55) Ohkubo, K.; Sakamoto, Y.; Suzuki, T.; Tsuzuki, T.; Kumaki, D.; Tokito, S.
 Synthesis, Structure, and Transport Property of Perfluorinated Oligofluorenes,.
 Chem. Eur. J. 2008, 14, 4472–4474.
- (56) Darmanin, T.; Nicolas, M.; Guittard, F. Synthesis and Properties of Perfluorinated Conjugated Polymers Based on Polyethylenedioxythiophene, Polypyrrole, and Polyfluorene. Toward Surfaces with Special Wettabilities. *Langmuir* 2008, *24*, 9739–9746.

- (57) Lee, J. K.; Fong, H. H.; Zakhidov, A. A.; Mccluskey, G. E.; Taylor, P. G. Semiperfluoroalkyl Polyfluorenes for Orthogonal Processing in Fluorous Solvents. *Macromolecules* 2010, , 1195–1198.
- (58) Fong, H. H.; Lee, J. K.; Lim, Y. F.; Zakhidov, A. A.; Wong, W. W. H.; Holmes, A. B.; Ober, C. K.; Malliaras, G. G. Orthogonal Processing and Patterning Enabled by Highly Fluorinated Light-Emitting Polymers. *Adv. Mater.* 2011, *23*, 735–739.
- (59) Chaikovskii, V. K.; Filimonov, V. D.; Funk, A. A.; Skorokhodov, V. I.; Ogorodnikov, V. D. 1,3-Diiodo-5,5-Dimethylhydantoin—An Efficient Reagent for Iodination of Aromatic Compounds. *Russ. J. Org. Chem.* **2007**, *43*, 1291–1296.
- (60) Cardona, C. M.; Li, W.; Kaifer, A. E.; Stockdale, D.; Bazan, G. C. Electrochemical Considerations for Determining Absolute Frontier Orbital Energy Levels of Conjugated Polymers for Solar Cell Applications. *Adv. Mater.* 2011, *23*, 2367– 2371.
- (61) Ohkita, H.; Ito, S.; Yamamoto, M.; Tohda, Y.; Tani, K. Intramolecular Excimer Emissions of Syn- and Anti-[3.3](3,9)Carbazolophanes in Solutions. J. Phys. Chem. A 2002, 106, 2140–2145.
- (62) Cho, Y.-J.; Wee, K.-R.; Son, H.-J.; Cho, D. W.; Kang, S. O. A Detailed Investigation of Light-Harvesting Efficiency of Blue Color Emitting Divergent Iridium Dendrimers with Peripheral Phenylcarbazole Units. *Phys. Chem. Chem. Phys.* 2014, *16*, 4510–4521.
- (63) Ray, K.; Misra, T. N. Spectroscopic Study of Nonamphiphilic 9-PhenylcarbazoleAssembled in Langmuir–Blodgett Films. *Langmuir* 1997, *13*, 6731–6736.
- (64) Adhikari, R. M.; Mondal, R.; Shah, B. K.; Neckers, D. C. Synthesis and

Langmuir

Photophysical Properties of Carbazole-Based Blue Light-Emitting Dendrimers. J. Org. Chem. 2007, 72, 4727–4732.

- (65) Berlman, I. Handbook of Florescence Spectra of Aromatic Molecules; Elsevier, 2012.
- (66) Vincent, J.-M. Recent Advances of Fluorous Chemistry in Material Sciences. *Chem. Commun.* 2012, 48, 11382–11391.
- (67) Li, M.; Tang, S.; Shen, F.; Liu, M.; Xie, W.; Xia, H.; Liu, L.; Tian, L.; Xie, Z.; Lu,
 P.; et al. Electrochemically Deposited Organic Luminescent Films: The Effects of
 Deposition Parameters on Morphologies and Luminescent Efficiency of Films. *J. Phys. Chem. B* 2006, *110*, 17784–17789.
- (68) Kang, B.; Kim, R.; Lee, S. B.; Kwon, S.-K.; Kim, Y.-H.; Cho, K. Side-Chain-Induced Rigid Backbone Organization of Polymer Semiconductors through Semifluoroalkyl Side Chains. J. Am. Chem. Soc. 2016, 138 (11), 3679–3686.
- (69) Cho, K. T.; Zhang, Y.; Orlandi, S.; Cavazzini, M.; Zimmermann, I.; Lesch, A.; Tabet, N.; Pozzi, G.; Grancini, G.; Nazeeruddin, M. K. Water-Repellent Low-Dimensional Fluorous Perovskite as Interfacial Coating for 20% Efficient Solar Cells. *Nano Lett.* 2018, *18*, 5467–5474.
- (70) Palumbo, F.; Mundo, R. D. Wettability: Significance and Measurement. In *Polymer Surface Characterization*; Sabbatini, L., Ed.; De Gruyter: Berlin, 2014; pp 207–245.
- (71) Zhang, X.; Shi, F.; Niu, J.; Jiang, Y.; Wang, Z. Superhydrophobic Surfaces : From Structural Control to Functional Application. *J. Mater. Chem.* 2008, *18*, 621–633.

- (72) Honda, K.; Morita, M.; Sakata, O.; Sasaki, S.; Takahara, A. Effect of Surface Molecular Aggregation State and Surface Molecular Motion on Wetting Behavior of Water on Poly(Fluoroalkyl Methacrylate) Thin Films. *Macromolecules* 2010, 43, 454–460.
 - (73) Pevzner, L.; Auer, M.; Trattnig, R.; Klapper, M.; List-Kratochvil, E. J. W.; Müllen,
 K. Controlling Polymer Solubility: Polyfluorenes with Branched Semiperfluorinated Side Chains for Polymer Light-Emitting Diodes. *Isr. J. Chem.*2014, *54*, 736–747.

ACS Paragon Plus Environment