

# Original Fluorinated Copolymers Achieved by Both Azide/Alkyne "Click" Reaction and Hay Coupling from Tetrafluoroethylene Telomers

## Aurélien Soules, Bruno Ameduri,\* Bernard Boutevin, and Gerard Calleja

Ingénierie et Architectures Macromoléculaires, Institut Charles Gerhardt, UMR 5253 CNRS ENSCM UMI UMII, Ecole Nationale Supérieure de Chimie de Montpellier, 8 rue de l'Ecole Normale, 34296 Montpellier Cedex 05, France

Received March 23, 2010; Revised Manuscript Received April 8, 2010

ABSTRACT: The synthesis and characterization of an original class of linear poly(alkyl aryl) ethers containing 1,2,3-triazolyl and fluorinated moieties based on oligo(tetrafluoroethylene) telomer are presented. These polymers were prepared, from  $\alpha,\omega$ -dipropargyl ether bisphenol AF and 1,10-diazido-1*H*,1*H*,2*H*,2*H*,9*H*,9*H*, 10*H*,10*H*-perfluorodecane, in 62% overall yields via the azide/alkyne "click" reaction and/or oxidative coupling of acetylenes (Hay reaction). The latter reactant was produced from the ethylene end-capping of oligo-(tetrafluoroethylene) followed by a nucleophilic substitution with sodium azide. A simple tuning of the reaction conditions allowed us to direct the originally favored "click" reaction toward a competitive homocoupling of the terminal alkynes, thus leading to copolymers with drastically different structures, as evidenced by size exclusion chromatography, DSC, Raman, and UV-vis spectroscopy. Hence, original poly(alkyl aryl) ether copolymers with a high thermal stability (higher than 300 °C) that exhibit alternating statistic or block microstructures were obtained.

### Introduction

Over the past decades, fluoropolymers have been attractive in the development of advanced materials endowed with high thermal and oxidative stabilities, chemical inertness, and superior electrical insulating ability for high-tech applications such as thin film coatings, cladding for optical fibers, membranes for fuel cells, and separators for lithium ion batteries.<sup>1–3</sup> Meanwhile, efforts have been made to develop thermally curable materials based on propargyl methacrylate<sup>4</sup> and linear polymers of propargyl derivatives of bisphenol.<sup>5–7</sup> Dipropargyl ether of bisphenol A and its B-staged materials have been attractive substitutes for epoxy resins involved in advanced composites, adhesives, coatings, and for electronics applications.<sup>8–10</sup> In fact, the obtained resins exhibit thermoset characteristics, excellent thermal stability (around 350 °C), low dielectric constants (ca. 2.77), and are highly hydrophobic matrices.

Furthermore, it is known that terminal acetylenes that have propargyl groups are able to undergo an oxidative homocoupling.<sup>11</sup> One of the main methods to obtain oligo- or polyacetylene consists in achieving such homocoupling via Hay's protocole<sup>12a,b</sup> (Scheme 1).

This coupling is based on dimerization through oxidation of copper(I) acetylides species by copper(II). The use of aminated bidendate ligands such as N,N,N,N'-tetramethylethylenediamine<sup>11b</sup> (TMEDA) or 2,2'-bipyridine<sup>13</sup> (bpy) enables the formation of copper(I) acetylide species. On the other hand, the ligand creates a bridge between copper(I) and copper(II) that favors electron transfer and thus increases the kinetics of the coupling. Indeed, acetylenic coupling is currently a powerful tool in molecular<sup>14</sup> and macromolecular designs.<sup>15</sup>

Acetylenic groups have also been involved in various reactions, and recently Sharpless' group<sup>16</sup> has popularized the azide/alkyne "click" reaction. This reaction is a variation of the Huisgen 1,3-

\*Corresponding author: tel 33 467 144 368; fax 33 467 147 220; e-mail Bruno.ameduri@enscm.fr.

dipolar cycloaddition reaction between terminal acetylenes and azides catalyzed by an organometallic complex. Different mechanisms of this reaction have been proposed. A recent one was suggested by Bock et al.,<sup>17</sup> who reported that "click" reaction is a multistep 1,4 regiospecific reaction involving the formation of complexes of copper(I) acetylide. The kinetics of this reaction<sup>18–20</sup> have shown that it was of second order with respect to the copper concentration when the metal is used in catalytic amounts. Usual catalytic systems are aromatic and aliphatic aminated ligands.<sup>21–25</sup>

This methodology has been successfully applied in organic chemistry,<sup>26,27</sup> supramolecular chemistry,<sup>28–30</sup> and materials science,<sup>31,32</sup> leading to interesting materials: dendronized polymers,<sup>31–34</sup> conjugated polymers,<sup>35</sup> or incorporation of 1,2,3-triazole ring into polymers by grafting.<sup>36–42</sup> Only a few groups have studied the incorporation of 1,2,3-triazole ring into the backbone of linear polymers by polycondensation.<sup>43–51</sup>

When the respective mechanisms of Hay coupling and "click" reaction are compared, it appears that in a system where both endgroups are present, the course of the reaction depends on various experimental conditions: (i) the presence or lack of oxygen, (ii) the copper (II) salt concentration, and (iii) the nature of the copper ligand. Under regular "click" reaction conditions (traces of oxygen, addition of an appropriate reducing agent, and aliphatic aminated ligand, such as N, N, N', N'', Pentamethyldiethylenetriamine), the "click" reaction is much faster than Hay coupling, and the latter is generally not observed.

Recently, Cummins et al.<sup>52a</sup> have reported that in the course of the grafting of polystyrene chains bearing alkyne functions by "click" reaction onto a surface bearing azide groups the coupling of these chains via the formation of diacetylenic segments occurred. Since then, homocoupling (according to Hay's protocol) of the alkyne extremities of a macromolecular polystyrene synthesized by ATRP has been further confirmed by the same group.<sup>52b</sup>

This work intends to bring some new insights in the still scarce examples of competitive Hay coupling and "click" reaction



<sup>*a*</sup> TMEDA = N, N, N, N'-tetramethylethylenediamine.

provided by the literature. The synthesis and characterization of an original class of linear poly(alkyl aryl) ethers containing 1,2,3triazolyl and fluorinated moieties [based on oligo(tetrafluoroethylene) telomers] is reported. By subtle changes in the reaction conditions, the copolymerization between a fluorinated telechelic telomer bearing azido functions and a propargylic oligomer containing terminal alkynes could be controlled from classic azide/alkyne "click" addition toward the promotion of a competitive homocoupling of the alkyne end groups, thus leading to either alternated or block copolymers bearing different functional groups.

#### **Experimental Section**

**Reactants.** Di(4-*tert*-butylcyclohexyl)peroxydicarbonate used as the initiator was kindly supplied from Akzo Nobel. Dimethyl sulfoxide (DMSO), tetrahydrofuran (THF), diethyl ether (from Aldrich), and *tert*-butanol (Acros Organics, 98%) were distilled prior to use. 1,6-Diiodoperfluorohexane was purchased from Daikin. Copper(I) bromide (Acros Organics, 95%) was washed with glacial acetic acid to remove any soluble oxidized species and then filtered, washed with ethanol, and dried. Hexafluorobisphenol AF, propargyl bromide, sodium azide, Na<sub>2</sub>SO<sub>4</sub>, and 2,2'-bipyridine (bpy) were purchased from Aldrich.

2,2'-bipyridine (bpy) were purchased from Aldrich. **Analyses and Characterizations.** <sup>1</sup>H, <sup>13</sup>C, and <sup>19</sup>F NMR spectra were recorded on a Brüker 400 MHz FT NMR spectrometer with either deuterated chloroform or acetone as solvents. Chemical shifts are reported in ppm relative to tetramethylsilane (TMS) for <sup>1</sup>H and <sup>13</sup>C spectra and to CFCl<sub>3</sub> for <sup>19</sup>F NMR spectra. Letters s, d, t, and q stand for singlet, doublet, triplet, and quintet, and the coupling constants are in hertz. Fourier transformed IR spectra were performed on a Nicolet 510P Fourier spectrometer with an accuracy of  $\pm 2$  cm<sup>-1</sup> using OMNIC software.

The relative viscosity measurements were achieved in a thermostated bath at 35 °C, using a Ubbelohde viscosimeter ref. no. 501 10 equipped with a capillary with an inner diameter of 0.53 mm. Determination of intrinsic viscosity was based on four reduced viscosity measurements at concentrations ranging from 0.1 to 0.5 g per 100 mL of acetone.

Size exclusion chromatography was carried out in DMF with a flow rate of 0.8 mL min<sup>-1</sup> and a PL gel Mix column at 30 °C. Detection was performed using a RI Spectra-Physics detector SP8430. Analyses were achieved by injection of 20  $\mu$ L of the polymer solution (5 mg mL<sup>-1</sup>) in DMF (polymer dissolved readily in DMF leading to a clear solution). The molecular weights and polydispersity indices were assessed using the Waters Breeze software package. The system was calibrated by using commercially available monodispersed poly(styrene) standards from Polymer Laboratories.

The Raman spectra were recorded on a Labram Aramis HORIBA Jobin Yvon with  $IR^2$  option (excitation wavelength 633.5 nm). The microscope lens was a LWD Olympus (X50). The spectral resolution was 1.6 cm<sup>-1</sup>.

The study of the thermal cross-linking of polymer 4 was performed by means of a Perkin-Elmer UV20 spectrometer with a scan speed of 480 nm/min. Polymer 4 was dissolved in THF (2 mg/mL), and the solution was spread on a quartz substrate and then spin-coated on a Karl Suss Technique SA apparatus (CT60 model) (acceleration of 1000 rpm, a spinning speed of 1500 rpm for 30 s) to produce thin films (~1  $\mu$ m thick) for UV analysis.

Differential scanning calorimetry (DSC) analyses were carried out with a Perkin-Elmer Pyris 1 DSC apparatus under a nitrogen atmosphere at a heating rate of 20 °C/min. The DSC system was first calibrated in temperature using indium and *n*-hexane. The sample was heated from -150 to 220 °C, followed by a cooling step and then a heating step again. The second runs led to the  $T_g$  values assessed from the inflection point in the heat capacity jump.

Thermogravimetric analyses were performed under air and nitrogen on a TGA Q50 apparatus from TA Instruments at a heating rate of 20  $^{\circ}$ C/min.

Synthesis of  $\alpha$ , $\omega$ -Dipropargyl Ether Bisphenol AF (A). To a flame-dried 250 mL three-neck round-bottom flask were added propargyl bromide (10.05 g, 53.7 mmol), bisphenol AF (compound **2**) (12.80 g, 107.4 mmol), and anhydrous potassium hydroxide (20.70 g, 150 mmol). The flask was flushed with nitrogen, and then dried acetone (20 mL) was added via a syringe. The mixture was stirred at room temperature for 12 h. The resulting solution was poured into diethyl ether (20 mL). The crude product was recrystallized twice from methanol to give a light yellow powder (11.13 g) (yield = 50%). FT IR (KBr, cm<sup>-1</sup>): 2280 ( $\nu_{C=C-H}$ ), 1000–1200 ( $\nu_{C-F}$ ). Raman shift (cm<sup>-1</sup>): 904 ( $\nu_{C-F}$ ), 1000–1200 ( $\nu_{aromatic C-Hin-plane bend$ ), 1480 ( $\nu_{C-O}$ ), 1600 ( $\nu_{ring stretch}$ ), 2133 cm<sup>-1</sup> ( $\nu_{C=C}$ ). 'H NMR (400 MHz;  $d_6$ -acetone):  $\delta$  (ppm) 3.1 (2 H, t, <sup>4</sup>J<sub>HH</sub> = 2.4 Hz), 4.8 (4 H, d, <sup>4</sup>J<sub>HH</sub> = 2.3 Hz), 6.8 (4 H, d, <sup>3</sup>J<sub>HH</sub> = 8.55 Hz), 7.4 (4 H, d, <sup>3</sup>J<sub>HH</sub> = 8.55 Hz). <sup>19</sup>F NMR (400 MHz;  $d_6$ -acetone):  $\delta$  (ppm) 158.8, 132.2, 126.7, 115.4, 100.4, 78.6, 75.4, 56.7.

Synthesis of 1,10-Diiodo-1H,1H,2H,2H,9H,9H,10H,10Hperfluorodecane  $(I-C_2H_4-C_6F_{12}-C_2H_4-I)$ . The batch bis-monoaddition of  $\alpha, \omega$ -diiodoperfluorohexane onto ethylene was performed in a 160 mL Hastelloy autoclave Parr system equipped with a manometer, a rupture disk, inlet and outlet valves, and a mechanical anchor. An electronic device regulated and controlled both the stirring and the heating of the autoclave. The autoclave was left closed for 20 min and purged with 30 bar of nitrogen pressure to prevent any leakage and degassed afterward. Then, a 2 mmHg vacuum was operated for 15 min. The initiator, di-4-tert-butylcyclohexyl peroxydicarbonate (4.22 g, 10 mmol) and 30.13 g (54.2 mmol) of I-C<sub>6</sub> $F_{12}$ -I in dry tertbutanol (40 mL) were introduced via a funnel tightly connected to the introduction valve. Next, ethylene (3.0 g, 0.1 mol) was introduced by double weighing. The autoclave was heated up to 50 °C for 7 h, and an increase of pressure from 5 to 13 bar was noted followed by a drop of pressure to 4 bar. Then, the autoclave was cooled to room temperature and put into an ice bath. After releasing the unreacted monomer, the autoclave was opened and tert-butanol was evaporated. The total product mixture was solubilized in THF and then precipitated from cold pentane. The fluorinated diiodo product was filtered, washed, and dried at room temperature under a 20 mmHg vacuum for 24 h, leading to a white powder in 80% yield. FT IR (KBr, cm<sup>-</sup> ): 1138 ( $\nu_{C-F}$ ). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>): δ (ppm) 3.2 (4 H, t, <sup>3</sup>J<sub>HH</sub> = 7.01 Hz), 2.6 (4 H, m). <sup>19</sup>F NMR (400 MHz; CDCl<sub>3</sub>): δ (ppm) -115.2 (4 F, m), -121.8 (4 F, m), -123.8 (4 F, m).

Synthesis of 1,10-Diazido-1H,1H,2H,2H,9H,9H,10H,10H-perfluorodecane ( $N_3$ - $C_2H_4$ - $C_6F_{12}$ - $C_2H_4$ - $N_3$ ) (**B**). A mixture composed of 7.80 g (12.8 mmol) of 1,10-diiodo-1H,1H,2H,2H,9H,9H,10H, 10H-perfluorodecane and 2.21 g (30.8 mmol) of sodium azide dissolved in DMSO (25 mL) and water (1 mL) was stirred at 50 °C for 48 h. Then, the reaction mixture was poured into water (1 L) and was extracted with diethyl ether. This procedure was repeated twice. The organic layer was washed with water twice, 10% sodium sulfite solution twice, water (3 times), brine, then dried over MgSO<sub>4</sub>, and filtered. The solvent was evaporated under reduced pressure to give 3.4 g of a pale green oil. The yield of the fluorinated diazide was 60%. FT IR (KBr, cm<sup>-1</sup>): 2100 ( $\nu_{N3}$ ), 1000–1200 ( $\nu_{C-F}$ ). <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta$  (ppm) 3.5 (4 H, t, <sup>3</sup>J<sub>HH</sub> = 7.07 Hz,), 2.3 (4 H, m). <sup>19</sup>F NMR (400 MHz, CDCl<sub>3</sub>): δ (ppm) –113.5 (4 F, m), –121.8 (4 F, m), –123.8 (4 F, m).

Synthesis of Poly(1,10-triazolofluorodecane-co-methylene ether hexafluorobisphenol AF) Copolymer (I). To a 100 mL three-neck round-bottom flask equipped with a magnetic stirrer were added copper bromide (57.1 mg, 0.4 mmol) and 2,2'-bipyridine (bpy) (141.7 mg, 0.8 mmol). The flask was sealed with three septa, and the suspension was purged with dry nitrogen for 60 min. In experiment 1 (Table 2) 1,10-diazido-1H,1H,2H,2H,9H,9H,10H, 10H-perfluorodecane (2.24 g, 5.10 mmol) and the aromatic dialkyne (2.03 g, 4.94 mmol) in 20 mL of THF were syringed through a septum.

The resulting mixture was stirred at room temperature for 48 h. The final mixture was passed through a short silica column to remove the copper catalyst. The mixture was precipitated from cold diethyl ether (500 mL). After filtration, the precipitate was dried under vacuum to give 1.5 g of a colorless gum (yield = 60%). Raman shift (cm<sup>-1</sup>) (Figure 2a): 904 ( $\nu_{C-F}$ ) 1000–1200 ( $\nu_{aromatic C-H in-plane bend$ ), 971, 1253, 1384, and 1487 ( $\nu_{triazole ring stretch$ ) 1480 ( $\nu_{C-O}$ ), 1600 ( $\nu_{aromatic ring stretch$ ). <sup>1</sup>H NMR (400 MHz,  $d_6$ -acetone):  $\delta$  (ppm) 3.0 (4 H, m), 4.9 (4 H, t, <sup>3</sup>J<sub>HH</sub> = 7.07 Hz), 5.3 (4 H, s), 7.4 (4 H, d, <sup>3</sup>J<sub>HH</sub> = 6.90 Hz), 7.2 (4 H, d, <sup>3</sup>J<sub>HH</sub> = 7.01 Hz), 8.4 (2 H, s). <sup>19</sup>F NMR (400 MHz,  $d_6$ -acetone):  $\delta$  (ppm) -63.2 (6 F, s), -113.5 (4 F, m), -121.8 (4 F, m), -124.3 (4 F, m). <sup>13</sup>C NMR (400 MHz,  $d_6$ -acetone):  $\delta$  (ppm) 159.8, 144.1, 132.2, 126.1, 125.3, 115.3, 62.4, 42.9.

Synthesis of Poly(bis(ether bisphenol AF) diacetylene) by Hay Coupling (3). The same mixture of copper bromide (57.1 mg, 0.4 mmol) and 2,2'-bipyridine (bpy) (141.7 mg, 0.8 mmol) was prepared as above and purged with dry nitrogen for 40 min. A solution of the aromatic dialkyne (A) (0.50 g, 1.21 mmol) in THF (10 mL) was syringed in the flask. The resulting mixture was stirred at room temperature for 48 h. The polymer was then precipitated from methanol. The white powder was filtered, precipitated from methanol twice, and dried at room temperature under a 20 mmHg vacuum for 24 h (yield = 65%). Raman shift (cm<sup>-1</sup>) (Figure 2c): 904 ( $\nu_{C-F}$ ), 1000–1200 ( $\nu_{aromatic C-H in-plane bend$ ), 1480 ( $\nu_{C-O}$ ), 1600 ( $\nu_{aromatic ring stretch$ ), 2264 ( $\nu_{C=C}$ ). <sup>1</sup>H NMR (400 MHz,  $d_6$ -acetone):  $\delta$  ppm 6.8 (4 H, d, <sup>3</sup>J<sub>HH</sub> = 8.55 Hz), 7.4 (4 H, d, <sup>3</sup>J<sub>HH</sub> = 8.55 Hz), 4.8 (4 H, d, <sup>4</sup>J<sub>HH</sub> = 2.30 Hz). <sup>19</sup>F NMR (400 MHz,  $d_6$ -acetone):  $\delta$  (ppm) –63.2 (6 F, m). <sup>13</sup>C NMR (400 MHz,  $d_6$ -acetone):  $\delta$  ppm 158.8, 132.2, 126.7, 79.2, 76.0, 71.1, 56.7.

Synthesis of Poly(1,10-triazolofluorodecane-co-methylene ether hexafluorobisphenol AF) Copolymer Combining "Click" Reaction and Hay Coupling (4). A 100 mL three-neck round-bottom flask equipped with a magnetic stirrer was filled with a mixture of copper(I) bromide (57.1 mg, 0.4 mmol), copper(II) bromide (25.2 mg, 0.2 mmol), and 2,2'-bipyridine (bpy) (141.7 mg, 0.8 mmol). The flask was then sealed with three septa. 1,10-Diazido-1H,1H,2H,2H,9H,9H,10H,10H-perfluorodecane (0.53 g, 1.20 mmol) and the aromatic dialkyne (A) (0.50 g, 4.9 mmol) in 20 mL of THF were syringed through a septum. The resulting mixture was stirred at room temperature for 48 h and then passed through silica powder to remove the copper catalyst. The mixture was concentrated and precipitated from cold diethyl ether (500 mL). After filtration, the precipitate was dried under vacuum to give 0.5 g of a colorless gum (yield = 50%). Raman shift (cm<sup>-1</sup>) (Figure 2d): 904 ( $\nu_{C-F}$ ) 1000–1200 ( $\nu$ aromatic C–H in-plane bend), 971, 1253, 1384, and 1487 ( $\nu_{\text{triazole ring stretch}}$ ) 1480 ( $\nu_{\text{C}-\text{O}}$ ), 1600 ( $\nu_{\text{aromatic ring stretch}}$ ), 2264 ( $\nu_{\text{C=C}}$ ). <sup>1</sup>H NMR (400 MHz,  $d_{6}$ -acetone):  $\delta$  (ppm) 3.0 (4 H, m), 4.9 (4 H, t, <sup>3</sup>J\_{HH} = 7.07 Hz), 5.3 (4 H, s), 7.4 (4 H, d, <sup>3</sup>J\_{HH} = 6.90 Hz), 7.2 (4 H, d, <sup>3</sup>J\_{HH} = 7.01 Hz), 8.4 (2 H, s). <sup>19</sup>F NMR (400 MHz,  $d_6$ -acetone):  $\delta$  (ppm) -63.2 (6 F, s), -113.5 (4 F, m), -121.8 (4 F, m), -124.3 (4 F, m). <sup>13</sup>C NMR (400 MHz, d<sub>6</sub>-acetone): δ (ppm) 159.8, 144.1, 132.2, 126.1, 125.3, 115.3, 62.4, 42.9.

#### **Results and Discussion**

**Monomer Synthesis.** Telechelic  $\alpha, \omega$ -dipropargyl ether hexafluorobisphenol AF (A) was prepared in satisfactory yield

Table 1. Experimental Conditions (Variation of Temperature (*T*), Reaction Time (*t*), and [NaN<sub>3</sub>]<sub>0</sub>/[IC<sub>2</sub>H<sub>4</sub>C<sub>6</sub>F<sub>12</sub>C<sub>2</sub>H<sub>4</sub>]<sub>0</sub> Initial Molar Ratio, and Yields of Telechelic N<sub>3</sub>-C<sub>2</sub>H<sub>4</sub>-C<sub>6</sub>F<sub>12</sub>-C<sub>2</sub>H<sub>4</sub>-N<sub>3</sub> Diazido (B))

entry	<i>T</i> (°C)	<i>t</i> (h)	$[NaN_3]_0/[IC_2H_4C_6F_{12}C_2H_4I]_0$	yield (%)	
1	RT	96	3	30	
2	RT	96	6	40	
3	50	48	3	>95	

from propargyl bromide and hexafluorobisphenol AF as reported by Dirlikov et al.<sup>8e</sup> and Hay.<sup>53</sup> Characteristic features of monomer (A) were evidenced by Raman and NMR spectroscopies. Characteristic band of C–F vibration appeared at 904 cm<sup>-1</sup> in the Raman spectrum (Figure S1 in the Supporting Information). The peaks observed in the 1100–1300 cm<sup>-1</sup> range and at 1600 cm<sup>-1</sup> were attributed to aromatic C–H inplane bend and aromatic ring stretch,<sup>54</sup> respectively. An intense band at 2133 cm<sup>-1</sup> characteristic of the triple-bond vibration of acetylene moieties<sup>54</sup> was also noted. Moreover, the two characteristic signals of the acetylenic carbon atoms were found in the <sup>13</sup>C NMR spectrum at 75.4 and 78.6 ppm while the aliphatic carbon in the  $\alpha$ -position (CH<sub>2</sub>O) appeared at 56.7 ppm. The <sup>1</sup>H NMR spectrum exhibited the protons in the ethynyl and CH<sub>2</sub>O groups as a triplet at 3.1 ppm and a doublet at 4.8 ppm, respectively.

1,10-Diazido-1H,1H,2H,2H,9H,9H,10H,10H-perfluorodecane (**B**) was obtained from commercially available  $\alpha, \omega$ diiodoperfluorohexane in two steps: (i) batch bis-monoaddition of ethylene onto  $\alpha, \omega$ -diiodoperfluorohexane and (ii) nucleophilic substitution of iodine atoms of the resulting 1,10-diiodo-1H,1H,2H,2H,9H,9H,10H,10H-perfluorodecane in the presence of sodium azide. Step 1 was adapted from the reaction of Manseri et al.,<sup>55</sup> but carrying out the reaction at 50 °C for 8 h with di-4-tert-butylcyclohexyl peroxydicarbonate as the initiator. This led to 1,10-diiodo-1H,1H,2H,2H,9H,9H, 10H,10H-perfluorodecane (I-C<sub>2</sub>H<sub>4</sub>-C<sub>6</sub>F<sub>12</sub>-C<sub>2</sub>H<sub>4</sub>-I) in 80% yield. Step 2 was based on Malik et al.<sup>56</sup> pioneering synthesis of fluorinated diazides (yield = 40%). Indeed, the reaction conditions were optimized to improve the yield. Particularly, temperature, reaction time, and initial  $[NaN_3]_0/[IC_2H_4C_6F_{12} C_2H_4I_{0}$  molar ratio were monitored (Table 1). When the reaction was carried out with an excess of NaN<sub>3</sub> (3 or 6 mol equiv, entries 1 and 2, Table 1) at room temperature, it proceeded smoothly and was not complete (30% and 40%) yields, respectively, even after 96 h), suggesting that the amount of excess NaN<sub>3</sub> was not a decisive parameter at room temperature. Instead, when the reaction was carried out at 50 °C with a 3-fold molar excess of NaN<sub>3</sub> with respect to  $I-C_2H_4-C_6F_{12}-C_2H_4-I$ , it reached completion after 48 h (entry 3, Table 1), yielding, after purification, 60% of 1,10-diazido-1H, 1H, 2H, 2H, 9H, 9H, 10H, 10H-perfluorodecane (N<sub>3</sub>-C<sub>2</sub>H<sub>4</sub>- $C_6F_{12}-C_2H_4-N_3$  (**B**).

The <sup>15</sup>F NMR spectrum of telechelic fluorinated diazido compound (Figure S2 in Supporting Information) revealed the low-field shift of the multiplet assigned to the difluoromethylene adjacent to methylene group from -114.8 to -113.6 ppm, while the other fluoromethylene signals did not shift, as expected. The <sup>1</sup>H NMR spectrum (Figure S3) showed the low-field shift of the  $-CH_2-X$  terminal group from 3.2 ppm (X = I) to 3.4 ppm (X = N<sub>3</sub>) because of the higher electron-withdrawing effect of azido group with respect to that of iodine. Finally, the FT IR spectrum (Figure S4) showed a strong sharp frequency at 2100 cm<sup>-1</sup>, characteristic of the azide function.<sup>56</sup> The other expected frequencies, corresponding to the C–F vibrations of the perfluorohexane central group, were observed in the range 1100-1200 cm<sup>-1</sup>.

Table 2. Experimental Conditions, Yields, Molecular Weights, Polydispersity Indices (PDIs), and Intrinsic Viscosities of the Polymers Synthesized from the Condensation of 1,10-Diazido-1*H*,1*H*,2*H*,9*H*,9*H*,10*H*,10*H*-perfluorodecane (B) with α,ω-Dipropargyl Ether Bisphenol AF (A)

expt	A/B/CuBr/bpy (mmol) <sup>a</sup>	r	atmosphere	yield (%)	$M_n^b$ (g/mol)	PDI	$[\eta^{35 ^{\circ}\mathrm{C}}]^c (\mathrm{dL}\mathrm{g}^{-1})$
1	4.94/5.10/0.40/0.80	$0.97^{d}$	$N_2/O_2$ traces	60	37 000	1.8	0.4
2	1.21/1.20/0.40/0.80	$0.99^{e}$	$N_2/O_2$ traces	65	50000 to $> 200000$	5.3	0.6
3	1.20/0.00/0.40/0.80		$N_2/O_2$ traces	43	5000 to 40 000	1.8	
4	1.21/1.20/0.40/0.80	$0.99^{e}$	O <sub>2</sub>	60	60 000	1.8	0.4

<sup>*a*</sup>A:  $n_{\alpha,\omega}$ -dipropargyl etter bisphenol AF: B:  $n_{1,10}$ -diazido1H,1H,2H,2H,9H,9H,10H,10H-perfluorodecane. <sup>*b*</sup> $M_n$  assessed by SEC (polystyrene standards). <sup>*c*</sup>Intrinsic viscosity assessed in acetone at 35 °C. <sup>*d*</sup>r = A/B. <sup>*e*</sup>r = B/A.





Polycondensation of  $\alpha, \omega$ -Dipropargyl Ether Hexafluorobisphenol AF (A) with 1,10-Diazido-1*H*,1*H*,2*H*,2*H*,9*H*,9*H*,10*H*, 10*H*-perfluorodecane (B). Cummins et al.<sup>52a</sup> reported that during the grafting of polystyrene derivative (in a confined medium) onto a surface by "click" reaction a homocoupling (Hay coupling) of the terminal alkynes was also observed. Starting from this statement, we have decided to determine the required experimental conditions to promote further the homocoupling of alkyne moieties in **A** with the objective to produce a block copolymer. Hence, it was of interest to investigate a series of reactions in which the experimental conditions were carefully selected to favor one reaction with regards to the others (Table 2).

Scheme 2 displays the predicted structure of the product resulting from the stoichiometric polycondensation by the azide/alkyne "click" reaction.<sup>51</sup> Similar reaction conditions as those reported by Lutz et al.<sup>57a,b</sup> were used.

The polycondensation was performed in THF at room temperature, using 0.4 mmol of CuBr and 0.8 mmol. of 2,2'bipyridine (bpy). The choice of the bpy ligand was driven by a recent extensive study from Matyjaszewski's group,<sup>22</sup> who reported that the nature of aminated ligands induced a neat effect onto kinetics in the following increasing order of magnitude: N, N, N', N'', N''-pentamethyldiethylenetriamine (PMEDTA) (×230) > N, N, N', N'', N''', N'''-hexamethyltriethylenetetraamine (HMTETA) (×55) > tris[(dimethylamino)ethyl]amine (Me<sub>6</sub>-TREN) ( $\times$  20) > 2,2':2',6''-terpyridine (tpy) (×8.6) > tris[(2-pyridyl)methyl]amine (TPMA) (×1.7) > no ligand  $(\times 1) > 2,2'$ -bipyridine (bpy)  $(\times 0.43)$ . The increase of the reaction rate by aminated aliphatic ligands is partially explained by their strong basic behavior, which is higher than that of aromatic amines. Indeed, various authors<sup>22,23</sup> have noted an increase of the "click" reaction rate in the presence of a base, which is assumed to favor the formation of copper(I) acetylide complexes. Moreover, aliphatic amines are more labile than ligands derived from pyridine, thus making easier the



Figure 1. Size exclusion chromatograms of copolymer 1 (Exp. 1, Table 2, A/B = 0.97) (upper figure) and copolymer 2 (Exp. 2, Table 2, B/A = 0.99) (lower figure) calibrated with polystyrene standards.

coordination of azide by copper(I) acetylide.<sup>25</sup> Here, 2,2'-bipyridine was used with the objective to slow down the rate of the "click" reaction.

Experiments 1 and 2 were focused on the influence of concentrations of the reactants onto the behavior of the polycondensation, under quasi-inert atmosphere, by simply varying the [dipropargyl]<sub>0</sub>/[diazido]<sub>0</sub> A/B molar ratio. Once the reactions completed, the total product mixtures were characterized by size exclusion chromatography (SEC). The SEC chromatograms corresponding to experiments 1 and 2 in Table 2 are presented in Figure 1.

Interestingly, the obtained SEC chromatograms evidenced a dependence of the molecular weight distributions versus  $\mathbf{A}/\mathbf{B}$  molar ratio values. In experiment 1, an excess of  $\mathbf{B}$  with respect to  $\mathbf{A}$  ( $n_{\alpha,\omega}$ -dipropargylether bisphenol AF/ $n_{1,10}$ -diazido-1H,1H,2H,2H,9H,9H,10H,10H-perfluorodecane = 0.97) resulted in a monomodal distribution centered at  $M_n = 37\,000$  g/mol with a polydispersity index = 1.8 (in polystyrene standards, Figure 1-1). The theoretical value of the average degree of polymerization (DP<sub>n</sub>) could be assessed by the Flory equation:

$$\mathrm{DP}_{\mathrm{n}} = \frac{1+r}{1+r-2pr}$$





where *p* is the extent of the reaction and *r* the initial molar ratio between the reactive functions (with  $r \le 1$ ).

When r = 0.97 and p = 1 (excess of telechelic diazido compound), i.e. experiment 1 (Table 2), the corresponding theoretical DP<sub>n</sub> value is 65. As the average molecular weight of monomeric unit is 426 g/mol, the resulting theoretical  $M_n$  value for r = 0.97 is 28 000 g/mol,<sup>51</sup> which is in close agreement with the experimental value of 37 000 g/mol. To confirm the high molecular weight of copolymer 1, the intrinsic viscosity was assessed in acetone at room temperature, giving 0.40 dL g<sup>-1</sup>. This value confirms that "click" reaction was very efficient, in spite of the excess of **B** with respect to **A** (r = 0.97).

However, the correlation of intrinsic viscosity with molecular weight for this original linear polymer could not be achieved by the Mark and Houwink equation since K and  $\alpha$ parameters have not been reported. In this case, the polycondensation seems to proceed via azide/alkyne "click" reaction as displayed in Scheme 3, and copolymer 1 is expected to exhibit a microstructure based on alternating aromatic and fluorinated units, bearing azido end groups.

The <sup>1</sup>H and <sup>13</sup>C NMR spectra of copolymer **1** were consistent with the proposed structure (Figures S5 and S6 in Supporting Information). The triazole ring formation was evidenced by the presence of characteristic signals at 8.5 ppm (<sup>1</sup>H NMR) and at 144.1 and 125.3 ppm (<sup>13</sup>C NMR).<sup>58</sup> Furthermore, strong low-field shifts of the aliphatic protons were noted for both precursors in the <sup>1</sup>H NMR spectrum. For example, the methylene groups of the fluorinated diazido reactant shifted from 3.6 to 4.9 ppm and from 2.3 to 3.0 ppm in polymer **1**. Similarly, the singlet attributed to the methylene group in CH<sub>2</sub>O of reactant A underwent a low-field shift from 4.9 to 5.3 ppm after copolymerization. Raman spectroscopy provided additional structural evidences (Figure 2a) with bands at 971, 1253, 1384, and 1487 cm<sup>-1</sup> that are characteristic of the triazole ring stretch.<sup>59</sup> No signal assigned to the triple bond vibration of acetylene moieties<sup>54</sup> was observed at 2133 cm<sup>-1</sup>.

In experiment 2, a small excess of  $\alpha,\omega$ -dipropargyl ether bisphenol AF (A) was added with respect to 1,10-diazido-1*H*,1*H*,2*H*,2*H*,9*H*,9*H*,10*H*,10*H*-perfluorodecane ( $n_{\alpha,\omega$ -dipropargyl ether bisphenol AF/ $n_{1,10}$ -diazido-1*H*,1*H*,2*H*,9*H*,9*H*,10*H*,10*H*-perfluorodecane = 1.01 and r = 0.99). The theoretical value of the average degree of polymerization assessed by the Flory equation was 199, leading to a theoretical  $M_n$  value of 85000 g/mol. The SEC chromatogram (Figure 1-2) showed the presence of a



Figure 2. Raman spectra of (a) copolymer 1, (b) copolymer 2, (c) homopolymer 3, and (d) copolymer 4 in the  $880-2300 \text{ cm}^{-1}$  range.

polymodal distribution covering a wide range of molecular weights (from 50 000 to more than 200 000 g/mol). The high molecular weight of copolymer **2** was further confirmed by a higher intrinsic viscosity value of 0.60 dL g<sup>-1</sup> (experiment 2, Table 2). Here, a strong discrepancy between theoretical and experimental  $M_n$  values is observed. To explain this result, the reaction pathway depicted in Scheme 4 is proposed. The excess of **A** allows some Hay acetylenic homocoupling between the terminal alkyne groups of the copolymers generated by "click" reaction. As a result, a high molecular weight copolymer exhibiting an original microstructure with bridging bisacetylene segments randomly distributed along the copolymer chain may be obtained.

<sup>13</sup>C NMR spectroscopy analysis (Figure S6 in Supporting Information) did not allow corroborating this mechanism as the characteristic peaks of the two diacetylenic carbons at 76.0 and 71.2 ppm were not detected, probably due to the expected low content of such isolated bridging units with Scheme 4. Polycondensation Reaction Combining "Click" Reaction (First Step, Major) and Hay Coupling (Second Step, Minor) Starting from α,ω-Dipropargyl Ether Hexafluorobisphenol AF (A) and 1,10-Diazido-1*H*,1*H*,2*H*,9*H*,9*H*,10*H*,10*H*-perfluorodecane (B)



Scheme 5. Synthesis of Poly(bis(ether bisphenol AF) diacetylene) by Hay Coupling of  $\alpha, \omega$ -Dipropargyl Ether Hexafluorobisphenol AF (A) (bpy = 2,2'-Bipyridine)



regards to the high molecular weight of the copolymeric chains. Also, to evidence the presence of diacetylenic units, copolymer **2** was characterized by Raman spectroscopy. Besides the signals observed in the 971–1500 cm<sup>-1</sup> range and at 1600 cm<sup>-1</sup> attributed to triazole ring stretch<sup>59</sup> and aromatic ring stretch,<sup>54</sup> respectively, the Raman spectrum (Figure 2b) showed a signal at 2264 cm<sup>-1</sup>, which may be assigned to the triple-bond vibration of diacetylene moieties.<sup>60,61</sup> No signal at 2133 cm<sup>-1</sup>, characteristic of the triple bond of terminal acetylene,<sup>54</sup> was noted.

To further demonstrate that Hay coupling may indeed occur in such an oxygen-poor atmosphere, a third reaction was carried out in the absence of bisazido compound (experiment 3, Table 2), under conditions similar to those used for the azide/alkyne "click" reaction in experiments 1 and 2 (Scheme 5).

Homopolymer **3** was isolated as a white fibrous material and showed excellent solubility in THF. The weight-average molecular weights as determined by size exclusion chromatography relative to polystyrene standards ranged from 42 000 to 200 000 g/mol (Figure S7 in Supporting Information).

The <sup>1</sup>H and <sup>13</sup>C NMR spectra of homopolymer **3** were consistent with the assigned structure. No residual ethynyl protons due to unreacted acetylene groups were observed for the polymer by <sup>1</sup>H NMR (Figure S8 in Supporting Information). The <sup>13</sup>C NMR spectra also showed that the terminal ethynyl carbons were converted into diacetylenic carbons after polymerization. For example, two diacetylenic



Figure 3. Size exclusion chromatogram of copolymer 4 (experiment 4, Table 2).

carbons at 76.0 and 71.1 ppm in the spectrum of homopolymer **3** (Figure S9) replaced the two ethynyl carbons at 78.6 and 75.4 ppm which were observed in the spectrum of monomer **A**. In the Raman spectrum (Figure 2c), the intense band corresponding to the triple-bond vibration of diacetylene moieties was observed at 2264 cm<sup>-1</sup>.<sup>60,61</sup> These results evidence that the Hay coupling reaction could be initiated in the presence of oxygen traces.

The presence of a band at  $2264 \text{ cm}^{-1}$  in the Raman spectra of both copolymer **2** and homopolymer **3**, which is assigned to diacetylenic moieties, brings evidence that some acetylene homocoupling occurred during the synthesis of copolymer **2**. The difference of intensity of this characteristic signal observed between both spectra is representative of the low content of such isolated bridging units in copolymer **2** with regards to the high molecular weight of the copolymeric chains. Hence, it is worth considering that Hay coupling occurred as a side reaction (Scheme 4, second step) when the "click" reaction was carried out with an excess of alkyne as in the case of experiment 2, in agreement with the work of Cummins et al.<sup>52a</sup>

Consequently, these first three experiments (Table 2) enabled us to target the experimental conditions (absence of copper(II) reductive agent, ligand based on pyridine derivative, and alkyne functions in excess) in which Hay homocoupling of terminal alkynes may occur when performing azide–alkyne "click" reaction.

This led us to implement the synthesis of an original fluorine-containing poly(alkyl aryl) ether bearing a block structure by promoting competition between "click" reaction and Hay homocoupling.

Copper(II) salts are known to induce initiation of Hay coupling by oxidation of copper(I) acetylide species.<sup>14</sup> Hence, experiment 2 was repeated in the presence of oxygen and a copper(II) salt to favor Hay homocoupling (experiment 4, Table 2). A small excess of  $\alpha, \omega$ -dipropargyl ether bisphenol AF (A) was added with respect to 1,10-diazido-1*H*,1*H*,2*H*, 2*H*,9*H*,9*H*,10*H*,10*H*-perfluorodecane (B) ( $n_{\alpha,\omega-\text{dipropargyl ether}}$  bisphenol AF/ $n_{1,10-\text{diazido-1}H,1H,2H,2H,9H,9H,10H,10H$ -perfluorodecane (B) ( $n_{\alpha,\omega-\text{dipropargyl ether}}$  bisphenol AF/ $n_{1,10-\text{diazido-1}H,1H,2H,2H,9H,9H,10H,10H$ -perfluorodecane = 1.01 and r=0.99). The suspension was purged with dry nitrogen for 10 min (experiment 4, Table 2). Interestingly, the SEC chromatogram (Figure 3) exhibited a quasi-monomodal distribution centered at  $M_n = 60\,000$  g/mol with a polydispersity index of 1.8 (polystyrene standards), as opposed to the multimodal distribution observed in experiment 2. The corresponding value of intrinsic viscosity obtained was 0.43 dL g<sup>-1</sup>.

The differences in molecular weight distributions observed by SEC between polymers **2** and **4** may be considered as an evidence that the new conditions favored Hay coupling enough to consume  $\alpha, \omega$ -dipropargyl ether bisphenol AF (A) species faster than in the course of the "click" reaction. Consumption of the alkyne groups by Hay coupling competitive to the azide—alkyne reaction would result in an evolution of the original r ratio (excess of alkynes) toward an excess of azide groups (Scheme 6). As in experiment 1, a monomodal distribution was observed.

The <sup>13</sup>C NMR spectrum (Figure S10 in Supporting Information) of the obtained polycondensate did not provide evidence for the characteristic signals of diacetylenic carbons, suggesting that the size of the diacetylenic segments were still rather small ( $m \ll n$ ).

A strong sharp frequency at  $2100 \text{ cm}^{-1}$  was observed in the FTIR spectrum (Figure S11 in Supporting Information). This result is consistent with the presence of terminal azide functions, as depicted in Scheme 6. As in the case of copolymer 2, the Raman spectrum of copolymer 4 (Figure 2d) exhibited the signal at  $2264 \text{ cm}^{-1}$  corresponding to the triple-bond vibration of diacetylene moieties.

**Thermal Properties.** In an attempt to provide further evidence of the formation of blocks in polymer **4** in contrast to polymers **1** or **2**, the thermal behaviors of the four polymers were investigated by differential scanning calorimetry (DSC). The corresponding DSC thermograms are displayed in Figure 4.

All polymers were amorphous. Copolymers 1 and 2 clearly showed only one glass transition temperature centered at 60 and 90 °C, respectively. The 30 °C difference may be explained by the higher molecular weight distribution of polymer 2. The diacetylene-containing polymer synthesized from experiment 3 exhibited an exothermic peak close to 183 °C, which was attributed to thermally activated cross-linking of diacetylenes, as reported by several authors.<sup>62–66</sup>

Interestingly, the DSC thermogram of copolymer obtained from experiment 4 exhibited two distinct thermal transitions centered at 90 and 152 °C. The first transition (90 °C) was assigned to a glass transition, as in copolymer **2**. The second transition at 152 °C may be attributed to block that would be composed of diacetylene moieties. To define the nature of this second block, we performed the thermal curing at 175 °C of copolymer **4**. After 15 min, the polymer film became insoluble in all organic solvents. Interestingly, the DSC analysis of cured polymer **4** (Figure 4) evidenced the presence of one glass transition at 90 °C. The second transition was not observed. Consequently, this transition could be attributed to the exothermic cross-linking of diacetylenes moieties in a poly(aryl) block.

To confirm the thermal cross-linking of diacetylenic moieties in copolymer **4**, ultraviolet absorption spectra were recorded before and after thermal curing. In the UV spectrum of the uncured film, the presence of diacetylenes units was evidenced by an absorption band at 254 nm.<sup>66</sup> The signals observed at 260 and 279 nm were assigned to triazole ring,<sup>67</sup> while no absorption bands in the visible region were noted.

After heating to 170 °C for 15 min, a new absorption band appeared in the spectrum as a broad signal centered at 470 nm, while the band at 254 nm vanished. This was concomitant with a drastic color change from colorless to dark red, which is known to result from  $\pi$ -delocalization along the cross-linked diacetylenes network.<sup>68</sup>

These additional thermal properties are consistent with the block structure of copolymer **4**, as depicted in Scheme 6.

Thermooxidative Stability. Thermal stabilities of copolymer 1 and homopolymer 3 were investigated by thermogravimetric analysis (TGA). The thermal behavior of poly-(1,10-triazolofluorodecane-*co*-methylene ether hexafluorobisphenol AF) copolymer 1 was established both under air (Figure 6a) and under nitrogen atmosphere (Figure 6b). Scheme 6. Polycondensation Mechanism Proposed for the Competition between Hay Coupling and "Click" Reactions Starting from α,ω-Dipropargyl Ether Hexafluorobisphenol AF (A) and 1,10-Diazido-1*H*,1*H*,2*H*,9*H*,9*H*,10*H*,10*H*-perfluorodecane (B)



Thermal gravimetric analysis of copolymer 1 obtained under air (Figure 6a) indicated that these original copolymers had a good thermooxidative stability with a weight loss starting at around 270 °C. Two stages were observed in the thermal decomposition. The first step from 300 to 473 °C corresponded to a 40 wt % loss and could be attributed to the loss of aliphatic segments due to the cleavage of the  $CH_2$ –N bonds, which has been previously reported to occur at 360 °C, by Hans et al.<sup>69</sup>



Figure 4. DSC thermograms of copolymer 1 (a), copolymer 2 (b), homopolymer 3 (c), copolymer 4 (d) before thermal curing, and copolymer 4 (e) after thermal curing (15 min at 170 °C).



Figure 5. UV spectra of copolymer 4 (exp. 4, Table 2) prior to thermal curing (dotted line) and after 15 min of thermal curing at 170 °C (solid line).



Figure 6. TGA thermograms of copolymer 1 (Expt 1, Table 2) at 20 °C min<sup>-1</sup> under air (a) and under nitrogen atmosphere (b).

and by Gaur et al.<sup>70</sup> Above 473 °C, the degradations of both aryl moieties<sup>71</sup> and of the triazole ring<sup>72</sup> were observed, with a complete decomposition reached at 520 °C.

The thermal degradation trace for copolymer 1 under nitrogen atmosphere was unchanged between 270 and 410 °C (Figure 6b), confirming that the first stage of the degradation of the copolymers is only temperature related. However, from 550 up to 600 °C, the decomposition was



Figure 7. TGA thermogram of homopolymer 3 (exp. 3, Table 2) at 20  $^{\circ}$ C min<sup>-1</sup> under air.

much slower and even reached a plateau above 650 °C up to 800 °C, showing a high residue weight (higher than 40%) at 800 °C. Such a difference of degradation rates above 550 °C between air and nitrogen atmosphere has already been reported in the case of polytriazole resins by Xue et al.,<sup>72</sup> who suggested that the second stage corresponds to a thermooxidative degradation. Under air, oxygen participates in the formation of chars at temperatures below 550 °C, which quickly decompose with increasing temperature. No residue remained at 800 °C (Figure 6a).

The TGA thermogram for homopolymer (experiment 3, Table 2) under oxygen atmosphere is presented in Figure 7. As expected, the thermal stability of the homopolymer was higher than that of copolymer 1, as justified by its aromatic backbone. A single weight loss was observed (10 wt % loss reached at about 550 °C) and corresponded to the thermal full degradation of the polymeric chain.

The results of thermal analysis demonstrated that these original polymers exhibit high thermooxidative stabilities under air.

### Conclusions

Original fluorinated copolymers containing triazoles and based on oligo(tetrafluoroethylene) were synthesized by condensation via azide/alkyne "click" reaction between a telechelic aryl diyne and a fluorinated telechelic diazido compound. The latter was synthesized in two steps from the bis(ethylenation) of the  $\alpha,\omega$ -diiodo fluorinated telomers followed by a nucleophilic substitution of iodine atoms by sodium azide. This polycondensation was simple, clean, occurred in mild conditions, and led to high yields.

However, under low oxygen amount and in the absence of copper(II) reductive agent, the homocoupling of terminal alkynes in polycondensates obtained by "click" reaction occurred when the alkyne concentration was higher than that of azide. The presence of isolated diacetylenic units was demonstrated by the presence of a signal at 2264 cm<sup>-1</sup> in the Raman spectra of the obtained copolymers. This side reaction enabled us to produce high molecular weight copolymers (>200 000 g/mol) via bridging central diacetylene units.

Furthermore, in the presence of oxygen, 2,2'-bipyridine as the ligand, and Cu(II) salt, the side reaction was turned into a competitive reaction leading to the synthesis of block copolymers. Such an original structure was confirmed by both DSC and UV-vis analyses. The corresponding DSC thermogram evidenced the presence of an exothermic peak close to 183 °C, which was attributed to thermally activated cross-linking of diacetylenes. The polymerization of diacetylenes moieties was further confirmed by the presence of a broad absorption band at 470 nm in the UV-vis spectrum of the thermally cured copolymer.

#### 4498 Macromolecules, Vol. 43, No. 10, 2010

Hence, thanks to the ability of the monomers to undergo either Hay coupling or "click" reaction, a simple tune of the reaction conditions allowed us to obtain three drastically different copolymers from a same set of precursors. These new fluorinated polymers exhibit interesting thermal and thermooxidative stabilities by the presence of the triazole ring, which can withstand high thermal temperatures (up to 550 °C) under air.

Acknowledgment. The authors thank DuPont Performance Elastomers Co. for partially financing this study, Dr. David Bourgogne (Inst. Charles. Gerhardt. Montpellier) for Raman spectroscopy analysis, and Akzo Nobel Co. for providing free sample of di(4-*tert*-butylcyclohexyl)peroxydicarbonate.

**Supporting Information Available:** Raman spectrum of hexafluorobisphenol AF dipropargyl ether, <sup>1</sup>H NMR, <sup>19</sup>F NMR, and infrared spectra of  $N_3C_2H_4C_6F_{12}C_2H_4N_3$ , <sup>1</sup>H and <sup>13</sup>C NMR spectra and SEC chromatogram of homopolymer **3**, and <sup>13</sup>C NMR and infrared spectra of copolymer **4**. This material is available free of charge via Internet at http://pubs. acs.org.

#### **References and Notes**

- (1) Scheirs, J. Modern Fluoropolymers; Wiley: New York, 1997.
- (2) Hougham, G.; Cassidy, P. E.; Johns, K.; Davidson, T. Fluoropolymers; Kluvert: New York, 1999; Vol. 2.
- (3) Ameduri, B.; Boutevin, B. Well-Architectured Fluoropolymers: Synthesis, Properties and Applications; Elsevier: Amsterdam, 2004.
- (4) D'Alelio, A. U.S. Pat. No. 5,562,231 1971. Assigned to The United States of America as represented by the Secretary of the Air (Washington, D.C.).
- (5) Picklesimer, L. G. U.S. Pat. No. 4,226,800, 1980. Assigned to The United States of America as represented by the Secretary of the Air (Washington, D.C.).
- (6) Wu et al. ACS Symp. Ser. 1990 417.
- (7) Sillion, B.; Rabillaud, G. Hetrocycle polymers with high glass transition temperatures. In Ebdon, J. R., Eastmond, G. C., Eds.; *High Tg Heterocyclic Polymers*;Blackie Publishers: Glasgow, UK, 1995; Chapter 7, pp 236–289.
- (8) (a) Dirlikov, S.; Feng, Y. Proc. ACS. Div. Polym. Mater. Sci. Eng. 1988, 59, 990–991. (b) Feng, Y.; Dirlikov, S. K. Proc. ACS Div. Polym. Mater. Sci. Eng. 1989, 60, 618–619. (c) Feng, Y.; Dirlikov, S. K. Proc. ACS. Div. Polym. Mater. Sci. Eng. 1989, 61, 835–836. (d) Dirlikov, S. K.; Feng, Y. 3rd Int. SAMPE Electron. Conf. 1989, 3, 169–172. (e) Dirlikov, S. K.; Feng, Y. Proc. Polym. Mater. Sci. Eng. 1990, 62, 603–604. (f) Dirlikov, S. K.; Feng, Y. Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.) 1990, 31, 322–323. (g) Chen, Z.; Wang, D.; Dirlikov, S. K. Polym. Mater. Sci. Eng. 1993, 69, 388–389.
- (9) (a) Goldschalx, J. P.; Inbasekaran, M. N.; Bartos, B. R.; Schek, D. M.; Laman, S. A. Int. SAMPE Tech. Conf. 1990, 22, 163. (b) Douglas, W. E.; Overend, A. S. Eur. Polym. J. 1991, 27, 1279–1285.
- (10) Richer, S.; Alamercery, S.; Paisse, O.; Raffin, G.; Sanglar, C.; Waton, H.; Grenier-Loustalot, M. F. Polym. Polym. Compos. 2001, 9 (2), 103–120.
- (11) (a) Glaser, C. Ber. Ditsch. Chem. Ges. 1869, 2, 422–424. (b) Glaser, C. Ann. Chem. Pharm. 1870, 154, 137–171.
- (12) (a) Hay, A. S. J. Org. Chem. 1960, 25, 1275–1280. (b) Hay, A. S. J. Org. Chem. 1962, 27, 3320–3322.
- (13) Raphael Acetylene Compounds in Organic Synthesis; Academic Press: New York, 1965; p 127.
- (14) Siemsen, P.; Levingston, R. C.; Diederich, F. Angew. Chem., Int. Ed. 2000, 39, 2632–2657.
- (15) Carpick, R. W.; Sasaki, D. Y.; Marcus, M. S.; Eriksson, M. A.; Burns, A. R. J. Phys.: Condens. Matter 2004, 16, R679–R697.
- (16) (a) Kolb, H. C.; Finn, M. G.; Sharpless, K. B. Angew. Chem., Int Ed. 2001, 40, 2004. (b) Rostovtsev, L. G.; Green, L. G.; Fokin, V. V.; Sharpless, K. B. Angew. Chem., Int. Ed. 2002, 41, 2596–2601.
- (17) Bock, V. D.; Hiemstra, H.; van Maarseveen, J. H. V. Eur. J. Org. Chem. 2006, 2006, 51–55.
- (18) Punna, S.; Kuzelka, J.; Wang, Q.; Finn, M. G. Angew. Chem., Int. Ed. 2005, 44, 2215–2221.
- (19) Himo, F.; Lovell, T.; Hilgraf, R.; Rostovtsev, V. V.; Noodleman, L.; Sharpless, K. B.; Fokin, V. V. J. Am. Chem. Soc. 2005, 127, 210– 216.

- (20) Meng, J-C.; Fokin, V. V.; Finn, M. G. Tetrahedron Lett. 2005, 46, 4543–4546.
- (21) Lewis, W. G.; Magallon, F. G.; Fokin, V. V.; Finn, M. G. J. Am. Chem. Soc. 2004, 126, 9152–9156.
- (22) Golas, P. L.; Tsarevsky, N. V.; Sumerlin, B. S.; Matyjaszewski, K. Macromolecules 2006, 39, 6451–6456.
- (23) Jang, H.; Fafarman, A.; Holub, J. M.; Kirshenbaum, K. Org. Lett. 2005, 7, 1951–1954.
- (24) Bodine, K. D.; Gin, D. Y.; Gin, M. S. J. Am. Chem. Soc. 2004, 126, 1638–1639.
   (25) P. U. V. M. V. M. K. J. K. F. J. C.
- (25) Bock, V. D.; Hiemstra, H.; Van Maarseveen, J. H. Eur. J. Org. Chem. 2005, 51–68.
- (26) Wang, Z. X.; Qin, H. L. Chem. Commun. 2003, 19, 2450-2455.
- (27) Mamat, C.; Ramenda, T.; Wuest, F. R. Mini-Rev. Org. Chem. 2009, 6, 21–26.
- (28) Badjic, J. D.; Balzani, V.; Credi, A.; Lowe, J. N.; Silvi, S.; Stoddart, J. F. Chem.—Eur. J. 2004, 10, 1926–1931.
- (29) Zhang, X.; Lian, X.; Liu, L.; Zhang, J.; Zhao, H. Macromolecules 2008, 41, 7863–7868.
- (30) Haensch, C.; Chiper, M.; Ulbricht, C.; Winter, A.; Hoeppener, S.; Schubert, U. S. *Langmuir* 2008, 24, 12981.
- (31) Scheel, A. J.; Komber, H.; Viot, B. I. Macromol. Rapid Commun. 2004, 25, 1175–1182.
- (32) Sumerlin, B. S.; Vogt, A. P. Macromolecules 2010, 43, 1-13.
- (33) Binder, W. H.; Sachsenhofer, R. *Macromol. Rapid Commun.* 2008, 29, 952–961.
- (34) Wu, P.; Feldman, A. K.; Nugent, A. K.; Hawker, C. J.; Scheel, A.; Voit, B. Angew. Chem., Int. Ed. 2004, 43, 3928–3934.
- (35) Van Steenis, DJVC.; David, O. R. P.; Van Strijdonck, G. P. F.; Van Maarseveen, J. H.; Reek, J. N. H. *Chem. Commun.* 2005, 34, 4333– 4335.
- (36) Helms, B.; Mynar, J. L.; Hawker, C. J.; Fréchet, J. M. J. J. Am. Chem. Soc. 2005, 126, 15020–15025.
- (37) Parrish, B.; Breiteinkamp, R. B.; Emrick, T. J. Am. Chem. Soc. 2005, 127, 7404–7408.
- (38) Carroll, J. B.; Jordan, B. J.; Xu, H.; Herdogan, B.; Lee, L.; Cheng, L. Org. Lett. 2005, 7, 2551–2558.
- (39) Fournier, D.; Hoogenboom, R.; Schubert, U. S. Chem. Soc. Rev. 2007, 36, 1369–1380.
- (40) Diaz, D. D.; Punna, S.; Holzer, P.; Mc Pherson, A. K.; Fokin, V. V. J. Polym. Sci., Part A: Polym. Chem. 2004, 42, 4392–4398.
- (41) Opsteen, J. A.; Van Hest, J. C. M. Chem. Commun. 2005, 1, 57-60.
- (42) Ossipov, D. A.; Hilborn, J. Macromolecules 2006, 39, 1709-1722.
- (43) Aucagne, V.; Leigh, D. A. Org. Lett. 2005, 8, 4505-4509.
- (44) Malkoch, M.; Vestberg, R.; Gupta, N.; Mespouille, L.; Dubois, P.; Mason, A. F.; Hedrick, J. L.; Liao, Q.; Frank, C. W.; Kingsbury, K.; Hawker, C. J. Chem. Commun. 2006, 2774–2777.
- (45) Diaz, D. D.; Rajapogopal, K.; Strable, E.; Schneider, J.; Finn, M. G. J. Am. Chem. Soc. 2006, 128, 6056–6071.
  (46) Yuanqin, Z.; Yangen, H.; Wei-Dong, M.; Hongqi, Li.; Feng-Ling,
- (46) Yuanqin, Z.; Yangen, H.; Wei-Dong, M.; Hongqi, Li.; Feng-Ling, Q. Polymer 2006, 47, 6272–6283.
- (47) Baut, N. L.; Diaz, D. D.; Punna, S.; Finn, M. G.; Brown, H. R. Polymer 2007, 48, 239–243.
- (48) Liu, Y.; Diaz, D. D.; Accurso, A.; Sharpless, K. B.; Fokin, V. V.; Finn, M. G. J. Polym. Sci., Part A: Polym. Chem. 2007, 45, 5182– 5188.
- (49) Qin, A.; Jim, C. K. W.; Lu, W.; Lam, J. W. Y.; Haussler, M.; Dong., Y.; Sung, H. H. Y.; Williams, I. D.; Wong, G. K. L.; Tang, B. Z. *Macromolecules* **2007**, *40*, 2308–2322.
- (50) Binauld, S.; Boisson, F.; Hamaide, T.; Pascault, J. P.; Drockenmuller, E.; Fleury, E. J. Polym. Sci., Part A: Polym. Chem. 2008, 46, 5506– 5517.
- (51) Hung, M.; Ameduri, B.; Soules, A.; Boutevin, B. (Assigned to Dupont Performance Elastomers), Provisional Patent DWS 172 2009.
- (52) (a) Cummins, D.; Duxbury, C. J.; Quaedflieg, P. J. L. M.; Magusin, P. C. M. M.; Koning, C. E.; Heise, A. Soft Matter 2009, 5, 804–811.
  (b) Duxbury, C. J.; Cummins, D.; Heise, A. J. Polym. Sci., Part A: Polym. Chem. 2009, 47, 3795–3802.
- (53) (a) Hay, A. S. *Polym. Lett.* **1970**, *8*, 97–101. (b) Hay, A. S. US Patent 3,594,175, **1971**. (c) Hay, A. S.; Bolon, D. A.; Leimer, K. R.; Clark, R. F. *J. Polym. Sci., Polym. Lett.* **1970**, *8*, 97–102.
- (54) Patterson, M. L.; Weaver, M. J. J. Phys. Chem. 1985, 89, 5051– 5057.
- (55) Manseri, A.; Ameduri, B.; Boutevin, B.; Kotora, M.; Hajek, M.; Caporiccio, G. J. Fluorine Chem. 1995, 73, 151–158.
- (56) Malik, A.; Tzeng, D.; Tcheng, P.; Baum, K. J. Org. Chem. 1991, 56, 3043–3044.

- (57) (a) Lutz, J. F.; Borner, H. G.; Weichenhan, K. Macromol. Rapid Commun. 2005, 26, 514–518. (b) Lutz, J. F. Angew. Chem., Int. Ed. 2007, 46, 1018–1025.
- (58) Mayot, E.; Gérardin-Charbonnier, C.; Selve, C. J. Fluorine Chem. 2005, 126, 715–720.
- (59) Pergolese, B.; Muniz-Miranda, M.; Bigotto, A. Vib. Spectrosc. 2008, 48, 202–205.
- (60) Gan, H.; Liu, H.; Li, Y.; Zhao, Q.; Li, Y.; Wang, S.; Jiu, T.; Wang, N.; He, X.; Yu, D.; Zhu, D. J. Am. Chem. Soc. 2005, 127, 12452– 12453.
- (61) Jahnke, E.; Lieberwirth, I.; Severin, N.; Rabe, J. P.; Frauenrath, H. Angew. Chem. 2006, 118, 5510. Angew. Chem., Int. Ed. 2006, 45, 5383–5388.
- (62) (a) Karangu, N. T.; Rezac, M. E.; Beckham, H. W. *Chem. Mater.* 1998, *10*, 567–572. (b) Karangu, N. T.; Girardeau, T. E.; Sturgill, G. K.; Rezac, M. E.; Beckham, H. W. *Polymer* 2001, *42*, 2031– 2037.
- (63) Badarau, C.; Wang, Z. Y. Macromolecules 2004, 37, 147-153.

- (64) Rezac, M. E.; Sorensen, E. T.; Beckham, H. W. J. Membr. Sci. 1997, 136, 249–252.
- (65) Miller, T. M.; Knowck, E. W.; Baird, T.; Hale, A. Chem. Mater. 1994, 6, 1569–1572.
- (66) Beckham, H. W.; Rubner, M. F. Macromolecules 1993, 26, 5192– 5197.
- (67) Wiley, R. H.; Smith, N. R.; Jonhson, D. M.; Moffat, J. J. Am. Chem. Soc. 1954, 76, 4933–4938.
- (68) Bloor, D.; Chance, R. R. Polydiacetylenes: Synthesis, Structure, and Electronic Properties; Martinus Nijhoff: Dordrecht, 1985.
- (69) Hans, B.; Ralph, D.; Sitki, A. J. Am. Chem. Soc. 1983, 105, 7681– 7685.
- (70) Gaur, B.; Lochab, B.; Choudhary, V.; Varna, I. K. J. Therm. Anal. Calorim. 2003, 71, 467–479.
- (71) Ghassemi, H.; Mc Grath, J. E.; Zawodzinski, T. A. Polymer 2006, 47, 4132–4139.
- (72) Xue, L.; Wan, L.; Hu, Y.; Shen, X.; Huang, F. *Thermochim. Acta* 2006, 448, 147–153.