# Catalysis Science & Technology

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: F. Ferretti, F. Scharnagl, A. Dallanese, R. Jackstell, S. Dastgir and M. Beller, *Catal. Sci. Technol.*, 2019, DOI: 10.1039/C9CY00951E.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the **author guidelines**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the ethical guidelines, outlined in our <u>author and reviewer resource centre</u>, still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/catalysis

# ARTICLE

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

# Additive-Free Cobalt-Catalysed Hydrogenation of Carbonates to Methanol and Alcohols

Francesco Ferretti,<sup>a,b</sup> Florian Korbinian Scharnagl,<sup>a</sup> Anna Dall'Anese,<sup>a,c</sup> Ralf Jackstell<sup>a</sup>, Sarim Dastgir,<sup>d</sup> and Matthias Beller<sup>a</sup>\*

Reduction of various organic carbonates to methanol and alcohols can be achieved in the presence of a molecularlydefined homogeneous cobalt catalyst. Specifically, the use of Co(BF<sub>4</sub>)<sub>2</sub> in combination with either commercial or tailormade tridentate phoshine ligands allows for additive-free hydrogenations of carbonates. Optimal results are obtained at relatively mild conditions (120°C, 50 bar hydrogen pressure) in the presence of xylyl-Triphos **L4**.

## Introductions

Published on 13 June 2019. Downloaded on 6/14/2019 6:05:45 AM

The catalytic hydrogenation of carbon dioxide to methanol is of general interest in the context of the so-called "Methanol Economy". This concept comprises the capture of carbon dioxide from the atmosphere and its conversion to methanol or dimethyl ether, using dihydrogen as pointed out originally by Asinger<sup>1</sup> and Olah<sup>2, 3</sup>. Although most efforts focused on heterogeneous catalysts, also the development of suitable molecularly-defined catalysts is interesting due to the potentially higher activity. Thus in recent years, notable contributions in this area have been made by the groups of Milstein,<sup>4</sup> Klankermayer and Leitner,<sup>5-7</sup> Olah and Prakash,<sup>8-13</sup> Sanford,14, 15 Himeda and Laurenczy,16 Wass,17 Martins and Pombeiro,<sup>18</sup> as well as our group.<sup>19, 20</sup> So far, a rutheniumbased PNP pincer complex constitutes the most productive homogeneous system with a reported turnover number (TON) of 9900, albeit after 10 days.<sup>12</sup> An alternative approach to the direct hydrogenation of carbon dioxide makes use of cyclic and/or acyclic organic carbonates. The former derivatives can be easily synthesised from carbon dioxide and epoxides, as already done on industrial scale in the so-called OMEGA process by Shell. The latter carbonates are mainly obtained from CO<sub>2</sub> by indirect methods (i.e alcoholysis of other carbon dioxide derivatives such as urea or cyclic carbonates) nowadays, but can also be directly prepared from CO<sub>2</sub> and alcohols. <sup>21-23</sup> Subsequent hydrogenation leads to methanol and the corresponding alcohols.<sup>24</sup> This indirect strategy for CO<sub>2</sub> reduction was first demonstrated by Milstein in 2011, who reported the selective hydrogenation of carbonates,

carbamates and formates to methanol using different ruthenium-PNN-pincer complexes.<sup>25-27</sup> Later on, the use of ruthenium-based NHC-pincer systems has been described.28, 29 The groups of Leitner and Klankermayer extensively studied 1,1,1-[Ru(Triphos)(TMM)] (Triphos tris(diphenylphosphinomethyl)ethane and TMM trimethylene methane) in hydrogenations of carboxylic and carbonic acid derivatives, including cyclic and acyclic carbonates in the presence or the absence of the additive HNTf<sub>2</sub>.<sup>30</sup> So far, the most productive catalyst for this reaction has been reported by the group of Kuiling Ding. By using the commercial ruthenium-MACHO pincer complex, they achieved catalyst TONs up to 87000 for hydrogenation cyclic carbonates, which is about one order of magnitude higher compared to the direct conversion of carbon dioxide to methanol, underlining the possible advantage of this indirect CO<sub>2</sub> reduction route.<sup>31</sup> Apart from expensive precious metal complexes, the first non-noble metal catalysts for this transformation were reported only very recently. In 2018, the groups of Leitner,<sup>32</sup> Rueping<sup>33</sup> and Milstein<sup>34</sup> at the same time reported manganese pincer complexes for the hydrogenation of organic carbonates under basic conditions.



Scheme 1: Overview of selected reported homogeneous systems for the hydrogenation of organic carbonates to the corresponding alcohols.

<sup>&</sup>lt;sup>a.</sup> Leibniz-Institut für Katalyse e.V. an der Universität Rostock, Albert-Einstein-Straße 29a, 18059 Rostock, Germany

<sup>&</sup>lt;sup>b.</sup> Dipartimento di Chimica, Università degli Studi di Milano, Via C. Golgi 19, 20133 Milano, Italy

<sup>&</sup>lt;sup>c</sup> Dipartimento di Scienze Chimiche e Farmaceutiche, Università di Trieste, Via Licio Giorgieri 1, 34127 Trieste, Italy

<sup>&</sup>lt;sup>d</sup> Qatar Environment and Energy Research Institute (QEERI), Hamad bin Khalifa University (HBKU), Qatar Foundation, Doha, Qatar

Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

### Journal Name

Modifying a system based on the combination of cobalt and Triphos, initially reported by Elsevier and de Bruin for the reduction of carboxylic acid, <sup>35</sup> our group succeeded in the direct hydrogenation of carbon dioxide with a homogeneous cobalt catalyst.<sup>19</sup> Later on, improved results have been obtained by us,<sup>20</sup> as well as by Klankermayer and Schieweck.<sup>7</sup> To the best of our knowledge, the applicability of such complexes for reduction of organic carbonates has not been reported yet. In this context, herein we describe the efficient hydrogenation of cyclic and acyclic carbonates in 2,2,2trifluoroethanol (TFE) in the presence of Co(BF<sub>4</sub>)<sub>2</sub>·6H<sub>2</sub>O and a modified Triphos ligand.

# **Results and Discussion**

ARTICLE

At the beginning of our investigations, different cobalt precursors in the presence of the ligand Triphos were tested for the hydrogenation of the model substrate diethyl carbonate at 120 °C and 50 bar  $\rm H_2$  (see

Table 1). Unfortunately, no active catalyst could be generated in the presence of coordinating anions such as halides (entries 1 and 2) acetyl acetonate (entries 3 and 4), carbonate and acetate (entries 6 and 7). Also the use of the cobalt hexafluoroacetylacetone did not show any appreciable yield of MeOH (entry 5). Finally, we found that  $Co(NTf_2)_2$  and Co(BF<sub>4</sub>)<sub>2</sub>·6H<sub>2</sub>O are both suitable for the hydrogenation of carbonates (entries 8 and 9), even at reduced catalyst loadings of 2 mol% (entries 10 and 11). Co(NTf<sub>2</sub>)<sub>2</sub> afforded the highest conversions but a lower selectivity than Co(BF<sub>4</sub>)<sub>2</sub>. Although the use of Co(NTf<sub>2</sub>)<sub>2</sub> gave good activities for CO<sub>2</sub> reduction,<sup>20</sup> here the low yield of alcohols is ascribed to the decomposition of the triflimide-anion which reacted with the substrate. In fact, we observed by GC-MS the formation of several unidentified by-products containing fragments derived both from diethyl carbonate and the NTf<sub>2</sub>-anion.

Table 1: Testing different cobalt precursors for the hydrogenation of diethyl carbonate.

	+ H.	Metal salt (5 mol%) L1 (6 mol%)	_	MaOH + 2E	011
1 mmol	50 bar	THF (2 mL) 120°C, 18 h	-	Meon + 2 El	2 EIOH

Entry	Co Precursor	Conversion [%]	Yield EtOH [%]	Yield MeOH [%]
1	CoCl <sub>2</sub>	6	<1	<1
2	CoF <sub>2</sub>	2	<1	<1
3	Co(acac) <sub>2</sub>	4	<1	<1
4	Co(acac) <sub>3</sub>	4	<1	<1
5	Co(acac <sup>F</sup> ) <sub>2</sub>	2	<1	<1
6	$CoCO_3 \cdot 0.33 \ H_2O$	1	<1	<1
7	Co(OAc) <sub>2</sub>	3	<1	<1
8	Co(NTf <sub>2</sub> ) <sub>2</sub>	60	37	13
9	Co(BF <sub>4</sub> ) <sub>2</sub> ·6H <sub>2</sub> O	36	31	25
10 <sup>a</sup>	Co(NTf <sub>2</sub> ) <sub>2</sub>	44	36	8
11ª	Co(BF <sub>4</sub> ) <sub>2</sub> ·6H <sub>2</sub> O	24	22	16

After identifying an active catalyst system, we tried to improve the comparably low activity investigating different ligands in the presence of cobalt tetrafluoroborate hexahydrate. Here, a variety of bidentate (L20 and L21), tridentate (L1 – L14) and

tetradentate ligands (**L15** – **L19**) was tried. Similar to Cocatalysed hydrogenation reactions of carboxylic3compounds, also in the case of carbonates solely ligands with the Triphos backbone were suitable. All the other ligands tested gave only traces of methanol and ethanol.

Table 2: Hydrogenation of diethyl carbonate: Variation of ligands in combination with  $Co(BF_4)_2$ - $6H_2O$ .



Entry	Ligand	Conversion [%]	Yield (EtOH) [%]	Yield (MeOH) [%]
1	L1	24	22	16
2	L2	37	32	26
3	L3	45	37	32
4	L4	57	48	42
5	L5	30	27	22
6	L6	4	<1	0
7	L7	4	<1	<1
8	L8	19	<1	<1
9	L9	29	<1	<1
10	L10	32	1	<1
11	L11	17	<1	0
12	L12	6	<1	<1
13	L13	5	1	<1
14	L14	4	<1	<1
15	L15	6	<1	<1
16	L16	2	<1	<1
17	L17	4	<1	0
18	L18	3	<1	0
19	L19	11	<1	0
20	L20	6	<1	0
21	L21	3	<1	<1
22	no ligand	4	~1	~1

General conditions: 1.0 mmol diethyl carbonate, 2 mol%  $Co(BF_4)_2$ · $6H_2O$ , 2.4 mol% ligand, 2 mL THF, 120 °C, 50 bar H<sub>2</sub>, 18 h. Conversions and yields were calculated *via* GC using hexadecane as internal standard.

Among the Triphos-type ligands, the xylyl-Triphos L4 revealed the highest productivity, followed by anisyl- (L3) and p-tolyl-Triphos (L2). The dimethylamino-substituted Triphos L5 showed a slightly better productivity than L1. Thus, the substitution of the phenyl ring of Triphos with electrondonating groups seems to be beneficial for the system activity. However, the results are difficult to rationalize only on the

Published on 13 June 2019. Downloaded on 6/14/2019 6:05:45 AM

Published on 13 June 2019. Downloaded on 6/14/2019 6:05:45 AM

#### Journal Name

base of the basicity of the phosphorus. The catalytic behaviour can be better explained taking into account the steric properties of the ligands. Indeed, Leitner and Klankermayer recently showed the benefit of using sterically hindered ligands by comparing the activity of L1, L2 and L4 in the ruthenium/triphos-catalysed hydrogenation of methyl benzoate and lactams. The increased activity in the order L4 > L2 > L1 is ascribed to the suppression of inactive hydride bridged ruthenium dimers formation.<sup>36</sup> The same trend was not noticed when cobalt was used instead of ruthenium for either the reduction of CO27, 20 or reductive transformation of carboxylic acids,37 suggesting a negligible role of dimers in catalyst deactivation. On the other hand,  $[(Triphos)_2Co_2(\mu-H_3)]^+$ was found inactive, in the absence of acid co-catalysts, for the synthesis of dimethoxymethane and methyl formate from CO2.7 Considering the absence of additives in the present system, the prevention of dimer formation is a possible explanation for the order of activity of the ligands.



Scheme 2: Hydrogenation of diethyl carbonate: Solvent screening.

Reaction conditions: 1.0 mmol diethyl carbonate, 2 mol% Co(BF<sub>4</sub>)<sub>2</sub>·6H<sub>2</sub>O, 2.4 mol% L1 or L4, 2 mL solvent, 120 °C, 50 bar H<sub>2</sub>, 18 h. Conversions and yields were calculated *via* GC using hexadecane as internal standard. The ethanol yield could not be determined in the case of isopropanol as solvent.

Next, the performance of the in situ-generated catalyst with commercial ligand L1 has been investigated in different solvents (Scheme 2). By far the best results were obtained with 2,2,2-trifluoroethanol (TFE) leading to 71% yield of both methanol and ethanol (conversion: 75%). Quantitative conversion and GC-yields for both alcohols have been achieved by combining the best solvent with the best ligand, L4. Previously, such beneficial effect of fluorinated solvents has been observed by Elsevier,<sup>38</sup> as well as by Klankermayer.<sup>7</sup> Interestingly, TFE gave significantly better results compared to the related solvent 1,1,1,3,3,3-hexafluoro isopropanol (HFIP). THF showed the best productivity as a non-fluorinated solvent. The sensitivity of the system towards water was shown by combining THF with 5 µL (0.28 mmol) of distilled water. Adding this small amount dropped the conversion from 24% to 10% and the yield of ethanol from 22% to 4%. Methanol formation could not be observed anymore. All other solvents resulted in low conversions, yields and selectivities. With an optimised system in hand, the hydrogenation of different organic carbonates was investigated in more detail (Table 3).

 
 Table 3: Hydrogenation of carbonates to the corresponding alcohols: Substrate scope View Article Ohline

 DOI: 10.1039/C9CY00951E

	Co(BF <sub>4</sub> ) <sub>2</sub> ·6H <sub>2</sub> O (2 mol%) L4 (2.4 mol%) 2.0 mL TFE 50 bar H-, 120 °C, 18 h		MeOH + ROH + R'OH		
	1-15	, -			
Entry	Substrate	Conv. [%]	MeOH [%]	ROH [%]	R'OH [%]
1		>99	85	-	-
2		>99	98	>99	-
3		92	96	73	-
4		>99	>99	>99	-
5		94	84	n.d.ª	89
6		>99	11	88	-
7	~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	>99	94	54	-
8		>99	92	97	91
9	F <sub>3</sub> C <sup>O</sup> O <sup>C</sup> F <sub>3</sub>	>99	80	n.d.ª	-
10	F = F = F = F $F = F = F$ $F = F = F$ $F =$	53	5	43	-
11		>99	85	75	-
12		>99	96	90	-

Reaction conditions: 1.0 mmol diethyl carbonate, 2 mol%  $Co(BF_4)_2$ · $GH_2O$ , 2.4 mol% L4, 2 mL TFE, 120 °C, 50 bar H<sub>2</sub>, 18 h. Conversions and yields were calculated *via* GC using hexadecane as internal standard. When R = R', yields are reported as 2 ROH. <sup>a</sup> The peak of ROH overlaps with the one of TFE in the gas-chromatogram.

Dimethyl carbonate **1** gave three equivalents of methanol in a yield of 85% at full conversion. Almost quantitative yields of both alcohols have been achieved for di-*n*-butyl carbonate **2**. Also the aromatic carbonate **3** was effectively converted to methanol and phenol. The asymmetric aromatic/aliphatic carbonates **4** and **5** yielded the three corresponding alcohols. For dibenzyl carbonate **6**, a low methanol yield (11%) was

#### ARTICLE

observed, even though the conversion and the yield of benzylic alcohol both have been high (<99%/88%). A similar behaviour was found for the perfluorinated carbonate 10, although at a lower conversion. It is worth noticing that the used cobalt source contains six equivalents of water and both benzyl alcohol and pentafluorophenol are good leaving groups. Thus, for 6 and 10 hydrolysis of the substrates would lead to formation of alcohol, carbon dioxide. This, at least in part, accounts for the discrepancy of methanol and alcohol yields. The asymmetric carbonate 8, which bears one hexafluorophenol unit yielded in 92% of methanol, along with 97% of 9-fluorenyl methanol and 91% of hexafluorophenol. Also the fluorinated substrate 9 was converted to methanol in high yield. Noteworthy, also the cyclic carbonates 12 and 13 were readily transformed to the diols and methanol. These carbonates are of particular interest vide supra, as they are commercially produced from carbon dioxide and epoxides or oxetanes.39



Scheme 3: Hydrogenation of the potential intermediates ethyl formate and formaldehyde.

As the hydrogenation of diethyl carbonate potentially occurs stepwise *via* ethyl formate and/or formaldehyde, these compounds have been investigated in separate hydrogenation experiments (Scheme 3). Both, ethyl formate and paraformaldehyde were completely hydrogenated, giving methanol in 86% and 88%, respectively, and ethanol in >99%. Therefore, although only traces of ethyl formate were detected by GC for the model substrate, we cannot exclude that these compounds indeed are intermediates in the hydrogenation of diethyl carbonate.

### Conclusions

In conclusion, we investigated the homogeneous cobaltcatalysed hydrogenation of organic carbonates for the first time. The combination of  $Co(BF_4)_2 \cdot 6H_2O$  with a Triphos-derived ligand L4 resulted in an active catalytic system suitable for reduction of both cyclic and acyclic carbonates. At relatively mild conditions, good to very good yields of methanol and the corresponding alcohols have been obtained using the solvent TFE.

## **Experimental Section**

View Article Online DOI: 10.1039/C9CY00951E

Journal Name

Page 4 of 6

# Materials

All chemicals were purchased from commercial sources and were used as received without additional purification, if not stated otherwise. Molecular hydrogen was purchased from Linde. All experiments were carried out under argon atmosphere by using standard Schlenk-techniques, unless stated otherwise. Solvents were dried and distilled or directly used from a solvent purification system (MBraun). THF was stored over molecular sieves 3 Å. Diethyl carbonate was distilled prior to use. The ligands L2 - L6,<sup>37</sup> L7 - L9,<sup>40</sup> L11,<sup>40</sup> L15,<sup>41</sup> L16,<sup>42</sup> L17,<sup>43</sup> L19,<sup>44</sup> and L20<sup>45</sup> have been synthesised according to literature-reported procedures.

Catalytic experiments were conducted in 4 mL screw cap vials, closed with a polytetrafluoroethylene (PTFE)/white rubber septum (Wheaton 13 mm Septa) and phenolic cap and connected with atmosphere by a needle, inside a 300 mL Parr autoclave and stirred with a magnetic stirring bar. GC measurements were carried out on a 7890A GC-System with HP-5 column (polydimethylsiloxane with 5% phenyl groups, length 30 m, i.d. 0.32 mm, film 0.25  $\mu$ m) and with a FID coupled with a 7693 autosampler from Agilent Technologies. Argon was used as carrier gas. GC-analyses for methanol quantification were performed on an Agilent HP-6890 chromatograph with a FID detector and an Agilent HP Ultra 1 column (19091A-105, 50 m, 0.20mm i.d., 0.33 mm film thickness, 100% dimethylpolysiloxane) using argon as carrier gas.

In a typical catalytic experiment, Co(BF<sub>4</sub>)<sub>2</sub>·6H<sub>2</sub>O (6.81 mg, 2.0 mmol) and ligand (2.4 mmol) were fast weighed in the air and transferred into a 4 mL glass vial. If used, solid substrates were also weighed in the air and added into the vial. The vial was subsequently set under argon. 2.0 mL solvent were added and the mixture stirred for 5-10 min. Then, liquid substrates were added and the vials were placed in a metal plate inside a 300 mL autoclave. After closing, the reactor was pressurised with hydrogen (about 20 bar), which was released again. This procedure was carried out three times, after which 50 bar H<sub>2</sub> were introduced. The autoclave was then heated inside an aluminium block to 120 °C for 18 h. Afterwards the reaction was quenched with an ice-bath and the reactor vented. Hexadecane (30 µL) was added to the reaction as internal standard for GC, along with 2 mL THF. After proper mixing, GC was measured of the sample.

## **Conflicts of interest**

There are no conflicts to declare.

#### Acknowledgements

Financial support from Qatar National Research Fund, a member of Qatar foundation, Qatar (*Grant numbers NPRP9-212-1-042, & NPRP8-235-1-055*), BMBF and the State of Mecklenburg-Vorpommern, Germany is gratefully acknowledged. We thank the analytical department of LIKAT for the support and Prof. Uwe Rosenthal for providing **L14**.

#### **Journal Name**

#### References

1. F. Asinger, *Methanol, Chemie- und Energierohstoff*, Akademie-Verlag, Berlin, 1987.

2. G. A. Olah, A. Goeppert and G. K. S. Prakash, *Beyond Oil and Gas: The Methanol Economy*, Wiley-VCH, Weinheim, 2nd edn., 2009.

- 3. G. A. Olah, Angew. Chem. Int. Ed., 2013, 52, 104-107.
- 4. J. R. Khusnutdinova, J. A. Garg and D. Milstein, *ACS Catal.*, 2015, **5**, 2416-2422.

5. S. Wesselbaum, T. vom Stein, J. Klankermayer and W. Leitner, *Angew. Chem. Int. Ed.*, 2012, **51**, 7499-7502.

6. S. Wesselbaum, V. Moha, M. Meuresch, S. Brosinski, K. M. Thenert, J. Kothe, T. vom Stein, U. Englert, M. Hölscher, J. Klankermayer and W. Leitner, *Chem. Sci.*, 2015, **6**, 693-704.

7. B. G. Schieweck and J. Klankermayer, *Angew. Chem. Int. Ed.*, 2017, **56**, 10854-10857.

- 8. J. Kothandaraman, A. Goeppert, M. Czaun, G. A. Olah and G. K. S. Prakash, *J. Am. Chem. Soc.*, 2016, **138**, 778-781.
- 9. S. Kar, A. Goeppert, J. Kothandaraman and G. K. S. Prakash, *ACS Catal.*, 2017, **7**, 6347-6351.

10. S. Kar, R. Sen, A. Goeppert and G. K. S. Prakash, *J. Am. Chem. Soc.*, 2018, **140**, 1580-1583.

- 11. S. Kar, A. Goeppert, V. Galvan, R. Chowdhury, J. Olah and G. K. S. Prakash, *J. Am. Chem. Soc.*, 2018, **140**, 16873-16876.
- 12. S. Kar, R. Sen, J. Kothandaraman, A. Goeppert, R. Chowdhury, S. B. Munoz, R. Haiges and G. K. S. Prakash, *J. Am. Chem. Soc.*, 2019, **141**, 3160-3170.
- 13. S. Kar, A. Goeppert and S. G. Prakash, *ChemSusChem*, 2019, DOI: 10.1002/cssc.201900324.
- 14. C. A. Huff and M. S. Sanford, J. Am. Chem. Soc., 2011, **133**, 18122-18125.
- 15. N. M. Rezayee, C. A. Huff and M. S. Sanford, *J. Am. Chem. Soc.*, 2015, **137**, 1028-1031.

16. K. Sordakis, A. Tsurusaki, M. Iguchi, H. Kawanami, Y. Himeda and G. Laurenczy, *Chem. Eur. J.*, 2016, **22**, 15605-15608.

17. D. Wass and M. Everett, *Chem. Commun.*, 2017, **53**, 9502-9504.

18. A. P. C. Ribeiro, L. M. D. R. S. Martins and A. J. L. Pombeiro, *Green Chem.*, 2017, **19**, 4811-4815.

19. J. Schneidewind, R. Adam, W. Baumann, R. Jackstell and M. Beller, *Angew. Chem. Int. Ed.*, 2017, **56**, 1890-1893.

20. F. K. Scharnagl, M. F. Hertrich, G. Neitzel, R. Jackstell and M. Beller, *Adv. Synth. Catal.*, 2018, **361**, 374-379.

21. S. Dabral and T. Schaub, Adv. Synth. Catal., 2019, **361**, 223-246.

22. M. Aresta, A. Dibenedetto and E. Quaranta, *J. Catal.*, 2016, **343**, 2-45.

23. H.-Z. Tan, Z.-Q. Wang, Z.-N. Xu, J. Sun, Y.-P. Xu, Q.-S. Chen, Y. Chen and G.-C. Guo, *Catal. Today*, 2018, **316**, 2-12.

24. P. H. Dixneuf, Nat. Chem., 2011, 3, 578.

25. E. Balaraman, C. Gunanathan, J. Zhang, L. J. W. Shimon and D. Milstein, *Nat. Chem.*, 2011, **3**, 609-614.

26. F. Hasanayn, A. Baroudi, A. A. Bengali and A. S. Goldman, Organometallics, 2013, **32**, 6969-6985.

27. Y. Li, K. Junge and M. Beller, *ChemCatChem*, 2013, **5**, 1072-1074.

 28. X. Wu, L. Ji, Y. Ji, E. H. M. Elageed and Gvie Gancie Catal.

 Commun., 2016, 85, 57-60.

29. J. Chen, H. Zhu, J. Chen, Z.-G. Le and T. Tu, *Chemistry – An Asian Journal*, 2017, **12**, 2809-2812.

30. T. vom Stein, M. Meuresch, D. Limper, M. Schmitz, M. Hölscher, J. Coetzee, D. J. Cole-Hamilton, J. Klankermayer and W. Leitner, *J. Am. Chem. Soc.*, 2014, **136**, 13217-13225.

31. Z. Han, L. Rong, J. Wu, L. Zhang, Z. Wang and K. Ding, *Angew. Chem. Int. Ed.*, 2012, **51**, 13041-13045.

32. A. Kaithal, M. Hölscher and W. Leitner, *Angew. Chem.*, 2018, **130**, 13637-13641.

33. V. Zubar, Y. Lebedev, L. M. Azofra, L. Cavallo, O. El-Sepelgy and M. Rueping, *Angew. Chem. Int. Ed.*, 2018, **57**, 13439-13443.

34. A. Kumar, T. Janes, N. A. Espinosa-Jalapa and D. Milstein, Angew. Chem. Int. Ed., 2018, 57, 12076-12080.

35. T. J. Korstanje, J. Ivar van der Vlugt, C. J. Elsevier and B. de Bruin, *Science*, 2015, **350**, 298-302.

36. M. Meuresch, S. Westhues, W. Leitner and J. Klankermayer, Angew. Chem. Int. Ed., 2016, 55, 1392-1395.

37. W. Liu, B. Sahoo, A. Spannenberg, K. Junge and M. Beller, Angew. Chem. Int. Ed., 2018, **57**, 11673-11677.

38. H. T. Teunissen and C. J. Elsevier, *Chem. Commun.*, 1998, 1367-1368.

39. H. Büttner, L. Longwitz, J. Steinbauer, C. Wulf and T. Werner, *Top. Curr. Chem.*, 2017, **375**, 50.

40. A. Dutta Chowdhury, R. Jackstell and M. Beller, ChemCatChem, 2014, 6, 3360-3365.

41. A. Phanopoulos, N. J. Brown, A. J. P. White, N. J. Long and P. W. Miller, *Inorg. Chem.*, 2014, **53**, 3742-3752.

42. J. Ellermann and K. Dorn, Chem. Ber., 1966, **99**, 653-657.

43. R. Adam, C. B. Bheeter, J. R. Cabrero-Antonino, K. Junge, R. Jackstell and M. Beller, *ChemSusChem*, 2017, **10**, 842-846.

44. C. Ziebart, C. Federsel, P. Anbarasan, R. Jackstell, W. Baumann, A. Spannenberg and M. Beller, *J. Am. Chem. Soc.*, 2012, **134**, 20701-20704.

45. K. Dong, X. Fang, S. Gülak, R. Franke, A. Spannenberg, H. Neumann, R. Jackstell and M. Beller, *Nat. Commun.*, 2017, **8**, 14117.

This journal is © The Royal Society of Chemistry 20xx



122x40mm (300 x 300 DPI)