

Article

Three-dimensional porous architectures based on Mn three-blades paddlewheel metallacryptates

Vittoria Marzaroli, Giulia Spigolon, Giuseppe Lococciolo, Martina Quaretti, Clarissa Salviati, Jeff W. Kampf, Giulia Licini, Luciano Marchio', Vincent L. Pecoraro, and Matteo Tegoni

Cryst. Growth Des., Just Accepted Manuscript • DOI: 10.1021/acs.cgd.8b01921 • Publication Date (Web): 31 Jan 2019 Downloaded from http://pubs.acs.org on February 1, 2019

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036

Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

Three-dimensional porous architectures based on Mn^{II/III} three-blades paddlewheel metallacryptates

Vittoria Marzaroli,^a Giulia Spigolon,^b Giuseppe Lococciolo,^a Martina Quaretti,^a Clarissa Salviati,^a Jeff W. Kampf,^c Giulia Licini,^b Luciano Marchiò,^a Vincent L. Pecoraro^{*c} and Matteo Tegoni^{*a}.

a. Department of Chemistry, Life Sciences, and Environmental Sustainability, Parco Area delle Scienze 11A, 43124 Parma, Italy. Tel. +39 0521 905424; Email: matteo.tegoni@unipr.it

b. Department of Chemical Sciences, University of Padova via Marzolo 1, 35131
 Padova, Italy.

c. Department of Chemistry, University of Michigan, Ann Arbor, MI, 48109-1055, USA. Tel.: +1 734 7631519; Email: vlpec@umich.edu

Abstract

Three metallacryptate supramolecular assemblies have been obtained using salicylhydroxamic acid derivatives (H₃L). The three ligands differ for the residue in *para* position with respect of the hydroxamic function (-H, -NH₂ and –(4-pyridyl)). The core of these supramolecules correspond to the formula $[(Mn^{II})_2(Mn^{III})_9(\mu^3-O)_4(OAc)_3(Shi)_6]^{2+}$ (abbreviated to $Mn_{11}L_6$) in all three compounds. Additional acetate or hydroxide ions, and DMF molecules are coordinated to the Mn^{III} ions. With L³⁻ = Shi³⁻ the Mn₁₁L₆ units assemble into a non-porous structure, where the metallacryptates are linked together through Na^I ions bridging between the units. Conversely, with L³⁻ = ρ -aShi³⁻ (NH₂ group) and ρ -pyShi (4-pyridyl group) the units assemble in parallel chains and into a MOF-like structure, respectively. In both solids, a honeycomb porous architecture was obtained, where infinite channels run along the crystal structure. With ρ -aShi³⁻, Na^I bridging ions and hydrogen bonds, provided by the presence of the amino group, characterize the interactions between the parallel chains of supramolecules. On the other hand with ρ -pyShi³⁻, the peripheral pyridyl groups point away from the metallacryptate units and are

coordinated to available positions on Mn^{III} ions of neighbouring molecules, with formation of a peculiar porous-coordination polymeric architecture.



Figure Channel-like cavities in compound **13**. The surface of the hexagonal channels is represented in green.

Three-dimensional porous architectures based on Mn^{II/III} three-blades paddlewheel metallacryptates *Vittoria Marzaroli,ª Giulia Spigolon,^b Giuseppe Lococciolo,ª† Martina Quaretti,ª Clarissa*

Salviati,^a Jeff W. Kampf,^c Giulia Licini,^b Luciano Marchiò,^a Vincent L. Pecoraro*^c and

Matteo Tegoni*a.

a. Department of Chemistry, Life Sciences, and Environmental Sustainability, Parco

Area delle Scienze 11A, 43124 Parma, Italy. Email: matteo.tegoni@unipr.it

Department of Chemical Sciences, University of Padova, via Marzolo 1, 35131
 Padova, Italy.

c. Department of Chemistry, University of Michigan, Ann Arbor, MI, 48109-1055,

USA. Email: vlpec@umich.edu

Abstract

Three metallacryptate supramolecular assemblies have been obtained using salicylhydroxamic acid derivatives (H₃L). The three ligands differ for the residue in *para* position with respect of the hydroxamic function (-H, -NH₂ and -(4-pyridyl)). The core of these supramolecules correspond to the formula [(Mn^{II})₂(Mn^{III})₉(µ³-O)₄(OAc)₃(Shi)₆]²⁺ (abbreviated to $Mn_{11}L_6$) in all three compounds. Additional acetate or hydroxide ions, and DMF molecules are coordinated to the Mn^{III} ions. With $L^{3-} = Shi^{3-}$ the Mn₁₁L₆ units assemble into a non-porous structure, where the metallacryptates are linked together through Na¹ ions bridging between the units. Conversely, with $L^{3-} = \rho$ -aShi³⁻ (NH₂ group) and p-pyShi³⁻ (4-pyridyl group) the units assemble in parallel chains and into a MOF-like structure, respectively. In both solids, a honeycomb porous architecture was obtained, where infinite channels run along the crystal structure. With p-aShi³⁻, Na¹ bridging ions and hydrogen bonds, provided by the presence of the amino group, characterize the interactions between the parallel chains of supramolecules. On the other hand with ppyShi³⁻, the peripheral pyridyl groups point away from the metallacryptate units and are coordinated to available positions on Mn^{III} ions of neighbouring molecules, with formation of a peculiar porous-coordination polymeric architecture.

Introduction

There is great interest today in developing porous coordination polymers and, in general, large ordered assemblies of metal complexes.^{1–6} These substances are promising materials that may have applications in gas storage, separations of small molecules, catalysis, luminescence and magnetism.⁷ For the construction of such materials, it is sometimes hard to predict the topology of the final architecture and to control the properties of the material. One successful approach for that purpose is constructing a 3D architecture, using pre-assembled polynuclear complexes, that exhibit at the molecular level the desired properties for the final material.^{8,9}

Metallacrowns, the inorganic analogues of crown ethers, provide an opportunity to exploit these strategies for the construction of 3D architectures.^{10–13} These metallamacrocyclic complexes are assembled from metal ions and bridging organic ligands such as hydroxamic acids, and are characterized by the repetition of a cyclic (M-N-O)_n connectivity (Scheme 1a). In metallacrowns, the oxygen atoms of the metallacycle point toward the center of the cavity, into which metal ions (from transition

(d-) to lanthanide (f-) elements) can be encapsulated.^{11,14,15} Closely related to

and metallacryptates.^{16–23} metallacrowns inverse metallacrowns Inverse are metallacrowns share with metallacrowns the cyclic repetition of a (M-N-O)_n connectivity, but the conformation of the metallacyclic ring brings the metals rather than the oxygen to the interior point of the cavity (Scheme 1b).^{16–19} In these constructs, the cavity is, therefore, occupied by anions such as oxide, hydroxide or halogenides, which coordinate to the metal ions. More complex 3D assemblies using the same, or closely similar, (M-N-O)_n repeat can lead to metallacryptates, the inorganic analogues of cryptates. In these molecules, one can often discern interconnected metallacrown or inverse metallacrown motifs and connectivities that form a cage into which cations or anions are trapped (Scheme 1c).²⁰⁻²³



Scheme 1. General schematic representations of the metallacyclic rings of

metallacrowns (a), inverse metallacrowns (b) and inverse metallacryptates (c).

Crystal Growth & Design

We have carried out in the past years an extensive investigation of the functional

properties of metallacrowns.^{11,14,15,24,25} The most promising in terms of their possible applications are their luminescence brightness,²⁶⁻³⁰ their single-molecule magnetic behavior,^{21,31,40–42,32–39} and their selectivity as hosts for both anionic or cationic species.43-51 These are all desirable properties to be incorporated into porous coordination polymers. Because metallacrowns are stable in solution over a wide range of conditions (e.g. pH, presence of competing ligands or metals, different solvents),^{15,45,52} they serve as ideal building blocks for the assembly of 3D- coordination polymers based on polymetallic species.^{11,12,53} Metallacrowns can be preassembled in solution and, therefore, converted into the desired solid state architectures by variation of the conditions of crystallization. This capacity to give rise to coordination polymers has been documented.54-63

Several three-dimensional MC-based architectures have been presented in the literature in the past few years.^{54–63} However, among these only a few were reported to possess real pores and none of them exhibited permanent porosity.^{59,61} We have

recently provided an important advancement in this field by reporting the preparation of

the first three-dimensional coordination polymer based on a MC framework that exhibits permanent porosity.¹⁰ This material was formed by Cu^{II}[12-MC_{Cu,L}-4] units, where the ligand L is a derivative of salicylhydroxamic acid, connected by Cu^{II} ions to form chessboard-like 2D layers that stack one above the other. The channels present in this framework have the capacity of being evacuated at high temperature, and filled with gas molecules with no loss of crystallinity.¹⁰

More recently, efforts have been presented in the literature on making extended solids of materials that may have individual units with SMM and MOF behavior.^{64–68} In view of obtaining these types of functional materials, we decided to move from copper to manganese assemblies. The latter can actually be more promising for revealing interesting magnetic properties as the result of the great single ion paramagnetism and magnetic anisotropy.⁶⁹ In fact, the first documented single molecule magnets (SMMs) were indeed collections of Mn^{III} and Mn^{IV.70,71} Furthermore, several metallacrowns and metallacryptates containing mixed-valence Mn assemblies have been shown to exhibit

Crystal Growth & Design

slow magnetic relaxation that is consistent with SMMs.^{21,22,31,33-36} In this paper we present the synthesis of three salicylhydroximate derivatives (Shi³⁻, Scheme 2) used to prepare self-assembled metallacryptate constructs which are three-fold axial symmetrical. On one hand, with all three ligands (H₃L) the obtained metallacryptate assemblies have general stoichiometry $Mn_{11}L_6$ and they contain both Mn^{\parallel} and Mn^{\parallel} ions. These molecules are the first examples of [2.2.2] metallacryptates, and among the very few metallacryptates isolated to date.²⁰⁻²³ Perhaps more importantly, by rational design of the ligands derivatives the three-fold symmetry of these molecules was fully exploited to obtain of three new 3D frameworks among which two are porous. By X ray structural characterization we demonstrated how a modification of the ligand by one atom on the aromatic ring of Shi³⁻ converts this molecular species into a 3D array allowing us to move from a non-porous molecular packing to honeycomb-like architectures where infinite channels run along the crystal structure.



Scheme 2. Representation of H₃Shi (a) and its two derivatives derivatives H₃*p*-aShi (b,

5) and H₃*p*-pyShi (c, **10**).

Experimental

Materials and methods

Chemicals were purchased from Sigma-Aldrich and TCI Chemicals, and used without further purification. Reactions performed under an inert atmosphere were carried out using Schlenk glassware using nitrogen as the inert gas. Flash column chromatography was performed using silica gel (230-400 mesh). Melting points were recorded by Stuart Melting Point SMP11. ¹H and ¹³C{¹H} NMR spectra were recorded on Bruker Avance-DPX-200, Bruker Avance 400, Varian MR400 and Varian Vnmrs500 spectrometers using standard pulse sequences. Chemical shifts were referenced to the residual

Crystal Growth & Design

3
4
5
6
7
/ 0
8
9
10
11
12
13
14
15
16
17
17
10
19
20
21
22
23
24
25
26
20
27
28
29
30
31
32
33
34
35
36
20
3/
38
39
40
41
42
43
44
45
16
40 47
4/
48
49
50
51
52
53
54
55
55
50
5/
58
59
60

signals of the solvents. The ¹³C{¹H} NMR spectra (50 MHz) were referenced to the CDCl₃ peak. The following abbreviations are used in reporting the multiplicity for NMR resonances: s=single, d=doublet, dd= doublet of doublet, t= triplet, and m=multiplet. FT-IR were recorded with a Perkin-Elmer FTIR 1650 or with a Perkin-Elmer FTIR Nexus spectrometer using a Smart Orbit HATR accessory equipped with a diamond crystal. Electrospray ionization mass spectra (ESI-MS) of compounds 2-5 were collected on a Micromass LCT TOF electrospray ionization mass spectrometer, using a capillary voltage of 3500 and a desolvation temperature of 350 °C. Samples (40 µM) were injected through direct infusion using a syringe pump at 11 µL/min, and the spectra recorded in full scan analysis mode in the range 100-2000 m/z. High resolution electrospray ionization mass spectrometry HRMS (ESI-QTOF) analyses of compounds 6-10 were performed with a Waters Xevo G2-S QTof in positive and negative mode (mixture of water/acetonitrile 50:50 with 0.1% of formic acid as mobile phase) with the following settings: solvent flow= 50 µL/min , dry gas = 800 L/h, dry Temp = 350 °C, detector potential = 2 KV. MS peak intensity for each analysis is reported as monoisotopic mass and the data were processed with Mass-Lynx 4.1.

X-ray crystallography. Single crystal X ray diffraction data of 11 were collected at 293 K on a Bruker Smart APEXII CCD diffractometer (Mo Ka; I = 0.71073 Å). Intensities were integrated from several series of exposure frames that covered the sphere of reciprocal space.⁷² Single crystal X ray diffraction data of metallacryptates 12 and 13 were collected with a Rigaku AFC10K Saturn 944+ CCD-based X-ray diffractometer equipped with a low temperature device and Micromax-007HF Cu-target micro-focus rotating anode (λ = 1.54187 A) operated at 1.2 kW power (40 kV, 30 mA). Rigaku d*trek images were exported to CrysAlisPro for processing.73 Absorption correction was applied using the program SADABS.74 The data collection for **12bis** was performed at the X-ray diffraction beamline (XRD1) of the Elettra Synchrotron, Trieste (Italy).⁷⁵ Datasets were collected at 100 K through the rotating crystal method. Data were acquired using a monochromatic wavelength of 0.700 Å on a Pilatus 2M hybrid-pixel area detector. The collected images were processes with CrysAlisPro.73 The structures of compounds 11-13 were solved by direct methods ShelXT,76 and refined with fullmatrix least squares,⁷⁷ using the Olex2 software package. The structures were analysed with the Mercury 3.10 software package.⁷⁸ Crystallographic data for **11-13** and for **12bis**

Page 13 of 66

Crystal Growth & Design

reported in this paper have been deposited with the Cambridge Crystallographic Data Centre (the deposition CCDC number: 1849184-1849186).

Synthesis of N-t-butyloxycarbonyl-4-aminosalicylic acid (2). 4-Aminosalicylic acid (1, 4.0 g, 0.026 mol) was dissolved in 50 mL of ethanol. Sodium hydroxide (2.1 g, 0.052 mol), dissolved in 20 mL of water, was added. Di-t-butyl dicarbonate (11.4 g, 0.052 mol), dissolved in 40 mL of ethanol, was added dropwise within 1 hour, and the solution stirred overnight. The solvent was removed in vacuo and hydrochloric acid (1 M) was added up to pH = 3. The precipitate was filtered off, washed with water, and dried under reduced pressure at room temperature to obtain a white powder (yield 3.7 g, 93 %). FT-IR (ATR, cm⁻¹) 3361, 2884, 1737, 1621, 1588, 1452, 1298, 1220, 1192, 1138, 1048, 1023, 984, 914, 872, 826, 775, 699, 643, 596, 540, 504, 464; ¹H NMR (400 MHz, δ, DMSO-D₆) 9.71 (1H, s, Ar-NH), 7.64 (1H, d, J = 8.7 Hz, Ar-6H), 7.12 (1H, d, J = 2.1 Hz, Ar-3H), 6.98 (1H, dd, J = 8.8, J = 2.1 Hz, Ar-1H), 1.47 (9H, s, Boc-CH₃); ESI-MS (QTOF, m/z) 276.25 ([M+Na]⁺), 292.21 ([M+K]⁺); Found: C, 56.8; H, 6.2; N, 5.6%. Calcd for C₁₂H₁₅NO₅: C, 56.9; H, 6.0; N, 5.5%.

Synthesis of N- <i>t</i> -butyloxycarbonyl-4-aminosalicyl-O-benzylhydroxamate (3).
Compound 2 (5.00 g, 0.0198 mol) was dissolved in 120 mL of DMF. Triethylamine (5.5
mL, 0.0395 mol), <i>O-</i> benzylhydroxylamine hydrochloride (6.3 g, 0.040 mol), EDC
hydrochloride (4.54 g, 0.0395 mol) and DMAP (0.30 g, 0.0024 mol) were added to the
reaction mixture in this order. The resulting mixture was stirred for 48 hours at room
temperature. DMF was removed under reduced pressure, and the resulting yellowish oil
diluted with ethyl acetate (50 mL). The organic phase was washed with a saturated
NaHCO ₃ solution (3 x 50 mL), brine and then treated with anhydrous Na ₂ SO ₄ . The
solvent was removed in vacuo and the product purified by flash column chromatography
(silica gel, ethyl acetate/hexane 1:1 as the eluent). Pure compound ${f 3}$ was isolated as a
brownish powder (yield 2.74 g, 40 %). ¹ H NMR (400 MHz, δ , DMSO-D ₆) 11.98 (1H, s,
OBz-OH), 11.66 (1H, s, Ar-OH), 9.60 (1H, s, Ar-NH), 7.55 (1H, d, J = 8.7 Hz, Ar-6H),
7.42 (5H, m, OBz-H), 7.13 (1H, s, Ar-3H), 6.92 (1H, d, J = 8.7 Hz, Ar-1H), 4.92 (2H, s,
OBz-CH ₂); ESI-MS (QTOF, <i>m/z</i>) 737.28 ([(M-H) ₂ Na] ⁻); Found: C, 63.4; H, 6.3; N, 7.7%.
Calcd for C ₁₉ H ₂₂ N ₂ O ₅ : C, 63.7; H, 6.2; N, 7.8%.

Crystal Growth & Design

Synthesis of 4-aminosalicyl-O-benzylhydroxamate (4). Compound 3 (2.09 g, 5.83
mmol) was dissolved in a dicholormethane/TFA mixture (1:1 v:v), and the solution
stirred for 2 hours at room temperature. The solvent was removed in vacuo. The
resulting oil was dissolved in 50 mL of ethyl acetate, washed with water (3 x 50 mL),
brine, and treated with anhydrous Na ₂ SO ₄ . The solvent was removed <i>in vacuo</i> , yielding
compound 4 as a brownish powder (yield 1.9 g, 91 %,). FT-IR (ATR, cm ⁻¹) 2859, 2603,
1611, 1543, 1497, 1472, 1430, 1389, 1321, 1255, 1196, 1142, 1109, 1017, 974, 840,
906, 857, 823, 796, 734, 717, 695, 602, 570, 539, 517, 492; ¹ H NMR (400 MHz, $\delta,$
DMSO-D ₆) 7.49 – 7.26 (7H, m, OBz-H + Ar-1H), 6.03 (1H, d, <i>J</i> = 9.7 Hz, Ar-6H), 5.96 (s,
1H, Ar-3H), 5.79 (2H, s, Ar-NH ₂), 4.88 (2H, s, Ar-NH ₂); ESI-MS (QTOF, <i>m/z</i>) 281.22
([M+Na] ⁺), 297.25 ([M+K] ⁺), 539.25 ([M ₂ +Na] ⁺); Elemental analysis found: C, 65.4; H,
5.4; N, 10.6%. Calc for C ₁₄ H ₁₄ N ₂ O ₃ : C, 65.1; H, 5.5; N, 10.8%.

Synthesis of 4-aminosalicylhydroxamic acid (H₃*p*-aShi, 5). Compound 4 (0.120 g, 0.464 mmol) was dissolved in 60 mL of methanol and hydrogenated in the presence of Pd/C (0.018 g, 15% w/w) under H₂ (p_{H2} = 30 psi) for 24 hours. The catalyst was filtered

off from the pale pink solution, the solvent removed *in vacuo*, and pure $H_{3}p$ -aShi (5)

	•	·	. ,
isolated as a dark red powder (yield 0.050 g, 92 %). ¹ H NMR	(400 MHz,	δ, DMSO	-D ₆)
7.32 (1H, d, J = 8.6 Hz, Ar-6H), 6.00 (1H, dd, J = 8.6, $J_{1, 3}$ 2.2 I	Hz, Ar-3H),	5.94 (1H,	d, <i>J</i>
= 2.2 Hz, Ar-3H), 5.71 (2H, s, Ar-NH ₂); ESI-MS (QTOF, <i>m/z</i>) 16	39.06 ([M+F	l]⁺); Found	: C,
50.3; H, 4.9; N, 16.4%. Calcd for C ₇ H ₈ N ₂ O ₃ : C, 50.0; H, 4.8; N,	16.7%.		

Synthesis of methyl 4-iodosalicylate (7). Conc. H₂SO₄ (2.02 mL) were slowly added at room temperature to a solution of 2-hydroxy-4-iodobenzoic acid **6** (4.00 g, 15.15 mmol) in dry methanol (37.2 mL). The reaction mixture was warmed to reflux for 12 hours. After cooling to room temperature the solvent was removed to dryness. The crude product was dissolved in CH₂Cl₂ and washed with a saturated NaHCO₃ aqueous solution and then with brine. The organic phase was dried over anhydrous Na₂SO₄, filtrated and concentrated under vacuum to gain product **7** as white solid that was not further purified (yield 3.57 g, 85%). m.p. 64-65 °C. FT-IR (KBr, cm⁻¹) 3202, 2949, 2844, 1681; ¹H-NMR (200 MHz, δ , CDCl₃) 3.98 (3H, s, CH₃), 7.27 (1H, dd, *J_{A,B}* = 8.4, J_{B,O}=1.7 Hz, Ar-H_B), 7.44 (1H, d, *J_{C,O}* = 1.6 Hz, Ar-H_C), 7.54 (1H, d, *J* = 8.4 Hz, Ar-H_A), 10.78

(1H, s, OH); ¹³C{¹H}-NMR (50 MHz, δ, CDCl₃) 52.69 (CH₃), 102.91 (I-C), 112.14(Ar-C),
127.19 (Ar-CH), 128.84 (Ar-CH), 130.85 (Ar-CH), 161.69 (C-OH), 170.50 (C=O); HR
ESI-MS (QTOF, *m/z*) 276.9353 ([M⁻]).

Synthesis of methyl 4-iodo-2-(methoxymethoxy)benzoate (8). Methyl-4-iodosalicylate 7 (3.60 g, 13.04 mmol) was dissolved in dry DMF (36 mL) under a N₂ atmosphere. K₂CO₃ (7.20 g, 52.17 mmol) and chloromethyl methyl ether (2.08 mL, 27.39 mmol) were slowly added at room temperature and the mixture stirred for 15 hours. The reaction mixture was then diluted with water and extracted with ethyl acetate. The organic phase was washed with brine, dried over anhydrous Na_2SO_4 , filtered and concentrated under vacuum, to obtain product 8 as white solid (yield 4.00 g, 95%). m.p. 76-80 °C. FT-IR (KBr, cm⁻¹) 3104, 3080, 3013, 2969, 2914, 2858, 2833, 1721; ¹H-NMR (200 MHz, δ, CDCl₃) 3.55 (3H, s, O-CH₃), 3.91 (3H, s, COOCH₃), 5.27 (2H, s, O-CH₂-O), 7.56 – 7.39 (2H, m, Ar-H_A, Ar-H_B), 7.61 (1H, s, Ar-H_C); ¹³C{¹H}-NMR (50 MHz, δ, CDCl₃) 52.36 (O-CH₃), 56.72 (COOCH₃), 95.42 (O-CH₂-O), 99.77 (I-C), 121.04 (C-CO), 125.85 (Ar-C),

131.12 (Ar-C), 132.68 (Ar-C), 157.09 (C-O), 166.23 (C=O); HR ESI-MS (QTOF, *m/z*) 344.9590 ([M+Na]⁺).

Synthesis of methyl-2-hydroxy-4-(pyridin-4-yl)benzoate (9). A mixture of methyl-4iodo-2-(methoxymethoxy)benzoate 8 (4.2 g, 13.04 mmol) and 4-pyridinylboronic acid (26.08 mmol, 3.21 g) in a Schlenk tube under nitrogen, was dissolved with degassed solutions of toluene (110 mL), ethanol (22 mL) and aqueous Na₂CO₃ (2 M, 37 mL). After addition of Pd(PPh₃)₄ (1.50 g, 0.13 mmol) the reaction mixture was heated to 80 °C and stirred for 15 h. The reaction mixture was then cooled to room temperature, filtered over celite and then concentrated under vacuum. The residue was diluted with ethyl acetate (50 mL) and extracted with HCl 1 M (4 x 50 mL). The aqueous phase was stirred for 2 hours, basified with saturated NaHCO₃ solution to pH=5 and extracted with ethyl acetate (4 x 100 mL). The organic phase was dried over anhydrous Na₂SO₄, concentrated under reduced pressure, and the residue purified by silica gel column chromatography (dichloromethane/methanol 95:5), affording the product 9 as a lightyellow solid. (yield 2.64g, 89%). m.p. 120-128 °C. FT-IR (KBr, cm⁻¹) 3150, 3063, 3015,

Crystal Growth & Design

2961, 1677; ¹ H-NMR (200 MHz, δ , CDCl ₃) 4.01 (3H, s, CH ₃), 7.17 (1H, dd, $J_{A,B}$ = 8.3,
$J_{B,O}$ = 1.8 Hz, Ar-H _B), 7.27 (1H, d, J = 1.7 Hz, Ar-H _C), 7.53 (2H, d, $J_{D,E}$ = 5.6 Hz, Py-H _D),
7.96 (1H, d, $J_{A,B}$ = 8.3 Hz, Ar-H _A), 8.72 (2H, d, J = 5.3 Hz, Py-H _E), 10.88 (1H, s, OH);
$^{13}\text{C}\{^1\text{H}\}\text{-NMR}$ (50 MHz, $\delta,$ CDCl_3) 52.69 (CH_3), 112.88 (C-CO), 116.19 (Ar-CH), 118.02
(Ar-CH), 121.86 (Py-CH), 130.94 (Ar-CH), 145.41 (Py-C), 147.11 (Ar-C), 150.54 (Py-
CH), 162.08 (C-OH), 170.38 (C=O); HR ESI-MS (QTOF, <i>m/z</i>) 230.0813 ([M+H] ⁺).

Synthesis of 4-(pyridin-4-yl)-salicylhydroxamic acid (10, H₃*p*-pyShi). Hydroxylamine hydrochloride (1.81 g, 26 mmol) and NaOH (1.56 g, 39 mmol) were dissolved in water (60 ml) and a solution of methyl-2-hydroxy-4-(pyridin-4-yl)benzoate 9 (2.98 g, 13 mmol) in 1,4-dioxane (40 ml) was added dropwise. The mixture was stirred at room temperature for 12 hours and then the solvent concentrated under vacuum. The product 10 was purified by crystallization from diethyl ether and obtained as a light-yellow solid. (yield 2.83 g, 95%). m.p. 178-184 °C. FT-IR (KBr, cm⁻¹) 3455, 3273, 1632, 1598; ¹H-NMR (200 MHz, δ , DMSO-D₆) 7.00 (2H, m, ArH_{*c*}, Ar-H_{*b*}), 7.64 (2H, d, *J* = 5.3 Hz, Py-H_{*D*}), 7.74 (1H, d, *J* = 7.8 Hz, Ar-H_{*A*}), 8.58 (2H, d, *J* = 5.3 Hz, Py-H_{*E*}); ¹³C{¹H}-NMR (50

MHz, δ, CDCl₃) 114.39 (Ar-CH), 115.19 (Ar-CH), 121.65 (Ar-C), 121.95 (Py-CH), 128.38 (Ar-CH), 138.08 (Py-C), 148.08 (Ar-C), 150.71 (Py-CH), 161.88 (C-OH), 165.19 (C=O); HR ESI-MS (QTOF, *m/z*) 231.0777 ([M+H]⁺).

Synthesis of $Mn_{11}Shi_6$ (11), $Mn_{11}\rho$ -aShi₆ (12) and $Mn_{11}\rho$ -pyShi₆ (13). The three $Mn_{11}L_6$ metallacryptates ($H_3L = H_3Shi$, H_3p -aShi and H_3p -pyShi) were prepared using the following procedure. Manganese(II) acetate tetrahydrate (122 mg, 0.50 mmol), the ligand (32 mg of H₃Shi, 34 mg of H₃*p*-aShi, or 46 mg of H₃*p*-pyShi, 0.21 mmol) and sodium acetate trihydrate (28 mg, 0.2 mmol) were singly dissolved in 2 mL DMF. The three solution were mixed under stirring in the following order: manganese(II) acetate, $H_{3}L$, and sodium acetate. The resulting dark brown solution was kept under stirring for 4 hours and then centrifuged to remove insoluble impurities. Slow evaporation of the supernatant at room temperature gave dark brown crystals suitable for XRD analysis within four weeks. Yields of compounds 11 and 13 were 28% and 2%, respectively. The synthesis of 12 was attempted several times, obtaining few crystals of the compound only twice. From the other synthesis, a 12-MC-4 of formula $\{Mn^{\parallel}(OAc)_2(O-DMF)_5[12-$

Crystal Growth & Design

$MC_{Mn,\rho-aShi}-4]$ (DMF) ₂ was obtained (compound 12bis). The structural description of this
12-MC-4 is provided as Supporting Information. The three complexes correspond to the
following formulas: $Na_4[(Mn^{II})_2(Mn^{III})_9(\mu^3-O)_4(OAc)_9(Shi)_6(DMF)_3](DMF)_3(H_2O)_{6.75}$ (11),
$Na_{3.5}H_{0.5}[(Mn^{II})_{2}(Mn^{III})_{9}(\mu^{3}-O)_{4}(OAc)_{9}(\rho-aShi)_{6}](DMF)_{7.5}(H_{2}O)_{6} $ (12), and
$H[(Mn^{II})_{2}(Mn^{III})_{9}(\mu^{3}-O)_{4}(OAc)_{3}(OH)_{3}(\rho-pyShi)_{6}](H_{2}O)_{6} (13).$ Several solvent molecules
(not refined) are present in the channels of compounds 12 and 13, as deduced by the
presence of residual electron density. ESI-MS (QTOF, $m/2$) of a solution of 11 in
methanol: <i>m/z</i> 1796 [Mn ₁₁ (O) ₄ (Shi ³⁻) ₆ (OAc) ₃ (OH) ₃] ⁺ ; 1810 [Mn ₁₁ (O) ₄ (Shi ³⁻
) ₆ (OAc) ₃ (OH) ₂ (OMe)] ⁺ ; 1824 [Mn ₁₁ (O) ₄ (Shi ³⁻) ₆ (OAc) ₃ (OH)(OMe) ₂] ⁺ ; 1838 [Mn ₁₁ (O) ₄ (Shi ³⁻
) ₆ (OAc) ₃ (OMe) ₃] ⁺ . ESI-MS (QTOF, m/z) of a solution of 12bis in methanol: m/z 994
$[Mn_5(p-aShi^{3-})_4(OAc)]^+$; Compounds 12 and 13 resulted insoluble in all solvents suitable
for ESI-MS characterization. Elemental analysis found for 11 : C, 34.5; H, 4.3; N, 6.5.
Calc for C ₇₈ H _{106.5} Mn ₁₁ N ₁₂ Na ₄ O _{52.75} : C, 34.0; H, 3.9; N, 6.1%. Elemental analysis found
for 12bis : C, 40.5; H, 4.9; N, 13.2. Calc for C ₅₃ H ₇₅ Mn ₅ N ₁₅ O ₂₃ : C, 40.7; H, 4.8; N, 13.4%.

Results and Discussion

Synthesis of the ligands.

The experimental procedure for preparing the ligand **5** ($H_3\rho$ -aShi) was optimized by modifying a previously reported route for the synthesis of hydroxamic acids (Scheme 3).⁷⁹ The Boc- protection of the amino group of the commercially available 4-aminosalicylic acid was followed by the condensation of the carboxylic function with *O*-benzylhydroxylamine. The (*N*-Boc, *O*-Bz) protected intermediate **3** was deprotected in two step to yield the final $H_3\rho$ -aShi (**5**) product.

Ligand **10** (H₃*p*-**pyShi**) could be obtained in very high yields via a four-step synthetic procedure from commercially available 4-iodosalicylic acid **6** (Scheme 4). After protection of the carboxylic acid as the methyl ester⁸⁰ and the phenol group as methoxymethylether (MOM) (80% overall yield), Suzuki coupling,^{81,82} followed by an acidic work-up allowed the insertion of the pyridine group and MOM protecting group removal affording **9** in high yields (89%). The protection of the phenol and carboxylic acid functional groups was necessary for obtaining an effective coupling reaction. Direct conversion in very high yields (95%) of the methyl ester **9** into the hydroxamic acid **10**

was achieved using hydroxylamine hydrochloride and NaOH in a mixture of dioxane

and water at room temperature.81,82



Scheme 3. Synthetic route to H₃*p*-aShi (5) from 4-aminosalicylic acid (1). a) Boc₂O,

NaOH, H₂O/EtOH, rt; b) Benzylhydroxylamine hydrochloride, triethylamine, EDC,

DMAP, DMF, rt; c) TFA, CH₂Cl₂; d) H₂, Pd/C, MeOH.



ACS Paragon Plus Environment

Scheme 4. Synthetic route to H₃p-pyShi (10) from 4-iodosalicylic acid (6). a) H₂SO₄,

MeOH, reflux, N₂, 18 h; b) MOM-CI, K₂CO₃, DMF, rt, N₂, 12 h; c) 4-Py-B(OH)₂,

Pd(PPh₃)₄, Na₂CO₃ aq. 2 M, Toluene/EtOH, 100 °C, N₂; d) HCl 1 M; e) NH₂OH·.HCl,

NaOH, H_2O /dioxane, rt.

General description of metallacryptate core in 11, 12 and 13.

The metallacryptates **11**, **12** and **13** were isolated after reaction of the ligands with manganese(II) acetate, and sodium acetate in DMF. All three metallacryptates (MCr) **11**, **12**, and **13** present a $[Mn^{II}]_2[Mn^{III}]_9$ polynuclear core, where nine Mn^{III} and two Mn^{II} are found (Figure 1). In all three compounds six hydroxamate ligands are present, which bridge between the manganese ions and give rise to a supramolecular complex that presents a crystallographic C_3 symmetry axis. Therefore, these assemblies are referred to as $Mn_{11}L_6$, where $H_3L = H_3Shi$, $H_3\rho$ -aShi or $H_3\rho$ -pyShi. The shape of the metallacryptate architecture is that of a three-bladed paddlewheel, where the blades are related by the crystallographic C_3 axis in all three compounds (Figures. 1 and 2). For

these reasons, we will first describe the structure of the blades, and how they are connected together to give a metallacryptate motif.



Figure 1 View of the $Mn_{11}L_6$ molecular unit of **11** along (a) and perpendicularly to (b) the crystallographic C_3 axis. Light blue spheres = Mn^{III} , purple spheres = Mn^{III} . The acetate ions bridging between blades are represented with thin lines.

The three molecules present a very similar MCr architecture and similar connectivities of the blades, although with significant differences. Figure 2 shows how two L³⁻ ligands, three Mn^{III} and one oxide ion are bound together. Two Mn^{II} are found at the apices of the assembly, sitting on the C_3 axis, and coincide with the points of connections of the three MCr blades. The two L³⁻ ligands bridge between one Mn^{II} and one Mn^{III} ion through the bridging (N, O)-(O, O) bis-chelating mode known for this ligand. The Mn^{II}

ions (Mn1 and Mn2) are coordinated to the hydroxamic (O,O) site of Shi³⁻ (purple spheres in Figure 2) in trigonal prismatic (**11** and **12**) or octahedral (**13**) geometry. Conversely, the (N,O) site is occupied by a Mn^{III} ion (Mn4 and Mn5, light blue spheres in Figure 2). A third Mn^{III}/L³⁻ interaction involves the coordination of the hydroximate O atom to a Mn^{III} (Mn3) which is found in the center of the blade and which is part of the Mn₃O core of the MCr assembly (see below).



Figure 2 Representations of **11** (a), **12** (b) and **13** (c). The L³⁻ ligands are represented as sticks. Light blue spheres = Mn^{III} , purple spheres = Mn^{II} . The cyan spheres in c represent Mn^{III} atoms of neighbouring MCr molecules. The crystallographic C_3 axis is represented in green in a, and is present in all three compounds. Labelling of atoms in b is the same as in a.

While the blades in compounds **11** and **12** are nearly planar, that of compound **13** is domed (see Figure S1, Supporting Information). Also, the blade in **13** bares two pyridyl groups that point away from the MCr unit and are coordinated to two neighbouring molecules. These two structural features of the blades in **13** (*i.e.* concavity and presence of pyridyl groups) have profound consequences on both the molecular MCr architecture and on its assembly in the solid state, as discussed below. In all three compounds, the three blades connect together ideally at the C_3 axis to form a MCr motif which has the connectivity Mn1-O-N-Mn4-O_{oxide}-Mn5-N-O-Mn2. This

connectivity in compound **11** is represented as spheres in Figure 3a. Associated to this connectivity is the [1.1.1] orthoester cryptand topology reported in Figure $3b.^{83-85}$ This organic cryptand bears a C-CH₃ connection points rather than a nitrogen as in Lehn-type cryptands, allowing the first atom of the arm to be an oxygen.⁸⁶ Finally, the MCr architecture sequesters a [Mn^{III}₃O]⁷⁺ unit, which is represented in yellow in Figure 3a.



Figure 3 a) Ball and stick representation of the metallacryptate connectivity in **11**. b) representation of a [*o*-Me₂-1.1.1] orthoester cryptand. The connectivity in a is obtained from that in b by conceptually replacing the C-C bonds with Mn^{III}-N bonds, and the C-CH₃ fragment with Mn^{II}. Light blue spheres = Mn^{III}, purple spheres = Mn^{II}, blue spheres = N, red spheres = O. The [Mn^{III}₃O]⁷⁺ unit is represented in yellow.

In this description of the MCr topology the oxide oxygen in the center of the blade is part of the MCr connectivity. Since an oxide ion is commonly found as a guest in supramolecular assemblies, the topology of our molecules is perhaps more appropriately described in terms of inverse metallacryptate (*inv*MCr) motifs, as represented in the Supporting Information (Figs. S2 and S3). For compounds **11** and **12**, the *inv*MCr connectivity is Mn1-O-N-Mn4-O-C-O-Mn5-N-O-Mn2 (Figure S2a). This

description differs from the previous analysis in two aspects. On one hand, the connectivity does not pass through the oxide oxygen of the blade, but rather through the O-C-O atoms of the carboxylates bridging between Mn4 and Mn5. From this perspective, the inverse metallacryptate topology is in analogy with that of a Lehn-type [2.2.2] cryptand (Figure S2b), where the oxygen atoms are ideally substituted by Mn^{III}. In this inverse metallacryptate the sequestered host in the *inv*MCr is a [Mn^{III}₃O₄]⁺ unit, which is reported in yellow in Figure S2a. Finally, all the oxide ions in the molecule are part of the latter [Mn^{III}₃O₄]⁺ quest unit.

In compound **13** the *inv*MCr connectivity is slightly different, since the two peripheral Mn^{III} of the blades (i.e. Mn4 and Mn5) are bridged by a hydroxide ion, and not by carboxylates. Therefore, the analog cryptand is still a [2.2.2], but with a methylene spacer rather than a propylene (Figure S3, Supporting Information).

It must be underlined that for both the metallacryptate and inverse MCr topologies, the connectivity does not correspond to (Mn-N-O)_n repeats as found in normal metallacrowns and metallacryptates.⁸⁷ Actually, starting from Mn1 the O-N-Mn^{III} repeat

inverts in correspondence of the carboxylates (compds. **11** and **12**) or the hydroxide bridging ligand (compd. **13**). This type of connectivity in metallacrowns has been found for a Ln₂[14-MC-4] complex of Shi³⁻ where the (Mn-N-O) repeat inverts in relationship to a Dy^{III} ion which is part of the metallacyclic ring.³¹ Remarkably, also in this structure a hydroxide ion is a bridge between two ring Mn^{III} atoms, and it is located in correspondence to the inversion point of the repeats.³¹

Coordination geometry of Mn^{II} and Mn^{III}. The molecular construct contains 11 Mn ions; the presence of nine Mn^{III} and two Mn^{II} is in agreement with the Bond Valence Sum.^{88,89} The results of this analysis, together with a detailed discussion of the coordination environment of the different Mn ions is reported as Supporting Information.

For all three MCr assemblies the nine Mn^{III} ions are located at the vertices of four interconnected $[Mn^{III}_{3}(\mu^{3}-O)]^{7+}$ units (Figure 4). Therefore, three Mn₃O units other than that in the core are present in the structure, one for each blade. Figure 4a shows the conceptual arrangement of these units, represented as triangles. The core Mn₃O units is indicated as T1 and it is represented as a light purple triangle. In **11** and **12**, T1





Figure 4 a) Conceptual representation of the connection between Mn₃O units. The

core T1 unit is represented as light blue triangles, the peripheral T3 units are

represented as magenta triangles. b) Superimposition of the T1 and T3 representations over the crystal structure of **11**. The C_3 axis is represented in blue.

T1 is the *hub* Mn₃O unit to which the remaining three $[Mn^{III}_{3}\mu_{3}$ -O]⁷⁺ units are linked as is indicated as T3 and represented in magenta in Figure 4. T3 units are connected to T1 by sharing a Mn^{III} at the vertex, and they are the *blade* Mn₃O units. T3 units are oriented almost perpendicularly to the plane of T1, and almost parallel to the *paddle shaft*, which

coincides with the 3-fold symmetry axis. In essence, in **11** and **12** each of the T3 motifs can be seen to originate from a substituted basic manganese acetate structure that has a core μ^3 -O and six bridging carboxylates between the three Mn^{III} atoms (Mn3, Mn4 and Mn5).⁹⁰ Here four of the carboxylates on two of the Mn atoms are displaced by the bidentate L³⁻ ligand. The presence of axially elongated manganese(III) centers fully agrees with the presence of Mn^{III} ions with a high-spin d⁴ configuration.^{91,92}

Possibly more interesting than the coordination environment of the Mn^{III} is that of the Mn^{III}. The Mn^{III} atoms are located at the apices of the MCr architecture (Mn1 and Mn2), they sit on the crystallographic C_3 axis and they coordinate six oxygen atoms of three hydroxamate groups. The Mn-O distances are in the range 2.17-2.19 Å, consistent with typical Mn^{II}-O distances.⁹³ In **11** and **12** their coordination geometry is a distorted trigonal prism, where the two triangular bases are perpendicular to the C_3 axis (Figure S4a and b). Actually, for Mn2 and Mn4 respectively, the rotation angles around the C3 axis of one base of the prism with respect to the other are 19 and 13 deg in **11**, and 11 and 20 deg in **12**. Since the expected values are 0 deg for an ideal trigonal prism and

60 deg for an ideal trigonal antiprism or an octahedron, the geometry at the Mn^{II} centers in **11** and **12** are closer to a prism rather than an antiprism. Conversely, the Mn^{II} atoms in **13** adopt a flattened trigonal antiprismatic coordination geometry (47 deg relative rotation angles of the bases, Figure S4c), likely the result of the presence of concave paddles. Notably, the prismatic coordination geometry of Mn1 and Mn2 in **11** and **12** is not accessible to high spin Mn^{III} as a consequence of its d⁴ configuration, while it can be adopted by a high-spin d⁵ Mn^{III} ion.

Supramolecular architectures in 11, 12 and 13.

The main structural core in all three reported structures is the MCr system, which can be viewed as a structural node in the supramolecular arrangement and crystal packing. We will provide here a description of the framework motifs that are generated by the $Mn_{11}L_6$ nodes assisted by the presence of sodium cations (in **11** and **12**), weak ligand interactions (in **12**), and by a reticular coordination bond (in **13**).

In **11** each T3 blade is connected with the other two symmetry related T3 blades by Na1 bridges as shown in Figure S6. The $Mn_{11}L_6$ core is surrounded by six Na1 cations

arranged in a flattened octahedral geometry, whose connection with six distinct MCr nodes generate the overall framework (Figure 5). Along the direction of the C_3 axes, and interacting with the Mn^{II} ions (Mn1 and Mn2), are positioned disordered Na2 and Na3 sodium cations. Na2 and Na3 do not contribute to the construction of the framework since they do not provide a bridging connection between symmetry related Mn₁₁L₆ nodes. Water molecules of crystallization are found in the interstices of the framework.



Figure 5. Representation of the framework of 11. Only Mn^{III} (purple) and Na^I (yellow)

atoms are depicted. Disordered Na2 and Na3 cations are not reported for clarity. The

metal ions of the metallacryptate building block is highlighted in darker color tones. View

along the 111 direction (A) and along the *a* axis (B).

Compound **12** exhibits an extensive packing arrangement of the $Mn_{11}L_6$ units (Figure 6). In more detail, the MCr units are connected through a dinuclear sodium-DMF moiety (Na2 and Na3 cations), resulting in a pillar that runs parallel to the *c* axis. The T3 blades then connect the pillars by means of the bridging Na1 cations and by extensive nets of hydrogen bonds between water molecules (O1w and O2w) and the peripheral amino groups of the *p*-aShi³⁻ ligand (Figure S7). The overall arrangement leads to the formation of hexagonal channels, occupied by solvent molecules, and which correspond to 39 % of the unit cell volume (calculated with a sphere of 1.2 Å radius, Figure S8, Supporting Information).



Figure 6 Representation of the framework of 12. Mn (purple) and Na (yellow) atoms are depicted together with DMF solvent molecules (light green). The metal ions of the

(A) and along the 110 direction (B).

In compound 13, the presence of the pyridyl fragment of p-pyShi³⁻ leads to the formation of an extensive 3D framework, whose nodes are represented by $Mn_{11}L_6$ units (Figure 7). Each node is bound to six neighboring nodes through twelve connections mediated by the pyridyl fragment. Six connections are diagonally directed above the T1 plane and six connections are oriented below the same plane. The six connections above the T1 plane are eclipsed with respect to those below T1. More specifically, the interaction between the six $Mn_{11}L_6$ nodes occurs through a coordinative bond between the Mn4 ion of T3 and the nitrogen of the peripheral pyridyl group (Figure 7). The arrangement of the p-pyShi³⁻ ligands results in a hexagonal framework when viewed along the c axis (Figure 8), which possesses a honeycomb arrangement of infinite, parallel channels. Also, along both the a and b directions smaller channels of trapezoidal sections are formed (Figure S9, Supporting Information). These interpenetrated channels correspond to 55% of the unit cell volume.



Figure 7 Two views of the $Mn_{11}L_6$ node in **13**, highlighting the twelve connections with six additional nodes (indicated with 1-6). Py_in and py_out indicate the pyridyl groups incoming and departing, respectively, to the indicated neighbouring $Mn_{11}L_6$ node (as numbers).



Figure 8 Channel-like cavities in **13**. Colors are as in Figure 7. The surface of the hexagonal channels is represented in green.

As for a comparison between compounds **12** and **13**, it is interesting to note that, although in low yields, the latter is selectively isolated from the mother liquors of crystallization. The same is not true for compound **12** which has been isolated alternatively to a **12-MC-4** species from solutions obtained from the same experimental setup. Actually, while the architecture in **13** is organized in a way that possibly optimizes the interactions between the peripheral pyridyl groups and the Mn^{III} atoms of adjacent units, a similar situation is not observed in **12**. Rather, the analysis of **12** and **12bis** showed that in both structures the packing allows the NH₂ groups, for instance, to form hydrogen bonds that may contribute to stabilize the observed architectures. Therefore,

we may put forward the hypothesis that the isolated architecture in **13** represents a quite stable one, while for the compounds obtained using p-aShi³⁻ the compounds **12** and **12bis** do not differ very significantly in terms of relative stability.

Conclusions

In this paper we showed that the use of Shi³⁻ ligands and manganese(II) acetate permits to the isolatation of stable metallacryptates supramolecules that are three-fold symmetric and contain multiple Mn^{II} and Mn^{III} ions. These molecules are metallacrown-related analogs of organic cryptates, and the first presenting the same connectivity along the three arms.

The presence of an amino or a pyridyl substituent in position 4 on the Shi³⁻ aromatic ring has allowed us to prepare crystalline materials where the $Mn_{11}L_6$ units are arranged differently in the three dimensions. In the case of the ligands that we have examined, both the amino and the pyridyl functions are involved in the interaction between neighbouring metallacryptate units. Perhaps more important, these groups correspond to the formation of porous structures, where chains of $Mn_{11}L_6$ units aligned along the

three-fold symmetry axis are assembled into honeycomb architectures. However, in the case of the *p*-aShi³⁻ ligand the units interact both through bridging Na¹ ions and through an extensive net of hydrogen bonds that involve the NH₂ function and water molecules. However, it is with the ligand bearing the pyridyl group that a direct interaction between metallacryptates was obtained. Actually, the presence of that function allowed the formation of peripheral *p*-pyShi³⁻-Mn^{III} interactions that resulted in the isolation of a porous metal-organic framework architecture.

In the future we aim to study these structures in terms both of their porosity, and of the change of their magnetic properties as a function of the absorption of guest molecules such as gases or volatile liquids.

ASSOCIATED CONTENT

Supporting Information.

The Supporting Information is available free of charge on the ACS Publications website at DOI: 10.1021/XXXXXXX.

1	
2	
3	
4	
5	
6	
7	
/ 0	
0	
9	
10	
11	
12	
13	
14	
15	
16	
17	
18	
19	
20	
21	
22	
23	
24	
25	
26	
20	
27 20	
20	
29	
30	
31	
32	
33	
34	
35	
36	
37	
38	
39	
40	
41	
42	
43	
44	
45	
46	
47	
48	
40	
79 50	
51	
51	
52	
53	
54	
55	
56	
57	
58	
59	
60	

Additional structural figures, Valence Bond Sum analysis, structural description of 12bis (Figures S1-S12, Tables1-3), NMR, FT-IR and ESI-MS Characterization Spectra (Figure S10-S32), crystallographic data (Table S4) (PDF). Accession Codes CCDC: 1849184-1849186 and 1884452 contain the supplementary crystallographic data for this paper. These data can be obtained free of charge via www.ccdc.cam.ac.uk/ data request/cif, or by emailing data request@ccdc.cam.ac. uk, or by contacting The Cambridge Crystallographic Data Centre, 12 Union Road, Cambridge CB2 1EZ, UK; fax: +44 1223 336033. AUTHOR INFORMATION **Corresponding Authors** * Matteo Tegoni, Email: matteo.tegoni@unipr.it; * Vincent L. Pecoraro, Email: vlpec@umich.edu.

ORCID

2 3 4 5 6	V. Marzaroli: 0000-0003-1781-2622
7 8 9 10	M. Quaretti: 0000-0001-7556-6031
11 12 13 14	G. Licini: 0000-0001-8304-0443
15 16 17 18	L. Marchiò: 0000-0002-0025-1104
19 20 21 22 23	V. L. Pecoraro: 0000-0002-1540-5735
24 25 26 27	M. Tegoni: 0000-0002-9621-0410.
28 29 30 31	Notes
32 33 34 35	The authors declare no competing financial interest. The manuscript was written
36 37 38	through contributions of all authors. All authors have given approval to the final version
39 40 41 42 43	of the manuscript. M.T. and V.L.P. contributed equally.
44 45 46 47	† Present address: Institut für Anorganische Chemie, Georg-August-Universität
48 49 50 51	Göttingen, Tammannstraße 4, 37077 Göttingen, Germany.
52 53	
54	
55 56	
50	
58	
59	

60

1

 \ddagger For each Mn₁₁L₆ in **12** and **13**, an excess of 0.5 and 1 negative charge was found. The structures exhibit a significant portion of the unit cells occupied by severely disordered solvent molecules that can easily accommodate the residual +0.5 or +1 charge in the form of disordered protons or sodium cations. This will result in the overall charge balance of the crystals. Here the formulae of **12** and **13** are reported considering as counterions 0.5 and 1 protons per molecules, respectively.

ACKNOWLEDGMENTS

The research leading to these results have received funding from the European Community's Seventh Framework Programme (FP7/2013-2017) under grant agreement n° 611488. This work was supported by the National Science Foundation under grant CHE-1361799 to V.L.P. M.T. and V.L.P. thank MAECI (Italian Ministry of Foreign Affairs and International Cooperation, Direzione Generale per la Promozione del Sistema Paese) for financial support through the bilateral Italy-USA project "Development of porous magnetic Metallacrowns for sensing applications". G.S. thanks University of Padova for financial support (G.S. fellowship through Strategic Project NAMECA).

REFERENCES

- Zhou, H.-C.; Long, J. R.; Yaghi, O. M. Introduction To Metal–Organic Frameworks. *Chem. Rev.* 2012, *112*, 673–674.
- (2) Zhou, H.-C. "Joe"; Kitagawa, S. Metal–Organic Frameworks (MOFs). *Chem. Soc. Rev.* 2014, *43*, 5415–5418.

(3) Batten, S. R.; Champness, N. R.; Chen, X.-M.; Garcia-Martinez, J.; Kitagawa, S.; Öhrström, L.; O'Keeffe, M.; Suh, M. P.; Reedijk, J. Coordination Polymers, Metal– organic Frameworks And The Need For Terminology Guidelines. *CrystEngComm* 2012, *14*, 3001–3004.

- (4) Jiang, J.; Zhao, Y.; Yaghi, O. M. Covalent Chemistry Beyond Molecules. *J. Am. Chem. Soc.* **2016**, *138*, 3255–3265.
- Janiak, C.; Vieth, J. K. MOFs, MILs And More: Concepts, Properties And Applications For Porous Coordination Networks (PCNs). *New J. Chem.* 2010, *34*, 2366–2388.

(6)	Fujita, D.; Ueda, Y.; Sato, S.; Mizuno, N.; Kumasaka, T.; Fujita, M. Self-Assembly
	Of Tetravalent Goldberg Polyhedra From 144 Small Components. Nature 2016,
	<i>540</i> , 563–566.
(7)	Furukawa, H.; Cordova, K. E.; O'Keeffe, M.; Yaghi, O. M. The Chemistry And
	Applications Of Metal-Organic Frameworks. <i>Science</i> 2013, 341, 1230444.
(8)	Cook, T. R.; Zheng, YR.; Stang, P. J. Metal-Organic Frameworks And Self-
	Assembled Supramolecular Coordination Complexes: Comparing And
	Contrasting The Design, Synthesis, And Functionality Of Metal-Organic Materials.
	<i>Chem. Rev.</i> 2013 , <i>113</i> , 734–777.
(9)	Tranchemontagne, D. J.; Mendoza-Cortes, J. L.; O'Keeffe, M.; Yaghi, O. M.
	Secondary Building Units, Nets And Bonding In The Chemistry Of Metal-Organic
	Frameworks. <i>Chem. Soc. Rev.</i> 2009 , <i>38</i> , 1257–1283.
(10) Atzeri, C.; Marchiò, L.; Chow, C. Y.; Kampf, J. W.; Pecoraro, V. L.; Tegoni, M.
	Design Of 2D Porous Coordination Polymers Based On Metallacrown Units.

Chem. Eur. J. 2016, 22, 6482-6486.

- (11) Ostrowska, M.; Fritsky, I. O.; Gumienna-Kontecka, E.; Pavlishchuk, A. V.
 Metallacrown-Based Compounds: Applications In Catalysis, Luminescence,
 Molecular Magnetism, And Adsorption. *Coord. Chem. Rev.* 2016, *327–328*, 304–332.
- (12) Pavlishchuk, A. V.; Satska, Y. .; Kolotilov, S. V.; Fritsky, I. Coordination Polymers And Oligonuclear Systems Based On Oximate Or Hydroxamate Building Blocks: Magnetic And Sorption Properties. *Curr. Inorg. Chem.* **2015**, *5*, 5–25.
- (13) Lamberts, K.; Tegoni, M.; Jiang, X.; Kou, H.-Z.; Englert, U. Silver Complexation
 By Metallacryptates. *Dalton Trans.* 2016, *45*, 284–295.
- (14) Mezei, G.; Zaleski, C. M.; Pecoraro, V. L. Structural And Functional Evolution Of Metallacrowns. *Chem. Rev.* 2007, *107*, 4933–5003.
- (15) Tegoni, M.; Remelli, M. Metallacrowns Of Copper(II) And Aminohydroxamates: Thermodynamics Of Self Assembly And Host–guest Equilibria. *Coord. Chem.*

1 ว	
2	
4 5	
6	
7 8	
9 10	
10	
12 13	
14	
15 16	
17 18	
19	
20 21	
22 23	
23 24	
25 26	
27	
28 29	
30 31	
32	
33 34	
35 36	
37	
38 39	
40 41	
42	
43 44	
45 46	
47	
48 49	
50 51	
52	
53 54	
55 56	
57	
58 59	
60	

Rev. **2012**, *256*, 289–315.

(16) Alexiou, M.; Katsoulakou, E.; Dendrinou-Samara, C.; Raptopoulou, C. P.; Psycharis, V.; Manessi-Zoupa, E.; Perlepes, S. P.; Kessissoglou, D. P. Di-2-Pyridyl Ketone Oxime In Zinc Chemistry: Inverse 12-Metallacrown-4 Complexes And Cationic Pentanuclear Clusters. *Eur. J. Inorg. Chem.* 2005, *2005*, 1964– 1978.
(17) Stemmler, A. J.; Kampf, J. W.; Pecoraro, V. L. Synthesis And Crystal Structure Of The First Inverse 12-Metallacrown-4. *Inorg. Chem.* 1995, *34*, 2271–2272.
(18) Alexiou, M.; Dendrinou-Samara, C.; Raptopoulou, C. P.; Terzis, A.; Kessissoglou, D. P. From Monomer Zinc-Oxamato Complexes To Tetranuclear Inverse 12-

Membered And Octanuclear 12-Membered Metallacrowns. Inorg. Chem. 2002,

41, 4732–4738.

- (19) Stamatatos, T. C.; Dionyssopoulou, S.; Efthymiou, G.; Kyritsis, P.; Raptopoulou,
 - C. P.; Terzis, A.; Vicente, R.; Escuer, A.; Perlepes, S. P. The First Cobalt

2	
3	
1	
т г	
5	
6	
7	
8	
0	
9	
10	
11	
12	
13	
11	
14	
15	
16	
17	
18	
10	
20	
20	
21	
22	
23	
24	
24	
25	
26	
27	
28	
20	
29	
30	
31	
32	
33	
24	
34	
35	
36	
37	
38	
30	
39	
40	
41	
42	
43	
44	
 4	
45	
46	
47	
48	
10	
49	
50	
51	
52	
53	
54	
54 57	
55	
56	
57	
58	
50	
59	
60	

Metallacrowns: Preparation And Characterization Of Mixed-Valence Cobalt(II/III), Inverse 12-Metallacrown-4 Complexes. Inorg. Chem. 2005, 44, 3374–3376. (20) Lah, M. S.; Gibney, B. R.; Tierney, D. L.; Penner-Hahn, J. E.; Pecoraro, V. L. The Fused Metallacrown Anion Na₂([Na_{0.5}[Ga(Salicylhydroximate)]₄]₂(μ_2 -OH)₄)⁻ Is An Inorganic Analog Of A Cryptate. J. Am. Chem. Soc. 1993, 115, 5857–5858. (21) Dendrinou-Samara, C.; Alexiou, M.; Zaleski, C. M.; Kampf, J. W.; Kirk, M. L.; Kessissoglou, D. P.; Pecoraro, V. L. Synthesis And Magnetic Properties Of A Metallacryptate That Behaves As A Single-Molecule Magnet. Angew. Chem. Int. Ed. 2003, 42, 3763-3766. (22) Zaleski, C. M.; Depperman, E. C.; Dendrinou-Samara, C.; Alexiou, M.; Kampf, J. W.; Kessissoglou, D. P.; Kirk, M. L.; Pecoraro, V. L. Metallacryptate Single-Molecule Magnets: Effect Of Lower Molecular Symmetry On Blocking Temperature. J. Am. Chem. Soc. 2005, 127, 12862–12872.

(23) Lutter, J. C.; Eliseeva, S. V; Kampf, J. W.; Petoud, S.; Pecoraro, V. L. A Unique

Crystal Growth & Design

2 3 4	Ln ^{III} {[3.3.1]Ga ^{III} Metallacryptate} Series That Possesses Properties Of Slow
5 6 7 8	Magnetic Relaxation And Visible/Near-Infrared Luminescence. Chem. Eur. J.
9 10 11 12 13	2018 , <i>24</i> , 10773-10783.
14 15 (2- 16	4) Chow, C. Y.; Trivedi, E. R.; Pecoraro, V.; Zaleski, C. M. Heterometallic Mixed 3d-
18 19 20	4f Metallacrowns: Structural Versatility, Luminescence, And Molecular
21 22 23 24	Magnetism. Comments Inorg. Chem. 2015, 35, 214–253.
25 26 27 28 (2)	5) Happ, P.; Plenk, C.; Rentschler, E. 12-MC-4 Metallacrowns As Versatile Tools For
29 30 31 32	SMM Research. <i>Coord. Chem. Rev.</i> 2015, <i>289–290</i> , 238–260.
33 34 35 36	6) Jankolovits, J.; Andolina, C. M.; Kampf, J. W.; Raymond, K. N.; Pecoraro, V. L.
37 38 39	Assembly Of Near-Infrared Luminescent Lanthanide Host(Host-Guest)
40 41 42 43	Complexes With A Metallacrown Sandwich Motif. Angew. Chem. Int. Ed. 2011,
44 45 46 47	<i>50</i> , 9660–9664.
48 49 50 51 (2)	7) Nguyen, T. N.; Chow, C. Y.; Eliseeva, S. V.; Trivedi, E. R.; Kampf, J. W.; Martinić,
52 53 54 55	I.; Petoud, S.; Pecoraro, V. L. One-Step Assembly Of Visible And Near-Infrared

2	
3	
1	
- -	
2	
6	
7	
8	
9	
10	
11	
11	
12	
13	
14	
15	
16	
17	
10	
10	
19	
20	
21	
22	
23	
24	
25	
∠_) ⊃¢	
20	
27	
28	
29	
30	
31	
27	
5Z	
33	
34	
35	
36	
37	
38	
20	
39	
40	
41	
42	
43	
44	
45	
16	
40	
4/	
48	
49	
50	
51	
52	
52	
22	
54	
55	
56	
57	
58	
59	
55	
00	

Emitting Metallacrown Dimers Using A Bifunctional Linker. *Chem. Eur. J.* **2018**, *24*, 1031–1035.

(28) Martinić, I.; Eliseeva, S. V.; Nguyen, T. N.; Pecoraro, V. L.; Petoud, S. Near-Infrared Optical Imaging Of Necrotic Cells By Photostable Lanthanide-Based Metallacrowns. *J. Am. Chem. Soc.* **2017**, *139*, 8388–8391.

(29) Trivedi, E. R.; Eliseeva, S. V; Jankolovits, J.; Olmstead, M. M.; Petoud, S.; Pecoraro, V. L. Highly Emitting Near-Infrared Lanthanide "Encapsulated Sandwich" Metallacrown Complexes With Excitation Shifted Toward Lower Energy. *J. Am. Chem. Soc.* **2014**, *136*, 1526–1534.

(30) Chow, C. Y.; Eliseeva, S. V.; Trivedi, E. R.; Nguyen, T. N.; Kampf, J. W.; Petoud,
S.; Pecoraro, V. L. Ga³⁺/Ln³⁺ Metallacrowns: A Promising Family Of Highly
Luminescent Lanthanide Complexes That Covers Visible And Near-Infrared
Domains. *J. Am. Chem. Soc.* 2016, *138*, 5100–5109.

(31) Boron, T. T.; Kampf, J. W.; Pecoraro, V. L. A Mixed 3d-4f 14-Metallacrown-5

2 3		
4 5 6		Complex That Displays Slow Magnetic Relaxation Through Geometric Control Of
6 7 8 9		Magnetoanisotropy. Inorg. Chem. 2010, 49, 9104–9106.
10 11 12 13	(32)	Deb, A.; Boron, T. T.; Itou, M.; Sakurai, Y.; Mallah, T.; Pecoraro, V. L.; Penner-
15 16 17		Hahn, J. E. Understanding Spin Structure In Metallacrown Single-Molecule
18 19 20 21		Magnets Using Magnetic Compton Scattering. J. Am. Chem. Soc. 2014, 136,
22 23 24 25		4889–4892.
26 27 28	(33)	Zaleski, C. M.; Tricard, S.; Depperman, E. C.; Wernsdorfer, W.; Mallah, T.; Kirk,
30 31 32		M. L.; Pecoraro, V. L. Single Molecule Magnet Behavior Of A Pentanuclear Mn-
33 34 35 36		Based Metallacrown Complex: Solid State And Solution Magnetic Studies. Inorg.
37 38 39 40		<i>Chem.</i> 2011 , <i>50</i> , 11348–11352.
41 42 43	(34)	Zaleski, C. M.; Depperman, E. C.; Kampf, J. W.; Kirk, M. L.; Pecoraro, V. L.
44 45 46 47		Synthesis, Structure, And Magnetic Properties Of A Large Lanthanide–Transition-
48 49 50 51		Metal Single-Molecule Magnet. Angew. Chem. Int. Ed. 2004, 43, 3912–3914.
52 53 54 55 56 57	(35)	Zaleski, C. M.; Kampf, J. W.; Mallah, T.; Kirk, M. L.; Pecoraro, V. L. Assessing
J /		

2	
3	
4	
5	
6	
7	
8	
9	
10	
11	
11	
12	
13	
14	
15	
16	
17	
18	
19	
20	
∠∪ ⊃1	
21	
22	
23	
24	
25	
26	
27	
28	
20	
29	
20	
31	
32	
33	
34	
35	
36	
37	
38	
30	
10	
40 11	
41	
42	
43	
44	
45	
46	
47	
48	
49	
50	
50	
51	
52	
53	
54	
55	
56	
57	
58	
59	
60	
00	

The Slow Magnetic Relaxation Behavior Of Ln^{III}₄Mn^{III}₆ Metallacrowns. Inorg. *Chem.* **2007**, *46*, 1954–1956. (36) Boron, T. T.; Lutter, J. C.; Daly, C. I.; Chow, C. Y.; Davis, A. H.; Nimthong-Roldán, A.; Zeller, M.; Kampf, J. W.; Zaleski, C. M.; Pecoraro, V. L. The Nature Of The Bridging Anion Controls The Single-Molecule Magnetic Properties Of DyX₄M 12-Metallacrown-4 Complexes. Inorg. Chem. 2016, 55, 10597–10607. (37) Chow, C. Y.; Bolvin, H.; Campbell, V. E.; Guillot, R.; Kampf, J. F.; Wernsdorfer, W.; Gendron, F. V; Autschbach, J.; Pecoraro, V. L.; Mallah, T. Assessing The Exchange Coupling In Binuclear Lanthanide(III) Complexes And The Slow Relaxation Of The Magnetization In The Antiferromagnetically Coupled Dy₂

Derivative. Chem. Sci. 2015, 6, 4148-4159.

(38) Zaleski, C. M.; Depperman, E. C.; Kampf, J. W.; Kirk, M. L.; Pecoraro, V. L. Using Ln^{III}[15-MC_{Cull(N)(S)-PheHA}-5]³⁺ Complexes To Construct Chiral Single-Molecule Magnets And Chains Of Single-Molecule Magnets. *Inorg. Chem.* 2006, *45*, 10022–10024.

2	
3	
4	
5	
6	
7	
8	
9	
10	
11	
12	
13	
14	
16	
17	
18	
19	
20	
21	
22	
23	
24	
25	
26	
27	
28	
29	
30	
31	
32	
33	
34	
35	
30 27	
رد در	
30	
40	
41	
42	
43	
44	
45	
46	
47	
48	
49	
50	
51	
52	
53	
54	
55	
56	
5/	
58	
59	
00	

(39) Stemmler, A. J.; Kampf, J. W.; Kirk, M. L.; Atasi, B. H.; Pecoraro, V. L. The Preparation, Characterization, And Magnetism Of Copper 15-Metallacrown-5 Lanthanide Complexes. *Inorg. Chem.* 1999, *38*, 2807–2817.
(40) Chow, C. Y.; Guillot, R.; Rivière, E.; Kampf, J. W.; Mallah, T.; Pecoraro, V. L.

Synthesis And Magnetic Characterization Of Fe(III)-Based 9-Metallacrown-3 Complexes Which Exhibit Magnetorefrigerant Properties. *Inorg. Chem.* **2016**, *55*, 10238–10247.

- (41) Atzeri, C.; Marzaroli, V.; Quaretti, M.; Travis, J. R.; Di Bari, L.; Zaleski, C. M.; Tegoni, M. Elucidation Of ¹H NMR Paramagnetic Features Of Heterotrimetallic Lanthanide(III)/Manganese(III) 12-MC-4 Complexes. *Inorg. Chem.* 2017, *56*, 8257–8269.
- (42) Pavlyukh, Y.; Rentschler, E.; Elmers, H. J.; Hübner, W.; Lefkidis, G. Magnetism
 Of Metallacrown Single-Molecule Magnets: From A Simplest Model To Realistic
 Systems. *Phys. Rev. B* 2018, *97*, 214408.

2	
3	
4	
5	
6	
7	
8	
0	
9 10	
10	
11	
12	
13	
14	
15	
16	
17	
18	
10	
ילו הר	
20	
21	
22	
23	
24	
25	
26	
27	
28	
29	
20	
20	
21	
32	
33	
34	
35	
36	
37	
38	
39	
40	
<u>⊿</u> 1	
+1 ∕\⊃	
42	
43	
44	
45	
46	
47	
48	
49	
50	
51	
52	
52 52	
22	
54	
55	
56	
57	
58	
59	
60	

(43) Lim, C.-S.; Tegoni, M.; Jakusch, T.; Kampf, J. W.; Pecoraro, V. L. Clarifying The Mechanism Of Cation Exchange In Ca(II)[15-MC_{Cu(II)Ligand}-5] Complexes. *Inorg. Chem.* 2012, *51*, 11533–11540.

(44) Dallavalle, F.; Remelli, M.; Sansone, F.; Bacco, D.; Tegoni, M. Thermodynamics
 Of Self-Assembly Of Copper(II) 15-Metallacrown-5 Of Eu(III) Or Gd(III) With (*S*)-α Alaninehydroxamic Acid In Aqueous Solution. *Inorg. Chem.* 2010, *49*, 1761–1772.

(45) Tegoni, M.; Furlotti, M.; Tropiano, M.; Lim, C. S.; Pecoraro, V. L. Thermodynamics
 Of Core Metal Replacement And Self-Assembly Of Ca²⁺ 15-Metallacrown-5.
 Inorg. Chem. 2010, *49*, 5190–5201.

(46) Grant, J. T.; Jankolovits, J.; Pecoraro, V. L. Enhanced Guest Affinity And Enantioselectivity Through Variation Of The Gd³⁺ [15-Metallacrown-5] Side Chain.

Inorg. Chem. 2012, 51, 8034-8041.

(47) Jankolovits, J.; Kampf, J. W.; Maldonado, S.; Pecoraro, V. L. Voltammetric Characterization Of Redox-Inactive Guest Binding To Ln(III)[15-Metallacrown-5]

2		
3 4 5		Hosts Based On Competition With A Redox Probe. Chem. Eur. J. 2010, 16,
6 7 8 9		6786–6796.
10 11 12 13	(48)	Jankolovits, J.; Lim, CS. S.; Mezei, G.; Kampf, J. W.; Pecoraro, V. L. Influencing
14 15 16 17		The Size And Anion Selectivity Of Dimeric Ln ³⁺ [15-Metallacrown-5]
18 19 20		Compartments Through Systematic Variation Of The Host Side Chains And
21 22 23 24		Central Metal. Inorg. Chem. 2012, 51, 4527–4538.
25 26 27 28	(49)	Jankolovits, J.; Cutland Van-Noord, A. D.; Kampf, J. W.; Pecoraro, V. L. Selective
29 30 31		Anion Encapsulation In Solid-State Ln(III)[15-Metallacrown-5] ³⁺ Compartments
32 33 34 35 36		Through Secondary Sphere Interactions. <i>Dalton Trans.</i> 2013, 42, 9803–9808.
37 38 39	(50)	Lim, CS.; Jankolovits, J.; Zhao, P.; Kampf, J. W.; Pecoraro, V. L. Gd(III)[15-
40 41 42 43		Metallacrown-5] Recognition Of Chiral α-Amino Acid Analogues. Inorg. Chem.
44 45 46 47		2011 , <i>50</i> , 4832–4841.
48 49 50 51	(51)	Tegoni, M.; Tropiano, M.; Marchiò, L. Thermodynamics Of Binding Of
52 53 54 55 56 57 58		Carboxylates To Amphiphilic Eu ³⁺ /Cu ²⁺ Metallacrown. <i>Dalton Trans.</i> 2009, 6705–

6708.

- (52) Tegoni, M.; Remelli, M.; Bacco, D.; Marchiò, L.; Dallavalle, F. Copper(II) 12-Metallacrown-4 Complexes Of α-, β- And γ-Aminohydroxamic Acids: A Comparative Thermodynamic Study In Aqueous Solution. *Dalton Trans.* 2008, 2693–2701.
- (53) Bodwin, J. J.; Cutland, A. D.; Malkani, R. G.; Pecoraro, V. L. The Development Of Chiral Metallacrowns Into Anion Recognition Agents And Porous Materials. *Coord. Chem. Rev.* 2001, *216–217*, 489–512.
- (54) Pavlishchuk, A. V.; Kolotilov, S. V.; Zeller, M.; Shvets, O. V.; Fritsky, I. O.;
 Lofland, S. E.; Addison, A. W.; Hunter, A. D. Magnetic And Sorption Properties Of
 Supramolecular Systems Based On Pentanuclear Copper(II) 12-Metallacrown-4
 Complexes And Isomeric Phthalates: Structural Modeling Of The Different Stages
 Of Alcohol Sorption. *Eur. J. Inorg. Chem.* 2011, *2011*, 4826–4836.
- (55) Pavlishchuk, A. V; Kolotilov, S. V; Zeller, M.; Thompson, L. K.; Fritsky, I. O.;

2 3 4 5		Addison, A. W.; Hunter, A. D. A Triple-Decker Heptadecanuclear (Cu ^{II}) ₁₅ (Cr ^{III}) ₂
6 7 8 9		Complex Assembled From Pentanuclear Metallacrowns. Eur. J. Inorg. Chem.
10 11 12 12		2010 , <i>2010</i> , 4851–4858.
13 14 15 16	(56)	Pavlishchuk, A. V.; Kolotilov, S. V.; Zeller, M.; Lofland, S. E.; Thompson, L. K.;
17 18 19 20		Addison, A. W.; Hunter, A. D. High Nuclearity Assemblies And One-Dimensional
21 22 23 24		(1D) Coordination Polymers Based On Lanthanide-Copper 15-Metallacrown-5
25 26 27		Complexes (Ln ^{III} = Pr, Nd, Sm, Eu). <i>Inorg. Chem.</i> 2017 , <i>56</i> , 13152–13165.
28 29 30 31	(57)	Pavlishchuk, A. V.; Kolotilov, S. V.; Zeller, M.; Lofland, S. E.; Kiskin, M. A.;
32 33 34 35		Efimov, N. N.; Ugolkova, E. A.; Minin, V. V.; Novotortsev, V. M.; Addison, A. W.
36 37 38		Supramolecular Maleate Adducts Of Copper(II) 12-Metallacrown-4: Magnetism,
40 41 42		EPR, And Alcohol Sorption Properties. Eur. J. Inorg. Chem. 2017, 2017, 4866-
43 44 45 46		4878.
47 48 49	(58)	Pavlishchuk, A. V; Kolotilov, S. V; Zeller, M.; Thompson, L. K.; Addison, A. W.
51 52 53		Formation Of Coordination Polymers Or Discrete Adducts Via Reactions Of

Gadolinium(III)-Copper(II) 15-Metallacrown-5 Complexes With Polycarboxylates:

ACS Paragon Plus Environment

2
3
1
4
5
6
7
, 0
0
9
10
11
12
12
13
14
15
16
10
17
18
19
20
20 ⊃1
21
22
23
24
27
25
26
27
28
20
29
30
31
32
22
33
34
35
36
27
57
38
39
40
лı
41
42
43
44
45
45
46
47
48
40
50
51
52
53
55
54
55
56
57
50
20
59
60

Synthesis, Structures And Magnetic Properties. *Inorg. Chem.* **2014**, *53*, 1320–1330.

- (59) Bodwin, J. J.; Pecoraro, V. L. Preparation Of A Chiral, 2-Dimensional Network
 Containing Metallacrown And Copper Benzoate Building Blocks. *Inorg. Chem.* 2000, *39*, 3434–3435.
- (60) Pecoraro, V. L.; Bodwin, J. J.; Cutland, A. D. Formation Of Chiral Solids Via A Molecular Building Block Approach. *J. Solid State Chem.* **2000**, *152*, 68–77.
- (61) Lim, C.-S.; Jankolovits, J.; Kampf, J. W.; Pecoraro, V. L. Chiral Metallacrown Supramolecular Compartments That Template Nanochannels: Self-Assembly And Guest Absorption. *Chem. Asian J.* **2010**, *5*, 46–49.
- (62) Cutland-Van Noord, A. D.; Kampf, J. W.; Pecoraro, V. L. Preparation Of Resolved Fourfold Symmetric Amphiphilic Helices Using Chiral Metallacrown Building Blocks. *Angew. Chem. Int. Ed.* **2002**, *41*, 4667–4670.
- (63) Wang, K.; Zou, H.-H.; Chen, Z.-L.; Zhang, Z.; Sun, W.-Y.; Liang, F.-P. A Series Of

	3D Metal Organic Frameworks Based On [24-MC-6] Metallacrown Clusters:
	Structure, Magnetic And Luminescence Properties. Dalton Trans. 2014, 43,
	12989.
(64)	Aulakh, D.; Xie, H.; Shen, Z.; Harley, A.; Zhang, X.; Yakovenko, A. A.; Dunbar, K.
	R.; Wriedt, M. Systematic Investigation Of Controlled Nanostructuring Of Mn_{12}
	Single-Molecule Magnets Templated By Metal-Organic Frameworks. Inorg.
	<i>Chem.</i> 2017 , <i>56</i> , 6965–6972.
(65)	Brunet, G.; Safin, D. A.; Jover, J.; Ruiz, E.; Murugesu, M. Single-Molecule
	Magnetism Arising From Cobalt(II) Nodes Of A Crystalline Sponge. J. Mater.
	Chem. C Mater. Opt. Electron. Devices 2017, 5, 835–841.
(66)	Campo, J.; Falvello, L. R.; Forcen-Vazquez, E.; Saenz de Pipaon, C.; Palacio, F.;
	Tomas, M. A Symmetric, Triply Interlaced 3-D Anionic MOF That Exhibits Both
	Magnetic Order And SMM Behaviour. <i>Dalton Trans.</i> 2016, 45, 16764–16768.
(67)	Wang, H. H.; Yang, J.; Liu, Y. Y.; Song, S.; Ma, J. F. Heterotrimetallic Organic

Framework Assembled With Fe^{III}/Ba^{II}/Na^I And Schiff Base: Structure And Visible Photocatalytic Degradation Of Chlorophenols. *Cryst. Growth Des.* **2015**, *15*, 4986–4992.

- (68) Aulakh, D.; Pyser, J. B.; Zhang, X.; Yakovenko, A. A.; Dunbar, K. R.; Wriedt, M. Metal-Organic Frameworks As Platforms For The Controlled Nanostructuring Of Single-Molecule Magnets. *J. Am. Chem. Soc.* **2015**, *137*, 9254–9257.
- (69) *Single-Molecule Magnets and Related Phenomena*; Winpenny, R., Ed.; Structure and Bonding; Springer-Verlag: Berlin/Heidelberg, 2006; Vol. 122.
- (70) Lis, T. Preparation, Structure, And Magnetic Properties Of A Dodecanuclear Mixed-Valence Manganese Carboxylate. *Acta Crystallogr. Sect. B Struct. Crystallogr. Cryst. Chem.* **1980**, *36*, 2042–2046.
- (71) Sessoli, R.; Gatteschi, D.; Caneschi, A.; Novak, M. A. Magnetic Bistability In A Metal-Ion Cluster. *Nature* **1993**, *365*, 141–143.

(72) Bruker. SMART (Control) And SAINT (Integration) Software. Bruker AXS Inc.:

Madison, WI, USA 1994.

- (73) Agilent. CrysAlis PRO. Agilent Technologies Ltd: Yarnton, Oxfordshire, England 2014.
- (74) Sheldrick, G. M. Area-Detector Absorption Correction. Siemens Industrial Automation Inc.: Madison, WI, USA 1996.

(75) Lausi, A.; Polentarutti, M.; Onesti, S.; Plaisier, J. R.; Busetto, E.; Bais, G.; Barba,

L.; Cassetta, A.; Campi, G.; Lamba, D.; Pifferi, A.; Mande, S. C.; Sarma, D. D.;

Sharma, S. M.; Paolucci, G. Status of the Crystallography Beamlines at Elettra.

Eur. Phys. J. Plus **2015**, *130*, 43.

- (76) Sheldrick, G. M. SHELXT Integrated Space-Group And Crystal-Structure Determination. *Acta Crystallogr. Sect. A Found. Adv.* **2015**, *71*, 3–8.
- (77) Sheldrick, G. M. Crystal Structure Refinement With SHELXL. *Acta Crystallogr. Sect. C Struct. Chem.* **2015**, *71*, 3–8.

(78) Macrae, C. F.; Bruno, I. J.; Chisholm, J. A.; Edgington, P. R.; McCabe, P.;

2
3
Δ
- -
2
6
7
8
0
10
10
11
12
13
11
14
15
16
17
18
10
19
20
21
22
23
20
24
25
26
27
28
20
29
30
31
32
22
24
34
35
36
37
20
20
39
40
41
42
43
11
44
45
46
47
48
40
49 50
50
51
52
53
51
54
55
56
57
58
50
22
60

Pidcock, E.; Rodriguez-Monge, L.; Taylor, R.; van de Streek, J.; Wood, P. A. Mercury CSD 2.0 – New Features For The Visualization And Investigation Of Crystal Structures. J. Appl. Crystallogr. 2008, 41, 466–470. (79) Tegoni, M.; Ferretti, L.; Sansone, F.; Remelli, M.; Bertolasi, V.; Dallavalle, F. Synthesis, Solution Thermodynamics, And X-Ray Study Of Cull [12]Metallacrown-4 With GABA Hydroxamic Acid: An Unprecedented Crystal Structure Of A [12]MC-4 With A Gamma-Aminohydroxamate. Chem. Eur. J. 2007, 13, 1300-1308. (80) Sisco, S. W.; Moore, J. S. Directional Cyclooligomers Via Alkyne Metathesis. J. Am. Chem. Soc. 2012, 134, 9114-9117. (81) Chowdhury, M. A.; Abdellatif, K. R. A.; Dong, Y.; Das, D.; Yu, G.; Velázquez, C. A.; Suresh, M. R.; Knaus, E. E. Synthesis And Biological Evaluation Of Salicylic Acid And N-Acetyl-2-Carboxybenzenesulfonamide Regioisomers Possessing A N-Difluoromethyl-1,2-Dihydropyrid-2-One Pharmacophore: Dual Inhibitors Of

Cyclooxygenases And 5-Lipoxygenase With Anti-Inflammatory Ac. Bioorg. Med.

ACS Paragon Plus Environment

2	
3	
4	
5	
6	
7	
8	
a	
10	
11	
11	
12	
13	
14	
15	
16	
17	
18	
19	
20	
21	
22	
23	
24	
25	
26	
27	
28	
29	
30	
31	
32	
32	
31	
25	
22	
20	
3/	
38	
39	
40	
41	
42	
43	
44	
45	
46	
47	
48	
49	
50	
51	
52	
53	
54	
55	
56	
57	
59, 58	
50	
72	
00	

Chem. Lett. 2009, 19, 6855-6861.

- (82) Adamski-Werner, S. L.; Palaninathan, S. K.; Sacchettini, J. C.; Kelly, J. W. Diflunisal Analogues Stabilize The Native State Of Transthyretin. Potent Inhibition Of Amyloidogenesis. *J. Med. Chem.* **2004**, *47*, 355–374.
- (83) Brachvogel, R.-C.; Maid, H.; von Delius, M. NMR Studies On Li⁺, Na⁺ And K⁺ Complexes Of Orthoester Cryptand *o*-Me₂-1.1.1. *Int. J. Mol. Sci.* 2015, *16*, 20641– 20656.
- (84) Brachvogel, R.-C.; Hampel, F.; von Delius, M. Self-Assembly Of Dynamic Orthoester Cryptates. *Nat. Commun.* **2015**, *6*, 7129.
- (85) Low, H.; Mena-Osteritz, E.; von Delius, M. Self-Assembled Orthoester Cryptands: Orthoester Scope, Post-Functionalization, Kinetic Locking And Tunable Degradation Kinetics. *Chem. Sci.* **2018**, *9*, 4785–4793.
- (86) Dietrich, B. Cryptands. In *Comprehensive Supramolecular Chemistry*, G.W. Gokel, Ed.; Elsevier: Oxford, 1996; Chapter 4, pp 153–211.

3	
1	
4 7	
2	
6	
7	
8	
9	
10	
11	
11	
12	
13	
14	
15	
16	
17	
18	
10	
19	
20	
21	
22	
23	
24	
25	
25	
20	
27	
28	
29	
30	
31	
32	
22	
22	
34	
35	
36	
37	
38	
39	
40	
д1	
41	
42	
43	
44	
45	
46	
47	
48	
0ד ۸۵	
49 50	
50	
51	
52	
53	
54	
55	
56	
50	
5/	
58	
59	
60	

(87) Pecoraro, V. L.; Stemmler, A. J.; Gibney, B. R.; Bodwin, J. J.; Wang, H.; Kampf, J.

W.; Barwinski, A. Metallacrowns: A New Class Of Molecular Recognition Agents.

In *Progress in Inorganic Chemistry*, Karlin, K. D., Ed.; 2007; Vol., pp 83–177.

(88) Brown, I. D.; Altermatt, D. Bond-Valence Parameters Obtained From A Systematic Analysis Of The Inorganic Crystal Structure Database. Acta Crystallogr. Sect. B Struct. Sci. 1985, 41, 244–247.

- (89) Thorp, H. H. Bond Valence Sum Analysis Of Metal-Ligand Bond Lengths In Metalloenzymes And Model Complexes. *Inorg. Chem.* **1992**, *31*, 1585–1588.
- (90) Hessel, L. W.; Romers, C. The Crystal Structure Of "Anhydrous Manganic Acetate." *Recl. des Trav. Chim. des Pays-Bas* **2010**, *88*, 545–552.

(91) Avdeef, A.; Costamagna, J. A.; Fackler, J. P. Crystal And Molecular Structure Of Tris(Tropolonato)Manganese(III), Mn(O₂C₇H₅)₃, A High-Spin Complex Having Structural Features Consistent With Jahn-Teller Behavior For Two Distinct MnO₆ Centers. *Inorg. Chem.* **1974**, *13*, 1854–1863.

1		
2		
3		
4		
5		
6		
7		
8		
9		
10		
11		
12		
13		
14		
15		
16		
17		
10		
20		
20		
22		
23		
24		
25		
26		
27		
28		
29		
30		
31		
32		
33		
34 25		
35		
30		
38		
39		
40		
41		
42		
43		
44		
45		
46		
47		
48		
49 50		
5U 51		
ו כ 50		
5∠ 53		
54		
55		
56		
57		
58		
59		

(92)	Fackler, J. P.; Avdeef, A. Crystal And Molecular Structure Of Tris(2,4-
	Pentanedionato)Manganese(III), $Mn(O_2C_5H_7)_3$, A Distorted Complex As Predicted
	By Jahn-Teller Arguments. Inorg. Chem. 1974, 13, 1864–1875.
(93)	van Gorkum, R.; Buda, F.; Kooijman, H.; Spek, A. L.; Bouwman, E.; Reedijk, J.
	Trigonal-Prismatic Vs. Octahedral Geometry For Mn ^{II} Complexes With Innocent
	Didentate Ligands: A Subtle Difference As Shown By XRD And DFT On
	[Mn(acac) ₂ (bpy)]. <i>Eur. J. Inorg. Chem.</i> 2005 , <i>2005</i> , 2255–2261.

For Table of Contents Use Only

Synopsis

Three metallacryptate supramolecular assemblies have been obtained using salicylhydroxamic acid derivatives. The periphery of thee ligands have been designed to obtain interactions between the metallacryptate units. By the use of ligands which bear amino (NH₂) or 4-pyridyl groups the units assemble into parallel chains and into a MOF-like structure. In both solids, a honeycomb porous structure is obtained.